(19)	Europäisches Patentamt European Patent Office	
(12)	EUROPEAN PAI	
(43)	Date of publication: 03.09.1997 Bulletin 1997/36	(51) Int. Cl. ⁶ : C04B 14/28 , C04B 7/52
(21)	Application number: 97103344.4	
(22)	Date of filing: 28.02.1997	
(84)	Designated Contracting States: AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE Designated Extension States:	 Frigeni, Gianmario 24132 Bergamo (IT) Cassar, Luigi 20097 San Donato Milanese (MI) (IT) Tognon, Gianpietro 24124 Bergamo (IT)
(30)	Priority: 01.03.1996 IT MI960398	
(71)	Applicant: ITALCEMENTI S.p.A. 24100 Bergamo (IT)	(74) Representative: Passini, Angelo et al NOTARBARTOLO & GERVASI S. R. L., Corso di Porta Vittoria, 9 20122 Milano (IT)
(72) •	Inventors: Cangiano, Stefano 25060 Torre de Roveri (BG) (IT)	

(54) Limestone filled Portland cements

(57) Limestone filled Portland cement wherein the fineness of limestone particles ranges from 5,000 to 12,000 Blaine and the fineness of clinker particles ranges from 1,500 to 3,000 Blaine.



Description

Field of the invention

5 The present invention relates to limestone filled Portland cements characterized by an optimal particle size and to the process for the preparation of same.

State of the art

- Cement is a hydraulic binder, i.e. a finely divided inorganic powder that, in admixture with water, forms a paste which cohagulates and hardens by hydration, and once hardened, it maintains its resistance also under water. As a hydraulic binder it must produce mortar or concrete capable of maintaining the necessary flow as long as required to reach, after given periods of time, predetermined mechanical resistance levels, and be endowed with a long-term stability in terms of volume.
- A major hydraulic constituent of cement is clinker, which consists of calcium silicates (at least two thirds by wt.), the remainder being aluminium oxide, iron oxide and other oxides.

In compliance with UNI ENV 197.1 standard, limestone filled Portland cements (type II) are hydraulic binders containing clinker (65 to 94% by wt.), limestone (6 to 35% by wt.) and minor constituents (0 to 5% by wt.), said minor constituents being selected from blast furnace slag, microsilica, pozzolana, flying ashes, calcined shales or mixtures thereof.

The above per cent amounts are exclusive of calcium sulphate, used to regulate the setting time, and optional additives.

UNI ENV 197.1 standard covers types of cement, with requirements for compressive strengths that, depending on the various cement classes, vary from 32.5 N/mm² to 52 N/mm², at 28 days.

It follows that both cements consisting exclusively of clinker and gypsum and the so-called mixed cements, like those filled with cements, have to possess mechanical properties complying with standards.

However, as shown from the data reported in the literature, the addition of a calcareous filler brings about a more or less marked reduction in the mechanical resistance properties of cement in standard mortar, if compared with those of Portland cement without filler (type I as per UNI ENV 197.1).

30

20

25

P. Krustolovic *et al.* (CCR, vol. 24, No. 5, 1994) state that the addition of 20% non-hydraulic filler reduces the compressive strength of mortar and concrete by 27%.

P. Livesey, in *Performance of limestone filled cement*, p. 6.1, confirms said results and states that the addition of 5% max. of calcareous filler does not affect the cement resistance, whereas the addition of 25% limestone causes a reduction in the mechanical resistance by 25%.

35 As disclosed in *Materiales de construcction*, vol. 24, No. 233, 1944, the addition of 10% max. of calcareous filler would not affect the mechanical resistance properties of standard mortar. However, should the amount of calcareous filler be as high as 15%, the resistance will fall by 27% and only by decreasing the water/cement ratio, the resistance properties may be kept constant.

S. Sprung and E. Siebel (Zement Kalk Gips, No. 1, pp. 1-11, 1991) maintain that, with calcareous filler contents ranging from 5% to 10%, the increased compactness of the cementitious paste structure caused by intragranular holes filling may bring about a slight increase in the standard resistance properties. With higher calcareous filler contents, the diluting effect produced by the filler on the clinker causes a reduction in the resistance of cement in standard mortar. Said authors state that, should a Portland cement be added with a calcareous filler in amounts of 15%, the standard mortar resistance will be reduced by 14%.

45 To obviate said inconvenience, Sprung and Siebel state that Portland cements filled with 20% to 30% limestone can have a mechanical resistance of 45 N/mm² only if prepared with clinker having fineness as high as 4,500 to 5,000 Blaine.

The commercial-scale production of clinker with such a high degree of fineness requires long grinding times and high power consumption.

50

55

The present invention

The Applicant has surprisingly been found that Portland cement containing 6% to 35% limestone, having mechanical properties as high as and, in some cases, better than those of Portland cement without inorganic filler, may be obtained with clinker having fineness even as low as 1,500 to 3,000 Blaine.

It is a characteristic of the claimed limestone filled Portland cement that the limestone particles fineness ranges from 5,000 to 12,000 cm²/g (Blaine) and the clinker particles fineness ranges from 1,500 to 3,000 Blaine.

In fact, it has been found that, when the clinker and limestone particles satisfy the aforementioned conditions, the mechanical properties of said mixed cement are substantially the same as and sometimes even better than those of

Portland cement without filler.

It is a further object of the present invention to provide a process for the preparation of the limestone filled Portland cement according to the present invention, comprising a separate grinding of clinker and limestone, followed by homogenization.

In fact, it has been found that the process of the invention envisaging a separate grinding of clinker and limestone is highly energy saving in respect of the processes encompassing a co-grinding of said components.

Description of the drawing

¹⁰ Figure 1 shows the plant wherein grinding of the components of the present invention takes place.

Detailed description of the invention

As already pointed out, in the limestone filled Portland cement according to the present invention, the fineness of the clinker (ground with gypsum) ranges from 1,500 to 3,000 Blaine, preferably from 1,600 to 2,500 Blaine. In fact, it has been found that, should a clinker with fineness above 3,000 Blaine be used in combination with a limestone having particle size ranging from 5,000 to 12,000 Blaine, the mechanical properties of the resulting cement become somehow, though limitedly, worse.

The clinker particle size distribution preferably ranges from 0 to 80 µm or, even better, from 10 to 40 µm.

In a particularly preferred embodiment of the invention, the clinker has fineness ranging from 1,600 to 2,800 Blaine, 40 μm maximum nominal diameter, and does not contain any fraction of fine particles ranging from 0 to 10 μm.

The fineness of the limestone of the invention ranges from 5,000 to 12,000 Blaine, preferably from 6,000 to 10,000 Blaine.

- At fineness values above 10,000 Blaine, the effect of the filler becomes less evident and at values above 12,000 Blaine the economic pros due to higher resistance properties reduce in respect of the economic cons due to higher energy consumption for grinding.
 - The average diameter of limestone particles ranges from 10 to 30 μ m and preferably is not higher than 15 μ m. The limestone to be used according to the present invention has to comply with UNI ENV 197.1 standard, i.e. have
- 30

45

20

5

a CaCO₃ content ≥75% by wt., a methylene blue adsorption ≤1.20 g/100 g and an organic matter content ≤0.50% by wt. The limestone content in the cement ranges from 6% to 35% by wt., preferably from 20% to 25% by wt. in respect of the cement, excluding gypsum and additives.

The best results are obtained with clinker fineness ranging from 1,600 to 1,700 Blaine, limestone fineness of 10,000 Blaine and with a distribution of the clinker particle size ranging from 10 to 40 μ m.

In the process for the preparation of Portland cement according to the present invention, clinker and limestone grinding takes place separately, preferably in a closed-circuit grinding mill essentially consisting of a hopper, a ball mill, an air classifier and a bag filter, as follows:

- i) the product to be ground is fed to a ball mill from a hopper;
- ii) the ground product goes through a vibrating pipeline to an air classifier, where the fraction of the desired fineness
 is separated from the coarser fraction, which is returned to the ball mill through a pipeline;

iii) the product having the desired fineness and particle size is filtered through a bag filter and collected.

The resulting components are homogenized by any mixer known in the art. With a view to optimizing energy consumption, the constituents, before being subjected to separate grinding, may be conveniently crushed, e.g. in a jawtype crusher.

Figure 1 shows a scheme of the grinding plant wherein grinding as per the above process is carried out.

In particular in this figure: (1) is the hopper, (2) the recycle vibrating pipeline, (3) the air classifier, (4) the ball mill, (5) the pipeline wherethrough the particles from ball mill (4) enter air classifier (3), (6) the bag filter.

The following examples illustrating the preparation of the claimed limestone filled cement and the relevant physicomechanical properties are conveyed by way of indication, not of limitation, of the present invention.

Example 1

Limestone and clinker, premixed with gypsum in a ratio of 5% by weight, were separately crushed in a jaw-type 55 crusher.

The particle size of the crushed materials is shown in Table 1.

EP 0 792 849 A1

Clinker ar	Clinker and limestone particle size after crushing				
<u>Clinker</u> /	<u>ʻgypsum</u>	Limestone			
Ø [mm]	Residue	Ø [mm]	Residue		
10	-	4	12		
4	30.5	2.8	23.7		
2.8	58	1.5	34.6		
1.5	80	1	38.3		
1	86.2	0.5	43.9		
0.5	91.2	0.3	54.4		
0.15	94.9	0.15	82.5		
0.088	95.8	0.1	99.1		
0.06	97.5				
-					

Table 1

10

5

15

20

25

35

The two components were then ground in the closed-circuit grinding mill shown in Figure 1.

The mill was ball type. The ball size and distribution were as follows: Ø 40 mm = 20%, Ø 15 mm = 70%, Ø 10 mm = 10%.

The per cent volume of balls in the mill was 33% and the power rating was 4 kW.

The material to be ground was taken from a hopper and fed to the ball mill by means of a vibrating pipeline. The 30 product leaving the mill went to an air classifier, where the desired fraction was separated from the coarser fraction, which was recycled to the mill.

During the several trials, the power rating adsorbed by the mill was measured by a wattmeter in order to calculate the specific power consumption with regard to the obtained product. In the aforesaid grinding mill, the mixture of clinker and gypsum was ground until obtaining two degrees of fineness, corresponding to a maximum nominal diameter of 40 μm (2,640 Blaine) and, respectively, of 80 μm (2,320 Blaine). The relevant products are hereinafter denominated CLK1 and CLK2.

The fine particle fraction ranging from 0 to 10 μ m in diameter was partially removed by the air classifier from product CLK1 to give product CLK3 having fineness of 1,640 Blaine.

Limestone was ground in said grinding mill until obtaining a fineness of \approx 10,000 Blaine. 40 The products obtained were analysed by a laser apparatus SYMPATEC HELOS. Table 2 shows the particle size distribution recorded.

45

50

	Per cent cumulative undersize materials produced in the closed-circuit grinding				ing mill	
5		CLINKER/GYP	SUM	LIME	STONE	
	Ø [µM]	CLK 1 % undersize	CLK 2 % undersize	CLK 3 % undersize	Ø [µm]	% undersize
	0.90	2.69	3.04	1.21	0.90	9.92
10	1.10	3.89	4.43	1.74	1.10	14.78
	1.30	5.00	5.73	2.21	1.30	19.56
	1.50	6.03	6.97	2.63	1.50	24.22
	1.80	7.46	8.7	3.19	2.60	30.90
15	2.20	9.19	10.81	3.81	3.10	39.12
	2.60	10.75	12.75	4.33	3.70	46.48
	3.10	12.54	14.96	4.86	4.30	54.40
20	3.70	14.51	17.39	5.40	5.00	62.09
	4.30	16.34	19.62	5.89	6.00	68.02
	5.00	18.34	22.05	6.47	7.50	73.27
	6.00	21.03	25.30	7.43	9.00	78.89
25	7.50	24.75	29.83	9.29	10.50	85.07
	9.00	28.22	34.03	11.72	12.50	89.79
	10.50	31.53	38.00	14.68	15.00	93.36
30	12.50	35.78	42.99	19.30	18.00	96.30
	15.00	40.75	48.83	25.80	21.00	97.39
	21.00	46.28	55.28	41.72	25.00	97.39
25	25.00	51.32	61.12	51.44	30.00	98.95
35	30.00	57.32	68.06	62.28	36.00	99.68
	36.00	63.75	75.53	73.38	43.00	100.00
	43.00	70.21	82.94	83.65	51.00	100.00
40	51.00	76.52	89.66	91.75	61.00	100.00
	61.00	82.49	94.85	97.18	73.00	100.00
	73.00	88.4	98.23	99.44	87.00	100.00
45	87.00	93.71	99.6	100	103.0	100.00
40	103.00	97.68	100	100	123.0	100.00
	123.00	99.57	100	100	147.0	100.00
	147.00	100.00	100	100		

Table	2

50

55

Example 2

Ground clinkers prepared as per Example 1 (CLK1, CLK2 and CLK3) were mixed and homogenized with 20% and 25% by wt. calcareous filler at 10,000 Blaine (prepared as described in Example 1).

Standard mortars in compliance with UNI EN 196.1 were prepared from the cements produced by mixing, to determine the mixture compressive strength and rheological properties.

EP 0 792 849 A1

The determination of the mortar consistency (workability) was carried out by means of a jerking plate in compliance with UNI 7044.

The results obtained are shown in Table 3.

5	Table 3					
	Specific surface (Blaine), flow and compressive strength of cements of the invention					th of the
10		Blaine	Flow %	Standard	l mortar CS	(N/mm2)
				2 days	7 days	28 days
	CLK 1	2320	46.7	20.13	31.0	45.4
	CLK 1 + 20%C	3856	53.9	24.32	35.3	45.2
15	CLK 1 + 25%C	4240	55.0	23.62	35.8	-
	CLK 2	2640	73.7	29.36	43.6	49.8
	CLK 2 + 20%C	4112	64.5	27.78	42.0	49.6
20	CLK 2 + 25%C	4480	61.4	28.41	41.5	46.0
	CLK 3	1640	61.5	18.01	35.9	51.2
	CLK 3 + 20%C	3312	71.2	23.97	41.4	51.4
	CLK 3 + 25%C	3730	70.3	24.29	40.04	46.1
25		Í.			1	Í

As may be inferred from Table 3, limestone filled cement develops with time the same compressive strength as the cement obtained with the same clinker but without addition of inert materials. In particular, the addition of 20% lime-30 stone increases the final resistance of cement CLK3 even at 28 days.

A really surprising feature concerns the increase in flow obtained with limestone filled cements CLK1 and CLK3 in respect of the corresponding Portland cements.

The effect of the calcareous filler is the greater, the lower the content of clinker fine particles ranging from 0 to 10 μ m in diameter.

³⁵ More specifically, a lower content of clinker fine particles can be made up by an addition of calcareous filler. Under said conditions, instead of exerting a diluting action, the filler appreciably increases short-term resistance without, how-ever, worsening resistance properties at 28 days.

Example 3

40

45

Three series of clinker and gypsum (CLK4, CLK5, CLK6) having average fineness of 2,000, 2,500 and 3,000 Blaine, respectively, were prepared substantially as described in Example 1.

Said test cements were added with limestone ground as per Example 1, at 6,000, 8,000 and 10,000 Blaine, respectively.

Standard mortars for the determination of compressive strengths were prepared as per Example 2. The results obtained are shown in Table 4.

50

55

_	Type of cement	Resistand	ce Propertie	es N/mm2
5		2 days	7 days	28 days
	CLK4	16.0	27.4	36.0
	CLK4 + C 6000	18.4	31.2	37.5
10	CLK4 + C 8000	20.3	32.8	37.9
	CLK4 + C 10000	19.0	32.9	37.8
	CLK5	20.9	37.1	45.7
	CLK5 + C 6000	21.2	37.2	46.3
15	CLK5 + C 8000	23.2	37.8	46.7
	CLK5 + C 10000	23.4	37.7	46.4
	CLK6	23.7	39.8	50.2
20	CLK6 + C 6000	23.0	36.5	45.3
	CLK6 + C 8000	24.2	36.3	42.8
	CLK6 + C 10000	23.3	36.9	42.5

Table 4

25

As may be inferred from Table 4, the effect of limestone is the greater, the more the fineness of the clinker is below 3,000 Blaine.

Furthermore, the clinker tends to produce a growing effect until fineness degrees of approx. 10,000 Blaine.

30

Claims

1. Limestone filled Portland cement wherein the fineness of limestone particles ranges from 5,000 to 12,000 Blaine and the fineness of clinker particles ranges from 1,500 to 3,000 Blaine.

35

40

- 2. A limestone filled Portland cement as claimed in claim 1, wherein the fineness of limestone particles ranges from 6,000 to 10,000 Blaine and the fineness of clinker particles ranges from 1,600 to 2,800 Blaine.
- 3. A limestone filled Portland cement as claimed in claims 1 and 2, wherein the limestone particles range from 0 to 30 μ m in average diameter.
- 4. A limestone filled Portland cement as claimed in claims 1 to 3, wherein the clinker particle size ranges from 0 to 80 μ m.
- 45 5. A limestone filled Portland cement as claimed in claim 4, wherein the clinker particle size ranges from 10 to 40 μm.
 - 6. A limestone filled Portland cement as claimed in claims 1 to 5, having a limestone content of 6% to 35% by wt. in respect of cement, excluding gypsum and additives.
- 50 7. A limestone filled Portland cement as claimed in claims 1 to 5, having a limestone content of 20% to 25% by wt. in respect of cement, excluding gypsum and additives.
 - 8. Process for the preparation of limestone filled Portland cement as claimed in claims 1 to 7, wherein clinker and limestone are ground separately and then homogenized.
- 55
- 9. A process for the preparation of limestone filled Portland cement as claimed in claim 8, wherein:

(i) the product to be ground is fed to ball mill (4) from hopper (1);

(ii) the ground product goes through a vibrating pipeline to an air classifier (3), where the fraction of the desired

EP 0 792 849 A1

fineness is separated from the coarser fraction, which is returned to the ball mill through a pipeline (5); (iii) the product having the desired fineness and particle size is filtered through bag filter (6) and collected.

A process for the preparation of limestone filled Portland cement as claimed in claim 9, wherein clinker and lime stone are crushed in a jaw-type crusher, before being separately ground, and finally homogenized after said separate grinding step.

10			
15			
20			
25			
30			
35			
40			
45			
50			
55			



FIG. 1



European Patent Office

EUROPEAN SEARCH REPORT

Application Number EP 97 10 3344

]	DOCUMENTS CONSID	DERED TO BE RELEVA	ANT	······································
Category	Citation of document with ind of relevant pass	lication, where appropriate, ages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	ZKG INTERNATIONAL, vol. 45, no. 7, 1 Ju pages 325-334, XP000 SCHILLER B ET AL: " EIGENSCHAFTEN VON ZE HAUPTBESTANDTEILEN" * the whole document	ly 1992, 291945 MAHLUNG UND MENTEN MIT MEHREREN	1,8	C04B14/28 C04B7/52
A	DE 38 34 494 A (KUEF 12 April 1990 * the whole document	RNER RUDOLF DR RER NA	AT) 1,3-5	
A	GB 968 794 A (SOCIET MATERIAUX BLANCS) 2 * page 2, left-hand 76 * * claim 1 *	FE INDUSTRIELLE DES September 1962 column, line 54 - l ^a	1 ine	
A,P	EP 0 715 892 A (KRU 1996 * the whole documen	PP POLYSIUS AG) 12 Ju	une 1	TECHNICAL FIELDS
A	CHEMICAL ABSTRACTS, 19 September 1994 Columbus, Ohio, US; abstract no. 140169 S. TSIVILIS ET AL: p. mill - applicati grinding" page 420; XP000494193 * abstract * & WORLD CEM., vol. 25, no. 6, 199 pages 34-38,	<pre>vol. 121, no. 12, d, "upgrading of a t. on to selective clin 4,/</pre>	1 t. ker	C04B
	The present search report has b	een drawn up for all claims		
	Place of search THF HAGUE	Date of completion of the sea 17 June 1997	rca Pi	Letz. C
X:p Y:p A:t O:1 P:i	CATEGORY OF CITED DOCUME particularly relevant if taken alone particularly relevant if combined with an locument of the same category echnological background non-written disclosure intermediate document	INTS T: theory or E: earlier pa after the tother D: document & : member document	principle underlying tent document, but p filing date t cited in the applicat t cited for other reaso of the same patent fat	the invention ublished on, or tion ons mily, corresponding



European Patent Office

EUROPEAN SEARCH REPORT

Application Number EP 97 10 3344

-

]	DOCUMENTS CONSID			
ategory	Citation of document with indi of relevant passa	cation, where appropriate, iges	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
	CHEMICAL ABSTRACTS, y 23 March 1987 Columbus, Ohio, US; abstract no. 89243j, A. GLASNOVIC ET AL.: on the grinding of Pu clinker and the propu mortar" page 297; column r; XP002033136 * abstract * & TEHNIKA, vol. 41, no. 7/8, 19 pages 16-19,	vol. 106, no. 12, "effect of limestone C [portland cement] erties of cement 86,	1,8	
A	FR 2 406 614 A (CIME 18 May 1979 * claim 1 *	NTS STE THIONVILLOISE)	1	
A	DE 822 966 C (F.L. S * page 2, line 103 - * claims *	MIDTH) line 105 *	1,8	TECHNICAL FIELDS SEARCHED (Int.Cl.6)
A	ZKG INTERNATIONAL, vol. 43, no. 1, Janu pages 13-19, XP00203 HG. ELLERBROCK ET "Korngrössenverteilu von Zement; Teil III Mahlprozesses" * the whole document	uary 1990, 33135 AL.: ung und Eigenschaften I: Einflüsse des t *	1	
Α	DE 31 38 342 A (POR H SC) 14 April 1983 * page 4; figure *	TLAND ZEMENTWERK WOTAN	1,8,9	
	The present search report has b	een drawn up for all claims		Francisco
	Place of search	געבער מאסער גער גער גער גער גער גער גער גער גער ג	Di	uetz. C
X: Y: A: O: P:	IHE HAGUE CATEGORY OF CITED DOCUME particularly relevant if taken alone particularly relevant if combined with and document of the same category technological background non-written disclosure intermediate document	NTS T : theory or prin E : earlier patent zfter the filin bother D : document cite L : document cite & : member of th document	ciple underlying document, but p g date ed in the applicat d for other reaso e same patent fa	the invention ublished on, or tion ons mily, corresponding