

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 815 319 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

12.12.2001 Bulletin 2001/50

(21) Application number: **96906118.3**

(22) Date of filing: **25.01.1996**

(51) Int Cl.7: **D21G 1/00**, D21H 19/00

(86) International application number:
PCT/SE96/00079

(87) International publication number:
WO 96/28609 (19.09.1996 Gazette 1996/42)

(54) **COATED PAPERBOARD FOR FORMED ARTICLES**

BESCHICHTETES PAPPATERIAL FÜR FORMKÖRPER

ARTICLES EN CARTON PORTANT UN REVETEMENT, POUR DES ARTICLES FORMES

(84) Designated Contracting States:
**AT BE CH DE DK ES FR GB GR IE IT LI LU MC NL
PT SE**

(30) Priority: **16.03.1995 SE 9500949**

(43) Date of publication of application:
07.01.1998 Bulletin 1998/02

(73) Proprietor: **KORSNÄS AB**
S-801 81 Gävle (SE)

(72) Inventors:
• **ERIKSSON, Göran**
S-804 26 Gävle (SE)
• **KARLSSON, Klas-Erik**
S-804 30 Gävle (SE)

- **LARSSON, Nils Ake**
S-804 27 Gävle (SE)
- **HAKANSSON, Sven**
S-814 91 Furuviik (SE)

(74) Representative: **Nilsson, Brita Linnea et al**
Stockholms Patentbyrå Zacco AB
Box 23101
104 35 Stockholm (SE)

(56) References cited:
• **DIALOG INFORMATION SERVICES, File 148,**
TRADE & INDUSTRY DATABASE(TM), Dialog
Accession No. 08147347, Supplier Number
17379701, FERGUSON KELLY H., "High-end
Coated Board Market Guides T-I's Technology
Selection"; & PULP & PAPER, Vol. 69, No. 9, p.
63(5), Sep. 1995.

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 815 319 B1

Description

[0001] The present invention relates to coated paperboard for formed articles, e.g. liquid packaging board or white top liner, a process for the production thereof, a production line, and a method of reducing the susceptibility to crack formation at folding of a coated paperboard.

Background of the invention

[0002] For resource saving and improved economics it is advantageous to reduce the amount of raw materials needed for the production of a specific type of product.

In a mill annually producing 200 000 tons of paper board for liquid packaging, a reduction of the amount of raw materials needed for 1 litre packages by 1 % would make it possible to pack for example 70 million litres of milk products more per year without increasing the amount of raw materials used.

In Sweden this corresponds to the yearly consumption of milk in a city of the size of Gothenburg.

[0003] However, savings of raw material should desirably be achieved without having to compromise with the quality requirements of the product.

[0004] Important properties of coated paperboard for formed articles are sufficient stiffness measured as bending force, good forming properties including low susceptibility to crack formation at folding, adequate surface for printing and adequate surface gloss. All of these required properties vary with the specific type of formed article which is to be produced from the coated paperboard.

[0005] A conventional way of producing board with high stiffness is to use a fibermatrix with three or more layers where the middle layer gives bulk and the two outer layers have a high elasticity modulus or high tensile stiffness. However, there are also coated board with high stiffness made from only two fiber layers.

[0006] In the production of coated paperboard it is known that the calendering operation together with the coating contributes to a good printing surface. However, at the same time the stiffness is to a certain extent reduced. In order to achieve an adequate surface for printing a calendering operation has been performed to reduce the surface roughness before the paperboard is subjected to a coating operation. Depending on the type of final product to be produced sometimes there is also performed a calendering operation after the coating operation to further improve the surface and increase the gloss to the desired level.

[0007] There are mainly two types of heatable or non-heatable calenders which are in use in paper mills today, namely hard nip calenders which have steel rolls, and soft nip calenders which have steel rolls where the counter rolls have a softer cover. The nip lengths in these soft nip calenders are typically approximately 1 cm.

[0008] A new type of calender is disclosed in Pulp & Paper International (PPI), May 1994, page 36. Surface properties of an uncoated board grade were reported to be improved with only minor loss of stiffness (bulk). The new calender is constructed to have a relatively soft elastic moving belt supported by a glide body or roll instead of the covered roll in a conventional soft calender. The elongated nip contour in combination with the soft elastic belt is reported to yield uniform specific pressures and nip lengths which typically would be four to six centimeter. This new type of calender has been named supersoft calender in said article, and said calender could be used in the present invention where a heatable calender with soft extended nip is required.

[0009] In the production of paperboard for formed articles the calendering operation has up to now been performed either before or both before and after the coating operation.

Description of the invention

[0010] It was surprisingly found that by deleting the conventionally used calendering operation before the coating operation and by performing a calendering operation only after the coating operation with a calender which is run at high temperature and has a soft extended nip in the production of coated paperboard for formed articles, it was possible to obtain coated paperboard with reduced susceptibility to crack formation at folding and with adequate or improved surface for printing and adequate or improved surface gloss for specific types of formed articles and at the same time much increased stiffness. By reducing the thus obtained increased stiffness to values previously set for a certain type of product, it is now possible to significantly reduce the grammage and thus the amount of raw materials needed.

[0011] Savings in raw material can be made in the amount of fibermatrix used and/or the amount of coating used.

[0012] Thus, the present invention provides in one aspect a coated paperboard for formed articles, including liquid packaging board and white top liner, which paperboard consists of a fibermatrix in one, two or more layers and a coating and has adequate surface for printing and adequate surface gloss for each specific type of formed articles. The characteristic features of said paperboard are that it has been calendered after coating with a heatable calender having a soft extended nip, and has reduced density and reduced grammage at a given value for bending force compared to corresponding coated paperboard which has been calendered before or before and after coating with a heatable or

non-heatable calender having a hard or soft nip.

[0013] The term "extended nip" is considered to comprise nip lengths of 3 to 10 cm, such as 4 to 8 cm, e.g. 6 to 7 cm.

[0014] The fibermatrix used in the present invention is preferably composed of sulphate pulp and/or mechanical pulp and/or recycled pulp, and is either unbleached or bleached. The coating of the board is composed of binders and usually also pigments to enhance the printability. Examples of common binders in this context are latex and starch, and examples of common pigments are clay and calcium carbonate.

[0015] The given value for bending force depends on the specific type of formed articles which are to be produced. Small formed articles or packages do not need as high values for bending force as larger ones. For example, for a coated liquid board from which smaller, such as 250 ml, packages are to be produced, values for bending force may be in the range of 50 to 100 mN, and for a coated liquid board from which larger, such as 1 liter, packages are to be produced values for bending force may be in the range of 200 to 300 mN.

[0016] Thus, in an embodiment of the invention there is provided coated paperboard for formed articles, wherein said given value for bending force is in the range of 20 to 300 mN, said reduction of density is in the range of 1 - 50 % and said reduction of grammage is in the range of 1 - 20%.

[0017] In another embodiment of the invention there is provided coated paperboard for formed articles, wherein said given value for bending force is in the range of 60 - 270 mN, said reduction of density is in the range of 1 to 35 % and said reduction in grammage is in the range of 1 -15 %.

[0018] The percent reduction of the density and the percent reduction of the grammage of the coated paperboard at a given value for bending force are calculated on a corresponding coated paperboard for the same specific type of formed articles which has been calendered before or before and after coating with a heatable or non-heatable calender having a hard or soft nip.

[0019] In a preferred embodiment the fibermatrix of the coated paperboard of the invention is composed of two layers.

[0020] In another preferred embodiment of the coated paperboard of the invention the fibermatrix is composed of unbleached sulphate pulp in the bottom layer and bleached sulphate pulp in the top layer and the coating comprises binders and pigments.

[0021] In another aspect of the invention there is provided a production line for the production of coated paperboard, which paperboard consists of a fibermatrix in one, two or more layers and a coating and has adequate surface for printing and adequate surface gloss for each specific type of formed articles. The characteristic feature of this new production line is that there is arranged, only after a coating device, a heatable calender with a soft extended nip.

[0022] Although a calendering operation with a heated calender having a soft extended nip is needed only after a coating operation for the production of coated paperboard for formed articles which paperboard consists of a fibermatrix in one, two or more layers and a coating and has adequate surface for printing and adequate surface gloss for each specific type of formed articles, the present invention also comprises production lines where there is additionally arranged a calender before the coating device. There may be special circumstances when such precalendering would be preferred, such as exceptionally high demands for surface properties. If a precalendering is performed then the savings of raw material will be less.

The precalendering before the coating operation may be performed with any type of calender.

[0023] In yet another aspect of the invention there is provided a process for the production of coated paperboard for formed articles with adequate surface for printing and adequate surface gloss for each specific type of formed articles, wherein the fibermatrix of the paperboard is composed of one, two or more layers. The characteristic feature of the process is that a calendering operation is performed only after a coating operation with a calender which is run at high temperature and has a soft extended nip.

[0024] In principal, the higher the temperature is, the better the surface properties of the coated paperboard will be. Typically the calender temperatures is in the range of 140 to 250 °C, but even higher temperatures are possible.

[0025] The present invention also comprises a process for the production of coated paperboard for formed articles wherein there is additionally performed a calendering operation before said coating operation.

[0026] In still another aspect of the invention there is provided a method of reducing the susceptibility to crack formation at folding of a coated paperboard with adequate surface for printing and adequate surface gloss for each specific type of formed articles, wherein the fibermatrix of the paperboard is composed of one, two or more layers. The characteristic feature of the method is that said coated paperboard is produced in a production line wherein a calendering operation is performed only after a coating operation with a calender which is run at high temperature and has a soft extended nip.

[0027] The present invention also comprises such a method, wherein there is additionally performed a calendering operation before said coating operation.

[0028] The following Examples will illustrate the different aspects of the invention.

[0029] In the examples a fibermatrix in two layers, a bottom layer of unbleached sulphate pulp and a top layer of bleached sulfate pulp, and a coating consisting of pigments and binders, were used.

[0030] The Print-surf roughness at 1000 kPa was measured according to ISO 8791-4:1992 (E).

EP 0 815 319 B1

The Gloss was measured according to Tappi, T 480.

The Density was measured according to SCAN P 7:75.

The Bending force was measured according to SCAN P 29:84.

The Uniformity variance was evaluated with the aid of an image analyzer "Kontron IBAS" system.

The grammage was measured in accordance with SCAN P6:75.

EXAMPLE 1

[0031] In a pilot trial it was shown that the uniformity of the coated surface was better when the calendering after coating was done with an extended soft nip in comparison with a conventional soft nip. The board was in this case calendered also before coating.

[0032] It was also shown that the density was lower when using an soft extended nip in comparison with a conventional soft calender.

	Print-surf roughness μm	Gloss	Density, kg/m^3	Uniformity variance, %
Soft nip	3.23	38	685	0.74
140°C	2.73	45	730	0.77
	2.43	51	749	0.80
Extended soft nip	3.24	32	661	0.63
140°C	3.06	39	680	0.62
	2.46	43	687	0.63

[0033] The uniformity of the coating was measured in an image analyzer in the wave length area 2.0-8.0 mm.

EXAMPLE 2

[0034] In another pilot trial it was shown that taking advantage of the decreased density, the stiffness could be increased by using the soft extended nip calender after coating. The effect was greatest when no calendering was done before coating and the coat weight was reduced.

	Print-surf roughness μm	Gloss	Grammage g/m^2	Bending force mN	Density kg/m^3
Cbc+ 21 g/m^2 coating	3.75	29	266	255	675
No Cbc+ 21 g/m^2 coating + Cac with SEN	3.75	31	266	266	650
Cbc+ 11 g/m^2 coating + Cac with SEN	3.75	27	266	267	660
No Cbc+ 11 g/m^2 coating+ Cac with SEN	3.75	32	266	280	639
Cbc = Calendering before coating Cac = Calendering after coating SEN = Soft Extended Nip					

EXAMPLE 3

[0035] In a mill trial the soft extended nip calender was used to produce the same surface as the reference quality which was calendered only before coating. When the extended nip calender was used the calendering was done only after coating.

EP 0 815 319 B1

	Grammage g/m ²	Gloss	Bending force, mN	Print-surf roughness μm	Density kg/m ³
Cbc+ 22 g/m ² coating	255	17	228	3.9	651
No Cbc+ 11 g/m ² coating + Cac with SEN	255	25	266	3.3	597
Cbc = Calendering before coating Cac = Calendering after coating SEN = Soft Extended Nip					

[0036] The stiffness increase measured as bending force was greater than in the pilot trials.

[0037] This increase in stiffness means that the grammage can be reduced from 255 g/m² to 245 g/m² keeping the other specifications at the same or even improved levels. This improvement makes it possible to further decrease the grammage.

[0038] Board from the mill trial was also tested against the susceptibility to crack formation at folding of a coated paper board.

[0039] The tendency of crack formation was measured by folding the board in a controlled manner according to a standardized method developed for this purpose and evaluating the crack tendency on a scale of 1 to 5 as follows:

- 0 = Perfect
- 1 = Good
- 2 = Tendency to crack
- 3 = Small crack
- 4 = Crack
- 5 = Big crack

	Susceptibility to crack formation	
	top side	bottom side
Cbc+ 22 g/m ² coating	3.2	3.0
No Cbc + 11 g/m ² coating + Cac with SEN	1.4	1.3

[0040] The board from the mill trial was also printed and the print result was evaluated. The overall print result and the uniformity of the print was better for the test quality.

	Uniformity Variance % (image analyzer 0.35-5.6 mm)
Cbc + 22 g/m ² coating	9.54
No Cbc + 11 g/m ² coating + Cac with SEN	8.15
Cbc = Calendering before coating Cac = Calendering after coating SEN = Soft Extended Nip	

Claims

1. Coated paperboard for formed articles, which paperboard consists of a fibermatrix in one, two or more layers and a coating and has adequate surface for printing and adequate surface gloss for each specific type of formed articles, **characterized in that** said paperboard has been calendered after coating with a heatable calender having a soft extended nip, and has reduced density and reduced grammage at a given value for bending force compared to corresponding coated paperboard which has been calendered before or before and after coating with a heatable or non-heatable calender having a hard or soft nip.

2. Coated paperboard according to claim 1, wherein said given value for bending force is in the range of 20 to 300 mN, said reduction of density is in the range of 1 - 50 % and said reduction of grammage is in the range of 1- 20 %.
3. Coated paperboard according to claim 2, wherein said given value for bending force is in the range of 60 - 270 mN, said reduction of density is in the range of 1 to 35 % and said reduction in grammage is in the range of 1 - 15 %.
4. Coated paperboard according to any one of the claims 1 - 3, wherein said paperboard is a white top liner.
5. Coated paperboard according to any one of the claims 1 - 3, wherein said paperboard is a liquid packaging board.
6. Coated paperboard according to any one of the claims 1 - 5, wherein said fibermatrix is composed of two layers.
7. Coated paperboard according to claim 6, wherein said fibermatrix is composed of unbleached sulphate pulp in the bottom layer and bleached sulphate pulp in the top layer and said coating comprises binders and pigments.
8. Production line for the production of coated paperboard, which paperboard consists of a fibermatrix in one, two or more layers and a coating and has adequate surface for printing and adequate surface gloss for each specific type of formed articles **characterized in that** there is arranged, only after a coating device, a heatable calender with a soft extended nip.
9. Production line for the production of coated paperboard according to claim 8, where there is additionally arranged a calender before the coating device.
10. Process for the production of coated paperboard for formed articles with adequate surface for printing and adequate surface gloss for each specific type of formed articles, wherein the fibermatrix of the paperboard is composed of one, two or more layers, **characterized in that** a calendering operation is performed only after a coating operation with a calender which is run at high temperature and has a soft extended nip.
11. Process for the production of coated paperboard according to claim 10, wherein there is additionally performed a calendering operation before said coating operation.
12. Method of reducing the susceptibility to crack formation at folding of a coated paperboard with adequate surface for printing and adequate surface gloss for each specific type of formed articles, wherein the fibermatrix of the paperboard is composed of one, two or more layers, **characterized in that** said coated paperboard is produced in a production line wherein a calendering operation is performed only after a coating operation with a calender which is run at high temperature and has a soft extended nip.
13. Method of reducing the susceptibility to crack formation at folding of a coated paperboard according to claim 12, wherein there is additionally performed a calendering operation before said coating operation.

Patentansprüche

1. Beschichtetes Pappmaterial für Formkörper, wobei das Pappmaterial aus einer Fasermatrix in einer, zwei oder mehr Schichten und einer Beschichtung besteht und eine zum Drucken geeignete Oberfläche und einem passenden Oberflächenglanz für jede spezielle Art von Formkörper, **dadurch gekennzeichnet, dass** das Pappmaterial mit einem erwärmbaren Kalandrier nach dem Beschichten kalandriert worden ist, der einen weichen verlängerten Spalt hat, und eine verringerte Dichte und ein verringertes Quadratmetergewicht bei einem gegebenen Wert für eine Biegekraft hat im Vergleich zu einem entsprechenden beschichteten Pappmaterial, das mit einem erwärmbaren oder nicht erwärmbaren Kalandrier mit einem harten oder weichen Spalt vor oder vor und nach dem Beschichten kalandriert worden ist.
2. Beschichtetes Pappmaterial nach Anspruch 1, wobei der gegebene Wert für die Biegekraft im Bereich von 20 bis 300 mN ist, die Verringerung der Dichte im Bereich von 1 bis 50% ist und die Verringerung im Quadratmetergewicht im Bereich von 1 bis 20% ist.
3. Beschichtetes Pappmaterial nach Anspruch 2, wobei der gegebene Wert für die Biegekraft im Bereich von 60 bis

270 mN ist, die Verringerung der Dichte im Bereich von 1 bis 35% ist und die Verringerung im Quadratmetergewicht im Bereich von 1 bis 15% ist.

4. Beschichtetes Pappmaterial nach einem der Ansprüche 1 bis 3, wobei das Pappmaterial ein weißer Deckliner ist.
5. Beschichtetes Pappmaterial nach einem der Ansprüche 1 bis 3, wobei das Pappmaterial ein Flüssigkeitsverpackungskarton ist.
6. Beschichtetes Pappmaterial nach einem der Ansprüche 1 bis 5, wobei sich die Fasermatrix aus zwei Schichten zusammensetzt.
7. Beschichtetes Pappmaterial nach Anspruch 6, wobei sich die Fasermatrix aus ungebleichter Sulfatpulpe in der Bodenschicht und gebleichter Sulfatpulpe in der oberen Schicht zusammensetzt und die Beschichtung Binder und Pigmente umfasst.
8. Produktionslinie zum Herstellen von beschichtetem Pappmaterial, wobei das Pappmaterial aus einer Fasermatrix in einer, zwei oder mehreren Schichten und einer Beschichtung besteht und eine passende Oberfläche zum Drucken und einen passenden Oberflächenglanz für jede spezielle Art von Formkörper hat, **dadurch gekennzeichnet, dass** nur nach der Beschichtungsvorrichtung ein erwärmbare Kalandrier mit einem weichen, verlängerten Spalt angeordnet ist.
9. Produktionslinie zur Herstellung von beschichtetem Pappmaterial nach Anspruch 8, wobei zusätzlich ein Kalandrier vor der Beschichtungseinrichtung angeordnet ist.
10. Verfahren zum Herstellen von beschichtetem Pappmaterial für Formkörper mit einer passenden Oberfläche zum Drucken und einem passenden Oberflächenglanz für jede spezielle Art von Formkörper, wobei die Fasermatrix des Pappmaterials sich aus einer, zwei oder mehreren Schichten zusammensetzt, **dadurch gekennzeichnet, dass** nur nach dem Beschichten ein Kalandrieren mit einem Kalandrier durchgeführt wird, der bei einer hohen Temperatur betrieben wird und einen weichen, verlängerten Spalt hat.
11. Verfahren zum Herstellen von beschichtetem Pappmaterial nach Anspruch 10, wobei zusätzlich ein Kalandrieren vor dem Beschichten durchgeführt wird.
12. Verfahren zum Reduzieren der Anfälligkeit zur Rissbildung beim Falten eines beschichteten Pappmaterials mit einer geeigneten Oberfläche zum Drucken und einem geeigneten Oberflächenglanz für jede spezielle Art von Formkörper, wobei die Fasermatrix des Pappmaterials sich aus einer, zwei oder mehreren Schichten zusammensetzt, **dadurch gekennzeichnet, dass** das beschichtete Pappmaterial in einer Produktionslinie hergestellt wird, in der ein Kalandrieren mit einem Kalandrier nur nach dem Beschichten durchgeführt wird, wobei der Kalandrier bei einer hohen Temperatur betrieben wird und einen weichen verlängerten Spalt hat.
13. Verfahren zum Reduzieren der Anfälligkeit hinsichtlich Rissbildung beim Falten eines beschichteten Pappmaterials nach Anspruch 12, wobei zusätzlich ein Kalandrieren vor dem Beschichten durchgeführt wird.

Revendications

1. Carton portant un revêtement destiné aux articles formés, ledit carton se composant d'une matrice de fibre constituée d'une, de deux ou davantage de couches et d'un revêtement, et présente une surface adéquate pour l'impression et un brillant de surface adéquat pour chaque type spécifique d'articles formés,
caractérisé en ce que ledit carton a été calandré après l'opération de revêtement avec une calandre pouvant être chauffée dotée d'un espacement souple étendu, et **en ce qu'il** présente une densité réduite et un grammage réduit à une valeur donnée pour la force de pliage par comparaison au carton portant un revêtement correspondant qui a été calandré avant, ou avant et après, l'opération de revêtement avec une calandre pouvant être chauffée ou non dotée d'un espacement souple ou rigide.
2. Carton portant un revêtement selon la revendication 1, dans lequel ladite valeur de la force de pliage est comprise entre 20 et 300 mN, ladite réduction de la densité est comprise entre 1 et 50 %, et ladite réduction du grammage est comprise entre 1 et 20 %.

EP 0 815 319 B1

3. Carton portant un revêtement selon la revendication 2, dans lequel ladite force de pliage est comprise entre 60 et 270 Nm, ladite réduction de la densité est comprise entre 1 et 35 %, et ladite réduction du grammage est comprise entre 1 et 15 %.

5 4. Carton portant un revêtement selon l'une quelconque des revendications 1 à 3, dans lequel ledit carton constitue une couverture avec une partie supérieure blanche.

5. Carton portant un revêtement conformément à l'une quelconque des revendications 1 à 5, dans lequel ledit carton constitue un carton d'emballage pour liquides.

10 6. Carton portant un revêtement selon l'une quelconque des revendications 1 à 3, dans lequel la matrice de fibre se compose de deux couches.

15 7. Carton portant un revêtement conformément à la revendication 6, dans lequel ladite matrice de fibre se compose d'une pâte au sulfate non blanchie dans la couche inférieure et d'une pâte au sulfate blanchie dans la couche supérieure, et ledit revêtement se compose de liants et de pigments.

20 8. Chaîne de fabrication destinée à la production de carton portant un revêtement, lequel carton se compose d'une matrice de fibre constituée d'une, de deux ou davantage de couches et d'un revêtement, et présente une surface adéquate pour l'impression et un brillant de surface adéquat pour chaque type spécifique d'articles formés, **caractérisée en ce qu'il** y est disposé, uniquement après un dispositif de revêtement, une calandre pouvant être chauffée dotée d'un espacement souple étendu.

25 9. Chaîne de fabrication destinée à la production de carton selon la revendication 8, dans laquelle est disposée en plus une calandre avant le dispositif de revêtement.

30 10. Processus pour la production de carton portant un revêtement pour articles formés présentant une surface adéquate pour l'impression et un brillant de surface adéquat pour chaque type spécifique d'articles formés, dans lequel la matrice de fibre du carton se compose d'une, de deux ou davantage de couches, **caractérisé en ce qu'une** opération de calandrage n'est effectuée qu'après une opération de revêtement, avec une calandre utilisée à haute température et dotée d'un espacement souple étendu.

35 11. Processus pour la production de carton portant un revêtement selon la revendication 10, dans lequel il est en outre réalisé une opération de calandrage avant ladite opération de revêtement.

40 12. Procédé destiné à réduire l'éventualité de la formation de fissures au moment du pliage d'un carton portant un revêtement présentant une surface adéquate pour l'impression et un brillant de surface adéquat pour chaque type spécifique d'articles formés, dans laquelle la matrice de fibre du carton se compose d'une, de deux ou davantage de couches, **caractérisée en ce que** ledit carton portant un revêtement est produit dans une chaîne de fabrication dans laquelle une opération de calandrage est n'est réalisée qu'après une opération de revêtement avec une calandre fonctionnant à une température élevée et dotée d'un espacement souple étendu.

45 13. Procédé pour réduire l'éventualité de la formation de fissures au moment du pliage d'un carton portant un revêtement selon la revendication 12, dans laquelle il est en outre réalisé une opération de calandrage avant ladite opération de revêtement.