

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 043 342 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
26.10.2005 Bulletin 2005/43

(51) Int Cl.7: **C08F 222/02**, C11D 3/37,
D06M 15/19

(21) Application number: **00107109.1**

(22) Date of filing: **06.04.2000**

(54) **Colorless polymaleates and uses thereof**

Farblose Polymaleate und ihre Anwendungen

Polymaléates incolores et leur utilisations

(84) Designated Contracting States:
DE FR GB

(30) Priority: **06.04.1999 US 286875**

(43) Date of publication of application:
11.10.2000 Bulletin 2000/41

(73) Proprietor: **National Starch and Chemical
Investment Holding Corporation
Wilmington, Delaware 19803-7663 (US)**

(72) Inventors:
• **Austin, Anne-Marie
Signal Mountain, Tennessee 37377 (US)**

• **Carrier, Allen M.
Hixson, Tennessee 37343 (US)**
• **Rodrigues, Klein A.
Signal Mountain, Tennessee 37377 (US)**

(74) Representative: **Held, Stephan et al
Meissner, Bolte & Partner
Postfach 86 03 29
81630 München (DE)**

(56) References cited:
EP-A- 0 745 662 DE-A- 19 516 957
GB-A- 2 152 919 US-A- 4 659 793
US-A- 5 064 563 US-A- 5 925 610

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 043 342 B1

Description

[0001] This invention relates to a low color or colorless polymaleate which is prepared by aqueous solution polymerization of maleic acid, an allylic sulfonate monomer, and a polyvalent transition metal ion. The polymaleates are useful as permanent press agents for textiles, and in laundry detergents to minimize calcium carbonate encrustation.


[0002] Polymaleates are commonly used as water treatment agents, dispersing agents, and chelating agents in applications where color of the polymer is not critical. Since polymaleates generally appear dark brown in color, such polymers are inappropriate for many detergent and textile applications where low color is desirable. This is especially true where the polymer is to be applied to a textile, for example, as a durable press resin where a high color polymer may cause undesired color formation on the textile.

[0003] There are many processes for preparing polymaleates and copolymers thereof, for example, such processes are disclosed in U.S. Patent Nos. 5,135,677; 5,064,563; 4,519,920; 4,555,557; 4,668,735; 4,589,995; and 4,659,793 wherein the polymaleates are prepared in an organic solvent or water. Unfortunately, these processes yield polymaleates which appear dark in color as evidenced by Gardner color number of greater than 8.

[0004] U.S. Patent No. 4,709,091 describes a process for preparing polymaleic acid which involves neutralizing maleic acid in an aqueous medium with an alkali metal hydroxide or ammonia, polymerizing the maleic acid in the presence of an initiator, and adding a further amount of the alkali metal hydroxide or ammonia. U.S. Patent No. 4,709,091 suggests that sulfonate comonomers may be used along with the maleic acid. The polymaleic acid polymers, however, appear dark in color as evidenced by Gardner color number of greater than 8.

[0005] It has now been discovered that a low color or colorless polymaleate, as determined by a Gardner color number of 8 or less, may be prepared by aqueous solution polymerization comprising:

- (a) 70 to 99.9 weight percent of maleic acid;
- (b) 0.1 to 30 weight percent of an allylic sulfonate monomer having the formula



wherein R_1 is selected from the group consisting of H, $\text{C}_1\text{-C}_4$ alkyl, $\text{C}_1\text{-C}_6$ alkoxy, $\text{C}_6\text{-C}_{10}$ aryl, ester, and COOH ; R_2 is O-R_3 wherein R_3 is selected from the group consisting of $\text{C}_1\text{-C}_4$ alkyl, $\text{C}_1\text{-C}_6$ alkoxy, and $\text{C}_6\text{-C}_{10}$ aryl; n is from 0 to 1; and M^+ is a cation selected from the group consisting of H^+ , NH_4^+ , alkali metals, alkaline earth metals, and quaternary organic amines; and

(c) 0.5 to 50 μmoles , based on the moles of monomer, of a polyvalent transition metal ion selected from group consisting of Group IVA, VA, VIA, VIIA, VIIIA, IB, IIB, and combinations thereof; wherein the weight percents are based on the total weight of monomer, provided that 10 to 60 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization.

[0006] According to an additional aspect the invention provides a method for imparting permanent press properties to a textile containing cellulose fibers wherein said method comprises (I) adding an aqueous solution of the low color or colorless polymaleate to a laundering process comprising at least one textile; and (II) heating the textile at a sufficient temperature for a sufficient time to react the polymaleate with the textile wherein water is removed from the textile, to impart permanent press properties to the textile. Optionally, the polymaleate is combined with a catalyst prior to Step (II).

[0007] According to an additional aspect the invention provides a low color or colorless polymaleate as determined by a Gardner color number of 8 or less, said polymaleate is prepared by aqueous solution polymerization comprising 70 to 100 weight percent, based on the total weight of monomer, of maleic acid; and 0.5 to 50 μmoles , based on the moles of monomer, of a polyvalent transition metal ion selected from group consisting of Group IVA, VA, VIA, VIIA, VIIIA, IB, IIB, and combinations thereof; provided that 40 to 55 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization.

[0008] The low color or colorless polymaleate of the present invention provides permanent press properties to textiles treated therewith and increases the resistance of such textiles to laundering abrasion. Such treated textiles display a significant reduction in wrinkles compared with nontreated textiles. Moreover, the treated textiles have a tactile sensation of feeling soft and retain their smoothness after laundering.

[0009] According to a further aspect the invention provides a cleaning composition containing a surfactant and the polymaleate. The polymaleate enhances or "builds" the cleaning efficiency of a surfactant by inactivating hardness ions such as calcium and magnesium, and other metal ions such as iron. The polymaleates soften water by seques-


tration. In addition, the polymaleates assist in cleaning by dispersing and suspending soils to prevent the redeposition of soils onto cleaned substrates. Fabrics washed with detergent compositions containing the polymaleate of the invention have much less calcium carbonate deposited on the fabric as compared to fabrics washed without the polymaleate. Moreover, fabrics washed with detergent compositions containing the polymaleate of the invention display significantly less graying as compared to fabrics washed with detergent compositions without the polymaleates of the invention.

[0010] The low color or colorless polymaleate as determined by a Gardner color number of 8 or less is prepared by aqueous solution polymerization of (a) 70 to 99.9 weight percent of maleic acid, (b) 0.1 to 30 weight percent of an allylic sulfonate monomer, and (c) 0.5 to 50 μ moles, based on the moles of monomer, of a polyvalent transition metal ion selected from group consisting of Group IVA, VA, VIA, VIIA, VIIIA, IB, IIB, and combinations thereof. The weight percents of the maleic acid and allylic sulfonate monomer are based on the total weight of monomer used to prepare the polymaleate.

[0011] As used herein, "polymaleate" includes copolymers and terpolymers of maleic acid. Preferably, the amount of maleic acid which is used to prepare the polymaleate is greater than 80 weight percent, more preferably greater than 90 weight percent, based on the total weight of monomers. Most preferably, the amount of maleic acid monomer which is used to prepare the polymaleate is greater than 98 weight percent. Preferably, the amount of allylic sulfonate monomer which is used to prepare the polymaleate is less than 20 weight percent, more preferably 8 or less weight percent, based on the total weight of monomers. Most preferably, the amount of allylic sulfonate monomer which is used to prepare the polymaleate is less than 2 weight percent.


[0012] The maleic acid may be present as maleic acid and/or maleic anhydride. In the embodiment of the invention wherein an allylic sulfonate comonomer is used with the maleic acid, 10 to 60 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization. Preferably 20 to 50 mole percent, more preferably 30 to 40 mole percent, of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization.

[0013] The allylic sulfonate monomer has the formula




wherein R_1 is selected from H, $\text{C}_1\text{-C}_4$ alkyl, $\text{C}_1\text{-C}_6$ alkoxy, $\text{C}_6\text{-C}_{10}$ aryl, ester, and COOH ; R_2 is OR_3 wherein R_3 is selected from $\text{C}_1\text{-C}_4$ alkyl, $\text{C}_1\text{-C}_6$ alkoxy, and $\text{C}_6\text{-C}_{10}$ aryl; n is from 0 to 1; and M^+ is a cation selected from H^+ , NH_4^+ , alkali metals, alkaline earth metals, and quaternary organic amines. Preferred alkali metals are sodium and potassium. Particularly preferred allylic sulfonate monomers are sodium methallyl sulfonate, sodium allyl sulfonate, and sodium 1-allyloxy-2-hydroxypropyl sulfonate.

[0014] In one embodiment of the invention, the allylic sulfonate monomer is sodium methallyl sulfonate having the formula



[0015] In one embodiment of the invention, the allylic sulfonate monomer is a copolymerizable surfactant having the formula



[0016] In the embodiment of the invention wherein a comonomer is not used with the maleic acid, 40 to 55 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization. Preferably 45 to 50 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization.

[0017] The polyvalent transition metal ion is used to prepare the polymaleates of the invention in an amount of from 0.5 to 50 μ moles, based on total moles of monomer used to prepare the polymaleate. Suitable polyvalent transition metal ions are selected from Group IVA, VA, VIA, VIIA, VIIIA, IB, and Group IIB transition metal ions. Combinations of transition metal ions may also be used. Preferably the transition metal ion is selected from vanadium ions, iron ions, and copper ions. The polyvalent transition metal ion is preferably used in an amount of from 1.6 to 33.2 μ moles, and more preferably 8.3 to 16.6 μ moles. If the amount of polyvalent transition metal ion used is less than 0.5 μ m, the residual monomer level in the polymaleate is unacceptable. If the amount of polyvalent transition metal ion used is greater than 50 μ moles, the color of the polymaleate is unacceptable as determined by a Gardner color number of greater than 8.

[0018] In one embodiment, the polymaleate is used to impart permanent press properties to a textile containing cellulose fibers. As used herein, "permanent press" shall be synonymous with wrinkle resistance, durable press, dimensional stability, shrinkage resistance, and wrinkle recovery. An aqueous solution of the polymaleate is applied to a textile, and the textile is heated in the presence of a catalyst at a sufficient temperature for a sufficient time to react the polymaleate with the textile wherein water is removed from the textile, to impart permanent press properties to the textile. The polymaleate may be applied in the form of an aqueous solution or sprayed.

[0019] Any method of applying the polymaleate to the textile is acceptable. Preferably, the textile is impregnated with an aqueous solution of the polymaleate. As used herein, "impregnate" refers to the penetration of the solution into the fiber matrix of the textile, and to the distribution of the solution in a preferably substantially uniform manner into and through the interstices in the textile. The solution therefore preferably envelopes, surrounds, and/or impregnates individual fibers substantially through the thickness of the textile as opposed to only forming a surface coating on the textile.

[0020] In a preferred embodiment of the invention, the aqueous solution of the polymaleate is applied to the textile in a textile manufacturing process as part of the durable press finishing operation.

[0021] The textiles may be woven or non-woven fabrics and include 100% cellulosic fabrics, for example, cotton, rayon, and linen, as well as blends, for example, polyester/cotton or polyester/rayon. Such blends preferably contain at least 20% of cellulose. Both white and colored (printed, dyed, yam-dyed, cross-dyed) fabrics can be effectively treated with the polymaleate of this invention. The textiles may comprise new or used clothing including previously worn clothing and/or laundered clothing. Preferably, the textiles contain free hydroxyl groups.

[0022] A catalyst may be used to speed up the reaction between the polymaleate and textile. The catalyst also increases the degree of crosslinking in the reaction of the carboxyl groups on the polymaleate and hydroxyl groups on the textile. While not wishing to be bound by any theory, the inventors believe that the catalyst decreases the zeta potential or the amount of negative charge on the textile surface and thus increases the amount of polymaleate which is deposited on the textile or fabric from the aqueous solution. Any substance that can accept an electron pair from a base can be used as a catalyst.

[0023] Preferably, the catalyst is a Lewis acid catalyst selected from dibutyltindilaurate, iron(III)chloride, scandium (III)trifluoromethanesulfonic acid, boron trifluoride, tin(IV)chloride, $\text{Al}_2(\text{SO}_4)_3 \cdot x\text{H}_2\text{O}$, $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, $\text{AlK}(\text{SO}_4)_2 \cdot 10\text{H}_2\text{O}$, and Lewis acids having the formula NX_p wherein N is a metal, X is a halogen atom or an inorganic radical, and p is an integer of from 1 to 4, such as BX_3 , AlX_3 , FeX_3 , GaX_3 , SbX_3 , SnX_4 , AsX_5 , ZnX_2 , and HgX_2 . More preferably, the Lewis acid catalyst is selected from $\text{Al}_2(\text{SO}_4)_3 \cdot x\text{H}_2\text{O}$, $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, $\text{AlK}(\text{SO}_4)_2 \cdot 10\text{H}_2\text{O}$. A combination of catalysts can also be used in the method of the invention.

[0024] The treated textile is cured at the normal temperatures provided by either a drying unit used in a textile manufacturing process such as a steam heated drying cylinder, an oven, or an iron. Drying temperatures generally range from 90°C to 300°C. Such temperatures permit water to be removed, thereby inducing crosslinking between the polymaleate and textile.

[0025] The residence time of the textile in the dryer unit, oven, or in contact with an iron ranges from 1 second to 200 seconds, depending on the temperature. The actual residence time for a particular textile sample depends on the temperature, pressure, type of fabric, and the type and amount of catalyst. Preferably, the time and temperature required to cure the polymaleate with the textile ranges from 2 to 60 seconds at a textile temperature ranging from 100°C to 250°C. After the textile with the solution of the polymaleate applied thereto is dried/cured, subsequent coatings or additives may be applied.

[0026] In a preferred embodiment, a textile treated with the polymaleate is ironed both on the inside and outside surfaces to maximize the amount of crosslinking and thus permanent press properties of the textile.

[0027] Preferred means of applying the aqueous solution of the polymaleate on a textile manufacturing machine are by puddle press, size press, blade coater, speedsizer, spray applicator, curtain coater and water box. Preferred size press configurations include a flooded nip size press and a metering blade size press.

[0028] Preferred means of applying the aqueous solution of the polymaleate on off-machine coating equipment in a textile manufacturing process are by rod, gravure roll and air knife. The solution may also be sprayed directly onto the textile or onto rollers which transfer the solution to the textile. In an especially preferred embodiment of the invention, impregnation of the textile with the aqueous solution of the polymaleate occurs by means of a puddle size press.

[0029] Preferred means of applying the aqueous solution of the polymaleate in a laundering process are by adding the solution to the rinse water during the rinse cycle in the laundering process. In an especially preferred embodiment of the invention, impregnation of the textile with the aqueous solution of the polymaleate occurs during the final rinse cycle in a laundering process. In an additional especially preferred embodiment of the invention, impregnation of the textile with the aqueous solution of the polymaleate occurs in a washing machine which contains at least one textile, the polymaleate and optionally a catalyst, wherein the washing machine is not operating so that the textile remains in contact with the treatment solution for a period of time to facilitate the impregnation of the treatment solution into the textiles. The washing machine is turned on to the spin cycle, the textiles are removed, dried and ironed.

[0030] Another preferred means of applying the aqueous solution of the polymaleate to a textile such as clothing is spraying by means of a pump or aerosol a solution of the polymaleate onto the textile and then ironing the textile.

[0031] The concentration of the polymaleate in the aqueous solution is sufficient to provide from 0.1 to 10 weight percent of polymaleate in the textile based on the oven-dry weight of the textile. Preferably, the concentration of polymaleate in the aqueous solution is sufficient to provide from 1 to 5 weight percent, more preferably from 2 to 4 weight percent of polymaleate in the textile based on the oven-dry weight of the textile.

[0032] In another embodiment, the low color or colorless polymaleates are used in a cleaning composition. The concentration of polymaleate in the cleaning composition is from 0.1 to 50 weight percent, preferably 0.5 to 20, based on the total weight of the cleaning composition. Examples of cleaning compositions are laundry detergents, prespotters, dishwashing detergents, and hard surface cleaners. Examples of articles which may be cleaned using the cleaning compositions are fabrics, such as clothing, linens, carpets, or upholstery; hard surfaces such as countertops, windows, floors, dishes, glasses or tiles; or automobiles.

[0033] The cleaning composition may be a solid or liquid composition. If the cleaning composition is solid, the cleaning composition may be in any of the usual physical forms, such as for example, powders, beads, flakes, bars, tablets, noodles, pastes, and slurries. If the cleaning composition is liquid, the cleaning composition preferably disperses or solubilizes the polymaleate. The cleaning composition may be aqueous or nonaqueous. For example, the polymaleate may be dissolved or dispersed in water, in one or more solvents or inert diluents. Preferably the cleaning composition is aqueous.

[0034] The cleaning compositions may contain any additional components which are used in cleaning compositions. Such additional components are well known to those skilled in the art and include one or more surfactants, builders, ion exchangers, alkalies, anticorrosion materials, antiredeposition materials, optical brighteners, fragrances, dyes, chelating agents, enzymes, whiteners, brighteners, antistatic agents, sudsing control agents, solvents, hydrotropes, bleaching agents, perfumes, bleach precursors, water, buffering agents, soil removal agents, soil release agents, softening agents, opacifiers, inert diluents, buffering agents, corrosion inhibitors, graying inhibitors, anti-redeposition agents, stabilizers, opacifiers, fillers, builders, phosphate co-builder, and phosphate-replacer builder. Combinations of such additional components may also be used.

[0035] Preferably cleaning compositions prepared using the polymaleates contain at least one surfactant. Suitable surfactants include nonionic, anionic, cationic, and amphoteric surfactants. The surfactants usable in the cleaning composition may also be soaps.

[0036] Anionic surfactants include, for example, from C₈ to C₁₂ alkylbenzenesulfonates, from C₁₂ to C₁₆ alkanesulfonates, from C₁₂ to C₁₆ alkylsulfates, from C₁₂ to C₁₆ alkylsulfosuccinates or from C₁₂ to C₁₆ sulfated ethoxylated alkanols.

[0037] Nonionic surfactants include, for example, from C₆ to C₁₂ alkylphenol ethoxylates, from C₁₂ to C₂₀ alkanol alkoxyates, and block copolymers of ethylene oxide and propylene oxide. Optionally, the end groups of polyalkylene oxides can be blocked, whereby the free OH groups of the polyalkylene oxides can be etherified, esterified, acetalized and/or aminated. Another modification consists of reacting the free OH groups of the polyalkylene oxides with isocyanates. The nonionic surfactants also include C₄ to C₁₈ alkyl glucosides as well as the alkoxyated products obtainable therefrom by alkoxylation, particularly those obtainable by reaction of alkyl glucosides with ethylene oxide.

[0038] Cationic surfactants contain hydrophilic functional groups where the charge of the functional groups are positive when dissolved or dispersed in an aqueous solution. Typical cationic surfactants include, for example, amine compounds, oxygen containing amines, and quaternary amine salts.

[0039] Amphoteric surfactants contain both acidic and basic hydrophilic groups. Amphoteric surfactants are preferably derivatives of secondary and tertiary amines, derivatives of quaternary ammonium, quaternary phosphonium or tertiary sulfonium compounds. The cationic atom in the quaternary compound can be part of a heterocyclic ring. The amphoteric surfactant preferably contains at least one aliphatic group, containing about 3 to 18 carbon atoms. At least one aliphatic group preferably contains an anionic water-solubilizing group such as a carboxy, sulfonate, or phosphono.

[0040] Generally, anionic surfactants, such as linear alkyl sulfonates (LAS) are preferred for use in solid cleaning compositions containing the polymaleate. Nonionic and anionic surfactant mixtures such as alcohol ethoxylates and LAS are preferred in liquid cleaning compositions containing the polymaleate. The surfactants are optionally present in an amount of from 0 to 50 weight percent, preferably from 2 to 45 weight percent, and more preferably from 5 to 40

weight percent of the cleaning composition.

[0041] Examples of builders which may be present in the cleaning composition include, for example, phosphates, such as pyrophosphates, polyphosphates, or sodium tripolyphosphate. Further examples are zeolites, sodium carbonate, poly(carboxylic acids), nitriloacetic acid, citric acid, tartaric acid, the salts of the aforesaid acids and the monomeric, oligomeric, or polymeric phosphonates. Combinations of builders may also be used. The builders are optionally present in an amount of from 0 to about 85 weight percent, preferably from 5 to 50 weight percent based on the total weight of the cleaning composition.

[0042] Liquid cleaning compositions containing the polymaleate can contain up to 80 weight percent water or solvents or combinations thereof. Typical solvents which may be used include oxygen containing solvents such as alcohols, esters, glycol, and glycol ethers. Alcohols that may be used in the cleaning compositions include, for example, methanol, ethanol, isopropanol, and tertiary butanol. Esters which may be used include, for example, amyl acetate, butyl acetate, ethyl acetate, and esters of glycols. Glycols and glycol ethers that are useful as solvents include, for example, ethylene glycol, propylene glycol, and oligomers of ethylene or propylene glycol.

[0043] Solid cleaning compositions containing the polymaleate preferably contain up to 60 weight percent of one or more solid inert diluents such as sodium sulfate, sodium chloride, sodium borate, or selected polymers such as polyethylene glycol or propylene glycol.

[0044] In a cleaning composition, the polymaleate enhances or "builds" the cleaning efficiency of a surfactant by inactivating hardness ions such as calcium and magnesium, and other metal ions such as iron. The polymaleates soften water by sequestration. In addition, the polymaleates assist in cleaning by dispersing and suspending soils to prevent the redeposition of soils onto cleaned substrates.

[0045] The following nonlimiting examples illustrate further aspects of the invention.

EXAMPLE 1

Preparation of polymaleate without allylic sulfonate.

[0046] A mixture containing 98 g of maleic anhydride, 75 g of water and 14 mg of ferrous ammonium sulfate hexahydrate ($10.7 \mu\text{moles Fe}^{2+}$ based on moles of monomer) were added to a reactor. The reactor was heated to 96°C to 98°C and the reaction temperature was maintained for 5 hours. Concurrently, 55 g of a 35% hydrogen peroxide solution was added to the reactor during the 5 hours. After the addition of the hydrogen peroxide was complete, the reaction temperature was maintained at 96°C to 98°C for an additional 2 hours to form a polymaleate product.

[0047] The polymaleate appeared amber to dark brown in color and was clear. The polymaleate was determined to have a Gardner Color Number of greater than 10.

EXAMPLE 2

Preparation of sodium polymaleate without allylic sulfonate.

[0048] A mixture containing 98 g of maleic anhydride, 75 g of water, 48 g of 50% NaOH (30 mole % carboxyl groups on the maleic acid were neutralized), 7 mg of ferrous ammonium sulfate hexahydrate ($5.4 \mu\text{moles Fe}^{2+}$ based on moles of monomer) were added to a reactor. The reactor was heated to 96°C to 98°C and the reaction temperature was maintained for 5 hours. Concurrently, 55 g of a 35% hydrogen peroxide solution was added to the reactor during the 5 hours. After the addition of the hydrogen peroxide was complete, the reaction temperature was maintained at 96°C to 98°C for an additional 2 hours to form a polymaleate product.

[0049] The polymaleate appeared amber in color during the polymerization, but upon cooling the residual maleic acid precipitated.

EXAMPLE 3

Preparation of a low color polymaleate with sodium methallyl sulfonate.

[0050] A mixture containing 76 grams of maleic anhydride (0.775 mol), 70 g of water, 62 g of a 50% solution of NaOH (50 mole % carboxyl groups on the maleic acid were neutralized), and 5.3 mg of ferrous ammonium sulfate hexahydrate ($5.4 \mu\text{moles Fe}^{2+}$ based on moles of monomer) were added to a reactor. The reactor was heated to 96°C to 98°C and the reaction temperature was maintained for 5 hours. The heat of neutralization caused a rapid rise in reaction temperature to 95°C - 98°C . The time duration during which the reactor temperature was at 50°C - 70°C was minimized to minimize the isomerization of maleic acid to fumaric acid, since the latter is extremely difficult to polymerize. When the temperature reached 96°C , 2.14 grams of sodium methallyl sulfonate (0.0135 mol) was added to the reaction mixture.

EP 1 043 342 B1

Concurrently, 55 g of a 35% hydrogen peroxide solution was added to the reactor during the 5 hours. After the addition of the hydrogen peroxide was complete, the reaction temperature was maintained at 96°C to 98°C for an additional 2 hours to form a polymaleate polymer product.

[0051] The polymaleate appeared pale yellow in color and was clear. The polymaleate was determined to have a Gardner Color Number of <1.

EXAMPLE 4

[0052] A polymaleate with sodium methallyl sulfonate was prepared according to the procedure in Example 3 except that 20 mole % of the carboxyl groups on the maleic acid were neutralized instead of 50 mole %.

[0053] The polymaleate appeared medium yellow in color and was clear. The polymaleate was determined to have a Gardner Color Number of 6.

EXAMPLE 5

[0054] A polymaleate with sodium methallyl sulfonate was prepared according to the procedure in Example 3 except that 40 mole % of the carboxyl groups on the maleic acid were neutralized instead of 50 mole %.

[0055] The polymaleate appeared pale yellow in color and was clear. The polymaleate was determined to have a Gardner Color Number of 3.

EXAMPLE 6 (Reference example)

Preparation of a low color polymaleate with copolymerizable surfactant (sodium-1 -allyloxy-2-hydroxypropylsulfonate).

[0056] A mixture containing 76 grams of maleic anhydride (0.775 mol), 70 g of water, 62 g of a 50% solution of NaOH (40 mole % carboxyl groups on the maleic acid were neutralized), and 5.3 mg of ferrous ammonium sulfate hexahydrate (5.4 μ moles Fe^{2+} based on moles of monomer) were added to a reactor. The reactor was heated to 96°C to 98°C and the reaction temperature was maintained for 5 hours. The heat of neutralization caused a rapid rise in reaction temperature to 95°C-98°C. The time duration during which the reactor temperature was at 50°C- 70°C was minimized to minimize the isomerization of maleic acid to fumaric acid, since the latter is extremely difficult to polymerize. When the temperature reached 96°C, 5.5 grams of sodium-1 -allyloxy-2-hydroxypropylsulfonate (COPS) (1.8 weight % based on total polymer solids) was added to the reaction mixture. Concurrently, 55 g of a 35% hydrogen peroxide solution was added to the reactor during the 5 hours. After the addition of the hydrogen peroxide was complete, the reaction temperature was maintained at 96°C to 98°C for an additional 2 hours to form a polymaleate polymer product.

[0057] The polymaleate appeared pale yellow in color and was clear. The polymaleate was determined to have a Gardner Color Number of 2.

EXAMPLES 7-9

[0058] Preparation of low color polymaleates with sodium methallyl sulfonate according to the procedure set forth in Example 3 except for variations in the amount of neutralization and amount of iron which are described in Table I.

[0059] The polymaleates appeared pale yellow in color and were clear. The polymaleates were determined to have Gardner Color Values of 2, <1, and 2, respectively.

EXAMPLES 10-14 (Example 12 being a reference example)

[0060] Preparation of polymaleates according to the procedure set forth in Example 5 except that different comonomers, as described in Table I, were used with maleic acid. All of the polymaleates precipitated except for Example 12 which was a polymaleate prepared with an allylic sulfonate comonomer.

EXAMPLES 15-17 (Example 17 being a reference example)

[0061] Preparation of polymaleates according to the procedure set forth in Example 2 except that different comonomers, as described in Table I, were used with maleic acid. All of the polymaleates precipitated except for Example 17 which was a polymaleate prepared with an allylic sulfonate comonomer.

EXAMPLES 18-24

[0062] Preparation of polymaleates according to the procedure set forth in Example 1 without a comonomer, except for variations in the amount of neutralization and amount of iron which are described in Table I.

[0063] The polymaleates either precipitated or had a Gardner Color Number of greater than 8, except for Example 24 which was 50 mole percent neutralized and 10 ppm of iron. The polymaleate of Example 24 was determined to have Gardner Color Values of 6.

TABLE I

Polymer	Allylic Sulfonate Monomer wt. %	Appearance/ Gardner Value (GCV)	Residual Maleic Acid %	% Neutralization Conc. Fe ²⁺ (based on moles of monomer)
Example 1	NONE	Dark Amber/ GCV=>12	1.5%	0 mole% 10.7 μ moles Fe ²⁺
Example 2	NONE	Precipitate		30 mole% 5.4 μ moles Fe ²⁺
Example 3	Sodium Methallyl Sulfonate 1.8%	Clear Pale Yellow/ GCV=<1	0.96%	50 mole% 5.4 μ moles Fe ²⁺
Example 4	Sodium Methallyl Sulfonate 1.8%	Clear Tea Colored/ GCV=6	1.05%	20 mole% 5.4 μ moles Fe ²⁺
Example 5	Sodium Methallyl Sulfonate 1.8%	Clear Pale Yellow/ GCV=3	0.62%	40 mole% 5.4 μ moles Fe ²⁺
Reference Example 6	Sodium-1-Allyloxy-2-Hydroxypropyl sulfonate	Clear Pale Yellow/ GCV=2	0.50%	50 mole% 5.4 μ moles Fe ²⁺
Example 7	Sodium Methallyl Sulfonate	Clear Pale Yellow/ GCV=<1	0.597%	50 mole% 2.7 μ moles Fe ²⁺
Example 8	Sodium Methallyl Sulfonate	Clear Pale Yellow/ GCV=2	1.32%	40 mole% 2.7 μ moles Fe ²⁺
Example 9	Sodium Methallyl Sulfonate	Clear Pale Yellow/ GCV=5		30 mole% 5.4 μ moles Fe ²⁺
Example 10	Sodium SulfoPhenyl Methallyl Ether	Precipitate Formed after 1 week	1.22%	40 mole% 5.4 μ moles Fe ²⁺
Example 11	Acrylamido Methyl Propane Sulfonate, Sodium Salt	Precipitate		40 mole% 5.4 μ moles Fe ²⁺
Reference Example 12	Sodium-1-Allyloxy 2-Hydroxypropyl Sulfonate	Clear Pale Yellow/ GCV=5	0.67%	40 mole% 5.4 μ moles Fe ²⁺
Example 13	Allylanisole	Precipitate		40 mole% 5.4 μ moles Fe ²⁺
Example 14	Dimethyl Diallyl Ammonium Chloride	Precipitate		40 mole% 5.4 μ moles Fe ²⁺
Example 15	Allyl Alcohol	Precipitate		30 mole% 5.4 μ moles Fe ²⁺
Example 16	Allyl Methacrylate	Precipitate		30 mole% 5.4 μ moles Fe ²⁺

TABLE I (continued)

Polymer	Allylic Sulfonate Monomer wt. %	Appearance/ Gardner Value (GCV)	Residual Maleic Acid %	% Neutralization Conc. Fe ²⁺ (based on moles of monomer)
Reference Example 17	Sodium-1-Allyloxy-2-Hydroxypropyl Sulfonate	Clear Amber/ GCV=7	0.55%	30 mole% 5.4 $\mu\text{mole Fe}^{2+}$
Example 18	NONE	Clear Amber/ GCV=12	0.25%	60 mole% 27 $\mu\text{mole Fe}^{2+}$
Example 19	NONE	Precipitate		60 mole% 0.54 $\mu\text{mole Fe}^{2+}$
Example 20	NONE	Clear Tea Colored/ GCV=12	1.39%	40 mole% 5.4 $\mu\text{mole Fe}^{2+}$
Example 21	NONE	Precipitate		40 mole% 2.7 $\mu\text{mole Fe}^{2+}$
Example 22	NONE	Precipitate		60 mole% 5.4 $\mu\text{mole Fe}^{2+}$
Example 23	NONE		27%	100 mole% 5.4 $\mu\text{mole Fe}^{2+}$
Example 24	NONE	Clear Pale Yellow/ GCV-6	0.734%	50 mole% 5.4 $\mu\text{mole Fe}^{2+}$

[0064] The test results in Table I show that low color or colorless polymaleates, as determined by a Gardner color number of 8 or less, were prepared with 70 to 99.9 weight percent of maleic acid, 0.1 to 30 weight percent of an allylic sulfonate monomer, and 0.5 to 50 mof a polyvalent metal ion, provided that 10 to 60 mole percent of the carboxylic acid groups on the maleic acid were neutralized prior to polymerization. In addition, the test results in Table I show that low color or colorless polymaleates, as determined by a Gardner color number of 8 or less, were prepared with 100 weight percent of maleic acid without a comonomer, and 0.5 to 50 μmol a polyvalent metal ion, provided that 40 to 55 mole percent of the carboxylic acid groups on the maleic acid were neutralized prior to polymerization.

EXAMPLE 25

Procedure for evaluating polymaleate prepared in Example 3 as permanent press agent in textile applications.

[0065]

1. Polymer solutions for two polymaleate samples as prepared in Example 3 were prepared at 8% polymaleic (on solids) and 4% sodium hypophosphite in one sample as a catalyst and aluminum potassium sulfate ($\text{AlK}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$) in aqueous solution as a catalyst in the other sample.
2. The polymaleate was placed into a 1 liter plastic container. The required amount of catalyst was added and deionized water was added until the total weight was 500g.
3. The polymaleate solution was mixed with a magnetic stirrer until all solids were dissolved and the solution was clear. The solution was removed from the stirrer. A control sample was prepared with no polymaleate polymer or catalyst.
4. For each polymaleate sample and for the control, a piece of the cotton swatch 14" x 14" (35,6 x 35,6 cm) was cut and all selvages from the fabric were removed.
5. The swatches were placed into their respective solutions and allowed to soak for 10 minutes.
6. The swatches were removed from the solutions and placed onto an embroidery hoop, stretching evenly until taut.
7. The hoops containing the swatches were placed into a laboratory oven set at 85°C for 5 minutes until dry and then removed from the oven.
8. The hoops containing the swatches were placed into a laboratory oven set at 185°C to cure the carboxyl groups on the polymaleate with the hydroxyl groups on the cotton swatch samples for 2 minutes. The swatches were

EP 1 043 342 B1

removed from the oven and allowed to cool.

9. The swatches were removed from the embroidery hoops and washed in a washing machine with 0.9g/L AATCC standard detergent and a 10 minute regular wash cycle with hot water and a cold rinse.

10. The swatches were dried in a tumble dryer on high heat for 20 minutes. Three white bath towels were added to the dryer along with the swatches for ballast. After 20 minutes, the swatches were removed immediately and set on a flat surface.

11. The smoothness of each swatch was visually observed and recorded. The test results are summarized in Table II.

TABLE II

Permanent Press Finishing on Cotton Swatches.				
Swatch Sample	Polymaleate/ wt. %	AlK (SO ₄) ₂ 12H ₂ O wt. %	NaH ₂ PO ₂ wt. %	Result
Control	None	0	0	very wrinkled
1	Example 3/ 8%	4%		very few wrinkles
2	Example 3/ 8%		4%	very few wrinkles

[0066] The test results in Table II show that the cotton swatches pretreated with a polymaleate according to the invention which was prepared with less than 2 weight percent of sodium methallyl sulfonate, and combined with a catalyst were significantly less wrinkled after washing than the control swatch which was not pretreated with a polymaleate.

EXAMPLE 26

[0067] Procedure for evaluating the polymaleate prepared in Example 4 for anti-encrustation properties in commercial laundry detergent formulations:

1. Black cotton interlock fabric available from Test Fabrics Inc. was cut into 7" x 7" (17,8 x 17,8 cm) swatches. Weigh a total of 40 grams (+/- 0.2g) of swatches for each test which is conducted in a tergitometer, trimming one of the swatches in each test as necessary to obtain the desired weight.

2. Add 1L of water having a hardness:(Ca:Mg = 2:1), 150 ppm as calcium carbonate, to each tergitometer.

3. Weigh the required amount of 1.24 g of TIDE powder detergent and 0.9 g of powder bleach into disposable weigh boats.

4. Weigh the specified amount of polymer into weigh boats, typically 4% dry/detergent weight. A control sample was prepared without any polymer.

5. Add the detergent and polymer to the tergitometer pots, and agitate for 30 seconds to homogenize the wash water. Add the fabric to the pots and wash for 10 minutes. During the wash cycle, the water temperature was approximately 93°F (34 °C), wash time 10 minutes, rinse time 5 minutes, agitator speed 80-100 rpm.

6. At the completion of the wash cycle, the tergitometer pots were drained, and 1 L of the water as described above was used to rinse the swatches for 5 minutes.

7. The swatches were dried in a tumble dryer on high heat for 20 minutes.

8. Steps 2-7 were repeated for a total of 5 wash/dry cycles.

9. From three separate swatches from each tergitometer pot, cut 2" x 2" (5,1 x 5,1cm) swatches. Weigh each swatch on the analytical balance and place in a labeled specimen cup.

10. Place each small swatch into 20 grams of 10% nitric acid, agitating slightly for 1 minute to dissolve the CaCO₃ on the swatch. Decant the nitric acid into a graduated cylinder. Rinse the swatch twice more with deionized water, decanting the water into the cylinder after each rinse. Add 1 ml of 12% KCl solution to the cylinder, then add deionized water to make up a volume of 200ml.

11. Filter 30-50ml of the solution to remove fibers, pour each sample into a labeled container and submit for the determination of ppm calcium with atomic absorption spectroscopy.

12. The percent of CaCO₃ was determined according to the following formula:

$$\text{Wt. \% CaCO}_3 = \frac{\text{ppm Ca} \times (x)^*}{40(\text{wt. of swatch})}$$

- x =(x00) dilution of solution after nitric acid wash, which is 2 in this case. The test results are summarized in Table III.

TABLE III


Polymer	Wt.% CaCO ₃ , based on weight of Fabric	Visual Color Examination
NONE (Control)	1.13 wt. %	Very Gray
Polymaleate of Ex. 4	0.57 wt. %	Much Less Gray

[0068] The test results in Table III show that fabrics washed with detergent compositions containing the polymaleate of the invention have much less calcium carbonate deposited on the fabric as compared to the fabric without the polymaleate. In addition, Table III also shows that fabrics washed with detergent compositions containing the polymaleate of the invention display significantly less graying as compared to fabrics washed with detergent compositions without the polymaleates of the invention.

Claims

1. A low color or colorless polymaleate as determined by a Gardner color number of 8 or less, said polymaleate is prepared by aqueous solution polymerization comprising:

- (a) 70 to 99.9 weight percent of maleic acid;
- (b) 0.1 to 30 weight percent of an allylic sulfonate monomer having the formula



wherein R₁ is selected from the group consisting of H, C₁₋₄ alkyl, C₁₋₆ alkoxy, C₆₋₁₀ aryl, ester, and COOH; R₂ is O-R₃ wherein R₃ is selected from the group consisting of C₁₋₄ alkyl, C₁₋₆ alkoxy, and C₆₋₁₀ aryl; n is from 0 to 1; and M⁺ is a cation selected from the group consisting of H⁺, NH₄⁺, alkali metals, alkaline earth metals, and quaternary organic amines; and

- (c) 0.5 to 50 μmoles, based on the moles of monomer, of a polyvalent transition metal ion selected from group consisting of Group IVA, VA, VIA, VIIA, VIIIA, IB, IIB, and combinations thereof;

wherein the weight percents are based on the total weight of monomer, provided that 10 to 60 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization.

2. The polymaleate according to Claim 1 wherein 20 to 50 mole percent of the carboxylic acid groups on the maleic acid are neutralized prior to polymerization.
3. The polymaleate according to Claim 1 wherein the amount of maleic acid which is used to prepare the polymaleate is greater than 80 weight percent and the amount of the allylic sulfonate monomer is less than 20 weight percent.
4. The polymaleate according to Claim 1 wherein the allylic sulfonate monomer is selected from the group consisting of alkali, alkaline earth metal and ammonium salts of allylic sulfonate monomers.
5. The polymaleate according to Claim 1 wherein the polyvalent transition metal ion is used in an amount of from 1.6 to 33.2 μmoles.
6. A method for imparting permanent press properties to a textile containing cellulose fibers comprising the steps of:
 - adding thereto the low color or colorless polymaleate of Claims 1 - 5 to a laundering process having at least one textile; and

heating the textile at a sufficient temperature for a sufficient time to react the polymaleate with the textile,


wherein water is removed from the textile and permanent press properties are imparted to the textile.

7. The method according to Claim 6 wherein a Lewis acid catalyst is combined with the polymaleate prior to heating the textile.
8. The method according to Claim 7 wherein the Lewis acid catalyst is selected from the group consisting of dibutyltindilaurate, iron(III)chloride, scandium(III)trifluoromethane sulfonic acid, boron trifluoride, tin(IV)chloride, $\text{Al}_2(\text{SO}_4)_3 \cdot x\text{H}_2\text{O}$, $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, $\text{AlK}(\text{SO}_4)_2 \cdot 10\text{H}_2\text{O}$, and Lewis acids having the formula NX_p wherein N is a metal, X is a halogen atom or an inorganic radical, and p is an integer of from 1 to 4.
9. A cleaning composition comprising at least one surfactant and from 0.1 to about 50 weight percent, based on the weight of the cleaning composition, of a low color or colorless polymaleate of Claims 1 - 8.
10. A method of cleaning comprising
 - preparing a cleaning composition comprising at least one surfactant and the polymaleate according to Claims 1 - 9,
 - contacting the cleaning composition with one or more articles, wherein at least one of the articles contains soil, and
 - removing at least a portion of the soil from the article containing soil, wherein the polymaleate disperses and suspends soils to prevent the redeposition of soils onto the cleaned articles.

Patentansprüche

1. Schwachgefärbtes oder farbloses Polymaleat, bestimmt durch eine Gardner-Farbzahl von 8 oder weniger, wobei das Polymaleat durch wässrige Lösungspolymerisation hergestellt ist, umfassend:

- (a) 70 bis 99,9 Gew.-% Maleinsäure
- (b) 0,1 bis 30 Gew.-% eines allylischen Sulfonatmonomers mit der Formel



wobei R_1 aus der Gruppe ausgewählt ist, die aus H, C_1 - C_4 -Alkyl, C_1 - C_6 -Alkoxy, C_6 - C_{10} -Aryl, Ester und COOH besteht, R_2 $\text{O}-\text{R}_3$ ist, wobei R_3 aus der Gruppe ausgewählt ist, die aus C_1 - C_4 -Alkyl, C_1 - C_6 -Alkoxy und C_6 - C_{10} -Aryl besteht; n 0 bis 1 ist; und M^+ ein Kation ist, ausgewählt aus der Gruppe, die aus H^+ , NH_4^+ , Alkalimetallen, Erdalkalimetallen und quaternären organischen Aminen besteht; und

(c) 0,5 bis 50 μmol , bezogen auf die Molmenge an Monomer, eines polyvalenten Übergangsmetallions, ausgewählt aus der Gruppe, die aus den Gruppen IVA, VA, VIA, VIIA, VIIIA, IB, IIB und Kombinationen daraus besteht;

wobei die Gew.-% auf das Gesamtgewicht an Monomer bezogen sind, mit der Maßgabe, dass 10 bis 60 Mol% der Carbonsäuregruppen in der Maleinsäure vor der Polymerisation neutralisiert sind.

2. Polymaleat nach Anspruch 1, wobei 20 bis 50 Mol% der Carbonsäuregruppen in der Maleinsäure vor der Polymerisation neutralisiert sind.
3. Polymaleat nach Anspruch 1, wobei die Menge der zur Herstellung des Polymaleats verwendeten Maleinsäure größer als 80 Gew.-% ist, und wobei die Menge des allylischen Sulfonatmonomers kleiner als 20 Gew.-% ist.
4. Polymaleat nach Anspruch 3, wobei das allylische Sulfonatmonomer aus der Gruppe bestehend aus Alkali-, Erdalkalimetallen und Ammoniumsalzen von allylischen Sulfonatmonomeren ausgewählt ist.

5. Polymaleat gemäß Anspruch 1, wobei das polyvalente Übergangsmetallion in einer Menge von 1,6 bis 33,2 µmol verwendet wird.

6. Verfahren zum Erzeugen von permanenten Bügeleigenschaften bei einem Cellulosefasern enthaltenden Textil, wobei das Verfahren umfasst:

Zugabe des schwach gefärbten oder farblosen Polymaleats nach Anspruch 1 bis 5 zu einem Waschverfahren, bei dem mindestens ein Textil vorliegt, und

Erhitzen des Textils auf eine hinreichende Temperatur für eine hinreichende Zeit, um dass Polymaleat mit dem Textil zur Reaktion zu bringen,

wobei Wasser von dem Textil entfernt wird, um permanente Bügeleigenschaften bei dem Textil zu erzeugen.

7. Verfahren nach Anspruch 6, wobei ein Levissäurekatalysator mit dem Polymaleat vor dem Erhitzen des Textils kombiniert wird.

8. Verfahren nach Anspruch 7, wobei der Levissäurekatalysator aus der Gruppe bestehend aus Dibutylzinndilaurat, Eisen(III)chlorid, Scandium(III)trifluoromethan, Sulfonsäure, Bortrifluorid, Zinn(IV)chlorid, $Al_2(SO_4)_3 \cdot xH_2O$, $MgCl_2 \cdot 6H_2O$, $AlK(SO_4)_2 \cdot 10H_2O$, und Levissäuren mit der Formel NX_p , wobei N ein Metall, X ein Halogenatom oder ein anorganischer Rest und p eine ganze Zahl von 1 bis 4 ist.

9. Reinigungszusammensetzung, umfassend mindestens ein Tensid und etwa 0,1 bis 50 Gew.-%, bezogen auf das Gewicht der Reinigungszusammensetzung, eines schwach gefärbten oder farblosen Polymaleats nach einem der Ansprüche 1 bis 8.

10. Reinigungsverfahren umfassend

Herstellen einer Reinigungszusammensetzung, die mindestens ein Tensid und Polymaleat nach einem der Ansprüche 1 bis 9 umfasst,

Inkontaktbringen der Reinigungszusammensetzung mit einem oder mehreren Artikeln, wobei mindestens einer der Artikel Schmutz enthält und


Entfernen mindestens eines Teils des Schmutzes von dem Schmutz enthaltenden Artikel, wobei das Polymaleat den Schmutz auflöst und suspendiert, um die erneute Absetzung von Schmutz auf den gereinigten Artikels zu vermeiden.

Revendications

1. Polymaléate faiblement coloré ou incolore, de la manière déterminée par un indice de couleur Gardner égal ou inférieur à 8, ledit polymaléate étant préparé par une polymérisation en solution aqueuse, comprenant :

(a) 70 à 99,9 % en poids d'acide maléique ;

(b) 0,1 à 30 % en poids d'un monomère sulfonate allylique répondant à la formule



dans laquelle R^1 est choisi dans le groupe consistant en H, des groupes alkyle en C_1 à C_4 , alkoxy en C_1 à C_6 , aryle en C_6 à C_{10} , ester et $COOH$; R^2 représente un groupe $O-R^3$ dans lequel R^3 est choisi dans le groupe consistant en des groupes alkyle en C_1 à C_4 , alkoxy en C_1 à C_6 et aryle en C_6 à C_{10} ; n a une valeur de 0 à 1 et M^+ représente un cation choisi dans le groupe consistant en H^+ , NH_4^+ , des métaux alcalins, des métaux alcalinoterreux, des amines organiques quaternaires ; et

(c) 0,5 à 50 µmoles, sur la base du nombre de moles du monomère, d'un ion de métal de transition polyvalent choisi dans le groupe consistant en les groupes IVA, VA, VIA, VIIA, VIIIA, IB, IIB, et leurs associations ;

dans lequel les pourcentages en poids sont basés sur le poids total de monomère, sous réserve qu'une

proportion de 10 à 60 % en moles des groupes acide carboxylique sur l'acide maléique soit neutralisée avant polymérisation.

2. Polymaléate suivant la revendication 1, dans lequel une proportion de 20 à 50 % en moles des groupes acide carboxylique sur l'acide maléique est neutralisée avant polymérisation.

3. Polymaléate suivant la revendication 1, dans lequel la quantité d'acide maléique qui est utilisée pour préparer le polymaléate est supérieure à 80 % en poids et la quantité du monomère sulfonate allylique est inférieure à 20 % en poids.

4. Polymaléate suivant la revendication 1, dans lequel le monomère sulfonate allylique est choisi dans le groupe consistant en des sels de métaux alcalins, de métaux alcalinoterreux et d'ammonium de monomères sulfonate allylique.

5. Polymaléate suivant la revendication 1, dans lequel l'ion de métal de transition polyvalent est utilisé en une quantité de 1,6 à 33,2 μ moles.

6. Procédé pour conférer des propriétés de repassage permanent à une matière textile contenant des fibres de cellulose, comprenant les étapes consistant :

à y ajouter le polymaléate faiblement coloré ou incolore des revendications 1 à 5 dans un procédé de blanchissage comportant au moins une matière textile ;
à chauffer la matière textile à une température suffisante pendant un temps suffisant pour la réaction du polymaléate avec la matière textile,

dans lequel l'eau est éliminée de la matière textile et des propriétés de repassage permanent sont conférées à la matière textile.

7. Procédé suivant la revendication 6, dans lequel un catalyseur du type acide de Lewis est combiné avec le polymaléate avant chauffage de la matière textile.

8. Procédé suivant la revendication 7, dans lequel le catalyseur du type acide de Lewis est choisi dans le groupe consistant en le dilaurate de dibutylétain, le chlorure de fer (III), le sel de scandium (III) d'acide trifluorométhanesulfonique, le trifluorure de bore, le chlorure d'étain (IV), $Al_2(SO_4)_3 \cdot xH_2O$, $MgCl_2 \cdot 6H_2O$, $AlK(SO_4)_2 \cdot 10H_2O$, et des acides de Lewis répondant à la formule NX_p , dans laquelle N représente un métal, X représente un atome d'halogène ou un radical inorganique et p représente un nombre entier de 1 à 4.

9. Composition nettoyante comprenant au moins un agent tensioactif et 0,1 à 50 % en poids, sur la base du poids de la composition nettoyante, d'un polymaléate faiblement coloré ou incolore des revendications 1 à 8.

10. Procédé de nettoyage comprenant :

la préparation d'une composition nettoyante comprenant au moins un agent tensioactif et le polymaléate suivant les revendications 1 à 9,
la mise en contact de la composition nettoyante avec un ou plusieurs articles, au moins un des articles contenant des salissures, et
l'élimination d'au moins une partie des salissures de l'article contenant des salissures,

dans lequel le polymaléate disperse et met en suspension les salissures pour empêcher les salissures de se redéposer sur les articles nettoyés.