



(11) **EP 1 768 803 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
06.10.2010 Bulletin 2010/40

(51) Int Cl.:
B22F 1/00 (2006.01) C22C 33/02 (2006.01)

(21) Application number: **05755291.1**

(86) International application number:
PCT/SE2005/001086

(22) Date of filing: **01.07.2005**

(87) International publication number:
WO 2006/004529 (12.01.2006 Gazette 2006/02)

(54) **SINTERED PART MADE OF STAINLESS STEEL POWDER**

GESINTERTES BAUTEIL AUS EDELSTAHPULVER

PART FRITTE FAIT DE POUDRE D'ACIER INOXYDABLE

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI
SK TR**

(30) Priority: **02.07.2004 SE 0401707**

(43) Date of publication of application:
04.04.2007 Bulletin 2007/14

(73) Proprietor: **HÖGANÄS AB**
263 83 Höganäs (SE)

(72) Inventors:
• **MÅRS, Owe**
S-263 51 Höganäs (SE)
• **CANTO LEYTON, Ricardo**
S-372 51 Kallinge (SE)

• **BERGMAN, Ola**
S-254 52 Helsingborg (SE)

(74) Representative: **Andersson, Mikael Per Robert et
al**
Awapatent AB
Box 1066
251 10 Helsingborg (SE)

(56) References cited:
WO-A-98/58093 WO-A-03/106077
JP-A- 59 047 358 US-A- 5 856 625
US-A- 5 856 625

• **DATABASE WPI Week 198417, Derwent**
Publications Ltd., London, GB; AN 1984-104389,
XP008093998 & JP 59 047358 A (STEEL CORP)
17 March 1984

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 768 803 B1

DescriptionFIELD OF THE INVENTION

- 5 **[0001]** The present invention concerns a sintered part made of a stainless steel powder.
[0002] The sintered powder metallurgical part has a high density.

BACKGROUND OF THE INVENTION

- 10 **[0003]** A primary goal in powder metallurgy is to achieve high density of compacted and sintered bodies. The document JP 59 047358 discloses steel powder for sintering. There are several methods of improving density, one of those methods is warm compaction which improves the compressibility of the powder giving a green body with higher green density. By applying die wall lubrication, which makes it possible to minimise the amount of internal lubricants used, the green density may also be increased. The use of high compaction pressures in combination with low amounts of lubricants
15 also results in elevated green densities. Soft annealing of a stainless steel powder, where the material is strain relieved and recrystallized, also improves the compressibility. After compaction the green body is subjected to a sintering operation in order to achieve a sintered body. High temperatures at sintering, i.e. above about 1180-1200°C lead to increased shrinkage during sintering and higher density of the body. However, high temperature sintering requires specially equipped sintering furnaces. Additionally the energy consumption will be increased.
- 20 **[0004]** Special problems are encountered when high density, stainless steel PM parts are manufactured due to the presence of chromium, which makes the steel resistant to corrosion.
[0005] Stainless steels have approximately above 10% chromium. Most often carbon is present in steels and will cause formation of chromium carbides. The formation of chromium carbides lowers the chromium content in the matrix, which in turn causes lower corrosion resistance. In order to avoid that the chromium content in the matrix is reduced,
25 carbide forming stabilizers, such as niobium, are often used. In this way the formation of chromium carbides can be avoided and instead niobium carbides are formed, a result of which is that the corrosion resistance can be maintained. However, a problem with the use of niobium is that high sintering temperatures are necessary for obtaining high sintered densities and the energy consumption is considerable.
- 30 **[0006]** It has now been found that, by using the new powder according to the present invention, the energy costs for producing sintered stainless steel PM parts can be reduced. Another significant advantage of using the new powder is that a comparatively higher sintered density can be obtained.
- 35 **[0007]** The sintered parts manufactured by using the new powder are of particularly interest within the automotive industry where the demands on both costs and performance of the parts are high. The new powder can also be used for sintered parts in exhaust systems, and especially for flanges in exhaust systems.
- 35 **[0008]** The present invention concerns compacted and sintered parts obtained of stainless steel powder compositions having high densities.

SUMMARY OF THE INVENTION

- 40 **[0009]** It has now surprisingly been found that, by adding vanadium as a stabiliser to a stainless steel powder, the sintering temperature and accordingly the energy consumption can be reduced, while the sintered density is similar or even increased in comparison with the presently used niobium stabiliser. Furthermore it has been found that the vanadium should be present in an amount of at least 4 times the combined amounts of carbon and nitrogen, whereby the amount of nitrogen should be less than 0.07% by weight and the amount of carbon should be less than 0.1% by weight. The
45 amount of vanadium should be in the range of 0.1-1% by weight.
- 50 **[0010]** Stainless steel compositions including vanadium are disclosed in WO 03/106077 publication and in the US patent 5 856 625. In WO 03/106077 there is not disclosed any effect or any actual examples of powders including vanadium. According to the US patent 5 856 625 the stainless steel powder preferably comprises 1.5-2.5% vanadium. This known stainless steel powder is intended for materials with high wear resistance and a high carbon content is necessary to achieve a proper amount of hard carbides in the matrix formed mainly from strong carbide forming elements such as Mo, V and W. Also the patent publication JP 59-47358 discloses a steel powder is comprising chromium, silicon, carbon and nitrogen. This powder may further contain nickel and/or copper and vanadium. The purpose of the the steel powder according to JP 59-47358 is to manufacture e.g. a sliding surface.

55 DETAILED DESCRIPTION OF THE INVENTION

- [0011]** The stainless steel powder according to the invention comprises 10-30% chromium, 0.1-1% vanadium, 0.5-1.5% silicon, less than 0.1% carbon and less than 0.07% nitrogen. Preferably the stainless steel powder comprises 10-20%

chromium, 0.15-0.8% vanadium, 0.7-1.2% silicon, less than 0.05% carbon and less than 0.05% nitrogen.

[0012] According to the invention there is provided a process of preparing compacted parts of stainless steel powder comprising the steps of: subjecting a pre-alloyed stainless steel powder consisting essentially of 10%-30% by weight of chromium, 0.5-1.5% by weight of silicon, less than 0.1 % by weight of carbon, less than 0.07% by weight of nitrogen, vanadium in an amount of at least 4 times the combined amounts of carbon and nitrogen, balance iron, wherein the amount of vanadium is 0.1-1% by weight, and nickel in an amount of less than 1% by weight optionally mixed with a lubricant to compaction; and sintering the compacted part at a temperature of 1150-1350°C.

[0013] According to the invention there is provided a sintered part having the composition of stainless steel powder consisting essentially of 10%-30% by weight of chromium, 0.5-1.5% by weight of silicon, less than 0.1% by weight of carbon, less than 0.07% by weight of nitrogen, balance iron, vanadium in an amount of at least 4 times the combined amounts of carbon and nitrogen, wherein the amount of vanadium is 0.1-1 % by weight, and nickel in an amount of less than 1 % by weight, having a sintered density of at least 7.20 g/cm³.

[0014] As the corrosion resistance in stainless steels is of great interest the vanadium content should be chosen so that vanadium carbides and nitrides are formed instead of chromium carbides and nitrides. Preferably the vanadium content will be chosen in relation to the actual carbon and nitrogen content in the sintered component to be able to form vanadium carbides and nitrides. It is believed that the vanadium carbides and nitrides formed are of type VC and NC and according to our present knowledge the vanadium content should preferably be minimum 4 times the carbon and nitrogen content of the powder. The actual carbon and nitrogen content in the sintered component may be higher than the content of the elements in the powder due to pick up during delubrication.

[0015] The amount of silicon should be between 0.5% to 1.5%. Silicon is an important element as it creates a thin coherent oxide layer during atomisation of the stainless steel melt, i.e. the silicon content should be 0.5% by weight or above. The oxide layer prevents further oxidation. A too high silicon level will lead to a decrease in compressibility, hence the silicon content should be 1.5% by weight or lower.

[0016] The amount of nitrogen should be as low as possible as nitrogen can have the same influence as carbon, i.e. sensitising the material through formation of chromium nitrides or chromium carbonitrides. Nitrogen has also a precipitation hardening effect which will decrease the compressibility. Therefore the nitrogen content should not exceed 0.07%, preferably not 0.05% by weight. In practice it is difficult to obtain nitrogen contents lower than 0.001%.

[0017] Other alloying elements are added to enhance certain properties, such as strength, hardness etc. The alloying elements are selected from the group consisting of molybdenum, copper, manganese and nickel.

[0018] Steels comprising deliberately added amounts of molybdenum, copper or manganese do not form part of the invention

[0019] According to the present invention ferritic stainless steels are preferred. Ferritic stainless steels are less expensive than austenitic stainless steels which are alloyed with nickel. Compared with an austenitic matrix a ferritic matrix has a lower coefficient of thermal expansion, which is beneficial for example in flanges in a stainless steel exhaust system. Therefore a preferred embodiment of the stainless steel according to the invention is essentially free from nickel. Specifically the ferritic stainless steel may comprise 10-20% by weight of chromium, 0-5% by weight of molybdenum, less than 1% by weight of nickel, less than 0.2% by weight of manganese.

[0020] Other possible additives are flow agents, machinability improving agents such as calcium fluoride, manganese sulfide, boron nitride or combinations thereof.

[0021] The stainless steel powder may be a gas or water atomised, pre-alloyed powder having an average particle size above about 20 µm, depending on the method of consolidation of the powder. Normally the average particle size is above about 50 µm.

[0022] Most often a lubricant is added prior to compaction in order to enhance the compressibility of the powder and to facilitate the ejection of the green component. The amount of lubricant is typically between 0.1% and 2%, preferably between 0.3% and 1.5%. The lubricants may be chosen from the group consisting of metal stearates, such as zinc or lithium stearate, Kenolube®, amide polymers or amide oligomers, ethylene bisstearamide, fatty acid derivatives or other suitable substances with a lubricating effect. Die wall lubrication alone or in combination with internal lubricants may also be used.

[0023] After an optional annealing the stainless steel powder is mixed with lubricant and other optional additives. The powder mixture is compacted at 400-1200 MPa and sintered at 1150-1350°C for 5 minutes to 1 hour to obtain a density of at least 7.20 g/cm³. However, the powder according to the invention can be used for producing parts having lower sintered density in order to reduce processing costs. The compaction step could be performed as cold compaction or warm compaction.

[0024] The high sintered density is obtained by increased shrinkage during the sintering and without being bound to any specific theory, it is believed that this shrinkage is a consequence of promoted volume diffusion. Vanadium carbides which are formed in presence of carbon will be dissolved at elevated temperatures, especially at sintering temperatures, but also at lower temperatures such as at annealing of the metal powder. Normally the sintering temperature for stainless steel powders is about 1150-1300°C.

Example 1

[0025] Three different melts having a chemical composition according to table 1 and containing niobium and vanadium as carbide forming elements were produced. Several mixtures were prepared for cold or warm compaction according to table 2 and 3. For cold compaction and warm compaction purposes lubricants were used. As a flow agent in warm compaction Aerosil A-200 from Degussa® was used.

Table 1. Chemical analysis of unannealed powders

Batch	Cr%	Nb%	V%	Si%	Mn%	Ni%	P%	C%	N%	O%	S%
A	11.85	---	0.29	0.68	0.23	0.053	0.008	0.024	0.014	0.144	0.0033
B	11.94	0.39	---	0.68	0.23	0.051	0.010	0.025	0.011	0.152	0.0027
C	11.79	0.58	---	0.73	0.23	0.056	0.009	0.026	0.011	0.143	0.0030

Table 2. Mixtures for cold compaction

Mixture no	Composition
4*	A + 1% lubricant
5	B + 1% lubricant
6	C + 1% lubricant
* = composition according to the invention	

Table 3. Mixtures for warm compaction

Mixture no	Composition
10*	A + 1% lubricant + 0.1% A-200
11	B + 1% lubricant + 0.1% A-200
12	C + 1% lubricant + 0.1% A-200
* = composition according to the invention	

[0026] The powder mixtures according to table 2 and 3 were compacted and green properties were determined for various compaction pressures. The results are presented in table 4. The compacted bodies were sintered at 1250°C in an atmosphere of hydrogen for 45 minutes and the sintered densities and mechanical properties were determined. The results are shown in table 5.

Table 4.

Mixture no	Compaction pressure	Green strength (Mpa)	Green density (g/cm ³)
4*	600	15.3	6.57
	700	18.0	6.69
	800	19.3	6.79
5	600	15.4	6.55
	700	18.1	6.68
	800	19.5	6.80

EP 1 768 803 B1

(continued)

Mixture no	Compaction pressure	Green strength (Mpa)	Green density (g/cm ³)
6	600	15.3	6.55
	700	18.1	6.68
	800	19.4	6.78
10*	600	31.3	6.73
	700	37.5	6.87
	800	39.9	6.96
11	600	30.1	6.71
	700	36.7	6.86
	800	40.4	6.96
12	600	29.4	6.71
	700	34.9	6.86
	800	39.4	6.96
* = composition according to the invention			

Table 5.

Mixture no	Compaction pressure (MPa)	Sintered density (g/cm ³)	Dimensional change (%)	Yield strength (MPa)	Tensile strength (MPa)
4*	600	7.36	-3.87	222	390
	700	7.42	-3.29	216	409
	800	7.45	-2.71	215	405
5	600	7.24	-3.48	204	366
	700	7.31	-3.09	208	375
	800	7.38	-2.82	228	384
6	600	7.10	-2.85	202	356
	700	7.20	-2.55	208	366
	800	7.26	-2.30	213	376
10*	600	7.42	-3.38	221	420
	700	7.47	-2.67	230	434
	800	7.49	-2.20	234	431
11	600	7.28	-2.93	206	371
	700	7.36	-2.52	210	386
	800	7.43	-2.20	216	400
12	600	7.16	-2.36	203	361
	700	7.27	-2.05	212	377
	800	7.33	-1.79	214	389
* = composition according to the invention					

[0027] From table 4 and table 5 it can clearly be identified that the sintered densities of the samples produced from the material according to the invention are improved, while the green densities of the material according to the invention are similar to the comparative materials. The mechanical properties of the sintered components are also improved with material according to the invention compared with known materials.

Example 2

[0028] In order to evaluate the influence of sintering temperatures and sintering times, powder mixtures 4, 5 and 6 were compacted into tensile test samples according to ISO 2740 in a uniaxially compaction movement at ambient temperature at 600 MPa. The obtained green samples were sintered at 1200°C, 1250°C and 1300°C in an atmosphere of hydrogen for 20 minutes and 45 minutes, respectively.

[0029] After sintering the sintered density of the sintered samples were measured according to ISO 3369. The results are shown in table 6. From table 6 it can be concluded that sintered densities above 7.2 g/cm³ can be obtained for a ferritic stainless steel powder provided vanadium is added, even at a sintering temperature as low as 1200°C. A sintering time of 20 minutes at a sintering temperature of 1250°C yields a sintered density of 7.35 g/cm³, whereas the corresponding density for the niobium stabilized ferritic stainless steel powder is 7.15 g/cm³ and 7.03 g/cm³ respectively, depending on the amount of niobium added.

[0030] The example reveals a surprisingly great impact on the shrinkage during sintering of a green body produced from ferritic stainless steel powder according to the invention.

Table 6.

Mixture no	Sintering time (min)	Sintered densities (g/cm ³) at different sintering temperatures		
		1200°C	1250°C	1300°C
4*	45	7.29	7.36	7.46
5	45	7.03	7.24	7.47
6	45	6.92	7.1	7.38
4*	20	-	7.35	-
5	20	-	7.16	-
6	20	-	7.03	-
* = composition according to the invention				

Example 3

[0031] In order to evaluate the influence of the nitrogen content of the stainless steel powder one melt was atomised and powder samples having different nitrogen content were prepared from the atomised powder by annealing in a nitrogen-containing atmosphere. As reference material powder annealed in an atmosphere of 100 % of hydrogen was used. The powder samples were mixed with 1% lubricant and the obtained compositions were cold compacted at different pressures into specimens. The specimens were sintered at 1250°C in an atmosphere of hydrogen for 45 minutes. The chemical analysis of the different powder samples is presented in table 7 except the nitrogen content, which was determined after annealing as presented in table 8. In table 8 the sintered density is presented for different specimens.

Table 7

Batch	Cr%	Nb%	V%	Si%	Mn%	Ni%	P%	C%	S%
D	12 14	0.01	0.29	0.83	0.13	0.05	0.001	0.012	0.012

Table 8

Batch	Compaction pressure (MPa)	%N	Sintered Density (g/cm ³)
D1	600	0.056	7.18
D1	700		7.28
D1	800		7.36
D2	600	0.072	7.13
D2	700		7.24
D2	800		7.31
D(ref)	600	0.019	7.23
D(ref)	700		7.34
D(ref)	800		7.39

[0032] It can be seen from example 3 that a nitrogen content above 0.07% will result in undesired sintered density.

Claims

1. A process of preparing compacted parts of stainless steel powder comprising the steps of:

- subjecting a pre-alloyed stainless steel powder consisting of 10%-30% by weight of chromium, 0.5-1.5% by weight of silicon, less than 0.1% by weight of carbon, less than 0.07% by weight of nitrogen, vanadium in an amount of at least 4 times the combined amounts of carbon and nitrogen, balance iron, wherein the amount of vanadium is 0.1-1% by weight, and nickel in an amount of less than 1% by weight optionally mixed with a lubricant to compaction
- sintering the compacted part at a temperature of 1150-1350°C.

2. The process according to claim 1, wherein sintering is made to a density of at least 7.20 g/cm³

3. A sintered part having the composition of stainless steel powder consisting of 10%-30% by weight of chromium, 0.5-1.5% by weight of silicon, less than 0.1% by weight of carbon, less than 0.07% by weight of nitrogen, vanadium in an amount of at least 4 times the combined amounts of carbon and nitrogen, balance iron, wherein the amount of vanadium is 0.1-1% by weight, and nickel in an amount of less than 1% by weight, having a sintered density of at least 7.20 g/cm³.

Patentansprüche

1. Verfahren für die Herstellung verdichteter Bauteile aus Edelstahlpulver, umfassend die Schritte des:

- Unterwerfens dem Verdichten eines vorlegierten Edelstahlpulvers bestehend aus 10 - 30 Gew.-% Chrom, 0,5 - 1,5 Gew.-% Silicium, weniger als 0,1 Gew.-% Kohlenstoff, weniger als 0,07 Gew.-% Stickstoff, Vanadium in einer Menge von mindestens 4 mal der kombinierten Mengen von Kohlenstoff und Stickstoff, wobei der Restbetrag Eisen ist, wobei die Menge an Vanadium 0,1 - 1 Gew.-% beträgt, und Nickel in einer Menge von weniger als 1 Gew.-%, wahlweise mit einem Gleitmittel gemischt,
- Sinterns des verdichteten Bauteils bei einer Temperatur von 1150 - 1350 °C.

2. Verfahren nach Anspruch 1, wobei das Sintern bis zu einer Dichte von mindestens 7,20 g/cm³ durchgeführt wird.

3. Gesintertes Bauteil, das eine Zusammensetzung von Edelstahlpulver aufweist bestehend aus 10 - 30 Gew.-% Chrom, 0,5 - 1,5 Gew.-% Silicium, weniger als 0,1 Gew.-% Kohlenstoff, weniger als 0,07 Gew.-% Stickstoff, Vanadium in einer Menge von mindestens 4 mal der kombinierten Mengen von Kohlenstoff und Stickstoff, wobei der Restbetrag

EP 1 768 803 B1

Eisen ist, wobei die Menge an Vanadium 0,1 - 1 Gew.-% beträgt, und Nickel in einer Menge von weniger als 1 Gew.-%, das eine gesinterte Dichte von mindestens 7,20 g/cm³ aufweist.

5 **Revendications**

1. Procédé de préparation de parties comprimées de poudre d'acier inoxydable comprenant les étapes consistant à :

- 10 - soumettre une poudre d'acier inoxydable pré-alliée constituée de 10 à 30 % en masse de chrome, 0,5 à 1,5 % en masse de silicium, moins de 0,1 % en masse de carbone, moins de 0,07 % en masse d'azote, du vanadium dans une quantité d'au moins 4 fois les quantités combinées de carbone et d'azote, et le reste étant du fer, dans lequel la quantité de vanadium est de 0,1 à 1 % en masse, et du nickel dans une quantité inférieure à 1 % en masse facultativement mélangé avec un lubrifiant jusqu'à compactage,
- 15 - fritter la partie comprimée à une température de 1 150 à 1 350 °C.

2. Procédé selon la revendication 1, dans lequel le frittage est effectué à une masse volumique d'au moins 7,20 g/cm³.

- 20 3. Partie frittée dont la composition de poudre d'acier inoxydable est constituée de 10 à 30 % en masse de chrome, 0,5 à 1,5 % en masse de silicium, moins de 0,1 % en masse de carbone, moins de 0,07 % en masse d'azote, du vanadium dans une quantité d'au moins 4 fois les quantités combinées de carbone et d'azote, et le reste étant du fer, dans lequel la quantité de vanadium est de 0,1 à 1 % en masse, et du nickel dans une quantité inférieure à 1 % en masse, ayant une mase volumique de frittage d'au moins 7,20 g/cm³.

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 59047358 A [0003] [0010]
- WO 03106077 A [0010]
- US 5856625 A [0010]