

⑬



Europäisches Patentamt
European Patent Office
Office européen des brevets

⑪ Publication number:

O 003 263
B1

⑫

EUROPEAN PATENT SPECIFICATION

④⑤ Date of publication of patent specification: **29.09.82**

⑤① Int. Cl.³: **G 03 C 1/72, G 03 C 5/00,**
C 07 F 15/06

②① Application number: **78300914.5**

②② Date of filing: **28.12.78**

⑤④ **A method of forming an image, and an imaging element for inhibiting image formation with cobalt (III) complexes.**

③⑩ Priority: **28.12.77 US 865275**

⑦③ Proprietor: **EASTMAN KODAK COMPANY**
343 State Street
Rochester, New York 14650 (US)

④③ Date of publication of application:
08.08.79 Bulletin 79/16

⑦② Inventor: **Adin, Anthony**
Kodak Park
Rochester New York (US)

④⑤ Publication of the grant of the patent:
29.09.82 Bulletin 82/39

⑦④ Representative: **Pepper, John H. et al,**
KODAK LIMITED Patent Department P.O. Box 114
190 High Holborn
London WC1V 7EA (GB)

⑧④ Designated Contracting States:
BE FR

⑤⑥ References cited:
FR - A - 2 267 571
US - A - 3 987 037

EP O 003 263 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Imaging element for inhibiting image formation with cobalt(III) complexes and method of forming an image

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to a cobalt(III) complex-containing photographic element which can be made negative-working or positive-working, depending upon the nature of the exposure given.

5

State of the Prior Art

Cobalt(III) complexes containing releasable ligands have been utilized in non-silver redox reactions photoinitiated by means of photoreductants or spectral sensitizers, as disclosed, for example, in *Research Disclosure*, Volumes 126 and 130, October 1974 and February 1975, Publications Nos. 12617 and 13023, respectively, published by Industrial Opportunities Limited, Homewell, Havant, Hampshire PO91EF, United Kingdom. Preferred reduction products of such a reaction are cobalt(II) and amines or ammonia. Either of these can in turn be used to form images, the cobalt (II) being chelated by compounds capable of forming at least bidentate chelates, or the amines being reacted with dye precursors, including diazo-coupler systems, to form a dye; or the cobalt(II) or amines can be used to bleach out preincorporated dye. Such imaging processes are disclosed in *Research Disclosure*, Volume 126, October 1974, Publication No. 12617, part III. Amplification can be achieved by using a reduction agent precursor capable of forming a reducing agent with the aforesaid reduction products, for the reduction of remaining cobalt(III) complexes. For example, certain of said chelating compounds for cobalt(II) form, when chelated, a reducing agent, as described in *Research Disclosure*, Volume 135, July 1975, Publication No. 13505, and o-phthalaldehyde will react with ammonia to form a reducing agent, as disclosed in *Research Disclosure*, Volume 158, June 1977, Publication No. 15874. Imaging elements based upon such reactions involving cobalt(III) complexes are useful, for example, in graphic arts as room-light handling contact films, e.g., as an intermediate in the preparation of printing plates.

The cobalt complex imaging elements of the prior *Research Disclosures* can be either negative-working or positive-working, but the same element is not both. That is, a separate image-forming material (e.g., a dye former) is used in those instances in which the element is to be negative-working, compared to those instances in which the element is positive-working (e.g., by bleaching out a pre-existing dye). It would be highly desirable to provide an imaging element wherein the same element can be made negative or positive working, merely by controlling the processing of the element.

A further aspect of said prior cobalt complex imaging elements is that they can develop background print-up because the unexposed photoinitiator in the background areas causes increased D_{min} (minimum density) upon handling as a result of room light activation of the photoinitiator. To avoid print-up, a peel-apart system can be used, that is, one wherein the layer of cobalt(III) complex relied upon for the imaging is removed from the image recording layer. Print-up is more difficult to avoid in integral systems, particularly when the exposed photo-reductant reduces the complex at room temperatures.

Therefore, there is a need for cobalt imaging systems which are less likely to suffer print-up when handled in room light conditions.

Metal complexes capable of releasing amines have been used prior to this invention to thermally activate image recording means such as diazo-coupler compositions. Examples are disclosed in U.S. Patent Nos. 3,469,984; 3,224,878; and 2,774,669. Because of their thermal instability, such complexes generate amines when overall heated, to cause diazo coupling or the like. There is no disclosure in this art of means for inhibiting such dye development.

Canadian J. Chem., Volume 54, pages 3685 through 3692 (1976), teaches that certain cobalt complexes, specifically $[(NH_3)_5Co(III)dimethylsulfoxide]^{3+}$, can be inhibited against thermal reduction by the addition of equimolar concentrations of p-toluenesulfonic acid. No suggestion is made that such acid can be photolytically generated.

Patents relating to the background of image formation using amines or cobalt complexes include U.S. Patents Nos. 2,774,669; 3,102,811; 3,469,984; 3,224,878; and Japanese Patent Publication No. 74/6234.

United Kingdom Patent No. 1,497,452 discloses the use of a cobalt complex and a photoreductant which may include an image-former. A layer containing such a composition may be coated on a support using a chlorinated hydrocarbon solvent.

Description of the Invention

According to this invention there is provided the method of forming an image comprising first exposing an imaging element containing a layer of an energy-activatable image precursor composition comprising at least one cobalt III complex having ligands releasable by said activating energy, said energy-activatable image precursor being a composition activatable by electromagnetic energy of any kind in areas where it has not been inhibited by an already exposed photoinhibitor, as hereinafter described, and said composition when activated by exposure to electromagnetic energy providing an image either by generating a density or by destroying a pre-existing density or altering its colour, and

before or after said first exposure placing the layer of the energy-activatable image precursor composition in contact with a layer of an image-forming material which generates an image in response to the release of the ligands and which contains, as a photoinhibitor, a single compound or a mixture of compounds which does not form a complex with cobalt and which responds to activating radiation having a wavelength greater than 300 nm, different from that activating said image precursor composition and which inhibits the release of ligands from the cobalt(III) complex or inhibits the effect of released ligands on the image-forming material upon exposure to activating radiation of a different wavelength to that activating the image precursor composition and after such contact exposing the image-forming material to said activating radiation of a different wavelength, one of said exposures being imagewise and the other uniform.

Description of the Preferred Embodiments

This invention relates to an imaging process wherein an imagewise exposure activates an image precursor composition comprising at least a cobalt(III) complex containing releasable ligands, to form an image, and wherein a second exposure photolytically generates the means for inhibiting such ligand release. More specifically, it has been discovered that a photoinhibitor such as a photolytic acid generator after suitable exposure will inhibit the release of ligands which would otherwise occur by activating the exposure of the image precursor composition.

An "image precursor composition", as used herein, is a composition as described which when appropriately activated by exposure, produces an image either by generating a density or by destroying a pre-existing density or altering its colour. Also as used herein, the precursor composition is "energy-activatable" if it is activatable by electromagnetic energy of any kind in areas where it is not inhibited by an already exposed photoinhibitor of the invention. The image precursor composition can be activated by thermal or light exposures of the type disclosed, for example, in *Research Disclosure*, Volume 147, July 1976, Publication No. 14719 depending upon the circumstances. Thermal exposure can occur through the use of infrared radiation or convection, but preferably it is achieved through conduction. As will be readily apparent, exposure of the image precursor composition is achieved by a different wavelength, that is different from that used to activate the photoinhibitor. Generally the image precursor composition is activated by longer wavelength energy than will activate the photoinhibitor.

In a highly preferred form, the exposure of the image precursor composition is achieved through the use of heat or light or both together. However, as noted, if light is used or is present in a thermal exposure, it is of a wavelength or an intensity that does not activate the photoinhibitor. Similarly, the light exposure used to imagewise activate the photoinhibitor to inhibit image formation can include energy of wavelengths and intensities that are incapable of activating the image precursor composition in preference to the photoinhibitor, as shown, in examples hereinafter described. To insure such discrimination, filters may be used, particularly for broad-band exposures. Preferably, if thermal energy is used to expose the image precursor composition, it is generated in a total absence of light, such as by a hot block, hot stylus, or heated rollers in a dark room.

As used herein, "photoinhibitor" means a single compound or a mixture of compounds which respond to activating radiation having a wavelength greater than 300 nm, to inhibit the release of ligands by the cobalt(III) complex.

The photoinhibitor can comprise one or more compounds which themselves have a sensitivity that responds to wavelengths longer than 300 nm, or it can comprise a compound whose sensitivity responds only to wavelengths shorter than 300 nm, and a spectral sensitizer which increases the native sensitivity to beyond 300 nm.

An imaging element containing the radiation-sensitive composition of the invention can comprise one or more operatively associated layers, with the image precursor composition being contained in one or more of the layers. That is, the image-forming material of the image precursor composition can either be admixed with the photoinhibitor, or it can be in a separate, adjacent layer where it responds to the ligands which are released by the cobalt(III) complex, as is more fully described hereafter. Thus, the photoinhibitor and the image precursor composition are in chemical association, that is, are either admixed together in a single layer, or are in contiguous layers either as manufactured or as processed.

Image Precursor Composition

This composition includes at least 1) a cobalt(III) complex containing releasable ligands and 2) an image-forming material capable of generating an image upon release of said ligands. If the cobalt(III) complex is thermally stable, i.e., it will not release ligands in response to an exposure which is primarily thermal in nature, then one or more destabilizer materials preferably is included, as defined and described hereafter.

An amplifier can also be included in the image precursor composition. As used herein, an "amplifier" is a reducing agent precursor composition or compound which interacts with the image precursor composition to generate additional initiators of the imaging reaction, whereby an internal gain, usually expressed as enhanced density, is achieved compared to that which results without the amplifier. Preferably, the initiators so generated are amines, and a highly useful example of an amplifier for generating such additional amine initiators is *o*-phthalaldehyde. The reason for such preference is that *o*-

phthalaldehyde also functions as an image-forming material, as is hereinafter described. Alternatively, the amplifiers can be compounds which chelate with the cobalt(II) produced from cobalt(III). Such chelating compounds contain conjugated π -bonding systems capable of forming with such cobalt(II), additional reducing agents for remaining cobalt(III) complexes. Typical amplifiers of this class, and
5 necessary restrictions concerning pKa values of the anions that can be used in the cobalt(III) complex in such circumstances, are described in *Research Disclosure*, Volume 135, July 1975, Publication No. 13505.

Any cobalt(III) complex containing releasable ligands and which is thermally stable at room temperature will function in this invention, whether or not it is thermally stable within the processing
10 temperatures used. Such complexes on occasion have been described as being "inert". See, e.g., U.S. Patent No. 3,862,842, Columns 5 and 6. However, the ability of such complexes to remain stable, i.e., retain their original ligands when stored by themselves or in a neutral solution at room temperature until a chemically or thermally initiated reduction to cobalt(II) takes place, is so well known that the term "inert" will not be applied herein.

Such cobalt(III) complexes feature a molecule having a cobalt atom or ion surrounded by a group
15 of atoms, ions or other molecules which are generically referred to as ligands. The cobalt atom or ion in the center of these complexes is a Lewis acid while the ligands are Lewis bases. While it is known that cobalt is capable of forming complexes in both its divalent and trivalent forms, trivalent cobalt complexes, i.e., cobalt(III) complexes, are employed in the practice of this invention, since the ligands
20 are relatively tenaciously held in these complexes, and released when the cobalt is reduced to the (II) state.

Preferred cobalt(III) complexes useful in the practice of this invention are those having a coordination number of 6. A wide variety of ligands can be used with cobalt(III) to form a cobalt(III) complex. The one of choice will depend upon whether the image-forming material described hereinafter relies upon
25 amines to generate a dye or the destruction of dye, or upon the chelation of cobalt(II) to form a dye image. In the latter case, amine ligands or non-amine ligands can be used, whereas in the former case amine ligands are preferred as the source of initiators for the image-forming reaction. Useful amine ligands include, e.g., methylamine, ethylamine, amines, and amino acids such as glycine nato. As used herein, "ammine" refers to ammonia specifically, when functioning as a ligand, whereas "amine" is
30 used to indicate the broader class noted above. Highly useful with all the embodiments of the image precursor composition hereinafter described are the ammine complexes. The other amine complexes achieve best results when used with particular destabilizer materials hereinafter described, for example, photoreductants.

The cobalt(III) complexes useful in the practice of this invention can be neutral compounds which
35 are entirely free of either anions or cations. As used herein, "anion" refers to non-ligand anions, unless otherwise stated. The cobalt(III) complexes can also include one or more cations and anions as determined by the charge neutralization rule. Useful cations are those which produce readily soluble cobalt(III) complexes, such as alkali metals and quaternary ammonium cations.

A wide variety of anions can be used, and the choice depends in part on whether or not an amplifier is used which requires that the element be free of anions of acids having pKa values greater than
40 about 3.5. Otherwise, the choice of anions is significant only to the extent that it determines whether or not the complex is thermally stable when heated to the temperature at which the composition or element is processed. As used herein, "thermally unstable" means that the complex decomposes at the temperature in question sufficiently to release enough ligands to start the intended reaction of the
45 image precursor composition, as described herein. If a thermally unstable complex is used with the image-forming material alone as the image precursor composition, the complex is preferably unstable only at temperatures greater than 100°C. If a thermally stable complex is to be used a destabilizer material must be included, the complex is preferably stable up to a temperature of at least 130°C.

The anions which tend to render the complex thermally unstable include those that decompose readily
50 to a radical, such as trichloroacetate; those forming unstable heavy metal salts, such as azido; and those which are themselves reducing agents, such as 2,5-dihydroxy-benzoate; N,N-dimethyl-dithiocarbamate; and 1-phenyl-tetrazolyl-5-thiolate.


55

60

65

0 003 263

Representative examples of complexes containing ligands which are reported as being thermally unstable above 100°C are listed below:



wherein X is a suitable anion and n is 0 to 3 and represents the number of anions necessary to satisfy the charge neutralization rule.

Except for the special condition of thermal instability noted above any anion can be selected if an anion is necessary for charge neutralization, provided the anion is compatible. As used herein, anions are considered "compatible" if they do not spontaneously cause a reduction of cobalt(III) complex at room temperature. As noted, a complex does not require anions if it is already neutral.

The following Table II is a partial list of particularly preferred cobalt(III) complexes within the scope of the invention. The suffix (U) designates those which are thermally unstable above about 100°C.

40

45

50

55

60

65

0 003 263

TABLE II

COBALT(III) COMPLEXES

5

hexa-ammine cobalt(III) benzilate

10

hexa-ammine cobalt(III) thiocyanate

hexa-ammine cobalt(III) trifluoroacetate

chloropenta-ammine cobalt(III) perchlorate

15

bromopenta-ammine cobalt(III) perchlorate

aquopenta-ammine cobalt(III) perchlorate

20

bis(methylamine) tetra-ammine cobalt(III)
hexafluorophosphatbis(dimethylglyoxime)bispyridine
cobalt(III)trichloroacetate (U)

25

bis(dimethylglyoxime)ethyloquo cobalt(III)

cobalt(III) acetylacetonate

30

tris(2,2'-bipyridyl)cobalt(III)
perchlorateaquopenta(methylamine) cobalt(III)
nitrate (U)

35

chloropenta(ethylamine) cobalt(III)
perfluorobutyrate (U)

trinitrotris-ammine cobalt(III)

40

trinitrotris(methylamine) cobalt(III) (U)

 μ -superoxodeca-ammine dicobalt(III)
perchlorate (U)

45

penta-ammine carbonato cobalt(III)
perchlorate

tris(glycinato) cobalt(III)

50

The image-forming material of the image precursor composition can comprise compounds or compositions in addition to the cobalt(III) complex and destabilizer material, if any, or it can be the same compound as is used as a destabilizer material. It can be a dye-forming material, or a dye which is bleachable. Examples of dye-forming materials which also comprise destabilizer materials used to interact with the cobalt(III) complex, as discussed hereinafter, include 4-methoxynaphthol, which forms a blue dye when oxidized, and protonated diamine destabilizer material which when associated with a conventional color coupler will form a dye when it is oxidized by the reduction of the cobalt(III) complex. Examples of image-forming materials used in addition to a destabilizer material include *o*-phthalaldehyde, also used as an amplifier; an ammonia-bleachable or color-alterable dye (cyanine dyes, styryl dyes; rhodamine dyes, azo dyes, and pyrylium dyes); a dye-precursor such as ninhydrin; or a diazo-coupler system. Details of these examples are set forth in *Research Disclosure*, Volume 126, October 1974, Publication No. 12617, Part III, noted above. Still another alternative is to admix with the cobalt(III) complex, chelating compounds which will react with cobalt(II) to form a dye image.


Ammonia-bleachable materials will, of course, produce an imagewise absence of dye in the exposed areas. As will be readily apparent, ammonia-bleachable materials and color-alterable

materials, when incorporated into an element, preferably are used in a separate adjacent layer that is associated with the photoinhibitor layer after the latter is exposed.

As noted above, the image precursor composition includes destabilizer materials in those instances wherein the cobalt(III) complex is thermally stable. As is implied by the term, destabilizer materials are those which render the otherwise thermally stable cobalt(III) complex susceptible to release of the ligands when appropriately exposed. The exact mechanism by which these destabilizer materials cause the release of the ligands from the cobalt complex is not understood in most instances, other than that such release does occur and cobalt(II) is produced, except where inhibited by the photoinhibitor photoproducts. Because the mechanism of these destabilizer materials is largely uncertain, the subclasses under which various examples fall are uncertain and not necessarily mutually exclusive. To be useful, the destabilizer materials must be compatible with the cobalt(III) complex. Usually, this is not a problem, "compatible destabilizer materials" being used here to mean materials that do not interfere with the complex, such as by precipitating it or by spontaneously reducing it.

Examples of destabilizer materials useful with the complex include organo-metallics such as ferrocene and 1,1-dimethylferrocene, and tricarbonyls such as N,N-dimethylaniline chromium tricarbonyl, as well as organic materials, and may or may not require an amplifier such as phthalaldehyde. For example, destabilizer materials comprising 4-phenyl catechol and quinone photoreductants, hereinafter described, do not require the use of an amplifier compound. Other destabilizer materials will not release the ligands, when appropriately exposed, in amounts sufficient to generate observable dye in the same or an adjacent layer without the presence of an amplifier such as *o*-phthalaldehyde. Still other destabilizer materials may release sufficient ligands to cause some dye formation, and at least some of these destabilizer materials can achieve much higher density if an amplifier is included. Therefore, in many of the embodiments of the invention, *o*-phthalaldehyde comprises part of the image precursor composition, for preferred results, whether or not it actually is required to produce observable results.

The behaviour of *o*-phthalaldehyde in an image precursor composition appears to involve, in the preferred embodiments, the formation with ammonia of an adduct which is a reducing agent (see structure A in equation 1 below). The adduct itself causes reduction of remaining cobalt(III) complex and releases more ligands. Such release produces an internal gain.




O 003 263

The initial NH_3 comes from the cobalt(III) complex on exposure, either because of its own thermal instability, or because of activation by a destabilizer material, by one of several mechanisms described hereafter. *o*-Phthalaldehyde also forms a dye imaging material, oligomer (B), in addition to its amplifying function as a reducing agent precursor for cobalt(III). Further explanation can be found in
 5 DoMinh et al, "Reactions of Phthalaldehyde with Ammonia and Amines", *J. Org. Chem. Vol. 42*, Dec. 23, 1977, p. 4217.

Useful destabilizer materials are the following thermally responsive organic materials and equivalents thereof:

- (a) 4-Phenyl catechol.
- 10 (b) Sulfonamidophenols and naphthols such as 4-phenylsulfonamido-2,6-dichlorophenol and 4-phenylsulfonamido-2-methyl-1-naphthol.
- (c) Other aromatic alcohols such as 4-methoxynaphthol and 1,4-dihydroxynaphthalene.
- (d) Pyrazolidones such as 4-hydroxymethyl-4-methyl-1-phenyl-3-pyrazolidone, 1-phenyl-4,4-dimethyl-3-pyrazolidone and the like.
- 15 (e) Acids having the formula:




wherein:

Z represents from about 4 to about 8 carbon atoms necessary to complete 1 or more aromatic or
 25 cycloalkyl rings such as a benzene, a naphthalene or a cyclohexane ring.

Suitable examples of such acids include, for example, phthalamic acid, 2-carboxy-cyclohexyl-carboxamide and amine salts thereof, including 2-carboxy-cyclohexylcarboxamide triethanolamine salt, and the like.


- (f) Ureas having the formula:



wherein:

T represents S or O; and
 35 R represents a hydrogen atom, an *o*-hydroxyphenyl group or an *o*-carbamoylphenyl group. Suitable compounds include: Urea, thiourea, 2-hydroxyphenyl urea and the like.

- (g) Salts having the formula:




wherein:

M represents a carbon or nitrogen atom
 45 T' represents a chemical bond or an alkylene group containing from 1 to 3 carbon atoms, and Z¹ represents from 4 to 6 nonmetallic atoms necessary to form an aromatic carbocyclic or heterocyclic ring.

Suitable examples of such salts including 1-(β -aminoethyl)-2-imidazolidinone trichloroacetate, 2-amino-2-thiazoline trichloroacetate, anilinium trichloroacetate and the like.

- (h) Morpholine precursors having the formula:




wherein:

Z² represents from 4 to 8 non-metallic atoms required to complete one or more heterocyclic rings;
 65 one example of such precursors being 3,3-bis(morphilino)oxindole.


(i) Aminimides in polymeric or simple compound form containing the structure:



including, for example, (N-methylpiperidine) 1-naphthoylimide; (trialkylamine) cinnamimides; bis(dialkyl-2-hydroxypropylamine) adipimides; (dialkyl-2-hydroxypropylamine) palmitimides or laurimides; bis(trialkylamine) sebacimides or azelamides; 2,2'-(p-phenylenebis-β-acryoyl)-bis-[1-hydroxypropyl-1,1-dimethylhydrazinium] dihydroxide bis(inner salt); and polymers having a repeating unit of the formula:



polymers having repeating units with pendant aminimide groups of the formula:



those described in U.S. Patent No. 4,016,340, issued April 5, 1977, and in *Research Disclosure*, Vol. 157, May 1977, Publication Nos. 15732, 15733 and 15776; (trialkylamine) arylimides such as (trimethylamine) benzimide and (trimethylamine) naphthimide, including arylimides substituted with hydroxy, lower alkyl or nitro; and trialkylamine aryl sulfonamides such as trimethylamine-p-toluene-sulfonimide.

(j) Amido-triazoles having the formula:



wherein:

R¹ represents a hydrogen atom or an alkyl group having from 1 to 5 carbon atoms, such as methyl, ethyl, iso-propyl and the like;

R² and R³ either both represent hydrogen atoms or taken together form an aromatic, a cycloalkyl or a heterocyclic ring; and

Z³ represents from 4 to 8 nonmetallic atoms necessary to complete one or more substituted or unsubstituted aromatic ring.

Such amido-triazoles including, for example, 5-methyl-1-(2)-N-(phenylcarbamoyl)benzotriazole, 5, 6-dichloro-1-(2)-N-(dimethyl carbamoyl) benzotriazole.

(k) Thiolate precursors having the formula:



wherein:

0 003 263

(o) Protonated arylene diamines having the structure:



wherein:

Ar represents a substituted or unsubstituted arylene group containing from 6 to 20 carbon atoms, R¹³ represents a hydrogen atom or an alkyl group having 1 to 3 carbon atoms, and, n' and n'' are each 1, 2 or 3; provided that the sum of n' and n'' is 3. Useful protonated p-phenylene diamines include those which are characterized by the loss of the extra proton when heated, creating the unprotonated form which undergoes a redox reaction with the cobalt(III) complex.

(p) Polymers having repeating units with the structure:



wherein:

R¹⁴ represents an organic polymer chain;

R¹⁵ represents an organic moiety or a carbon-to-carbon bond;

Ar is arylene including substituted arylene, such as phenylene and naphthylene, wherein the substituents, if any, are electron withdrawing groups such as nitro, sulfoalkyl containing from 1 to 5 carbon atoms, halogen such as chloride, fluoride and the like, and substituted alkyl such as trihalosubstituted methyl; and

R¹⁶ represents a hydrogen atom or an alkyl group having from 1 to 3 carbon atoms.

All of the preceding destabilizers induce the release of the ligands from the cobalt(III) complex in the presence of heat. As noted, they may or may not require the presence of an amplifier-dye former such as phthalaldehyde. Some of them, such as destabilizer materials (a) through (d), are quite clearly reducing agents per se. Some like destabilizer material (k) are heat-responsive reducing agent precursors. Some, such as destabilizer material (e) and others are heat-responsive amine precursors. They are particularly useful with amine-responsive reducing agents and reducing agent precursors such as phthalaldehyde that form reducing agents in the presence of amines. Some such as destabilizer materials (h), (i) and (j) are believed to be base precursors which form a base in the presence of heat. Destabilizer materials (a) through (d) which are direct reducing agents do not require the presence of an amplifier such as o-phthalaldehyde, although an amplifier is effective to increase the speed of an element or composition of the invention which incorporates these compounds.


Quinone photoreductants are yet another class of destabilizer materials which are useful in inducing the release of amines from the cobalt complex. The quinones which are particularly useful as photoreductants include ortho- and para-benzoquinones and ortho- and para-naphthoquinones, phenanthrenequinones and anthraquinones. The quinones may be unsubstituted or incorporate any substituent or combination of substituents that does not interfere with the conversion of the quinone to the corresponding reducing agent. A variety of such substituents are known in the art and include, but are not limited to, primary, secondary and tertiary alkyl, alkenyl and alkynyl, aryl, alkoxy, aryloxy, alkoxyalkyl, acyloxyalkyl, aryloxyalkyl, aryloxyalkoxy, alkylcarbonyl, carboxy, primary and secondary amino, aminoalkyl, amidoalkyl, anilino, piperidino, pyrrolidino, morpholino, nitro, halide and other similar substituents. Aryl substituents are preferably phenyl substituents. Alkyl, alkenyl and alkynyl substituents, whether present as sole substituents or in combination with other atoms, typically contain 20 or fewer (preferably 6 or fewer) carbon atoms.

A preferred class of photoreductants are internal hydrogen source quinones; that is, quinones incorporating labile hydrogen atoms. These quinones are more easily photo-reduced than quinones which do not incorporate labile hydrogen atoms.

Particularly preferred internal hydrogen source quinones are 5,8-dihydro-1,4-naphthoquinones having at least one hydrogen atom in each of the 5- and 8-ring positions. Other preferred incorporated hydrogen source quinones are those which have a hydrogen atom bonded to a carbon atom to which is also bonded the oxygen atom of an oxy substituent or a nitrogen atom of an amine substituent with the further provision that the carbon-to-hydrogen bond is the third or fourth bond removed from at least

0 003 263

R¹⁹ represents a hydrogen or a halogen atom such as chlorine or bromine;
Z⁶ represents a




5

R²⁰ represents a hydrogen atom or an alkyl group having 1 to 5 carbon atoms; and
X^{1⊖} is a suitable anion. Useful examples include N-methyl-3-phenyl-2,1-benzisozolium
perchlorate and N-methyl-3-phenyl-2,1-benzisoxazolium fluorosulfonate; and
10 (d) other halogenated organic compounds such as idoform and the like.
Highly preferred class (a) photoinhibitors are those having the formula:

15

20




wherein:

- 25 E represents a hydrogen atom, a methyl or trihalomethyl group;
R²¹ represents a hydrogen atom or an alkoxy group having from 1 to 5 carbon atoms, such as
methoxy, ethoxy and the like;
R²² represents a hydrogen or a halogen atom such as chlorine or fluorine, a nitro group or an alkyl,
dialkylamine, or alkoxy group containing from 1 to 5 carbon atoms in the alkyl portion such as methyl,
30 ethyl, isopropyl and the like;
R²³ represents a hydrogen atom or an alkoxy group having from 1 to 5 carbon atoms, or together
with R²⁴ comprises the non-metallic atoms necessary to complete an aromatic ring;
R²⁴ represents a hydrogen atom or together with R²³ comprises the non-metallic atoms necessary
to complete an aromatic ring;
35 Z⁷ represents the non-metallic atoms necessary to complete one or more substituted or
unsubstituted heterocyclic rings containing from 6 to 10 atoms, such as S-triazine, quinoline,
quinoxaline, pyrazine, pyrimidine, and the like.
m'' is 0, 1 or 2; and
X'' represents a halogen atom such as chlorine or bromine. Particularly useful examples include
40 S-triazines having the formula:

45

50




wherein:

X'', R²¹, R²², R²³, and R²⁴ are as defined above, and
Y is the same or different from X'' and is selected from the group consisting of halogen and
hydrogen, at least one of X'' and Y being halogen.

55

Class (b) photoinhibitors are highly preferred which have the formula:

60



65 wherein:

0 003 263

R²⁵ represents an alkyl group having from 1 to 3 carbon atoms, an aralkyl group having from 7 to 8 carbon atoms, such as benzyl, phenethyl and the like, or when taken together with R²⁶, the atoms necessary to complete a fused heterocyclic ring such as indole and the like;

5 R²⁶ represents a halogen atom such as chlorine, bromine and the like, or together with R²⁵ it forms a fused heterocyclic ring;

R²⁷ represents a hydrogen atom or an alkoxy group having from 1 to 3 carbon atoms, such as methoxy, ethoxy and the like; and

X''' represents a halogen atom such as a chlorine, bromine or fluorine atom.

The following Table I is a partial listing of useful photoinhibitors of the invention:

10

TABLE I
Photoinhibitors

	PI 1 — iodoform
15	PI 2 — 2,4-bis(trichloromethyl)-6-(p-anisyl)-s-triazine
	PI 3 — 2,4-bis(trichloromethyl)-6-(4-methoxystyryl)-s-triazine
20	PI 4 — 2,4-bis(trichloromethyl)-6-[4-dimethylaminophenyl]-1,3-butadienyl]-s-triazine
	PI 5 — 2-tribromomethylquinoline
	PI 6 — 2-tribromomethylquinoxaline
25	PI 7 — 2-tribromomethyl-4-oxo-4H-1-benzopyran
	PI 8 — N-methyl-o-nitrotrifluoroacetanilide
	PI 9 — N-benzyl-o-nitrotrifluoroacetanilide
30	PI 10 — N-benzyl-2-nitro-5-methoxy-trifluoroacetanilide
	PI 11 — 2,4-bis(trifluoromethyl)-6-(1-naphthyl)-s-triazine
35	PI 12 — 2,4-bis(trichloromethyl)-6-(4-methoxy-1-naphthyl)-s-triazine
	PI 13 — 6-bromo-8-nitro-N-trifluoroacetyl-benzo[b]piperidine
	PI 14 — N-methyl-3-diazo-4-quinolinium-p-toluenesulfonate
40	PI 15 — 2,4-bis(trichloromethyl)-6-[p-dimethylamino]styryl]-s-triazine
	PI 16 — N-methyl-3-phenyl-2,1-benzisoxazolium perchlorate
45	PI 17 — N-methyl-3-phenyl-2,1-benzisoxazolium fluorosulfonate
	PI 18 — carbon tetrabromide
	PI 19 — β -tribromoethanol
50	PI 20 — hexabromoethane
	PI 21 — ethyl tribromoacetate
55	PI 22 — tribromoacetamide
	PI 23 — tribromomethylbenzene
	PI 24 — pentabromoethane
60	PI 25 — α,α,α -tribromoacetophenone
	PI 26 — 3-nitro- α,α,α -tribromoacetophenone
65	PI 27 — 2,3-bis(tribromomethyl) quinoxaline.

Elements

In the simplest form of the invention an imaging element comprises a support coated with a single layer containing an image precursor composition and a photoinhibitor as described above. Alternatively, the image precursor composition and the photoinhibitor can be in one or more layers.

5 Alternatively the outermost layer can be coated on a separate support and disposed in reactable association subsequently, such as after exposure of the photoinhibitor composition. For example, the image-forming material can be included either as an integral portion of the element of the invention, or it can be subsequently associated therewith as a separate image-recording layer. In those

10 embodiments wherein the image-forming material is an integral part of the element, it can either be admixed with the image precursor (cobalt(III) complex) preferably as a dye-forming material, or it can be in a separate, adjacent layer. In those embodiments wherein it is admixed with the cobalt(III) complex, it is highly preferred that the image-forming material is also an amplifier, such as *o*-phthalaldehyde which also functions as a reducing agent precursor.

Yet another alternative is to imbibe the photoinhibitor into the image precursor composition, such as by spraying or otherwise applying a solution of the photoinhibitor to the element already containing the precursor composition.

Preferably the image precursor composition and photoinhibitor are contained in a layer or layers coated onto a support. Any conventional photographic support can be used in the practice of this invention. Typical supports include transparent supports, such as film supports and glass supports, as well as opaque supports, such as metal and photographic paper supports. The support can be either

20 rigid or flexible. The most common photographic supports for most applications are paper and transparent film supports. Suitable exemplary supports are disclosed in *Product Licensing Index*, Volume 92, December 1971, Publication No. 9232, at page 108, and *Research Disclosure*, Volume 134, June 1975, Publication No. 13455, published by Industrial Opportunities Limited, Homewell, Havant, Hampshire PO9 1EF, United Kingdom. The support can incorporate one or more subbing layers for the purpose of altering its surface properties so as to enhance the adhesion of the radiation-sensitive coating to the support.

The image-precursor composition can include a binder. Any binder compatible with cobalt(III) complexes can be used, for example, the binders listed in the aforesaid Publication No. 12617 of

30 *Research Disclosure*, especially paragraph I(D). Typical of such binders are acetates, cellulose compounds, vinyl polymers, polyacrylates and polyesters. In those embodiments relying upon *o*-phthalaldehyde as the image-forming material and/or as an amplifier, it is preferred that the binder be selected which will maximize the minimum neutral densities produced during exposure and development. Highly preferred examples of such binders include certain polysulfonamides, for

35 example, poly(ethylene-co-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenesulfonamide) and poly(ethylene-co-hexamethylene-1-methyl-2,4-benzenedisulfonamide), and poly(methacrylonitrile).

The coating solvent selected will, of course, depend upon the makeup of the composition, including the binder if any. Typical preferred solvents which can be used alone or in combination are lower alkanols, such as methanol, ethanol, isopropanol, *t*-butanol and the like; ketones, such as methyl-

40 ethyl ketone, acetone and the like; water; ethers, such as tetrahydrofuran, and the like; acetonitrile; dimethyl sulfoxide, dimethylformamide and chlorinated hydrocarbon solvents which are not effective as acid generators, because they volatilize out of the coating.

The proportions of the non-binder reactants forming the composition to be coated on the imaging element can vary widely, depending upon which materials are being used.

45 A useful range of coating coverage of cobalt(III) complex is between about 5 and about 50 mg/dm².


Since a cobalt(III) complex is always present, the molar amounts of other components are expressed per mole of complex. Thus, if destabilizer materials are incorporated in the composition in addition to cobalt(III) complex, they can vary widely such as from 0.004 moles of ferrocene to 5 moles

50 of other destabilizers per mole of complex. For example, 5-*n*-butylbarbituric acid can be present in an amount of between about 0.005 moles and about 5 moles per mole of the complex. The photoinhibitor can be present in an amount from 0.005 to 2.5 moles per mole of cobalt(III) complex. For example, 2,4-bis(trichloromethyl)-6-(*p*-anisyl)-*s*-triazine can be present in those amounts.

Typically, the energy-activatable composition is coated onto the support in a solution by such means as whirler coating, brushing, doctor-blade coating, hopper coating and the like. Thereafter, the solvent is evaporated. Other exemplary coating procedures are set forth in the *Product Licensing Index*, Volume 92, December 1971, Publication No. 9232, at page 109, published by Industrial Opportunities Limited, Homewell, Havant, Hampshire PO9 1EF, United Kingdom. Addenda such as coating aids and plasticizers can be incorporated into the coating composition.

60 In certain instances, an overcoat for the energy-activatable layer of the element can provide improved handling characteristics, and can help to retain otherwise volatile components. Useful

examples include crosslinked gelatin overcoats crosslinked with a crosslinking agent such as hexamethoxy methyl melamine, and polymers having the recurring units:



wherein:

R²⁸ represents a hydrogen atom or an alkyl group having from 1 to 3 carbon atoms;

R²⁹ represents an alkylene group having from 1 to 3 carbon atoms;

R³⁰ represents an alkyl group having from 1 to 3 carbon atoms;

m' is 1 or 0;

Z⁸ represents from 3 to 8 non-metallic atoms necessary to complete one or more saturated or unsaturated heterocyclic ring;

D represents —NH— or —O—; and

x, y, z and z' represent weight percents of the recurring units of the polymer and

$$25 \leq x \leq 90$$

$$10 \leq y \leq 75$$

$$0 \leq z \leq 10$$

$$0 \leq z' \leq 10.$$

The preferred form of the overcoat is a dual coating first of gelatin crosslinked as noted, and as a final coat, a layer of cellulose acetate having an acetyl content of 19 weight percent and an ash content of 0.04 weight percent.

Figs. 1A through 1C are schematic sectional views of an element of the invention, each view illustrating a step in a positive-working processing of the element in accordance with the invention;

Figs. 2A and 2B are sectional views similar to those of Figs. 1A through 1C, wherein a negative-working process is demonstrated; and

Fig. 3 is a sectional view similar to that of Fig. 1, but illustrating still another embodiment.

Further details of the imaging element, and the process of use, can be understood by reference to the drawings. In Fig. 1A, element 10 comprises a support 12 and a layer 14 containing, in admixture, an energy-activatable image precursor composition designated by wavy lines, a photoinhibitor, and an image-forming material such as a dye-forming material. The element is exposed through an image 18 to radiation which activates the photoinhibitor, preferably light, designated by arrows 16. The radiation activates the photoinhibitor in portions 20 and 22 of Fig. 1B to inhibit the image precursor composition, as indicated by the absence of wavy lines, but not in the unexposed portion 24.

Imaging elements containing light-activatable photoreductants are usable even though they also contain light-activatable photoinhibitors because the photoinhibitors are generally activated more rapidly than the photoreductants. Generally the photoinhibitors are activated by shorter wavelength radiation than the photoreductants. Therefore it may be desirable to interpose an optional filter 25, shown in phantom in Fig. 1A, which transmits shorter wavelength radiation 16 that activates the photoinhibitor but does not transmit longer wavelength radiation that activates the photoreductant. For example, if the photoinhibitor is iodoform and the image precursor composition includes a quinone photoreductant, a "Wratten 18A" filter, manufactured by Eastman Kodak Company, can be used. "Wratten" is a trade mark.

Thereafter, as shown in Fig. 1B, the entire element is given a uniform exposure to thermal radiation or light which activates the image precursor composition as indicated by arrows 26. If the image precursor composition contains a photoreductant, the uniform exposure is to light and it is necessary to prevent the photoinhibitor in portion 24 from responding. A preferred method for accomplishing this is the interposition of a suitable filter 28, shown in phantom in Fig. 1B. Such a filter is selected to cut off the light wavelengths which are necessary for the photo-activation of the

photoinhibitor, and to transmit the wavelengths, usually longer, useful in activating the photoreductant. For example, if the photoinhibitor is iodoform and the image precursor composition includes a quinone photoreductant, a "Wratten 2A" filter can be used.

5 The effect of the uniform exposure of the image precursor composition is to generate a dye in portion 24, Fig. 1C, and none in the inhibited portions 20 and 22, thus rendering element 10 positive-working. The dye is schematically shown by the superimposed straight lines.

For example, the presently preferred embodiment features *o*-phthalaldehyde as an amplifier and dye-forming material incorporated in layer 14, along with an *s*-triazine photoinhibitor such as 2,4-bis(trichloromethyl)-6-(*p*-anisyl)-*s*-triazine, hexaammine cobalt(III) trifluoroacetate complex and either 10 5-butylbarbituric acid or diphenylhydantoin as a destabilizer. Imagewise exposure to light activates the photoinhibitor. A subsequent overall thermal exposure, such as at 150°C for the barbituric acid and 130°C for the hydantoin, causes reduction of the complex, release of ammonia, formation of the adduct of phthalaldehyde further reduction of remaining cobalt(III) complex, release of more ammonia, and amplified dye formation.

15 Alternatively, the image-forming material of the image precursor composition, which can be, for example, *o*-phthalaldehyde as noted above, can be disposed in an adjacent layer 30, shown in phantom in Figs. 1B and 1C. As shown, layer 30 can be positioned as an overlay in contact with element 10 after the imagewise exposure as shown in Fig. 1A, or alternatively, it can be overcoated onto layer 14 as an integral portion of element 10. In either case the uniform exposure which activates the image precursor 20 composition, arrows 26, will develop the release of NH₃ ligands in portion 24 only. The NH₃ ligands will migrate to portion 32 of the layer 30 as shown by arrows 34, where either a dye is formed or a pre-incorporated dye is bleached or altered in color. Thereafter, layer 30 can be removed from or retained on, element 10.

In Fig. 2A, the same element as in Fig. 1A is given a different treatment to render it negative- 25 working. Specifically, the same identical element, regardless of the image precursor composition used, is rendered negative-working merely by changing the exposure sequence. That is, the process step effectuated by imagewise exposure is now an exposure capable of activating the image precursor composition rather than the photoinhibitor. Parts similar to those previously described bear the same reference numerals to which the distinguishing suffixes "a" are added. For purposes of comparing this 30 negative-working mode to the positive-working mode previously discussed, it is again assumed that the image-forming material of the image precursor composition is a dye-forming material. Thus, element 10a comprises the same coating 14a on support 12a as described before. However, imagewise exposure (arrows 16a) through image 18a must not activate the photoinhibitor. If exposure 16a is thermal, only the image precursor composition is activated. In such instance, image 18a is selected so 35 as not to significantly reradiate in the "dark" areas. If however, exposure 16a is broadband light radiation, it preferably passes through a suitable filter 28a, shown in phantom, selected to prevent transmission of radiation sufficient to activate the photoinhibitor, but to allow transmission of radiation sufficient to activate the image precursor composition. As noted before, a "Wratten 2A" filter is effective if the photoinhibitor is iodoform and the image precursor composition contains a quinone 40 photoreductant destabilizer. In the case where a photoreductant destabilizer material is used, an optional subsequent thermal exposure can be included. Dye imagewise develops in areas 20a and 22a, Fig. 2B.

The element is then given overall exposure arrows 26a of Fig. 2B, to radiation which activates the photoinhibitor to prevent background printup. As in the case of the imagewise exposure step of Fig. 1A, 45 it may be desirable in some instances to interpose a suitable filter 25a, shown in phantom, to insure that the exposure 26a does not activate the image precursor composition.

As in the case of the process shown in Figs. 1B and 1C, the negative image can be formed instead in an adjacent layer, not shown, by transfer of ligands thereto from layer 14a.

50 If the photoinhibitor includes a compound having a response only to radiation of wavelengths shorter than 300 nm. and a spectral sensitizer, as described above, it is contemplated that the element of the invention is one in which the photoinhibitor and the image precursor composition each occupy two separate but adjacent layers 40 and 50, element 10b of Fig. 3. In this manner, the spectral sensitizer will sensitize only the photoinhibitor and not also the cobalt(III) complex or the destabilizer material, so that photoinitiation of the inhibitor will not also act to activate the image precursor 55 composition. If the photoinhibitor does not inherently produce a volatile acid capable of being readily transferred to the layer containing the image precursor composition, for the inhibition step, the photoinhibitor layer can optionally include sodium trifluoroacetate, to produce in the presence of the non-volatile acid generated by the photoinhibitor, trifluoroacetic acid which is sufficiently volatile.

60

Examples

Examples 1—3

Use of Organo-Metallic Destabilizer

65 Stock solution A was prepared by dissolving 265 mg of the cobalt complex, hexaamminecobalt(III) trifluoroacetate, 535 mg of *o*-phthalaldehyde as amplifier and image-former and 30 mg of 2,4-

bis(trichloromethyl)-6-p-methoxystyryl-s-triazine as photoinhibitor in 2 g of acetone. To this solution was added 10 g of a 20% solution of the binder poly(ethylene-cohexamethylene-1-methyl-2,4-benzenedisulfonamide) in 1:1 acetone/methylethylketone.

Solution B was prepared by dissolving 4 mg of the destabilizer ferrocene (dicyclopentadienyl iron) in 6 g of acetone. Solution C was prepared by dissolving 4 mg of the destabilizer 1,1-dimethylferrocene in 6 g of acetone. Solution D was prepared by dissolving 10 mg of the destabilizer N,N-dimethylaniline chromium tricarbonyl in 6 g of acetone.

To 1.0 g of stock solution A was added 0.1 g of solution B to form the coating solution for Example 1. This solution was then coated with a 100-micron doctor blade on a subbed poly(ethylene-terephthalate) support, dried, and overcoated with a 5% aqueous solution of poly(acrylamido-co-N-vinyl-2-pyrrolidinone-co-2-acetoacetoxyethylmethacrylate using a 50-micron doctor blade, and dried. After drying, the film was exposed through a silver negative for about 8 seconds to the light from a 400 watt medium pressure mercury arc lamp in an IBM Microcopier IID exposing apparatus and dye-developed by heating, face up, for five seconds on a heated block at 160°C. A high density, positive image resulted. Similar results were obtained when solutions C and D were substituted for solution B to make the coating solutions for Examples 2 and 3.

Example 4

4-Phenyl Catechol as A Destabilizer Material Without Phthalaldehyde

20 mg of $[\text{Co}(\text{NH}_3)_6](\text{CF}_3\text{CO}_2)_3$, 7 mg of the destabilizer, 4-phenyl catechol and 16 mg of iodoform as the photoinhibitor were dissolved in 700 mg of acetone. 1.4 g of a 15 percent solution of cellulose acetate butyrate, as binder, in acetone were added and the resulting solution was coated with a 100 micron doctor blade on a subbed poly(ethylene terephthalate) support. This film was exposed for 8 seconds through a 0.3 log E silver step tablet in a copying apparatus containing a 400-watt medium pressure mercury arc lamp (commercially available as a Micro Master Registered Trade Mark Diazo T.M. Copier). The exposed film was placed in face-to-face contact with a diazo-coupler recording element as an image forming layer (commercially available from Eastman Kodak Company as Kodak Registered Trade Mark Diazo Type M) and the sandwich was passed twice through a set of rollers heated to 140°C at a speed of 12.7 cm per minute. A positive bluish image of the step tablet was produced with minimum densities of 0.07 and maximum densities of 0.5, when read using red light.

Examples 5—6

Use of Sulfonamidophenyls and Naphthols as Destabilizer Materials

The following composition was prepared:

35	Acetone (solvent)	81.5 g
40	Poly(ethylene-co-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide (binder)	11.1 g
	N,N-bis(2-hydroxyethyl)dodecanamide (destabilizer enhancer)	0.748 g
45	$[\text{Co}(\text{NH}_3)_6](\text{CF}_3\text{CO}_2)_3$	1.73 g
	2-4-bis(trichloromethyl)-6-(p-methoxystyryl)-s-triazine (photoinhibitor)	0.0196 g
50	2,4-bis(trichloromethyl)-6-(p-anisyl)-s-triazine (photoinhibitor)	0.288 g
	<i>o</i> -Phthalaldehyde (amplifier and image-former)	3.46 g
55	"SF—1066" Surfactant, a dimethyl polyoxyalkylene ether copolymer supplied by General Electric Company (coating aid)	0.92 g

60 To identical 4.0 g portions of the above solution were added respective 12.0 mg portions of the following sulfonamidophenol destabilizers:

Example 5

4-phenylsulfonamido-2,6-dichlorophenol

65

0 003 263

Example 6

4-phenylsulfonamido-2-methyl-1-naphthol

The resulting solutions were then coated with a 150-micron doctor blade on subbed poly(ethylene terephthalate) support, dried and then overcoated with a 4.7% aqueous solution of poly(acrylamido-Co-N-vinyl-2 pyrrolidinone-Co-2-acetoacetoxy methacrylate copolymer (50:45:5 by weight) containing 0.05% Surfactant 10G, a nonylphenoxyglycerol coating aid, with a 50-micron doctor blade.

Samples of the dried coatings were then exposed for about two seconds through a 0.15 log E step tablet in an IBM Microcopier IID exposing apparatus. Processing for a 7.3 second contact time at 150—155°C in a Canon Kal-Developer Model 360 VC resulted in positive images for each coating.

Further coating samples were similarly exposed and dye-developed for ten seconds, face up, on a hot block. The neutral D-max obtained as a function of process temperature follows:

	Example	Temperature	D-min	D-max
15	5	145°C	0.03	0.04
	5	150°C	0.03	0.08
20	5	155°C	0.04	0.15
	5	160°C	0.04	0.60
25	5	165°C	0.04	0.72
	5	170°C	0.08	2.10
30	6	145°C	0.08	2.79
	6	150°C	0.08	3.14
	6	155°C	0.08	3.19
35	6	160°C	0.23	3.21
	6	165°C	0.31	3.28
40	6	170°C	0.66	3.37

Example 7

Other Naphthol Destabilizer Materials

A solution was prepared by dissolving 200 mg of $[\text{Co}(\text{NH}_3)_6] (\text{CF}_3\text{CO}_2)_3$, 400 mg of the amplifier and image-former *o*-phthalaldehyde, and 200 mg of 2,4-bis(trichloromethyl)-6-*p*-methoxystyryl-*s*-triazine as photoinhibitor in 2 g of acetone. To this solution were added 8 g of a 20% solution of the binder poly(ethylene-co-hexamethylene-1-methyl-2,4-benzenedisulfonamide) in acetone.

In 2 g of this solution was dissolved 1 mg of the destabilizer, 4-methoxynaphthol. This solution was coated with a 100 micron doctor blade on subbed poly(ethylene terephthalate) support, dried, and then overcoated with a 5% aqueous solution of the overcoat polymer of Example 1 using a 50 micron doctor blade. After drying, the film was exposed and dye-developed in the manner described in Example 1, to give a neutral positive image with a D-max of 2.7 and a D-min of 0.08.

55

60

65

0 003 263

Example 8

A Pyrazolidine as a Destabilizer Material

The following composition was prepared:

5	Acetone (solvent)	15.87 g
	Poly(ethylene-co-1,4-cyclohexylenedi- methyl-1-methyl-2,4-benzenedisulfon- amide) (binder)	77.6 g
10	N,N-bis(2-hydroxyethyl)dodecanamide (destabilizer enhancer)	0.65 g
	[Co(NH ₃) ₆](CF ₃ ·CO ₂) ₃	1.73 g
15	2,4-bis(trichloromethyl-6-(p-methoxy- styryl)-s-triazine (photoinhibitor)	0.017 g
	2,4-bis(trichloromethyl)-6-(p-anisyl)-s- triazine (photoinhibitor)	0.25 g
20	<i>o</i> -Phthalaldehyde (amplifier and image- former)	3.01 g
25	GE SG—1066 Surfactant (coating aid)	0.80 g

To a 3.8 g portion of this composition was added 6.5 mg of 4-hydroxymethyl-4-methyl-1-phenyl-3-pyrazolidone.

30 The resulting solution was then coated with a 150-micron doctor blade on a subbed poly(ethylene terephthalate) support, and dried. The coating was overcoated with a 5% aqueous solution of the overcoat polymer of Example 1 containing 0.05% Surfactant 10G with a 50-micron doctor blade.

A sample of the dried coating was then exposed for about 16 seconds through a 0.15 log E step tablet to the light from a medium pressure mercury arc lamp in an IBM Microcopier IID exposing apparatus and heat processed for a 5.5-second contact time at 150°C in a Canon Kal-Developer, Model 360 VC. A positive image with neutral D-max of about 2.73 and a brownish D-min of 0.21 was obtained.

Example 9

Another Pyrazolidone Destabilizer

40 A solution was prepared by dissolving 200 mg of [Co(NH₃)₆](CF₃·CO₂)₃, 400 mg of *o*-phthalaldehyde (amplifier and image-former), and 200 mg of the photoinhibitor 2,4-bis(trichloromethyl)-6-p-methoxystyryl-s-triazine in 2 g of acetone. To this solution were added 8 g of a 20% solution of the binder poly(ethylene-co-hexamethylene-1-methyl-2,4-benzenedisulfonamide) in acetone.

45 In 2 g of the above solution was dissolved 1 mg of 4,4-dimethyl-1-phenyl-3-pyrazolidone. This solution was coated with a 4-mil doctor blade on subbed poly(ethylene terephthalate) support, dried, and then overcoated with a 5% aqueous solution of the overcoat polymer of Example 1 using a 50-micron doctor blade. After drying again, the film was exposed through a silver negative for about 8 seconds in an IBM microcopier IID exposing apparatus and heat-processed, face up, for five seconds on a 160°C hot block to give a neutral positive image with a D-max of 3.0 and a D-min of 0.05.

Example 10

Acids as Destabilizer Materials

55 An image precursor composition solution was prepared for Example 10 comprising 400 mg of [Co(NH₃)₆](CF₃·CO₂)₃, 800 mg of *o*-phthalaldehyde as amplifier and image-former, 200 mg of N,N-bis(2-hydroxyethyl) dodecanamide as destabilizer enhancer, and 40 mg of 2,4-bis(trichloromethyl)-6-p-methoxystyryl-s-triazine as photoinhibitor in 20 gms of 20% poly(ethylene-co-1,4-cyclohexylenedi-methylene-1-methyl-2,4-benzenedisulfonamide (binder) in acetone.

60 To two grams of this solution was added 4 mg of phthalamic acid, and the solution was then coated on subbed poly(ethylene terephthalate) with a 100-micron coating knife. A 50-micron overcoat of the overcoat polymer of Example 1 (5% in water) was then applied after drying. The resulting film was exposed for 8 seconds in an IBM Microcopier IID exposing device through a 0.3 log E step tablet and heated for 5 seconds, face up, on a 160°C hot block. A positive neutral image with a D-max/D-min ratio of 2.0/0.06 was produced.

0 003 263

Example 11

Example 10 was repeated except that 4 mg of the destabilizer, 2-carboxycyclohexylamide was used in place of the phthalamic acid. A positive image was produced having D-max/D-min ratio of 2.1/0.06.

5

Example 12

A Urea as a Destabilizer Material

A solution of an image precursor composition was prepared by dissolving 266 mg of $[\text{Co}(\text{NH}_3)_6](\text{CF}_3\text{-CO}_2)_3$ and 534 mg *o*-phthalaldehyde as amplifier and image-former in 2 g of acetone and adding to this 10 g of a 20% solution of the binder, poly(ethylene-*co*-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide) in acetone.


In 2 g of this solution, were dissolved 8 mg of iodoform as photoinhibitor and 5 mg of 1-(2-hydroxyphenyl)urea as destabilizer. This solution was coated with a 100-micron doctor blade and overcoated with a 5% aqueous solution of the overcoat polymer of Example 1 using a 50-micron doctor blade. The film was dried and exposed through a silver negative for 8 seconds on a Microcopier IID and dye-developed by heating, face up, for 5 seconds on a 160°C hot block to produce a neutral positive image with a maximum density of 2.8.

15

Example 13

Example 12 was repeated except that the photoinhibitor iodoform was replaced with 1 mg of

20



25

The film was exposed through a silver negative for 7 seconds to a 650-watt incandescent light source (commercially available under the trade name Nashua 120 Multi-Spectrum Copier). When dye-developed by the process described in Example 10, a neutral positive image with a maximum density of 2.3 was produced.

30

Example 14

Salts as Destabilizer Materials

In 3.8 g of a 13.6% solution of the binder, poly(ethylene-*co*-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide) in acetone were dissolved 66.4 mg of $[\text{Co}(\text{NH}_3)_6](\text{CF}_3\text{-CO}_2)_3$, 120 mg of the image-former *o*-phthalaldehyde; 9.9 mg of the photoinhibitor, 2,4-bis(trichloromethyl)-6-(*p*-anisyl)-*s*-Triazine; 26 mg of *N,N*-bis(2-hydroxyethyl) dodecanamide as destabilizer enhancer; and 12 mg of SF-1066 surfactant (from General Electric). To this solution was added 9.6 mg of 1-(β -aminoethyl)-2-imidazolidione trichloroacetate as destabilizer and the resulting solution was coated with a 150-micron doctor blade on subbed poly(ethylene terephthalate) support. This coating was then overcoated with a 4.5% solution of the overcoat polymer of Example 1 in water with 0.06% 10G surfactant coating aid using a 50-micron doctor blade.

35


40

The dried coating was exposed for 2 seconds through a 0.15 log E step tablet using a Micro Master Diazo T.M. Copier and dye-developed by heating, face up, in a 150°C Canon Kai-Developer, Model 360 VC for 5.5 seconds. A brownish positive image having a D-max of 0.98 and a D-min of 0.17 to blue light was obtained.


45

It is believed that the destabilizer underwent the following thermal decomposition to generate an amine:

50



55



60

Examples 15—16

In Example 15, Example 14 was repeated except that the destabilizer material comprised 2-amino-2-thiazoline trichloroacetate. Example 16 was a repetition of Example 14 except the destabilizer material was anilinium trichloroacetate. Both of these produced a satisfactory positive image.

65

0 003 263

Example 17

Use of a Morpholine Precursor Destabilizer Material

In 78 g of acetone were dissolved 15.9 g of the binder, poly(ethylene-*co*-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide); 650 mg of N,N-bis(2-hydroxyethyl) dodecanamide as destabilizer enhancer; 1.66 g of $[\text{Co}(\text{NH}_3)_6] (\text{CF}_3\text{-CO}_2)_3$; 17 mg of 2,4-bis(trichloromethyl)-6-(*p*-methoxystyryl)-*s*-triazine as photoinhibitor; 250 mg of the photoinhibitor, 2,4-bis(trichloromethyl)-6-(*p*-anisyl)-*s*-triazine; 3.0 g of *o*-phthalaldehyde as amplifier and image-former; and 800 mg of SF—1066 surfactant (General Electric). To 3.8 g of this solution were added 3.2 mg of the destabilizer, 3,3-bis(morpholino)oxindole. The resulting solution was coated with a 150-micron doctor blade on subbed poly(ethylene terephthalate) support, dried, and subsequently overcoated with a 4.5% solution of the overcoat polymer of Example 1 in water with 0.05% 10G surfactant coating aid using a 50-micron doctor blade.

The dried coating was exposed for 8 seconds through a 0.15 log E silver step tablet using the Micro Master Diazo T.M. Copier and dye developed by heating, face up, on a 150°C hot block. A neutral positive image having a D-max of 2.56 and D-min of 0.06 was obtained.

Examples 18—27

Aminimides as Destabilizer Materials

A solution of an image precursor composition was prepared as follows:

20	12.9 g	Poly(ethylene- <i>co</i> -1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide (binder)
25	81.6 g	Acetone (solvent)
	0.30 g	General Electric SF—1066 Surfactant
30	0.65 g	Recrystallized N,N-bis(2-hydroxyethyl)-dodecanamide (destabilizer enhancer)
	3.01 g	<i>o</i> -phthalaldehyde (amplifier and image-former)
35	0.25 g	2,4-bis(trichloromethyl)-6- <i>p</i> -anisyl- <i>s</i> -triazine (photoinhibitor)
	0.017 g	2,4-bis(trichloromethyl)-6-[<i>p</i> -methoxystyryl]- <i>s</i> -triazine (photoinhibitor)
40	1.66 g	$[\text{Co}(\text{NH}_3)_6] (\text{CF}_3\text{-CO}_2)_3$

45 To 10.0 g samples of the preceding solution were added the aminimides of Table III. A separate control was prepared using the destabilizer, 5,5-diphenylhydantoin in place of the aminimide.

50



55

60

65

0 003 263

TABLE III
Aminimides

5	Example	Aminimide	Amount (mg)
	Control	None (5,5-diphenylhydantoin)	20.8
10	18	(trimethylamine)cinnamimide	16.8
	19	bis(dimethyl-2-hydroxypropyl-amine)adipimide	14.3
15	20		
20			19.3
25	21	(Dimethyl-2-hydroxypropylamine) palmitimide	29.3
30	22	(Dimethyl-2-hydroxypropylamine) laurimide	24.8
	23	(Dimethyl-2-hydroxypropylamine) myristimide	27.0
35	24	bis(trimethylamine)sebacimide	13.0
	25	Poly[(N,N-dimethyl-2-hydroxypropylamine)methacrylimide]	15.3
40	26	Poly[(trimethylamine)methacrylimide]	11.8
	27	bis(trimethylamine)azelamide	13.8

45 After mixing the resulting solutions, handcoatings were made utilizing a 150-micron wet laydown upon a transparent, subbed, poly(ethylene terephthalate (support). The coatings were appropriately dried and then overcoated with a 50-micron wet laydown of 4.5% aqueous solution of the overcoat polymer of Example 1 containing 0.6% 10G surfactant and dried. Coating samples were sensitometrically exposed in an IBM Microcopier IID exposing unit and dye-developed by heating, face up, for 5 to 10 seconds in a 150°C Canon Kalfite processor. All samples and the control developed black dye in the non-image areas and remained clear in the exposed areas, and thus were positive-working. Example 18 was 1.2 log E slower and 0.3 higher in neutral D-max than the control which exhibited a D-max of 2.6.

55 It was further found that Example 18 gave a substantial improvement over the control in processing, or development, latitude.

Examples 28—31


Use of Triazole Destabilizer Materials

60 In 81.5 g of acetone were dissolved 11.1 g of poly(ethylene-co-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide) (binder), 748 mg of N,N-bis(2-hydroxyethyl)dodecanamide (destabilizer enhancer), 1.73 g of [(Co(NH₃)₆)] (CF₃-CO₂)₃, 19.6 mg of 2,4-bis(trichloromethyl)-6-(p-methoxystyryl)-s-triazine (photoinhibitor), 288 mg of 2,4-bis(trichloromethyl)-6-(p-anisyl)-s-triazine (photoinhibitor), 3.46 g of o-phthalaldehyde (image-former) and 920 mg of SF—1066 surfactant
65 (obtained from General Electric).

0 003 263

Example 28

To 4.0 g of this solution were added 9.5 mg of the destabilizer 5-methyl-1(2)-N-(anilino-carbonyl)benzotriazole, having the formula:




the anilino-carbonyl group being a thermally releasable blocking group.

15 The resulting solution was coated with a 150-micron doctor blade on a subbed poly(ethylene terephthalate) support, dried and then overcoated with a 4.7% solution of the overcoat polymer of Example 1 in water containing 0.05% 10G surfactant coating aid, using a 50-micron doctor blade.


The dried coating was then exposed for 2 seconds through a 0.15 log E silver step tablet using a Micro Master Diazo T.M. Copier and dye-developed by heating, face up, on a 160°C hot block. A

20 brownish, positive image having a D-max of 1.30 and D-min of 0.58 to blue light was obtained. Examples 29—31 were the same as Example 28, with approximately the same results, except that the destabilizer materials were:


25 **Example 29**



35 **Example 30**



45 **Example 31**



55 **Example 32**

Thiolate Precursor Destabilizer Material

8.2 mg of 2-methyl-2-[2-pyridyl]-5-chlorobenzothiazoline (destabilizer); 24.7 mg of N,N-bis(2-hydroxyethyl)-dodecanamide (destabilizer enhancer); 63.1 mg of [Co(NH₃)₆] (CF₃CO₂)₃; 0.7 mg of 2,4-bis(trichloromethyl)-6-[p-methoxystyryl]-s-triazine (photoinhibitor); 9.5 mg of 2,4-bis(trichloromethyl)-6-[p-anisyl]-s-triazine (photoinhibitor); 114.4 mg of *o*-phthalaldehyde (image-former); and 30.4 mg of SF—1066 surfactant were added to 3.6 g of 17% poly(ethylene-co-1,4-cyclohexylene-dimethylene-1-methyl-2,4-benzenedisulfonamide) (binder) in acetone. This solution was coated with a 150-micron doctor blade on subbed poly(ethylene terephthalate) support and dried. This image precursor

60 composition layer was then overcoated with a 5% solution of poly(acrylamide-co-N-vinyl-2-

65

0 003 263

pyrrolidone-co-2-acetoacetoxyethylmethacrylate) in water with 0.05% surfactant 10G coating aid using a 50-micron doctor blade and dried. A sample of the film coating was exposed through a silver negative for 8 seconds on an IBM Microcopier IID device and dye-developed by heating in a 155°C Canon Kal-developer, model 360 VC for 5.5 seconds. A black, positive image with a neutral D-min of 0.12 and a D-max of 3.2 was produced.

Examples 33—35

Example 32 was repeated except that the destabilizer material was, respectively, 2-methyl-2-carboxamidothiazolidine, 2-methyl-2-[2-pyridyl]benzothiazoline, and 2-methyl-2-[4-nitrophenyl]benzothiazoline. When tested at equivalent chemical levels and similar exposure and processing conditions, these materials also yielded satisfactory results.

Example 36

Use of a Blocked Mercaptotetrazole as a Destabilizer Material

0.037 moles of 1-phenyl-[3-toluenesulfonyl]propionyloxy]-5 mercaptotetrazole (See Table IV), 29.9 mg of N,N-bis(2-hydroxyethyl) dodecanamide as destabilizer enhancer, 69.0 mg of $[\text{Co}(\text{NH}_3)_6] \text{CF}_3\text{-CO}_2)_3$, 0.8 mg of the photoinhibitor 2,4-bis(trichloromethyl)-6-[p-methoxystyryl]-s-triazine, 11.5 mg of the photoinhibitor 2,4-bis(trichloromethyl)-6-[p-anisyl]-s-triazine, 138.5 mg of *o*-phthalaldehyde as amplifier and dye-former, and 36.8 mg of SF—1066 surfactant were added to 3.7 g of 12% poly(ethylene-co-1,4-cyclohexylene-dimethylene-1-methyl-2,4-benzenedisulfonamide) (binder) in acetone. This solution was coated with a 150-micron doctor blade on a subbed poly(ethylene terephthalate) support and dried. This basecoat was then overcoated with a 4.7% solution of the overcoat polymer of Example 1 in water with a 0.05% surfactant 10G coating aid using a 50-micron doctor blade and dried. A sample of the film coating was exposed through a silver negative for 2 seconds on an IBM Microcopier IID device and dye-developed by heating on a 170°C hot block for 10 seconds, support side down. A positive image was produced with a D-min of 0.19 and a D-max of 0.90.

Examples 37—41

Example 36 was repeated except that equivalent amounts of the blocked mercaptotetrazoles listed in Table IV were substituted for that of Example 36. When similarly exposed and processed, the elements of Examples 37—41 produced comparable results.

35

40

45

50


55

60

65

0 003 263

TABLE IV
Mercaptotetrazoles



Example 42

Use of a Cyclic Imide as the Destabilizer Material

45 In 2 g of a 20% solution of poly(ethylene-co-1,4-cyclohexylene-dimethylene-1-methyl-2,4-benzenedisulfonamide) (binder) in 95:5 acetone:H₂O were dissolved 40 mg of [Co(NH₃)₆] (CF₃·CO₂)₃, 48 mg o-phthalaldehyde (amplifier and image-former), 5 mg of succinimide as destabilizer, and 30 mg of iodoform as photoinhibitor. This solution was coated with a 100-micron doctor blade on a subbed poly(ethylene terephthalate) support. This film was exposed through a silver negative for 0.5 seconds

50 on an IBM microcopier IID device and dye-developed by heating for 10 seconds face-up on a 145°C hot block. A black positive image with a neutral density D-max of 1.4 and a D-min of 0.04 was formed.

Example 43

55 In 10 gms of a 20% solution of the binder, poly(ethylene-co-1,4-cyclohexylene-dimethylene-1-methyl-2,4-benzenedisulfonamide) in acetone were dissolved 200 mg of [Co(NH₃)₆] (CF₃·CO₂)₃, 400 mg phthalaldehyde (image-former), 25 mg 5,5-diphenylhydantoin (destabilizer) and 20 mg 2,6-bis(trichloromethyl)-6-p-methoxystyryl-s-triazine (photoinhibitor). This solution was coated as in Example 42 and aged for one week to allow sensitometry to stabilize. A sample was exposed through a silver

60 negative for four seconds in the IBM Microcopier IID device. Ten seconds dye-development by heating on a 140°C hot block produced a black positive image with a D-max of 2.05 and a D-min of 0.05.

Example 44

Use of a Barbiturate as a Destabilizer Material

65 A stock solution was prepared by adding 798 mg of [Co(NH₃)₆] (CF₃·CO₂)₃, 1.6 g of o-phthalaldehyde image-former, and 60 mg of 2,4-bis(trichloromethyl)-6-p-anisyl-s-triazine photo-

inhibitor to 30 g of 20% solution of poly(ethylene-co-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide) in acetone.

In 1 g of acetone were dissolved 3 mg of 5-n-butylbarbituric acid. 0.1 g of this solution was then added to 1.0 g of the stock solution, coated, overcoated, exposed, and processed as in Example 7 to give a positive image with a D-max of 3.0 and a D-min of 0.1.

Example 45

Use of a Quinone Photoreductant as a Destabilizer Material

75 mg of $[\text{Co}(\text{NH}_3)_6] (\text{CF}_3\text{-CO}_2)_3$ and 60 mg of 2-(N-ethyl-N-benzylamino)-3-chloro-1,4-naphthoquinone, a photoreductant, were dissolved in 1.7 g of 2-methoxyethanol. To this solution, 3.4 g of a 15 percent solution of cellulose acetate butyrate in acetone was added to form a stock solution.

A quantity of 40 mg of iodoform was dissolved in 1 g of chloroform. To this solution, a quantity of 2 g of the above stock solution was added. The resulting solution was coated with a 100-micron doctor blade on a subbed poly(ethylene terephthalate) support.

A sample of this film was exposed for 2 minutes through a silver test object on a U.V. exposing device, available commercially as a Canon Kalfite Printer 340VC. This exposure imagewise generated inhibitor. The film was then given an overall 30-second exposure to tungsten light using a Nashua 120 Multi-Spectrum Copier to photogenerate reductant. The exposed film was placed in face-to-face contact with a diazo recording element (commercially available under the trade name Kodak Diazo Type M) and the sandwich was passed twice at 76.2 cm per minute through a set of rollers heated to a temperature of 100°C. A positive image was developed with a maximum density of 1.0 and a minimum density of 0.07 measured in red light. (The heating step was used to increase the dye-development reaction).

Examples 46—47

Using a Quinone Photoreductant to be Either Positive- or Negative-Working

In 1 g of dioxane were dissolved 120 mg of iodoform (photoinhibitor) and 25 mg of the destabilizer 2-dibenzylamino-3-chloro-1,4-naphthoquinone. To this solution was added a second solution consisting of 120 mg of $[\text{Co}(\text{NH}_3)_6] (\text{CF}_3\text{-CO}_2)_3$ and 166 mg *o*-phthalaldehyde (image-former) in a 20% solution of the binder poly(ethylene-co-1,4-cyclohexylenedimethylene-1-methyl-2,4-benzenedisulfonamide) in 95:5 by volume acetone:H₂O. This solution was coated with a 100-micron doctor blade on subbed poly(ethylene terephthalate) support and overcoated with a 10% solution of (copolyester 1,1,3-trimethyl-5-carboxy-3-(p-carboxyphenyl)indan bisphenol A) in toluene.

A dried coating was exposed to visible light for 0.5 seconds on an IBM Microcopier IID device through a silver negative and a Wratten 2A filter which removes ultraviolet radiation. Upon heating for 15 seconds face-up on a 140°C hot block, a dense black negative image was formed.

Example 47 comprised a repetition of Example 46, except that the element was exposed for 6 seconds on an IBM Microcopier IID through a silver negative and a Wratten 34 filter which passes ultraviolet radiation, followed by a 0.5 seconds dye-development exposure through a Wratten 2A filter. Fifteen seconds of heating face-up on a 140°C hot block developed a dense positive image.

Claims

1. The method of forming an image comprising first exposing, to radiation which activates a photoinhibitor compound or mixture of compounds, as hereinafter described, an imaging element containing, in one or more adjacent layers, (a) an energy-activatable image precursor composition comprising at least one cobalt III complex having releasable ligands; (b) an image-forming material which generates an image in response to the release of the ligands, said energy-activatable image precursor being a composition activatable by electromagnetic energy of any kind in areas where it is not inhibited by an already exposed photoinhibitor, as hereinafter described, and said composition when activated by exposure to electromagnetic energy providing an image either by generating a density or by destroying or changing a pre-existing density; and (c) as a photoinhibitor, a single compound or a mixture of compounds which does not form a complex with cobalt and which responds to activating radiation having a wavelength greater than 300 nm and which inhibits the release of ligands from the cobalt III complex or inhibits the effect of released ligands on the image-forming material upon exposure to activating radiation of a different wavelength to that activating the image precursor composition, and thereafter exposing the imaging element to radiation of a wavelength which activates the energy activatable image precursor.

2. The method according to Claim 1 wherein the layer of the image-forming material is adjacent to the layer of the energy-activatable image precursor composition on a single support.


3. The method according to Claim 2 wherein the imaging precursor composition is activated by uniform heating.

4. An imaging element containing, in one or more adjacent layers, (a) an energy-activatable image precursor composition comprising at least one cobalt III complex having releasable ligands; (b) an image-forming material which generates an image in response to the release of the ligands, said

energy-activatable image precursor being a composition activatable by electromagnetic energy of any kind in areas where it is not inhibited by an already exposed photoinhibitor, as hereinafter described, and said composition when activated by exposure to electromagnetic energy providing an image either by generating a density or by destroying or changing a pre-existing density; and (c) as a photoinhibitor, a single compound or a mixture of compounds which does not form a complex with cobalt and which responds to activating radiation having a wavelength greater than 300 nm and which inhibits the release of ligands from the cobalt III complex or inhibits the effect of released ligands on the image-forming material upon exposure to activating radiation of a different wavelength to that activating the image precursor composition.

5. An imaging element as claimed in Claim 4, in which the photoinhibitor is a heterocyclic compound having at least one trihalomethyl substituent group.

6. An imaging element as claimed in Claim 5, in which the photoinhibitor is a heterocyclic compound having the formula:



25 in which,

E represents a hydrogen atom, a methyl or trihalomethyl group;

R²¹ represents a hydrogen atom or an alkoxy group having up to 5 carbon atoms;

R²² represents a hydrogen atom, a halogen atom, a nitro group or an alkyl, dialkylamino or alkoxy group having up to 5 carbon atoms in the alkyl portion;

30 R²³ represents a hydrogen atom or an alkoxy group having up to 5 carbon atoms, or together with R²⁴, the non-metallic atoms necessary to complete an aromatic ring;

R²⁴ represents a hydrogen atom, or together with R²³, the non-metallic atoms necessary to complete an aromatic ring;


35 Z⁷ represents the non-metallic atoms necessary to complete one or more heterocyclic rings containing from 6 to 10 atoms;

m'' is 0, 1 or 2; and

X'' represents a halogen atom.

7. An imaging element as claimed in Claim 5, in which the photoinhibitor is 2,4-bis(trichloromethyl)-6-(p-anisyl)-s-triazine; 2,4-bis(trichloromethyl) 6-(4-methoxystyryl)-s-triazine; 2,4-bis(trichloromethyl)-6-[4-(4-dimethylaminophenyl)-1,3-butadienyl]-s-triazine; 2-tribromomethylquinoline, 2-tribromomethylquinoxaline; 2-tribromomethyl-4-oxo-4H-1-benzopyran; 2,4-bis(trichloromethyl)-6-(1-naphthyl)-s-triazine; 2,4-bis(trichloromethyl)-6-(4-methoxy-1-naphthyl)-s-triazine; tribromomethylbenzene; or 2,3-bis(tribromomethyl)quinoxaline.

8. An imaging element as claimed in Claim 4, in which the photoinhibitor has the formula:



55 in which,

R²⁵ represents an alkyl group having up to 3 carbon atoms, an aralkyl group having 7 or 8 carbon atoms, or when taken together with R²⁶, the atoms necessary to complete a fused heterocyclic ring,

R²⁶ represents a halogen atom, or when taken together with R²⁵, the atoms necessary to complete a fused heterocyclic ring;


60 R²⁷ represents a hydrogen atom or an alkoxy group having up to 3 carbon atoms; and

X''' represents a halogen atom.

9. An imaging element as claimed in Claim 8, in which the photoinhibitor is N-methyl-o-nitrotrifluoroacetanilide; N-benzyl-o-nitrotrifluoroacetanilide; N-benzyl-2-nitro-5-methoxy-trifluoroacetanilide; or 6-bromo-8-nitro-N-trifluoroacetylbenzo [b] piperidine.


65

10. An imaging element as claimed in Claim 4, in which the photoinhibitor has the formula:



in which,

- 10 R¹⁷ represents a hydrogen atom, a phenyl group or an alkyl group having up to 4 carbon atoms;
 R¹⁸ represents an alkyl group having up to 4 carbon atoms, or an adamantyl group;
 R¹⁹ represents a hydrogen or a halogen atom;
 Z⁶ represents a



group, and;

- R²⁰ represents a hydrogen atom or an alkyl group having up to 5 carbon atoms; and
 X' represents an anion.

20 11. An imaging element according to Claim 4, in which said photoinhibitor is N-methyl-3-diazo-4-quinolinium-p-toluenesulphonate; N-methyl-3-phenyl-2,1-benzisoxazolium perchlorate or N-methyl-3-phenyl-2,1-benzisoxazolium fluoroborate.

25 12. An imaging element as claimed in Claim 4 in which the photoinhibitor is one of the halogenated organic compounds iodoform, carbon tetrabromide, β -tribromoethanol, hexabromoethane, ethyl tribromoacetate, tribromoacetamide, tribromomethyl benzene, pentabromoethane, α,α,α -tribromoacetophenone or 3-nitro- α,α,α -tribromoacetophenone.

30 13. An imaging element as claimed in any of the preceding claims, in which the cobalt III complex is unstable and the complex decomposes at a temperature greater than 100°C sufficiently to release enough ligands to start the reaction of the image precursor composition.

35 14. An imaging element as claimed in any of the Claims 4 to 12 in which the cobalt III complex is thermally stable up to a temperature of at least 130°C and there is present in the image precursor composition a destabilizer compound which renders the otherwise thermally stable cobalt III complex susceptible to release of the ligands when appropriately exposed but which does not interfere with the cobalt III complex.

40 15. An imaging element as claimed in any of the preceding claims, in which the image precursor composition contains an amplifier which is a reducing agent precursor composition or compound which interacts with the image precursor composition to generate additional initiators of the imaging reaction, whereby an internal gain, usually expressed as an enhanced density, is achieved compared to that which results without the amplifier.

16. An imaging element as claimed in Claim 15, in which the amplifier is o-phthalaldehyde.

Revendications

45 1. Procédé de formation d'image consistant

— à réaliser une première exposition à un rayonnement qui active un composé photoinitiateur ou un mélange de tels composés, comme décrit ultérieurement, d'un produit formateur d'image contenant, dans une ou plusieurs couches adjacentes, (a) une composition constituant un précurseur d'image, activable par une énergie, comprenant au moins un complexe de cobalt III ayant des ligands libérables,
 50 (b) une substance formatrice d'image qui crée une image en réponse à la libération des ligands, ce précurseur d'image activable par une énergie étant une composition activable par toute énergie électromagnétique dans les plages où elle n'est pas inhibée par un photoinitiateur déjà exposé, comme décrit ultérieurement, cette composition, lorsqu'elle est activée par une exposition à une énergie électromagnétique, fournissant une image par formation d'une densité ou bien par destruction ou
 55 modification d'une densité préexistante et (c) comme photoinitiateur, un composé unique ou un mélange de composés qui ne forme pas un complexe avec le cobalt et qui est sensible à un rayonnement activateur ayant une longueur d'onde supérieure à 300 nm et qui inhibe la libération des ligands du complexe de cobalt III ou qui inhibe l'action des ligands libérés sur la substance formatrice d'image lors d'une exposition à un rayonnement activateur d'une longueur d'onde différente de celle qui active la
 60 composition précurseur d'image,

et ensuite à exposer le produit formateur d'image à un rayonnement d'une longueur d'onde qui active le précurseur d'image activable par une énergie.


2. Procédé conforme à la revendication 1, dans lequel la couche de la substance formatrice d'image est adjacente à la couche de la composition constituant le précurseur d'image activable par
 65 une énergie sur un seul support.

3. Procédé conforme à la revendication 2, dans lequel la composition constituant le précurseur d'image est activée par un chauffage uniforme.

4. Produit formateur d'image contenant, dans une ou plusieurs couches adjacentes, (a) une composition constituant un précurseur d'image, activable par une énergie, comprenant au moins un complexe de cobalt III ayant des ligands libérables, (b) une substance formatrice d'image qui crée une image en réponse à la libération des ligands, ce précurseur d'image activable par une énergie étant une composition activable par toute énergie électromagnétique dans les plages où elle n'est pas inhibée par un photoinitiateur déjà exposé, comme décrit ultérieurement, et cette composition, lorsqu'elle est activée par une exposition à une énergie électromagnétique, fournissant une image par formation d'une densité ou bien par destruction ou modification d'une densité préexistante, et (c) comme photoinitiateur, un composé unique ou un mélange de composés qui ne forme pas une complexe avec le cobalt et qui est sensible à un rayonnement activateur ayant une longueur d'onde supérieure à 300 nm et qui inhibe la libération des ligands du complexe de cobalt III ou qui inhibe l'action des ligands libérés sur la substance formatrice d'image lors d'une exposition à un rayonnement activateur d'une longueur d'onde différente de celle qui active la composition formant précurseur d'image.

5. Produit formateur d'image conforme à la revendication 4, dans lequel le photoinhibiteur est un composé hétérocyclique ayant au moins un groupe substituant trihalogénométhyle.

6. Produit formateur d'image conforme à la revendication 5, dans lequel le photoinhibiteur est un composé hétérocyclique de formule:



où E représente un atome d'hydrogène, un groupe méthyle ou trihalogénométhyle,

R²¹ représente un atome d'hydrogène ou un groupe alkoxy ayant jusqu'à 5 atomes de carbone,

R²² représente un atome d'hydrogène, un atome d'halogène, un groupe nitro ou bien un groupe alkyle, dialkylamino ou alkoxy dans lequel le radical alkyle a jusqu'à 5 atomes de carbone,

R²³ représente un atome d'hydrogène ou un groupe alkoxy ayant au plus 5 atomes de carbone ou bien, associé à R²⁴, R²³ représente les atomes non métalliques nécessaires pour compléter un noyau aromatique,

R²⁴ représente un atome d'hydrogène ou bien associé à R²³, R²⁴ représente les atomes non métalliques nécessaires pour compléter un noyau aromatique,


Z⁷ représente les atomes non métalliques nécessaires pour compléter un ou plusieurs hétérocycles contenant de 6 à 10 atomes,

m'' est égal à 0, 1 ou 2,

X'' représente un atome d'halogène.

7. Produit formateur d'image conforme à la revendication 5, dans lequel le photoinhibiteur est la 2,4-bis (trichlorométhyl)-6-(p-anisyl)-s-triazine, la 2,4-bis (trichlorométhyl)-6-(4-méthoxystyryl)-s-triazine, la 2,4-bis(trichlorométhyl)-6-[4-(4-diméthylaminophényl)-1,3-butadiényl]-s-triazine, la 2-tribromométhylquinoléine, la 2-tribromométhylquinoxaline, le 2-tribromométhyl-4-oxo-4H-1-benzopyrane, la 2,4-bis(trichlorométhyl)-6-(1-naphtyl)-s-triazine, la 2,4-bis(trichlorométhyl)-6-(4-méthoxy-1-naphtyl)-s-triazine, le tribromométhylbenzène ou la 2,3-bis(tribromométhyl)quinoxaline.

8. Produit formateur d'image conforme à la revendication 4, dans lequel le photoinhibiteur a la formule:



où R²⁵ représente un groupe alkyle ayant au plus 3 atomes de carbone, un groupe aralkyle ayant 7 ou 8 atomes de carbone, ou bien, associé à R²⁶, R²⁵ représente les atomes nécessaires pour compléter un hétérocycle condensé,


0 003 263

R²⁶ représente un atome d'halogène ou bien, associé à R²⁵, R²⁶ représente les atomes nécessaires pour compléter un hétérocycle condensé,

R²⁷ représente un atome d'hydrogène ou un groupe alkoxy ayant au plus 3 atomes de carbone, X''' représente un atome d'halogène,

9. Produit formateur d'image conforme à la revendication 8, dans lequel le photoinhibiteur est le N-méthyl-o-nitrotrifluoroacétanilide, le N-benzyl-o-nitrotrifluoroacétanilide, le N-benzyl-2-nitro-5-méthoxytrifluoro-acétanilide ou la 6-bromo-8-nitro-N-trifluoroacétylbenzo [b] pipéridine.

10. Produit formateur d'image conforme à la revendication 4, dans lequel le photoinhibiteur a la formule:




où R¹⁷ représente un atome d'hydrogène, un groupe phényle ou un groupe alkyle ayant au plus 4 atomes de carbone,

R¹⁸ représente un groupe alkyle ayant au plus 4 atomes de carbone ou bien un groupe adamantyle,

R¹⁹ représente un atome d'hydrogène ou d'halogène,

Z⁶ représente



R²⁰ représente un atome d'hydrogène ou un groupe alkyle, ayant au plus 5 atomes de carbone, X' représente un anion.

11. Produit formateur d'image conforme à la revendication 4, dans lequel le photoinhibiteur est le p-toluènesulphonate de N-méthyl-3-diazo-4-quinolinium, le perchlorate de N-méthyl-3-phényl-2,1-benzisoxazolium ou le fluoroborate de N-méthyl-3-phényl-2,1-benzisoxazolium.

12. Produit formateur d'image conforme à la revendication 4, dans lequel le photoinhibiteur est un des composés organiques halogénés iodoforme, tétrabromure de carbone, β-tribromoéthanol, hexabromoéthane, tribromoacétate d'éthyle, tribromoacétamide, tribromométhyl benzène, pentabromoéthane, α,α,α-tribromoacétophénone ou 3-nitro-α,α,α-tribromoacétophénone.

13. Produit formateur d'image conforme à l'une quelconque des revendications précédentes dans lequel le complexe de cobalt III est instable et se décompose à une température supérieure à 100°C en quantité suffisante pour libérer assez de ligands pour amorcer la réaction de la composition constituant un précurseur d'image.

14. Produit formateur d'image conforme à l'une quelconque des revendications 4 à 12 dans lequel le complexe de cobalt III est thermiquement stable jusqu'à une température d'au moins 130°C et dans lequel la composition constituant un précurseur d'image contient un composé destabilisant qui rend le complexe de cobalt III, autrement stable thermiquement, susceptible de libérer des ligands quand il est exposé d'une manière appropriée, mais qui n'interfère pas avec le complexe de cobalt III.

15. Produit formateur d'image, conforme à l'une quelconque des revendications précédentes, dans lequel la composition constituant un précurseur d'image contient un amplificateur qui est une composition ou un composé précurseur d'agent réducteur qui réagit avec la composition constituant un précurseur d'image pour créer des initiateurs supplémentaires de la réaction de formation d'image, ce que fournit un gain interne, habituellement exprimé sous forme d'une densité accrue, comparé à celui obtenu sans amplificateur.

16. Produit formateur d'image conforme à la revendication 15, dans lequel l'amplificateur est l'ophtalaldéhyde.

Patentansprüche

1. Verfahren zur Herstellung eines Bildes, bei dem ein Bildaufzeichnungsmaterial zunächst einer Strahlung exponiert wird, die eine Photoinhibitorverbindung oder Mischung von Verbindungen, wie im folgenden beschrieben, aktiviert und das Bildaufzeichnungsmaterial in einer oder mehreren einander benachbarten Schichten enthält: (a) eine durch Energie aktivierbare Bildvorläuferzusammensetzung mit mindestens einem Kobalt(III)komplex mit freisetzbaren Liganden; (b) ein bilderzeugendes Material, das als Folge der Freisetzung der Liganden ein Bild erzeugt, wobei der durch Energie aktivierte Vorläufer eine Zusammensetzung ist, die in Bezirken, in denen sie durch einen bereits exponierten Photoinhibitor, wie im folgenden beschrieben, nicht inhibiert ist, durch elektromagnetische Energie jeder Art aktivierbar ist und wobei die Zusammensetzung, wenn sie durch Exponierung mit elektromagnetischer Energie aktiviert wird, entweder durch Erzeugung einer Dichte oder durch Zerstörung oder Veränderung

einer zunächst vorhandenen Dichte ein Bild erzeugt, und (c) als einen Photoinhibitor eine einzelne Verbindung oder eine Mischung von Verbindungen, die mit Kobalt keinen Komplex bilden, und die auf aktivierende Strahlung einer Wellenlänge von größer als 300 nm ansprechen und die das Freisetzen von Liganden aus dem Kobalt(III)komplex inhibieren oder die den Effekt von freigesetzten Liganden auf das bildnerzeugende Material bei Exponierung mit aktivierender Strahlung einer Wellenlänge, die verschieden ist von der Wellenlänge, die die Bildvorläuferzusammensetzung aktiviert, inhibieren, und bei dem das Bildaufzeichnungsmaterial danach einer Strahlung einer Wellenlänge exponiert wird, die den durch Energie aktivierbaren Bildvorläufer aktiviert.


2. Verfahren nach Anspruch 1, bei dem sich die Schicht des bildnerzeugenden Materials auf einem Träger benachbart zur Schicht der durch Energie aktivierbaren Bildvorläuferzusammensetzung befindet.

3. Verfahren nach Anspruch 2, bei dem die Bildvorläuferzusammensetzung durch gleichförmiges Erhitzen aktiviert wird.

4. Bildaufzeichnungsmaterial, das in einer oder mehreren einander benachbarten Schichten enthält: (a) eine durch Energie aktivierbare Bildvorläuferzusammensetzung mit mindestens einem Kobalt(III)komplex mit freisetzbaren Liganden; (b) ein bildnerzeugendes Material, das als Folge der Freisetzung der Liganden ein Bild erzeugt, wobei der durch Energie aktivierbare Bildvorläufer eine Zusammensetzung ist, die in Bezirken, in denen sie durch einen bereits exponierten Photoinhibitor, wie im folgenden beschrieben, nicht inhibiert ist, durch elektromagnetische Energie jeder Art aktivierbar ist und wobei die Zusammensetzung, wenn die durch Exponierung mit elektromagnetischer Energie aktiviert wird, entweder durch Erzeugung einer Dichte oder durch Zerstörung oder Veränderung einer zunächst vorhandenen Dichte ein Bild erzeugt, und (c) als einen Photoinhibitor eine einzelne Verbindung oder eine Mischung von Verbindungen, die mit Kobalt keinen Komplex bilden und die auf aktivierende Strahlung einer Wellenlänge von größer als 300 nm ansprechen und die das Freisetzen von Liganden aus dem Kobalt(III)komplex inhibieren oder die den Effekt von freigesetzten Liganden auf das bildnerzeugende Material bei Exponierung mit aktivierender Strahlung einer Wellenlänge, die verschieden ist von der Wellenlänge, die die Bildvorläuferzusammensetzung aktiviert, inhibieren.

5. Bildaufzeichnungsmaterial nach Anspruch 4, in dem der Photoinhibitor eine heterocyclische Verbindung mit mindestens einem Substituenten aus einer Trihalomethylgruppe ist.

6. Bildaufzeichnungsmaterial nach Anspruch 5, in dem der Photoinhibitor eine heterocyclische Verbindung der folgenden Formel ist:



worin bedeuten:

E ein Wasserstoffatom, eine Methyl- oder eine Trihalomethylgruppe;

R²¹ ein Wasserstoffatom oder eine Alkoxygruppe mit bis zu 5 C-Atomen;

R²² ein Wasserstoffatom, ein Halogenatom, eine Nitrogruppe oder eine Alkyl-, Dialkylamino- oder Alkoxygruppe mit bis zu 5 C-Atomen im Alkylteil;

R²³ ein Wasserstoffatom oder eine Alkoxygruppe mit bis zu 5 C-Atomen oder gemeinsam mit R²⁴ die nichtmetallischen Atome, die zur Vervollständigung eines aromatischen Ringes erforderlich sind;

R²⁴ ein Wasserstoffatom oder gemeinsam mit R²³ die nichtmetallischen Atome, die zur Vervollständigung eines aromatischen Ringes erforderlich sind;

Z⁷ die nichtmetallischen Atome, die zur Vervollständigung von einem oder mehreren heterocyclischen Ringen mit 6 bis 10 Atomen erforderlich sind;


m'' = 0, 1 oder 2; und

X'' ein Halogenatom.

7. Bildaufzeichnungsmaterial nach Anspruch 5, in dem der Photoinhibitor besteht aus: 2,4-Bis(trichlormethyl)-6-(p-anisyl)-2-triazin; 2,4-Bis(trichlormethyl)-6-(4-methoxystyryl)-s-triazin; 2,4-Bis(trichlormethyl)-6-[4-(4-dimethylaminophenyl)-1,3-butadienyl]-s-triazin; 2-Tribrommethylchinolin; 2-Tribrommethylchinoxalin; 2-Tribrommethyl-4-oxo-4H-1-benzopyran; 2,4-Bis(trichlormethyl)-6-(1-naphthyl)-s-triazin; 2,4-Bis(trichlormethyl)-6-(4-methoxy-1-naphthyl)-s-triazin; Tribrommethylbenzol oder 2,3-Bis(tribrommethyl)chinoxalin.

0 003 263

8. Bildaufzeichnungsmaterial gemäß Anspruch 4, in dem der Photoinhibitor der folgenden Formel entspricht:



worin bedeuten:


R²⁵ eine Alkylgruppe mit bis zu 3 C-Atomen, eine Aralkylgruppe mit 7 oder 8 C-Atomen oder gemeinsam mit R²⁶ die Atome, die zur Vervollständigung eines ankondensierten heterocyclischen Ringes erforderlich sind;

15 R²⁶ ein Halogenatom oder gemeinsam mit R²⁵ die Atome, die zur Vervollständigung eines ankondensierten heterocyclischen Ringes erforderlich sind;

R²⁷ ein Wasserstoffatom oder eine Alkoxygruppe mit bis zu 3 C-Atomen und X''' ein Halogenatom.

9. Bildaufzeichnungsmaterial nach Anspruch 8, in dem der Photoinhibitor besteht aus N-Methyl-o-nitrotrifluoroacetanilid; N-Benzyl-o-nitrotrifluoroacetanilid; N-Benzyl-2-nitro-5-methoxytrifluoroacetanilid oder 6-Brom-8-nitro-N-trifluoroacetylbenzo[b]piperidin.

10. Bildaufzeichnungsmaterial nach Anspruch 4, in dem der Photoinhibitor der folgenden Formel entspricht:




worin bedeuten:

R¹⁷ ein Wasserstoffatom, eine Phenylgruppe oder eine Alkylgruppe mit bis zu 4 C-Atomen;

R¹⁸ eine Alkylgruppe mit bis zu 4 C-Atomen oder eine Adamantylgruppe;

R¹⁹ ein Wasserstoff- oder Halogenatom;

Z⁶ eine Gruppe einer der Formeln:



und

40 R²⁰ ein Wasserstoffatom oder eine Alkylgruppe mit bis zu 5 C-Atomen und X' ein Anion.

11. Bildaufzeichnungsmaterial nach Anspruch 4, in dem der Photoinhibitor besteht aus: N-Methyl-3-diazo-4-chinolinium-p-toluolsulphonat; N-Methyl-3-phenyl-2,1-benzisoxazoliumperchlorat oder N-methyl-3-phenyl-2,1-benzisoxazoliumfluoroborat.

45 12. Bildaufzeichnungsmaterial nach Anspruch 4, in dem der Photoinhibitor aus einer halogenierten organischen Verbindung bestehend aus Jodoform, Tetrachlorkohlenstoff, β-Tribrommethanol, Hexabrommethan, Ethyltribromacetat, Tribromacetamid, Tribrommethylbenzol, Pentabrommethan, α,α,α-Tribromacetophenon oder 3-Nitro-α,α,α-Tribromacetophenon besteht.

13. Bildaufzeichnungsmaterial nach einem der vorstehenden Ansprüche, in dem der Kobalt(III)-komplex instabil ist und sich der Komplex bei einer Temperatur von größer als 100°C ausreichend zersetzt, um genug Liganden freizusetzen, die die Reaktion der Bildvorläuferzusammensetzung in Gang setzen.

14. Bildaufzeichnungsmaterial nach einem der Ansprüche 4 bis 12, in dem der Kobalt(III)komplex bis zu einer Temperatur von mindestens 130°C stabil ist und in dem in der Bildvorläuferzusammensetzung eine Destabilisatorverbindung vorhanden ist, die bewirkt, daß der ansonsten thermisch stabile Kobalt(III)komplex Liganden freisetzt, wenn eine angemessene Exponierung erfolgt und die den Kobalt(III)komplex nicht stört.

15. Bildaufzeichnungsmaterial nach einem der vorstehenden Ansprüche, in dem die Bildvorläuferzusammensetzung einen Verstärker enthält, der aus einer Reduktionsmittelvorläuferzusammensetzung oder einer Verbindung, die mit der Bildvorläuferzusammensetzung unter Erzeugung zusätzlicher Initiatorer der bilderzeugenden Reaktion reagiert, besteht, wodurch ein innerer Vorteil erreicht wird, der sich normalerweise, im Vergleich zu einem Material ohne Verstärker, durch eine erhöhte Dichte ausdrückt.

65 16. Bildaufzeichnungsmaterial nach Anspruch 15, in dem der Verstärker aus o-Phthalaldehyd besteht.

FIG. 1a




FIG. 1b





FIG. 1c



0003 263

FIG. 2a




FIG. 2b





FIG. 3