

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 039 503
A1

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **81103356.2**(51) Int. Cl.³: **C 22 C 1/02**(22) Date of filing: **04.05.81**(30) Priority: **05.05.80 US 146833**(71) Applicant: **Olin Corporation, 427 North Shamrock Street, East Alton Illinois 62024 (US)**(43) Date of publication of application: **11.11.81 Bulletin 81/45**


(72) Inventor: **Parikh, Prakash D., 42 Fansrock Road, Hamden Connecticut (US)**
 Inventor: **Stone, Louis P., 590 Field Street, Naugatuck Connecticut (US)**
 Inventor: **Shapiro, Eugene, 926 Ridge Road, Hamden Connecticut (US)**
 Inventor: **Tyler, Derek E., 399 Jinny Hill Road, Cheshire Connecticut (US)**

(84) Designated Contracting States: **DE FR GB IT SE**

(74) Representative: **Patentanwälte Dr. Elisabeth Jung Dr. Jürgen Schirdewahn, Dr. Gerhard Schmitt-Nilson Dr. Gerhard B. Hagen Dipl.-Ing. Peter Hirsch Clemensstrasse 30, D-8000 München 40 (DE)**

(54) **Method of processing copper base alloys and cast copper base alloys produced in accordance with this method.**

(57) The disclosure teaches improved cast copper alloys exhibiting surprisingly good hot rollability. A method is taught of processing copper base alloys to provide cast structures having good hot rollability, especially those containing silicon and tin. In accordance with the method of the invention, ingots are direct chill cast in a mold from liquid metal wherein the melt temperature entering the mold is 100 to 350°C in excess of the liquidus temperature.



EP 0 039 503 A1

ELISABETH JUNG DR. PHIL., DIPL.-CHEM.
JÜRGEN SCHIRDEWAHN DR. RER. NAT., DIPL.-PHYS.
GERHARD SCHMITT-NILSON DR.-ING.
GERHARD B. HAGEN DR. PHIL.
PETER HIRSCH DIPL.-ING.

PATENTANWÄLTE
PROFESSIONAL REPRESENTATIVES BEFORE THE EUROPEAN PATENT OFFICE

8000 MÜNCHEN 40, May 4, 1981
P. O. BOX 40 14 68
CLEMENSSTRASSE 30
TELEFON: (089) 34 50 67
TELEGRAMM/CABLE: INVENT MÜNCHEN
TELEX: 5-29 686

0039503

OLIN CORPORATION, East Alton, Illinois, U.S.A.

Method of processing copper base alloys and cast copper base alloys produced in accordance with this method.

BACKGROUND OF THE INVENTION

The present invention deals with the provision of cast structures having good hot rollability.

The commercial production of wrought copper base alloys is naturally seriously affected by edge cracking of the alloys during hot rolling or hot working. Silicon-tin bronzes in particular have been found to be susceptible to this edge cracking phenomenon. This is naturally a serious problem commercially. Ternary copper base alloys which contain silicon and tin are even more susceptible to the edge cracking phenomenon, but these ternary alloys are nonetheless desirable for commercial production because they provide a good combination of stress corrosion resistance, high strength and formability.

Various means have been suggested in the art in order to counteract the edge cracking problem, especially in silicon and tin containing copper base alloys. Such means have included both different combinations of elemental additions and ways to vary the hot working process. For example, copper base alloys containing silicon and tin together with mischmetal are taught in U.S. Patent 4,148,633. While this patent does provide improvement in the edge cracking phenomenon, it is naturally desirable to provide even greater improvement and to provide such improvement without the necessity for adding alloying additions. Of further interest is "A Preliminary Assessment of the Value of Minor Alloy Additions in Counteracting the Harmful Effect of Impurities on the Hot Workability of Some Copper Alloys" by R.J. Jackson et al. in the Journal of the Institute of Metals, Volume 98 (1970), Pages 193-198. This article discusses

copper alloys which contain impurities such as lead and bismuth. These metals may have their tendencies to crack during hot working reduced by the addition of such materials as thorium, uranium and mischmetal. Other patents of interest include U.S. 1,881,257, U.S. 1,956,251, German 756,035, U.S. 2,257,437, U.S. 2,062,448 and U.S. 3,923,555.

It is, therefore, a principal object of the present invention to provide a method of processing silicon-tin bronzes to provide cast structures having good hot rollability.

10 It is a still further object of the present invention to provide such a method which yields a copper base alloy which is resistant to edge cracking during hot working.

It is a further object of the present invention to provide a method as aforesaid which does not rely on expensive processing variations or alloying additions.

It is a still further object of the present invention to provide improved cast copper alloys which are resistant to edge cracking during hot rolling.

20 Further objects and advantages of the present invention will appear from a consideration of the following specification.

SUMMARY OF THE INVENTION

The foregoing objects and advantages are readily accomplished in accordance with the method of the present invention. The method of the present invention is a method for processing copper base alloys especially those containing silicon and tin to provide cast structures having good hot workability. Hot rolling is the preferred processing practice, however, any hot working step is contemplated in accordance with the process of the present invention, such as drawing or
30 extrusion. Throughout the present specification, however,

0039503

hot rolling will be discussed as the preferred hot working step.

In accordance with the method of the present invention ingots are direct chill cast, preferably of silicon-tin bronzes, in a mold from liquid metal wherein the melt temperature entering the mold is 100 to 350°C in excess of the liquidus temperature. This simple, convenient and expeditious practice provides a copper base alloy which is resistant to edge cracking during hot rolling.

10 The present invention also provides improved cast structures which exhibit surprisingly good hot rollability. The cast copper base alloys comprise a first external inversely segregated surface zone, a second bulk ingot zone and a subsurface denuded zone bridging said first and second zones exhibiting a uniform coarse grain structure which is devoid of second phases. Although the improved cast structures are preferably present in silicon-tin bronzes as aforesaid, it is a finding of the present invention that the present process preferentially provides said structures with resultant
20 improved hot rollability in copper alloys generally, as, for example, in aluminum bronzes, tin bronzes and tin brasses. In view of the remarkable improvement effected by the present invention with regard to the particularly troublesome silicon-tin bronzes, the present invention will be discussed hereinbelow with regard to this alloy system.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a photograph of a DC cast silicon-tin bronze showing the subsurface region thereof produced using conventional processing with the photograph taken at a
30 magnification of 12X;

0039503

Figure 2 is a photograph of a heavily cracked plate produced from the casting of Figure 1 by hot rolling said casting, with the photograph at a magnification of 0.6X;

Figure 3 is a photograph of a DC cast silicon-tin bronze of substantially the same composition as in Figure 1 produced in accordance with the present invention showing the subsurface region thereof with the photograph at a magnification of 12X; and

10 Figure 4 is a photograph of a crack-free plate produced by hot rolling the casting of Figure 3, with the photograph taken at a magnification of 0.6X.

DETAILED DESCRIPTION

In preparing castings for molten metal, it is necessary to superheat the liquid metal in order to provide sufficient fluidity to fill the mold. In accordance with conventional practice, an excess superheat is avoided in order to maximize utilization of energy, minimize pickup of harmful gases, minimize the loss of volatile elements and minimize wear on refractory parts.

20 Hence, normal pouring practices for silicon-tin bronzes provide for a 30 to 70°C superheat at the point where the liquid metal enters the casting mold.

In accordance with the process of the present invention, surprisingly improved cast structures are obtained utilizing higher than normal superheats in direct chill casting. The process of the present invention superheats the liquid metal to a temperature of from 100 to 350°C in excess of the liquidus temperature, and preferably 150 to 250°C in excess of the liquidus temperature. Ingots are then cast in a mold
30 from the liquid metal wherein the melt temperature entering

0039503

the mold is in said higher superheated range. It is surprising and unexpected to find that this simple and expeditious practice yields the improvements of the present invention.

10 Ingots cast by the DC or direct chill casting method exhibit characteristic structural features that are inherent in the modes of heat extraction effected by this technique. Thus, a typical DC casting arrangement provides for the transfer of molten metal into a water cooled copper mold via a downspout distributor or similar distribution means. Solidification of the liquid metal is effected by heat transfer through the water cooled mold and by the direct impingement of water onto the ingot as it emerges from the mold. The ingot shell with associated fine grained structure is formed rapidly under high rates of heat extraction when the molten metal and mold are in contact. After reaching some critical thickness the ingot shell shrinks away from the mold wall. Solidification continues but under lower heat transfer conditions. Accordingly, the subsurface region so formed

20 exhibits a coarser structure. Solidification of the major part of the ingot section is achieved by the direct impingement of the sub-mold coolant onto the ingot surface. The resultant structure is fine adjacent to the above subsurface region, and coarsens gradually on approaching the ingot center. Typically, the high growth rate conditions operative during this solidification of the bulk realizes formation of columnar grains.

30 The formation of the subsurface region is of particular relevance to the present invention. In solidifying alloys, solute rich phases are formed in the dendrite arms and at

0039503

grain boundaries. These phases possess lower melting temperatures than the primary dendrites. Accordingly, during formation of the above discussed subsurface region, when the heat extraction process is diminished the temperature of the ingot shell increases and these solute rich phases tend to remelt. As a result, inverse segregation and seams or spikes of these phases form along grain boundaries in these reheated regions. These features can and frequently are detrimental to the hot rolling performance of the resultant cast silicon-tin bronze.

In accordance with the present invention, it has now been found that in preparing direct chill castings, particularly of silicon-tin bronzes, that the structural features in the subsurface region can be controlled by manipulating the superheat as discussed hereinabove. When using conventional practice with superheats of 30 to 70°C, the subsurface regions contain spikes or grain boundary films of low melting point silicon-tin rich phases as clearly shown in Figure 1. The hot rollability of such structures is very poor. Cracking initiated at these grain boundary features propagates extensively into the bulk of the ingot as clearly shown in the heavily cracked plate produced by hot rolling the material of Figure 1, shown clearly in Figure 2.

However, the use of higher superheats in accordance with the practice of the present invention surprisingly and unexpectedly avoids formation of these seams of low melting point phases as clearly shown in Figure 3. In addition, the subsurface region exhibits a uniform coarse grain structure which is devoid of second phase. The associated hot rollability is exceptionally good as shown in Figure 4.

0039503

Cracks which may be initiated in the exterior inversely segregated surface zone are blunted in this subsurface region so that the hot rollability of the resultant ingot is excellent.

Thus, as clearly shown in Figure 3, the cast copper alloys of the present invention are characterized by a first external inversely segregated surface zone, a second internal bulk ingot zone, a subsurface denuded zone bridging said first and second zone exhibiting a uniform coarse grain structure which is devoid of second phases. Thus, in accordance with the present invention there are no distinctive phases that bridge the zone between the outside (inversely segregated region) and the bulk of the casting, i.e., the casting is characterized by the presence of a denuded zone as clearly shown in Figure 3. This should be contrasted to the continuum of second phases which characterize conventional processing as clearly shown in Figure 1. Hence, cracks initiated in the ingot of Figure 3 would be blunted by the denuded zone, but would propagate through the continuum of the ingot of Figure 1. Naturally, the thickness of the zones will depend upon the particular alloy composition and exact processing conditions.

As indicated hereinabove, the process of the present invention preferably deals with silicon and tin containing copper base alloys. The preferred silicon content is from 1 to 6% and the preferred tin content is from 0.2 to 5%. Naturally, if desired for particular properties, alloying additions may readily be added to the silicon-tin bronze, such as mischmetal, chromium, manganese, iron, nickel and the like. Chromium is a particularly preferred addition in an amount of at least 0.03% and preferably in an amount from

0039503

0.03 to 1.0%. Also, conventional impurities may be readily tolerated.

The process of the present invention and improvements obtained thereby may be readily seen from a consideration of the following illustrative example.

EXAMPLE I

DC castings 6" x 30" in cross section were prepared from alloys having the following compositions:

	<u>Alloy A</u>	<u>Alloy B</u>
10	Silicon - 2.97%	2.93%
	Tin - 1.61%	1.71%
	Chromium - 0.29%	0.24%
	Copper - Essentially Balance	Essentially Balance

These alloys exhibit a liquidus temperature of about 1050°C.

An ingot was direct chill cast from Alloy A such that the melt temperature entering the casting mold was 1130°C, that is, superheat conditions of 80°C in excess of liquidus were utilized. The resultant cast structure is shown in Figure 1.

As clearly shown in Figure 1, the subsurface regions contain
20 spikes or grain boundary films of lower melting point tin rich phases. The hot rollability of this casting was poor as clearly shown in Figure 2 wherein the ingot was hot rolled from 840°C at two passes with a 15% reduction in each pass. When hot rolling was attempted, cracking was initiated at the aforesaid grain boundaries and propagated extensively into the bulk of the ingot.

When the aforesaid casting practice was modified to Alloy B in accordance with the process of the present invention with all conditions remaining comparable except that the melt
30 temperature entering the casting mold was increased to 1225°C in accordance with the practice of the present invention, i.e., superheat conditions of 175°C in excess of liquidus, a

preferred coarse subsurface region was obtained free from grain boundary films as clearly shown in Figure 3. The subsurface region was a denuded zone which exhibited a uniform coarse grain structure devoid of second phases. As a result, when the ingot was hot rolled in the same manner as indicated above for Alloy A, the hot rollability of Alloy B was excellent as clearly shown in Figure 4.

The patents set forth in this application are intended to be incorporated by reference herein.

10 This invention may be embodied in other forms or carried out in other ways without departing from the spirit or essential characteristics thereof. The present embodiment is therefore to be considered as in all respects illustrative and not restrictive, the scope of the invention being indicated by the appended claims, and all changes which come within the meaning and range of equivalency are intended to be embraced therein.

20

30

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A method of processing copper base alloys to provide cast structures having good hot workability which is characterized in that it comprises direct chill casting ingots of said alloys in a mold from liquid metal wherein the melt temperature entering the mold is 100 to 350°C in excess of the liquidus temperature, to provide a copper base alloy which is resistant to edge cracking during hot working.
2. A method according to claim 1 characterized in that said alloy is a copper base alloy containing silicon and tin.
3. A method according to claim 1 or 2 characterized in that the liquid metal is superheated to said temperature prior to entering the mold.
4. A method according to any one of claims 1 to 3 characterized in that said resistant cast structure has good hot rollability and including the step of hot rolling said ingot to provide a hot rolled material free from edge cracking.
5. A method according to claim 2 characterized in that said copper base alloy contains from 1 to 6% silicon and from 0.2 to 5% tin.
6. A method according to any one of claims 1 to 5 characterized in that the melt temperature entering the mold is 150 to 250°C in excess of the liquidus temperature.

7. A method according to any one of claims 1 to 6 characterized in that the resulting cast ingot exhibits a subsurface region having a uniform coarse grain structure which is devoid of second phase.
8. A cast copper base alloy characterized in that it is produced in accordance with the method of any one of claims 1 to 7.
9. Cast copper base alloys having good hot workability characterized by comprising a first external inversely segregated surface zone, a second internal bulk ingot zone, and a subsurface denuded zone bridging said first and second zones exhibiting a uniform coarse grain structure which is devoid of second phases.
10. Cast alloys according to claim 9 characterized in that said alloy is a copper base alloy containing silicon and tin.
11. Cast alloys according to claim 10 characterized in that said silicon content is 1 to 6% and said tin content is 0.2 to 5%.




FIG-1



FIG-2




FIG-3




FIG-4



European Patent
Office

EUROPEAN SEARCH REPORT

0039503
Application number
EP 81 10 3356

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. Cl. ³)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
A	<u>US - A - 2 066 512 (ARCHER)</u> * Page 1, right-hand column, lines 26-29 *	1	C 22 C 1/02
	--		
AD	<u>US - A - 4 148 633 (PARIKH)</u> * Claim 1 *	1,4	

			TECHNICAL FIELDS SEARCHED (Int. Cl. ³)
			C 22 F 1/08 C 22 C 9/10 1/02
			CATEGORY OF CITED DOCUMENTS
			X: particularly relevant A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: conflicting application D: document cited in the application L: citation for other reasons
			&: member of the same patent family, corresponding document
The present search report has been drawn up for all claims			
Place of search	Date of completion of the search	Examiner	
The Hague	13-08-1981	LIPPENS	