

(18)



Europäisches Patentamt

European Patent Office

Office européen des brevets

(11) Publication number:

0 053 948
B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **26.09.84**

(51) Int. Cl.³: **C 22 C 19/05**

(21) Application number: **81305828.6**

(22) Date of filing: **10.12.81**

(54) **Nickel-chromium-cobalt base alloys and castings thereof.**

(30) Priority: **10.12.80 GB 8039492**

(43) Date of publication of application:
16.06.82 Bulletin 82/24

(45) Publication of the grant of the patent:
26.09.84 Bulletin 84/39

(84) Designated Contracting States:
AT BE CH DE FR GB IT LI NL SE

(56) References cited:
FR-A-1 071 278
FR-A-2 037 772
FR-A-2 136 231
GB-A- 607 616
GB-A-1 036 179

(73) Proprietor: **Inco Europe Limited**
Thames House Millbank (Fifth Floor)
London SW1P 4QF (GB)

(72) Inventor: **Shaw, Stuart Walter Ker**
17 Kempson Avenue Wyde Green
Sutton Coldfields West Midlands (GB)

(74) Representative: **Greenstreet, Cyril Henry et al**
Thames House (Fifth floor) Millbank
London SW1P 4QF (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

EP 0 053 948 B1

Description

This invention relates to improved castable nickel-chromium-cobalt base alloys and castings of these alloys.

5 Nickel-chromium and nickel-chromium-cobalt base alloys containing titanium and aluminium develop, on suitable heat-treatment, a high level of creep-rupture strength at high temperatures and are widely used in applications giving rise to high stress at elevated temperatures, such as gas turbine engine rotor blades and vanes. However, the need to use impure fuels such as diesel oil in land-based and marine propulsion turbines gives rise to sulphidation attack. Operation in marine and other
10 chloride-containing environments also results in severe corrosion problems.

Many gas turbine and other components, particularly those of complex design, are best produced by prevision casting, and there is thus a need for an alloy that can be cast to shape and possesses, in the cast form, a high level of strength at elevated temperatures in conjunction with good resistance to corrosion in sulphur- and chloride-containing environments and structural stability, i.e. freedom from
15 sigma-phase formation, after extended service at elevated temperatures.

In our UK specification No. 1 367 661 we have described and claimed alloys that exhibit this combination of properties and contain from 0.02 to 0.25% carbon, from 20 to 25% chromium, from 5 to 25% cobalt, one or both of molybdenum (up to 3.5%) and tungsten (up to 5%) in such amounts that the value of %W+0.5 (%Mo) is from 0.5 to 5%, from 1.7 to 5% titanium and from 1 to 4% aluminium,
20 with the provisos that the sum of the aluminium and titanium contents is from 4 to 7% and the ratio of titanium to aluminium is from 0.75:1 to 4:1, from 0.5 to 3% tantalum, from 0 to 3% niobium, from 0.005 to 1.0% zirconium and from 0 to 1.99% hafnium, with the proviso that the value of %Zr+0.5 (%Hf) is from 0.01 to 1%, from 0.001 to 0.05% boron, and from 0 to 0.2% in total of yttrium or lanthanum or both, the balance, apart from impurities, being nickel in an amount of at least 30%. All the
25 percentages and ratios in this composition range, and elsewhere in the present specification and claims, are by weight.

One alloy according to this specification is available commercially under the designation IN-939, with the nominal composition:

30 C 0.5% Cr 22.5%, Co 19%, W 2%, Ti 3.7%,
Al 1.9%, Ta 1.4%, Nb 1.0%, Zr 0.1%,
B 0.01%, Ni balance.

After heat-treatment consisting of solution-heating for 4 hours at 1150°C, air-cooling and then ageing
35 for 16 hours at 850°C, equiaxed castings of Alloy IN-939 (made by vacuum melting followed by remelting and casting under vacuum) typically have a creep-rupture life at 870°C under a stress of 185 N/mm² (19 kgf/mm²) of about 1250 hours, which corresponds to about 850 hours at the same temperature under the high stress of 200 N/mm². When the alloys are directionally-solidified to produce a columnar crystal structure the creep-rupture life, when stressed along the major crystal axis,
40 is increased to about 1170 hours at 870°C and 200 N/mm².

In UK Specification No. 1 367 661 creep-rupture test results are also given for two alloy compositions with and without additions of hafnium. Comparison of the results for the hafnium-containing and hafnium-free alloys shows that the presence of 0.75% hafnium had little or no effect on the creep-rupture life, though it produced some increase in the elongation at rupture.

45 The present invention is based on the discovery that by means of a special correlation of the contents of titanium, aluminium, niobium and hafnium in a range of alloy compositions that also contain nickel, chromium, cobalt, tungsten (with or without molybdenum), tantalum, carbon, boron and zirconium, the creep-rupture life of castings of the alloys, particular in the directionally-solidified form, can be further substantially increased.

50 According to the invention, nickel-chromium-cobalt alloys contain from 20 to 23% chromium, from 17 to 23% cobalt, from 1 to 2.5% tungsten, from 0 to 0.5% molybdenum, from 0.4 to 1.2% niobium, from 0.6 to 1.4% tantalum, from 2.95 to 3.85% titanium, from 1.6 to 2.8% aluminium, from 0.3 to 1.3% hafnium, from 0.005 to 1% zirconium, from 0.001 to 1% boron, and from 0.01 to 0.25% carbon, the balance part from impurities, being nickel, with the proviso that the contents of niobium,
55 hafnium, titanium and aluminium (in wt. % of the alloy) are so correlated that they satisfy the expression:

28327 Nb+804 Hf₂+36956 Ti+115057 Al
-6676 Nb²-564 Hf²-4847 Ti²-54349 Al²
60 +8392 Al³-5255 (Nb×Ti)≥153123.

The value of this expression is referred to herein as the Correlation Factor, and advantageously it is at least 153223.

In general the contents of zirconium, boron and carbon preferably lie within the narrower ranges
65 0.005—0.15% zirconium, 0.002—0.02% boron and 0.05 to 0.20% carbon though smaller amounts of

carbon and boron may be present in single-crystal castings where their contribution to grain-boundary strengthening is not required.

Within the preferred composition range the alloys of the invention, in the directionally-solidified form and after solution-heating and ageing, may exhibit creep-rupture lives in excess of 1600 hours, at 200 N/mm² and 870°C.

The effect of the required correlation with hafnium and aluminium in restricting the contents of titanium and niobium is shown for alloys that contain 0.7% hafnium and 2% aluminium in the accompanying drawing, in which the alloys having compositions corresponding to points in the area defined by the ellipse have a Correlation Factor of at least 153 223.

Apart from the constituents set forth above, impurities, that may be present include small amounts of silicon, manganese and iron, though these should be kept as low as possible. The silicon content should not exceed 1%, and preferably is less than 0.5%, most preferably not more than 0.2%, as it impairs the corrosion resistance. Manganese should be less than 1%, and is preferably not more than 0.2%. The iron content may be as much as 3%, but is preferably not more than 0.5%. Traces of nitrogen and sulphur may also be present, but preferably not more than 0.005% each.

A preferred alloy according to the invention has the normal composition:

Cr 22%, Co 19%, W 2%, Ta 1.1%, Ti 3.4%,
Nb 0.8%, Hf 0.7%, Al 2%, C 0.15%, Zr 0.1%,
B 0.01%, balance Ni and impurities.

The Correlation Factor calculated for this composition is 153 855.

The alloys could be prepared by vacuum melting and then subjected to vacuum refining, e.g. by holding under vacuum for from 15 minutes to 1 hour. In the production of castings by remelting the alloys, the cast stick or other initial form should be remelted and cast under vacuum.

The alloys have good castability and are particularly suitable for the production of cast shaped articles and parts. To obtain the best properties, in particular creep-rupture life, resistance to thermal fatigue, and ductility, the castings are preferably directionally solidified to obtain a columnar crystal structure, but the invention specifically includes shaped castings made from the alloys both with substantially equiaxed and with columnar crystal structures. Such castings include parts of gas turbine engines, for example gas turbine rotor or stator blades, both with and without cooling passages, and integrally bladed turbine rotor discs. Directional solidification may be effected in any manner conventionally employed for high-temperature alloys.

To develop the desired creep-rupture properties, the castings must be subjected to a heat-treatment comprising solution-heating and ageing. The solution-heating preferably consists in heating for from 2 to 24 hours at from 1120 to 1200°C, and is followed by ageing in the temperature range from 1020 to 650°C for from 2 to 24 hours. The ageing may be effected in a single stage, or in two stages, e.g. from 2 to 12 hours at 1020—870°C and then from 6 to 48 hours at 860—650°C. Suitable heat treatments are:

- (i) 4 hours/1160°C+16 hours/843°C (single ageing)
- (ii) 8 hours/1160°C+4 hours/900°C+16 hours/760°C (double ageing).

Between each stage of heat-treatment the alloy may be air-cooled.

The importance of maintaining the alloy composition and Correlation Factor within the range according to the invention is shown by tests performed on a series of alloys having the compositions set forth in Table I below. Of these, Alloys 1 to 3 are in accordance with the invention, while Alloys A to E are not. All the alloys were melted and cast in vacuum and cast using a hot refractory or exothermic mould with a chill base to produce castings having a columnar crystal structure. The castings were heat treated as indicated in Table II, and standard creep-rupture test pieces were machined from them so that the whole of the test piece had a columnar crystal structure extending axially of the test piece.

The test pieces were then subjected to creep-rupture tests under a stress of 200 N/mm² at 870°C, with the results set out in Table II, which also includes the Correlation Factor calculated from the alloy compositions.

The test results show that the creep-rupture lives of Alloys 1 to 3 according to the invention are substantially better than those of Alloys A to E, of which Alloy E is IN-939.

O 053 948

TABLE I
Composition (weight %)

Alloy No.	C	Cr	Co	W	Nb	Ta	Hf	Ti	Al	Zr	B
1	0.14	22.2	19.0	2.0	0.8	1.1	0.7	3.5	2.3	0.09	0.007
2	0.16	22.0	18.9	2.0	0.8	1.1	0.8	3.5	2.0	0.09	0.006
3	0.15	22.3	18.9	2.1	0.9	1.1	0.7	3.5	1.9	0.11	0.009
A	0.16	22.1	18.7	1.8	1.3	1.1	1.0	3.0	2.2	0.11	0.009
B	0.15	21.9	18.8	1.8	0.3	1.2	1.0	3.4	2.1	0.11	0.008
C	0.15	22.1	18.6	1.9	1.3	1.1	0.9	3.3	2.1	0.10	0.010
D	0.15	22.4	18.9	1.9	0.5	1.1	0.6	3.8	2.4	0.10	0.010
E	0.11	22.6	18.6	2.0	1.0	1.4	—	3.7	2.1	0.10	0.020

TABLE II
Creep-rupture properties
at 200 N/mm²/870°C

	Alloy No.	Heat-treatment	Life (h)	Elong. (%)	Correlation factor
25	1	(a)	2414	21.0	153 162
	2	(a)	1807	26.3	153 781
30	3	(b)	2007	21.0	153 759
	A	(a)	1306	30.2	151 967
35	B	(a)	1284	15.8	152 055
	C	(a)	1408	26.6	152 095
	D	(a)	1691	26.3	152 329
40	E	(c)	1164	30.6	—

(a) 8 h/1160°C AC*+4 h, 900°C AC+16 h/760°C AC.

(b) 8 h/1160°C AC+16 h 760°C AC.

(c) 4 h/1160°C AC+16 h 850°C AC.

*AC=air-cooled.

Hot-corrosion tests were carried out on an alloy according to the invention having the composition, in per cent by weight (Alloy 4)

C 0.15, Cr 22.0, Co 19.0, W 2.0, Nb 0.8, Ta 1.1,
Hf 0.7, Ti 3.6, Al 2.0, Zr 0.10, B 0.01, Ni balance

and on a specimen of IN-939 (Alloy E). Cylindrical test pieces machined from heat-treated castings of the alloys were exposed for 500 hours in a rig burning marine diesel fuel, at an air:fuel ratio of 30:1. Ditertiary butyl sulphide was added to raise the sulphur content of the fuel to 3% by weight, and ASTM sea salt was added to the hot gas stream at a concentration in air of 10 ppm. The specimens were heated at 704°C and thermally cycled to room temperature using forced air cooling once every 24 hours. The depth of penetration of the corrosion from the surface of the specimens was then measured, and found to be as follows:

Alloy No.	Average penetration in micrometers
4	2.5, 7.5, 7.5, 5.0 (four specimens)
E	38

Although primarily intended for the production of castings, the alloys may also be useful in the wrought forms. They may be used to produce single crystal castings, for example single-crystal gas turbine blades or vanes. If heat-treated in vacuum, they may be rapidly quenched after each stage of heating by gas fan quenching.

Claims

1. A nickel-chromium-cobalt alloy, characterised in that it contains in percent by weight from 20 to 23% chromium, from 17 to 23% cobalt, from 1 to 2.5% tungsten, from 0 to 0.5% molybdenum, from 0.4 to 1.2% niobium, from 0.6 to 1.4% tantalum, from 2.95 to 3.85% titanium, from 1.6 to 2.8% aluminium, from 0.3 to 1.3% hafnium, from 0.005 to 1% zirconium, from 0.001 to 1% boron, and from 0.01 to 0.25% carbon, the balance, apart from impurities (including Si less than 1%, Mn less than 1% and Fe less than 3%) being nickel, wherein the contents in wt.% of niobium, hafnium, titanium and aluminium are so correlated that they satisfy the expression (the Correlation Factor):

$$28327 \text{ Nb} + 804 \text{ Hf} + 36956 \text{ Ti} + 115057 \text{ Al} \\ - 6676 \text{ Nb}^2 - 564 \text{ Hf}^2 - 4847 \text{ Ti}^2 - 54349 \text{ Al}^2 \\ + 8392 \text{ Al}^3 - 5255 (\text{Nb} \times \text{Ti}) \geq 153123.$$

2. An alloy according to claim 1 in which the carbon content is from 0.05 to 0.20%, the zirconium content is from 0.005 to 0.15% and the boron content is from 0.002 to 0.02%.
3. An alloy according to claim 1 or claim 2 in which the value of the Correlation Factor is at least 153223.
4. An alloy according to claim 1 that contains about 22% chromium, about 19% cobalt, about 2% tungsten, about 1.1% tantalum, about 3.4% titanium, about 0.8% niobium, about 0.7% hafnium, about 2% aluminium, about 0.15% carbon, about 0.1% zirconium, and about 0.01% boron, the balance, apart from impurities, being nickel.
5. A directionally-solidified casting made from an alloy according to any preceding claim.

Patentansprüche

1. Eine Nickel-Chrom-Kobalt-Legierung, die dadurch gekennzeichnet ist, daß sie folgende Gehalte (in Gew.-%) aufweist: 20 bis 23% Chrom, 17 bis 23% Kobalt, 1 bis 2,5% Wolfram, 0 bis 0,5% Molybdän, 0,4 bis 1,2% Niob, 0,6 bis 1,4% Tantal, 2,95 bis 3,85% Titan, 1,6 bis 2,8% Aluminium, 0,3 bis 1,3% Hafnium, 0,005 bis 1% Zirkon, 0,001 bis 1% Bor und 0,01 bis 0,25% Kohlenstoff, der Restgehalt, mit Ausnahme von Verunreinigungen (einschließlich weniger als 1% Si, weniger als 1% Mn und weniger als 3% Fe) ist Nickel, wobei die Gehalte (in Gew.-%) von Niob, Hafnium, Titan und Aluminium so miteinander in Wechselbeziehung stehen, daß sich folgender Ausdruck (Korrelationsfaktor) ergibt:

$$28327 \text{ Nb} + 804 \text{ Hf} + 36956 \text{ Ti} + 115057 \text{ Al} \\ - 6676 \text{ Nb}^2 - 564 \text{ Hf}^2 - 4847 \text{ Ti}^2 - 54349 \text{ Al}^2 \\ + 8392 \text{ Al}^3 - 5255 (\text{Nb} \times \text{Ti}) \geq 153123.$$

2. Eine Legierung gemäß Anspruch 1, deren Kohlenstoffgehalt 0,05 bis 0,20%, Zirkongehalt, 0,005 bis 0,15% und Borgehalt 0,002 bis 0,02% beträgt.
3. Eine Legierung gemäß Anspruch 1 oder 2, bei welcher der Korrelationsfaktor mindestens 153223 beträgt.
4. Eine Legierung gemäß Anspruch 1 mit folgenden Gehalten: Etwa 22% Chrom, etwa 19% Kobalt, etwa 2% Wolfram, etwa 1,1% Tantal, etwa 3,4% Titan, etwa 0,8% Niob, etwa 0,7% Hafnium, etwa 2% Aluminium, etwa 0,15% Kohlenstoff, etwa 0,1% Zirkon und etwa 0,01% Bor; Rest (mit Ausnahme von Verunreinigungen) Nickel.
5. Ein aus einer Legierung gemäß irgendeinem der obigen Ansprüche hergestelltes Gußstück mit gerichteter Erstarrung.

Revendications

1. Alliage nickel-chrome-cobalt, caractérisé en ce qu'il contient en pourcentage pondéral de 20 à 23% de chrome, de 17 à 23% de cobalt, de 1 à 2,5% de tungstène, de 0 à 0,5% de molybdène, de 0,4 à 1,2% de niobium, de 0,6 à 1,4% de tantale, de 2,95 à 3,85% de titane, de 1,6 à 2,8% d'aluminium de 0,3 à 1,3% d'hafnium, de 0,005 à 1% de zirconium, de 0,001 à 1% de bore, et de 0,01 à 0,25% de carbone, le complément, en-dehors des impuretés (y compris Si à moins de 1%, Mn à moins de 1% et Fe à moins de 3%) étant du nickel, où les teneurs en pourcentage pondéral en niobium, hafnium, titane et aluminium sont corrélées de manière telle qu'elles satisfont à l'expression (facteur de corrélation):

O 053 948

28327 Nb+804 Hf+36956 Ti+115057 Al
—6676 Nb²—564 Hf²—4847 Ti²—54349 Al²
+8392 Al²—5255 (Nb×Ti)≥153123.

- 5 2. Alliage selon la revendication 1, où la teneur en carbone est de 0,05 à 0,20%, la teneur en zirconium est de 0,005 à 0,15% et la teneur en bore est de 0,002 à 0,02%.
3. Alliage selon l'une des revendications 1 ou 2, où la valeur du facteur de corrélation est d'au moins 153 223.
- 10 4. Alliage selon la revendication 1 contenant environ 22% de chrome, environ 19% de cobalt, environ 2% de tungstène, environ 1,1% de tantale, environ 3,4% de titane, environ 0,8% de niobium; environ 0,7% d'hafnium, environ 2% d'aluminium, environ 0,15% de carbone, environ 0,1% de zirconium, et environ 0,01% de bore, le complément, en-dehors des impuretés, étant du nickel.
5. Moulage directionnellement solidifié fait à partir d'un alliage selon l'une quelconque des revendications précédentes.

15

20

25

30

35

40

45

50

55

60

65

O 053 948

