

⑩



Europäisches Patentamt
European Patent Office
Office européen des brevets

⑪ Publication number:

**0 093 476
B1**

⑫

EUROPEAN PATENT SPECIFICATION

⑬ Date of publication of patent specification: **04.09.85**

⑭ Int. Cl.⁴: **C 10 G 35/06, C 10 G 45/68**

⑮ Application number: **83200611.8**

⑯ Date of filing: **29.04.83**

⑰ **Conversion of certain hydrocarbons using calcined TEA silicate catalyst.**

⑱ Priority: **30.04.82 US 373729**

⑲ Date of publication of application:
09.11.83 Bulletin 83/45

⑳ Publication of the grant of the patent:
04.09.85 Bulletin 85/36

㉑ Designated Contracting States:
BE DE FR GB IT NL SE

㉒ References cited:
**EP-A-0 023 802
US-A-4 104 294
US-A-4 235 701
US-A-4 341 622**

㉓ Proprietor: **UNION CARBIDE CORPORATION**
Old Ridgebury Road
Danbury Connecticut 06817 (US)

㉔ Inventor: **Garska, Daniel Christopher**
421 Second Street
St. Albans West Virginia (US)
Inventor: **Flanigen, Edith Marie**
502 Woodland Hills Road
White Plains New York (US)

㉕ Representative: **Urbanus, Henricus Maria, Ir.**
et al
c/o Vereenigde Octrooibureaux Nieuwe
Parklaan 107
NL-2587 BP 's-Gravenhage (NL)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

EP 0 093 476 B1

Description

Background of the invention

1. Field of the invention

5 This invention relates to the preparation of streams containing recoverable benzene, toluene, and xylenes ("BTX") from initial by-product effluent streams that contain other components, notably monoolefins and diolefins. In one aspect, the invention concerns the removal by conversion of these other components which ordinarily prevent recovery by distillation or solvent extraction of benzene-toluene-xylenes aromatics from the streams. In another aspect, it concerns a low severity process for treating the
10 by-product streams with a specified catalyst, and under defined reaction conditions, both to produce benzene-toluene-xylenes from the initial stream and to reduce or eliminate those components that otherwise would interfere with the economic recovery of these aromatics from the streams.

2. Description of prior art

15 The preparation of light olefins and diolefins, mainly ethylene, propylene, and butadiene, by the thermal pyrolysis, or cracking, of petroleum fractions is well known and widely practiced. (See for example, Kirk & Othmer's "Encyclopedia of Chemical Technology", Second Edition, Vol. 8, pp. 503—514). In these pyrolytic cracking processes, hydrocarbons ranging from ethane, through LPG (liquefied petroleum gas, chiefly propane with a few percent butanes), naphtha, heavy gas oil, to even crude petroleum oil, are
20 subjected to high temperature conditions, at low pressure and for a short time, to produce a maximum of the desired product. These thermal processes vary widely, and the yields from any one process depend not only on process equipment and conditions, but on such extraneous factors as the presence or absence of diluents and other reactants, e.g., oxygen, hydrogen, steam, etc.

Even the best of the pyrolytic processes is less than ideally selective. As a consequence, the total
25 reactor effluent will contain not only the desired olefin or diolefin, but a variety of other components, ranging from methane gas to high boiling polycyclic hydrocarbons. These by-products are conventionally separated, usually by distillation and/or absorption, so as to concentrate the main desired products for ultimate recovery, and to produce one or more by-product effluent streams.

The by-product effluents contain a mixture of hydrocarbon types, including paraffins, monoolefins,
30 diolefins, aromatics, cyclics, and various substituted and polynuclear aromatics. Unless the by-product effluent stream or streams contains a particularly valuable or desirable component, making removal economical, the by-product effluent streams are of only limited utility. The lighter gases are useful only as fuel, while the heavier, normally liquid, components usually termed "dripolene", if not hydrogenated and then subjected to BTX extraction, are customarily either burned locally as fuel or else hydrogenated to
35 saturate the unstable diolefins, and then blended with other gasoline fractions as motor fuel.

It has long been recognized that some of these byproduct effluent streams, particularly the dripolene fractions, contain potentially valuable benzene, toluene, and xylenes (including ethylbenzene). Unfortunately, they also contain diolefins and monoolefins, which effectively interfere with most existing solvent extraction processes, such as the Udex and Sulfolane processes, for the extraction of aromatics
40 from paraffins. Some of these olefins have boiling points similar to those of the BTX aromatics, and hence cannot be removed by fractional distillation. Selective hydrogenation to saturate the olefins and diolefins is practiced, and widely so, but the process tends to be expensive. Moreover, the diolefins in dripolene tend to be thermally unstable, forming catalyst-deactivating and exchanger-fouling carbonaceous deposits.

A variety of catalysts has been proposed for treating one or more of the by-product effluents from
45 pyrolytic cracking processes so as to render the streams more valuable or more amenable to subsequent processing. (A tabulation of representative references identifying many of these processes, and many catalysts having conceivably useful activity for these processes, is appended). (see Table V, Page 19).

It is an object of the present invention to provide a process for preparing a stream from which benzene-toluene-xylenes may be recovered, by catalytically treating by-product effluent streams from
50 pyrolytic hydrocarbon cracking processes. A further object is to provide a process for treating such by-product effluent stream in a simplified, low severity, operation so as both to produce benzene-toluene-xylenes (BTX), and, simultaneously, to decrease the content of interfering components. Still another object is to remove those monoolefins and diolefins which have heretofore interfered with the solvent extraction of BTX from dripolene and the like.

Summary of the invention

Briefly, in accordance with the invention, a stream from which benzene, toluene, and xylenes may be recovered readily is prepared by contacting a pyrolytic hydrocarbon cracking by-product effluent stream, containing substantial amounts of interfering monoolefins and diolefins, calcined with a TEA-silicate
60 molecular sieve catalyst under low severity hydrocarbon processing conditions. As a result of this treatment, not only are the olefins hydrogenated to non-interfering aliphatics, but a substantial fraction of the aliphatics is dehydrocyclized to benzene-toluene-xylenes.

One of the remarkable aspects of the invention is that the same low severity conditions of temperature, pressure, and space velocity, which are suitable for hydrogenation with a TEA-silicate catalyst, are also
65 suitable for the dehydrogenation reaction involved in aromatization. Thus, a simple processing scheme,

with only a single reactor stage, is often adequate both to reduce to a minimal content, or eliminate the olefinic constituents that would interfere with the economic recovery of aromatics, and to produce benzene-toluene-xylenes from the feed stream.

A further important advantage of the invention resides in its ability to process any of a variety of the byproduct effluent streams from pyrolytic cracking processes. As set out more fully below, these by-product effluent streams customarily include a C₄ fraction composed predominantly of butanes, butenes, and butadiene; a C₅ fraction composed mainly of pentanes, pentenes, pentadienes and cyclic C₅ compounds; a C₆—C₈ "dripolene" fraction containing BTX aromatics together with interfering olefins (i.e., having a similar boiling range); and a C₉-plus fraction, including some BTX along with higher alkylated benzenes and polynuclear aromatics and aliphatics. Each of these streams, plus others that may be present in a particular plant may be processed according to the invention.

The calcined TEA-silicate catalyst for use with the present invention, to be identified more fully below, is described in Grose et al. U.S. 4,104,294. It is believed to be isostructural with zeolite ZSM-12; see Rosinski et al. U.S. 3,832,449. TEA-silicates are crystalline metal organosilicates having identifiable X-ray diffraction characteristics and other properties that have been described in the reference above.

Various other aspects of the invention are set out below.

Description of preferred embodiments

1. Pyrolytic cracking processes

Pyrolytic cracking processes for the preparation of light olefins and diolefins such as ethylene, propylene, and/or butadiene, have been described in the literature, and accordingly no detailed exposition is called for here.

In essence, the thermal pyrolysis, or cracking, of petroleum fractions may utilize as feed stocks hydrocarbons such as ethane, LPG (liquefied petroleum gas, chiefly propane with a few percent butanes), naphtha, heavy gas oil, or crude petroleum oil. These are subjected to controlled high temperature, low pressure, short time, pyrolytic cracking to produce the desired product or products. Thereafter the reactor effluent is subjected to a combination of condensation, fractional distillation, absorption, and perhaps other unit operations, to segregate various effluent streams enriched in one or more desirable components. The precise arrangement of product recovery streams forms no part of the present invention, and indeed it is probable that no two pyrolytic cracking plants utilize the same recovery scheme.

For example, the reactor effluent liquid may be subjected to fractional distillation to separate one or more fractions rich in benzene (B.P. 80.103°C.), toluene (B.P. 110.623°C.), and/or the xylenes, namely ethylbenzene (B.P. 136.187°C.), p-xylene (B.P. 138.348°C.), m-xylene (B.P. 139.102°C.), and o-xylene (B.P. 144.414°C.). This fraction, or fractions is desirably solvent extracted, as for example by the Udex or solfolane process, to recover the BTX aromatic/aromatics.

In the absence of prior treatment, such as by the process of the present invention, solvent extraction is ineffective to extract the aromatics from the remaining aliphatics, inasmuch as solvents selective for aromatics will also extract many olefins and diolefins. However, the diolefins and the aromatics cannot be separated by fractional distillation; for example, benzene, with a boiling point of 80.103°C., is not easily distilled from the 2,4-hexadienes, which boil at about 80.0°C. Similarly, the various dimethylpentenes boil within a range of 72.2°C. to 85.0°C.

Be that as it may, and howsoever produced or constituted, there inevitably will be one or more by-product effluent streams which contain diverse mixtures of hydrocarbon (and perhaps non-hydrocarbon) components, varying both with respect to boiling point and chemical classification. It is this diversity that either complicates or prevents the recovery of useable components.

By way of example, in an illustrative pyrolytic cracking plant, the total reactor effluent may be segregated into a predominantly gaseous fraction including recoverable ethylene and propylene; a crude C₄ fraction, a distillation cut which includes hydrocarbons with primarily four carbon atoms each; a crude C₅ fraction, another distillation cut which primarily contains hydrocarbon molecules with five carbon atoms each, and generally containing a large quantity of unsaturated and cyclic compounds, including olefins and lesser amounts of C₄'s and lighter C₆'s and heavier; a C₆—C₈ fraction, sometimes referred to as pyrolysis gasoline or dripolene; and a C₉ plus fraction, a heavier distillation cut which primarily includes hydrocarbons with at least nine carbon atoms, along with lesser amounts of C₅—C₈ hydrocarbons. The C₉ fraction generally is produced as the distillation bottoms from the processing of dripolene to remove pyrolysis gasoline, and contains components as widely varying as styrene, ethyltoluenes, and trimethylbenzenes, to heavier compounds including ethylnaphthalene, diphenyl, and dimethylnaphthalene.

An illustrative C₄ fraction, giving both the range and a typical composition, is set out in Table I below:

TABLE I
Illustrative C₄'s composition

Compound	Observed range	Typical composition
Lights	0.4—5.0 wt. %	1.1
Methylacetylene, Propadiene	0.1—1.0	0.7
n & i-Butane	2.4—15.0	3.8
1-Butene and Isobutylene	20.0—39.0	33.8
t-2-Butene	4.0—7.0	5.7
c-2-Butene	3.0—5.0	4.5
1,3-Butadiene	41.0—54.0	44.6
Vinylacetylene	0.4—1.5	0.7
Ethylacetylene	0.1—0.5	0.2
C ₅ +	0.2—5.0	4.1

Illustrative C₅ compositions, from two different plants, "A" and "B", are likewise represented in Table II below:

TABLE II
Illustrative C₅'s compositions
Plant A

		Plant B			
		Observed range	Typical composition	Observed range	Typical composition
C ₄ and Lighter	0—1.5 wt. %	0.7	1.4—8.1	5.5	
n & i-Pentanes	0.14.4	7.2	17.3—44.60	23.6	
C ₅ Olefins	0.1—11.3	4.6	6.6—37.4	9.9	
Pentadienes	9.7—35.3	20.0	3.5—12.9	4.2	
Isoprene	2.4—43.0	13.1	5.0—16.8	5.9	
Cyclopentane	1.6—7.5	3.2	0—2.0	—	
Cyclopentene	2.2—10.3	5.4	2.0—14.4	2.3	
Cyclopentadiene	0.60—2.8	1.4	1.0—20.6	4.6	
C ₆ Paraffins	1.1—7.2	4.2	1.3—10.5	10.1	
C ₆ Olefins	—	—	0.3.0	0.2	
Benzene	0.4—5.1	1.3	0—23.8	23.8	
Dicyclopentadiene	19.3—48.1	32.1	1.0—21.0	1.8	
Other C ₆ +	1.5—14.8	6.8	0.9.0	8.1	

Illustrative C₉ compositions, again from Plant "A" and Plant "B", are described in Table III below:

TABLE III
Illustrative C₉'s compositions
Plant A

		Plant A		Plant B	
		Observed range	Typical Composition	Observed range	Typical composition*
5	C ₅ —C ₈				
10	Nonaromatics	0.5—5.4	0.5	0.2—3.4	0.2
	BTX	0—9.8	1.7	0—31.9	1.2
	Styrene	0.3—10.0	1.8	0.16.8	5.0
15	dicyclopentadiene	7.2—40.0	29.2	4.7—42.0	40.5
	Methyl dicyclo- pentadiene and Dimethyldicyclo- pentadiene	4.4—21.2	4.4	0—6.5	1.6
20	Methyl Styrenes	2.3—19.0	6.8	0.15.0	3.6
25	C ₃ Benzenes	8.0—26.0	12.7	0—12.5	7.3
	Indane	0.2—16.9	13.8	0—6.9	0.2
	Indene	3.9—15.6	9.9	1.0—13.0	9.8
30	Naphthalenes	0.6—9.3	3.5	3.0—15.0	14.1
	Other C ₁₀₊	10.7—32.6	15.7	14.6—48.6	16.7

35 It will be appreciated, as noted earlier, that these compositions may vary quite widely, depending upon the initial feed to the pyrolytic cracking unit, the type of pyrolytic cracking unit, conditions, in the pyrolytic unit, and the type and conditions of the product recovery section. The by-product effluent streams may likewise be blended with each other where this is desired, or may include recycle components from elsewhere in the product recovery section.

40 2. Catalyst

The catalyst used in the present process is commonly termed calcined TEA-silicate, a newly discovered crystalline silica polymorph described in Grose et al. U.S. 4,104,294.

45 The class of crystalline metal organosilicates are synthesized from reaction systems essentially free of aluminum-containing reagents and are either entirely free of framework AlO₄-tetrahedra or contain no crystallographically significant amounts thereof. These compositions, as a class, are called TEA-silicates and have the following as-synthesized composition in terms of moles of oxides:




wherein R represents the tetraethylammonium cation, M represents an alkali metal cation, and x has a value of from 0 to 15 depending upon the degree of hydration of the composition. TEA-silicates possess a definite crystal structure whose X-ray powder diffraction pattern shows the following significant lines:

TABLE IV
Interplanar spacing d-(Å) Relative intensity

5	11.9±0.2	S
	10.2±0.2	M
	4.76±0.1	W
10	4.29±0.08	VS
	3.87±0.07	VS
15	3.66±0.07	W
	3.49±0.07	W
	3.38±0.07	M
20	3.20±0.06	W
	3.05±0.05	W
25	2.64±0.03	W

These values were determined by standard techniques. The radiation was the K-alpha doublet of copper, and a scintillation-counter spectrometer with a strip-chart pen recorder was used. The peak heights "I" and the positions as a function of 2 times theta, where theta is the Bragg angle, were read from the spectrometer chart. From these, the relative intensities 100 I/I₀, where I₀ is the intensity of the strongest line or peak and d (obs.), the interplanar spacing in Å corresponding to the recorded lines, were calculated. In Table IV the relative intensities are given in terms of the symbols S=strong, M=medium, W=weak and VS=very strong. It should be understood that this X-ray diffraction pattern is characteristic of all the forms of TEA-silicate.

The crystalline metal organosilicates can be suitably synthesized by preparing a reaction system which in terms of moles of oxides has a composition within the range:



wherein R represents the tetraethylammonium cation and M represents an alkali metal cation, preferably sodium, potassium or lithium, said reaction mixture having a pH of greater than 12. The reaction mixture is preferably formed from the hydroxide of the alkali metal employed and the tetraethylammonium cation can be provided from an appropriate salt or base thereof such as tetraethylammonium bromide and tetraethylammonium hydroxide. Any reactive source of SiO₂ such as silica sols, gels, solid amorphous silicas or alkali metal silicates can be utilized in the same manner as SiO₂ is conventionally supplied to reaction mixtures in the preparation of synthetic zeolites. The reaction system is maintained at a temperature within the range of 125° to 150°C. until crystals of TEA-silicate are formed, usually a period of from about 70 to 250 hours. Thereafter the crystals are separated from the mother liquor and recovered by filtration or other conventional means. After washing with water, the TEA-silicate crystals are dried either in vacuum or an inert atmosphere such as air at moderate temperatures, 100°—110°C.

The crystalline organosilicates described herein are substantially free of alumina, but may contain very minor amounts thereof due to the presence of alumina as an impurity in the reactants employed, principally the silica source. Accordingly, the molar ratio of alumina to silica will be in the range of zero to less than 0.005.

Neither the tetraethylammonium nor the alkali metal cations of the TEA-silicates can be removed by ion-exchange techniques. The organic cations, however, can be decomposed thermally by calcination at temperatures of 400°C. or higher in an oxidizing or inert atmosphere such as air or nitrogen, respectively. Thermal decomposition of the organic cations does not affect the essential crystalline structure of the composition and the X-ray powder diffraction pattern is essentially unaltered.

Calcination to thermally decompose the TEA cations produces an apparent pore diameter of greater than 6.2 Angstroms. Thereafter, the calcined TEA-silicate is desirably washed to remove any metals or trace contaminants.

When used in the present process, calcined TEA-silicate may be employed either alone or in intimate admixture with independently active catalytic components, as for example the noble metals such as platinum, or other catalytically active metals such as molybdenum, vanadium, zinc, etc. The techniques of introducing catalytically active metals to a molecular sieve zeolite are disclosed in the literature, and

preexisting metal incorporation techniques are suitable. See, for example, Rabo et al. U.S. 3,236,761 and U.S. 3,236,762.

The physical form of the calcined TEA-silicate catalyst depends on the type of the catalytic reactor being employed. Calcined TEA-silicate by itself is a fine-grain granule or powder, and is desirably compacted into a more readily usable form (e.g., larger agglomerates), usually with a silica or alumina binder for fluidized bed reactions, or pills, prills, spheres, extrudates, or other shapes of controlled size to accord adequate catalyst-reactant contact. As indicated, the catalyst may be employed either as a fluidized catalyst, or in a fixed or moving bed, and in one or more reaction stages.

3. Conversion parameters

An unusual, if not unique, feature of the present invention is that the reaction conditions are low severity as compared with many preexisting processes. Indeed, the conversion parameters, while broad, may be selected to provide a high degree of versatility, depending upon the feed composition and on the desired product quality.

With respect to temperature, a temperature within the range of 300—700°C., more preferably within the range of 350—600°C., is adequate for many, if not all, conversions. Higher temperatures give more rapid and more complete reaction, but tend to produce undesirable by-products, chiefly coke, and may otherwise disturb the optimum balance of product composition with on-stream ease of operation.

The pressure, almost uniquely, is desirably quite low. Atmospheric pressure operation has been used successfully in the laboratory, but under specific conditions may be as high as 10.1×10^6 Pa or more. A desirable range is from atmospheric pressure to about 0.7×10^6 Pa. High pressures facilitate hydrogenation; lower pressures facilitate dehydrocyclization. The optimum pressure will therefore depend on process economics, considering whether it is more desirable to hydrogenate olefins than to produce a high yield of BTX aromatics.

Process stream flow rate, as expressed in units of weight hourly space velocity (WHSV), or weight of hydrocarbon feed per unit weight of catalyst, is suitably within the range of 0.1 to 20, more desirably 0.5—5.0. High WHSV's permit more economic plant construction, while lower WHSV's permit more complete reaction at given temperature pressure conditions.

If desired, a gaseous or gasifiable diluent may be introduced along with the hydrocarbon feed to the silicalite catalyst. This diluent may be inert, typified by steam, nitrogen or a low boiling paraffin, or may be reactive with the feed under catalysis conditions (e.g., hydrogen). Hydrogen is particularly desirable as it minimizes coke formation and deposition on the catalyst, with resulting premature deactivation, and also facilitates hydrogenation. As demonstrated below, however, the technique of the present invention need not utilize hydrogen.

If either an inert or a reactive gas is employed, diluent/hydrocarbon molar (gas volume) ratios, optimally, of from 0.1 to 10 may be employed.

It is usually necessary that the catalyst be regenerated, either periodically or continuously, to remove the carbonaceous coke-like deposits from the catalyst. In a fluidized bed operation, a portion of the catalyst is continuously withdrawn from the reactor and then subjected to regeneration by combustion with air or other oxygen containing gas, after which it is continuously recycled to the reactor. In a moving bed operation, the removal of catalyst followed by regeneration may be effected either continuously or periodically. In a fixed bed operation, it is generally desirable that two or more reactors be used in parallel, so that when one is processing the hydrocarbon feed, the other is out of service and being regenerated. Regeneration conditions of approximately 450—650°C, preferably 500—600°C. may be employed.

4. Example I

A specific example for the conversion of a C₉-plus feed is presented below. From the data, it is apparent that olefins and diolefins are converted by hydrogenation; that acyclic and cyclic nonaromatic components are dehydrocyclized to aromatic compounds; that C₉ plus alkylbenzenes, indane, indene, and methylstyrenes are converted in substantial part to the more desirable C₆—C₈ aromatics; and that, apparently, higher alkylnaphthalenes are converted by hydrogenolysis to recoverable naphthalene and methyl naphthalenes. Additionally, it is likely that the organic sulfur and nitrogen contents are lowered.

In the example herein, a C₉ plus by-product hydrocarbon effluent from the thermal pyrolysis unit was reacted over 37g of 15.9 mm extrudates of TEA-silicate with a 15% alumina binder. The reaction vessel was 1.91 cm OD stainless steel tubular reactor.

The reaction pressure was ambient; the reaction temperature was approximately 450°C.; and the space velocity of the feed varied from 0.7—0.8 g feed/g catalyst/hr. The molar ratio of SiO₂—to—Al₂O₃ in the catalyst was 377:1.

Samples of the liquid products, trapped in an ice water condenser, were taken after one hour and after six hours on stream. Five gas product samples were taken periodically.

The feed had the following analysis:

Analysis of C ₉ -plus hydrocarbon feed		
	Compounds	Weight percent
5	C ₅ —C ₈ Nonaromatics	0.19
	Benzene	0.31
	Toluene	0.10
10	Ethylbenzene, Mixed Xylenes	0.80
	Dicyclopentadiene, Styrene	45.46
15	C ₉ Alkylbenzenes, Methylstyrenes	10.61
	Indan	0.21
	Indene	9.83
20	naphthalene	12.67
	Methylnaphthalenes	1.45
25	Other C ₉ + Hydrocarbons	18.37

The gas samples were analyzed on a Hewlett Packard 5830A gas chromatograph equipped with a thermal conductivity detector. A forty foot stainless steel column with an OD of 31.8 mm packed with 20% tributylphosphate on 35—80 mesh Chromasorb P (acid washed) was used. The thermal conductivity detector temperature was set at 250°C., and the column temperature was ambient (approximately 20—22°C.). Gas samples were injected into the column off-line, through an eight port gas switching valve, via a gas syringe. The sample gas volume was approximately 0.3 cc; the carrier gas rate was 30 cc/min of helium.

Liquid samples for both product and feed were analyzed on a Hewlett Packard 5730A gas chromatograph, using a 5705A thermal conductivity detector. A ten foot stainless steel column with an OD of 31.8 mm, packed with 15% Carbowax 20M on 40/60 mesh Chromasorb P (acid washed), was used. The detector temperature was set at 250°C. The column was maintained in an oven, with a temperature programmed from 55°C. to 190°C. at 4°C./min; the injector temperature was 250°C. A sample size of approximately 2 ml. was used, and the helium carrier gas rate was 30 cc/min.

The following yields were determined:

0 093 476

Product analyses from conversion of C₉₊ Hydrocarbons using TEA-silicate

Compounds	(Weight percent yield)	
	Product 1 hr.	Composition 6 hr.
Methane	8.8	0.3
Ethane, Ethylene	1.3	0.3
Propane	9.4	0.1
Propylene	0.0	0.1
C ₄ 's	9.9	0.7
C ₅ to C ₈ Nonaromatics	3.5	12.0
Benzene	13.4	3.1
Toluene	12.3	4.0
Mixed Xylenes	10.1	6.7
C ₉₊ Hydrocarbons	31.3	72.8

Example II

A crude butadiene by-product hydrocarbon from an olefins production unit was reacted over 0.25 g of powdered catalyst (TEA-silicate) in a thermal chromatograph microreactor at 450°C. Crude butadiene flow rate was 5 cc/min at ambient pressure. The molar ratio of SiO₂—to—Al₂O₃ in the catalyst was 377:1. The reaction products were collected in a liquid nitrogen trap and then were allowed to purge into a gas chromatograph OV-101 column with a helium carrier gas. Analyses were run on both a flame detector and a thermal conductivity detector.

Example III

The extrudate catalyst used in Example I was tested in the microreactor for the conversion of crude butadiene byproduct. All conditions and the amount of catalyst were the same as in Example II.

Analyses of the crude butadiene feed in Examples II and III, and of the products from the reactions are shown below:

Analysis of crude butadiene feed	
Compounds	Weight percent
C ₃ 's and lighter	1.24
Isobutane	2.57
n-Butane	8.68
1-Butene, Isobutylene	33.74
t-2-Butene	4.15
c-2-Butene	2.44
1,3-Butadiene	45.72
C ₄ Acetylenes	1.28
C ₅ Hydrocarbons	0.19

Product analyses from conversion of crude
butadiene using TEA-silicate catalyst

	Compounds	Example II	Example III
5	C ₁ —C ₄	32.5	38.2
	C ₅ +C ₆ Aliphatics	9.5	8.1
	Benzene	3.9	3.3
10	C ₇ Aliphatics	3.8	4.7
	Toluene	11.4	7.6
15	C ₈ Aliphatics	3.1	6.3
	Ethylbenzene, Xylenes	14.3	11.3
20	C ₉ + Hydrocarbons	21.5	20.7

Thus it is apparent that there has been provided, according to the invention, a process that is uniquely effective in treating by-product effluent streams from pyrolytic cracking processes.

TABLE V

References

25	Mobil Oil U.S. Patent 3,442,795
	Mobil Oil U.S. Patent 3,702,886
	Mobil Oil U.S. Patent 3,728,408
30	Mobil Oil U.S. Patent 3,760,024
	Mobil Oil U.S. Patent 3,790,471
	Mobil Oil U.S. Patent 3,813,330
	Mobil Oil U.S. Patent 3,970,544
	Mobil Oil U.S. Patent 4,097,367
35	Mobil Oil U.S. Patent 4,105,541
	Mobil Oil U.S. Patent 4,120,910
	Mobil Oil U.S. Patent 4,150,006
	Mobil Oil U.S. Patent 4,150,062
40	Mobil Oil U.S. Patent 4,157,293
	Mobil Oil European Patent Application 15,132
	Mobil Oil European Patent Application 23,089
	Mobil Oil European Patent Application 26,030
45	Shell Internationale Research Maatschappij, Uk Patent Application 2,044,289
	Shell Internationale Research Maatschappij, UK Patent Application 2,044,290
50	Shell Internationale Research Maatschappij, NL Patent 7,902,019
	Shell Internationale Research Maatschappij, NL Patent Application 8,001,342
55	Union Carbide U.S. Patent 3,444,253
	Union Carbide U.S. Patent 3,497,462
	Union Carbide U.S. Patent 4,061,724
60	Union Carbide U.S. Patent 4,170,571
	Union Carbide U.S. Patent 4,257,885
	Erdolchemie Ger. Offen. DE 2,936,036
65	B.P. Belg. Patent 862,051

Claims

1. A low severity process for the preparation of a benzene-toluene-xylenes enriched stream containing minimal monoolefin and diolefin content, from a feed stream comprising a by-product effluent of a process for the pyrolytic cracking of hydrocarbons to produce light olefins or diolefins, said by-product effluent stream containing olefins and diolefins, said process comprising contacting said by-product effluent stream, under low severity conditions including a temperature within the range of 300—700°C., a pressure within the range of 0—10.1×10⁶ Pa and a weight hourly space velocity within the range of 0.1 to 20, with a catalyst essentially comprising a calcined TEA-silicate.
2. Process of claim 1 wherein said conditions include a temperature within the range of about 350—600°C., a pressure within the range 0.1—0.7×10⁶ Pa and a weight hourly space velocity within the range of 0.5—5.0.
3. Process of claim 1 wherein said by-product effluent comprises a C₄ stream.
4. Process of claim 1 wherein said by-product effluent comprises a C₅ stream.
5. Process of claim 1 wherein said by-product effluent comprises a whole or fractionated dripolene stream.
6. Process of claim 1 wherein said feed stream is admixed with a diluent.
7. Process of claim 6 wherein said diluent is steam.
8. Process of claim 6 wherein said diluent is hydrogen.
9. Process of claim 6 wherein said diluent is a low boiling paraffin.
10. Process of claim 6 wherein said diluent is a mixture of a low boiling paraffin, hydrogen and/or steam.

Patentansprüche

1. Mildes Verfahren zur Herstellung eines Stroms, der an Benzol, Toluol und Xylole angereichert ist und einen minimalen Gehalt an Monoolefinen und Diolefinen aufweist, aus einem Ausgangsstrom, umfassend den Nebenprodukt-Abstrom eines Verfahrens zum pyrolytischen Cracken von Kohlenwasserstoffen zur Erzeugung von leichten Olefinen oder Diolefinen, wobei der Nebenprodukt-Abstrom Olefine und Diolefine enthält und wobei das Verfahren das Zusammenbringen des erwähnten Nebenprodukt-Abstroms unter milden Bedingungen bei einer Temperatur im Bereich von 300 bis 700°C, einem Druck im Bereich von 0 bis 10,1×10⁶ Pa und einem aus das Gewicht bezogenen stündlichen Durchsatz im Bereich von 0,1 bis 20, mit einem Katalysator umfaßt, der im wesentlichen ein calciniertes TEA-Silicat enthält.
2. Verfahren nach Anspruch 1, wobei die erwähnten Bedingungen eine Temperatur im Bereich von 350 bis 600°C, einen Druck im Bereich von 0,1 bis 0,7×10⁶ Pa und einen auf das Gewicht bezogenen stündlichen Durchsatz im Bereich von 0,5 bis 5,0 umfassen.
3. Verfahren nach Anspruch 1, wobei der Nebenprodukt-Abstrom einen C₄-Strom umfaßt.
4. Verfahren nach Anspruch 1, wobei der Nebenprodukt-Abstrom einen C₅-Strom umfaßt.
5. Verfahren nach Anspruch 1, wobei der Nebenprodukt-Abstrom einen ganzen oder fraktionierten Dripolenstrom umfaßt.
6. Verfahren nach Anspruch 1, wobei der Ausgangsstrom mit einem Verdünnungsmittel vermischt ist.
7. Verfahren nach Anspruch 6, wobei das Verdünnungsmittel (Wasser)dampf ist.
8. Verfahren nach Anspruch 6, wobei das Verdünnungsmittel Wasserstoff ist.
9. Verfahren nach Anspruch 6, wobei das Verdünnungsmittel ein niedrig siedendes Paraffin ist.
10. Verfahren nach Anspruch 6, wobei das Verdünnungsmittel ein Gemisch aus einem niedrig siedenden Paraffin, Wasserstoff und/oder (Wasser)dampf ist.

Revendications

1. Procédé à faible sévérité pour la préparation d'un produit enrichi en benzène-toluène-xyliènes à teneur minimale en mono-oléfines et en dioléfines à partir d'un courant de charge comprenant un effluent de sous-produits d'un procédé de craquage pyrolytique d'hydrocarbures pour former des oléfines ou des dioléfines légères, le courant d'effluent de sous-produits contenant des oléfines et des dioléfines, procédé qui consiste à faire entrer en contact ledit courant effluent de sous-produits, dans des conditions de faible sévérité comprenant une température dans l'intervalle d'environ 300 à 700°C, une pression dans l'intervalle d'environ 0 à 10,1×10⁶ Pa et une vitesse spatiale horaire en poids dans l'intervalle d'environ 0,1 à 20, avec un catalyseur essentiellement formé d'un TEA-silicate calciné.
2. Procédé suivant la revendication 1, dans lequel lesdites conditions impliquent une température dans l'intervalle d'environ 350 à 600°C, une pression dans l'intervalle d'environ 350 à 600°C, une pression dans l'intervalle d'environ 0,1 à 0,7×10⁶ Pa et une vitesse spatiale horaire en poids dans l'intervalle de 0,5 à 5,0.
3. Procédé suivant la revendication 1, dans lequel ledit effluent de sous-produits est un courant en C₄.
4. Procédé suivant la revendication 1, dans lequel ledit effluent de sous-produits comprend un courant en C₅.
5. Procédé suivant la revendication 1, dans lequel ledit effluent de sous-produits comprend un courant de dripolène entier ou fractionné.

0 093 476

6. Procédé suivant la revendication 1, dans lequel ledit courant de charge est mélange avec un diluant.

7. Procédé suivant la revendication 6, dans lequel ledit diluant est de la vapeur.

8. Procédé suivant la revendication 6, dans lequel ledit diluant est de l'hydrogène.

5 9. Procédé suivant la revendication 6, dans lequel ledit diluant est une paraffine de bas point d'ébullition.

10. Procédé suivant la revendication 6, dans lequel ledit diluant est un mélange d'une paraffine de bas point d'ébullition, d'hydrogène et/ou de vapeur.

10

15

20

25

30

35

40

45

50

55

60

65