

①⑨



Europäisches Patentamt
European Patent Office
Office européen des brevets

①⑪ Publication number:

**0 098 072
B1**

①⑫

EUROPEAN PATENT SPECIFICATION

④⑤ Date of publication of patent specification: **01.10.86**

⑤① Int. Cl.⁴: **G 03 C 7/30**

②① Application number: **83303424.2**

②② Date of filing: **14.06.83**

⑤④ **Color photographic elements containing scavengers for oxidized developing agents.**

③⑩ Priority: **18.06.82 US 389994**

④③ Date of publication of application:
11.01.84 Bulletin 84/02

④⑤ Publication of the grant of the patent:
01.10.86 Bulletin 86/40

⑧④ Designated Contracting States:
DE FR GB

⑤⑨ References cited:
EP-A-0 011 567

⑦③ Proprietor: **EASTMAN KODAK COMPANY**
343 State Street
Rochester New York 14650 (US)

⑦② Inventor: **Ross, Robert Edward**
2587 Browncroft Boulevard
Rochester New York 14625 (US)
Inventor: **Gaugh, Wilbur Seth**
1658 Schlegal Road
Webster New York 14580 (US)

⑦④ Representative: **Baron, Paul Alexander Clifford**
et al
Kodak Limited Patent Department Headstone
Drive
Harrow Middlesex HA1 4TY (GB)

EP 0 098 072 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

Description

This invention relates to color photographic elements containing scavengers for oxidized developing agents.

It is known in the art to add scavengers for oxidized developing agents to photographic elements in order for the scavenger to interact with the oxidized developing agents and prevent them from reacting at an undesired location or at an undesired point in time. Included among the scavengers for oxidized developing agents known in the art are the ballasted 2,5-disulfonamidophenols shown in U.S. Patent 4,205,987 and the 2-, or 4-sulfonamidophenols shown in *Research Disclosure*, February, 1979, Item No., 17842. *Research Disclosure* is published by Industrial Opportunities Ltd., Homewell, Havant, Hampshire, PO9 1EF, United Kingdom.


It is known in the art that certain phenols are dye-forming couplers and that they will react with oxidized color developing agents to form cyan dye. 4-Sulfonamidophenols are specifically disclosed in U.S. Patent 3,737,316 as being dye-forming couplers.

In view of the knowledge which those skilled in the art possess regarding the ability of phenols to couple with oxidized color developing agents, it would be expected that the scavengers described in U.S. Patent 4,205,987 and the *Research Disclosure* referred to above, would couple with oxidized color developing agents to form dye stain and therefore would be of limited utility in color photographic elements intended to be processed with oxidized color developing agents where such stain would be objectionable. Thus, the sulfonamidophenols of U.S. Patent 4,205,987 and the *Research Disclosure* have found their principal utility in those image transfer materials which do not employ color developing agents for processing or in those materials where the scavenger is in a layer where it is not visible upon viewing of the final image.

The 2,5-disulfonamidophenols of U.S. Patent 4,205,987 and 4-sulfonamidophenols of the *Research Disclosure* do in fact couple with oxidized color developing agents to form undesirable color stain.

This problem is solved with a color photographic element comprising a support, at least one silver halide emulsion layer and a scavenger for oxidized developing agent, characterized in that the scavenger is a 2,4-disulfonamidophenol or an alkali labile precursor of such phenol. Such 2,4-disulfonamidophenols do not couple with oxidized developing agents to form dyes.

Preferred sulfonamidophenol scavengers for oxidized color developing agents used in the present invention can be represented by the structural formula:




wherein:

G is hydroxy or an alkali labile precursor thereof.

Each R¹ is individually alkyl of 1 to 30 carbon atoms, aryl of 6 to 30 carbon atoms or heterocyclyl of 5 to 30 atoms containing one or more ring heteroatoms selected from nitrogen, oxygen, sulfur and selenium; and

R², R³ and R⁴ are each individually hydrogen, halogen, alkyl of 1 to 30 carbon atoms, alkoxy of 1 to 30 carbon atoms, aryl of 6 to 30 carbon atoms or aryloxy of 6 to 30 carbon atoms, the scavenger being of sufficient bulk so as to be non-diffusible in the layers of the element.

Especially preferred sulfonamidophenol scavengers have the structural formula:



wherein:

each R¹ is individually alkyl of 1 to 30 carbon atoms, or aryl of 6 to 30 carbon atoms; and







R², R³ and R⁴ are each individually hydrogen, alkyl of 1 to 30 carbon atoms or alkoxy of 1 to 30 carbon atoms.

In particularly preferred scavengers R³ is alkyl of 1 to 4 carbon atoms or alkoxy of 1 to 4 carbon atoms and R² and R⁴ are hydrogen.


As indicated above, G is a hydroxy group or an alkali labile precursor of a hydroxy group. In the alkali labile precursors, the hydrogen atom of the hydroxy group is replaced with a blocking group which is removed upon contact with base. Typical blocking groups are removable by hydrolysis or by intramolecular nucleophilic displacement. Typical groups removable by hydrolysis are acyl groups such as aliphatic and aromatic carbonyl and sulfonyl groups. Typical groups removable by intramolecular nucleophilic displacement are described in U.S. Patent 4,310,612.

The alkyl, alkoxy, aryl, and aryloxy substituents described above can be further substituted. Representative such substituents include halogen, nitro, alkyl, aryl, alkenyl, alkoxy, aryloxy, alkenyloxy, heterocyclyl, alkylcarbonyl, arylcarbonyl, alkenylcarbonyl, alkylsulfonyl, arylsulfonyl, alkenylsulfonyl, amino, aminocarbonyl, aminosulfonyl, carboxy, alkoxy, alkoxy, aryloxy, alkenyloxy, alkenylsulfonyl, and the like. Thus, alkyl is inclusive of, e.g., arylalkyl and aryloxyalkyl, and aryl is inclusive of, e.g., alkaryl and alkoxyaryl. The alkenyl groups referred to above can also be substituted, e.g. aralkenyl. The amine portions of these further substituents include primary, secondary, and tertiary amines as well as acylated amines.


Representative scavengers of the present invention are shown below.




0 098 072




(7)




(8)




(9)



(10)




(11)




(12)

5



(13)


10



(14)

20

25



(15)

30

35

The compounds used in the present invention are known compounds or similar to known compounds and can be prepared by known reactions. To prepare compounds in which the sulfonamido groups in the 2- and 4-position are identical, a 2,4-diaminophenol is reacted with the appropriate sulfonyl halide. If dissimilar sulfonamido groups are desired, a 2-amino-4-nitrophenol or a 4-amino-2-nitrophenol is reacted with an appropriate sulfonyl halide to attach one of the groups to the amino substituent, the nitro group is then reduced and a second sulfonyl halide is attached to the amino group formed by reduction of the nitro group. If blocked compounds are to be prepared, the blocking group can be attached to the hydroxy either before or after attachment of the sulfonamido groups. Representative preparations are shown in the working examples.

45

The scavengers used in this invention can be used in the ways and for the purposes that scavengers for oxidized developing agent are employed in the art. They can be incorporated in a silver halide emulsion layer of the photographic element or in a separate layer of the element. When incorporated in a separate layer, that layer is preferably an interlayer between silver halide emulsion layers although it can be an undercoat layer coated below all of the silver halide emulsion layers or an overcoat layer coated above all of the silver halide emulsion layers.

50

The amount of scavenger compound employed will depend upon the particular purpose for which the scavenger is to be used and the degree of scavenging desired. Typically useful results are obtained when the scavenger is employed in an amount of between 5 and 2000 mg/sq. meter.

55

The scavenger can be incorporated in photographic elements by techniques known in the art. In certain preferred embodiments, the scavenger is dissolved in a high boiling solvent, such as a water insoluble coupler solvent and then dispersed either in a silver halide emulsion layer or in a separate vehicle such as gelatin. Typical useful coupler solvents are moderately polar solvents such as tritolylphosphate, di-N-butylphthalate, diethylauramide, 2,4-dipentylphenol, and the like. Typical vehicles are gelatin, and other hydrophilic colloids commonly employed in silver halide photographic elements. These vehicles are described in *Research Disclosure*, December 1978, Item No. 17643, Section IX. The scavengers can be introduced into the element in a polymeric latex. Suitable techniques for dispersing the scavengers in a latex are described in U.S. Patents 4,203,716 and 4,214,047 and in *Research Disclosure*, July 1977, Item 15930 and July 1980, Item 19551.

60

The photographic elements of the present invention can be simple monochrome color elements comprising a support bearing a layer of the silver halide emulsion, or they can be multicolor multilayer

65

elements. They can be designed for processing with separate solutions or for in-camera processing. Multicolor elements contain dye image-forming units sensitive to each of the three primary regions of the spectrum. Each unit can be comprised of a single emulsion layer or of multiple emulsion layers sensitive to a given region of the spectrum. The layers of the element, including the layers of the image-forming units, can be arranged in various orders as known in the art. In an alternative format, the emulsion or emulsions can be disposed as one or more segmented layers, e.g., as by the use of microvessels or microcells, as described in Belgian Patent 881,513.

A preferred photographic element according to this invention comprises a support bearing at least one blue-sensitive silver halide emulsion layer having associated therewith a yellow image dye-providing material, at least one green-sensitive silver halide emulsion layer having associated therewith a magenta image dye-providing material and at least one red-sensitive silver halide emulsion layer having associated therewith a cyan image dye-providing material, the element containing a scavenger of this invention. Preferably the scavenger is in an interlayer between silver halide emulsion layers sensitive to different regions of the visible spectrum although it can be in a silver halide emulsion layer or in an interlayer between silver halide emulsion layers sensitive to the same region of the visible spectrum.

The photographic elements of the present invention can contain additional layers conventional in photographic elements, such as overcoat layers, spacer layers, filter layers, antihalation layers, pH lowering layers (sometimes referred to as acid layers and neutralizing layers), timing layers, opaque reflecting layer, opaque light-absorbing layers and the like. The support can be any suitable support used with photographic elements. Typical supports include polymeric films, paper (including polymer-coated paper), glass and the like. Details regarding supports and other layers of the photographic elements of this invention are contained in *Research Disclosure*, December 1978, Item 17643, referred to above.

The light-sensitive silver halide emulsions employed in the photographic elements of this invention can include coarse, regular or fine grain silver halide crystals or mixtures thereof and can be comprised of such silver halides as silver chloride, silver bromide, silver bromiodide, silver chlorobromide, silver chloriodide, silver chlorobromiodide, and mixtures thereof. The emulsions can be negative working or direct positive emulsions. They can form latent images predominantly on the surface of the silver halide grains or in the interior of the silver halide grains. They can be chemically and spectrally sensitized in accordance with usual practices. The emulsions typically will be gelatin emulsions although other hydrophilic colloids can be used in accordance with usual practice. Details regarding the silver halide emulsions are contained in *Research Disclosure*, Item 17643, December, 1978 and the references listed therein.

The photographic silver halide emulsions can contain other addenda conventional in the photographic art. Useful addenda are described, for example, in *Research Disclosure*, December 1978, Item 17643. Useful addenda include spectral sensitizing dyes and desensitizers, antifoggants, masking couplers, DIR (development inhibitor-releasing) couplers, DIR compounds, anti-stain agents, image dye stabilizers, absorbing materials such as filter dyes and UV absorbers, light scattering materials, coating aids, plasticizers and lubricants.

Depending upon the dye-image-providing material employed in the photographic element, it can be incorporated in the silver halide emulsion layer or in a separate layer associated with the emulsion layer. The dye-image-providing material can be any of a number known in the art, such as dye-forming couplers, bleachable dyes, dye developers and redox dye-releasers, and the particular one employed will depend on the nature of the element and the type of image desired.

Dye-image-providing materials employed with conventional color materials designed for processing with separate solutions are preferably dye-forming couplers; i.e., compounds which couple with oxidized developing agent to form a dye. Preferred couplers which form cyan dye images are phenols and naphthols. Preferred couplers which form magenta dye images are pyrazolones and pyrazolotriazoles. Preferred couplers which form yellow dye images are benzoylacetylides and pivalylacetylides.

Dye-image-providing materials useful in diffusion transfer film units contain a dye group and a monitoring group. The monitoring group, in the presence of an alkaline processing solution and as a function of a silver halide development, is responsible for a change in mobility of the dye group. These dye-image-providing materials can be initially mobile and rendered immobile as a function of silver halide development, as described in U.S. Patent 2,983,606. Alternatively, they can be initially immobile and rendered mobile, in the presence of an alkaline processing solution, as a function of silver halide development. This latter class of materials include redox dye-releasing compounds. In such compounds, the monitoring group is a carrier from which the dye is released as a direct function of silver halide development or as an inverse function of silver halide development, 3-pyrazolidones such as 1-phenyl-3-pyrazolidone and 1-phenyl-4,4-dimethyl-3-pyrazolidone being preferred developing agents. Compounds which release dye as a direct function of silver halide development are referred to as negative-working release compounds, while compounds which release dye as an inverse function of silver halide development are referred to as positive-working release compounds.

A preferred class of negative-working release compounds are the ortho or para sulfonamidophenols and naphthols described in U.S. Patents 4,054,312, 4,055,428 and 4,076,529. In these compounds the dye group is attached to a sulfonamido group which is ortho or para to the phenolic hydroxy group and is released by hydrolysis after oxidation of the sulfonamido compound during development.

A preferred class of positive-working release compounds are the nitrobenzene and quinone compounds described in U.S. Patent 4,139,379. In these compounds the dye group is attached to an electrophilic cleavage group, such as a carbamate group, ortho to the nitro group or the quinone oxygen, and is released upon reduction of the compound by an electron donor compound contained in the element or the processing composition, unless the electron donor is oxidized during development.


The developing agents which can be used to develop the photographic elements of this invention, the oxidized form of which can be reduced by the scavengers of this invention, include aminohydroxy-pyrazoles, aminophenols and phenylene diamines. Some developing agents, when used for certain applications, are referred to in the art as electron transfer agents. The particular developing agent employed will depend on the particular type of photographic element to be processed.

Representative preferred color developing agents include: 4-amino-N-ethyl-N-β-hydroxy-ethyl-3-toluidine, N,N-diethyl-p-phenylenediamine, 3-methyl-N,N-diethyl-p-phenylenediamine, 3-methoxy-N,N-diethyl-p-phenylenediamine and N,N,N',N'-tetramethyl-p-phenylenediamine.

The term "non-diffusible" used herein has the meaning commonly applied to the term in photography and denotes materials that for all practical purposes do not migrate or wander through organic colloid layers such as gelatin in an alkaline medium, in photographic elements and preferably when processed in a medium having a pH of 10 or greater. The term "diffusible" has the converse meaning and denotes the materials having the property of diffusing effectively through the colloid layers of photographic elements in an alkaline medium.


The term "associated therewith" as used herein is intended to mean that the materials can be in either the same or different layers so long as the materials are accessible to one another during processing.

Preparation of Compound 1



A mixture of 4.5 g (0.03 mole) 2-amino-4-nitrophenol and palladium on charcoal catalyst in 60 ml dimethylformamide was reduced in a Parr bottle with 40 psi hydrogen until the theoretical amount was taken up. Immediately after removal of the catalyst by filtration, 6.3 g (0.075 mole) sodium bicarbonate and 21.7 g (0.06 mole) 4-dodecyloxybenzenesulfonyl chloride were added with stirring and the mixture was heated to drive off carbon dioxide. The product isolated by pouring the reaction mixture into ice water was recrystallized in turn from methanol, ethanol/hexane, and acetonitrile to yield 7.5 g nearly colorless crystals, m.p. 137—139°C with the correct elemental analysis for Compound 1.

Preparation of Compound 8



To a -10°C solution of 46.2 g (0.3 mole) 4-amino-2-nitrophenol in 500 ml tetrahydrofuran and 240 ml pyridine was added dropwise over 10 minutes with stirring 34.4 g (0.3 mole) methanesulfonyl chloride. After stirring 18 hours the liquid reaction mixture was poured into a vigorously stirred solution of 240 ml concentrated hydrochloric acid in 800 ml water and the resulting precipitate was collected, washed, dried, decolorized, and recrystallized from acetonitrile to yield 32.5 g yellow crystals of (2b), m.p. $164-6^{\circ}\text{C}$, with the correct infrared and NMR spectrum and a good elemental analysis. A solution of 15 g (0.065 mole) (2b) in 80 ml tetrahydrofuran and 80 ml methanol was hydrogenated overnight over palladium on charcoal in a Parr apparatus. Then the catalyst was removed by filtration and the solvent by evaporation. The resultant gray solid (2c) was dissolved in 200 ml tetrahydrofuran and 50 ml of pyridine and a solution of 21 g (0.065 mole) 1-hexadecanesulfonyl chloride in 100 ml tetrahydrofuran was added dropwise with stirring. After 4 hours the reaction mixture was poured onto 600 ml ice water containing 50 ml concentrated hydrochloric acid and the precipitate collected. Recrystallization from acetonitrile afforded 15.7 g white crystals, m.p. $147-9^{\circ}\text{C}$, with the correct analysis and spectra for Compound 8.

The following Examples illustrate the invention.


Examples

To evaluate the scavenger compounds used in the photographic elements of this invention with respect to their effectiveness as interlayer scavengers for oxidized color developing agents a color negative test photographic element was employed represented by the following schematic structure:


Overcoat: Gelation 0.86 g/m ² , Hardener 1.75%		
Emulsion Layer:	Silver Halide	1.61 g/m ²
	Yellow Coupler	0.34 g/m ²
	Gelatin	2.42 g/m ²
Interlayer:	Test Compound	0.123 mmol/m ²
	Gelatin	0.62 g/m ²
Cyan Layer:	Cyan Coupler	1.12 g/m ²
	Gelatin	2.42 g/m ²
Film Support		

In this element the hardener is bis(vinylsulfonylmethyl)ether and the couplers have the following structures:

Yellow Coupler:



Cyan Coupler:





Couplers and test compounds were coated as dispersions in dibutylphthalate or comparable coupler solvent. In this photographic element, oxidized color developing agent, originating in the emulsion layer as the exposed silver halide develops, can react with the yellow coupler to form a yellow dye. It can also migrate through the interlayer to the cyan layer to react with coupler there to form a cyan dye. Reactive test compounds in the interlayer can also react with oxidized color developing agent, thus limiting cyan dye formation to the cyan layer. For color negative photographic elements, it is usually more desirable that the scavenger compound reduce oxidized developing agent rather than coupling with it, since the latter reaction can result in unwanted dye stain.

Scavenging efficiency of each test compound was determined by measuring the developed density ratio of cyan dye (at 665 nm) to yellow dye (at 450 nm). The more active scavenger compounds used in the invention reduce this red/blue density ratio to about 0.20 from a control value (no scavenger in the interlayer) of about 0.40.

One sample of each of the photosensitive elements, prepared as described above to contain a different desired test compound, was exposed through a graduated density test object and then processed by the color negative C-41 process described in the *British Journal of Photography*, July 12, 1974, pp. 597-8. The cyan dye contamination (red density) of the final yellow dye image (blue density) was then measured for the samples. Coupling of the scavenger to form a cyan dye was determined by visual inspection of a cross-section of the sample. If cyan dye density was observed in the interlayer, the scavenger was considered to have coupled with oxidized color developing agent. The results are presented in the following table.

TABLE I

	Test Compound	Red/Blue Density Ratio	Coupling With Cyan Coupler
5	None (Control)	0.40	No
	*A (Comparison)	0.36	Yes
10	**B (Comparison)	0.40	Yes
	1 (Invention)	0.18	No
	3 (Invention)	0.18	No
15	4 (Invention)	0.19	No




It can be seen from the above table that the control and comparison compounds at equimolar levels show less scavenging ability and greater propensity for undesired coupling to form dye than do the scavenger compounds used in the invention.

Claims

1. A color photographic element comprising a support, at least one silver halide emulsion layer, and a scavenger for oxidizing developing agent, characterized in that the scavenger is a 2,4-disulfonamidophenol or an alkali labile precursor of such phenol.

2. A photographic element of Claim 1, characterized in that the scavenger has the structural formula:



wherein:

G is hydroxy or an alkali labile precursor thereof;

each R¹ is individually alkyl of 1 to 30 carbon atoms, or aryl of 6 to 30 carbon atoms or heterocyclyl of 5 to 30 atoms containing one or more ring hetero atoms selected from nitrogen, oxygen, sulfur and selenium; and

R², R³ and R⁴ are each individually hydrogen, halogen, alkyl of 1 to 30 carbon atoms, alkoxy of 1 to 30 carbon atoms, aryl of 6 to 30 carbon atoms or aryloxy of 6 to 30 carbon atoms, the alkyl, alkoxy, aryl and aryloxy groups being optionally substituted and the scavenger being of sufficient bulk so as to be non-diffusible in the layers of the element.


3. A photographic element of Claims 1 or 2, characterized in that the scavenger is in an interlayer between two silver halide emulsion layers.

4. A photographic element of Claims 1 or 2, characterized in that the scavenger is in a silver halide emulsion layer.


5. A photographic element of any of Claims 1 to 4, characterized in that the silver halide emulsion layer has associated therewith an image dye-providing material.

6. A photographic element of Claim 5, characterized in that the image dye-providing material is a dye-forming coupler.


7. A photographic element of any of Claims 1 to 6, characterized in that the scavenger has the formula:



8. A photographic element of any of Claims 1 to 6, characterized in that the scavenger has the formula:




9. A photographic element of any of Claims 1 to 6, characterized in that the scavenger has the formula:



Patentansprüche

1. Farbphotographisches Element mit einem Träger, mindestens einer Silberhalogenidemulsionsschicht und einer Abfangverbindung für oxidierte Entwicklerverbindung, dadurch gekennzeichnet, daß die Abfangverbindung ein 2,4-Disulfonamidophenol oder eine alkalilabile Vorläuferverbindung eines solchen Phenols ist.

2. Photographisches Element nach Anspruch 1, dadurch gekennzeichnet, daß die Abfangverbindung der folgenden Strukturformel entspricht:



in der bedeuten:

G eine Hydroxygruppe oder eine alkalilabile Vorläufergruppe hiervon;

R¹ jeweils eine Alkylgruppe mit 1 bis 30 Kohlenstoffatomen oder eine Arylgruppe mit 6 bis 30 Kohlenstoffatomen oder eine Heterocyclylgruppe mit 5 bis 30 Atomen, die ein oder mehrere Ringheteroatome, ausgewählt aus Stickstoff, Sauerstoff, Schwefel und Selen enthält und

R^2 , R^3 und R^4 jeweils ein Wasserstoff- oder Halogenatom, eine Alkylgruppe mit 1 bis 30 Kohlenstoffatomen, eine Alkoxygruppe mit 1 bis 30 Kohlenstoffatomen, eine Arylgruppe mit 6 bis 30 Kohlenstoffatomen oder eine Aryloxygruppe mit 6 bis 30 Kohlenstoffatomen,

wobei gilt, daß die Alkyl-, Alkoxy-, Aryl- und Aryloxygruppe gegebenenfalls substituiert sein können und die Abfangverbindung genügend sperrig ist, um in den Schichten des Elementes nicht zu diffundieren.


3. Photographisches Element nach Anspruch 1 oder 2, dadurch gekennzeichnet, daß die Abfangverbindung in einer Zwischenschicht zwischen zwei Silberhalogenidemulsionsschichten untergebracht ist.

4. Photographisches Element nach Ansprüchen 1 oder 2, dadurch gekennzeichnet, daß die Abfangverbindung in einer Silberhalogenidemulsionsschicht untergebracht ist.


5. Photographisches Element nach einem der Ansprüche 1 bis 4, dadurch gekennzeichnet, daß der Silberhalogenidemulsionsschicht ein einem Bildfarbstoff lieferndes Material zugeordnet ist.

6. Photographisches Element nach Anspruch 5, dadurch gekennzeichnet, daß das einen Bildfarbstoff liefernde Material ein einen Farbstoff liefernder Kuppler ist.


7. Photographisches Element nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß die Abfangverbindung der folgenden Formel entspricht:



8. Photographisches Element nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß die Abfangverbindung der folgenden Formel entspricht:




9. Photographisches Element nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß die Abfangverbindung der folgenden Formel entspricht:



Revendications

1. Produit pour la photographie en couleurs, comprenant un support, au moins une couche d'émulsion aux halogénures d'argent et un composé pour immobiliser les développeurs oxydés, caractérisé en ce que le composé d'immobilisation est un 2,4-disulfonamidophénol ou un précurseur de ce phénol labile en milieu alcalin.

2. Produit photographique de la revendication 1 caractérisé en ce que, le composé d'immobilisation a la formule structurale:



où:

G est un groupe hydroxy ou un précurseur labile en milieu alcalin de celui-ci;

chaque R¹ est individuellement un groupe alkyle de 1 à 30 atomes de carbone, ou un groupe aryle de 6 à 30 atomes de carbone ou un groupe hétérocyclique de 5 à 30 atomes contenant un ou plusieurs hétéro atomes sur le cycle choisis parmi l'azote, l'oxygène, le soufre, le sélénium; et

R², R³, R⁴, sont chacun individuellement un atome d'hydrogène, un atome d'halogène, un groupe alkyle de 1 à 30 atomes de carbone, un groupe alkoxy de 1 à 30 atomes de carbone, un groupe aryle de 6 à 30 atomes de carbone et un groupe aryloxy de 6 à 30 atomes de carbone, les groupes alkyle, alkoxy, aryle et aryloxy étant facultativement substitués et le composé d'immobilisation étant d'encombrement suffisant pour pas diffuser dans les couches du produit.


3. Produit photographique conforme aux revendications 1 ou 2, caractérisé en ce que le composé d'immobilisation est dans une intercouche entre deux couches d'émulsion aux halogénures d'argent.

4. Produit photographique conforme aux revendications 1 ou 2 caractérisé en ce que le composé d'immobilisation est dans une couche d'émulsion aux halogénures d'argent.

5. Produit photographique conforme à l'une quelconque des revendications 1 à 4 caractérisé en ce que la couche d'émulsion aux halogénures d'argent est associée avec une substance fournissant le colorant formateur d'image.


6. Produit photographique conforme à la revendication 5, caractérisé en ce que la substance fournissant le colorant formateur d'image est un coupleur formateur de colorant.

7. Produit photographique conforme à l'une quelconque des revendications 1 à 6 caractérisé en ce que le composé d'immobilisation a la formule:



(1)

8. Produit photographique conforme à l'une quelconque des revendications 1 à 6 caractérisé en ce que le composé d'immobilisation a la formule:



(3)

9. Produit photographique conforme à l'une quelconque des revendications 1 à 6, caractérisé en ce que le composé d'immobilisation a la formule:

