

12

EUROPEAN PATENT APPLICATION

21 Application number: 84303695.5

51 Int. Cl.³: **G 02 B 5/172**

22 Date of filing: 01.06.84

30 Priority: 01.06.83 US 499898

43 Date of publication of application:
12.12.84 Bulletin 84/50

84 Designated Contracting States:
AT BE CH DE FR GB IT LI NL SE

71 Applicant: Corning Glass Works
Houghton Park
Corning New York 14831(US)

72 Inventor: Bhagavatula, Venkata Adisheshaiah
137 Field Street Mountainbrow Apts. 3
Corning New York(US)

72 Inventor: Nolan, Daniel Aloysius
28 Skyline Drive
Corning New York 14830(US)

74 Representative: Boon, Graham Anthony et al,
Elkington and Fife High Holborn House 52/54 High
Holborn
London, WC1V 6SH(GB)

54 Polarization-retaining single-mode optical waveguide.

57 An optical fiber is disclosed for operating single polarization, single-mode at wavelength λ . The fiber core (15, 21) is surrounded by cladding having the refractive index lower than the average refractive index of the core. The core is characterized in that it comprises a plurality of transparent laminae (16, 17, 23, 24, 31, 32, 37, 38), each having a refractive index different from that of the adjacent laminae. The thickness of each lamina is equal to or less than wavelength λ .




Fig. 1

-1-

"POLARIZATION-RETAINING SINGLE-MODE OPTICAL WAVEGUIDE"

In many applications of single-mode optical waveguides, such as sensors and coherent optical communication systems, it is important that the propagating optical signal retain the polarization characteristics of the input light in the presence of external or internal depolarizing perturbations. The change of the polarization state of a propagating signal can be prevented or reduced by employing a fiber that is birefringent, i.e. the core refractive index is different for two orthogonally polarized light waves.

The polarization performance of a single-mode fiber can be characterized by its beat length L , where L is defined as $2\pi/\Delta\beta$, and $\Delta\beta$ is the difference in the propagation constants of the two orthogonal polarizations. It is desirable to make fibers with a beat length L of 1 mm or less.

Optical fibers in which a slight improvement in polarization performance is achieved by distorting the core symmetry are disclosed in U.S. Patent No. 4,184,859 and in the publication by V. Ramaswamy et al., "Influence of Noncircular Core on the Polarization Performance of Single Mode Fibers", Electronics Letters, Vol. 14, No. 5, pp. 143-144, 1978. However,

the Ramaswamy publication reports that measurements on borosilicate fibers with noncircular cores indicate that the noncircular geometry and the associated stress-induced birefringence decrease L to about 5.5 cm and hence are not sufficient to improve polarization performance in single-mode fibers to the extent necessary to achieve polarization stabilized, single-mode propagation.

10 The inventions disclosed in U.S. Patents Nos. 4,179, 189 and 4,274,854 are based upon the recognition that orthogonally polarized waves are more efficiently decoupled in a waveguide that is fabricated in such a manner as to deliberately enhance stress-induced, or strain birefringence. Those patents teach that such behavior is accomplished by introducing a geometrical and material asymmetry in the preform from which the optical fiber is drawn. The strain-induced birefringence is introduced by at least partially surrounding the single-mode waveguide by an outer jacket having a
20 different thermal coefficient of expansion (TCE) than that of the waveguide and a thickness along one direction that is different from its thickness along a direction orthogonal to the one direction. Other fibers having stress-induced birefringence are taught in U.S. Patents No. 4,354,736 and 4,360,371.

30 The publication, H. Matsumura et al., "Fundamental Study of Single Polarization Fibers", Proc. Sixth European Conference on Optical Communication, University of York, U.K., September 1980, pp 49-52, describes a fiber of the type disclosed in the aforementioned U.S. Patent No. 4,360,371. Such a fiber exhibits a low beat length L because of both an anisotropic stress and a non-circular core. A minimum beat length of 0.77 mm

is reported for a fiber having a core of silica doped with 27 mole % GeO_2 , the core exhibiting an ellipticity of greater than 80%. However, such a fiber would possess an attenuation of approximately 20 dB/km or more, thus making it unsuitable for use as a long distance transmission line. This publication reports that a B_2O_3 -doped single polarization fiber suitable for use as a long distance transmission line exhibited a coupling length L of 1.5 mm.

10 A single-mode fiber having an azimuthally asymmetric refractive index profile to increase the difference between the propagation constants of the two orthogonal polarizations of the single mode signal is taught in the publication, T. Okoshi et al., "Single-Polarization Single-Mode Optical Fibre with Refractive-Index Pits on Both Sides of Core", Electronics Letters, Vol. 16, No. 18, August 28, 1980, pp 712-713. This publication describes a fiber having a circular central region which is divided into a central, rectangularly-
20 shaped core and circular segments of low index along the long sides of the central region. That fiber is reported to have a beat length of 2.3 mm.

 The stabilization of the polarization state in an optical waveguide has also been accomplished by employing an optically anisotropic single crystal as the light conducting medium. For example, see U.S. Patent No. 4,077,699 (Dyott et al.). That the birefringent properties of crystals may be explained in terms of the anisotropic electrical properties of the
30 molecules of which the crystals are composed is pointed out in the text: Born et al. Principles of Optics, Pergamon Press, New York (1975) pp 705-708. It is further stated that "form birefringence" may also arise

on a scale that is larger than molecular when there is an ordered arrangement of similar particles of optically isotropic material whose size is larger compared with the dimensions of molecules but small compared with the wavelength of light. Such a medium may be visualized as an assembly of thin parallel plates of thickness t_1 , dielectric constant ϵ_1 and refractive index n_1 immersed in a medium having a dielectric constant ϵ_2 and refractive index n_2 . The widths of the spaces between the plates is t_2 . After deriving the difference between dielectric constants parallel to the plates and normal to the plates, Born et al. conclude that the composite assembly behaves like a negative uniaxial crystal. The difference between the refractive indices n and n parallel to and normal to the plane of the plates, respectively, is given as

$$n_{\parallel}^2 - n_{\perp}^2 = \frac{f_1 f_2 (n_1^2 - n_2^2)^2}{f_1 n_2^2 + f_2 n_1^2} \quad (1)$$

where $f_1 = t_1 / (t_1 + t_2)$ and $f_2 = 1 - f_1$.

The aforementioned Dyott et al. patent indicates that an optical waveguide fiber having a crystalline core and glass cladding is subject to such defects as voids lying between the crystal and the glass. Also, since the cylindrical core must be formed as a single crystal, the formation of long lengths of such fiber is very difficult, 200mm lengths of defect-free crystal being mentioned in said Dyott et al. patent.

It is therefore an object of the present invention to provide an improved polarization stabilized or single polarization single-mode optical waveguide fiber.

Briefly, the present invention pertains to an optical fiber capable of operating single polarization, single-mode at a wavelength λ . The fiber includes a core member surrounded by a cladding member having an average refractive index lower than the average refractive index of the core member. The fiber is characterized in that one or both of the core and cladding members comprises a plurality of transparent laminae. Each of the laminae has a refractive index different from that of the adjacent laminae, and the thickness of each of the laminae is approximately equal to or less than the wavelength λ .

In the accompanying drawings:

Figure 1 is a cross-sectional view of an embodiment of the invention wherein both core and cladding are laminated.

Figure 2 is a cross-sectional view of a fiber wherein only the core is laminated and the cladding contains stress rods.

Figure 3 is an enlarged view of the core of the fiber of Figure 2.

Figures 4 and 5 are refractive index profiles taken through the axis of the core of Figure 3 in directions perpendicular to the laminae and along the laminae, respectively.

Figures 6 and 7 are illustrative of various alternative profiles which may be employed in place of those of Figures 4 and 5.

Figures 8 and 9 illustrate the cross-sectional configurations of two types of rectangular cores.

Figure 10 is a cross-sectional view of a fiber core having curved laminations.

Figure 11 is a graph wherein both the quantity $(n_{||}^2 - n_{\perp}^2)$ and beat length L are plotted as a function of n_1 for a specific value of n_2 .

Figure 12 is a cross-sectional view of a laminated optical fiber core containing an annular refractive index depression.

Figure 13 is a refractive index profile taken along the central lamina of Figure 12.

The present invention relates to an optical fiber in which form birefringence exists due to the fact that either the core or the cladding or both are constructed of substantially parallel, longitudinally extending laminae of transparent material, adjacent ones of which exhibit different refractive index. In addition, the fiber may contain birefringence caused by one or more of such other factors as stress, refractive index pits adjacent the core, and the like.

Referring to Figure 1 there is shown a fiber 14 comprising a core 15 of transparent material surrounded by a transparent cladding 18. Core 15 may be formed of a plurality of transparent laminae 17, adjacent ones of which are separated by transparent laminae 16. In an embodiment which is preferred from the standpoint of

ease of manufacturing, the core comprises the aforementioned laminated structure, and the cladding is either a homogeneous layer, or it consists of a plurality of concentric layers.

From the standpoint of performance, i.e., the ability to maintain the plane of polarization of an input signal, in addition to the laminated core 15, the cladding 18 should also be laminated. In Figure 1 the cladding comprises transparent laminae 20 separated by transparent laminae 19 of different refractive index than laminae 20. Cladding laminae 19 and 20 are perpendicular to core laminae 16 and 17. The birefringent properties of the core member 15 and the cladding member 18 can be characterized in terms of equation (1), and therefore, the thickness of any of the lamina 16, 17, 19 or 20 must be approximately equal to or less than the wavelength λ of the light to be propagated through the fiber. It is thought that a fiber would be effective for the purpose of maintaining the polarization of a propagated signal even if the laminae thicknesses were slightly greater than λ , although its performance would not be as effective as it would be if the thickness was equal to or less than λ .

Figure 2 illustrates an embodiment wherein the core 21 is a laminated structure comprising a plurality of alternately disposed laminae 23, 24 that extend parallel to the fiber axis. The refractive index of laminae 23 is different from that of laminae 24. Cladding 26 is a homogeneous material having a refractive index n_c that is lower than the average refractive index of laminae 23 and 24. Figure 2 also illustrates the use of stress rods 27, the birefringent effect of which may add to or subtract from the effect

produced by the laminated core. A birefringent effect is also induced by the stress caused by employing alternate laminae which have different TCE.

Figure 3 is an enlarged view of core 21, the diameter of which is 2a. The thickness of laminae 23 is shown to be t_1 , the refractive index thereof being n_1 . The thickness of laminae 24 is shown to be t_2 , the refractive index thereof being n_2 . The refractive index of the cladding material surrounding the core is n_c , as shown in Figure 2.

Refractive index profiles taken through the core axis in a direction perpendicular to the laminae and along the laminae are illustrated in Figures 4 and 5, respectively. The dashed line marked n_{av} , which is the average refractive index of the core due to the contributions of laminae 23 and 24, is somewhat higher than the cladding refractive index n_c .

Figures 6 and 7 are intended to be illustrative of various profiles which satisfy the requirements of the present invention. Whereas all of the lamina 23 are shown by Figure 4 to have a refractive index n_1 , these lamina could have different refractive indices as shown in Figure 6, wherein the core refractive index is plotted as a function of radius. Also, as shown in Figure 7, the refractive index within a lamina can be any non-step profile including any α -type profile or other gradation. Figure 7 also shows that the refractive index within a lamina can increase as a function of distance from the center of the lamina as shown by curve 28, or it can decrease or follow some other function of distance as indicated by curves 29 and 30.

The circularly-shaped core 21 of Figures 2 and 3 is a convenient shape for coupling light from certain

sources to the fiber. However, other core shapes such as elliptical or rectangular may be employed in the fiber of the present invention. Figures 8 and 9 illustrate two rectangular shapes. In Figure 8, laminae 31 and 32 form a rectangularly-shaped core having regions 33 of transparent material on opposite sides thereof. Regions 33 can be formed of a material having a refractive index n_3 which is lower than the cladding refractive index, in which case they are known as refractive index pits. As taught in the aforementioned Okoshi et al. publication, such refractive index pits function to create a birefringence, and such birefringence can add to the effect of the laminated core. Similarly, regions 36 of transparent material are located on opposite sides of the rectangular core illustrated in Figure 9. In addition, Figure 9 illustrates that the overall shape of the core and adjacent refractive index pits may be elliptical. Whereas laminae 31 and 32 of Figure 8 are parallel to the long dimension of the rectangular core, laminae 37 and 38 are perpendicular thereto. Also, regions 33 and 36 of Figures 8 and 9 could be omitted, in which case they would be replaced by cladding material. Some of the possible combinations of the refractive indices of various parts of the fiber are listed in Table 1.

TABLE 1

Some Possible Refractive Index Combinations

- a) $n_1 > n_2 > n_c$
- b) $n_1 > n_c > n_2$
- c) $n_2 > n_1 > n_c$
- d) $n_2 > n_c > n_1$
- e) $n_1 > n_2 > n_c > n_3$
- f) $n_1 > n_2 > n_3 > n_c$

10 In accordance with the present invention the various portions of the fiber, including the core laminae, can be formed of any transparent material having the required refractive index, provided that such material can be formed into a fiber. Examples of such transparent material are glass, plastic, crystalline material and combinations thereof. For example, low temperature glasses of the type disclosed in U.S. Patents Nos. 4,285,730 and 4,362,819 could be laminated with plastic material. Also, one or more of the lamina could be dye-doped and thereby function as an optically
20 active medium suitable for use as a laser or amplifier.

As stated previously, the thicknesses of the laminae which constitute the core and/or the cladding should be approximately equal to or less than the wavelength of light to be propagated through the fiber during operation thereof as a polarization stabilized or single polarization single-mode fiber. The minimum effective thicknesses of the laminae are diffusion limited and must therefore be greater than 100 angstroms.

30 The following theoretical example illustrates the manner in which fibers designed in accordance with the

-11-

present invention can achieve submillimeter beat lengths. Assume that the fiber is to be operated at a wavelength of 632.8 nm. The core is constructed in accordance with Figure 8, and the cladding is a homogeneous layer of glass having a refractive index of 1.46. The core diameter is 6.0 μm and w , the smaller dimension of the rectangular core is 3.0 μm . The thicknesses t_1 and t_2 are assumed to be equal, the maximum permissible value thereof being about 0.63 μm in view of the operating wavelength. Laminae 31 have a refractive index of about 1.5. Laminae 32 have a refractive index of about 1.45. The ratio $t_1/(t_1+t_2)$ is 0.5, and the average refractive index n_{av} is therefore about 1.475. Refractive index pits 33, which have a thickness of 1.5 μm , exhibit a refractive index of about 1.445. The aforementioned refractive index values can be obtained by adding to silica appropriate amounts of one or more dopants such as GeO_2 , P_2O_5 , Al_2O_3 , B_2O_3 and F. Other optical quality glasses which could provide the necessary refractive indices are also known.

If the operating V-value is assumed to be 3, the following birefringence characteristics of the fiber can be estimated, assuming that the two types of birefringence that are considered are additive. It is noted that the cutoff V-value would be about 4 in order to obtain single-mode operation. The quantity $(n_{||}^2 - n_{\perp}^2)$ is plotted in Figure 11 as a function of the refractive index n_1 for fibers in which the value of n_2 is 1.45. Three different curves are plotted for the parameter $f_1 = 0.1, 0.25$ and 0.5 . The beat length L of the fiber operated at 632.8 nm is the ordinate expressed along the right side of the graph. The uppermost curve

indicates that at f_1 equal to 0.5 and n_1 equal to 1.55, the beat length is about 0.8 mm. It is noted that the quantity $(n_H^2 - n_L^2)$ is about 2.5×10^{-3} for this value of beat length.

10 The waveguide effect caused by the generally rectangular core having low index pits on opposite sides there of (see the above-identified Okoshi et al. publication) results in a beat length of about 2.3 mm. If the form birefringence and that due to the refractive index pits are additive, the fiber beat length at 632.8 nm will be about 0.5 mm. It is noted that stress birefringence effects are not considered in this example. The addition of stress rods such as those illustrated in Figure 3 could result in an even lower beat length.

20 Fibers of the type illustrated in Figure 1 could be fabricated by forming a preform of slabs of glass having the appropriate refractive index. The widths and thicknesses of the glass slabs would be proportional to the widths and thicknesses of the lamina in the resultant fiber. The preform so formed could be heated at one end and drawn into a fiber.

30 To form a fiber wherein only the core is laminated, slabs of glass having the appropriate refractive index can be stacked as indicated above and then drawn into an intermediate fiber having an average diameter in the range of about 4 to 10 mm. This drawing operation will cause adjacent slabs to adhere to one another. The outer surface of the resultant intermediate fiber can be ground and polished to the desired cross-sectional configuration such as circular. It can then be provided with a layer of cladding glass by inserting it into a tube or by rotating it in a lathe

while directing thereon a stream of glass soot as taught in U.S. Patent No. 4,360,371.

Another method of fabrication is disclosed in U.S. Patent Application Serial No. entitled "Method of Forming Optical Fiber Having Laminated Core" (A. Sarkar) filed on even date herewith.

10 The potentially high bandwidth of single-mode optical fibers can be achieved only if the total dispersion for the HE_{11} mode is equal to zero or as near as possible to zero at the operating wavelength. Copending application Serial No. 328,369 entitled "Low Dispersion, Low-Loss Single-Mode Optical Waveguide" filed on December 7, 1981 and the continuation-in-part application Serial No. filed teaches a fiber design which results in dispersion minimization over a wide wavelength range. The technique employed in said copending application can be utilized in combination with the laminated core design described hereinabove to achieve low dispersion, polarization
20 stabilized, single-mode propagation. The core of such a fiber is illustrated in Figure 12. Circular core 70 is formed of laminae 72, adjacent ones of which are separated by laminae 74 of different refractive index. One or more regions of depressed refractive index may exist within the core, as taught in said copending application, to reduce dispersion or to provide low dispersion operation over a wide band of wavelengths. In Figure 12 the depressed refractive index region is in the form of an azimuthally symmetric ring 76. As
30 shown in Figure 13, which is the refractive index profile of centrally located lamina 74, the refractive index n_1 of lamina 74 may decrease to a value of n_d in region 76. The dashed line in Figure 13 is

illustrative of the fact that the refractive index n_d of region 76 can be lower than the cladding refractive index n_c . Whereas the index depression is shown in Figure 13 as being flat, it can be any shape such as rounded or V-shaped. Region 76 could also be azimuthally asymmetric. Furthermore, there may be more than one region of depressed refractive index. An index depression may be superimposed on any type of lamina index profile. For example, any of the profiles 28, 29 or 30 of Figure 7 could have superimposed thereon one or more index depressions of the type described above. Whereas the thicknesses of the core laminae must be no greater than approximately the wavelength λ to be propagated through the fiber, the width s of the index depression must be greater than λ .

CLAIMS:






1. An optical fiber capable of operating polarization stabilized or single polarization, single-mode at a wavelength λ , said fiber having a core member surrounded by a cladding member having an average refractive index lower than the average refractive index of said core member, said fiber being characterized in that one or both of said core and cladding members comprises a plurality of transparent laminae, each of said laminae having a refractive index different from that of the adjacent laminae, the thickness of each of said laminae being approximately equal to or less than the wavelength λ .
2. A fiber in accordance with claim 1 wherein said core is circular.
3. A fiber in accordance with claim 1 wherein said core is non-circular.
4. A fiber in accordance with claim 1 wherein said core is rectangular.
5. A fiber in accordance with claim 4 wherein said core laminae extend parallel to the long side of said core.
6. A fiber in accordance with claim 4 wherein said core laminae extend perpendicular to the long side of said core.






7. A fiber in accordance with claim 1 wherein said laminae are flat.




8. A fiber in accordance with claim 1 wherein said laminae are curved.

9. A fiber in accordance with claim 1 wherein the refractive index of one type of said core laminae is less than the average refractive index of said cladding.

10. A fiber in accordance with claim 1 wherein, at least those lamina, which are located in the central region of the core and which have a refractive index greater than that of the laminae adjacent thereto, have at least two off axis regions of depressed refractive index, the widths of said depressed refractive index regions being greater than λ .

*Fig. 1**Fig. 2**Fig. 3**Fig. 4**Fig. 5*

*Fig. 6**Fig. 7**Fig. 8**Fig. 9**Fig. 10*

*Fig. 11**Fig. 12**Fig. 13*