

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 156 536
A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 85301438.9

(51) Int. Cl.⁴: E 04 D 5/12

(22) Date of filing: 01.03.85

(30) Priority: 23.03.84 US 592620
23.03.84 US 592711

(43) Date of publication of application:
02.10.85 Bulletin 85/40

(84) Designated Contracting States:
DE FR GB IT

(71) Applicant: MINNESOTA MINING AND
MANUFACTURING COMPANY
3M Center, P.O. Box 33427
St. Paul, MN 55133(US)

(72) Inventor: Levens, Dennis L. c/o Minnesota Mining and
Manufac. Company 2501 Hudson Road P.O. Box 33427
St. Paul Minnesota 55133-3427(US)

(72) Inventor: Renstrom, Richard L. c/o Minnesota Mining
and
Manufac. Company 2501 Hudson Road P.O. Box 33427
St. Paul Minnesota 55133-3427(US)

(74) Representative: Baillie, Iain Cameron et al,
c/o Ladas & Parry Isartorplatz 5
D-8000 München 2(DE)

(54) Spliceable sheet material and transfer tape for use in making same.

(57) Heat-sealable sheet material for use in the fabrication of lapped-seam membranes. In a presently preferred construction, linear low density polyethylene film is adhered to one lateral border of cured polymerized EPDM composition; preferably the adhesive is protected with a removable liner, e.g., a polyester film until lapped-seam splicing is to be carried out. A transfer tape based on thermoplastic heat-sealable adhesive carried by a strippable liner also constitute part of the invention. The transfer tape is advantageously applied to a sheet of uncured EPDM compound and the resultant assembly subjected to heat and pressure to cure the compound and bond the heat-sealable adhesive firmly thereto.

EP 0 156 536 A2

0156536

**SPLICEABLE SHEET MATERIAL AND TRANSFER
TAPE FOR USE IN MAKING SAME**

Background of the Invention

This invention relates to the sealing of
5 overlapped rubbery olefinic polymer (i.e., homopolymer,
copolymer, terpolymer, etc.) sheets to each other, to
spliceable sheets, to a method of making such sheets, and
to a transfer tape having particular utility in the
manufacture of the heat-sealable sheets.

10 Rubberly olefinic polymer sheet material finds
widespread industrial use in applications where it is
necessary to contain or exclude liquids. Compared to vinyl
sheet material, the rubbery olefinic polymer sheet
materials have longer life, greater flexibility and
15 resilience at low temperatures, ability to withstand high
temperatures without stretching or softening unduly, and
superior resistance to ultraviolet light. The most widely
used rubbers for formulating these sheets are polymers of
ethylene, propylene, and diene monomers (commonly known as
20 EPDM), butyl rubber, and blends of the two. In making
rubbery sheet material, the olefinic polymers are commonly
blended with desired fillers, coloring agents, extenders,
vulcanizing or crosslinking agents, antioxidants, etc. to
form a "compound", which is then calendered or extruded
25 into sheets (commonly known as "membranes"), typically on
the order of 1.5 millimeters thick and 2 to 6 meters wide.
These membranes are then heated to perhaps 150°C. for 2
hours to effect vulcanization.

For many of the applications in which rubbery
30 membranes are employed, it is necessary to overlap and
splice the edges of a large number of sheets. Rubbers,
which have low energy surfaces, are unreceptive to many
adhesives. Accordingly the splicing procedure has
heretofore typically involved the steps of cleaning the
35 overlapped areas, applying a primer solution to each face,
allowing the solvent to evaporate, applying a contact

0156536

adhesive solution to each face, again allowing the solvent to evaporate to leave a tacky adhesive surface, mating the contact adhesive-coated surfaces, and compacting the spliced area with a heavy steel roller. Operating in this way, it is possible to form extremely large spliced membranes which can be used to line water reservoirs, irrigation canals, sewage lagoons, industrial waste pits, and solar energy ponds; such products are popularly designated "geomembranes". The splicing process is, however, extremely labor-intensive and costly.

Another important application for spliced rubbery membranes is in the installation of flat roofs for commercial, institutional, and industrial buildings. Spliced membranes are laid over new or existing roofs and typically either fastened down (e.g., at 40-centimeter intervals) with metal battens or ballasted with round river-washed stones. When employed on a roof, extremely rigorous demands are placed on the rubbery membranes, particularly on the splices. Roof temperatures may approach the boiling point of water when exposed to the summer sun, and they may sink to -30°C . -- or even lower -- during the winter.

In all of the applications for spliced membranes just described, the splicing has been a tedious and time-consuming part of fabrication. How to simplify the preparation of lapped splices has remained an unsolved problem.

Brief Description of the Invention

The present invention provides an easy, simple, rapid, and effective technique for splicing rubbery membranes to form larger membranes. The resultant splices are strong, resistant to temperature extremes, and able to withstand the expansion and contraction that results from exposure to summer and winter conditions, all the while maintaining a water-tight seal.

0156536

One aspect of the invention relates to spliceable sheet material having particular utility in the fabrication of lapped-seam membrane roofing, comprising in combination a rubbery water-impermeable membrane consisting essentially of thermoset olefinic polymer having on one side, at least in a border area along one edge, a thin layer of firmly bonded heat-sealable adhesive of a type that wets the membrane. A presently preferred material for the rubbery olefin polymer membrane is EPDM, and a presently preferred adhesive is linear low density polyethylene having a softening point (as defined in ASTM Test D-16, Procedure 19) of at least 80°C., preferably 100°C., and most preferably at least 120°C. (It should be recognized that the term "polyethylene" may include the normally employed stabilizers, fillers, extenders, processing aids, pigments, and the like.) Other suitable adhesives can be formulated from thermoplastic blends of polyethylene and polypropylene, homopolymers of olefin monomers, polymers of two or more olefin monomers, etc., provided that the softening point meets the stated temperature requirement. To enhance processability, the melt index of the adhesive is desirably at least 0.5 dl/g, a melt index of about 1 being presently preferred. For convenience in use, the softening point of the heat-sealable adhesive should not exceed 250°C., and preferably is significantly lower, to minimize the possibility of degrading the rubbery membrane.

A presently preferred spliceable sheet material of the type described in the preceding paragraph is one in which linear low density polyethylene is adhered to the border area on one side of the rubbery sheet material adjacent a lateral edge and also on the border area on the other side adjacent the opposite lateral edge, this arrangement lending itself to a natural shingling type of overlapping.

A simple but unique transfer tape having particular utility in making the spliceable border areas of the sheet material just described comprises a release liner having strippably adhered to one face a thin layer of heat-

Q156536

sealable adhesive. A preferred transfer tape construction comprises a polyester film release liner, e.g., biaxially oriented polyethylene terephthalate, carrying a heat-sealable thermoplastic polyolefin layer, e.g., linear low density polyethylene. Spliceable rubbery sheet material may then conveniently be fabricated by placing the adhesive surface of the transfer tape in contact with the appropriate area or areas of the rubbery membrane and applying sufficient heat and pressure to melt the adhesive and bond it to the membrane. A particularly preferred method is to place the transfer tape in contact with the unvulcanized sheet material, apply sufficient pressure to maintain intimate contact between the tape material and heat the assembly to a temperature high enough to vulcanize (i.e., crosslink, or thermoset) the olefin polymer and, at the same time, soften the adhesive, thereby permitting it to wet and upon cooling, bond firmly to the olefinic polymer sheet. The release liner may then remain in place to protect the adhesive from contamination and be removed at the time a splice is to be made.

Because it is difficult, expensive, and time-consuming to conduct field evaluations of products made in accordance with the invention, a number of tests have been developed to provide information that relates directly to some aspect of roofing end use requirements. These tests, which incorporate built-in safety factors, are briefly described below.

1. T-Peel Test. In this test, two 2.54-cm wide x 15-cm long x 1.14-mm thick strips of commercially available EPDM-based membrane, each provided with a 38-micrometer layer of heat-activatable adhesive, are superposed in coextensive adhesive-to-adhesive contact and approximately 5 cm at one end laminated for one minute in a press at 160°C. and 20 kPa. Conventional T-peel tests are then performed in tensile testing equipment in which the jaws are separated at a rate of 30.5 cm/minute. For roofing applications, initial values should be at least 8.8 N/cm

0156536

when tested at room temperature. After being subjected to any one of the conditions described below and then re-tested, T-peel values should be at least 17.5 N/cm.

- 5 a. Temperature Cycling. T-peel samples are exposed to room temperature for one week, -18°C. for one week, room temperature for another week, -18°C. for one week, and then tested.
- 10 b. Hot Water Immersion. Two hours after being prepared, T-peel samples are immersed for 24 hours in 70°C. water, removed, dried, and tested at room temperature.
- 15 c. Delayed Hot Water Immersion. 24 hours after being prepared, the T-peel samples are immersed in 70°C. water for 24 hours, removed, and tested as in sub-paragraph "b".
- 20 d. High Humidity. T-peel samples are exposed to 38°C. and 100% relative humidity for one week, removed, dried, and tested at room temperature.
- 25 e. Heat Aging. Samples are placed in a 70°C. oven for one week, removed, and tested at room temperature.
- f. Heat Resistance. T-peel samples are heated as in sub-paragraph "e" but tested at 70°C.
- 30 g. Weather Resistance. Samples are exposed to the artificial weathering conditions provided by a "Weatherometer" machine in accordance with ASTM Test D-750. Tests are performed after 250 and 500 hours.

h. Freeze-Thaw Resistance. T-peel samples are immersed in room temperature water for one week and then placed in a -18°C . freezer for one week. They are removed and tested at room temperature.

5

2. Softening Point. Strips of the heat-sealable roofing membrane 2.54 cm wide are overlapped 2.54 cm adjacent one end of each and bonded for one minute, adhesive-to-adhesive, in a 160°C . press at a pressure of 20 kPa. The spliced strip is then removed and tested in accordance with a modified form of ASTM-D816 Procedure 19. In this test, the end of one strip is gripped between the jaws of a holder, the remainder of the spliced strip extending vertically, with a 2.27-kg weight attached to the free end. The assembly is then placed in a 65°C . oven and the temperature raised $0.5^{\circ}\text{C}/\text{minute}$ until failure occurs; the acceptable threshold temperature is 120°C .

10

15

3. Dynamic Shear. Samples, prepared as in the softening point test, are mounted in a tensile testing machine, the jaws of which are separated at the rate of 1.3 mm/minute until failure occurs. A force of 275 kPa or more is considered acceptable.

20

4. Static Shear. Lap-spliced samples are prepared as in the preceding two tests. One end of the spliced sample is gripped in the jaws of a holder, with the remainder of the sample extending vertically. To the free end is then attached a 2.27-kg weight and the assembly placed in an 82°C . oven. Failure should not occur in less than 24 hours.

25

5. Low Temperature Flexibility. Two 2.54 cm x 12.5 cm strips of heat-sealable roofing membrane are superposed in adhesive-to-adhesive contact and bonded in a 160°C . press under a pressure of 20 kPa for one minute. The

30

0156536

resulting laminate is conditioned in a freezer maintained at -34°C . for 24 hours. An operator, wearing gloves to avoid heating the samples, then bends the sample around a 1.27-cm. diameter refrigerated steel rod, removes it, and
5 bends it in the opposite direction around the rod, repeating the cycle five times. No evidence of delamination should occur.

Detailed Description

The invention will now be described with the aid
10 of illustrative but non-limiting examples, in which all parts and percentages are by weight unless otherwise indicated.

Example 1

A linear low density polyethylene (Union Carbide
15 "G-Resin 7047 Natural 7"), having a melt index of 1.0, was extruded through a slot die having an opening of 0.56 mm at a die head temperature of 250°C . Immediately after emerging from the die, the extruded polyethylene film was contacted by a 38-micrometer polyester film; the resulting laminate
20 was pulled between a rubber roll and metal roll, located approximately 75 mm from the die opening. The rolls were driven at a considerably faster surface speed than the rate at which the polyethylene was extruded, so that the polyethylene thickness was reduced to approximately 90
25 micrometers. Samples approximately 75 mm x 100 mm were then cut from the laminate and used for further testing. The polyethylene was tack-free at room temperature.

A sample of the laminate was positioned with the polyethylene layer against a smooth sheet of 1.5-mm cured
30 EPDM rubber, and placed for 30 seconds in a press heated to 218°C . under a pressure of approximately 35 kPa. The sample was then removed from the press and allowed to cool to room temperature, after which the polyester release liner was stripped away, exposing the heat-sealable polyethylene
35 surface. The stripping force required was about 0.03 N/cm

0156536

width. Values of at least about 0.02 N/cm are desirable for ease in processing, values somewhat in excess of 0.1 N/cm being satisfactory but not preferred. Significantly higher stripping values make the product more difficult for
5 the end user to remove the release liner.

Example 2

A polyethylene-polypropylene blend (Eastman Chemical Company "Tenite" 5321E polyallomer) was extruded through a 0.38-mm 240°C. die head and processed as in
10 Example 1.

The adhesive-coated EPDM products made in accordance with the preceding examples were then tested in accordance with the previously described procedures. Results are tabulated below:

0156536

TABLE I

	<u>Test</u>	<u>Acceptable</u>	<u>Example</u>	
			<u>1</u>	<u>2</u>
	1. <u>T-Peel, N/cm</u>			
5	a. Initial	8.8	35*	35*
	b. Temperature Cycling	17.5	35*	35*
	c. Hot Water Immersion	17.5	35*	35*
	d. Delayed Hot Water Immersion	17.5	35*	35*
10	e. High Humidity	17.5	35*	35*
	f. Heat aging	17.5	35*	35*
	g. Heat Resistance	17.5	35*	35*
	h. Weather Resistance	17.5	35*	35*
	i. Freeze-Thaw Resistance	17.5	35*	35*
15	2. <u>Softening Point, °C.</u>	= 120	127*	162*
	3. <u>Dynamic Shear, N/cm</u>	70	90*	90*
	4. <u>Static Shear, Hours</u>	= 24	168	168
	5. <u>Low Temperature Flexibility</u>	No delamin- ation	No delamin- ation	No delamin- ation
20				

* Failure occurred within the rubber, the splice remaining intact.

In factory production operations, it has been found convenient to apply the lined heat-sealable adhesive directly to the uncured EPDM rubber membrane in 5.0 - 7.5-cm strips along the border of one side adjacent the edge. The assembly is then subjected to 375 kPa pressure at 150°C. to cure the EPDM rubber and simultaneously bond the heat-sealable adhesive firmly thereto. Workers in the field lay out the rubber membrane in a manner such that the heat-sealable portion of one

0156536

strip of material overlaps the edge of an adjacent strip of material, after which they remove the liner. Heat is then applied, either directly to the adhesive or to the opposite side of the adhesive-bearing rubber membrane in the splice
5 area, to soften the adhesive and cause it to bond firmly to the underlying edge of the adjacent strip.

In circumstances where the rubber membrane has an embossed or irregular surface, adhesion in the splice area will be enhanced if confronting border portions of the
10 overlapped strips are both provided with a heat-sealable coating. This construction can be achieved during factory production by making sure that a first heat-sealable transfer tape is positioned on one side adjacent one edge and a second heat-sealable transfer tape is positioned on
15 the other side adjacent the second edge.

In some circumstances, it may be advantageous to coat one entire side of the rubber membrane with heat-sealable coating. With completely coated membranes of this type, rolls of the membrane may be slit to any desired
20 width, e.g., to fit narrow portions of a roof, while still maintaining heat-sealable coating adjacent each edge.

Another advantage achieved by overall coating with heat-sealable adhesive is the ability to seal directly to the upper surface of batten strips that have been nailed or
25 otherwise affixed to the roof substrate, thereby permitting completely imperforate roofing membrane construction. For such purposes, it is advantageous to use batten strips made of polyethylene, which are not only moisture- and rust-resistant but also inherently possess heat-sealable
30 properties and are compatible with the thermoplastic olefinic heat-sealable coating on the roofing membrane.

If, of course, the polyethylene batten strips are used only in the spliced areas, it is adequate to have heat-sealable adhesive only in the border area of the lower membrane,
35 where it will contact the batten strip.

It will be appreciated that varying the composition of the rubber membrane may make it desirable to

0156536

modify the heat-sealable adhesive composition. Also, as indicated earlier in the discussion of this invention, the performance requirements for roof construction are somewhat more strenuous than may be required for such other applications as pond or swimming pool liners; for such uses, other heat-sealable adhesives should be able to perform effectively. Those skilled in the art will, however, have no difficulty in determining suitable adhesives to be employed in appropriate circumstances, considering the foregoing discussion.

CLAIMS

0156536

1. A spliceable sheet material having particular utility for use in the fabrication of lapped-seam membrane roofing, comprising in combination:

5 a rubbery water-impermeable membrane consisting essentially of thermoset olefin polymer, said membrane having on one side, at least in a border area along one edge, a thin layer of firmly bonded heat-sealable adhesive that is capable of
10 wetting the thermoset olefin polymer and that has a softening point of at least about 80°C..

2. The sheet material of claim 1 wherein the heat-sealable adhesive has a softening point of at least
15 100°C.

3. The sheet material of claim 1 wherein the heat-sealable adhesive has a softening point of at least 120°C. but not more than 250°C.

4. The sheet material of claim 3 wherein the
20 olefin polymer consists essentially of polymerized ethylene, propylene, and diene monomers (EPDM).

5. The sheet material of claim 4 wherein the heat-sealable adhesive is linear low density polyethylene having a melt index of about 1.0.

25 6. The sheet material of claim 1 wherein the heat-sealable adhesive is protectively covered by a strippable liner.

7. A transfer tape comprising a release liner having strippably bonded to one face a thin layer of
30 thermoplastic heat-sealable adhesive.

0156536

8. The transfer tape of claim 7 wherein the release liner is a film of biaxially oriented polyethylene terephthalate and the adhesive is a polyolefin having a softening point of at least 80°C..

5 9. A spliced membrane made by overlapping the adjacent borders of the sheet material of claim 1, so that the heat-sealable adhesive is interposed between the two thermoset olefin polymer membranes, and applying sufficient heat and pressure to bond the overlapped borders to each
10 other.

10. The spliced membrane of claim 9 wherein the T-peel values of the spliced borders are at least equal to 17.5 N/cm, the dynamic shear is at least 70 N/cm, the softening point is at least 120°C., the static shear is at
15 least 24 hours, and the low temperature flexibility requirements are satisfactory, all as measured in accordance with the tests described herein.

11. A method of making the spliceable sheet material of claim 1 comprising the steps of:

- 20 a. obtaining an uncured but curable sheet of polyolefinic compound,
b. placing in contact with a lateral border on one side of said sheet a transfer tape comprising a thermoplastic olefinic layer carried by a strippable release liner, the
25 olefinic layer of the tape having a softening point of at least 80°C, and being in contact with said sheet, to form an assembly,
c. subjecting said assembly to elevated pressure and temperature for a time sufficient to cure
30 said compound and firmly bond the heat-sealable thermoplastic olefinic layer to the cured sheet material, said release liner remaining in position until said sheet
35 material is to be spliced, at which time it is removed.