(1) Publication number:

0 170 091

**A1** 

(12)

#### **EUROPEAN PATENT APPLICATION**

(21) Application number: 85108260.2

(51) int. Ci.4: C 11 D 17/00

(22) Date of filing: 07.02.83

(30) Priority: 05.02.82 GB 8203398 13.04.82 GB 8210670

02.07.82 GB 8219227 23.12.82 GB 8236664

- (43) Date of publication of application: 05.02.86 Bulletin 86/6
- Designated Contracting States:
   AT BE CH DE FR GB IT LI LU NL SE
- Publication number of the earlier application in accordance with Art. 76 EPC: 0 086 614

- (7) Applicant: Albright & Wilson Limited
  Albright & Wilson House Hagley Road West
  Oldbury Warley West Midlands, B68 ONN(GB)
- 72 Inventor: Akred, Brian John 12 Cross Lane Whitehaven Cumbria CA28 6TW(GB)
- (72) Inventor: Messenger, Edward Tunstall Ramsey House Camerton Workington Cumbria(GB)
- (72) Inventor: Nicholson, William John 24 Earls Raod Bransty Whitehaven Cumbria(GB)
- (4) Representative: Savidge, Roger Gordon
  Madgwick et al,
  c/o Albright & Wilson Limited 1 Knightsbridge Green
  London SW1X 7QD(GB)

54 Liquid detergent compositions.

(57) Pourable, fluid, non sedimenting, laundry detergent composition, comprising water, surfactant, builder, a surfactant desolubilising electrolyte and, optionally, the usual minor ingredients, consist essentially of: at least one predominantly aqueous liquid phase which is separable into a distinct layer by centrifuging the composition at 800 times normal earth gravity at 25°C for 17 hours, and which contains at least part of the electrolyte and one or more other phases which together contain at least part of the builder as solid particles dispersed in the composition and at least part of the surfactant.

The present invention relates to novel, aqueous-based, pourable, fluid detergent compositions containing effective quantities of detergent builder. It is a divisional of Application No. 83300605.9, published as E.P.A. 0086614.

## DEFINITIONS

The term "builder" is sometimes used loosely in the detergent art to include any non-surfactant whose presence in a detergent formulation enhances the cleaning effect of the formulation. More usually, however, the term is restricted to those typical "builders", which are primarily useful as a means of preventing or ameliorating the adverse effects on washing of calcium and magnesium ions e.g. by chelation, sequestering, precipitation or absorption of the ions, and secondarily as a source of alkalinity and buffering. The term "Builder" is used herein in the latter sense, and refers to additives which ameliorate the aforesaid adverse effects to a substantial extent. It includes sodium or potassium tripolyphosphate and other phosphate and condensed phosphate salts such as sodium or potassium orthophosphates, pyrophosphates, metaphosphates or tetraphosphate, as well as phosphonates such as acetodiphosphonates, amino tris methylene phosphonates and ethylenediamine tetramethylene phosphonates. It also includes alkali metal carbonates, zeolites and such organic sequestrants as salts of nitrilotriacetic acid, citric acid and ethylene diamine tetracetic acid, polymeric polycarboxylic acids such as polyacrylates and maleic anhydride based copolymers.

For the avoidance of doubt, "Builder" is used herein to include water soluble alkali metal silicates such as sodium silicate, but excludes additives such as carboxymethyl cellulose, or polyvinyl pyrrolidone whose function is primarily that of soil suspending or anti-redeposition agent.

"Electrolyte" is used herein to denote those water soluble ionic compounds which dissociate at least partially in aqueous solution to provide ions, and which tend to lower the solubility or micellar concentration of surfactants in such solutions by a "salting out"

effect. It includes water soluble dissociable, inorganic salts such as, for example alkali metal or ammonium, chlorides, nitrates, phosphates, carbonates, silicates, perborates and polyphosphates, and also certain water soluble organic salts which desolubilise or "salt out" surfactants. It does not include salts of cations which form water insoluble precipitates with the surfactants present.

"Hydrotrope" denotes any water soluble compound which tends to increase the solubility of surfactants in aqueous solution. Typical Hydrotropes include urea and the alkali metal or ammonium salts of the lower alkyl benzene sulphonic acids such as sodium toluene sulphonate.

As used herein "Soap" means an at least sparingly water soluble salt of a natural or synthetic aliphatic monocarboxylic acid, which salt has surfactant properties. The term includes sodium, potassium, lithium, ammonium and alkanolamine salts of C8-22 natural and synthetic fatty acids, including stearic, palmitic, oleic, linoleic, ricinoleic, behenic and dodecanoic acids, resin acids and branched chain monocarboxylic acids.

The "Usual Minor Ingredients" includes those ingredients other than Water, Active Ingredients, Builders and Electrolytes which may be included in laundry detergent compositions, typically in proportions up to 5%, and which are compatible in the relevant Formulation with a pourable, chemically stable Non-sedimenting composition. The term includes antiredeposition agents, perfumes, dyes, optical brightening agents, Hydrotropes, solvents, buffers, bleaches, corrosion inhibitors, antioxidants, preservatives, scale inhibitors, humectants, enzymes and their stabilizers, bleach activators, and the like.

As used herein "Functional Ingredients" means ingredients which are required to provide a beneficial effect in the wash liquor and includes ingredients which contribute to the washing effectiveness of the composition e.g. surfactants, Builders,

bleaches, optical brighteners, buffers, enzymes and antiredeposition agents, and also anti-corrosives but excludes water,
solvents, dyes, perfume, Hydrotropes, sodium chloride, sodium
sulphate, solubilisers and stabilisers whose sole function is to
impart stability, fluidity or other desirable characteristics to a
concentrated formulation. "Payload", means the percentage of
Functional Ingredients based on the total weight of the composition.
"Active Ingredients", means surface active materials.

All references herein to "Centrifuging", unless stated to the contrary, are to be construed as referring to centrifuging at  $25^{\circ}$ C for 17 hours at 800 times normal gravitational force.

The expression "Separable Phase" is used herein to denote phases which are each separable from the mixture to form a distinct layer upon Centrifuging. Unless the context requires otherwise all references to the composition of Separable Phases are references to the compositions of the centrifugally separated phases and references to the structure of a composition relate to the uncentrifuged composition. A single Separable Phase may comprise two or more thermodynamically distinct phases, which are not separable from each other on Centrifuging as in, for example, a stable emulsion.

"Dispersed" is used herein to describe a phase which is discontinuously distributed as discrete particles or droplets in at least one other phase. "Co-continuous" describes two or more interpenetrating phases each of which extends continuously through a common volume, or else is formed of discreet elements which interact to form a continuous matrix tending to maintain the position and orientation of each element in relation to the matrix when the system is at rest. "Interspersed" describes two or more phases which are either Co-continuous or of which one or more is Dispersed in the other or others.

References to solid phases are to substances actually present in the composition in the solid state at ambient temperature, and including any water of crystallization or hydration unless the context requires otherwise. A "Solid Layer" is a solid, pasty or non-pourable gelatinous layer formed on Centrifuging.

"Total Water" refers to water present as liquid water in a predominantly aqueous phase, together with any other water in the composition, e.g. water of crystallisation or hydration or water dissolved or otherwise present in any predominantly non-aqueous phase. "Dry Weight" refers to residual weight after removal of Total Water and also of any solvent which has a boiling point below 110°C.

The term "Formulation" is used to describe the combination of ingredients which make up the Dry Weight of a composition. Thus the same Formulation may be exemplified by a number of compositions, differing in their Percentage Dry Weight.

All references herein to viscosities unless otherwise stated are to the viscosity as measured on a cup and bob viscometer at 25°C after two minutes running using a 20 mm internal diameter flat bottomed cup, 92 mm long, and a 13.7 mm diameter bob, 44 mm long, with conical ends having a 45° horizontal angle, and 4mm diameter spindle, rotating at 350 rpm. The tip of the bob was 23mm from the base of the cup. This corresponds to Contraves "Rheomat 30" viscometer using measuring system C at speed setting 30. These conditions are un-suitable for measuring viscosities greater than 12 Pascal Seconds at which partial loss of contact between the bob and the sample may arise.

"Pourable" as used herein means having a viscosity of less than 11.5 Pascal Seconds.

"L1" phase denotes a fluid, isotropic, micellar solution of surfactant in water, which occurs at concentrations between the critical micellar concentration and the first lyotropic mesophase, wherein the surfactant molecules aggregate to form spherical or rod shaped micelles.

"G" phase refers to a liquid crystal phase of the type, also known in the literature as "neat phase" or "lamellar phase" in which the surfactant molecules are arranged in parallel layers of indefinite extent separated by layers of water or an aqueous solution. The layers may be bilayers or interdigited layers of surfactant. The "G" phase for any given surfactant or surfactant mixture normally exists in a narrow range of concentrations. Pure "G" phases can normally be identified by examination of a sample under a polarising microscope, between crossed polarisers.

Characteristic textures are observed in accordance with the classic paper by Rosevear, JAOCS Vol. 31 P628 (1954) or in J. Colloid and Interfacial Science, Vol. 30 No. 4, P.500 (1969).

"Yield Points" whenever referred to herein are as measured on an RML Series II "DEER" (R.T.M.) Rheometer at 25°C.

All percentages, unless otherwise stated, are by weight, based upon the total weight of the composition.

References herein to "sedimentation" include references to upward as well as downward separation of solid particles. "Non-sedimenting" means non-sedimentary under normal conditions of storage unless otherwise stated. Typically "Non-sedimenting" implies no significant sedimentation after three months at room temperature under normal earth gravity. The term does not exclude compositions which show a degree of syneresis, whereby a part of the aqueous phase separates to form a clear layer external to a homogeneous gel or dispersion. Such partly separated systems can usually be Dispersed by shaking. This is in contrast to sedimented systems wherein a solid sediment separates from the dispersion,

which generally presents substantially greater problems in Dispersing and dispensing the product.

#### TECHNICAL BACKGROUND

Liquid detergents have hitherto been used mainly for light duty applications such as dish washing. The market for heavy duty detergents, e.g. laundry detergents, has been dominated by powders, due to the difficulty of getting an effective amount of surfactant and in particular of Builder into a stable liquid formulation. Such liquids should in theory be cheaper than powder detergents since they would avoid the need to dry and would in many instances replace the sulphate filler conventionally used in powder detergents with water. They also offer the possibilities of greater convenience and more rapid dissolution in wash water than powder. Attempts to provide solutions of the Functional Ingredients have been relatively unsuccessful commercially. One reason for this lack of success has been that the most commonly used and cost effective Functional Ingredients, e.g. sodium tripolyphosphate and sodium dodecyl benzene sulphonate, are insufficiently soluble in aqueous compositions. Potassium pyrophosphate and amine salts of the Active Ingredients which are more soluble, have been tried as alternatives but have not been found cost effective.

Unbuilt liquid detergents containing high levels of surfactant have been marketed for laundry use, but are unsuitable for hard water areas and have enjoyed only limited success.

A different approach is to attempt to suspend the excess Builder as a solid in the liquid solution of surfactant. The problem however has been to stabilise the system to maintain the Builder in suspension and prevent sedimentation. This has in the past required relatively sophisticated formulations, preventing realisation of the potential cost saving, and relatively low concentrations of solid Builder, giving limited washing effectiveness. This approach has been conditioned by certain

assumptions: that the detergent should as far as possible be in solution; that the amount of suspended solid should be minimised to avoid difficulties in stabilising the suspension against sedimentation; and that special thickeners or stabilisers were essential to prevent sedimentation.

The products hitherto introduced commercially have suffered from certain serious drawbacks. In particular, the individual compositions have been proved highly sensitive to relatively small variations in Formulation and manufacturing procedure. Departure from a particular composition, optimised within fairly narrow limits, generally results in instability and diminished shelf life. The formulator has therefore been restricted to particular ingredients and proportions, which have not included many of the most effective combinations of surfactants and Builder for laundry purposes.

Because no general adequate theoretical explanation for the stability of such systems has been proposed, it has not proved possible to predict which compositions will be stable and which unstable, or how to set about stabilising any given surfactant Builder combination which may be desired for reasons of washing effectiveness or cost. Each composition has had to be discovered by trial and error, and little flexibility has existed for adapting the individual compositions to special requirements.

Moreover, in general, the Payload has been undesirably low. In addition, the proportion of Builder to Active Ingredient has generally been less than is preferred for optimum washing, and expensive ingredients, not usually required in powder Formulations, have often been needed to increase the amount of Functional Ingredient in solution, and to inhibit sedimentation of the suspended solid.

## INTRODUCTION TO THE INVENTION

We have now discovered that by observing certain conditions it is possible to formulate Non-sedimenting, Pourable, fluid, aqueous based detergent compositions which have novel structural features and which can employ as surfactant virtually any surfactant or surfactant combination which is useful in laundry applications, in desired optimum proportions with any of the commonly used detergent Builders. In general, compositions of our invention can be obtained, which contain substantially higher Payloads at effective Builder to surfactant ratio than have hitherto been attainable.

Preferred embodiments of our invention exhibit at least some of the following advantages compared with products marketed hitherto: Higher Payload; increased Builder to surfactant ratio; improved stability; lower cost due to use of cheaper ingredients and ease of production; satisfactory mobility; improved washing performance; "non-drip" characteristics, permitting the compositions to be added to the compartments of washing machines designed to operate with powders, without premature release; a consistency suitable for automatic dispensing; and the flexibility to select optimum surfactant combinations for the requirements of any particular market.

We have found that in general, contrary to what had been assumed in the art, the higher the amount of undissolved material the more stable the composition. We have discovered, in particular, that the lower the proportion of the Active Ingredients dissolved in the liquid aqueous phase, and the higher the proportion present as an Interspersed structure of solid or lamellar phase, the more readily can a Non-sedimenting, Pourable product be obtained at high Payloads. We have further discovered that most surfactants commonly used in powder detergents can have a stabilising effect on aqueous suspensions of Functional Ingredients, when present in certain novel structured states in the composition, which may, at high Payloads, be sufficient to stabilise the composition without the presence of

special stabilisers, not otherwise required for the Formulation. We have also discovered that surfactants can be constrained to form an open three dimensional structure conferring stability on aqueous suspensions, by the presence of Electrolytes and by controlling the conditions of mixing. We have discovered that by applying the above principles it is possible to formulate laundry detergents as thixotropic gels which may contain suspended particles of solid Builder, which have particular advantages over conventional detergent suspensions.

## THE PRIOR ART

The prior art on liquid detergents is extremely voluminous. However, for the purpose of this invention the numerous references to light duty liquids and to unbuilt or built clear liquid laundry detergents in which all ingredients are present in solution may be disregarded. The Builder level in each case is substantially less than desirable.

Recent general summaries of the current state of the art include JAOCS (April 1981) P356A - "Heavy Duty Laundry Detergents" which includes a review of the typical commercially available liquid formulations, and "Recent Changes in Laundry Detergents" by Rutkowski, published in 1981 by Marcel Dekker Inc. in the Surfactant Science Series.

The two principle avenues of approach to the problem of formulating fully built liquid detergents, have been to emulsify a surfactant in an aqueous solution of Builder or to suspend a solid Builder in an aqueous solution or emulsion of surfactant.

The former approach is exemplified by U.S.P.3235505, U.S.P.3346503, U.S.P.3351557, U.S.P.3509059, U.S.P.3574122, U.S.P.3328309 and Canadian Patent 917031. In each of these patents an aqueous solution of a water soluble Builder is sufficiently concentrated to salt out the surfactant (usually a liquid non-ionic



type) and the latter is dispersed in the aqueous medium as colloidal droplets, with the aid of various emulsifiers. In each case the system is a clear emulsion, which generally, contains relatively low levels of Builder, and which is undesirably expensive due to the cost of using soluble Builders.

The alternative approach is exemplified by B.P. 855893, B.P.948617, B.P.943271, B.P.2028365, E.P.38101, Australian P.522983, U.S.P 4018720 U.S.P.3232878, U.S.P.3075922 and U.S.P.2920045. The formulations described in these patents separate, on Centrifuging, into a Solid Layer comprising the majority of the sparingly soluble Builder and an aqueous layer containing at least the majority of the Active Ingredients. Commercial products corresponding to examples of two of these patents have been marketed recently in Australia and Europe. The stability of these compositions is generally highly sensitive to minor variations in Formulation. Most require expensive additives which are not Functional Ingredients.

A different approach is to suspend solid builder in an anhydrous liquid non-ionic surfactant e.g. BP 1600981. Such systems are costly, restrictive with regard to choice of surfactant and give unsatisfactory rinsing properties.

Several patents describe emulsions in which the Builder is in the dispersed phase of an emulsion rather than in suspension. U.S.P.4057506 describes the preparation of clear emulsions of sodium tripolyphosphate, and U.S.P.4107067 describes inverse emulsions in which an aqueous solution of Builder is dispersed in a liquid crystal surfactant system.

Reference may also be made to the numerous patents relating to hard surface cleaners, in which an abrasive is suspended usually in an aqueous solution of surfactant, e.g. B.P.2031455, U.S.P.3281367 and U.S.P.3813349. U.S.P.3956158 describes suspensions of abrasive in a gel system of interlocking fibres of, e.g. asbestos or soap. However, the low levels of surfactant, absence of Builder and


presence of high concentrations of abrasive, generally preclude these patents from being of any assistance in the formulating of laundry detergents.

Powder detergents are normally prepared by spray drying aqueous slurries, which may superficially resemble liquid detergent formulations, but which are not required to be stable to storage, and which, are prepared and handled at elevated tempertures. Such slurries are generally not Pourable at ambient temperature. Patents describing the preparation and spray drying of such slurry intermediates include U.S.P.3639288 and W. German OLS 1567656.

Other publications of possible interest are:

Australian patent 507431, which describes suspensions of Builder in aqueous surfactant, stabilised with sodium carboxymethyl cellulose or clay as a thickening agent. However, the levels of Functional Ingredients, and in particular of Builder, in the formulations exemplified, are not sufficient for a fully acceptable commercial product;

- U.S.P.3039971 describes a detergent paste containing the Builder in solution;
- Fr. Patent 2283951 describes suspensions of zeolite Builders in nonionic surfactant systems; the compositions are, however, stiff pastes rather than Pourable fluids.
- B.P. 1506427 and B.P. 1468181 describe suspensions of Builder in aqueous surfactant, which are generally insufficiently stable for commercial purposes.
- A.C.S. Symposium series No. 194 "Silicates in Detergents" describes the effect of silicates on liquid detergents.



It will be understood that each of the foregoing patent references was selected from the very extensive prior art, and relevant aspects highlighted with the aid of hindsight, using our knowledge of the invention as a guide to such selection and highlighting. The ordinary man skilled in the art at the time of our first claimed priority, and withouht foreknowledge of the applicant's invention, would not necessarily have selected those patents as being particularly significant or those aspects as being of special interest or relevance.

The foregoing summary does not therefore represent the overall picture of the art possessed by the ordinary skilled man. We believe that the latter has generally held the view, either that fully built liquid detergents containing sparingly soluble Builders were unattainable, or that progress towards such formulations would be by suspending the Builder in aqueous solutions of the surfactant, earlier, alternative approaches having failed.

# THE INVENTION

According to one embodiment, the invention provides a Non-sedimenting, Pourable, fluid, built, detergent composition, containing Active Ingredients which comprise a substantially linear alkyl benzene sulphonate, said composition having a Payload of at least 25% by weight, and comprising at least one, predominantly aqueous, liquid Separable Phase containing dissolved Electrolyte and one or more other Separable Phases, Interspersed therewith, which contain suspended solid particulate Builder, said Electrolyte comprising at least 4.7% and preferably at least 5.6% by weight of the composition of sodium carbonate and being present in at least sufficient amount to maintain at least a substantial proportion of the total Active Ingredients of the composition in at least one of said other phases, and thereby inhibiting sedimentation of said Builder.

According to a second embodiment the invention provides a Non-sedimenting, Pourable, fluid detergent composition comprising at least one predominantly aqueous liquid Separable Phase, containing sufficient dissolved Electrolyte selected from alkali metal chlorides, phosphates, condensed phosphates, phosphonates, citrates, nitrilotriacetates, ethylene diamine tetracetates, carbonates, silicates, and mixtures thereof to provide from 2 to 4.5 gram ions per litre of said phase total of akali metal cations; at least one other Separable Phase containing Active Ingredients; and suspended solid Builder; said composition having a Payload between the minimum concentration to provide a Non-sedimenting composition and the maximum concentration to provide a Pourable composition.

According to a third embodiment our invention provides a Non-sedimenting, Pourable, fluid detergent composition having a Payload of greater than 25% which, on Centrifuging, is separable into a single liquid layer containing sufficient dissolved Electrolyte consisting essentially of sodium chloride, sodium phosphate, sodium carbonate, sodium silicate, sodium tripolyphosphate or mixtures thereof to provide from 2 to 4.5 gram ions sodium per litre of said layer and a Solid Layer containing surfactant and Builder.

According to a fourth embodiment our invention comprises a Non-sedimentary, Pourable, fluid, detergent composition containing Active Ingredients which comprise a substantially linear alkylbenzene sulphonate, said composition having a Payload of at least 25% by weight which separates on Centrifuging into a predominantly aqueous liquid layer containing sufficient dissolved Electrolyte to provide from 2 to 4.5 gm ions per litre of alkali metal and at least one other layer, said at least one other layer comprising solid Builder and at least part of said Active Ingredient.

According to a fifth embodiment our invention comprises a Non-sedimenting, Pourable, fluid detergent composition having a Payload of at least 35% and comprising Active Ingredient, dissolved Electrolyte and suspended solid Builder, which separates on Centrifuging into a predominantly aqueous layer containing sufficient of said dissolved Electrolyte to provide from 2 to 4.5 gm

ions alkali metal per litre of said aqueous layer, and at least one other layer containing solid Builder and at least part of said Active Ingredients, the weight ratio of the total Builder to the total Active Ingredients being greater than 1.2:1.

In more detail, our invention provides Non-Sedimenting, Pourable, fluid detergent compositions comprising Active Ingredients and Dispersed solid Builder said compositions comprising at least one predominantly aqueous liquid phase and one or more other phases separable from said predominantly aqueous liquid phase by Centrifuging and containing Active Ingredient present in at least one of said one or more other phases, and a Builder, present in at least one of said one or more other phases, said one or more other phases being Interspersed with the predominantly aqueous phase, all of which compositions exhibit at least some, but not necessarily all, of the following characteristics: They are thixotropic; they are gels; they comprise a continuous, at least predominantly aqueous Separable Phase, containing dissolved Electrolyte, a Separable Phase containing a substantial proportion of the Active Ingredient as spheroids or vesicles Interspersed with said at least predominantly aqueous phase, and a Dispersed solid phase consisting at least predominantly of Builder; said one or more other phases are at least predominantly non-aqueous; the compositions have a high Payload of Functional Ingredients, typically greater than 20% by weight, e.g. 25 to 75%, more usually at least 30% preferably at least 35% most preferably at least 40% by weight; they contain a high ratio of Builder to Active Ingredient e.g. greater than 1:1 preferably 1.2:1 to 4:1; they contain more than 5 and preferably more than 8% by weight of Active Ingredients; the predominantly aqueous phase contains a concentration of less than 15%, preferably less than 8%, e.g. less than 2%, typically, in the case of nonionic surfactant or alkyl benzene sulphonates, less than 0.5% by weight dissolved Active Ingredients; the proportion by weight of Active Ingredient in the predominantly aqueous phase to total Active Ingredient in the composition is less than 1:1.5 preferably less than 1:2 e.g. less than 1:4; the at least one predominantly aqueous liquid phase contains sufficient Electrolyte to provide a concentration of at least 0.8, typically at least 1.2, preferably 2.0 to 4.5 gram ions per litre of total alkali metal and/or ammonium cations: the

0170091

compositions contain at least 15% by weight, preferably more than 20% by weight of Builder; the Builder is at least predominantly sodium tripolyphosphate; the Builder comprises a minor proportion of alkali metal silicate, preferably sodium silicate; the bulk viscosity of the composition is between 0.1 and 10 pascal seconds, preferably between 0.5 and 5 pascal seconds; the composition has a Yield Point preferably of at least 2 e.g. at least 5, preferably less than 200 e.g. 10 to 150 dynes/sq.cm; a phase containing Builder comprises solid particles having a maximum particle size below the limit at which the particles tend to sediment; the particles have, adsorbed on their surfaces at least one crystal growth inhibitor sufficient to maintain the solid particles below the limit at which the particles tend to sediment; the composition contains an agglomeration inhibitor sufficient to prevent flocculation or coagulation of the solid particles.

## CLASSIFICATION BY CENTRIFUGING

Aqueous based liquid laundry detergents containing suspended solid builder can, in general, conveniently be classified by Centrifuging as hereinbefore defined.

Three principal types of laundry liquid having a continuous aqueous phase and dispersed solid are distinguishable, which will be hereinafter referred to as Group I, Group II and Group III suspensions.

The first Group of laundry suspensions is characteristic of the prior art discussed above which relates to suspensions of solid Builder in aqueous solutions or emulsions of surfactant. On Centrifuging as defined herein, Group I compositions separate into a Solid Layer consisting essentially of Builder, and a viscous liquid layer comprising water and surfactant. Formulation factors tending to form Group 1 compositions include the use of the more water soluble surfactants, such as alkyl ether sulphates, the presence of solubilising agents such as Hydrotropes and water miscible organic solvents, relatively low levels of Electrolyte and relatively low Payloads. Group 1 compositions normally display at least some of the following typical properties. The bulk viscosity of the composition

is determined by, and is similar to, the viscosity of the aqueous liquid layer. The aqueous layer typically has a viscosity of from 0.1-1.0 pascal seconds. Viscosities of the compositions are generally also under 1 pascal second, e.g. 0.3 to 0.6 pascal seconds. The compositions usually have yield points of less than 4, often less than 1, dyne cm $^{-2}$ . This implies a relatively unstructured composition. This is confirmed by neutron scattering and x-ray diffraction studies and by electron microscopy. Subjection to high shear rate renders many Group I compositions unstable.

Group II is essentially distinguished from Group I in that at least the major proportion of the surfactant is present in a Separable Phase, which is distinct from the predominantly aqueous liquid phase containing the Electrolyte. This Group is distinguished from Group III in that at least the major portion of the surfactant separates on centrifuging as a liquid or liquid crystal layer.

Group II compositions typically show a three layer separation on Centrifuging, giving a non-viscous liquid aqueous layer (e.g. less than 0.1 pascal seconds, usually less than 0.02 pascal seconds), which contains Electrolyte but little or no surfactant, a viscous liquid layer which contains a major proportion of the Active Ingredients and a Solid Layer consisting predominantly of Builder.

Group II compositions have, typically, a very low yield point on being first prepared but become more gel like on ageing. The viscosity of the composition is usually between 1 and 1.5 pascal seconds. The compositions of this type show evidence of lamellar structure in X-ray and neutron diffraction experiments and by electron microscopy.

Most Centrifuged Group II compositions have the liquid or liquid crystal surfactant layer uppermost, but we do not exclude compositions in which the aqueous Electrolyte layer is uppermost or in which there are two or more Solid Layers distinguishable from each other, at least one of which may sediment upwardly, in relation to either or both liquid layers on Centrifuging.

0170091

The essential distinction of Group III from the other Groups is that at least a substantial proportion of the surfactant Centrifuges into a Solid Layer.

Group III compositions may Centrifuge into more than one Solid Layer. Normally both surfactant and Builder sediment downwardly on Centrifuging and the two phases are intermixed. However some Group III compositions may provide an upwardly sedimentary surfactant phase or more than one surfactant phase at least one of which may sediment upwardly. It is also possible for some or all of the Builder to sediment upwardly.

The third Group of laundry liquids is typical of those compositions of the present invention prepared from those surfactants which are more sparingly soluble in the aqueous phase, especially anionic surfactants such as sodium alkyl benzene sulphonates, as well as mixtures of such surfactants with minor proportions of non-ionic surfactant. Group III compositions typically separate on Centrifuging into two layers. The first of which is an aqueous layer containing dissolved Electrolyte and the second is a Solid Layer comprising Builder and surfactant.

The rheological properties of Group III, typically, show the strongest evidence for structure. The Viscosity of the suspension is substantially greater than that of the aqueous layer, e.g. typically 1.2 to 2 Pascal seconds The compositions generally have a fairly high Yield Point, e.g. greater than 10 dynes cm and a very short recovery time after subjection to shear stresses in excess of the Yield Point, e.g. usually 20 to 100 minutes. On recovery after subjection to very high shear stresses many Group III compositions exhibit increased Viscosity and greater stability.

There is a gradual progression from Group I to Group III with some compositions having some properties characteristic of one group and some characteristic of another. Soap based compositions of our invention, for example, may show, in addition to a liquid layer and a Solid Layer, a small amount of a third layer which is liquid on Centrifuging, but have rheological properties characteristic of Group III.

Compositions at the borderline of Groups I and II are sometimes unstable but maybe converted into stable Group II compositions of the invention by addition of sufficient Electrolyte and/or by increasing Pay Load. Most Group I compositions may be converted into Group II if sufficient Electrolyte is added. Similarly, addition of more Electrolyte tends to convert Group II compositions into Group III. Conversely, Group III can generally be converted to Group II, and Group II to Group I, by addition of Hydrotrope. Some Group III compositions may be converted directly to Group I and vice versa by addition of Hydrotrope or Electrolyte respectively.

# CLASSIFICATION BY DIFFRACTION AND MICROSCOPY

Compositions of our invention and of the prior art, have been examined by x-ray and neutron diffraction and by electron microscopy.

Samples for neutron diffraction studies were prepared using deuterium oxide in place of water. Water was kept to a minimum, although some ingredients, normally added as aqueous solutions (e.g. sodium silicate), or as hydrates, were not available in a deuterated form.

Deuterium oxide based compositions were examined on the Harwell small angle Neutron Scattering Spectrometer. Both deuterium oxide based and aqueous samples were also examined using a small angle x-ray diffractometer. Aqueous samples were freeze fracture etched, coated with gold or gold/paladium and studied under the Lancaster University Low Temperature Scanning Electron Microscope. Competitive commercial compositions, which are not, of course, available in a deuterated form, could not be examined by neutron scattering.

0170091

As in the case of Centrifuging, the three techniques described above all provide an indication of three broad categories of liquid detergent suspension, which appear to correspond generally to the Group I, Group II and Group III compositions, described under "Classification by Centrifuging".

The first category of composition, which included, generally those compositions belonging typically to Group I, was characterised under both neutron and x-ray analysis by high levels of small angle scattering and an absence of discrete peaks, corresponding to regular, repeating, structural features. Some compositions showed broad indistinct shoulders or humps, others a smooth continuum.

Small angle scattering is scattering very close to the line of the incident beam and is usually dominated by scattering from dilute dispersions of inhomogeneities in the composition. The shoulders or humps observed with some Group I compositions additionally show a form and angular displacement typical of concentrated micellar solutions of surfactant (L1 phase).

Under the electron microscope typical Group 1 compositions gave a largely featureless granular texture with crystals of Builder distributed apparently at random. These results were consistent with the hypothesis based on their rheological properties that typical Group I compositions are relatively unstructured and lacking detectable lamellar features. However some members of Group I showed evidence under the electron microscope of spherical structures of approximately 5 microns diameter.

A very different type of pattern was obtained from typical Group II compositions. These showed relatively low levels of small angle scattering near the incident beam, a peak typical of concentrated micellar solution ( $L_1$  phase) and a sharply defined peak or peaks corresponding to a well defined lamellar structure. The positions of the latter peaks were in a simple numerical ratio, with first, second and, sometimes, third order peaks usually

distinguishable. The peaks were evidence of relatively broadly spaced lamellae (36-60 Angstrom). Under the electron microscope lamellar structures were visible.

Typical Group III compositions gave relatively narrow and intense small angle scattering, together with distinct peaks indicative of a lamellar structure. The peaks were broader than in the case of typical Group II compositions, and second and third order peaks were not always separately distinguishable. In general the displacement of the peaks indicated a lamellar structure with the lamellae more closely spaced than in the case of typical Group II compositions (e.g. 26-36 Angstrom). Lamellar structures were clearly visible under the electron microscope. In some instances spheroidal structures could also be observed e.g. of approximately 1 micron diameter.

## PROPOSED STRUCTURE

We believe that the foregoing properties can most readily be explained by the hypothesis that our invention embodies a novel structure of matter in which solid Builder is suspended in a structured arrangement of solid surfactant hydrate, and/or of "G" phase surfactant in association with an  $L_1$  phase micellar solution and/or vesicles.

Preferred embodiments of our invention and in particular, Group III compositions, are believed to comprise pourable gel systems in which there may be two or more Co-continuous or Interspersed phases. The properties of the Group III compositions can be explained on the basis that they are thixotropic gels comprising a relatively weak three dimensional network of solid surfactant hydrate Interspersed with a relatively non viscous aqueous phase which contains dissolved Electrolyte, but little or no surfactant. The network prevents sedimentation of the network-forming solids, and any suspended discrete particles. The network forming solids may be present as platelets, sheets of indefinite

0170091

extent, or fibres or alternatively, as asymetric particles joined into or interacting to provide, a random mesh, which is Interspersed with the liquid. The structure is sufficiently stable to inhibit or prevent precipitation on storage and will also limit the extent of spreading of the gel on a horizontal surface, however the structure is weak enough to permit the compositions to be poured or pumped. The solid structure is composed at least predominantly of surfactant hydrate e.g. sodium alkyl benzene sulphonate or alkyl sulphate. Thus no other stabilising agent is required over that required in the end-use of the composition. Such gels may, in particular, exhibit a clay-like structure, sometimes referred to as a "house of cards" structure, with a matrix of plate shaped crystals orientated at random and enclosing substantial interstices, which accomodate the particles of builder. The solid surfactant may, in some instances be associated with, or at least partially replaced by "G" phase surfactant.

In the case of Group II compositions there may be four thermodynamically distinct phases of which only three are Separable Phases under the conditions herein defined.

The phases detected by diffraction comprise a lamellar phase, which is probably a "G" phase, but possibly in some instances surfactant hydrate or a mixture thereof with "G" phase, and predominantly aqueous "L1" micellar solution, together with the solid Builder. There is also a predominantly aqueous solution containing Electrolyte but less than 75% particularly 50%, usually less than 40%, more usually less than 20% typically less than 10% most typically less than 5% e.g. less than 2% of the total weight of Active Ingredients.

The Builder is suspended in a system which may comprise a network of "G" phase and/or spheroids or vesicles, which may have an onion like structure, or outer shell, formed from successive layers of surfactant e.g. as "G" phase, and which may contain at least one of the predominantly aqueous phases, e.g. the electrolyte

0170091

solution, or more probably the "L1" micellar solution. At least one of the predominantly aqueous phases is the continuous phase. Evidence for the presence of vesicles is provided by microscopy in the case of the compositions containing olefin and paraffin sulphonates.

### **SURFACTANTS**

The compositions of our invention preferably contain at least 5% by weight of surfactants. Preferably the surfactant constitutes from 7 to 35% by weight of the composition, e.g. 10 to 20% by weight.

The surfactant may for example consist substantially of an at least sparingly water-soluble, salt of sulphonic or mono esterified sulphuric acids e.g. an alkylbenzene sulphonate, alkyl sulphate, alkyl ether sulphate, olefin sulphonate, alkane sulphonate, alkylphenol sulphate, alkylphenol ether sulphate, alkylethanolamide sulphate, alkylethanolamide ether sulphate, or alpha sulpho fatty acid or its esters each having at least one alkyl or alkenyl group with from 8 to 22, more usually 10 to 20, aliphatic carbon atoms. Said alkyl or alkenyl groups are preferably straight chain primary groups but may optionally be secondary, or branched chain groups. The expression "ether" hereinbefore refers to polyoxyethylene, polyoxypropylene, glyceryl and mixed polyoxyethylene-oxy propylene or mixed glyceryl-oxyethylene or glyceryl-oxy propylene groups. typically containing from 1 to 20 oxyalkylene groups. For example, the sulphonated or sulphated surfactant may be sodium dodecyl benzene sulphonate, potassium hexadecyl benzene sulphonate, sodium dodecyl dimethyl benzene sulphonate, sodium lauryl sulphate, sodium tallow sulphate, potassium oleyl sulphate, ammonium lauryl monoethoxy sulphate, or monoethanolamine cetyl 10 mole ethoxylate sulphate.

Other anionic surfactants useful according to the present invention include fatty alkyl sulphosuccinates, fatty alkyl ether sulphosuccinates, fatty alkyl sulphosuccinamates, fatty alkyl ether

sulphosuccinamates, acyl sarcosinates, acyl taurides, isethionates, Soaps such as stearates, palmitates, resinates, oleates, linoleates, and alkyl ether carboxylates. Anionic phosphate esters may also be used. In each case the anionic surfactant typically contains at least one aliphatic hydrocarbon chain having from 8 to 22 preferably 10 to 20 carbon atoms, and, in the case of ethers one or more glyceryl and/or from 1 to 20 ethyleneoxy and or propyleneoxy groups.

Certain anionic surfactants, such as olefin sulphonates and paraffin sulphonates are commercially available only in a form which contains some disulphonates formed as by-products of the normal methods of industrial manufacture. The latter tend to solubilise the surfactant in the manner of a Hydrotope. However, the olefin and paraffin sulphonates readily form stable compositions which, on Centrifuging, contain a minor portion of the total surfactant in the aqueous phase, and which show evidence of spheroidal structures. These compositions are valuable, novel, laundry detergents and which accordingly constitute a particular aspect of the present invention.

Preferred anionic surfactants are sodium salts. Other salts of commercial interest include those of potassium, lithium, calcium, magnesium, ammonium, monoethanolamine, diethanolamine, triethanolamine and alkyl amines containing up to seven aliphatic carbon atoms.

The surfactant may optionally contain or consist of nonionic surfactants. The nonionic surfactant may be e.g. a C<sub>10-22</sub> alkanolamide of a mono or di- lower alkanolamine, such as coconut monoethanolamide. Other nonionic surfactants which may optionally be present, include ethoxylated alcohols, ethoxylated carboxylic acids, ethoxylated amines, ethoxylated alkylolamides, ethoxylated alkylohenols, ethoxylated glyceryl esters, ethoxylated sorbitan esters, ethoxylated phosphate esters, and the propoxylated or ethoxylated and propoxylated analogues of all the aforesaid ethoxylated nonionics, all having a C<sub>8-22</sub> alkyl or alkenyl group and up to 20 ethyleneoxy and/or propyleneoxy groups, or any other

nonionic surfactant which has hitherto been incorporated in powder or liquid detergent compositions e.g. amine oxides. The latter typically have at least one  $C_{8-22}$ , preferably  $C_{10-20}$  alkyl or alkenyl group and up to two lower (e.g.  $C_{1-4}$ , preferably  $C_{1-2}$ ) alkyl groups.

The preferred nonionics for our invention are for example those having an HLB range of 7-18 e.g. 12-15.

Certain of our detergents may contain cationic surfactants, and especially cationic fabric softeners usually as a minor proportion of the total active material. Cationic fabric softeners of value in the invention include quaternary amines having two long chain (e.g.  $C_{12-22}$  typically  $C_{16-20}$ ) alkyl or alkenyl groups and either two short chain (e.g.  $C_{1-4}$ ) alkyl groups, or one short chain and one benzyl group. They also include imidazoline and quaternised imidazolines having two long chain alkyl or alkenyl groups, and amido amines and quaternised amido amines having two long chain alkyl or alkenyl groups. The quaternised softeners are all usually salts of anions which impart a measure of water solubility such as formate, acetate, lactate, tartrate, chloride, methosulphate, ethosulphate, sulphate or nitrate. Compositions of our invention having fabric softener character may contain smectite clays.

Compositions of our invention may also contain amphoteric surfactant, which may be included typically in surfactants having cationic fabric softener, but may also be included, usually as a minor component of the Active Ingredients, in any of the other detergent types discussed above.

Amphoteric surfactants include betaines, sulphobetaines and phosphobetains formed by reacting a suitable tertiary nitrogen compound having a long chain alkyl or alkenyl group with the appropriate reagent, such as chloroacetic acid or propane sultone. Examples of suitable tertiary nitrogen containing compounds include:

tertiary amines having one or two long chain alkyl or alkenyl groups, and optionally a benzyl group, any other substituent being a short chain alkyl group; imidazolines having one or two long chain alkyl or alkenyl groups and amidoamines having one or two long chain alkyl or alkenyl groups.

Those skilled in the detergent art will appreciate that the specific surfactant types described above are only exemplary of the commoner surfactants suitable for use according to the invention. Any surfactant capable of performing a useful function in the wash liquor may be included. A fuller description of the principal types of surfactant which are commercially available is given in "Surface Active Agents and Detergents" by Schwartz Perry and Berch.

## BUILDERS

The Builder, in preferred compositions of our invention is believed to be normally present, at least partially, as discrete solid crystallites suspended in the composition. The crystallites typically have a size of up to 60 eg 5 to 50 microns.

We have found that Formulations containing sodium tripolyphosphate as Builder, or at least a major proportion of sodium tripolyphosphate in admixture with other Builders, exhibit stability and mobility over a wider range of Dry Weight than corresponding Formulations with other Builders. Such Formulations are therefore preferred. Our invention, however, also provides compositions comprising other Builders such as potassium tripolyphosphate, carbonates, zeolites, nitrilo triacetates, citrates, metaphosphates, pyrophosphates, phosphonates, EDTA and/or polycarboxylates, optionally but preferably, in admixture with tripolyphosphate. Orthophosphates may be present, preferably as minor components in admixture with tripolyphosphate, as may alkali metal silicates.

The last mentioned are particularly preferred and constitute a feature of our preferred embodiments since they perform several valuable functions. They provide the free alkalinity desirable to saponify fats in the soil, they inhibit corrosion of aluminium surfaces in washing machines and they have an effect as Builders. In addition, they are effective as Electrolytes to "salt out" Active Ingredients from the predominantly aqueous liquid phase thereby reducing the proportion of Active Ingredient in solution and improving the stability and fluidity of the composition.

Accordingly, we prefer that compositions of our invention should contain at least 1% and up to 12.3% by weight of the composition preferably at least 2% and up to 10%, most preferably more than 3% and up to 6.5% e.g. 3.5 to 5% of alkali metal silicate, preferably sodium silicate measured as SiO<sub>2</sub> based on the total weight of composition.

Typically, the silicate used to prepare the above compositions has an Na<sub>2</sub>O: SiO<sub>2</sub> ratio of from 1:1 to 1:2 or 1:1.5 to 1:1.8. It will however be appreciated that any ratio of Na<sub>2</sub>O (or other base) to SiO<sub>2</sub>, or even silicic acid could be used to provide the silicate in the composition, and any necessary additional alkalinity provided by addition of another base such as sodium carbonate or hydroxide. Formulations not intended for use in washing machines do not require silicates provided that there is an alternative source of alkalinity.

The Builder normally constitutes at least 15% by weight of the compositions, preferably at least 20%. We prefer that the ratio of Builder to surfactant is greater than 1:1 preferably 1.2:1 to 5:1.

## ELECTROLYTE

The concentration of dissolved organic material and more particularly of Active Ingredients in the predominantly aqueous, liquid phase is preferably maintained at a low level. This may be achieved by selecting, so far as possible, surfactants which are

sparingly soluble in the predominantly aqueous phase, and keeping to a minimum the amount of any more soluble surfactant which is desired for the particular end use. For a given surfactant system and Payload, we have found that it is generally possible to stabilise the system in accordance with an embodiment of our invention by including in the at least one predominantly aqueous phase a sufficient quantity of Electrolyte.

An effect of the Electrolyte is to limit the solubility of Active Ingredient in the at least one predominantly aqueous phase, thereby increasing the proportion of surfactant available to provide a solid, or liquid crystal, matrix which stabilises the compositions of our invention. A further effect of the Electrolyte is to raise the transition temperature of the "G" phase to solid for the surfactant. One consequence of raising the phase transition temperature is to raise the minimum temperature above which the surfactant forms a liquid or liquid crystal phase. Hence surfactants which in the presence of water are normally liquid crystals or aqueous micellar solutions at ambient temperature may be constrained by the presence of Electrolyte to form solid matrices or "G" phases.

Preferably, the proportion of Electrolyte dissolved in the at least one predominantly aqueous phase is sufficient to provide a concentration of at least 0.8 preferably at least 1.2 e.g 2.0 to 4.5 gram moles per litre of alkali metal, alkaline earth metal and/or ammonium cations. The stability of the system may be further improved by ensuring so far as possible that the anions required in the composition are provided by salts which have a common cation, preferably sodium. Thus, for example, the preferred Builder is sodium tripolyphosphate, the preferred anionic surfactants are sodium salts of sulphated or sulphonated anionic surfactants and any anti-redeposition agent, e.g. carboxymethyl cellulose, or alkali, e.g. silicate or carbonate are also preferably present as the sodium salts. Sodium chloride, or other soluble inorganic sodium salts may be added to increase the Electrolyte concentration

and minimise the concentration of Active Ingredients in the predominantly aqueous liquid phase. The preferred electrolyte, however, is sodium silicate. Alkaline earth metals are only normally present when the Active Ingredients comprise surfactants, such as olefin sulphonates or non-ionics which are tolerant of their presence.

It is possible, alternatively, but less preferably to choose salts of potassium, ammonium, lower amines, alkanolamines or even mixed cations.

## STABILISING SUSPENDED SOLID

The particle size of any solid phase should be less than that which would give rise to sedimentation. The critical maximum limit to particle size will vary according to the density of the particles and the density of the continuous phase and the yield point of the composition.

Compositions of our invention preferably contain a particle growth inhibitor. The particle growth inhibitor is believed to function by adsorption onto the faces of suspended crystallites of sparingly soluble solids preventing deposition of further solid thereon from the saturated solution in the predominantly aqueous liquid phase. Typical particle growth inhibitors include sulphonated aromatic compounds. Thus for example, a sodium alkyl benzene sulphonate such as sodium dodecyl benzene sulphonate when present as a surfactant is itself a particle growth inhibitor and may be sufficient to maintain particles of, for example, builder in the desired size range without additional stabilisers. Similarly, lower alkyl benzene sulphonate salts such as sodium xylene sulphonate or sodium toluene sulphonate have stabilising activity, as well as being conventionally added to liquid detergents as Hydrotropes. our invention, however, the presence of the lower alkyl benzene sulphonates is less preferred. Sulphonated naphthalenes especially methyl naphthalene sulphonates are effective crystal growth

inhibitors. They are not, however, normal ingredients of detergent compositions and therefore on cost grounds they are not preferred. Other particle growth inhibitors include water soluble polysaccharide derivatives such as sodium carboxymethyl cellulose, which is frequently included in detergent compositions as a soil anti-redeposition agent. We, therefore prefer that it should be present in minor amounts in compositions according to our invention, sufficient to perform its normal functions in detergent compositions and to assist in stabilising the suspension, but preferably not sufficient to increase so substantially the viscosity of the predominantly aqueous liquid phase as to impair the pourability of the composition.

Another group of particle growth inhibitors which may optionally be included in compositions according to our invention are the sulphonated aromatic dyes, especially the sulphonated aromatic optical brightening agents, which are sometimes included in powder formulations.

Typical examples include 4,4'-bis (4-phenyl-1,2,3-triazol-2-yl-2,2'-stilbene disulphonate salts and 4,4'-diphenylvinylene-2,2'-biphenyl disulphonate salts. Such particle growth inhibitors may be included instead of, or more usually in addition to, for example, a sulphonated surfactant.

Other effective particle growth inhibitors include lignosulphonates and C  $_{6-18}$  alkane sulphonate surfactants, which latter compounds may also be present as part of the surfactant content of the composition.

The presence of an agglomeration inhibitor is also preferred. The agglomeration inhibitor for use according to our invention may also conveniently be sodium carboxymethyl cellulose. It is preferred that the composition should include an effective agglomeration inhibitor which is chemically distinct from the

particle growth inhibitor, despite the fact that, for example, sodium carboxymethyl cellulose, is capable of performing either function. It is sometimes preferred, when preparing the detergent composition to add the crystal growth inhibitor to the composition prior to the agglomeration inhibitor, and to add the agglomeration inhibitor subsequent to the solid phase, so that the crystal growth inhibitor is first adsorbed onto the solid particles to inhibit growth thereof and the agglomeration inhibitor is subsequently introduced to inhibit agglomeration of the coated particles.

Other agglomeration inhibitors which may less preferably be used include polyacrylates and other polycarboxylates, polyvinyl pyrrolidone, carboxy methyl starch and lignosulphonates.

The concentration of the crystal growth inhibitor and agglomeration inhibitor can be widely varied according to the proportion of solid particles and the nature of the dispersed solid as well as the nature of the compound used as the inhibitor and whether that compound is fulfilling an additional function in the composition. For example, the preferred proportions of alkyl benzene sulphonate are as set out hereinbefore in considering the proportion of surfactant. The preferred proportions of sodium carboxy methyl cellulose are up to 2.5% by weight of the composition preferably 0.5 to 2% by weight e.g. 1 to 2% although substantially higher proportions up to 3 or even 5% are not excluded provided they are consistent in the particular formulation with a pourable composition. The sulphonated optical brighteners may typically be present in proportions of 0.05 to 1% by weight e.g. 0.1 to 0.3% although higher proportions e.g. up to 5% may less preferably be present in suitable compositions.

# ALKALINITY

The compositions of our invention are preferably alkaline, being desirably buffered with an alkaline buffer adapted to provide a pH above 8 eg above 9 most preferably above 10 in a wash liquor containing the composition diluted to 0.5% Dry Weight. They preferably have sufficient free alkalinity to require from 0.4 to 12 mls. preferably 3 to 10 mls of N/10 HCl to reduce the pH of 100 mls. of a dilute solution of the composition, containing 0.5% Dry Weight, to 9, although compositions having higher alkalinity may also be commercially acceptable. In general lower alkalinities are less acceptable in commercial practice, although not excluded from the scope of our invention.

The alkaline buffer is preferably sodium tripolyphosphate and the alkalinity preferably provided at least in part by sodium silicate. Other less preferred alkaline buffers include sodium carbonate.

#### SOLUBILISERS

Hitherto, liquid detergent compositions have commonly contained substantial concentrations of Hydrotropes and/or organic water miscible hydroxylic solvents such as methanol, ethanol, isopropanol, glycol, glycerol, polyethylene glycol and polypropylene glycol. Such additives are often necessary to stabilise Group I formulations. However, in Group II and III formulations of the present invention, they may have a destabilising effect which often requires the addition of extra amounts of Electrolyte to maintain stability. They are, moreover, costly and not Functional Ingredients. They may, however, in certain circumstances, promote Pourability. We do not therefore totally exclude them from all compositions of our invention, but we prefer that their presence be limited to the minimum required to ensure adequate Pourability. If not so required we prefer that they be absent.

## PAYLOAD

Selection of the appropriate Payload is generally important to obtain desired stability and Pourability. Optimum Payload may vary considerably from one type of Formulation to another. Generally speaking it has not been found possible to guarantee Non-sedimenting compositions below about 35% by weight Payload, although some types of Formulation can be obtained in a Non-sedimenting form below 30% Payload, and sometimes as low as 25% Payload. In particular we have obtained Soap based Formulations at concentrations below 25% Payload eg 24%. We do not exclude the possibility of making such Formulations at Payloads down to 20%.

Prior art references to stable compositions at low Payloads have either been limited to particular Formulations using special stabilisers, or have not provided sufficiently stable suspensions to satisfy normal commercial criteria.

For any given Formulation according to our invention a range of Payloads can be identified within which the composition is both stable and pourable. Generally below this range, sedimentation occurs and above the range the Formulation is too viscous. The acceptable range may be routinely determined for any given Formulation by preparing the suspension using the minimum water required to maintain a stirrable composition, diluting a number of samples to progressively higher dilutions, and observing the samples for signs of sedimentation over a suitable period. For some Formulations the acceptable range of Payloads may extend from 30%, or 35% to 60, or 70%, or even 75% by weight for others it may be much narrower, e.g. 40 to 45% by weight.

If no stable Pourable range can be determined by the above methods, the Formulation should be modified according to the teaching herein e.g. by the addition of more sodium silicate solution or other Electrolyte.

Typically Group III Formulations show an increase in Yield Point with increasing Payload. The minimum stable Payload for such typical Group III Formulations usually corresponds to a Yield Point of about 10-12 dynes/cm<sup>2</sup>.

### PREPARATION

Compositions of our invention can, in many instances be readily prepared by normal stirring together of the ingredients. However, some Formulations according to the invention are not fully stable unless the composition is subjected to more prolonged or vigorous mixing. In some extreme cases the solid content of product may require comminution in the presence of the liquid phase. The use of a colloid mill for the latter is not excluded, but is not generally necessary. In some instances mixing under high shear rate provides products of high viscosity.

The order and conditions of mixing the ingredients are often important in preparing a stable structured mixture according to our invention. Thus a system comprising: water, sodium dodecylbenzene sulphonate, coconut monoethanolamide, sodium tripolyphosphate, sodium silicate, sodium carboxymethyl cellulose and optical brightener at 45% Dry Weight was unstable when the compounds were mixed in the order described above, but when mixed with the coconut monoethanolamide and sodium tripolyphosphate added as the last of the Functional Ingredients, a stable composition was formed.

A method of preparation that we have found generally suitable for preparing stable mixtures from those Formulations which are capable of providing them, is to mix the Active Ingredients or their hydrates, in a concentrated form, with concentrated (e.g. 30 to 60%, preferably 45-50%) aqueous silicate solution, or alternatively, a concentrated solution of any other non-surfactant Electrolyte required in the Formulation. Other ingredients are then added including any anti-redeposition agents, optical brightening agents and foaming agents. The Builder, when not required to provide the

initial Electrolyte solution, may be added last. During mixing, just sufficient water is added at each addition to maintain the composition fluid and homogeneous. When all the Functional Ingredients are present, the mixture is diluted to provide the required Pay Load. Typically, mixing is carried out at ambient temperature where consistent with adequate dispersion. Certain ingredients, e.g. non-ionic surfactants such as coconut monoethanolamide require gentle warming e.g. 400 for adequate dispersion. This degree of warming may generally be achieved by the heat of hydration of sodium tripolyphosphate. To ensure sufficient warming we prefer to add the tripolyphosphate in the anhydrous form containing a sufficiently high proportion of the high temperature rise modification commonly called "Phase I". The foregoing procedure is only one of several methods that may be satisfactorily used for all or most of the compositions of our invention. Some Formulations are more sensitive to the order and temperature of mixing than others.

## FORMULATION TYPES

Typically, our Formulations may most conveniently be an anionic type (Type "A") in which the Active Ingredient preferably consists at least predominantly of sulphated or sulphonated anionic surfactant, optionally with a minor proportion of non-ionic surfactant.

Considering type "A" Formulations according to our invention in more detail, we particularly distinguish high foaming sulphate or sulphonate Formulations and low foaming Formulations.

High foaming Formulations may typically be based on sodium constraints or branched chain alkyl benzene sulphonate, alone or in admixture with a constraint alkyl sulphate and/or constraints alkyl 10-10 mole ether sulphate. Small amounts (e.g. up to 1% of the weight of the compositions) of Soap may be present to aid rinsing of the fabric. Nonionic foam boosters and stabilisers, such as constraints acyl (e.g. coconut) monoethanolamide or diethanolamide or their

0170091

ethoxylates, ethoxylated alkyl phenol, fatty alcohols or their ethoxylates may optionally be present as foam boosters or stabilisers, usually in proportions up to about 6% of the Dry Weight of the composition.

The sodium alkyl benzene sulphonate may be totally or partially replaced, in the above Formulations by other sulphonated surfactants including fatty alkyl xylene or toluene sulphonates, or by e.g. alkyl ether sulphates (preferably) or alkyl sulphates, paraffin sulphonates and olefin sulphonates, sulphocarboxylates, and their esters and amides, including sulphosuccinates and sulphosuccinamates, alkyl phenyl ether sulphates, fatty acyl monoethanolamide ether sulphates or mixtures thereof.

Preferably the sulphated or sulphonated anionic surfactant consists substantially of alkyl benzene sulphonate preferably sodium alkyl benzene sulphonate, e.g. C alkyl benzene sulphonate. The proportion of alkyl benzene sulphonate in the absence of foam boosters is preferably from 20 to 60% e.g. 30 to 55% of the Dry Weight of the composition.

Alternatively, the anionic surfactant may comprise a mixture of alkyl benzene sulphonate, and alkyl sulphate and/or alkyl ether sulphate and/or alkyl phenol ether sulphate in weight proportions of e.g. from 1:5 to 5:1 typically 1:2 to 2:1 preferably 1:1.5 to 1.5:1 e.g. 1:1. In the latter case the total anionic surfactant is preferably from 15 to 50% e.g. 20 to 40% of the Dry Weight of the compositions, in the absence of foam booster.



The alkyl sulphate, and/or alkyl ether sulphate for use in admixture with the alkyl benzene sulphonate typically has an average of from 0 to 5 ethyleneoxy groups per sulphate group e.g. 1 to 2 groups.

According to a preferred specific embodiment our invention provides a Pourable, Non-sedimenting, fluid detergent composition consisting essentially of water and: (A) from 10 to 20% based on the weight of the composition of Active Ingredients comprising a substantially linear sodium alkyl benzene sulphonate having from 10 to 20 aliphatic carbon atoms and optionally an alkyl ethoxy sulphate having an alkyl group with from 10 to 20 carbon atoms, and/or a minor proporition of a non-ionic surfactant and/or of a soap; (B) at least 15% of Builder partly present as solid and selected from condensed phosphates, zeolites, citrates, nitrilotriacetates, ethylenediamine tetracetates, orthophosphates and silicates, wherein at least 50% by weight of said Builder is sodium tripolyphosphate -and said Builder further comprises at least 4.7%, based on the total weight of the composition, of sodium carbonate; (C) optionally up to 2.5% by weight of the composition, of carboxymethylcellulose; (D) optionally up to 1% by weight of the composition of optical brightening agent; and (E) optionally minor proportions of ingredients selected from enzymes, bleaches, antifoams, smectite clays, fragrances, cationic fabric softeners, dyes and sodium chloride.

According to a second preferred specific embodiment our invention provides a Pourable, Non-Sedimenting, fluid, liquid detergent composition consisting essentially of water and (A) from 10 to 20% based on the weight of the composition of a mixture of a substantially linear  $C_{10-18}$  alkyl benzene sulphonate and  $C_{10-20}$  alkyl 1-10 mole ethoxy sulphate; (B) at least 15% by weight of the composition of total Builder partly present as suspended solid, selected from sodium tripolyphosphate, zeolite, sodium carbonate, sodium silicate and mixtures thereof; (C) an aqueous Separable Phase containing sufficient dissolved Electrolyte selected from sodium

tripolyphosphate, sodium carbonate, sodium silicate and mixtures thereof to provide from 2 to 4.5 gm ions per litre sodium in said phase; and (D) optionally any of the Usual Minor Ingredients; the Payload of said composition being above the minimum at which the composition is Non-sedimenting but below the maximum at which it is Pourable.

In an alternative Formulation the anionic surfactant consists substantially of alkyl sulphate and/or, alkyl ether sulphate. The total concentration of Active Ingredients in the absence of foam booster is preferably from 15 to 50% of the Dry Weight of the composition. Typically the Active Ingredients comprise an average of from 0 to 5 e.g. 0.5 to 3 ethyleneoxy groups per molecule of sulphated surfactant. The fatty alkyl chain length is preferably from 10 to 20C, higher chain lengths being preferred with higher ethylene-oxy content.

The foregoing types may be varied by substituting for all or part of the anionic active content, any of the sulphated or sulphonated anionic surfactant classes hereinbefore specified.

Soap may be added to any of the foregoing detergent Formulations as an aid to rinsing the fabric. Soap is preferably present for this purpose in concentrations of from 0 to 6% preferably 0.1 to 4% e.g. 0.5 to 2% by Dry Weight of the composition. The amount of Soap is preferably less than 25% of the total sulphated and sulphonated surfactant, to avoid foam suppression; typically less than 10%.

Foam boosters and/or stabilisers may be incorporated in any of the foregoing types of high foam anionic detergent. The foam boosters or stabilisers are typically  $C_{10-18}$  alkyl nonionic surfactants such as coconut monoethanolamide or diethanolamide or their ethoxylates, alkyl phenol ethoxylates, fatty alcohols or their ethoxylates or fatty acid ethoxylates. The foam booster and/or stabiliser is added typically in proportions up to 20% of the Dry

Weight of the composition e.g. 0.1 to 6% preferably 0.5 to 4%. The presence of foam booster and/or stabiliser may permit a reduction of total concentration of Active Ingredients in a high foam product. Typically, compositions comprising alkyl benzene sulphonate with a foam booster and/or stabiliser will contain from 15 to 40% of alkyl benzene sulphate based on the weight of the composition preferably 20 to 36% e.g. 25% with from 2 to 6% e.g. 4% of nonionic surfactant, the lower proportions of anionic surfactant being preferred with higher proportions of nonionic surfactant and vice versa. The other sulphated or sulphonated anionic surfactant Formulations discussed above may be similarly reduced in active concentration by inclusion of foam boosters and/or stabilisers.

The Builder is preferably sodium tripolyphosphate, optionally but preferably with a minor proportion of soluble silicate although the alternative Builders hereinbefore described may be employed instead, as may mixed Builders. The proportion of Builder in type "A" Formulations is usually at least 30% of the Dry Weight of the composition, preferably from 35% to 85% e.g. 40 to 80%. Builder proportions in the range 50 to 70% of Dry Weight are particularly preferred. The Builder to Active Ingredients ratio should desirably be greater than 1:1 preferably from 1.2:1 to 4:1 e.g. from 1.5:1 to 3:1.

Low foaming Formulations are generally dependent upon the presence of lower proportions of sulphated or sulphonated anionic surfactant than in the high foam types together with higher, but still minor, proportions of Soap, and/or the addition of non-ionic, silicone, or phosphate ester foam depressants.

Our invention therefore provides, according to a further specific embodiment, a Non-sedimenting Pourable fluid, aqueous based detergent composition, comprising an at least predominantly aqueous phase containing Electrolyte in solution, and suspended particles of Builder, said composition comprising from 15 to 50% based on Dry Weight of Active Ingredient, at least 30% of Builder based on Dry Weight, a ratio of Builder to Active Ingredient greater than 1:1,

and optionally the Usual Minor Ingredients, wherein the surfactant comprises from 15 to 50% based on the Dry weight of the composition of sulphated and/or sulphonated anionic surfactant and an effective amount of at least one foam depressant.

Preferably, the foam depressant is selected from Soap, in a proportion of from 20 to 60% based on the weight of sulphated or sulphonated anionic surfactant, C alkyl nonionic foam depressant in a proportion of up to 10% of the Dry Weight of the composition, C alkyl phosphate ester in a proportion of up to 10% of the Dry Weight of the composition and silicone antifoams.

The function of Soap as a foam depressant is dependant on the proportion of Soap to sulphated or sulphonated anionic surfactant. Proportions of 10% or less are not effective as foam depressants but are useful as rinse aids in high foaming detergent compositions. Foam depressant action requires a minimum proportion of about 20% of soap based on the sulphated and/or sulphonated surfactant. If the proportion of soap to sulphated/sulphonated surfactant in a type "A" detergent is above about 60% by weight, the foam depressant action is reduced. Preferably, the proportion of Soap is from 25 to 50% e.g. 30 to 45% of the weight of sulphated/sulphonated surfactant.

Low foaming detergents may contain, in addition to, or instead of soap, a nonionic foam depressant. This may, for example, be a C acyl monoethanolamide e.g. rape monoethanolamide, a 16-22 alkyl phenol ethoxylate, C alcohol ethoxylate or 16-22 fatty acid ethoxylate. Alternatively, or additionally, the composition may contain an alkali metal mono and/or di C alkyl phosphate ester. The nonionic or phosphate ester foam depressant is typically present in the Formulation in a proportion of up to 10%, preferably 2 to 8% e.g. 3 to 4% based on Dry Weight.

Silicone antifoams may also be used, as or as part of, the foam depressant. The effective concentration of these last in the formulation is generally substantially lower than in the case of the other foam depressants discussed above. Typically, it is less than

2%, preferably less than 0.1%, usually 0.01 to 0.05% e.g. 0.02% of the Dry Weight of the formulation.

Our Formulations preferably contain the Usual Minor Ingredients. Certain fabric softeners, such as clays, may be included, however cationic fabric softeners are not normally effective in anionic based Formulations, but may sometimes be included in specially formulated systems.

The type "B" Formulations of our invention comprise Soap as the principal active component. They may additionally contain minor amounts of nonionic or other anionic surfactants.

The typical percentage Dry Weight of type "B" Formulations may be rather lower than type "A", e.g. 20 to 60%, preferably 29 to 45%. The total proportion of Active Ingredients is usually between 10 and 55%, preferably 15 to 40% e.g. 20 to 30% of the Dry Weight of the composition. Builder proportions are typically 20 to 80% of Dry Weight. In general the mobility of type "B" Formulations can be improved by including sufficient water soluble inorganic electrolyte, especially sodium silicate, in the Formulation.

High foam Soap Formulations may typically contain Active Ingredient consisting substantially of Soap, optionally with a minor proportion of a nonionic foam booster and/or stabilizer as described in relation to type "A" Formulations, and/or with sulphated anionic booster such as alkyl ether sulphate or alkyl ether sulphosuccinate.

Low foam type B Formulations may contain a lower concentration of Soap together with minor proportions of sulphated and or sulphonated anionic surfactant, nonionic or phosphate ester foam depressants and/or silicone antifoams.

The relationship between sulphated and/or sulphonated anionic surfactants and Soap in a type "B" low foam formulation is the converse of that in a type "A" low foam formulation. In a type "B" formulation, the sulphated and/or sulphonated anionic surfactant

acts as foam suppressant when present in a proportion of from about 20 to about 60% of the weight of the Soap.

The nonionic, phosphate ester and silicone foam depressants are, conveniently, substantially as described in relation to type "A" detergents.

"Type "B" detergents may contain any of the Usual Minor Ingredients. As in the case of type "A" Formulations, cationic fabric softeners are not normally included, but other fabric softeners may be present.

Non-ionic based detergents (type "C") represent a further aspect of the present invention. There has been a trend towards the use of non-ionic surfactants in laundry detergents because of the increasing proportion of man-made fibre in the average wash. Non-ionics are particularly suitable for cleaning man-made fibres. However, no commercially acceptable, fully built, non-ionic liquid detergent has yet been marketed.

Even in the detergent powder field, the choice and level of non-ionic surfactant has been restricted. Many of the detergent Formulations of our invention hereinbefore described have been designed to give stable, Pourable, fluid detergent compositions having a washing performance equivalent to existing types of powder Formulation, or to compositions which could readily be formulated as powders. However, it has not hitherto been possible to formulate certain types of potentially desirable nonionic based detergents satisfactorily, even as powders. This is because "solid" compositions containing sufficiently high proportions of the desired nonionic surfactant often form sticky powders which do not flow freely and may give rise to packaging and storage problems. Such surfactants have therefore had to be restricted to below optimum proportions of detergent powders, or to low Pay Load, dilute, or light duty, liquid compositions.

Preferably the surfactant is present as a hydrated solid or liquid crystal Separable Phase.

Any of the nonionic surfactants hereinbefore described or any mixture thereof may be used according to this embodiment of the invention. Preferably, the surfactant comprises a C alkyl group, usually straight chain, although branched chain and/or unsaturated hydrocarbon groups are not excluded. Preferably, the nonionic surfactants present have an average HLB of 12 to 15.

The preferred nonionic surfactant in Type C Formulations is fatty alcohol ethoxylate.

For high foam type "C" Formulations, we prefer C 12-16 nonionics having 8 to 20 ethylenoxy groups, alkyl phenol ethoxylate having 6-12 aliphatic carbon atoms and 8 to 20 ethyleneoxy groups together optionally with a minor proportion e.g. 0 to 20% of the Dry Weight of the composition of anionic surfactant preferably sulphated and/or sulphonated anionic e.g. alkyl benzene sulphonate, alkyl sulphate, alkyl ether sulphate, paraffin sulphonate, olefin sulphonate or any of the other sulphated or sulphonated surfactants described above, but not including substantial amounts of any foam depressant. The Formulation may however include a nonionic foam booster and/or stabiliser such as C acyl monoethanolamide typically in proportions as described above in relation to type "A" Formulations. Preferably the non-ionic Active Ingredients together have an HLB of 12-15.

Low foam nonionic compositions according to our invention are especially preferred. They preferably comprise 10 to 40% based on Dry Weight of the composition of C alkyl 5 to 20 mole ethyleneoxy, nonionic surfactants such as fatty alcohol ethoxylates, fatty acid ethoxylates or alkyl phenol ethoxylates, having a preferred HLB of 12 to 15. They optionally contain a minor proportion, e.g. up to 10% by weight of the composition of any of the anionic sulphated and/or sulphonated surfactants hereinbefore

described in relation to type "A" detergents, and they contain a foam depressant such as a mono, di- or trialkyl phosphate ester or silicone foam depressant, as discussed hereinbefore in the context of low foaming type "A" detergents.

Type "C" Formulations may contain any of the Usual Minor Ingredients.

In particular, nonionic based detergents of our invention may incorporate cationic fabric softeners. The cationic fabric softeners may be added to type "C" Formulations, in a weight proportion based on the nonionic surfactant of from 1:1.5 to 1:4 preferably 1:2 to 1:3. The cationic fabric softeners are cationic surfactants having two long chain alkyl or alkenyl groups, typically two C alkyl or alkenyl groups, preferably two tallowyl groups. Examples include di C alkyl di (lower, e.g. C alkyl) ammonium salts, e.g. di tallowyl dimethyl ammonium chloride, di (C alkyl) benzalkonium salts e.g. ditallowyl methyl benzyl ammonium chloride, di C alkyl amido imidazolines and di C acyl amido amines or quaternised amino amines, e.g. bis (tallow amido ethyl) ammonium salts.

Formulations containing cationic fabric softeners preferably do not contain sulphated or sulphonated anionic surfactants or soaps. They may however contain minor proportions of anionic phosphate ester surfactants e.g. up to 3% by weight of the composition preferably up to 2%. They may additionally or alternatively contain minor proportions (e.g. up to 3%, preferably 1 to 2% by weight of amphoteric surfactants such as betaines and sulphobetaines. They may also contain smectite clays, and the Usual Minor Ingredients.

#### Minor Ingredients

Compositions of the invention may contain the Usual Minor Ingredients. Principal of these are antiredeposition agents, optical brightening agents and bleaches.

The most commonly used antiredeposition agent in making detergents is sodium carboxymethyl cellulose (SMC), and we prefer that this be present in compositions of this invention, e.g. in conventional amounts, e.g. greater than 0.1 but less than 5%, and more usually between 0.2 and 4%, especially 0.5 to 2% preferably 0.7 to 1.5%. Generally speaking SCMC is effective at concentrations suitable for use in powder detergents. The OBA may be present in conventional amounts. However we have found that OBA's in some liquid detergent (e.g. type "C" formulations) tend to be slightly less efficient than in powder detergents and therefore may prefer to add them in slightly higher concentrations relative to the Formulation than is normal with powders. Typically concentrations of OBA between 0.05 and 0.5% are sufficient e.g. 0.075 to 0.3% typically 0.1 to 0.2%. Lower concentrations could be used but are unlikely to be effective, while higher concentrations, while we do not exclude them, are unlikely to prove cost effective and may, in some instances give rise to problems of compatibility.

Typical examples of OBA's which may be used in the present invention include: ethoxylated 1, 2-(benzimidazolyl) ethylene; 2-styrylnaphth[1,2d-]oxazole; 1,2-bis(5' methyl-2-benzoxazolyl) ethylene; disodium-4,4'-bis(6-methylethanolamine-3-anilino-1,3,5-triazin-2"-yl)-2,2'-stilbene sulphonate; N-(2-hydroxyethyl-4,4'-bis (benzimidazolyl)stilbene; tetrasodium 4,4'-bis [4"-bis(2"-hydroxymthyl)-amino-6"(3"-sulphophenyl) amino-1", 3", 5"-triazin-2"-yl amino]-2,2'-stilbenedisulphonate; disodium-4-(6"-sulphonaphtho[1',2'-d]triazol-2-yl)-2-stilbenesulphonate; disodium 4,4'-bis [4"-(2"'-hydroxyethoxy)-6"-amino-1",3",5"-triazin-2"-yl amino] 2,2'-stilbenedisulphonate; 4-methyl-7-dimethyl aminocoumarin; and alkoxylated 4,4'-bis-(benzimidazolyl) stilbene.

Bleaches may optionally be incorporated in liquid detergent compositions of our invention subject to chemical stability and compatibility. Encapsulated bleaches may form part of the suspended solid.

The action of peroxy bleaches in compositions of our invention may be enhanced by the presence of bleach activators such as tetra acetyl ethylenediamine, in effective amounts.

Photoactive bleaches such as zinc or aluminium sulphonated phthalocyanin, may be present

Perfumes and colourings are conventionally present in laundry detergents in amounts up to 1 or 2%, and may similarly he present in compositions of our invention. Provided normal care is used in selecting additives which are compatible with the Formulation, they do not affect the performance of the present invention.

Proteolytic and amylolitic enzymes may optionally be present in conventional amounts, together optionally with enzyme stabilizers and carriers. Encapsulated enzymes may be suspended.

Other Minor Ingredients include germicides such as formaldehyde, opacifiers such as vinyl latex emulsion and anticorrosives such as benzotriazole.

Compositions of our invention are, in general, suitable for laundry use and our invention provides a method of washing clothes or other soiled fabric by contacting and, preferably, agitating them in an aqueous wash liquor containing any composition of the invention as described herein. Low foam compositions herein described are in particular of use in automatic washing machines. The compositions may also be used in the washing of dishes, or the cleaning of hard surfaces, the low foam products being particularly suitable for use in dishwashing machines. These uses constitute a further aspect of the invention.

Compositions of our invention may, generally, be used for washing clothes in boiling water, or for washing at medium or cool temperatures, e.g. 50 to 80°C, especially 55 to 68°C, or 20 to 50°C especially 30 to 40°C, respectively. Typically the compositions may be added to the washwater at concentrations of

between 0.05 and 3% Dry Weight based on the wash water preferably 0.1 to 2%, more usually 0.3 to 1% e.g. 0.4 to 0.8%.

The invention will be illustrated by the following examples: wherein all figures relate to % by wt. based on total composition, unless otherwise stated.

#### Compositions of the Various Feedstocks Materials

### 1. Sodium $C_{10-14}$ linear alkyl benzene sulphonate

For all formulations the alkyl benzene sulphonate used was the sodium salt of the largely para-sulphonated "Dobane" JN material. (Dobane is a Registered Trade Mark).

The composition is as follows:-

C10	Сјј	$c_{12}$	C <sub>13</sub>	C <sub>14</sub>	C <sub>15</sub>
13.0	27.0	27.0	19.0	11.0	1.0

This composition refers only to the alkyl chain length.

#### 2. Coconut Monoethanolamide

Has the following composition:RCO(NHCH<sub>2</sub>CH<sub>2</sub>OH)

where R is as follows:-

	C <sub>5</sub>	0.5%
	C <sub>7</sub>	6.5%
	و٥	6.0%
	C <sub>11</sub>	49.5%
	C <sub>13</sub>	19.5%
	C <sub>15</sub>	8.5%
Stearic	C <sub>17</sub>	2.0%
Oleic	C <sub>17</sub>	6.0%
Linoleic	C <sub>17</sub>	1.5%

#### 3. Sodium alpha olefin sulphonate

This material is the sodium salt of sulphonated  $C_{16}/C_{18}$  olefin having the following approximate composition.

55.0%	C <sub>16</sub>	Terminal	olefin
45.0%	C <sub>18</sub>	Terminal	olefin

### 4. C12-18 Alcohol + 8 moles Ethylene Oxide

This material is an average 8 mole ethylene oxide condensate of an alcohol of the following composition:-

C <sub>10</sub>	3.0%
C <sub>12</sub>	57.0%
C <sub>14</sub>	20.0%
C <sub>16</sub>	9.0%
C <sub>18</sub>	11.0%

# 5. Sodium $C_{14-17}$ n-Alkane Sulphonate

This material was prepared by neutralising sulphonated  $C_{14}$ -  $C_{17}$  normal paraffins with sodium hydroxide and contained 10% disulphonates based on total Active Ingredients.

### 6. Sodium C12-C18 Sulphate

This refers to the sodium salt of a sulphated fatty alcohol having the following composition:-

C10	3.0%
C <sub>12</sub>	57.0%
C <sub>14</sub>	20.0%
C <sub>16</sub>	9.0%
C18	11.0%

#### 7. Sodium Tripolyphosphate

This material was added as anhydrous Na5P3010 containing 30% Phase I.

#### 8. Sodium Silicate

This material is added to Formulations as a viscous aqueous solution containing 47% solids with a Na<sub>2</sub>0:SiO<sub>2</sub> ratio of 1:1.6.

#### 9. Optical Brightener

The optical brightening agent for Examples 51 to 66 was the disodium salt of 4;4'- [di(styryl-2-sulphonic acid)] biphenyl which is marketed under the trademark "TINOPAL CBS-X". The optical brightener for Examples 1 to 50 was a mixture of the aforesaid Optical brightener with the disodium salt of 4;4'- [di(4-chlorostyryl-3-sulphonic acid)] biphenyl which mixture is marketed under the trademark "TINOPAL ATS-X".

#### Note

All alcohols and their ethylene oxide adducts referred to are straight chained and primary.

All the examples were prepared by adding the surfactant, usually as hydrated solid, to a 47% solution of the silicate. The other ingredients were then added in the order shown in the tables reading from top to bottom, except that the principal Builder was added last. At each stage, a small addition of water was made, whenever it was required in order to maintain a fluid homogeneous system. Finally, the composition was diluted to the desired percentage Dry Weight. The entire preparation was carried out as close as possible to ambient temperature consistent with adequate dispersion of the ingredients. In the case of examples 20,21,22 and 23, a concentrated aqueous solution of the electrolyte (i.e. sodium sulphate, sodium chloride, sodium carbonate and potassium carbonate respectively) was used in place of the solution of silicate in the above procedure. In some instances, especially with relatively high melting non-ionic surfactants, such as coconut monoethanolamide, gentle warming e.g. to about 40°C was required to ensure complete dispersion. In all the Examples in which sodium tripolyphosphate was used in substantial amounts this temperature was achieved by the heat of hydration without external heating.

	Eg. 1	Eg. 2	Eg. 3	Eg. 4	Eg. (a)	5 (b)	(c)	Eg. 6	Eg. 7	Eg. 8
Sodium C <sub>10-14</sub> linear alkyl benzene sulphonate	12.4	. 15.9	12.2	15.6	11.2	12.0	13.0	14.0	12.0	12.0
Coconut monoethanolamide	1.6	2.1	1.6	2.1	1.5	1.6	1.7	1.9	1.6	1.6
Sodium tripolyphosphate	26.0	19.1	25.6	18.7	26.2	28.0	30.4	32.7	28.0	28.0
Sodium Silicate	6.5	8,5	6.4	6.3	6.0	6.4	7.0	7.5	6.4	6.4
Sodium carboxymethyl cellulose	<b>.</b>	ı	1.4	1.8	1.5	1.6	1.7	1	1.6	1.6
Optical Brightening Agent	ı	1	.0.2	0.2	0.15	0.16	0.17	0.18	1	0.16
Benzotriazole	. 1	1	1	1	ı	t	•	1	1	0.007
Perfume	ı	1	ŧ	t	1	1	ŧ	1	1	0.03
Water	to 100	to 100	to 100	to 100	to 100	to 100	) to 100	0 to 100	to 100	700 ot

!

	Eg. 9	6	Eg. 10	10			
	(a)	(p)	(a)	(p)	Eg. 11	Eg. 12	
Sodium C <sub>10-14</sub> linear alkyl benzene sulphonate	11.6	12.6	17.0	18.0	11.6	6*6	
Coconut monoethanolamide	1.5	1.7	1.5	1.5	1.5	1.3	
Sodium tripolyphosphate	30.2	32.7	25.5	27.0	25.7	23.1	
Sodium Silicate	6.2	6.7	5.8	6.2	3. 5	5,3	
Sodium carboxymethyl cellulose	1.5	1.7	1.5	1.5	1.5	2.0	
Optical Brightening Agent	0.15	0.17	0.16	0.17	0.13	. 0.14	
Water	to 100	to 100					

Components	Eg. 13	Eg. 14	Eg. 15	Eg. 16	Eg. 17	Eg. 18	Eg. 19
Triethanolamine C16-C18 alkyl sulphate	0.6	ı	1	ı	ŧ	t	ŧ
Sodfum C16-18 alkyl sulphate	<b>i</b>	10.0	1	1	ı	ı	1
Sodium salt of alpha. sulpho C16-18 fatty acid methyl ester	t	ŧ	8 5	ŧ	1	1	ı
Sodium salt of three mole ethoxylate of C16-18 alcohol sulphate	1		1	9.6	ı	í	ı
Disodium C16-18 alkyl sulphosuccinamate	1	i	ı	i	10.8	1	,
Sodium salt of two mole ethoxylate of C12-14 alcohol sulphate	1	1	t	1	ı	10.8	ı
Sodium C9-C13 linear alkylbenzene sulphate	1	1	1	ı	1	1	12.0
Coconut monoethanolamide	1.2	1.3	1.1	.13	1.4	1.5	1.6
Sodium tripolyphosphate	21.0	23.4	19.8	22.5	25.3	25.3	28.1
Sodium silicate	4.8	5.4	4.5	5.1	<b>3.</b> 8	5.9	6.5
Sodium carboxymethyl cellulose	1.2	1.3	1.1	1.3	1.4	1.5	•
Optical brightening agent	0.11	0.12	0.10	0.13	0.14	0.14	
Water	to 100	to 100	to 100	to 100	to 100	to 100	7 <b>0091</b> :::
			•		•		

					1	1		٠
Components	Eg. 20	Eg. 21	Eg. 22	Eg. 23	Eg (a)	Eg. 24 (b)	(c)	Eg. 25
Sodium C10-14 linear alkylbenzene sulphonate	12.1	12.1	12.1	12.1	15.0	17.0	18.0	12.5
Coconut monoethanolamide	1.6	1.6	1.6	1.6	•	ı	8	1.7
Sodium tripolyphosphate	28.2	28.2	28.2	28.2	16.7	18.9	20.0	29.1
Sodium silicate	í	ı	1	î		3.8	4.0	ľ
Sodium sulphate	7.5	1	1	t	1	ŧ	ı	t
Sodium chloride	ŧ	6.2	ı	ŧ	i	1	1	ı
Sodium carbonate	1	f	5.6	I	4.2	4.7	5.0	ı
Potassium carbonate	t	ı	ı	7.3	1	ı	1	1
Sodium carboxymethyl cellulose	1.6	1.6	1.6	1.6	1.3	1.5	1.6	1.7
Optical brightening agent	0.15	0.15	0.15	0.15	0.17	0.19	0.20	0.15
Water	to 100	to 10	to 100 to 100 to 100 to	Ä				

Components	Eg. 26	Eg. 27	Eg. 28	Eg. 29	Eg. 30	Eg. 31	Eg. 32
Sodium C10-14 linear alkylbenzene sulphonate	11.2	10.2	16.1	15.0	13.3	10.2	14.2
Coconut monoethanolamide	1.5	1.3	2.2	1.9	1.8	1.4	1.9
Zeolite A	34.8	15.8	f	1	ı	ı	ı
Trisodium Citrate	1	1	1	1	31.0	ŧ	ı
Trisodium nitrilo triacetate	1	8	30.6	14.0	1	ı	i
Sodium Tripolyphosphate	1	15.8	1	14.0	i	15.8	33.1
Sodium Orthophosphate	,	t	1	1	1	8.8	ŧ
Sodium silicate	0.9	យ	8.8	D 6		7.0	CO FA
Sodium carboxymethyl cellulose	មា	<del>ن</del> ا	2.2	6.1	8		
Optical brightening agent	0.14	0.13	0.2	0.19	0.17	0.13	0.18
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100

- 53; -

Components	Eg. 33	Eg. 34
Sodium C10-C14 linear alkylbenzene sulphonate	12.0	13.1
Coconut monoethanolamide	1.6	1.7
Sodium Tripolyphosphate	28.0	30.7
Sodium silicate	6.4	7.0
Sodium xylene sulphonate	-	5.5
Sodium carboxymethyl cellulose	1.6	1.7
Optical brightening agent	-	0.18
Detergent Enzymes (Esperase Slurry 8.0)	0.07	-
Water	to 100	to 100

Components	Eg. 35	Eg. 36	Eg. 37	Eg. 38	Eg. 39	Eg. 40	Eg. 41	Eg. 42	
Triethanolamine C16-18 alkyl sulphate	7.9	1	1	i	1	ì	1	1	
Sodium C16-18 alpha olefin sulphonates	1	11.0	12.8	12.4	t	1	ŧ	1	
Sodium C14-C17 n-alkane sulphonate	ı	1	ŧ	1	12.0	11.1	12.4	13.2	
Coconut monoethanolamide	1.1	1.5	1.7	1.7	1.6	1.5	1.7	1.7	
Sodium tripolyphosphate	18.5	25.7	30.1	29.1	28.1	25.9	29.1	30.8	
Sodium silicate	6.4	5.9	8.6	10.1	6.5	7.4	10.1	12.4	
Sodium carboxymethyl cellulose	1.1	1.5	1.7	1.7	1.6	1.5	1.7	1.7	Ċ
Optical brightening agent	0.10	0.14	0.17	0.16	0.16	0.14	0.16	0.16	170
Water	to 100 6	091							

	E,	g. 48		
Components	(a)	(.b)	(c)	Eg. 49
Sodium C10-14 linear alkylbenzene sulphonate	8.5	9.0	10.0	3.6
Fifteen moles ethoxylate of C16-C18 alcohol	-	-	-	7.1
Sodium salt of a 50:50 mixed mono and di C16-18 alkyl phosphate	1.7	1.8	2.0	-
Sodium tripolyphosphate	25.5	27.0	29.0	24.9
Sodium silicate Sodium carboxymethyl cellulose	5.1 1.4	5.4 1.4	6.0 1.6	3.6 0.7
Optical brightening agent	0.17	0.18	0.20	0.14
Silicone defoamer	-	-	-	0.02
Water	to 100	to 100	to 100	to 100

Components	(a) Eg	Eg. 50	(2)	F. 5.1	7. CR	7. 7.	73	
	3	2	3			rg • 62		E.G. 53
Sodium salt of three mole ethoxylate of C12-15 alcohol sulphate	t	ı	1	1	ì	3.7	1	ı
Sodium C10-14 linear alkylbenzene sulphonate	•	1	1	1	4.1	ı	ı	i
Coconut monoethanolamide	1.8	2.1	2.3	2.6	ı	1	ı	t
Eight mole ethoxylate of C12-18 alcohol	5.8	9.9	7.5	ı	8.2	7.5	10.8	4.6
2-tallow-1-methyl-1-(tallow-amidoethyl) imidazoline methyl sulphate	1	ı		1	1	1	ı	2.5
Sodium salt of a 50:50 mixed mono and di C16-18 alkyl phosphate	•	1	1	1	0.8	0.7	0.7	9.0
Fifteen moles ethoxylate of C16-C18 alcohol	,	ı	1	1	. 1	ı	î	4.6
Five mole ethoxylate of C13-C15 alcohol	1	ı	1	8.3	t	1	i	i
Sodium tripolyphosphate ·	21.4	24.5	27.5	30.6	24.6	22.4	21.8	21.7
Sodium silicate	4.9	5.6	6.3	7.0	0.9	5.5	5.3	5.0
Sodium carboxymethyl cellulose	1.0	1.1	1.3	1.4	1.2	•••• • •	1.0	0.9
Optical brightening agent	0.11	0.12	0.14	0.15	0.13	0.12	0.11	1
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100	20 1 20 1

Components Sodium C <sub>10–14</sub> Linear Alkyl Benzene Sulphonate	Eg. 56 -	Eg. 57 11.4	Eg. 58 11.8	Eg. 59	Eg. 60
Sodium C <sub>12</sub> branched chain Alkyl Benzene Sulphonate	11.4	t	t	1	ı
Coconut monoethanolamide	1.5	ŧ	`1	1.6	1.4
Coconut diethanolamide	t	1.5	1	ŧ	ı
Sodium ethylenediamine tetrakis (methenephosphonate)	i	-1	1	0.25	2.3
Sodium Tripolyphosphate	26.7	26.7	27.6	28.0	25.5
Sodium Silicate	6.2	6.2	6.4	6.4	5.8
Sodium Carboxymethylcellulose	1.5	1.5	1.6	1.6	1.4
Optical Brightening Agent	0.15	0.15	0.15	0.15	0.13
Water	to 100	to 100	to 100	to 100	to 100

- 59 -

	Eg. 61	Eg. 62
Sodium C10-14 Linear alkyl benzene sulphonate	5.2	6.5
Sodium C16-18 Alkyl Sulphate	3.7	4.6
Sodium 1 mole ethoxy C14-15 alkyl ether sulphate	4.5	5.5
C12-18 alcohol 8 mole ethoxylate	1.5	1.9
Sodium Tripolyphosphate	-	29.6
Sodium silicate	18.6	-
Sodium carbonate	14.9	-
Sodium carboxymethylcellulose	1.5	1.8
Optical Brightening Agent	0.15	0.18
Water	to 100	to 100

Sodium C <sub>10-14</sub> linear alkylbenzene sulphonate	Eg. 63	Eg. 64	Eg. 65 11.5	Eg. 66 10.9
Sodium C <sub>14-16</sub> alkyl olefin sulphonate	17.9	17.9	1	ı
Sodium C <sub>16-18</sub> alkyl sulphate	ı	1	7.6	7.2
C <sub>12-18</sub> alcohol 8 mole ethoxylate	2.7	2.7	2.9	2.7
Sodium Tripolyphosphate	13.4	1	14.3	
Zeolite A	1	13.4	,	13.6
Sodium Silicate	8.9	8,9	9.6	9.0
Sodium Carboxymethylcellulose	1.4	1.4	1.5	1,5
Optical Brightening Agent	0.14	0.14	0.15	0.15
Water	to 100	to 100	to 100	to 100

\_ 61 \_

Of the Examples, 1 and 2 represent a basic type A Formulation. 3 and 4 a type A formulation with SCMC and optical brightener, 5(a), (b) and (c) represent a type A Formulation at three different Pay loads, 6 and 7 demonstrate that neither SCMC nor optical brightener is essential to obtain a Non-sedimenting Formulation; 8 contains anticorrosive and perfume; 9 (a) and (b) illustrate a high Builder to Active ratio Formulation (3:1) at two Pay Loads, 10(a) and (b) illustrate a relatively low Builder to Active Formulation at two Pay Loads; 11 corresponds to a Non-sedimenting Formulation obtained by centrifuging the Formulation of Example 9 at low Payload for only three hours and decanting the supernatent liquor; 12 illustrates the effect of relatively high SCMC levels; 13 to 19 illustrate Type A Formulations with various anionic surfactants; 20 to 24 illustrate various Electrolytes, and 25 is a Formulation in which sodium tripolyphosphate is the sole Electrolyte; 26 to 31 illustrate various Builders and mixtures thereof; 32 is a high Builder to Active Formulation; 33 is an enzyme Formulation; 34 contains Hydrotrope; 35 has a triethanolamine salt of the surfactant; 36 to 38 illustrate olefin sulphonate and 39 to 42 paraffin sulphonate Formulations, in each case with successively increased Electrolyte; 43 to 46 illustrate type B formulations, 43 at three Pay Loads and 44 to 46 with increasing Electrolyte; 47 corresponds to Type B Formulation obtained after centrifuging 43 at low Pay Load for only three hours; 48 and 49 illustrate low foam Type A and C Formulations respectively; 50 to 54 illustrate various Type C Formulations; 55 is a Type C Formulation with cationic fabric softener; 56 illustrates a branched chain alkyl benzene sulphonate, 57 coconut diethanolamide and 58 a nonionic free formulation; 59 and 60 illustrate the use of phosphonate builders; 61 to 62 relate to formulations particularly adapted to different parts of the North American market, being respectively phosphate free and high phosphate; 63 to 66 are formulations adapted to the needs of certain Asian markets.

The comparative example represents a commercial Formulation currently being marketed in Australia corresponding to Australian Patent 522983. The comparative example was the material as purchased, except for the neutron scattering results which were carried out on a sample prepared in accordance with the example of the patent to match the commercial Formulation as analysed and using deuterium oxide instead of water. The composition, by analysis was; were

A. Corresponding to Australian P. 522983 (Example)	%
Sodium ClO-14 linear alkylbenzene sulphonate	12
Sodium salt of three mole ethoxylate of	3
C12-15 alcohol sulphate	
Sodium tripolyphosphate	15
Sodium carbonate	2.5
Optical brightener (Tinopal LMS)	0.5
Sodium carboxymethyl cellulose	1.0
Water	to 100

#### 3. Example Test Results

The foregoing examples were subjected to various tests, the results of which are tabulated:

Note The Phases separated from the centrifuge test are numbered from the bottom (i.e. the densest layer) upwards.

Examples	1		2	
1. Centrifuge Test Results				
i. No. of Phases Separated	1	2	! 1	2
ii. Description	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin
		liquid		liquid
iii. Proportion (%)	80.9	19.1	_	
iv. Surfactant content (%)	-	人0.1	_	
v. Loss on Drying at 1109 (%)	-	74.8		
vi. Viscosity (Pa.S) at 2093	_	0.01		
2. Classification (Group)	111		111	
by Centrifuging				
3. Viscosity (Pa.S)				
4. Yield Points (Dynes/an2)				
5. Neutron Diffraction Results				
i. Micellar scattering				
ii.a No. of other peaks				
b Description				
c Structural repeat distance (Å)				
iii. Suggested Structure				
6. X-ray Diffraction Results				
i. Micellar Scattering				
ii.a No. of other peaks				
b Description				
c Structural repeat distance (A)				
iii. Suggested Structure				·
7. Electron Microscopy Results				
i. Corresponding Figure No.				
ii. Description				
8. Mobility	Pourable		Pourable	
9. Stability	No sediment	tation over	No sediment	ation
	12 months at	t ambient	over 12 mont	hs at
	laboratory t	temperatures	ambient labo	ratory
	!		: temperature	

Examples	3		4		5(a)	
1.						
i.	1	2	1	2	1	2
ii.	Opaque	clear	Opaque	clear	Opaque	clear
		thin	solid/paste	thin	solid/paste	thin
		liquid		liquid		liquid
iii.			-		75	25
iv.						0.1
٧.						77.3
vi.						0.01
2.	III		III		III	
3.	-		-		1.70	
4.					12	
5.						
<u>i.</u>					Present - na	rrow
ii.a					one	
<u>a</u>					narrow	
c					33.4 A	
iii.					Lamellar hyd	rated soli
6.						
i.				, .,		
ii.a						
b	•					
iii.						
7.		<u></u>				
<u>i.</u>						<del>,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,</del>
ii.						
8.	Pourable		Pourable		Readily pour	able
9.	No sedimentat	ion over	No sedimenta	ation	No sediment	
	12 months at a	ambient	over 12 month	ths at	12 months a	t ambient
	laboratory ts	nperatures	ambient tem	perature	temp.	

xamples	5(b)		5(c)		917	70091
·•	3(0)					
	1	2	1	2	1	2
	Opaque	clear	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
	<b>50.14</b> pas se	liquid	•	liquid		iiquid
iii.	81.7	18.3	86	14%		
iv.		0.1	-	0.1		
٧.		75.7		74%		
vi.		0.01		0.01		
2.	III		III		III	
3.	2.60		4.86		4.58	
4.	36		178			
5.						
i.			Present-nam	W		
ii.a			two			
<u></u> b			narrow, broa	d		
			34.9 A, 26.7			
iii.			2 Discrete 1	amellar		
			structures			
6.						
i.			Present			
ii.a	······································		one			
b			narrow			
C			31 A			
iii.			on ageing t	ime two lamellar		
,,,,			structures l	nave merged		
7.						
i.						*
ii.	Lamellar Fe	atures				
8.	Pourable		Viscous but	Pourable	Pourable	
9.	No sediment	ation over	No sediment	ation	No sediment	
	12 months a	at ambient also	over 12 mor	ths at	12 months a	t ambient
	3 months at	t 0° and 37°C	ambient ter	p.	temp.	

Examples	7		8		9(a)	
1.		:				
i.	1	2	1	2	1	2
ii.	Opaque .	clear	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
		liquid		liquid		liquid
iii.						
iv.						
٧.						
vi.						
2.	III		III		III	
3. 4.	3.04		2.84		4.00	
4.				<u> </u>		
5.						
<u>i.</u>						
ii.a				<u> </u>		
<u>b</u>		1				
<u>c</u>		1				
iii.						
6.						•
i.						
ii.a		i i		Ī		···
b					· · · · · · · · · · · · · · · · · · ·	
c		į.				
iii.		İ				
7.						
<u>i.</u> ii.					,	
71.						
8.	Pourable	   	Pourable		Pourable	
9.	No sedimentat	ion over	No sedimentat	ion	No sedimentat	ion over
	12 months at	ambient ;	over 12 month	is at	12 months at	ambient
	tem.	į	ambient temp.	1	temp.	

Examples 9(b)	10(a)		10(b)	
1.				
i. 1 2	1	2	1	2
ii. Opaque clear	Opaque	clear	Opaque	clear
solid/paste thin	solid/paste	thin	solid/paste	thin
liquid		liquid		liquid
iii.				
įv.				
٧.				
vi.				
2. III	III		III	
3. 8.75	3.85		8.00	
4.				
5.				
i				
ii.a				·····
b				
С				
iii.				
6.				
i			•	
ii.a				
b				
C				
iii.		-		
7.		•		
i				
ii.			·	
8. Viscous but pourable	Pourable		Viscous but	pourable
9. No sedimentation over	No sedimenta	ntion	No sedimenta	ation over
12 months at ambient	over 12 mont	ths at	12 months at	ambient
temp.	ambient temp	)•	temp.	

Examples	11		. 12		13	
1.						
<u>i.</u>	1	2	1	2	1	2
ii.	Opaque	clear	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
<del></del>		liquid		liquid		liquid
<u> 111.</u>						
iv.						
٧.						
<u>vi.</u>						
2.	III		III		III	
3.	2.48		0.93			
<u>4.</u> 5.					48	
5.						
<u>i.</u>						·
ii.a			<u> </u>			
<u> </u>						<del></del>
<u>c</u>						
iii.						
6.						<del> </del>
i.						
ii.a						
b				aga ang aga araway ang aga araway ang aga aga aga aga aga aga aga aga aga		
С						
iii.						
7.						
i.						
ii.						
8.	Pourable	\$ <u>\$</u>	Readily pour	able	Viscous but	Pourable
9.	No sedimentati	ion over	No sedimenta	ation	No sedimenta	tion over
	12 months at a	mbient	over 12 mont	ths at	12 months at	: ambient
	temp.		ambient temp	).	temp.	

Examples	amples 14		15		16		
1.							
i.	1	2	1	2	1	2	3
ii.	Opaque	clear	Opaque	clear	Opaque	clear	solid
	solid/paste	thin	solid/paste	thin	solid/paste	thin	
		liquid		liquid		liquid	
iii.	92.4% (w/w)	7.6%			72 (vol/vol)	12	16
iv.		1.7%				0.3	
<u>v.</u>		80.7%				76.3	<del>*</del>
vi.		0.01					
2.	III		III			<u> </u>	
3.	1.95		3.00			2.97	
2. 3. 4. 5.	<u> </u>						
5.							
<u>i.</u>							
<u>ii.a</u>							
<u>b</u>		****					
<u>. c</u>			1				
iii.							
6.							.,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,
i.							
ii.a						7	
b							
C							
iii.							
7.							
i.							·····
ii.							
8.	Pourable		Viscous bu	t pourable	Pou	rable	
9.	No sedimentation over		No sedimentation over		No sedimentation over		
	12 months at ambient		6 months at ambient		6 months at ambient		
	temp.		temp.		ten	p <b>.</b>	

xample						
.6	1	2	1	2	1	2
<u>i.</u>	Opaque	clear	Opaque	clear	Opaque .	clear
ii.	solid/paste	thin	solid/paste	viscous	solid/paste	thin
	5011d/pasa	liquid	·	liquid		liquid
	. 65.5	34.5	90 (vol/vol)	10		0.1%
		7.9				74.7%
iv.		72.1				0.01%
<u>v.</u>						
vi.	III		III		III	
2.	5.15		6.46		2.20	
3.	7.17		4		36	
4.						
5.			Present & in	cludes peak		
<u>i.</u>	_		one			
<u>ii.</u>			very narrow			
	<u>b</u>		57.6 Å			
	<u>c</u>		Micellar + "	G" Phase		
ii.	i •					
6.						
1.			very broad			
ii	-8		two			
<u></u>	b		narrow at 5	)Å, broad at 26Å		
	С		50 Å			
	i.		Micellar +	"G" Phase		
7.	-					
i.						
<u></u>						
•	•					
8.	Viscous but	t pourable	Viscous but	; pourable	Pourable	
	No sodimor	tation over	No sediment	tation over	No sediment	ation ov
9.	10 months		6 months		6 months a	t ambien
	-	מנ מוטוכוונ	temp.		temp.	
	tem.		I wib.			

Examples	20		21		01 22	70091
1.						
i	1	2	1	2	1	2
ii.	Opaque	clear	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
		liquid		liquid		liquid
iii.	<b>7</b> 5	25	78	22	75	25
iv.		0.1		0.1		0.4
٧.		74.6		79.6		79.1
vi.		0.01		0.01		0.01
2.	III		III		III	
3.	2.60		<b>4.2</b> 8		2.48	
4.						
5.				•		
i.			Present			
ii.a			one			
b			sharp			
c		•	33.4 Å			
iii.			Lamellar hyd	rated solid		
6.						
<u>i.</u>			Present		<u> </u>	
<u>ii.a</u>			one			
<u>b</u>			sharp			
<u>c</u>			32 Å			
iii.			Lamellar Hyd	rated solid		
7.						
<u>i.</u>						
ii.						
8.	Pourable		Viscous but	pourable	Pourable	
9.	No sedimenta	tion over	No sedimenta	ntion over	No sedimenta	
	12 months at	anbient	12 months at	t ambient	12 months a	
	temp. also 3	months at	temp. also 3	months at	temp. also	3 months at
	$0$ and $37^{\circ}$ C		0 and 37°C		0 and 37°C	

Examples 23		24(b)		24(c)		
1.						
<u>i.</u>	1	2	1	2	1	2
ii.	Opaque	clear	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
		liquid		liquid		liquid
iii.	. 70	30				·
iv.		0.1		0.1		0.1
<u>v.</u>		70.4		84		· 82.9
vi.	<u>.</u>	0.01		0.01		0.01
2.	III		III		III	
3.	3.21	····	0.88		1.87	
4.	·		-			
5.						
<u>i.</u>		V-1, 1, 2, 2, 3, 1, 1, 1, 2, 3, 1, 1, 1, 1, 1, 1, 1, 1, 1, 1, 1, 1, 1,				
ii.a	l	· <del></del>		<del>,,, ,, ,, ,, ,,,,,,,,,,,,,,,,,,,,,,,,</del>		
b	)					-
	· · · · · · · · · · · · · · · · · · ·				·	
iii.						
6.				<del></del>		
i.						
ii.a	<u> </u>	· · · · · · · · · · · · · · · · · · ·				<del></del>
<u> </u>						
						<del></del>
iii.	<del></del>			<del></del>		<del></del>
					·	
7.		_				
<u>i.</u>						
ii.						
8.	Pourable		Readily Poura	ble	Pourable	
9.	No sedimentat	ion over	No sedimentat	ion over	No sedimentat	ion over
-	12 months at		3 months at		12 months at	
	temp. also 3		temp.		temp.	entre runte
	0 and 37°C					
					•	

Examples	24(c)		25		26	
1.						
i	1	2	11	2	1	2
ii.	Opaque	clear	Opaque .	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
		liquid		liquid		liquid
iii.			60 (vo]/vo])	40		
iv.		0.1		0.1		
<u>v.</u>		80		84.6		<del></del>
vi.		0.01		0.01		
2.	III		III		III	
2.	2.38		2.20		1.99	
4.						
5.						
i.			Present - na	irrow		
<u>ii.a</u>	<del> </del>		one			
<u>b</u>			sharp		<u> </u>	
c			34.5 Å			
iii.			lamellar hyd	trated solid		
6.						
i.			Present			
ii.a			one			
<u> </u>			Sharp			
C			33 Å			
iii.			<del></del>	drated solid		
7.				-		<u> </u>
<u>i.</u>						
ii.						
8.	Pourable		Pourable		Readily pour	able
9.	No sedimenta	tion over	No sediment	ation over	No sedimenta	tion over
	12 months at	ambient	9 months a	t ambient	6 months at	ambient
	temp.		temp.		temp.	

				<b>~</b>			0091
Examples	27		7	28		29	
1.	,	_			•		•
<u>i.</u>	1	2	1	2	3	1	2
ii.	Opaque	clear	Opaque	clear	solid	Opaque	clear
	solid/paste	thin	solid/paste			solid/paste	thin
		liquid		liquid			liquid
<u>iii.</u>			20(vol/vol)	35	45	74	26
iv.	, , <u> </u>						8.0
<u>v.</u>							58.5
vi.							
2.	III			II		III	
2. 3. 4. 5.	1.31		.6	.91	·	8.46	
4.					·····		
5.							
i.							
ii.a							
b							
С							
iii.							<u>.</u> .
			•				
6.							
i.							
ii.a							
<u> </u>			<del></del>	· · · · · · · · · · · · · · · · · · ·			<del></del>
			<del></del>				
iii.	. <del> </del>	<u> </u>					
1110							
7.				· · · · · · · · · · · · · · · · · · ·			
,. i.							
ii.					<u>,</u>		
11.							
8.	Readily Pour	able	Viscous	s but poura	ble	Viscous but	pourable
9.	No sedimenta	tion over		imentation		No sedimenta	tion over
	2 months at	ambient	9 mont	ths at ambi	ent	3 months at	ambient
	tem.	İ	temp.			temp.	*

Exa	mples	3	0		31		`32	
1.							_	•
	i.	1	2	3	1		1	2
	ii.	Opaque	clear	solid	Opaque .	i	Opaque .	clear
		solid/paste	thin		solid/paste	i i	solid/paste	thin
			liquid			liquid		liquid
	iii.	50(vol/vol)	20	30			87	13
	iv.							0.1
	٧.							75
	vi.							0.01
2.			III		III		III	
<u>2.</u> <u>3.</u>			3.11		0.33		6.50	
4.								
5.								
	i.							
	ii.a							
	<u> </u>							
	c		<del>,</del>					
	iii.		<del></del>					
		•		•				
6.								•
Ů.	·	•	,					
	ii.a	)						
	<u></u>							
	iii							
	1114							
7								
1								
	<u>i.</u>							
	ii.							
۲	 B.	Pourable	<del>-</del>		Readily Po	urable	Viscous bu	t pourable
	•							
-	3.	No sedimen	ntation over	r	No sedimen	ntation over	No sedimer	ntation over
•	- •		at ambient		2 months	at ambient	12 months	at ambient
		temp.			temp.		temp.	
		carh.			1 · r			

Examples	33		34		<b>9</b> .1 7	70091
1.						<del></del>
i	1	2	1	2	1	2
ii.	Opaque	clear	Opaque	cloudy	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
		liquid		liguid	-	liquid
iii.	80	20	72	<b>2</b> 8		
iv.		0.1		27		
٧.				45		
vi.		0.01		0.3		
2.	III		III		III	
3.	2.63		7.0		1.10	
4.					. 3	
5.						
i.						
ii.a						
b						
С						
iii.						
6.						
<u>i.</u>						<del></del>
ii.a		·				
ь						
С						
iii.			-			
7.						
<u>i.</u>						
ii.						
8.	Pourable		Viscous but p	ourable	Readily pour	able
9.	No sedimentat	tion over	No sedimentat	ion over	No sedimenta	tion over
	12 months at	ambient	9 months at	ambient	4 months at	ambi ent
	temp.		temp.		temp.	

				- 79	'. <b>-</b>	·	(	
Exa	mples	36		37			<sub>38</sub> 017	70091
1.								
	i.	1	2	1	2	1	2	3
	ii.	Opaque	claudy	Opaque	clady	Opaque	clear	viscous
		solid/paste	viscous	solid/paste	viscous	solid/paste	thin	liquid
			liquid		liquid		liquid	
	iii.	75(vol/vol)	25	85(vo1/vo1)	15			
	iv.		16.7		15.0			
	v.	٠, ٠	65.5		59.3			
	vi.		1		0.5			V
2.	·	III		II	I		II	
<u>3.</u>		3.70		6.	36		3.74	
4.		0.5 to	2	0.	5 to 2		0.5 to 2	·
5.		very broad w	rith super-					
	<u>i.</u>	imposed peak	(	······································				
	ii.a	one						
	<u>b</u>	narrow	·	· · · · · · · · · · · · · · · · · · ·				
	<u> </u>							
	iii.	micellar pha	ase +	•				
		"G" Phase						
6.								
-	<u>i.</u>	Present						<del> </del>
	ii.a	two		·				<del></del>
	_ b	sharp, shar	rp					····
-	c	57, 38 Å						
	iii.	micellar ph	nase +					
		"G" Phase						
7.						<b>1</b>		
	<u>i.</u>							
	ii.	Lamellar fo	eatures some					
		concentric	structures		·			
8.		Viscous but	pourable	Viscous but	pourable	Poural	b <b>l</b> e	
9.		No sediment		No sedimenta		1	edimentat	
	-	6 months a	t ambient	9 months at	t ambient	9 m	onths at a	ambi ent
		temp.		temp.	-	temp	•	
							•	
							•	

Examples	39		40			410170	0091
1.							
i.	1	2	1	2	1	2	3
ii.	Opaque	clear	Opaque	clear	Opaque		Opaque
	solid/paste	viscous	solid/paste	viscous	solid/past	e _	gel led
		liquid		liquid		liquid	solid
iii.	66	34	77	23			
iv.		12		10		4.4	
٧.		68		61		58.1	
vi.		0.15		0.15		0.07	
2.	III			III		III	
3.	3.10		2	2.87		3.21	
4.	0.5		(	.5		0.5	
5.							
i.	Present very	y broad					
ii.a	one						
b	broad						
c	31 Å						
	Micellar +	"G" Phase					
6.							
i.	Present ver	y broad			ļ <u>-</u>		
<u>ii.a</u>	one						
b	sharp						
	28.5 Å						
iii.	Micellar +	"G" Phase					
7.							
<u>i.</u>					<del>                                     </del>		
ii.						mellar and oheroidal fe	atures _
8.	Pourable		Poura	ble		curable	
9.	No sedimen	tation over	No se	dimentation ove	`	o sedimentat	
	12 months	at ambient •	9 mo	nths at ambient	6	months at	anbient
	temp.		temp.		t	anp.	

Examples		42		43(a)		43(b)	<u> </u>
1.					į		
<u>i.</u>	1	2	3	1	2	1	2
ii.	Opaque	thin	Opaque	Opaque	viscous	Opaque	clear
÷	solid/paste	liquid	gel led	solid/paste	clear	solid/paste	thin
			solid	·	liquid		liquid
iii.	·			58.0	42.0		······································
iv.	· · · · · · · · · · · · · · · · · · ·			**************************************	3.0		·
٧.					91.4		
vi.				· · · · · · · · · · · · · · · · · · ·			
2.	III			III		III	
3.	4.10	· . · · · · · · · · · · · · · · · · · ·		0.73	-	0.97	
4.	4						
5.							
<u>i.</u>							
ii.a							
<u>b</u>							
C							
iii.	-	•					
6.	-						
i.							
ii.a	····		<u> </u>				
Ь							
С							
iii.				•			
		· <del></del>		•			
7.							
i.		<del> </del>					
ii.							
8.	Viscous but	pourable		Viscous but	pourable	Viscous but	pourable
9.	No sedimenta	tion over	!	No sedimenta	tion over	No sediment	ation over
-	4 months at	ambient	<u> </u>	12 months at	ambient	12 months a	t ambient
	temp.			temp.		tem.	

Ex	amples	43(c)		. 4	4	·	. ·	5	
1.									
	i.	1	2	1	2	3./	1	2	3
	ii.	Opaque	clear	Opaque	clear	Clear	Opaque	clear	clear
		solid/paste	viscous	solid/paste	thin	viscous	solid/paste	thin	viscous
			liquid		liquid	liquid		liquid	liquid
	iii.				· · · • · · · · · · · · · · · · · · · ·		30(v/v)	න	10
	iv.						····		
	<u>v.</u>					ł			·
	vi.	**************************************				<u> </u>			
<u>2.</u>		III			II			II	
<u>3.</u>		1.72			1.19		2	.74	
4.		<del></del>				-			
5.									
	<u>i.</u>	<del></del>			-				
	ii.a							<del> </del>	
	<u>b</u>			······································					
	<u>c</u>				······································				
	iii.								
<del></del> 6.		<del></del>							
υ.	i.								
	ii.a			•					
	b								
	С			· · · · · · · · · · · · · · · · · · ·					<del></del>
	iii.							•	
<del>7.</del>						<del>,,,,</del>			*
• •	i.								
	ii.								
8.		Viscous but	pourable	Vis	cous but	pourable	Viscou	s but po	urable
9.		No sedimenta	tion	No :	sedimenta	ition over	No sed	imentati	on over
		over 12 month	ns at	9 1	nonths at	ambient	9 mon	ths at a	mbient
		ambient temp.	, i	ten	<b>)</b> •		temp.		

1.         1         2         3         1         2         1         2           ii. Opaque clear solid/ thin viscus paste liquid liquid         Opaque clear solid/paste viscus solid/paste viscus solid/paste thin liquid         Opaque clear solid/paste thin liquid         Opaque clear solid/paste thin liquid         Opaque clear solid/paste thin liquid         Opaque clear solid/paste thin liquid         Opaque clear solid/paste thin liquid         Opaque clear solid/paste viscus solid/paste viscus solid/paste thin liquid         Opaque clear solid/paste viscus solid/paste viscus solid/paste viscus solid/paste thin liquid         Opaque clear solid/paste viscus solid/paste viscus solid/paste viscus solid/paste thin liquid         Opaque clear solid/paste viscus solid/	Examples			46		47		48(a)	
11.	1.								
Solid/ thin viscus   Solid/paste viscus   Solid/paste   thin   Diquid   D		i	1	2	3	1	2	1	2
paste   1iquid   1i		ii.	Opaque	clear	clear	Opaque	clear	Opaque	clear
fiji.     40(v/v)     50     10     78.0     22       fiv.     0.1     80       v.     80     0.01       2.     II     III     III       3.     2.48     11.0     1.58       4.     5.     1.     1.       fi.a     b     c     1.       fii.a     b     c     1.       fii.a     b     c     1.       fii.a     c     1.     1.       fii.     fii.     1.     1.       fii.     fii.     1.     1.       fii.     fiii.     1.     1.       fii.     fiii.     1.     1.       fii.     fiii.     1.     1.       fii.     fiii.     1.     1.       fiii.     fiiii.     1.     1.       fiii.     fiii.				thin	viscous	solid/paste	viscous	solid/paste	thin
fifi.         40(v/v)         50         10         78.0         22           iv.         0.1         80         0.01         2.         80         0.01         2.         III         IIII         IIII         IIII         3.         2.48         11.0         1.58         4.         5.         6.         7.         7.			paste	liquid	liquid		liguid		liquid
iv.         80           vi.         0.01           2.         II         III         III           3.         2.48         11.0         1.58           4.         1.58         1.58           5.         1.10         1.58           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           6.         1.10         1.10           7.         1.10         1.10           8.         1.10         1.10           9.         1.10         1.10           1.10         1.10         1.10           1.10         1.10         1.10           1.10         1.10		iii.			<del></del>			78.0	22
v.         80           vi.         0.01           2.         II         III         III           3.         2.48         11.0         1.58           4.         1         1         1           ii.a         b         c         1           ii.a         b         c         1           iii.a         b         c         1           iii.         7         1         1           ii.         1i         1         1           iii.         1         1         1           ii.				<u> </u>					0.1
vi.         0.01           2.         II         III         III           3.         2.48         11.0         1.58           4.         11.0         1.58           5.         1         1           11.a         1         1     <				, <u></u>					80
2. II III III  3. 2.48 11.0 1.58  4. 5.							<i>E</i>	<u>.</u>	0.01
3. 2.48 11.0 1.58  4. 5.	2.			II		III	<del>*************************************</del>	i III	
4.  5.  i.  ii.a  b  c  iii.  6.  i.  ii.a  b  c  iii.  7.  i.  ii.  ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient					<u> </u>	1		·	
i. ii.a b c iii.  6. i. ii.a b c iii.a b c iii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient							·		
i. ii.a b c iii.  6. i. ii.a b c iii.a b c iii.  7. i. ii.  8. Viscous but pourable Viscous but pourable Readily pourable 9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient			<u></u>				<del> </del>	İ	
ii.a b c iii.  6. i. ii.a b c iii.a  7. i. ii. ii.  No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient	٥.	•							
b c iii.  6.  i. ii.a b c iii.  7.  i. ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient							······································		
c iii.  6. i. ii.a b c iii.  7. i. ii.  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient			<del></del>						
iii.  6.  i.  ii.a  b  c  iii.  7.  i.  ii.  ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient						1	<del></del>		
6.  i. ii.a  b  c iii.  7.  i. ii.  8. Viscas but pourable Viscas but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient						1			
ii.a  b  c  iii.  7.  i.  ii.  8. Viscaus but pourable Viscaus but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient		111.							
ii.a  b  c  iii.  7.  i.  ii.  8. Viscaus but pourable Viscaus but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient	_	<del></del>		<u></u>					
ii.a  b  c  iii.  7.  i.  ii.  No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient	о.								
c iii.  7.  i. ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient						1		<u> </u>	
c iii.  7. i. ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient									
7.  i.  ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient						1	<del></del>		
7.  i.  ii.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient						1			
i.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient		111.							
i.  8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient		<del></del>				1			
8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient	/.								
8. Viscous but pourable Viscous but pourable Readily pourable  9. No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient						1		1	
9. No sedimentation over No sedimentation over No sedimentation over 9 months at ambient 4 months at ambient 6 months at ambient		ii.				1			
9 months at ambient 4 months at ambient 6 months at ambient	8.	<del></del>	Viscous	but poura	ble	Viscous but po	ırable	Readily po	ırable
9 months at ambient 4 months at ambient 6 months at ambient	9.		No sedin	mentation	over	No sedimentation	on over	No sedimen	tation over
						4 months at a	mbient	6 months	at ambient
			temp.			temp.		temp.	,

Examples	48(b)		48 (	(c)		49			
1.									
i.	1	2	1		2	1	2	3	
ii.	Opaque	clear	Opaque		clear	Opaque .	clear	waxy	
	solid/paste	thin	solid/pa	aste	thin	solid/past	e thin	solid	
	·	liquid			liquid		liquid		
iii.	80	20	82		18.0	31.9(v/v)	23.4	44.7	
iv.		∠0.1			∠ 0.1		<b>∠0.1</b>	29.6	
٧.		79	i		76.6		67.1	50.2	
vi.		∠ 0.01	1		< 0.01		< 0.01		
2.	III		!	III			III		
3.	2.31			3.65			5.95		
4.	•								
5.									
i.									
ii.a									
b									
c			İ				- · · · · · · · · · · · · · · · · · · ·		
iii.		· · · · · · · · · · · · · · · · · · ·					·		
••••					•				
6.		<del></del>	ì						
i.									
ii.a									
<u> </u>									
c									
iii.			Ì						
			Ĭ.						
7.									
i.									
<del>''-</del> ii.									
, , •									
8.	Pourable		Paur	rable		Vis	cous but po	urable	
9.	No sediment	ation over	. No	sedime	entation over		sedimentati		
	12 months a	t ambient	12 1	months	at ambient	; 12	months at a	mbient	
	temp.		ten	p.		ter	p <b>.</b>		

Examples	50(a)		50(b)		<b>017</b> 50(c)	0091
1.						
i. 1		2	1	2	1	2
	paque	clear	Opaque	clear	Opaque	clear
•	olid/paste	thin	solid/paste	thin	solid/paste	thin
	·	liquid		liquid		liquid
iii. 76	5	24	77.5	22.5	80	20
iv.		0.1		0.1		0.1
٧.		81		79.7		78%
vi.		0.01		0.01		0.01
2.	III		III		III	
3.	0.58		1.60		3.89	
4.						
5.	_					
i.			Very small			
ii.a	·		one			
b			very narrow	1		
С			65 Å			
iii.			Micellar+	"G" Phase		
			("G" Predon	minates)		
6.						
i.			Very small	l		
ii.a			two			
ь			Narrow at	54Å, & 28Å		
С			54 Å			
iii.			"G" Phase	+ some micellar		
7.					·	
<u>i.</u>						
ii.						
8. R	Readily pourab	le	Pourable		Viscous but	pourable
9. N	lo sedimentati	on over	No sediment	tation over	No sedimenta	tion over
1	12 months at a	mbient	12 months	at ambient	12 months at	ambient
t	temp.		temp.		temp.	

Examples 51				52		<u>g</u> 170091				
1.										
	i.	1	2	3	1	2	3	1	2	3
	ii.	Opaque	clear	clear	Opaque	clear	clady	Opaque	clear	waxy
		solid	thin	oily	solid	thin	viscous	solid	thin	solid
		paste	liquid	layer	paste	liquid	liquid("G")	paste	liquid	
	iii.	59(v/v)	39	2	45(v/v)	19	36	36(v/v)	30	34
	iv.					0.2	49		0.1	31.5
	<u>v.</u>	·····				72	48		82	
شبييها	vi.					0.01	1.0		0.01	
2.		I	I			II		II	I	
<u>3.</u>		1	1.40			4.42		1.	42	
4.						0.5		0.	5	· · · · · · · · · · · · · · · · · · ·
5.										
	i.				narrow/s	trong		narrow/w	eak	
	ii.a				one			one		
	<u>b</u>				broad			narrow		
	С				54.2 Å	-		56.1 Å		
	iii.			·-	Micellar	+ "G" Pr	nase	"G" Phas	e see	
6.									··········	
	<u>i.</u>				narrow	····				
	ii.a				two					
•	Ь		· · · · · · · · · · · · · · · · · · ·		narrow at	t 51Å & 2	16Å			
	<u> </u>				51 Å				·	
	iii.				micel lar	"G" Phas	æ			
7.	<u> </u>									
	i.									
	ii.							Lamella	r feature	žs
8.		Viscous b	out poura	ble	Visca	is but po	urable	Viscous	but pour	able
9.		No sedime			No sec	limentati	on over	No sedin	rentation	over
		12 months	at ambi	ent	6 mor	iths at a	nbient	4 month	ns at ant	ient
		temp.			temp.			temp.		

Examples 54			55			56		
1.								
i.	1	2	3	1	2	3	1	2
ii.	Opaque	clear	waxy	Opaque	clear	waxy	Opaque	clear
	solid/	thin	solid	solid/	thin	solid	solid/	thin
	paste	liquid		paste	liquid		paste	liquid
iii.	43(v/v)	19	38	40(v/v)	27	33	76	24
iv.		< 0.1	32.9		< 0.2			0.05
٧.		71.6	51.5		82.2			
vi		< 0.01						
2.	II	I		III			III	<del></del>
3.	1.	80		1.86			2.43	
4.	< 0.	5						
5.	•							
<u>i.</u>								
ii.a								
b								
<u>c</u>								
iii.								
6.								
<u>i.</u>			·· · · · · · · · · · · · · · · · · · ·					
ii.a								
ь								
<u>C</u>								
iii.								
7.		<del></del>						<u></u>
i.								
<del>''</del> ii.								
8.	Pourable	2		Pourable			Pourable	
9.	No sedin	mentation (	over	No sedim	entation ove	r	No sedime	ntation over
				1 _			1.	
	4 month	ns at ambie	ent	3 months	s at ambient	•	I month a	t laboratory

Exampl	es 57	57			59	
1.		<u> </u>		(3		
i.	1	2	1	2	1	2
ii.	Opaque	clear	Opaque	clear	Opaque	clear
	solid/paste	thin	solid/paste	thin	solid/paste	thin
		liquid		liquid		liquid
iii	. 82.5	17.5	64.9	35.1	77.0	23.0
iv.		0.02		0.3		0.4
٧.					· · · · · · · · · · · · · · · · · · ·	•
vi.						
2.	III		III	·	III	
3.	1.8		2.1		2.9	
4.						,
5.						
i.						
ii.	a	*				
	b					
	С					
iii		. —				
6.						
<u>i.</u>						
ii.	.a				<u> </u>	
	b				<u> </u>	<del></del>
	С					
iii	i <b>.</b>			-		
7.						
<u>i.</u>						
ii.	•					
8.	Pourable		Pourable		Pourable	
9.	No sedimenta	tion over	No sedimentat	tion over	No sedimentat	
	1 month at 1	aboratory	1 month at la	aboratory	1 month at la	boratory
	ambient temp	•	ambient temp.		ambient temp.	

Example	xamples 60			ഖ		62		
1.		į			· · ·			
i.	1 2		1	2	3	1	2	
ii.	Opaque c	lear	Opaque	clear	Opaque	Opaque	clear	
	solid/ t	hin	solid/	thin	solid	solid/	viscous	
	paste 1	iquid	paste	liquid	paste	paste	liquid	
iii.	73.0 2	7.0	5(v/v)	45	50	95.0	5.0	
iv.		0.1		0.05			26.2	
٧.								
vi.		ı						
2.	III			III		III		
3.	2.2			8.1		6.0		
4.		ł						
5.								
i.							÷	
ii.a		Ì		•				
b		ļ						
С								
iii.								
6.							•	
<u>i.</u>	·							
ii.a								
<u>b</u>	***************************************							
<u>C</u>								
iii.								
			W		·			
7.								
<u>i.</u>	· · · · · · · · · · · · · · · · · · ·							
ii.								
8.	Pourable		Vi sca	s but pour	able	Viscous	but pourable	
9.	No sedimentati	on over	No sec	himentation	over	No sedim	entation over	
	1 month at lab	oratory	1 mont	h at labor	atory	1 month	at laboratory	
	ambient temp.		ambien	it temp.		ambient	temp.	

Examp	les &		64			65	
1.							
<u>i.</u>	1	2	1	2	1	2	3
ii	. Opaque	Claudy	Opaque	Clady	Opaque	clear	Solid/
	solid/	viscous	solid/	viscous	solid/	thin	paste
	paste	liquid	paste	liquid	paste	liquid	
iii	i. 42.8	57.2	51.0	49.0	10(v/v)	40	50
iv.	,	21.3		22.5	<u> </u>	0.01	·····
<u>v.</u>							
vi.	·		<del></del>	······································	<u> </u>		
2.	111		III	·····		III	
<u>3.</u> <u>4.</u>	3.26		5.60	)	<u> </u>	0.75	
4.					1	<del>,</del>	<del></del>
5.							
<u>i.</u>					<u> </u>		·
ii.	a				<u> </u>		<del></del>
	b	<u> </u>					
	С	<u> </u>					
iii	•	1	····				
<del></del>		<u> </u>				<del></del>	<del></del>
6.					İ		
<u>i.</u>		<u>:</u>			<u> </u>		
ii.		<u> </u>		···	<del></del>	<del></del>	
	b	<u>;</u>	· · · · · · · · · · · · · · · · · · ·				
	C	1		<del></del>			
iii	•						
7	_		·				<del></del>
7.		***************************************		•			
<u>i.</u>		<u> </u>	·		<del>-   </del>	<del></del>	
ii.							
8.	Pourable		Pourable			Readily p	ourable
9.	No sedimentati	on over	No sedimen	ntation over		No sedime	ntation
	1 month at lab	oratory	1 month at	laboratory		over 1 mo	nth at
	ambient temp.		ambient te	_			y ambient
							-
		or awry		_			

		Exa	mples	66			<del></del>	0170091
1. i			1			2		-
i ii iii iv v		Opaque	solid	paste	Clear	thin	liqui	<u>d</u>
jii		64.0			36.0			<del></del>
1 V					0.2			_
v vi		····	<b></b>					<del></del>
$\frac{\mathbf{v}_1}{2}$		111						_
<del>2.</del> 3.		0.56	· <u>·</u> ·········					<del></del>
4.								
5.								<del></del>
i.								
ii	a							
	b							
iii	С							
6.					****			
i								
ii	a							
	b							
	С				•			
<del>iii</del> 7.			<del></del>				,	
i.								
ii								
8.		Readily	Poura	ble				
9.		No sed	mentat	ion over				<del></del>
		1 monti	n at la	boratory				
		ambien	t tempe	ratures				<del></del>



# Comparative Example

I.	4	1	2
	i. ii. 0:		
		aque	Opaque
		olid	viscous
		este	liquid
		24	76
	iv.		17.3
	V.		77.0
	vi.		0.26
2.		I	
3.		0.3	
			•
4.		4	
5.		very broad wi	th
	i.	superimposed p	eaks
	ii.a	None	
	b	-	
	C	_	
	111.	conc. micellar d	ispersion
6.			
	i.	very wide	
	ii.a	one	
	Ь	small	
	C	20A	
	711.	conc. micellar d	ispersion
7.			1570151011
•	i.		
	ii.	Spheroidal featur	MAC.
	11.	Spherordar reacui	res
8.		Readily	
		Pourable	
9.		No sedimentation	over
<b>~</b> .		12 months at ambi	ont
			CHE
		temperature	
			•

Certain of the foregoing examples were tested for washing performance as follows:-

#### Series 1

Representative high foaming formulations were each compared with a standard powder formulation in machine washing tests on two different standard soiled fabric samples.

<u>Example</u>	Cotton	Polyester/Cotton	Condition	ons
31	95%	100% )	Temp.	50°C
55	90%	70% )	Water	300 ppm calcium carbonate
16	100%	100%	Time	30 mins.
33	95%	110%	Conc. =	Equivalent effective Wash
Powder Standard	100%	100%		Solids

The term "Effective Wash Solids" refers to the sum of the Active Ingredient and Builder. The powder standard was used at 6gm/l and the Examples adjusted to give the same % Effective Wash Solids in the wash Liquor.

### Series 2

Representative formulations of both high and low foaming types were tested against equal wt. dosage at three temperatures.

			Cotton		Poly	ester	/Cotton	
Example	% Effective Wash Solids	<u>40</u> <u>0</u>	<u>60</u> <u>°</u>	<u>85</u> <u>0+</u>	40	. <u>0</u>	<u>60</u> <u>0</u>	<u>85 0+</u>
43 (c)	93	75	100	95	75	85	50	
36	66	85	85	100	80	95	75	
50 (c)	93	110	110	95	180	200	200	
Powder	100	100	100	100	100	100	100	
Standar	<b>r</b> d							
Conditio	ons: Temp	400,	600 and	85°C+				
	Water	300 p	om hardn	ess				
	Time	30 mi	30 mins.					
	Conc.	6 gm/	l (as re	ceived)				

•

:

### Series 3

In this series low foaming non-ionic based examples were tested against the powder standard.

Example	% Effective Wash Solids	Cotton	Polyeste Cotton	r/	
52	70	110%	100%	Condit	<del></del>
53 54	66 61	105% 115%	90% 120%	Temp. Water	50°C 300 ppm hardness
				Time Conc.	30 mins
				powder	6 gm/1
				examples	ııgm/ı
Powder Standard	100	100%	100%		

## Series 4

Two low foam non-ionic formulations were tested on naturally soiled fabric (15 successive washes with natural soiling)

Conditions:	Temperature	50 °C
	Water	300 ppm hardness (wash and rinse)
	Wash time	30 mins
	Fabric	65: 35 white polyester:cotton
	Concentration	EQUAL WEIGHT i.e. 6 gm/l

#### Results:

### Example

52	=	100% Std	)	Optical whitener efficiency
54	<b>300</b>	75% Std	)	
52	=	95-100%	)	Soil Removal and
54	=	95-100%	)	Deposition efficiency

The two examples were also compared against the three liquid laundry products which have performed best in our tests out of all those available commercially in Europe at the date of testing.

Both examples gave superior washing performance to all three commercial products.

- 1. A Non-sedimenting, Pourable, fluid, detergent composition containing Active Ingredients which comprise a substantially linear alkyl benzene sulphonate, said composition having a Payload of at least 25% by weight and comprising: at least one, predominantly aqueous, liquid Separable Phase containing dissolved Electrolyte; and one or more other Separable Phases Interspersed therewith, which contain suspended solid particulate Builder; the Electrolyte comprising at least 4.7% based on the weight of the composition of sodium carbonate and being sufficient to salt out at least a substantial proportion of the surfactant from said predominantly aqueous phase to form a part of said other phase or phases thereby inhibiting sedimentation of said Builder.
- 2. A Non-sedimenting, Pourable, fluid, detergent composition comprising: at least one, predominantly aqueous, liquid Separable Phase containing sufficient dissolved Electrolyte selected from alkali metal chlorides, phosphates, condensed phosphates, phosphonates, citrates, nitrilotriacetates, ethylenediamine tetracetates, carbonates, silicates and mixtures thereof to provide from 2 to 4.5 gm ions per litre of said phase of alkali metal; at least one other Separable Phase containing Active Ingredients; and suspended solid Builder; the Payload of said composition being above the minimum level at which the Formulation is Non-sedimenting but below the maximum level at which the Formulation is Pourable.
- 3. A Non-sedimenting, Pourable, fluid detergent composition having a Payload of greater than 25% which, on Centrifuging is separable into a single liquid layer containing sufficient dissolved Electrolyte consisting essentially of sodium chloride, sodium silicate, sodium carbonate, sodium phosphate and sodium tripolyphosphate or mixtures thereof to provide from 2 to 4.5 gm ions sodium per litre of said layer and a Solid Layer containing surfactant and Builder.

- 4. A Non-sedimenting, Pourable, fluid, detergent composition containing Active Ingredients which comprise a substantially linear alkyl benzene sulphonate, said composition having a Payload of at least 25% by weight which separates on Centrifuging into a predominantly aqueous liquid layer containing sufficient dissolved Electrolyte to provide from 2 to 4.5 gm ions per litre of alkali metal and at least one other layer, said at least one other layer comprising solid Builder and at least part of said Active Ingredient.
- 5. A Non-sedimenting, Pourable, fluid, detergent composition having a Payload of at least 35% and comprising Active Ingredient, dissolved Electrolyte and suspended solid Builder, which separates on Centrifuging into a predominantly aqueous layer containing sufficient of said dissolved Electrolyte to provide from 2 to 4.5 gm ions alkali metal per litre of said aqueous layer, and at least one other layer containing solid Builder and at least part of said Active Ingredients, the weight ratio of the total Builder to the total Active Ingredients being greater than 1.2:1.
- 6. A composition according to any foregoing claim having a Payload of at least 35% by weight.
- 7. A composition according to any foregoing claim having a yield point of at least 10 dynes per cm<sup>2</sup>.
- 8. A composition according to any foregoing claim having a weight ratio of Builder to Active Ingredient of from 1.2: 1 to 4:1.
- 9. A composition according to any foregoing claim wherein the Builder comprises sodium tripolyphosphate.
- 10. A composition according to any foregoing claim containing at least 15% by weight thereof of Builder.
- 11. A composition according to claim 10 containing at least 20% by weight thereof of Builder.

- 12. A composition according to any foregoing claim containing more than 8% by weight thereof of Active Ingredient.
- 13. A composition according to any foregoing claim having a pH greater than 8 when dissolved in a wash liquor at a concentration of 0.5% Dry Weight.
- 14. A composition according to claim 13 having a pH greater than 10 when dissolved in a wash liquor at a concentration of 0.5% Dry Weight.
- 15. A composition according to any foregoing claim having sufficient free alkalinity to require 0.4 to 12 mls one tenth Normal hydrochloric acid to reduce the pH of 100 mls of diluted composition at 0.5% Dry Weight to 9.
- 16. A composition according to claim 15 having sufficient free alkalinity to require from 3 to 10 mls. one-tenth normal hydrochloric acid to reduce the pH of 100 mls. of diluted composition at 0.5% Dry Weight to 9.
- 17. A composition according to any foregoing claim wherein the Active Ingredients comprise at least a major proportion of a sulphated and/or sulphonated anionic surfactant.
- 18. A composition according to claim 1 wherein said solid Builder comprises a condensed phosphate, phosphonate, carbonate, zeolite and/or orthophosphate.
- 19. A composition according to either of claims 1 and 18 wherein said dissolved electrolyte consists essentially of said carbonate, and an alkali metal condensed phosphate, orthophosphate, citrate, nitrilotriacetate, chloride and/or ethylenediamine tetracetate.
- 20. A composition according to any of claims 1, 18 and 19 where the total Builder comprises a major proportion by weight thereof, of sodium tripolyphosphate.

- 21. A composition according to any foregoing claim wherein the Active Ingredients constitute from 10 to 20% of the weight of said composition.
- 22. A composition according to any of claims 17 to 21, wherein said sulphated and/or sulphonated anionic surfactant comprises a mixture of a sustantially linear C10-14 alkyl benzene sulphonate and a C10-20 alkyl 1 to 10 mole ethyleneoxy sulphate.
- 23. A composition according to any foregoing claim containing an effective amount of an antiredeposition agent.
- 24. A composition according to claim 23 wherein the antiredeposition agent is a carboxymethylcellulose.
- 25. A composition according to claim 24 containing from 0.5 to 2% by weight of said composition of alkali metal or ammonium carboxymethyl cellulose.
- 26. A composition according to any foregoing claim containing an effective amount of an optical brightening agent.
- 27. A Pourable, Non-sedimenting, fluid detergent composition consisting essentially of water and: (A) from 10 to 20% based on the weight of the composition of Active Ingredients comprising a substantially linear sodium alkyl benzene sulphonate having from 10 to 20 aliphatic carbon atoms and optionally an alkyl ethoxy sulphate having an alkyl group with from 10 to 20 carbon atoms, and/or a minor proportion of a non-ionic surfactant and/or of a soap; (B) at least 15% of Builder partly present as solid and selected from condensed phosphates, zeolites, citrates, nitrilotriacetates, ethylenediamine tetracetates, orthophosphates and silicates, wherein at least 50% by weight of said Builder is sodium tripolyphosphate and said Builder further comprises at least 4.7%, based on the total weight of the composition, of sodium carbonate; (C) optionally up to 2.5% by weight of the composition, of carboxymethylcellulose; (D) optionally up to 1% by weight of the composition of optical

brightening agent; and (E) optionally minor proportions of ingredients selected from enzymes, bleaches, antifoams, cationic fabric softeners, smectite clays, fragrances, dyes and sodium chloride.

- 28. A Pourable, Non-Sedimenting, fluid, liquid detergent composition consisting essentially of water and: (A) from 10 to 20% based on the weight of the composition of a mixture of substantially linear C10-18 alkyl benzene sulphonate and C10-20 alkyl 1-10 mole ethoxy sulphate; (B) at least 15% by weight of the composition of total Builder partly present as suspended solid, selected from sodium tripolyphosphate, zeolite, sodium carbonate, sodium silicate and mixtures thereof; (C) an aqueous Separable Phase containing sufficient dissolved Electrolyte selected from sodium tripolyphosphate, sodium carbonate, sodium silicate and mixtures thereof to provide from 2 to 4.5 gm mole per litre of sodium ion in said phase; and (D) optionally any of the Usual Minor Ingredients; the Payload of said composition being above the minimum at which the composition is Non-sedimenting but below the maxium at which it is Pourable.
- 29. A composition according to any of claims 22, 27 and 28 wherein the weight ratio of said alkyl benzene sulphonate to said alkyl ether sulphate is between 5:1 and 1:5.
- 30. A composition according to any foregoing claim which, on recovery after exposure to high shear stress, exhibits increased viscosity.
- 31. A composition according to any of claims 2 to 26 and 28 to 30 containing at least 4.7% by weight sodium carbonate.
- 32. A composition according to any foregoing claim, wherein the Electrolyte and Builder consist essentially of sodium tripolyphosphate and sodium carbonate.
- 33. A composition according to any foregoing claim wherein the proportion of sodium tripolyphosphate is from 14 to 32.7% of the weight of the composition.

- 34. A composition according to claim 33, wherein the proportion of sodium tripolyphosphate is greater than 15.8% by weight.
- 35. A composition according to any foregoing claim containing from 2.1 to 18% by weight of substantially linear sodium alkyl benzene sulphonate.
- 36. A composition according to claim 35 containing at least 9.0% by weight of sodium alkyl benzene sulphonate.
- 37. A composition according to claim 36 containing at least 9.9% by weight of sodium alkyl benzene sulphonate.
- 38. A composition according to claim 37 containing at least 11.2% by weight of sodium alkyl benzene sulphonate.
- 39. A composition according to claim 38 containing at least 12% by weight of alkyl benzene sulphonate.
- 40. A composition according to claim 39 containing at least 12.6% by weight alkyl benzene sulphate.
- 41. A composition according to any foregoing claim containing up to 9.6% by weight of sodium alkyl ether sulphate.
- 42. A composition according to any of claims 1 to 26 wherein said Electrolyte consists essentially of sodium carbonate and/or sodium silicate, and/or sodium tripolyphosphate.
- 43. A composition according to any foregoing claim wherein the Active Ingredients comprise a minor proportion of a non-ionic surfactant.
- 44. A composition according to any foregoing claim wherein the Electrolyte comprises a nitrate.
- 45. A method of washing clothes or other soiled fabric which comprises agitating them in an aqueous wash liquor containing a composition according to any foregoing claim.



## **EUROPEAN SEARCH REPORT**

EP 85 10 8260

	DOCUMENTS CONS	01.400.700.				
Category	Citation of document with indication, where appropriate, of relevant passages			Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)	
D,A	US-A-3 574 122 al.) * abstract *	(T.A. PAYNE	et		C 11 D	17/00
D,A	US-A-3 346 503 * claim 1 *	- (J.M. HUGGII	NS)			
D,A	US-A-3 075 922 * claim 1 *	- (H.E. WIXON	)			
D,A	US-A-4 018 720 al.) * claims 1-4,25		EL et			
A	DE-A-2 921 366 WILSON LTD.) * claims 1,2,10			:	TECHNICAL SEARCHED	Int. Cl.4)
A	GB-A-2 031 941 WILSON LTD.) * claims 1,2 *	- (ALBRIGHT &				
A	GB-A- 930 394 (COLGATE-PALMOLI * examples 4-6,	VE CO.) claims 1,2	*			
	The present search report has b	been drawn up for all clai	ms			
	Place of search BERLIN	Date of completion 22-10-		SCHUL	Examiner TZE D	
Y: p d A: te O: n	CATEGORY OF CITED DOCL articularly relevant if taken alone articularly relevant if combined w occument of the same category echnological background on-written disclosure termediate document		T: theory or prir E: earlier patent after the filin D: document cit L: document cit &: member of th document	document date ed in the ap ed for othe	, but published or oplication r reasons	i, or