

⑯ EUROPEAN PATENT APPLICATION

⑯ Application number: 86113099.5

⑮ Int. Cl.³: C 22 C 1/09

⑯ Date of filing: 23.09.86

⑯ Priority: 30.09.85 JP 217489/85

⑯ Applicant: TOYOTA JIDOSHA KABUSHIKI KAISHA
1, Toyota-cho Toyota-shi
Aichi-ken 471(JP)

⑯ Date of publication of application:
06.05.87 Bulletin 87/19

⑯ Inventor: Kubo, Masahiro
Toyota Jidosha K.K. 1, Toyota-cho
Toyota-shi Aichi-ken(JP)

⑯ Date of deferred publication of search report: 13.01.88

⑯ Inventor: Dohnomoto, Tadashi
Toyota Jidosha K.K. 1, Toyota-cho
Toyota-shi Aichi-ken(JP)

⑯ Designated Contracting States:
DE FR GB

⑯ Inventor: Tanaka, Atsuo
Toyota Jidosha K.K. 1, Toyota-cho
Toyota-shi Aichi-ken(JP)

⑯ Inventor: Hirai, Hidetoshi
Toyoda Automatic Loom Works Ltd. 2-1 Toyodacho
Kariya-shi Aichi-ken(JP)


⑯ Representative: Bühlung, Gerhard, Dipl.-Chem. et al,
Patentanwaltsbüro Tiedtke-Bühlung-Kinne
Grupe-Pellmann-Grams-Struif Bavariaring 4
D-8000 München 2(DE)

⑯ Composite material including alumina-silica short fiber reinforcing material and aluminum alloy matrix metal with
moderate copper and silicon contents.

EP 0 220 495 A3

⑯ A composite material is made from alumina-silica type short fibers embedded in a matrix of metal. The metal is an alloy consisting essentially of between approximately 1.5% to approximately 6% of copper, between approximately 0.5% to approximately 2% of silicon, and remainder substantially aluminum. The short fibers may be all alumina short fibers, or may be all amorphous alumina-silica short fibers, or may have a substantial proportion of the mullite crystalline form included in them. The fiber volume proportion of the alumina-silica type short fibers may desirably be between approximately 5% and approximately 50%, and may more desirably be between approximately 5% and approximately 40%. And, in the desirable case that the fiber volume proportion of the alumina-silica type short fibers is between approximately 5% and approximately 20%, then the copper content of said aluminum alloy matrix metal is desired to be between approximately 2% and approximately 6%.

FIG. 18





EP 86 11 3099

DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
X	EP-A-0 074 067 (SUMITOMO CHEMICAL CO.) * Claim 1; page 12, line 13; page 3, line 24 - page 6, line 4.*	1,2	C 22 C 1/09
Y	---	3-9	
Y	US-A-4 152 149 (S. HORIKIRI et al.) * Claims 1,4; column 2, line 39 - column 6, line 39 *	3-7	
Y	---	8,9	
	FR-A-1 556 070 (GENERAL TECHNOLOGIES CORP.) * Abstract II, nos. 2,9,10 *	-----	
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 22 C B 22 D F 16 J
The present search report has been drawn up for all claims			
Place of search	Date of completion of the search	Examiner	
THE HAGUE	29-10-1987	SCHRUERS H. J.	

CATEGORY OF CITED DOCUMENTS

X : particularly relevant if taken alone
Y : particularly relevant if combined with another document of the same category
A : technological background
O : non-written disclosure
P : intermediate document

T : theory or principle underlying the invention
E : earlier patent document, but published on, or after the filing date
D : document cited in the application
L : document cited for other reasons
& : member of the same patent family, corresponding document