(1) Publication number:

0 245 034 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 87303885.5

(f) Int. Cl.4: **B 65 D 65/40**, B 32 B 15/08


22) Date of filing: 30.04.87

30 Priority: 02.05.86 JP 101165/86 02.05.86 JP 101166/86

- 43 Date of publication of application: 11.11.87
 Bulletin 87/46
- Ø Designated Contracting States: DE FR GB
 - Date of deferred publication of search report: 28.09.88 Bulletin 88/39

- Applicant: MITSUI PETROCHEMICAL INDUSTRIES, LTD., 2-5, Kasumigaseki 3-chome Chiyoda-ku, Tokyo 100 (JP)
 Applicant: SHIONOGI SEIYAKU KABUSHIKI KAISHA, 12, Dosho-machi, 3-chome Higashi-ku, Osaka-shi, Osaka 541 (JP)
 Applicant: TAISEI KAKO CO., LTD.,, 12-20, Honjyo nishi 2-chome Oyodo-ku, Osaka-shi Osaka-fu (JP)
- (7) Inventor: Itaya, Kozo, 1-151-2, Hamadera Showa-machi, Sakai-shi Osaka-fu (JP) Inventor: Nishida, Hirotaka, 1788-11, Aomadani, Minoo-shi Osaka-fu (JP) Inventor: Fukuda, Kazutoshi, 5, Yushudai nishi 2-chome, Ichihara-shi Chiba-ken (JP)
- Representative: Myerscough, Philip Boyd et al, J.A.Kemp & Co. 14, South Square Gray's Inn, London, WC1R 5EU (GB)
- 64 Packaging structure and process for production thereof.
- A packaging structure composed of a composite synthetic resin sheet having a depressed portion formed therein for holding an article and a metal foil bonded to the sheet, said composite sheet being a three-layer sheet composed of an interlayer of high-density polyethylene and outside layers of a propylene polymer bonded to both surfaces of the interlayer, the interlayer having a thickness of 120 to 800 micrometers, each of the outside layers having a thickness of 15 to 80 micrometers, and the thickness of the interlayer being at least 2.5 times the total thickness of both outside layers; a process for production thereof; and a process for producing a composite (synthetic) resin sheet suitable as a material for the aforesaid packaging structure.

P 0 245 034 /





EUROPEAN SEARCH REPORT

Application Number

87 30 3885

Category	Citation of document with indication, we of relevant passages	vhere appropriate,	Relevant	CLASSIFICATION OF TH
Α	EP-A-0 150 979 (UNILEVER * Page 2, lines 20-24,30- lines 4-7,16-17; page 7,	33; page 6.	to claim	B 65 D 65/40 B 32 B 15/08
Α	GB-A-2 111 908 (CHISSO CO * Claims 1-3,5; page 2, 1-4	DRP.) ines 3-9,16-18	1	
3				
				TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			-	B 32 B
				B 65 D
77704				
	The present search report has been drawn u	p for all claims		
Place of search Date of completion of the search			Examiner	
THE	HAGUE	07-07-1988	IBAR	ROLA TORRES O.M.

X: particularly relevant if taken alone
Y: particularly relevant if combined with another document of the same category
A: technological background
O: non-written disclosure
P: intermediate document

D: document cited for other reasons

&: member of the same patent family, corresponding