

12 **EUROPEAN PATENT APPLICATION**

21 Application number: **87111990.5**

51 Int. Cl.4: **G11B 13/04**, **G11B 11/10**

22 Date of filing: **18.08.87**

30 Priority: **20.08.86 JP 194961/86**
20.08.86 JP 194962/86
22.08.86 JP 195616/86

43 Date of publication of application:
02.03.88 Bulletin 88/09

84 Designated Contracting States:
AT DE FR GB NL

71 Applicant: **SONY CORPORATION**
7-35 Kitashinagawa 6-Chome Shinagawa-ku
Tokyo 141(JP)

72 Inventor: **Aratani, Katsuhisa**
c/o Sony Corporation 7-35 Kitashinagawa
6-chome
Shinagawa-ku Tokyo(JP)
 Inventor: **Tanaka, Tomiji**
c/o Sony Corporation 7-35 Kitashinagawa
6-chome
Shinagawa-ku Tokyo(JP)


74 Representative: **Patentanwälte TER MEER -**
MÜLLER - STEINMEISTER
Mauerkircherstrasse 45
D-8000 München 80(DE)

54 **Thermo-magnetic recording method applying power modulated laser on magnetically coupled double layer structure of perpendicular anisotropy film.**

57 Thermomagnetic recording method using a thermomagnetic recording medium having a superposed layer (5) of magnetically coupled first and second magnetic thin films (3,4) is disclosed. The magnetic thin film includes a portion where the respective magnetic moments of the first and second thin films are coupled in opposite directions to each other (mode C). The method comprises heating the superposed layer in a first heating state in which the superposed layer (5) is heated at a temperature T_1 which is higher than the Curie temperature T_{C1} of the first magnetic thin film (3) and will not cause the inversion of the magnetic moment of the second magnetic thin film (4) or in a second heating state in which the superposed layer (5) is heated at a temperature T_2 which is higher than the Curie temperature T_{C1} and is high enough to cause the inversion of the magnetic moment of the second magnetic thin film (4) by modulating heating condition according to an information signal to be recorded; and forming recording magnetization on the thermomagnetic recording medium by cooling the heated superposed layer of the thermomagnetic recording medium.

In the method, real-time overwriting information can be achieved without using a modulated external magnetic field.

FIG. 1



**Thermomagnetic Recording Method Applying Power Modulated Laser on a Magnetically Coupled
Double Layer Structure of Perpendicular Anisotropy Film**

BACKGROUND OF THE INVENTION:

The present invention relates to a thermomagnetic recording method using a laser beam to write data on a thermomagnetic recording medium, and more particularly relates to the method using a power modulated laser beam which can overwrite data without using external magnetic field modulation.

In an optomagnetic recording method or a thermomagnetic recording method, a recording medium having a magnetic thin film having perpendicular anisotropy is initialized by magnetizing the thin film beforehand in one direction perpendicular to the surface of the recording medium, and then a bit perpendicularly magnetized in a direction opposite the initial direction of magnetization by local heating of the recording medium, for example, by laser beam irradiation to record binary information.

In the optomagnetic recording method or the thermomagnetic recording method, the recorded information needs to be erased (initialization of the recording medium) prior to rewriting information, and hence it is impossible to carry out recording at a high transmission rate. Several overwrite systems, namely, recording systems not requiring such an independent erasing process preceeding to rewriting, have been proposed. Among the thermomagnetic recording methods for overwriting system, prospective methods are, for example, a thermomagnetic recording method using an external magnetic field modulation in which the polarity of an external magnetic field acting on a recording medium is inverted according to an information signal, and a thermomagnetic recording method of a two-head system employing an erasing head initialize the medium prior to recording in addition to a recording head. In the thermomagnetic recording method of an external magnetic field modulation system, for example, as disclosed in Japanese Patent Provisional Publication (Kokai) No. 60-48806, to record information on an amorphous ferrimagnetic thin film recording medium having an easy direction of magnetization perpendicular to the surface of the thin film, a magnetic field of a polarity corresponding to an input digital signal is applied to a region on the recording medium to be irradiated by a heating beam.

However, high-speed recording at a high information transmission rate by the thermomagnetic recording method of an external magnetic field modulation system requires an electromagnet capable of operating at a very high frequency on the order of megahertz (MHz). It is difficult to make such an electromagnet. Even if such an electromagnet is available, such an electromagnet is not capable of practical application due to its high power consumption rate and high heat generation. The thermomagnetic recording method of a two-head system has disadvantages that an additional head is necessary, the two heads must be spaced apart, load on the driving system increases to deteriorate the economic effect, and the apparatus is not suitable for mass production.

35

OBJECT AND SUMMARY OF THE INVENTION:

Accordingly, it is an object of the present invention to provide a thermomagnetic recording method capable of overwriting informations.

It is another object of the present invention to provide a thermomagnetic recording method using a power modulated laser beam without using a modulated external magnetic field.

It is further object of the present invention to provide a thermomagnetic recording method in which, recorded information is stable upon preservation.

It is still further object of the present invention to provide a thermomagnetic recording method in which signal reproduction can be achieved with high S/N ratio.

According to the present invention, there is provided a thermomagnetic recording method using a thermomagnetic recording medium having a superposed film formed of magnetically coupled first and second magnetic thin films and including a portion in which the respective magnetic moments of the first and second magnetic thin films are coupled opposite to each other which comprises heating the thermomagnetic recording medium in a first heating state where the thermomagnetic recording medium is heated at a temperature T_1 higher than the Curie temperature T_{C1} of the first magnetic thin film and will not cause the inversion of the magnetic moment of the second magnetic thin film or in a second heating state

in which the thermomagnetic recording medium is heated at a temperature T_2 which is higher than the Curie temperature T_{C1} and is high enough to cause the inversion of the magnetic moment of the second magnetic thin film by modulating heating condition according to an information signal to be recorded; and cooling the heated thermomagnetic recording medium to record binary information.

- 5 Overwriting information is achieved simply by modulating the intensity or duration of irradiation of a heating beam, such as a laser beam, according to an information signal to be recorded.

BRIEF DESCRIPTION OF THE DRAWINGS:

10

Figures 1 and 8 are diagrammatic illustrations of assistance in explaining the procedure of implementing preferred embodiments of the present invention, showing modes of magnetization;

Figure 2 is a schematic, fragmentary sectional view of a thermomagnetic recording medium employed in the embodiment of the present invention, showing the laminated construction;

15

Figures 3 and 9 are schematic views showing exemplary recording apparatuses;

Figures 4 and 10 are illustrations of assistance in explaining the transition of modes of magnetization;

Figure 5 is a diagram showing the variation of mode of magnetization with the variation of the intensity of an external magnetic field;

20

Figure 6 is an illustration of assistance in explaining another embodiment of the present invention, showing modes of magnetization; and

Figure 7 is a schematic, fragmentary view of assistance in explaining a manner of applying an external magnetic field to a thermomagnetic recording medium, in another embodiment of the present invention.

25

Figure 11 is a graph showing the temperature dependency of the coercive force and magnetization of magnetic thin film used in one embodiment.

DESCRIPTION OF THE PREFERRED EMBODIMENTS:

30

Fig. 1 shows the magnetization state of the superposed film structure 5, formed of a first magnetic thin film 3 and a second magnetic thin film 4 magnetically coupled with each other.

35

The superposed film structure 5 having a recording portion in which the respective directions of the respective magnetically coupled magnetic moments of a first magnetic thin film 3 and a second magnetic thin film 4 are the same (state A) and a recording portion in which the respective directions of the magnetically coupled magnetic moments are opposite to each other (state C) is heated in a heating mode in which the laminated film is heated at a temperature T_1 which is higher than the Curie temperature T_{C1} of the first magnetic thin film 3 and will not cause the inversion of the magnetic moment of the second magnetic thin film 4 under the influence of an external magnetic field H_1 or in a heating mode in which the laminated film is heated at a temperature T_2 which is higher than the Curie temperature T_{C1} and is high enough to cause the inversion of the magnetic moment of the second magnetic thin film 4 under the influence of the external magnetic field H_1 by modulating heating condition according to an information signal to be recorded, and then the heated laminated film is cooled for recording magnetization of the thermomagnetic recording medium.

45

G-1. Constitution of the Thermomagnetic Recording Medium;

50

The constitution of a thermomagnetic recording medium employed in the first embodiment of the present invention will be described briefly with reference to Fig. 2. A transparent dielectric film 2 serving as a protective film or an interference film is formed over one surface (lower surface, in Fig. 2) of a transparent substrate 1 such as a glass plate or an acrylic resin plate. A double-layer magnetic film 5 comprising a first magnetic thin film 3 and a second magnetic thin film 4 is formed over the transparent dielectric film 2. The surface (lower surface) of the double-layer magnetic film 5 is coated with a dielectric film 6 serving as a protective film. The dielectric films 2 and 6 may be omitted or the dielectric film 6 may be a metallic film.

55

Further a metallic film (not shown) may be formed over the dielectric film 6.

There are various possible magnetic materials for forming the first magnetic thin film 3 and second magnetic thin film of the double-layer magnetic film 5. In this embodiment, the magnetic material is assumed to be an amorphous alloy RE_xTM_{1-x} containing $x = 10$ to 40 atm% of one or more than one of rare earth metals (RE) such as Nd, Sm, Gd, Tb, Dy and Ho, and $1-x = 90$ to 60 atm% of one or more than one of transition metals such as Cr, Mn, Fe, Co, Ni and Cu. The magnetic material may contain a small amount of elements other than those rare earth metals and transition metals. In such a magnetic amorphous RE-TM alloy, the magnetic moment of RE and that of TM are coupled antiparallel with each other except when RE is Nd or Sm. Accordingly, the amorphous magnetic RE-TM alloy is so-called ferrimagnetic material, and the total magnetization is the difference between the respective sublattice magnetization of RE and TM (addition of the respective sublattice magnetization when the direction of magnetic moment is taken into consideration). When RE is either Nd or Sm, or a mixture of Nd and Sm, the respective magnetic moments of RE and TM are coupled in parallel, and hence the amorphous magnetic RE-TM alloy is so-called ferromagnetic material. In this case, the total magnetization is the addition of the respective sublattice magnetization of RE and TM. In this embodiment, RE is Gd, Tb, Dy or Ho.

Laser light R for recording or reproducing is projected, for example, as shown in Fig. 3, on the thermomagnetic recording medium 10 from the side of the transparent substrate 1 (Fig. 2), while the respective magnetic field H_1 and H_2 of magnets 11 and 12 are applied to the thermomagnetic recording medium 10 from the side of the protective dielectric film 6 as shown in Fig. 3 or from the side of the transparent substrate 1. In Fig. 3, the magnets 11 and 12 are spaced apart, however, as will be described hereinafter, the magnets 11 and 12 may be disposed adjacent to each other or the magnets 11 and 12 may be the same magnets. In the case of Fig. 3, the thermomagnetic recording medium 10 is a disk, which is driven for rotation by the spindle 16 of a driving motor 15, and the magnets 11 and 12 are different from each other in polarity; the magnets 11 and 12 may be the same in polarity, which will be described hereinafter.

Possible modes of the double-layer magnetic film 5 formed by superposing the magnetic thin films 3 and 4 of a RE-TM alloy in a temperature range below the respective Curie temperatures T_{C1} and T_{C2} of the magnetic thin films 3 and 4 are manifested by four modes A to D as shown in Fig. 4. The respective easy directions of magnetization of the magnetic thin films 3 and 4 are supposed to be perpendicular to the surface of the films, namely, the magnetic thin films 3 and 4 are supposed to be so-called perpendicular anisotropy magnetic thin films, however, only either one of the magnetic thin films 3 and 4 may be a perpendicular anisotropy magnetic thin film.

Referring to Fig. 4, in the modes A and B, the respective directions of the respective magnetic moments of the respective TMs of the first magnetic thin film 3 and the second magnetic thin film 4 are the same as indicated by arrows shown by solid lines, and those of the REs of the magnetic thin film 3 and the magnetic thin film 4 are the same as indicated by arrows shown by broken lines. In the modes C and D, the respective directions of the respective magnetic moments of the respective TMs of the first magnetic thin film 3 and the second magnetic thin film 4 are opposite to each other as indicated by arrows shown by solid lines in Fig. 4, and those of the REs of the magnetic thin film 3 and the magnetic thin film 4 are opposite to each other as indicated by arrows shown by broken lines in Fig. 4, so that a region where the directions of the magnetic moment of the TM and the magnetic moment of RE change through an angle of 180° , namely, an interface magnetic wall, is formed at the interface of the first magnetic thin film 3 and the second magnetic thin film 4. This interface magnetic wall is designated as a interface wall 7. An interface magnetic wall energy per unit area (σ_w erg/cm²) is stored in the interface wall 7.

45

G-2. Transition of Mode of Magnetization:

Magnetic energies E_A , E_B , E_C and E_D (erg/cm²) of the modes A to D shown in Fig. 4 when an external magnetic field H (Oe) is applied to the double-layer magnetic film 5 are expressed approximately by Zeeman energy and the interface wall energy density σ_w in erg/cm² unit as follows

$$\begin{aligned} E_A &= -M_{s1}h_1H - M_{s2}h_2H \\ E_B &= M_{s1}h_1H + M_{s2}h_2H \\ E_C &= M_{s1}h_1H - M_{s2}h_2H + \sigma_w \\ E_D &= -M_{s1}h_1H + M_{s2}h_2H + \sigma_w \end{aligned}$$

where M_{s1} and M_{s2} are the saturation magnetizations M_s (emu/cm³) of the magnetic thin films 3 and 4, respectively, and h_1 and h_2 are the respective thicknesses (cm) of the magnetic thin films 3 and 4. The saturation magnetization M_s is obtained by subtracting the sublattice magnetization M_{TM} of TM (transition metal) from the sublattice magnetization M_{RE} of RE (rare earth

metal). The saturation magnetization M_s is defined generally by

$$M_s = |M_{RE} - M_{TM}|$$

However, in the present invention, the saturation magnetization M_s is defined by

$$M_s = M_{RE} - M_{TM}$$

- 5 Accordingly, when $M_{RE} \geq M_{TM}$ or $M_{RE} < M_{TM}$, $M_s \geq 0$, or $M_s < 0$, respectively. Further, the respective rectangular ratios of the magnetic thin films 3 and 4 are 1 (one), and the direction of the external magnetic field H indicated by an arrow in Fig. 4 is supposed to be a positive direction. However, in practice, the rectangular ratio need not necessarily be 1 (one). Although the magnetic energies of the modes A to D are determined approximately on the basis of Zeeman energy and the magnetic domain wall energy density σ_w ,
10 more strictly, the stray magnetic field of the adjacent bits must be taken into consideration, however, the stray magnetic field is not taken into consideration herein.

- When the coercive force of the first magnetic thin film or magnetic field to invert the magnetization of the first magnetic thin film 3 is H_{c1} (Oe) and that of the second magnetic thin film 4 is H_{c2} . Then, the energy necessary for inverting the magnetization of the first magnetic thin film 3, namely, the coercive force energy
15 E_1 (erg/cm²) and the energy necessary for inverting the magnetization of the second magnetic thin film 4, namely, the coercive force energy E_2 (erg/cm²) are expressed by

$$E_1 = 2|M_{s1}|h_1H_{c1}$$

$$E_2 = 2|M_{s2}|h_2H_{c2}$$

- To change the mode of magnetization from a mode j ($j = A$ to D) to a mode i ($i = A$ to D , $j \neq i$), $E_i - E_j$
20 $= E_{ij}$ must be greater than the coercive force energy (E_1 , E_2 or $E_1 + E_2$). For example, to change the mode of magnetization from the mode A to the mode B, an inequality:

$$E_{AB} = E_A - E_B > E_1 + E_2$$

must be satisfied. Accordingly,

$$-2M_{s1}h_1H - 2M_{s2}h_2H > 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2}$$

25

G-3. Change of Mode of Magnetization According to Temperature Variation - (1)

- Change of the mode of magnetization of the magnetic thin films of the double-layer magnetic film 5 with
30 temperature variation caused by laser irradiation or the like will be described with reference to Fig. 1.

- Suppose that a recording bit of the double-layer magnetic film 5 of the thermomagnetic recording medium 10 is in the mode A (Fig. 1) at room temperature T_R , and the bit of the double-layer magnetic film 5 in the mode A is irradiated by laser light for recording. The intensity of the laser light or the duration of laser irradiation is controlled according to a recording signal to heat the double-layer magnetic film 5
35 selectively to a first temperature T_1 or to a second temperature T_2 . The first temperature T_1 is higher than the Curie temperature T_{c1} of the first magnetic thin film 3 and is a temperature at which the inversion of magnetization of the second magnetic thin film 4 will not occur when the second magnetic thin film 4 is subjected to the influence of an external magnetic field H_1 , while the second temperature T_2 is higher than the first temperature T_1 and is a temperature high enough to cause the inversion of magnetization of the
40 second magnetic thin film 4 when the second magnetic thin film 4 is subjected to the influence of the external magnetic field H_1 . That is, an area around the bit heated by the laser light is under the influence of the external magnetic field H_1 of the magnet 11, which is strong enough to invert the magnetization of the second magnetic thin film 4 at the temperature T_2 .

- Upon cooling the double-layer magnetic film 5 to the temperature T_{c1} after the same has been heated
45 to such a temperature, a spontaneous magnetization appears in the first magnetic thin film 3. The external magnetic field H_1 , and the saturation magnetization M_{s1} and thickness h_1 of the first magnetic thin film 3 are determined selectively to meet an inequality:

$$\sigma_w > 2|M_{s1}|h_1H_1$$

- at the temperature T (near the temperature T_{c1}) where a spontaneous magnetism appears in the first
50 magnetic thin film 3 to make the exchange energy acting between the two magnetic thin layers dominant rather than the Zeeman energy in determining the direction of the magnetism of the first magnetic thin film 3. Accordingly, when the temperature T of the double-layer magnetic film 5 coincides with the temperature T_{c1} , the double-layer magnetic film 5 is in the mode A or the mode B where the respective directions of magnetization of the first and second magnetic thin films are the same. When the heating temperature is T_1 ,
55 the mode A is established and, when the heating temperature is T_2 , the mode B is established.

When the recording bit is cooled further, for example, to a temperature near the room temperature T_R , the initial mode A is established in the bit in the mode A at the temperature T. Mode B in which the direction of magnetization is opposite to that of the initial state is established in the bit in the mode B at temperature T, however, as shown in Fig. 3, the magnet 12 applies an external magnetic field H_2 meeting conditions which will be described in G-4 to the thermomagnetic recording medium 10 at a temperature near the room temperature T_R to invert the magnetism of the second magnetic thin film 4, so that the mode C (Fig. 4) is established in the double-layer magnetic film 5.

When a recording bit in the mode C of the double-layer magnetic film 5 of the thermomagnetic recording medium 10 is heated to a temperature above the temperature T_{c1} , the magnetization of the first magnetic thin film 3 disappears and the same state of magnetization as that of a recording bit in the mode A in the initial state heated to the temperature above the temperature T_{c1} is established in the recording bit. Accordingly, the mode A is established in the recording bit cooled after being heated to the temperature T_1 , while the mode B is established in the recording bit cooled after being heated to the temperature T_2 . Thus, a mode of recording magnetization according to the temperature T_1 or T_2 is obtained. A recording bit in the mode B is changed into a recording bit in the mode C at least prior to the successive overwriting operation to turn the direction of magnetization of the second magnetic thin film 4 in the direction of magnetization of the second magnetic thin film in the mode A.

A recording bit in which the respective directions of the magnetically coupled magnetic moments of the first magnetic thin film 3 and second magnetic thin film 4 of the double-layer magnetic film 5, namely, a recording bit in the mode A, and a recording bit in which the respective directions of magnetically coupled magnetic moments of the same are opposite to each other, namely, a recording bit in the mode C, are heated to the temperature T_1 or T_2 according to information signals by regulating the heating condition to establish new mode of magnetization for recording magnetization regardless of the initial mode of magnetization, and thereby overwrite is achieved.

G-4. Conditions for Overwrite - (1);

Conditions for overwrite will be described hereinafter.

In changing the temperature T of the double-layer magnetic film 5 under the influence of the magnetic field H_1 as shown in Fig. 1, conditions for restraining the mode A from changing to the other modes in the temperature range from the room temperature T_R to a temperature below the Curie temperature T_{c1} of the first magnetic thin film 3 ($T_R \leq T < T_{c1}$) are expressed by inequalities:

$$\begin{aligned} -2M_{s1}h_1H_1 - 2M_{s2}h_2H_1 &< 2|M_{s1}|h_1H_{c1} - 2|M_{s2}|h_2H_{c2} \\ -2M_{s1}h_1H_1 - \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ -2M_{s2}h_2H_1 - \sigma_w &< 2|M_{s2}|h_2H_{c2} \end{aligned}$$

and conditions for restraining the mode C from changing to the other modes are expressed by inequalities:

$$\begin{aligned} 2M_{s1}h_1H_1 + \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ -2M_{s2}h_2H_1 + \sigma_w &< 2|M_{s2}|h_2H_{c2} \end{aligned}$$

A condition for restraining the inversion of sublattice magnetization of the second magnetic thin film 4 while the temperature T of the double-layer magnetic film 5 is in the range from a temperature above the temperature T_{c1} to a temperature below the second temperature T_2 ($T_{c1} < T < T_2$) is expressed by an inequality:

$$|H_1| > H_{c2}$$

and a condition for causing the inversion of the sublattice magnetization of the second magnetic thin film 4 when the temperature T of the double-layer magnetic film 5 is above the temperature T_2 is expressed by an inequality:

$$|H_1| < H_{c2}$$

In cooling the double-layer magnetic film 5 after heating the same to such a temperature, a condition for allowing the direction of the magnetization of the first magnetic thin film 3 is determined by the exchange coupling with the direction of the magnetization of the second magnetic thin film 4 upon the arrival of the temperature T of the recording bit of the double-layer magnetic film 5 of the thermomagnetic recording medium 10 approximately at the Curie temperature T_{c1} of the first magnetic thin film 3 (T is approximately equal to T_{c1}) is

$$\sigma_w > 2|M_{s1}|h_1|H_1|$$

and conditions for restraining the mode A from changing to the other modes in the temperature range of $T_R \leq T < T_{c1}$ are the same as those in the heating process, while conditions for restraining the mode B from

changing to the other modes are

$$2M_{s1}h_1H_1 + 2M_{s2}h_2H_1 < 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2}$$

$$2M_{s1}h_1H_1 - \sigma_w < 2|M_{s1}|h_1H_{c1}$$

$$2M_{s2}h_2H_1 - \sigma_w < 2|M_{s2}|h_2H_{c2}$$

- 5 Conditions for restraining the mode A from changing to the other modes when the external magnetic field H_2 (the positive direction is indicated by an arrow in Fig. 1) to the double-layer magnetic film 5 at the room temperature are

$$-2M_{s1}h_1H_2 - 2M_{s2}h_2H_2 < 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2}$$

$$-2M_{s1}h_1H_2 - \sigma_w < 2|M_{s1}|h_1H_{c1}$$

10 $-2M_{s2}h_2H_2 - \sigma_w < 2|M_{s2}|h_2H_{c2}$

and conditions for causing the mode B into the mode C are

$$2M_{s1}h_1H_2 + 2M_{s2}h_2H_2 < 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2}$$

$$2M_{s1}h_1H_2 - \sigma_w < 2|M_{s1}|h_1H_{c1}$$

$$2M_{s2}h_2H_2 - \sigma_w > 2|M_{s2}|h_2H_{c2}$$

- 15 Thus the use of a two-layer magnetic film 5 meeting all the foregoing conditions enables overwrite.

In the foregoing description, the variation of mode of magnetization has been explained with reference to the modes A, B and C, however, overwrite is possible when the modes A, B and D are employed when the direction of magnetization of the second magnetic thin film 4 is to be turned in a direction opposite to that described hereinbefore. That is, in such a case, the modes A, B, C and D correspond to the modes B, A, D and C of the foregoing embodiment, respectively, and the saturation magnetization M_s is defined by

$$M_s = M_{TM} - M_{RE}$$

to apply the foregoing conditions for overwrite without change.

25 G-5. State of Magnetization for Reproduction and Preservation - (1);

To enable overwrite, it is necessary, as mentioned hereinbefore, that the directions of magnetization in the second magnetic thin film 4 are the same regardless of the signal recording condition (the direction of magnetization of the first magnetic thin film 3), and there are recording bits in which the respective
30 directions of the sublattice magnetization of the first magnetic thin film 3 and second magnetic thin film 4 of the double-layer magnetic film 5 are the same and recording bits in which the respective directions of the sublattice magnetization of the first magnetic thin film 3 and the second magnetic thin film 4 are opposite to each other. However, problems occur in reproducing recorded information or in preserving the thermomagnetic recording medium, when there are recording bits in which the directions of sublattice magnetization
35 are antiparallel.

When the respective directions of sublattice magnetization of the magnetic thin films 3 and 4 are antiparallel, the thickness h_1 of the first magnetic thin film 3 needs to be thick to improve the reproducing characteristics, and it is preferable, as apparent from the calculation of the magnetizing process, that the thickness h_2 of the second magnetic thin film 4 also is thick, and hence the thickness of the double-layer
40 magnetic film 5 is considerably large, which requires a laser having a large output capacity. However, under existing circumstances, it is difficult to acquire such a laser having a large output capacity of small size, for example, a semiconductor laser. Furthermore, even if the thermomagnetic recording medium is preserved at the room temperature, the double-layer magnetic film having the magnetic thin films in which the respective directions of sublattice magnetization are antiparallel is unstable to heat and magnetic field. Still
45 further, in a recording bit in which the directions of secondary lattice magnetization are antiparallel, only the magnetic thin film 3 stores information. Therefore, in reproducing the recorded information by the use of Kerr effect, the information can be read only from the side of the magnetic thin film 3. Particularly, when the Curie temperature T_{c2} of the second magnetic thin film 4 is higher than the Curie temperature T_{c1} of the first magnetic thin film 3 ($T_{c1} < T_{c2}$), the Kerr rotational angle θ_{k2} of the second magnetic thin film 4, in
50 general, is greater than the Kerr rotational angle θ_{k1} of the first magnetic thin film 3 ($\theta_{k1} < \theta_{k2}$). Accordingly, the SN ratio is improved when the signal is read from the side of the second magnetic thin film 4, however, such a way of reading signals is impossible when the directions of sublattice magnetization of the magnetic thin films are antiparallel. Accordingly, it is desirable that the direction of sublattice magnetization of the second magnetic thin film 4 and the direction of sublattice magnetization of the first magnetic thin film are
55 the same in reproducing recorded information or in preserving the thermomagnetic recording medium.

Conditions for making the respective directions of sublattice magnetization of the first and second magnetic thin films will be described hereinafter. Conditions for changing the mode C into the mode B by applying a third external magnetic field H_3 (the positive direction of the magnetic field is indicated by the arrow shown in Fig. 1) to a magnetic recording medium having recording bits in the modes A and C are

$$\begin{aligned} 2M_{s1}h_1H_3 + \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ -2M_{s2}h_2H_3 + \sigma_w &> 2|M_{s2}|h_2H_{c2} \end{aligned}$$

At the same time, necessary conditions for inhibiting the transition of the mode A to the mode B, C or D are

$$\begin{aligned} -2M_{s1}h_1H_3 - 2M_{s2}h_2H_3 &< 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2} \\ -2M_{s1}h_1H_3 - \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ 2M_{s2}h_2H_3 - \sigma_w &< 2|M_{s2}|h_2H_{c2} \end{aligned}$$

The operating temperature and the temperature of the magnetic recording medium during reproducing need to meet those conditions. When a further external magnetic field H_{ex} , for example, the external magnetic field H_2 shown in Fig. 1, is applied in addition to the third external magnetic field H_3 to the thermomagnetic recording medium, further conditions to align the magnetization direction during preservation, which will be described hereinafter, in addition to the foregoing conditions need to be satisfied. The positive direction of the external magnetic field H_{ex} is the same as that of the external magnetic field H_3 , and hence, in some cases, $H_{ex} < 0$. First, conditions for restraining the mode A from changing are obtained by substituting the H_3 of the foregoing expressions by H_{ex} . Conditions for restraining the mode B established by changing the mode C from changing are

$$\begin{aligned} 2M_{s1}h_1H_{ex} + 2M_{s2}h_2H_{ex} &< 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2} \\ 2M_{s1}h_1H_{ex} - \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ 2M_{s2}h_2H_{ex} - \sigma_w &< 2|M_{s2}|h_2H_{c2} \end{aligned}$$

Although the conditions for reproducing and preservation have been explained with reference to the variation of the modes A, B and C, the same transition of the modes is possible when the modes A, B and D are used when the direction of magnetization of the second magnetic thin film 4 in the initial state is opposite to that explained hereinbefore. In such a case, the modes A, B, C and D correspond to the modes B, A, D, and C in the foregoing description, respectively. Thus, the mode D at the completion of overwrite is changed to the mode A which is suitable for reproducing and preservation.

30

G-6. Example of the Thermomagnetic Recording Medium - (1);

Concrete examples of magnetic materials for forming the magnetic thin films 3 and 4 of the double-layer magnetic film 5 of the thermomagnetic recording medium 10 will be described hereinafter.

RE-TM ferrimagnetic thin films serving as the first magnetic thin film 3 and the second magnetic thin film 4 were formed in that order over a glass plate serving as the transparent substrate 1 (Fig. 2) by a DC magnetron sputtering apparatus to form a double-layer magnetic film 5. In this case, the dielectric film 2 was omitted. The RE-TM ferrimagnetic thin films 3 and 4 were formed by alternately superposing RE (rare earth metal) and TM (transition metal) layers. To prevent the oxidation of the double-layer magnetic film 5 consisting of the magnetic thin films 3 and 4, the double-layer magnetic film 5 was coated with a protective film 6 having a thickness of 800 angstroms (the lower surface in Fig. 2). The individual films were formed under the same conditions as those for forming the double-layer magnetic film 5. The magnetic characteristics of the films and the interface wall energy density σ_w were evaluated. The materials, film thickness and characteristics at the room temperature of the magnetic thin films 3 and 4 are tabulated in Table 1.

45

50

55

Table 1

	First magnetic thin film	Second magnetic thin film
Material	TbFe	GdTbFeCo
Thickness (\AA)	310	1500
Curie point ($^{\circ}\text{C}$)	137	192
Saturation magnetization (emu/cm ³)	95	145
Coercive force (kOe)	9.8	2.6

In both the first magnetic thin film 3 and the second magnetic thin film 4, the sublattice magnetization of the RE is greater than that of the TM (RE rich) at the room temperature. The interface magnetic wall energy density at the room temperature was 2.0 erg/cm² which was calculated by comparing the MH loops of the respective single layer films and the double-layer film.

An external magnetic field of 20 kOe was applied to the thermomagnetic recording medium having the double-layer magnetic film 5 thus formed to initialize the double-layer magnetic film 5 in the mode A shown in Fig. 4. Then, the thermomagnetic recording medium was heated to a temperature T with the external magnetic field H₁ (Fig. 1) of 0.3 kOe applied thereto, and then the thermomagnetic recording medium was cooled to the room temperature. During the heating and cooling process, the thermomagnetic recording medium was irradiated from the side of the transparent substrate 1 (the glass plate) by a linearly polarized light of 830 nm in wavelength to observe the condition of magnetization by Kerr effect. When the temperature T was 150°C, the mode A of magnetization remained unchanged after heating and cooling. When the temperature T was 200°C, the mode of magnetization changed from the mode A to the mode B, in which the respective directions of magnetization of the magnetic thin films 3 and 4 were inverted after heating and cooling.

Then, the external magnetic field H₂ (Fig. 1) of 5 kOe was applied to the thermomagnetic recording medium which was in the mode B at the room temperature, whereby the mode of magnetization of the double-layer magnetic film 5 was caused to changed from the mode B to the mode C. When the external magnetic field H₂ was applied to the thermomagnetic recording medium in the mode A, the mode of magnetization remained unchanged.

The same thermomagnetic recording medium in the mode C at the room temperature was heated to the temperature T with the external magnetic field H₁ applied thereto, and then the thermomagnetic recording medium was cooled to the room temperature. When the temperature T was 150°C, the mode of magnetization was the mode A after heating and cooling, while the mode of magnetization was the mode B after heating and cooling, when the temperature T was 200°C.

The sample double-layer magnetic film subjected to the measurement meets the conditions for overwriting described in article G-4. at temperatures: the room temperature, 50°C, 75°C, 100°C, 125°C and 150°C. At temperatures other than those temperatures, since M_s, 1/H_c and σ_w vary continuously, it is considered that, substantially, the foregoing conditions are satisfied. The value of the external magnetic field necessary for changing the mode of magnetization at each temperature agreed well with the value calculated on the basis of the expressions representing the conditions, from which it is apparent that the foregoing expressions representing the conditions for overwriting provides appropriate conditions for the practical application of the thermomagnetic recording method of the present invention.

Fig. 5 shows the transition of the mode of magnetization of the double-layer magnetic film 5 consisting of the magnetic thin films 3 and 4 having properties shown in Table 1 with the variation of the external magnetic field H at the room temperature. In Fig. 5, H_{01} is intensity of the external magnetic field where the transition of the mode D to the mode A (or the mode C to the mode B) occurs; H_{02} is intensity of the same where the transition of the mode B to the mode C (or the mode A to the mode D) occurs; H_{03} is intensity of the same where the transition of the mode C to the mode A (or the mode D to the mode B) occurs. The intensity of the external magnetic field causing the transition of the mode of magnetization was measured on the basis of Kerr effect. From the intensity of the external magnetic field H_{03} and the data shown in Table 1, calculated interface wall energy density σ_w equals to 2.0 erg/cm². The calculated values of H_{01} and H_{02} calculated by using the calculated interface wall energy density σ_w agreed well with the measured values, respectively.

Referring to Fig. 5, when the mode of magnetization during recording is either the mode A or the mode C (or either the mode B or the mode D), the reproduction of recording bits in the modes A or B is possible when an external magnetic field of a magnetic intensity of H_{exA} (or H_{exB}) meeting

$-H_{02} < H_{exA} < -H_{02}$ (or $H_{01} < H_{exB} < H_{02}$) is applied to the double-layer magnetic film.

When the mode of magnetization of the double-layer magnetic film 5 is the mode A or the mode B in reproducing recorded signals, both the magnetic thin films 3 and 4 of the double-layer magnetic film 5 are available for reading the signals, which improves the SN ratio of the reproduced signals as mentioned above as compared with the SN ratio of the reproduced signals reproduced from the double-layer magnetic film 5 in the mode C (or the mode D).

When the mode of magnetization at the end of overwrite is either the mode A or the mode C (or either the mode B or the mode D), preservation and reproduction in the mode A or the mode B are possible by applying an external magnetic field of H_{exA} (or H_{exB}) meeting the foregoing condition to the double-layer magnetic film 5. If another magnetic field of H_{exC} is applied to the double-layer magnetic film 5 in applying the external magnetic field of H_{exA} (or H_{exB}) is applied, in preservation or in reproduction, an inequality:

$-H_{02} < H_{exC} < H_{02}$ (or $-H_{02} < H_{exD} < H_{02}$) must be satisfied.

30

G-7. Another Embodiment:

In the embodiment shown in Fig. 1, when the magnetic compensating point of the second magnetic thin film 4 is between the room temperature and the temperature T_2 , the external magnetic fields of H_1 and H_2 are the same in the direction of magnetic field as shown in Fig. 6.

When the external magnetic fields of H_1 and H_2 are the same in the direction of magnetic field as shown in Fig. 6, both the external magnetic fields of H_1 and H_2 can be formed by a single magnet 13 as shown in Fig. 7. A thermomagnetic recording medium 10 is irradiated by a laser light R at a position near the magnet 13 where the intensity of the magnetic field of the magnet 13 is not the maximum, so that the intensity H_1 of the external magnetic field at the irradiated position is smaller than the intensity H_2 ($H_1 < H_2$).

Further embodiment will be described hereinafter, in which the external magnetic field H_2 is not required to change the mode B into the mode C, when the second magnetic thin film has a magnetic compensation temperature between room temperature and recording temperature T_2 . In the embodiment similar double-layer magnetic film 5 as shown in Fig. 2 is employed and the magnetization condition changes as shown in Fig. 8.

Referring to Fig. 8, a double-layer magnetic film 5 having a recording portion in which the respective directions of the respective magnetic moments of a first magnetic thin film 3 and a second magnetic thin film 4, which are coupled magnetically, are the same (mode A) and a recording portion in which the respective directions of the respective magnetic moments of the magnetically coupled first magnetic thin film 3 and the second magnetic thin film 4 are opposite to each other (mode C) is heated in a heating mode in which the superposed magnetic film is heated at a temperature T_1 which is higher than the Curie temperature T_{C1} of the first magnetic thin film 3 and will not cause the inversion of the sublattice magnetization of the second magnetic thin film 4 or in a heating mode in which the superposed magnetic film 5 is heated at a temperature T_2 which is higher than the Curie temperature T_{C1} and is high enough to cause the inversion of the sublattice magnetization of the second magnetic thin film 4 by modulating heating condition according to an information signal to be recorded, and then the heated superposed magnetic film 5 is cooled for recording the magnetic moment in the thermomagnetic recording medium.

The second magnetic thin film 4 has a compensation temperature between the room temperature T_R has a compensation temperature between the room temperature T_R and the temperature T_2 at which the superposed magnetic film 5 is heated in the first heating mode. The direction of the sublattice magnetization of the second magnetic thin film 4 is inverted during the course of cooling.

Possible modes of the double-layer laminated magnetic film 5 formed by laminating the magnetic thin films 3 and 4 of a RE-TM alloy in a temperature range below the respective Curie temperatures T_{C1} and T_{C2} of the magnetic thin films 3 and 4 are manifested by four modes A to D as shown in Fig. 10. The respective easy directions of magnetization of the magnetic thin films 3 and 4 are supposed to be perpendicular to the surface of the thin films, namely, the magnetic thin films 3 and 4 are supposed to be so-called perpendicular anisotropy magnetic thin films, however, only either one of the magnetic thin films 3 and 4 may be a perpendicular anisotropy magnetic thin film.

Referring to Fig. 10, in the modes A and B, the respective directions of the respective magnetic moments of the respective TMs of the first magnetic thin film 3 and the second magnetic thin film 4 are the same as indicated by arrows shown by solid lines, and those of the REs of the magnetic thin film 3 and the magnetic thin film 4 are the same as indicated by arrows shown by broken lines. In the modes C and D, the respective directions of the respective magnetic moments of the respective TMs of the first magnetic thin film 3 and the second magnetic thin film 4 are opposite to each other as indicated by arrows shown by solid lines in Fig. 10, and those of the REs of the first magnetic thin film 3 and the second magnetic thin film 4 are opposite to each other as indicated by arrows shown by broken lines in Fig. 10, so that a region where the directions of the magnetic moment of TM and the magnetic moment of RE change through an angle of 180° , namely, an interface magnetic wall, is formed in the interface of the first magnetic thin film 3 and the second magnetic thin film 4. This interface magnetic wall is designated as an interface wall 7. An interface magnetic wall energy per unit area (σ_w erg/cm²) is stored in the interface wall 7.

G-8. Change of Mode of Magnetization According to Temperature Variation - (2);

Change of the mode of magnetization of the magnetic thin films of the superposed magnetic film 5 with temperature variation caused by laser irradiation or the like will be described with reference to Fig. 8, in which arrows of solid lines shown in the magnetic thin films 3 and 4 indicate the magnetic moment (magnetization) of TM (transition metal) and arrows of broken lines indicate the magnetic moment (magnetization) of RE (rare earth metal).

Suppose that a recording bit of the double-layer magnetic film 5 of the thermomagnetic recording medium 10 is in the mode A (Fig. 8) at the room temperature T_R , and the bit of the superposed magnetic film 5 in the mode A is irradiated by laser light for recording. The intensity of the laser light or the duration of laser irradiation is controlled according to a recording signal to heat the laminated magnetic film 5 selectively to a first temperature T_1 or to a second temperature T_2 . The first temperature T_1 is higher than the Curie temperature T_{C1} of the first magnetic thin film 3 and is a temperature at which the inversion of the sublattice magnetization of the second magnetic thin film 4 will not occur when the second magnetic thin film 4 is subjected to the influence of an external magnetic field H_{ex} , which will be described hereinafter, while the second temperature T_2 is higher than the first temperature T_1 and the compensation temperature of the second magnetic thin film 4, and is a temperature high enough to cause the inversion of the sublattice magnetization of the second magnetic thin film 4 when the second magnetic thin film 4 is subjected to the influence of the external magnetic field H_{ex} . Fig. 11 shows the temperature characteristics of the magnetization and the coercive force of the second magnetic thin film 4. The second magnetic thin film 4 has a compensation temperature T_{comp} between the room temperature T_R and the second temperature T_2 . Qualitatively, the intensity of the external magnetic field H_{ex} is greater than the coercive force H_c ($H_{ex} > H_c$) at the room temperature T_R and at the second temperature T_2 , and the coercive force H_c is greater than the intensity of the external magnetic field H_{ex} ($H_{ex} < H_c$) at the temperature T_1 and at the compensation temperature T_{comp} . Accordingly, the direction of sublattice magnetization of the second magnetic thin film 4 is inverted at the room temperature T_R and at the temperature T_2 by the external magnetic field H_{ex} of the magnet 11 which is shown in Fig. 9. More strict quantitative conditions will be described in article G-9.

In the initial condition in the mode A, the total magnetization of the second magnetic thin film is pointing upward in Fig. 8 because the sublattice magnetization of RE is larger than that of TM. When the temperature of the superposed thin film 5 is raised over the compensation temperature T_{comp} , the total magnetization of the second magnetic thin film 4 is pointing downward because over the compensation temperature the sublattice magnetization of TM is larger than that of RE. When the temperature is further

raised to T_2 , the total magnetization M_{s2} again inverted to follow the direction of the external magnetic field H_{ex} . In other words, the sublattice magnetizations are inverted at the temperature T_2 under the influence of the external magnetic field H_{ex} . Upon cooling the superposed magnetic film 5 to the temperature T_{C1} , after the same has been heated to the temperature T_1 or T_2 , spontaneous magnetization appears again in the first magnetic thin film 3, in which the exchange energy between the first magnetic thin film 3 and the second magnetic thin film 3 is more dominant than the Zeeman energy of the external magnetic field in determining the direction of the magnetic moment of the first magnetic thin film 3. That is, the saturation magnetization M_{s1} and the film thickness h_1 of the first magnetic thin film 3 in relation to the external magnetic field H_{ex} and the interface wall energy density σ_w are decided selectively so as to meet an inequality

$$\sigma_w > 2|M_{s1}|h_1H_{ex}$$

at a temperature T (a temperature near the temperature T_{C1}) at which a spontaneous magnetization appears in the first magnetic thin film 3. Accordingly, when the temperature T of the thermomagnetic recording medium coincides with the temperature T_{C1} , the mode A or B, in which the respective directions of the respective magnetization of the magnetic thin films 3 and 4 of the superposed magnetic film 5 are the same. The mode A is established when the heating temperature is T_1 , and the mode B is established when the heating temperature is T_2 .

When the recording bit of the thermomagnetic recording medium is cooled further, for example, to a temperature near the room temperature T_R , the initial mode A is established in the bit in the mode A, while the mode B in which the direction of the magnetic moment is opposite to that of the initial state is established in the bit in the mode B. However, to meet the conditions for the transition of the mode of magnetization from the mode B to the mode C, the magnetic moment of the second magnetic thin film 4 is inverted, and thereby the mode of magnetization of the laminated magnetic film 5 assumes the mode C as shown in Fig. 4.

During the course of cooling from the temperature T_2 , the direction of the total magnetization M_{s2} is changed from the M_{s2} at T_2 , just cooled to lower temperature than the compensation temperature. Though, the superposed thin film 5 is still under influence of the external magnetic field H_{ex} , the total magnetization of the magnetic thin film 4 again is changed the direction to point upward as shown in Fig. 8, the mode C.

When a recording bit in the mode C of the superposed magnetic film 5 of the thermomagnetic recording medium 10 is heated to a temperature above the temperature T_{C1} , the magnetization of the first magnetic thin film 3 disappears and the same mode of magnetization as that of a recording bit heated from the initial mode A is established in the recording bit. Accordingly, the mode of a recording bit heated to the temperature T_1 and then cooled becomes the mode A, while the mode of a recording bit heated to the temperature T_2 and then cooled becomes the mode C. Therefore, the mode of recording magnetization is dependent on the heating temperatures T_1 and T_2 .

Thus, a recording bit in which the respective directions of the magnetically coupled magnetic moments of the first magnetic thin film 3 and second magnetic thin film 4 of the superposed magnetic film 5 are the same, namely, a recording bit in the mode A, and a recording bit in which the respective directions of magnetically coupled magnetic moments of the first magnetic thin film 3 and the second magnetic thin film 4 are opposite to each other, namely, a bit in the mode C, are heated to the temperature T_1 or T_2 by regulating the heating condition according to information signals to establish a new mode of magnetization in the recording bit to enable overwrite irrespective of the initial mode of magnetization of the recording bit.

G-9. Conditions for Overwrite - (2);

Conditions for overwrite will be described hereinafter.

In changing the temperature T of the superposed magnetic film 5 under the influence of the external magnetic field H_{ex} as shown in Fig. 8, conditions for restraining the mode A from changing to the other modes in the temperature range from the room temperature T_R to a temperature below the Curie temperature T_{C1} of the first magnetic thin film 3 ($T_R \leq T < T_{C1}$) are expressed by inequalities:

$$-2M_{s1}h_1H_{ex} - 2M_{s2}h_2H_{ex} < 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2}$$

$$-2M_{s1}h_1H_{ex} - \sigma_w < 2|M_{s1}|h_1H_{c1}$$

$$-2M_{s2}h_2H_{ex} - \sigma_w < 2|M_{s2}|h_2H_{c2}$$

and conditions for restraining the mode C from changing are expressed by inequalities:

$$2M_{s1}h_1H_{ex} + \sigma_w < 2|M_{s1}|h_1H_{c1}$$

$$-2M_{s2}h_2H_{ex} + \sigma_w < 2|M_{s2}|h_2H_{c2}$$

A condition for restraining the inversion of the sublattice magnetization of the second magnetic thin film 4 while the temperature T of the superposed magnetic film 5 is in the range from a temperature above the temperature T_{C1} to a temperature below the second temperature T_2 ($T_{C1} < T < T_2$) is expressed by an inequality:

$$5 \quad |H_{ex}| < H_{c2}$$

and a condition for causing the inversion of the sublattice magnetization of the second magnetic thin film 4 when the temperature T of the superposed magnetic film 5 is above the temperature T_2 ($T > T_2$) is expressed by an inequality:

$$|H_{ex}| > H_{c2}$$

10 In cooling the superposed magnetic film 5 after heating the same to such a temperature, a condition for allowing the magnetization of the first magnetic thin film 3 is determined by the exchange energy with the magnetization of the second magnetic thin film 4 upon the fall of the temperature T of the recording bit of the superposed magnetic film 5 of the thermomagnetic recording medium 10 near to the Curie temperature T_{C1} of the first magnetic thin film 3 (T is approximately equal to T_{C1}) is:

$$15 \quad \sigma_w > 2|M_{s1}|h_1H_{ex}$$

and conditions for restraining the mode A from changing to the other modes in the temperature range of $T_R \leq T < T_{C1}$ are the same as those for the heating process, while conditions for allowing the transition of the mode B to the mode C are:

$$2M_{s1}h_1H_{ex} + 2M_{s2}h_2H_{ex} < 2|M_{s1}|h_1H_{C1} + 2|M_{s2}|h_2H_{C2}$$

$$20 \quad 2M_{s1}h_1H_{ex} - \sigma_w < 2|M_{s1}|h_1H_{C1}$$

$$2M_{s2}h_2H_{ex} - \sigma_w > 2|M_{s2}|h_2H_{C2}$$

When all the foregoing conditions for overwrite are satisfied by the superposed magnetic film 5, overwrite is feasible.

While the thermomagnetic recording medium is preserved at the room temperature, naturally, the mode A is maintained, however, the mode C may be maintained or the transition of the mode C to the mode B may occur.

Conditions for maintaining the mode C are:

$$\sigma_w < 2|M_{s1}|h_1H_{C1}$$

$$\sigma_w < 2|M_{s2}|h_2H_{C2}$$

30 and conditions for allowing the transition of the mode C to the mode B are:

$$\sigma_w < 2|M_{s1}|h_1H_{C1}$$

$$\sigma_w > 2|M_{s2}|h_2H_{C2}$$

Thus, the least necessary condition for the mode C is to satisfy either one of the sets of conditions.

When the conditions for restraining the transition of the mode C to other mode among those conditions for overwrite are not satisfied partly, namely, when the mode of magnetization changes from the mode C to the mode A while the thermomagnetic recording medium is heated from the room temperature T_R to the Curie temperature T_{C1} of the first magnetic thin film 3 ($T_R < T < T_{C1}$), there must be a temperature T_{CA} to provide

$$2M_{s1}h_1H_{ex} - \sigma_w = 2|M_{s1}|h_1H_{C1}$$

40 in that temperature range. In such a case, a necessary condition for overwrite is:

$$T_{BC} < T_{CA}$$

where T_{BC} is a temperature at which the mode of magnetization changes from the mode B to the mode C while the thermomagnetic recording medium is cooled after being heated to the temperature T_2 . However, even if this condition is not satisfied, overwrite is possible when the inversion of the magnetic moment of the first magnetic thin film 3 does not occur while the temperature drops from the temperature T_{BC} to the temperature T_{CA} . Naturally, the temperature T of the thermomagnetic recording medium must be below the temperature T_{CA} during reproduction, when there is such a temperature T_{CA} .

Although the variation of mode of magnetization has been explained in the foregoing description with reference to the modes A, B and C, overwrite is possible when the modes A, B and D are employed when the initial direction of magnetic moment of the second magnetic thin film 4 is turned in the opposite direction. That is, in the latter case, the modes A, B, C and D correspond to the modes B, A, D and C of the foregoing embodiment, respectively, and the saturation magnetic flux density M_s is defined by:

$$M_s = M_{TM} - M_{RE}$$

to apply the foregoing conditions for overwrite without change.

55

G-10. Mode of Magnetization for Reproduction and Preservation - (2):

As explained previously, problems occur in reproducing recorded information or in preserving the thermomagnetic recording medium, when there are recording bits in which the directions of the sublattice magnetic moments are antiparallel. Accordingly, it is desirable that the direction of sublattice magnetization of the second magnetic thin film 4 and the direction of sublattice magnetization of the first magnetic thin film 3 are the same in reproducing recorded information or in preserving the thermomagnetic recording medium.

Conditions for making the respective directions of sublattice magnetization of the first and second magnetic thin films parallel will be described hereinafter. Conditions for changing the mode of magnetization from the mode C to the mode B by applying another external magnetic field H_{ex1} (the positive direction of the magnetic field is indicated by the arrow indicating the direction of the external magnetic field H_{ex}) to a magnetic recording medium having recording bits in the modes A and C are:

$$\begin{aligned} 2M_{s1}h_1H_{ex1} - \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ -2M_{s2}h_2H_{ex1} - \sigma_w &> 2|M_{s2}|h_2H_{c2} \end{aligned}$$

Naturally, the following conditions for inhibiting the transition of the mode A to the other mode, in addition to the foregoing conditions, must be satisfied.

$$\begin{aligned} -2M_{s1}h_1H_{ex1} - 2M_{s2}h_2H_{ex1} &< 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2} \\ -2M_{s1}h_1H_{ex1} - \sigma_w &< 2|M_{s1}|h_1H_{c2} \\ -2M_{s2}h_2H_{ex1} - \sigma_w &< 2|M_{s2}|h_2H_{c2} \end{aligned}$$

The operating temperature and the temperature of the thermomagnetic recording medium during reproducing need to meet those conditions. When a further external magnetic field H_{ex2} is applied to the thermomagnetic recording medium, further conditions, which will be described hereinafter, in addition to the foregoing conditions need to be satisfied. The positive direction of the external magnetic field H_{ex2} is the same as that of the external magnetic field H_{ex1} and hence, in some cases, $H_{ex2} < 0$. First, conditions for restraining the mode A from changing are obtained by substituting the H_{ex1} of the foregoing inequalities by H_{ex2} . Conditions for restraining the mode B established by changing the mode C from changing are:

$$\begin{aligned} 2M_{s1}h_1H_{ex2} + 2M_{s2}h_2H_{ex2} &< 2|M_{s1}|h_1H_{c1} + 2|M_{s2}|h_2H_{c2} \\ 2M_{s1}h_1H_{ex2} - \sigma_w &< 2|M_{s1}|h_1H_{c1} \\ 2M_{s2}h_2H_{ex2} - \sigma_w &< 2|M_{s2}|h_2H_{c2} \end{aligned}$$

Although the conditions for reproducing and preservation have been explained with reference to the variation of the modes A, B and C, the same transition of the modes is possible when the modes A, B and D are used when the direction of magnetization of the second magnetic thin film 4 in the initial state is opposite to that explained hereinbefore. In such a case, the modes A, B, C and D correspond to the modes B, A, D and C in the foregoing description, respectively. Thus, the mode D at the completion of overwrite is changed to the mode A which is suitable for reproducing and preservation.

G-11. Example of the Thermomagnetic Recording Medium - (2):

Concrete examples of magnetic materials for forming the magnetic thin films 3 and 4 of the superposed magnetic film 5 of the thermomagnetic recording medium 10 will be described hereinafter.

RE-TM ferrimagnetic thin films serving as the first magnetic thin film 3 and the second magnetic thin film 4 were formed in that order over a glass plate serving as the transparent substrate 1 by a DC magnetron sputtering apparatus to form a superposed magnetic film 5. In this case, the dielectric film 2 was omitted. The RE-TM ferrimagnetic thin films 3 and 4 were formed by alternately laminating RE (rare earth metal) and TM (transition metal) layers. To prevent the oxidation of the superposed magnetic film 5 consisting of the magnetic thin films 3 and 4, the superposed magnetic film 5 was coated with a protective film 6 having a thickness of 800 angstroms (the lower surface in Fig. 2). The individual films were formed under the same conditions as those for forming the laminated magnetic film 5. The magnetic characteristics of the films and the magnetic domain wall energy density σ_w were evaluated. The materials, film thickness and characteristics at the room temperature of the magnetic thin films 3 and 4 are tabulated in Table 2.

Table 2

	First magnetic thin film	Second magnetic thin film
Material	TbFe	GdTbFeCo
Thickness (\AA)	310	2000
Curie point ($^{\circ}\text{C}$)	135	202
Saturation magnetization (emu/cm^2)	115	134
Coercive force (kOe)	9.2	1.8

In both the first magnetic thin film 3 and the second magnetic thin film 4, the sublattice magnetization of RE is greater than that of TM (RE rich) at the room temperature. The respective magnetic compensation points of the first magnetic thin film 3 and the second magnetic thin film 4 are temperatures around 130°C and 155°C , respectively. The magnetic domain wall energy density σ_w at the room temperature is 1.8 erg/cm^2 .

An external magnetic field of 20 kOe was applied to the thermomagnetic recording medium having the superposed magnetic film 5 thus formed to initialize the superposed magnetic film 5 in the mode A as shown in Fig. 10. Then, the thermomagnetic recording medium was heated to a temperature T with the external magnetic field H_{ex} (Fig. 1) of 2.3 kOe applied thereto, and then the thermomagnetic recording medium was cooled to the room temperature. During the heating and cooling process, the thermomagnetic recording medium was irradiated from the side of the transparent substrate 1 (the glass plate) by a linearly polarized light of 830 nm in wavelength to observe the condition of magnetization by Kerr effect. When the temperature T was 150°C , the mode A of magnetization remained unchanged after heating and cooling. When the temperature T was 200°C , the direction of the magnetization of the second magnetic thin film 3 occurred upon the arrival of the temperature of the thermomagnetic recording medium at 178°C . During the cooling process, the mode B was established when the thermomagnetic recording medium was cooled to 130°C . When the thermomagnetic recording medium was cooled further down to 47°C , the mode of magnetization changed from the mode B to the mode C, which was maintained when the thermomagnetic recording medium was cooled to the room temperature. The mode C remained unchanged when $H_{\text{ex}} = 0$.

The same thermomagnetic recording medium in the mode C at the room temperature was heated and cooled with the external magnetic field H_{ex} of 2.3 kOe applied thereto. When the heating temperature T was 150°C , the mode of magnetization after heating and cooling was Mode A, while the mode of magnetization after heating and cooling was the mode B when the heating temperature T was 200°C .

The present invention is not limited to the foregoing embodiment. For example, the ferrimagnetic thin films of the superposed magnetic film employed in the foregoing embodiment may be substituted by ferromagnetic thin films.

Although the present invention has been described in the preferred embodiment thereof, in which the magnetic coupling energy between the two magnetic thin films is produced by the exchange coupling of the magnetic thin films, the magnetic coupling energy may be produced by the magnetostatic coupling or by the exchange coupling and magnetostatic coupling of the two magnetic thin films.

According to the thermomagnetic recording method of the present invention, the intensity of a heating beam such as, for example, a laser beam, or the duration of irradiation by the heating beam is modulated according to information signals to regulate the heating temperature at which the thermomagnetic recording medium is heated between first and second heating temperatures for the effective recording of information in the thermomagnetic recording medium.

Claims

1. Thermomagnetic recording method using a thermomagnetic recording medium having a superposed layer (5) of magnetically coupled first and second magnetic thin films(3,4),which comprises: heating said layer in a first heating state in which said layer is heated at a temperature T_1 which is higher than Curie temperature T_{C1} of said first magnetic film (3) and will not cause the inversion of magnetic moment of said second magnetic thin film (4) and in a second heating state in which said layer is heated at a temperature T_2 which is higher than the Curie temperature T_{C1} and is high enough to cause the inversion of magnetic moment of said second magnetic thin film(4) said first and second heating states being modulated according to an information signal to be recorded; and forming recording magnetization on the thermomagnetic recording medium by cooling the heated layer of said thermomagnetic recording medium.

2. Thermomagnetic recording method using a thermomagnetic recording medium having a superposed magnetic film (5) of magnetically coupled first and second magnetic thin films (3,4) which comprises: modulating mode of heating said magnetic film between a first heating state in which said magnetic film is heated at a temperature T_1 which is higher than the Curie temperature T_{C1} of the first magnetic thin film (3) and will not cause the inversion of the sublattice magnetization of the second magnetic thin film (4) and a second heating state in which said magnetic film is heated at a temperature T_2 which is higher than the Curie temperature T_{C1} and is high enough to cause the inversion of the sublattice magnetization of said second magnetic thin film (4) having a compensation temperature between the room temperature and the temperature T_2 according to an information signal to be recorded; forming a magnetic record on the thermomagnetic recording medium by cooling the laminated magnetic film from the heating state to make the direction of the sublattice magnetization of said first magnetic thin film the same as the direction of the sublattice magnetization of said second magnetic thin film(4) by the exchange energy of said first and second magnetic thin films; and cooling said magnetic film to the room temperature to invert the sublattice magnetization of said second magnetic thin film.

3. A method of reproducing signals recorded in a thermomagnetic recording medium having a superposed magnetic film(5) formed by magnetically coupled first and second magnetic thin films (3,4) and having a recording part where the respective direction of the respective magnetic moments of said first and second magnetic thin films are opposite to each other and a recording part where the respective directions of the respective magnetic moments of the first and second magnetic thin films are the same, comprising: applying a magnetic field to said magnetic film so that the respective directions of the respective magnetic moments of the first and second magnetic thin films are turned in the same direction prior to reading signals from said magnetic film: and reproducing signals from said laminated magnetic thin film by means of a magnetooptic effect.

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. II

