



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 271 005  
A3**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: **87117905.7**

(51) Int. Cl.4: **G03C 7/26 , G03C 7/34**

(22) Date of filing: **03.12.87**

(30) Priority: **06.12.86 JP 291277/86**  
**29.01.87 JP 20101/87**

(43) Date of publication of application:  
**15.06.88 Bulletin 88/24**

(84) Designated Contracting States:  
**DE FR GB IT NL**

(88) Date of deferred publication of the search report:  
**26.04.89 Bulletin 89/17**

(71) Applicant: **KONICA CORPORATION**  
**No. 26-2, Nishi-Shinjuku 1-chome**  
**Shinjuku-ku**  
**Tokyo 106(JP)**


(72) Inventor: **Sasaki, Masao**  
**Konica Corp. 28 Horinouchi**  
**Odawara-shi Kanagawa-ken(JP)**  
Inventor: **Onodera, Kaoru**  
**Konica Corp. 28 Horinouchi**  
**Odawara-shi Kanagawa-ken(JP)**  
Inventor: **Komorita, Kazuo**  
**Konica Corp. 28 Horinouchi**  
**Odawara-shi Kanagawa-ken(JP)**  
Inventor: **Nakatsugawa, Hiroshi**  
**Konica Corp. 28 Horinouchi**  
**Odawara-shi Kanagawa-ken(JP)**

(74) Representative: **Henkel, Feller, Hänzeli &**  
**Partner**  
**Möhlstrasse 37**  
**D-8000 München 80(DE)**


(54) **Silver halide photographic light-sensitive material excellent in dye-image preservability.**

(57) A silver halide photographic light-sensitive material improved in light fading resistance of cyan dye-images and, particularly, in discoloration resistance in low density area of the images. The photographic material is comprises a support having thereon at least one silver halide emulsion layer and at least one non-light-sensitive layer, and the silver halide emulsion layer contains a cyan-dye forming coupler represented by the following formula [I] or [II] and at least one of the silver halide emulsion layer containing the above cyan-dye forming coupler and the non-light-sensitive layer adjacent to the emulsion layer contains an liquid UV absorbent which is liquid state at an ordinary temperature together with a high boiling organic solvent having the dielectric constant of not more than 0.6 in the ratio by weight of from 0.65 to zero to said UV absorbent contained in said layer.

Formula [I]



Formula [II]



EP 0 271 005 A3



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number

EP 87 11 7905

| DOCUMENTS CONSIDERED TO BE RELEVANT   |   |  |  |
|---|---|--|--|
| Category  | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim                              | CLASSIFICATION OF THE APPLICATION (Int. Cl. 4) |
| P, X<br>L   | EP-A-0 213 700 (KONISHIROKU)<br>* Whole document *<br>-----                   | 1-22   | G 03 C 7/26<br>G 03 C 7/34                     |
|   |   |  | TECHNICAL FIELDS SEARCHED (Int. Cl. 4)         |
|   |   |  | G 03 C 7/00                                    |
| The present search report has been drawn up for all claims  |   |  |  |
| Place of search<br>THE HAGUE  |   | Date of completion of the search<br>13-02-1989 | Examiner<br>MAGRIZOS S.                        |
| <div>CATEGORY OF CITED DOCUMENTS</div> <div><div>X : particularly relevant if taken alone<br/>Y : particularly relevant if combined with another document of the same category<br/>A : technological background<br/>O : non-written disclosure<br/>P : intermediate document</div><div>T : theory or principle underlying the invention<br/>E : earlier patent document, but published on, or after the filing date<br/>D : document cited in the application<br/>L : document cited for other reasons<br/>.....<br/>&amp; : member of the same patent family, corresponding document</div></div> |   |  |  |