

12 **EUROPEAN PATENT APPLICATION**

21 Application number: 89307639.8

22 Date of filing: 27.07.89

51 Int. Cl.4: **C08L 23/28 , C08L 23/02 ,  
C08L 11/00 , //(C08L23/28,  
23:02,11:00),(C08L23/02,23:28,  
11:00),(C08L11/00,23:28,23:02)**

30 Priority: 27.07.88 JP 187578/88

43 Date of publication of application:  
14.02.90 Bulletin 90/07

84 Designated Contracting States:  
**BE DE FR GB IT NL SE**

71 Applicant: **TONEN SEKIYUKAGAKU**  
**KABUSHIKI KAISHA**  
1-1, Tsukiji 4-chome Chuo-ku  
Tokyo 104(JP)

Applicant: **EXXON CHEMICAL JAPAN LTD.**  
TBS Kaikan Bldg Akasaka 5-chome  
Minato-ku  
Tokyo(JP)

72 Inventor: **Sezaki, Eiji**  
8-425, Shimodacho 5-chome Kohoku-ku  
Yokohama-shi Kanagawa-ken(JP)  
Inventor: **Isono, Masatoshi**  
1-3, Chidori-cho Kawasaki-ku  
Kawasaki-shi Kanagawa-ken(JP)  
Inventor: **Akami, Masatoshi**  
Dream Heights 11-406 1403, Matano-cho  
Totsuka-ku  
Yokohama-shi Kanagawa-ken(JP)  
Inventor: **Endo, Hisafumi**  
6-5-501, Kamitsuruma 5-chome  
Sagamihara-shi Kanagawa-ken(JP)

74 Representative: **Dew, Melvyn John et al**  
**Exxon Chemical Limited Exxon Chemical**  
**Technology Centre P.O. Box 1**  
**Abingdon Oxfordshire, OX13 6BB(GB)**

**EP 0 354 685 A1**

54 **Thermoplastic elastomer composition.**

57 A thermoplastic elastomer composition prepared by dynamically vulcanizing a composition comprised (A) polyolefin 5-50 wt. parts, (B) brominated butyl rubber 5-50 wt. parts, (C) polychloroprene rubber 5-50 wt. parts and (D) process oil 10-50 wt. parts in the presence of peroxide is disclosed.

## THERMOPLASTIC ELASTOMER COMPOSITION

The present invention relates to a thermoplastic elastomer composition having good mechanical strength, thermal stability, moldability, oil resistance, and durability.

Thermoplastic elastomers are in general use for automotive parts etc., as an intermediate material of rubber and plastics and also as a replacement for rubber.

5 Heretofore, there have been proposed a variety of thermoplastic elastomers. For example, Japanese Patent Publication No. 34210/1978 discloses a thermoplastic composition composed of a partially crosslinked monoolefin copolymer rubber and a polyolefin resin, with the former being ethylene-propylene copolymer (EPM) or ethylene-propylene-nonconjugated diene terpolymer (EPDM), which is an elastomer, and the latter being polyethylene or polypropylene. The partial crosslinking is accomplished under dynamic  
10 conditions, usually during mastication.

The above-mentioned composition composed of a partially crosslinked monoolefin copolymer rubber and a polyolefin resin has improved tensile characteristics, flexibility, and rebound resilience, but is unsatisfactory in moldability and long-term thermal resistance and stability. To overcome this disadvantage, there was proposed a process for producing a partially crosslinked thermoplastic elastomer composition  
15 which comprises heat-treating dynamically in the presence of an organic peroxide a mixture composed of (a) 90~40 parts by weight of peroxide-crosslinkable olefin copolymer rubber, (b) 10~60 parts by weight of peroxide-decomposable olefin plastics (with the total amount of (a) and (b) being 100 parts by weight), (c) 5~100 parts by weight of peroxide-noncrosslinkable hydrocarbon-based rubbery substance and/or (d) petroleum softener. (See Japanese Patent Publication No. 15741/1981). The typical examples of components (a), (b), and (c) are ethylene-propylene copolymer rubber or ethylene-propylene-nonconjugated diene copolymer rubber, isotactic polypropylene, and polyisobutylene or butyl rubber, respectively.  
20

A disadvantage of this composition is that the ethylene-propylene copolymer rubber or ethylene-propylene-nonconjugated diene copolymer rubber is crosslinked by a peroxide, whereas the polyisobutylene or butyl rubber is not crosslinked but undergoes molecular fission. Therefore, the composition is poor in mechanical strength, moldability, permanent compression set, and heat resistance.  
25

To overcome this disadvantage, there was proposed a thermoplastic elastomer composition which is partially crosslinked with a metal oxide and/or metal chloride in place of an organic peroxide. (See Japanese Patent Laid-open No. 291639/1986). According to this disclosure, the composition is composed of (A) 10~90 parts by weight of crystalline polypropylene, (B) 10~90 parts by weight of halogenated (chlorinated) butyl rubber (with the total amount of (A) and (B) being 100 parts by weight), (C) 10 to 120 parts by weight of olefin copolymer rubber, and (D) 1~90 parts by weight of modified polyolefin.  
30

This composition has a disadvantage of being poor in mechanical strength because only the chlorinated butyl rubber is crosslinked by ZnO or ZnCl<sub>2</sub>. For the composition to have improved mechanical strength, it is necessary that the olefin copolymer rubber (such as EPDM) also be crosslinked. This is accomplished  
35 only by the use of an organic peroxide. Unfortunately, an organic peroxide does not crosslink the chlorinated butyl rubber but causes molecular fission, resulting in a great decrease in mechanical strength, modulus, and moldability.

In view of the foregoing, the present applicant proposed a thermoplastic elastomer composition having superior mechanical strength which is incorporated with brominated butyl rubber in place of chlorinated  
40 butyl rubber and is crosslinked with a peroxide. This composition is based on the finding that unlike chlorinated butyl rubber, brominated butyl rubber can be crosslinked by a peroxide without molecular fission. This composition comprises (A) 10~90 parts by weight of crystalline polypropylene, (B) 10~90 parts by weight of brominated butyl rubber, (C) 10~120 parts by weight of olefin copolymer rubber for 100 parts by weight of the total amount of (A) and (B), and (D) 10~150 parts by weight of petroleum softener for 100  
45 parts by weight of the total amount of (A) and (B), said composition being crosslinked by a peroxide crosslinking agent. (See Japanese Patent Application No. 085530/1987).

It is known that a blend of thermoplastic olefin resin and two rubber components (especially halogenated butyl rubber and polychloroprene) provides a thermoplastic olefin polymer composition having good physical strength, processability, flowability, and oil resistance, and low permanent compression set. For  
50 example, Japanese Patent Laid-open No. 148246/1986 discloses thermoplastic elastomer composition which comprises (A) a polyolefin resin, (B) halogenated (chlorinated or brominated) butyl rubber, and (C) polychloroprene rubber, said composition being partially crosslinked with a metal oxide (ZnO).

The above-mentioned thermoplastic elastomer composition which is partially crosslinked with a metal oxide (ZnO) is superior in oil resistance but is liable to degradation due to moisture absorption, because ZnO is deliquescent.

There is thus a desideratum to provide a thermoplastic elastomer composition which has improved mechanical strength, elasticity, moldability, long term thermal stability, gas impermeability, damping properties, oil resistance, and durability.

The thermoplastic elastomer composition of the present invention generally has the above-mentioned improved properties because it contains chloroprene rubber and is crosslinked with a peroxide.

Thus it has now been found that a thermoplastic elastomer composition has superior oil resistance and durability when it contains brominated butyl rubber (which is compatible with a polyolefin and can be crosslinked by a peroxide without molecular fission) and chloroprene rubber (which has superior oil resistance and durability) and is crosslinked with a peroxide.

According to the present invention there is provided a thermoplastic elastomer composition which comprises (A) 5 to 50 parts by weight of polyolefin, (B) 5 to 50 parts by weight of brominated butyl rubber, (C) 5 to 50 parts by weight of chloroprene rubber, and (D) 10 to 50 parts by weight of petroleum softener, said composition being formed by crosslinking in the presence of a peroxide crosslinking agent.

The thermoplastic elastomer composition of the present invention is composed of the components which are explained by the following embodiments.

#### (A) Polyolefin

The polyolefin (component A) is a homopolymer or copolymer of  $\alpha$ -olefins such as ethylene, propylene, 1-butene, 1-hexene, and 4-methyl-1-pentene. It is preferably crystalline polypropylene. The term "crystalline polypropylene" as used in this specification denotes both the homopolymer of propylene and the copolymer of propylene and the above-mentioned  $\alpha$ -olefins. It preferably has a melt flow rate (MFR for short hereinafter) of 0.3 to 60 g/10 min, more preferably 1 to 40 g/10 min, and most preferably 3 to 30 g/10 min. The copolymer preferably contains more than 60 wt% of propylene. Crystalline polypropylene has the highest melting point among polyolefins. It contributes to the improvement of heat resistance and mechanical strength.

The above-mentioned polyolefins may be used alone or in combination with one another as component A. The content of component A should be 5 to 50 parts by weight, preferably 5 to 40 parts by weight.

#### (B) Brominated butyl rubber

The brominated butyl rubber (component B) is brominated isobutylene-isoprene copolymer rubber. It preferably contains more than 0.5 wt% of bromine, more preferably 0.5 to 8 wt%, and most desirably 0.5 to 4.0 wt%. With a bromine content less than 0.5 wt%, it may not be completely crosslinked due to molecular fission. In addition, it should preferably have a Mooney viscosity of  $ML_{1+8}$  (100 °C) of 30 to 100 and preferably a degree of unsaturation of 0.5 to 4.0 mol%.

It has been found that brominated butyl rubber differs markedly from chlorinated butyl rubber in crosslinking properties although they are both halogenated butyl rubber. That is, the latter cannot be crosslinked by a peroxide on account of molecular fission, whereas the former forms crosslinked rubber which disperses into the composition, imparting heat resistance, damping properties, and gas impermeability to the composition, and also plays a role of binder at the interface between the polyolefin phase and the chloroprene phase. In other words, the brominated butyl rubber makes chloroprene rubber miscible with the polyolefin. The content of component B should be 5 to 50 parts by weight. With a content less than 5 parts by weight, component B does not fully exhibit the above-mentioned characteristics. With a content in excess of 50 parts by weight, component B has an adverse effect on flowability and hence on moldability. A preferred content of component B is from 5 to 40 parts by weight.

#### (C) Chloroprene rubber

The chloroprene rubber (component C) contributes to the improvement of flexibility and oil resistance of the composition owing to its inherently superior oil resistance. It preferably has a Mooney viscosity  $ML_{1+4}$  (100 °C) of 20 to 120. The content of component C should be 5 to 50 parts by weight. With a content less than 5 parts by weight, component C does not impart sufficient oil resistance. With a content more than 50 parts by weight, component C has an adverse effect on the flowability and hence on moldability. A preferred content of component C is from 5 to 40 parts by weight.

## (D) Petroleum softener

The petroleum softener is a high-boiling petroleum fraction. It is used to lower the intermolecular force of rubber when rubber is processed by rolling, thereby facilitating processing and helping the dispersion of carbon black or white carbon. It is also used to lower the hardness of vulcanized rubber, thereby increasing its flexibility and resilience and improving its moldability. It is classified as of paraffin type, naphthene type, and aromatic type and may otherwise be termed a process oil. The content of the petroleum softener should be 10 to 50 parts by weight. With a content less than 10 parts by weight, it does not fully produce its effect; and with a content in excess of 50 parts by weight, it lowers the heat resistance and mechanical strength of the composition and also oozes out, impairing the appearance of the composition. A preferred content of the petroleum softener is from 15 to 40 parts by weight.

## (E) Crosslinking agent

The crosslinking agent used in the present invention is a peroxide, including, for example, hydroperoxides, dialkyl peroxides, diacyl peroxides, ketal peroxides, ketone peroxides, carbonate peroxides, and ester peroxides. Specific examples of the peroxide include dicumyl peroxide, di-tert-butyl peroxide, 2,5-dimethyl-2,5-di-(tert-butylperoxy)hexane, 2,5-dimethyl-2,5-di-(tert-butylperoxy)hexyne-3, 1,3-bis(tert-butylperoxyisopropyl)benzene, 1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane, n-butyl-4,4-bis(tert-butylperoxy)valerate, benzoyl peroxide, p-chlorobenzoyl peroxide, 2,4-dichlorobenzoyl peroxide, tert-butyl peroxybenzoate, tert-butyl peroxyisopropylcarbonate, diacetyl peroxide, lauroyl peroxide, and tert-butylcumyl peroxide.

In the case of a conventional composition which contains brominated butyl rubber (which is a halogenated butyl rubber) but does not contain olefin copolymer rubber, crosslinking is generally accomplished with the aid of ZnO. This is because ZnO crosslinks halogenated butyl rubber but does not crosslink olefin copolymer rubber, and a peroxide crosslinks olefin copolymer rubber but does not crosslink a halogenated butyl rubber (due to molecular fission).

A disadvantage of ZnO is that it combines with Cl to form ZnCl<sub>2</sub> which remains in the composition, causing the degradation of the composition. In other words, ZnCl<sub>2</sub> increases the moisture absorption and lowers the durability of the resulting composition because of its high deliquescence. This disadvantage is eliminated in the present invention by employing brominated butyl rubber (as a halogenated butyl rubber) which is crosslinked by a peroxide without molecular fission, and also by employing a peroxide in place of ZnO. As a result, the present invention provides a pure composition having superior characteristic properties.

For sufficient crosslinking of the brominated butyl rubber, the peroxide is preferably used in an amount of 0.05 parts by weight or more for 100 parts by weight of the total amount of components A, B, C, and D. The upper limit is preferably 10 parts by weight, because excess peroxide brings about excessive crosslinking to decrease the flowability of the resulting composition. A preferred amount ranges from 0.1 to 5 parts by weight.

The crosslinking agent used in the present invention may be used in combination with one or more than one kind of crosslinking auxiliary. Examples of the crosslinking auxiliary include sulfur (as simple substance), organic and inorganic sulfur compounds, alkylphenol resin, formaldehyde resin, heat-reactive phenolic resin, triallyl cyanurate (TAC), triallyl isocyanurate (TAIC), ethylene glycol methacrylate (EDMA), trimethylol propane trimethacrylate (TMPT), and p-quinonedioxime (GMF). The crosslinking auxiliary is preferably used in an amount of 0.05 to 10 parts by weight, more preferably 0.1 to 5 parts by weight for 100 parts by weight of the total amount of component A, B, C, and D.

## (F) Unsaturated carboxylic acid-modified polyolefin

The optional unsaturated carboxylic acid-modified polyolefin (component F) is a polyolefin modified with an unsaturated carboxylic acid or anhydride thereof. Examples of the unsaturated carboxylic acid or anhydride thereof include monocarboxylic acids (such as acrylic acid and methacrylic acid), dicarboxylic acids (such as maleic acid, fumaric acid, and itaconic acid), and dicarboxylic anhydrides (such as maleic anhydride and itaconic anhydride). Preferable among them are dicarboxylic acids and anhydrides thereof.

The polyolefin to be modified with the unsaturated carboxylic acid or anhydride thereof includes homopolymers and copolymers of  $\alpha$ -olefins as in the case of component A mentioned above.

The content of the unsaturated carboxylic acid or anhydride thereof is preferably 0.1 to 10 wt% of the

modified polyolefin (100 wt%). With a content less than 0.1 wt%, the resulting modified polyolefin does not generally sufficiently improve the compatibility of the polyolefin and brominated butyl rubber. With a content in excess of 10 wt%, the resulting modified polyolefin does not generally produce any additional effect but is wasted.

5 The composition of the present invention is preferably incorporated with component F (when present) in an amount of 2 to 40 parts by weight, more preferably 2 to 20 parts by weight for 100 parts by weight of the total amount of components A, B, C, and D. With an amount less than 2 parts by weight, component F does not generally improve the mechanical strength of the resulting composition; and with an amount in excess of 40 parts by weight, component F does not generally produce any additional effect but is wasted.

10

#### Other components

15 The thermoplastic elastomer composition of the present invention may be incorporated with stabilizers (such as antioxidant, UV light absorber, and metal poison inhibitor), additives (such as slip agent, antistatic agent, electric properties improver, flame retardant, processability improver, and pigment), and inorganic fillers (such as talc, calcium sulfate, barium sulfate, mica, and calcium silicate), according to need.

20 The thermoplastic elastomer composition of the present invention can be produced by mixing the above-mentioned components and melting and kneading the resulting mixture for dynamic thermal treatment. The kneading may be accomplished by the use of open-type apparatus (such as mixing roll) or closed-type apparatus (such as Banbury mixer, single- or twin-screw extruder, kneader, and continuous mixer), which are known well. Preferable among them are closed-type apparatus. It is desirable to perform kneading under an environment of inert gas such as nitrogen or carbon dioxide gas. The kneading is preferably carried out for 1 to 10 minutes, preferably 2 to 5 minutes, at a temperature (usually 130 to 250 °C, preferably 160 to 250 °C) at which the half-life period of the organic peroxide to be used is 1 25 minute. It is desirable to mix the components for 1 to 10 minutes, add the crosslinking agent and other additives, and knead the resulting mixture for 1 to 10 minutes.

30 The thermoplastic elastomer composition obtained as mentioned above can be molded into any desired shapes by any apparatus commonly used for thermoplastic resins. It is suitable for extrusion molding and calendaring, and especially for injection molding.

#### Examples

35 The invention will be described in more detail with reference to the following examples.

#### Examples 1 to 12

40 The thermoplastic elastomer composition was prepared from the following components according to the formulation shown in Table 1.

Component A: Polypropylene ("Y201" having an MFR of 1 g/10 min, made by Tonen Sekiyukagaku K.K.), referred to as "PP" hereinafter, or propylene-ethylene block copolymer ("BJ3I5" made by Tonen Sekiyukagaku K.K.), referred to as "PP-block" hereinafter.

45 Component B: Brominated butyl rubber ("Bromobutyl 2244" having a Mooney viscosity of  $ML_{1+8}$  - (125 °C) of 47, a bromine content of 2 wt%, and a degree of unsaturation of 2 mol%, made by Exxon Chemical), referred to as "BrIR" hereinafter.

Component C: Chloroprene rubber ("Denka Chloroprene M30" having a Mooney viscosity  $ML_{1+4}$  - (100 °C) of 38, made by Denki Kagaku Kogyo K.K.), referred to as "CR" hereinafter.

50 Component D: Naphthene-type process oil softener ("Sunsen 4240" made by Sun Oil Co. in the U.S.), referred to as "softener" hereinafter.

Crosslinking agent: 2,5-dimethyl-2,5-di(t-butylperoxy)hexane ("Perhexa 25B", made by Nippon Oils and Fats Co., Ltd.), referred to as "peroxide" hereinafter.

55 Crosslinking auxiliary: Trimethylolpropane trimethacrylate ("NK ester TMPT", made by Shin-Nakamura Kagaku K.K.) referred to as "TMPT", hereinafter.

Component F: Unsaturated carboxylic acid-modified propylene-ethylene block copolymer ("CMPC-800X" containing 0.3 wt% of acid added, made by Tonen Sekiyukagaku K.K.), referred to as "modified PP" hereinafter.

The formulation shown in Table 1 is expressed in terms of parts by weight. The total quantity of PP (or PP block), BrIIR, CR, and softener is 100 parts by weight. The quantities of peroxide, TMPT, and modified PP are based on the total quantity of PP (or PP block) BrIIR, CR, and softener which is 100 parts by weight.

At first, the above-mentioned components, excluding peroxide and TMPT, were preliminarily mixed by melting at 165 °C for 1 to 5 minutes in a Banbury mixer. Then, the peroxide and TMPT were added, and mixing was continued at 175 °C for 2 to 10 minutes. The resulting mixture was made into a sheet by injection molding and the sheet was cut into pellets. The pellets were made into test pieces for the measurement of the following properties.

(1) MFR: JIS K7210, 10-kg load, 230 °C.

(2) Tensile strength and elongation at break: JIS K6301, No. 3 dumbbell, at a pulling rate of 500 mm/min.

(3) Spring hardness: JIS K6301, type A.

(4) Permanent compression set: JIS K6301, at 70 °C, for 22 hours, 25% compression.

(5) Tear strength: JIS K6301, type B, at a pulling of 500 mm/min.

(6) Oil resistance: JIS K6301, JIS No. 3 oil, at 100 °C for 70 hours.

(7) Moisture absorption: volatile matter which vaporizes at 110 °C for 24 hours.

#### Comparative Example 1

The same procedure as in Example 1 was repeated except that component B was not used and component C (CR) was replaced by ethylene-propylene rubber (EPR). The test pieces were examined in the same manner as in Example 1. The results are shown in Table 1.

#### Comparative Example 2

The same procedure as in Example 1 was repeated except that the crosslinking agent (peroxide) was replaced by ZnO and the crosslinking auxiliary (TMPT) was replaced by "Permalax" (dicatchol borate of di-o-triguanidine, made by Dupont). The test pieces were examined in the same manner as in Example 1. The results are shown in Table 1.

Table 1

Example(Compar.Example)	1	2	3	4	5	6	7	8	9	10	11	12	(1)	(2)
Formulation														
PP	21	21	10	40	21	-	21	21	10	40	21	-	20	21
PP block	-	-	-	-	-	21	-	-	-	-	-	21	-	-
BrilR	21	10	25	20	16	21	21	10	25	20	16	21	-	21
CR	21	32	25	20	26	21	21	32	25	20	26	21	-	21
Softener	37	37	40	20	37	37	37	37	40	20	37	37	20	37
Modified PP	-	-	-	-	-	-	3	3	3	3	10	20	-	-
EPR	-	-	-	-	-	-	-	-	-	-	-	-	60	-
Peroxide	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	-
TMPT	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	-
ZnO	-	-	-	-	-	-	-	-	-	-	-	-	-	4
Permalax	-	-	-	-	-	-	-	-	-	-	-	-	-	2
Physical properties														
MFR (g/10 min)	10	15	7	20	10	10	10	15	7	20	20	30	20	10
Tensile strength at break (kg/cm <sup>2</sup> )	80	75	65	120	85	80	95	90	80	135	110	130	70	74
Tensile elongation at break (%)	250	250	200	300	230	250	300	300	250	350	350	400	300	200
Spring hardness	73	72	60	95	72	72	73	72	60	95	85	95	72	72
Permanent compression set (%)	35	37	30	45	35	35	35	37	30	45	40	45	40	38
Tear strength (kg/cm <sup>2</sup> )	30	32	35	50	33	30	40	42	35	55	45	50	30	30
Oil resistance (%)	40	30	40	20	35	42	40	30	40	20	30	25	150	40
Moisture absorption (%)	0.1	0.1	0.1	0.05	0.1	0.1	0.1	0.1	0.1	0.05	0.1	0.05	0.1	2.0

It is noted from Table 1 that the thermoplastic elastomer composition of the present invention, which contains brominated butyl rubber and chloroprene rubber and is crosslinked with a peroxide, is superior in oil resistance, moldability, mechanical strength, and durability (with very little moisture absorption).

5     Containing brominated butyl rubber that is crosslinked with a peroxide, and chloroprene rubber, the thermoplastic elastomer composition of the present invention has good flexibility, high mechanical strength, high rubber elasticity (small permanent compression set), good long-term durability, good moldability, and superior oil resistance.

10     Because of good flexibility, strength, durability, and moldability, the thermoplastic elastomer composition can be easily made into automotive parts (such as rack and pinion boot, cable outer coating, spoiler, side protector, and bumper) by injection molding, blow molding, or extrusion molding.

### Claims

15

1) A thermoplastic elastomer composition which comprises (A) 5 to 50 parts by weight of polyolefin, (B) 5 to 50 parts by weight of brominated butyl rubber, (C) 5 to 50 parts by weight of chloroprene rubber, and (D) 10 to 50 parts by weight of petroleum softener, said composition being formed by crosslinking in the presence of a peroxide crosslinking agent.

20

2) A thermoplastic elastomer composition according to Claim 1, wherein the brominated butyl rubber is one which contains 0.5 wt% or more of bromine.

3) A thermoplastic elastomer composition according to Claim 1 or 2, which further comprises (F) 2 to 40 parts by weight of an unsaturated carboxylic acid-modified polyolefin for 100 parts by weight of the total amount of components (A), (B), (C), and (D).

25

4) A thermoplastic elastomer composition according to Claim 3, wherein the unsaturated carboxylic acid-modified polyolefin comprises from 0.1 to 10 wt% of acid or anhydride modifier, preferably a dicarboxylic acid or anhydride.

30

5) A thermoplastic elastomer composition according to any of the preceding claims which comprises from 5 to 40 parts by weight of (A) and/or (B) and/or (C) and/or (optionally) (F) (as defined in Claim 3) and/or from 15 to 40 parts by weight of (D).

6) A thermoplastic elastomer composition according to any of the preceding claims crosslinked with from 0.1 to 5.0 parts by weight of peroxide per 100 parts by weight of the total of (A), (B), (C) and (D).

7) A thermoplastic elastomer composition according to any of the preceding claims wherein the polyolefin component (A) is crystalline polypropylene.

35

8) A thermoplastic elastomer composition according to any of claims 2 to 7 wherein component (B) contains 0.5 to 4 wt% bromine.

9) The use of a composition according to any preceding claim in molding applications.

40

45

50

55



DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
Y	EP-A-0 190 497 (EXXON) * Claims 1,2,10,24 * & JP-A-61 148 246 (Cat. D) ---	1-9	C 08 L 23/28 C 08 L 23/02 C 08 L 11/00 //
Y	GB-A-2 011 430 (UNIROYAL) * Claims 1,8-10,27-28 * ---	1-9	(C 08 L 23/28 C 08 L 23:02 C 08 L 11:00 )
A	WO-A-8 607 600 (EXXON) * Claims 1,6-7 * & JP-A-61 291 639 (Cat. D) ---	3-4	(C 08 L 23/02 C 08 L 23:28 C 08 L 11:00 )
A	FR-A-2 324 679 (POLYSAR) * Claims 1,4 * -----	1	(C 08 L 11/00 C 08 L 23:28 C 08 L 23:02 )
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C 08 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 08-11-1989	Examiner VAN HUMBEECK F.W.C.
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			