



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 413 352 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **90115803.0**

(51) Int. Cl.⁵: **C09D 157/04**

(22) Date of filing: **17.08.90**

(30) Priority: **17.08.89 JP 213226/89**

(43) Date of publication of application:
20.02.91 Bulletin 91/08

(84) Designated Contracting States:
DE FR GB

(71) Applicant: **Nippon Paint Co., Ltd.**
2-1-2, Oyodokita Oyodo-ku
Osaka-shi Osaka-fu(JP)

(72) Inventor: **Urano, satoshi**
2-6-14, Kasumisaka., Tanabe-cho
Tsuzukigun, Kyoto(JP)
Inventor: **Tsubonwa, Noriyuki**
2-26-21, Arakawa, Higashiosaka-shi
Osaka(JP)
Inventor: **Aoki, Krei**
1-16-7, Shikanosainishi
Ikoma-shi, Nara(JP)
Inventor: **Umemoto, Hirotooshi**
138-97, Oneo, Hirono-cho
Uji-shi, Kyoto(JP)

(74) Representative: **Hansen, Bernd, Dr.**
Dipl.-Chem. et al
Hoffmann, Eitle & Partner Patent- und
Rechtsanwälte Arabellastrasse 4
D-8000 München 81(DE)

(54) **Solvent based coating composition.**

(57) Disclosed is a solvent based coating composition comprising at least one kind of vinyl polymer and an organic solvent, wherein any one of said vinyl polymer has at least one kind selected from the group consisting of an active hydrogen-containing group and a substituted acylamide group, and said vinyl polymer contains the above described two kinds of group as a whole.

EP 0 413 352 A2


SOLVENT BASED COATING COMPOSITION

FIELD OF THE INVENTION

The present invention relates to a solvent based coating composition, in particular to a one-pack coating composition which is stable at ambient temperature.

BACKGROUND OF THE INVENTION

A compound having a reactive substituted acylamide group and a polymerizable carbon-carbon double bond, i.e. a substituted acylamide compound represented by the following formula (1), is known to the art, as a compound which achieves crosslinking reaction (Japanese Kokai Specification No. 275259/1986);



wherein R represents a hydrogen atom or a lower alkyl group, and X represents an alkoxy group, an amino group, an amide group, an iminoxy group or a sulfide group, which may be substituted with other groups.

Polymers which contain both an active hydrogen and a substituted acylamide group, prepared by polymerizing the above described substituted acylamide compounds with active hydrogen-containing ethylenic unsaturated compounds, have also been proposed in Japanese Kokai Specification No. 46207/1988. In addition, there has been proposed a water dispersible resin which is obtained by polymerizing the above described substituted acylamide compounds with acidic group- or basic group-containing ethylenic unsaturated compounds (see Japanese Kokai Specification No. 46203/1988).

Further studies have been conducted on applications of the polymer prepared from the substituted acylamide compounds to paint.

SUMMARY OF THE INVENTION

The present invention provides a solvent based coating composition comprising at least one kind of vinyl polymer and an organic solvent, wherein any one of said vinyl polymers has at least one kind selected from the group consisting of an active hydrogen-containing group and a substituted acylamide group, and said vinyl polymer contains the above described two kinds of group as a whole.

DETAILED DESCRIPTION OF THE INVENTION

According to the present invention, it is essential that a substituted acylamide group and an active hydrogen-containing group are present in the resinous components of the coating compositions. Accordingly, the above described two kinds of the functional groups may be contained in one resin. In addition, the above described two kinds of the functional groups may be contained in different resins, that is two kinds of resins. Further, the one functional group, for example the substituted acylamide group may be contained in two kinds of the resins.

The active hydrogen-containing group of the present invention includes a carboxyl group, a hydroxyl group, an amino group, a thiol group, a sulfonic acid group and the like.

The vinyl polymers used for the coating composition according to the present invention can be synthesized by polymerizing the substituted acylamide compounds (1) through carbon-carbon double bonds.

Monomers used for the synthesis include active hydrogen group-containing ethylenic unsaturated

compounds and, if necessary, ethylenic unsaturated compounds without such functional groups. These monomeric compounds are suitably combined to form the polymers. The polymerization conditions of these monomeric compounds can be greatly varied in accordance with monomers used in the polymerization, a polymerization degree and the like.

5 The active hydrogen-containing ethylenic unsaturated compounds include unsaturated acids (for example, acrylic acid, methacrylic acid, crotonic acid, cinnamic acid, 2-isopropylacrylic acid, trans-2-decenoic acid, cis-2-decenoic acid, α -chloroacrylic acid, β -trans-nitroacrylic acid, isocrotonic acid, 2-pentenic acid, 2-ethylacrylic acid, tiglic acid, 3,3-dimethylacrylic acid, propylacrylic acid, itaconic acid, 2-methyl-3-ethylacrylic acid, 2-ethylcrotonic acid, maleic acid, trimethylacrylic acid, butylacrylic acid, 2-methyl-2-
10 hexenoic acid, 3-methyl-3-propylacrylic acid, 2,3-diethylacrylic acid, 4-methyl-2-hexenoic acid, 3,3-diethylacrylic acid, 3-tert-butylacrylic acid, 2,3-dimethyl-3-ethylacrylic acid, 3-methyl-isopropylacrylic acid, 2-octenoic acid, 2-pentylacrylic acid, 2-butylcrotonic acid, 2-nonenoic acid, 2-hexylacrylic acid and 4-ethyl-2-octenoic acid), unsaturated alcohols (for example, monoesters of the above described unsaturated acids and glycols (such as, ethylene glycol and propylene glycol), crotonic alcohol, cinnamyl alcohol and o-
15 hydroxystyrene), unsaturated amides (for example, acrylamide, methacrylamide, crotonamide, cinnamamide, p-benzamidestyrene, methylacrylamide, glycolate-methyl ether and methacrylamide propanesulfonic acid), unsaturated sulfonic acids or salts thereof (for example, 2-sulfoethyl acrylate, 2-sulfoethyl methacrylate, t-butylacrylamidesulfonic acid, 4-sulfophenyl acrylate and p-vinylbenzenesulfonic acid), unsaturated phosphoric acids (for example, acidphosphoxyethyl methacrylate, 3-chloro-2-amidephosphoxypropyl methacrylate, acidphosphoxypropyl methacrylate, vinylphosphate and isopropenyl phosphate) and
20 the like. These may be used singly or in combination.

The vinyl polymers of the present invention are polymerized from the above described two kinds of monomer, but other monomers without the above described functional groups may be used, if necessary. The other monomers include monoolefines and diolefines (for example, styrene, α -methylstyrene, α -ethylstyrene, isobutylene, 2-methylbutene-1, 2-methylpentene-1, 2,3-dimethylbutene-1, 2,3-dimethylpentene-1, 2,4-dimethylpentene-1, 2,3,3-trimethylheptene-1, 2,3-dimethylhexene-1, 2,4-dimethylhexene-1, 2,5-dimethylhexene-1, 2-methyl-3-ethylpentene-1, 2,3,3-trimethylpentene-1, 2,3,4-trimethylpentene-1, 2,3,4-trimethylpentene-1, 2-methyloctene-1, 2,6-dimethylheptene-1, 2,6-dimethyloctene-1, 2,3-dimethyldecene-1, 2-methylnonadecene-1, ethylene, propylene, butylene, amylene, hexylene, butadiene-1,3 and isoprene),
30 halogenated monoolefines and diolefines (for example, α -chlorostyrene, α -bromostyrene, 2,5-dichlorostyrene, 2,5-dibromostyrene, 3,4-dichlorostyrene, ortho-, meta- and para-fluorostyrene, 2,6-dichlorostyrene, 3-fluoro-4-chlorostyrene, 3-chloro-4-fluorostyrene, 2,4,5-trichlorostyrene, dichloromonofluorostyrene, 2-chloropropene, 2,6-difluorostyrene, 2-chlorobutene, 2-chloropentene, 2-chlorohexene, 2-bromobutene, 2-bromoheptene, 2-fluorohexene, 2-fluorobutene, 2-iodopropene, 2-iodopentene, 4-bromoheptene, 4-chloroheptene, 4-fluoroheptene, cis- and trans-1,2-dichloroethylene, 1,2-dibromoethylene, 1,2-difluoroethylene, 1,2-diiodoethylene, chloroethylene(vinyl chloride), 1,1-dichloroethylene(vinylidene chloride), bromoethylene, fluoroethylene, iodoethylene, 1,1-dibromoethylene, 1,1-difluoroethylene, 1,1-diiodoethylene, 1,1,2-trifluoroethylene and chlorobutadiene), esters of organic and inorganic acids (for example, vinyl acetate, vinyl propionate, vinyl butyrate, vinyl isobutyrate, vinyl caproate, vinyl enanthate, vinyl benzoate, vinyl toluate, vinyl-p-chlorobenzoate, vinyl-o-chlorobenzoate, vinyl-p-methoxybenzoate, vinyl-p-ethoxybenzoate, methyl methacrylate, ethyl methacrylate, propyl methacrylate, butyl methacrylate, amyl methacrylate, hexyl methacrylate, heptyl methacrylate, octyl methacrylate, decyl methacrylate, methyl crotonate, ethyl tiglate, methyl acrylate, ethyl acrylate, propyl acrylate, isopropyl acrylate, butyl acrylate, isobutyl acrylate, amyl acrylate, hexyl acrylate, 2-ethylhexyl acrylate, heptyl acrylate, octyl acrylate, allyl
45 chloride, allyl cyanide, allyl bromide, allyl fluoride, allyl iodide, allyl chloride carbonate, allyl nitrate, allyl thiocyanate, allyl acetate, acetate propionate, allyl butyrate, allyl valerate, allyl caproate, decyl- α -chloroacrylate, methyl- α -cyanoacrylate, ethyl- α -cyanoacrylate, amyl- α -cyanoacrylate, decyl- α -cyanoacrylate, dimethyl maleate, diethyl maleate, diallyl maleate, dimethyl fumarate, diethyl fumarate, and diethyl glutaconate), organic nitriles (for example, acrylonitrile, methacrylonitrile, ethacrylonitrile, 3-octenenitrile, crotonitrile and oleonitrile) and the like.
50

The above described monomer compounds are subjected to polymerization, for example radical polymerization, in a solvent which is inert to the polymerization reaction. In the case of the radical polymerization, the usual radical initiators are used. The radical initiators include azobisisobutyronitrile, benzoyl peroxide, cumene hydroperoxide, tetramethylthiuram disulfide, 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile), acetylcyclohexylsulfonyl peroxide, 2,2'-azobis(2,4-dimethylvaleronitrile) and the like. The initiators are generally used in a quantity of 0.1 to 10 % by weight based on the total of the monomers. The polymerization temperature is usually 20 to 200 °C, preferably 80 to 150 °C.

The solvent employed in the polymerization reaction is inert to the polymerization reaction, but includes

hydrocarbons, ethers, ketones, esters, alcohols, amides, sulfoxides and the like. The solvent may be substituted with a group which is inert to the polymerization reaction. The substituted acylamide compounds (I) and the solvent for polymerization are explained in Japanese Kokai Specification Nos. 2752591/1986 and 46207/1988.

5 In the polymerization, other additives, for example polymerization regulator and the like, may be added in case of need.

It is desirable that the equivalence of the substituted acylamide group in the resin components used in the present invention is 1×10^{-5} or more, preferably within the range of 1×10^{-4} to 50×10^{-4} . The equivalence of the substituted acylamide group is expressed by the equivalence of the substituted
10 acylamide group based on 1 g of all resin components. In the event that the equivalence of the substituted acylamide group is less than 1×10^{-5} , the paint can not be sufficiently cured. It is desirable that the equivalence of the active hydrogen (expressed by the equivalence of the active hydrogen existing in all resin components of 1 g in the same manner as the above described equivalence of the substituted acylamide group) is 1×10^{-5} or more, preferably within the range of 5.0×10^{-4} to 50×10^{-4} . If the
15 equivalence of the active hydrogen is less than 1×10^{-5} , the paint can not be sufficiently cured when baked. Number of the substituted acylamide groups in one molecule of the polymer is not limited, but preferably at least 6, more preferably at least 8. At least 6 substituted acylamide groups enhance curing ability at a low temperature and physical properties of cured coatings.


The preparation of the above described vinyl polymer, i.e. the limitation of the equivalences of the
20 respective functional groups, has been known to the person skilled in the art and can be achieved by selecting the polymerization conditions, the modification conditions and other conditions. The number average molecular weight of the vinyl polymer is a molecular weight which has been usually used for the paints and it is desirable that the number average molecular weight of the resins is for example 1,000 to 100,000, preferably 1,000 to 50,000. If the number average molecular weight is out of the range, the cured
25 film is poor in coating properties.

The coating composition according to the present invention can be used as a clear paint as it is. In addition, the anti-sagging agents, the shedding-preventing agents, the surface tension-regulating agents, the antioxidants, the photostabilizers, the ultraviolet absorbers, the setting preventing agents and the like may be added in accordance with the usual art of producing paints.

30 The solvent based coating composition of the present invention is formed by dispersing the above mentioned components in an organic solvent other than water. Examples of the organic solvents are hydrocarbons, ketones, ethers, esters, alcohols, amides (e.g. dimethylformamide), sulfoxides (e.g. dimethylsulfoxide), nitriles (e.g. acetonitrile) and the like. The organic solvent preferably has a solubility parameter of 8.0 to 20.0, more preferably 8.2 to 18.0. Solubility parameters of less than 8.0 give rise to precipitation of
35 solid components. The organic solvent may be present in the coating composition in an amount of 1 to 1,000 parts by weight based on the amount of the solid ingredients.

The coating composition according to the present invention may be used for various kinds of use, for example the final coating, the intermediate coating, the undercoating and the like, and used as various kinds of paint, for example paints for automobiles, paints for household electric utensiles and industrial paints.

40 In the curing reaction of the substituted acylamide compound, the substituted acylamide group is attacked by the active hydrogen containing compound, e.g. the hydroxyl group containing compound, and cured with the active hydrogen containing compound by means of a nucleophilic substitution reaction, as shown in the following reaction equation;



[wherein R' and R'' represent alkyl groups and X represents the same as mentioned in the formula (1).]

As above described, the coating composition according to the present invention has the substituted

acylamide group which is reacted with the active hydrogen atom by heating to form a cured film. The substituted acylamide group is stable at ambient temperature, so that the coating composition containing the same can be used as the one pack coating composition. The coating composition of the present invention shows advantages in that the curing degree is constant within a certain temperature range, for example a range of 80 to 140 °C, and thus the curing conditions can be very easily selected.

EXAMPLE

The present invention is illustrated by the following Examples which, however, are not to be construed as limiting the present invention to their details.

Preparation of vinyl polymer A

To 400 g of butyl acetate was added 316 g of methyl methacrylate, 116 g of n-butyl acrylate and 82.5 g of N-(t-butoxycarbonyl)methacrylamide to dissolve at 120 °C, to which a mixture of 10 g of azobisisobutyronitrile and 100 g of butyl acetate was added dropwise with stirring in nitrogen atmosphere. It was then aged for 2 hours to obtain a polymer A having a nonvolatile content of 46.9 % by weight and a number average molecular weight of 10,000.

Synthesis of B-G

A polymer was synthesized from the monomers and solvents shown in Table-1 in the same manner as the vinyl polymer A. The number average molecular weight and nonvolatile content are shown in Table 1.

Table 1

5			Vinyl polymer							
			A	B	C	D	E	F	G	
10	Monomer	M ₁ ¹⁾	82.5	113.9			130	.		
		M ₂ ²⁾			200					
		M ₃ ³⁾				200				
		Styrene			100	150	150		70	150
		Methyl methacrylate	316	67.5			425.5	150		
		n-Butyl acrylate	116			210	237.5		145	
		Ethyl acrylate		63.0						
		2-Ethylhexyl acrylate		154.0	300	300	90	87.0		23.7
		Methacrylic acid		43.6						
		2-Hydroxyethyl methacrylate								
25	Solvent		Butyl acetate	t-Butanol	Butyl acetate	Butyl acetate	t-Butanol	Butyl acetate	Butyl acetate	
	Sp		8.47	10.82						
	Nonvolatile content (%)			46.9	39.3	45.0	45.0	25.0	60.6	50.0
30	Number average molecular weight		10,000	8,000	5,000	10,000	11,000	9,800	8,000	

¹⁾ N-(t-butoxycarbonyl)methacrylamide

2) N-(ϵ -caprolactamcarbonyl)methacrylamide

³⁾ N-(2,6-di-*t*-butyl-*p*-methoxyphenoxy carbonyl) methacrylamide

40 Examples 1 to 6

(Synthesis of pigment pastes)

45 The vinyl polymer (c) and the pigment (d) were preliminary mixed with xylol or without any solvent, and then ground with glass beads at room temperature for 40 minutes in a paint conditioner to form a pigment paste.

50 (Preparation of coating compositions)

One vinyl polymer, another vinyl polymer and the pigment paste were mixed with stirring at room temperature to obtain a coating composition.

55 (Baking process)

The respective coating compositions according to Examples 1 to 6 were diluted with the solvent used in

the polymerization to regulate the viscosity at 30 seconds as measured by means of the Ford cup #4. The resulting coating compositions were sprayed on a steel plate in accordance with the usual method and set for 5 minutes followed by baking for 30 minutes at 120 °C to obtain a three-dimensional cured film.

The pencil hardness, the solvent resistance and water resistance of the respective compositions are shown in Table-2.

Table 2

		Examples No.				
		1	2	3	4	5
	(a) Vinyl polymer (weight)	A (168)	B (100)	C (100)	D (102)	E (200)
	(b) Another vinyl polymer (weight)	F (134)	F (25)	G (280)	G (200)	
	Pigment (c) Vinyl polymer (weight)	- ()	F (70)	-	G (70)	E (70)
	paste (d) Pigment (weight)	- ()	Taipake * CR-95 (40)	-	CR-95 (50)	CR-95 (50)
	Pencil hardness	3H	H	2H	H	H
	Solvent resistance	o	o	o	o	o

* White titanium oxide pigment available from Ishihara Sangyo Co., Ltd.

Example 6

(Preparation of a coating composition)

A coating composition was prepared by mixing the above obtained polymer and 40.2 g of trimethylol-propane.

(Baking process)

The obtained coating composition was applied on a steel panel by a bar coater and allowed to leave for 5 minutes. It was then baked at 120 °C for 30 minutes to obtained a cured film.

The obtained film had a pencil hardness of 2H and excellent solvent resistance.

Claims

1. A solvent based coating composition comprising at least one kind of vinyl polymer and an organic solvent, wherein any one of said vinyl polymer has at least one kind selected from the group consisting of an active hydrogen-containing group and a substituted acylamide group, and said vinyl polymer contains the above described two kinds of group as a whole.
2. The coating composition according to Claim 1 comprising (i) a vinyl polymer having a substituted acylamide group, (ii) a vinyl polymer having an active hydrogen-containing group, and (iii) an organic solvent.
3. The coating composition according to Claim 1 comprising (I) a vinyl polymer which has both a substituted acylamide group and an active hydrogen-containing group, and (II) an organic solvent.
4. The coating composition according to Claim 1 wherein said substituted acylamide group is present in an equivalence of 1×10^{-5} or more.
5. The coating composition according to Claim 1 wherein said active hydrogen is present in an equivalence of 1×10^{-5} or more.
6. The coating composition according to Claim 1 wherein said substituted acylamide group is present at

least 6 groups in one molecule.

7. The coating composition according to Claim 1 wherein said organic solvent has a solubility parameter of 8.0 to 20.0.

5

10

15

20

25

30

35

40

45

50

55

Fig. 3




Fig. 2




Fig. 4




Fig. 1 Prior art




Fig. 5




Fig. 6

