

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 484 960 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **91119058.5**(51) Int. Cl.⁵: **C21D 8/04, C22C 38/14**(22) Date of filing: **08.11.91**

(30) Priority: **09.11.90 JP 302697/90**
27.11.90 JP 321054/90

(43) Date of publication of application:
13.05.92 Bulletin 92/20

(84) Designated Contracting States:
AT CH DE FR GB IT LI

(86) Date of deferred publication of the search report:
03.03.93 Bulletin 93/09

(71) Applicant: **NIPPON STEEL CORPORATION**
6-3 Otemachi 2-chome Chiyoda-ku
Tokyo 100(JP)

(72) Inventor: **Yamada, Teruaki, c/o Hirohata**
Seitetsusho
NIPPON STEEL CORP., 1, Hirohata-ku Fujicho
Himeji-shi(JP)

Inventor: **Oda, Masahiko, c/o Hirohata**
Seitetsusho
NIPPON STEEL CORP., 1, Hirohata-ku Fujicho
Himeji-shi(JP)

Inventor: **Nishimoto, Yuzo, c/o Hirohata**
Seitetsusho
NIPPON STEEL CORP., 1, Hirohata-ku Fujicho
Himeji-shi(JP)

Inventor: **Kubo, Hiroshi, c/o Hirohata**
Seitetsusho
NIPPON STEEL CORP., 1, Hirohata-ku Fujicho
Himeji-shi(JP)


Inventor: **Nouno, Michihiro, c/o Hirohata**
Seitetsusho
NIPPON STEEL CORP., 1, Hirohata-ku Fujicho
Himeji-shi(JP)

(74) Representative: **Vossius & Partner**
Siebertstrasse 4 P.O. Box 86 07 67
W-8000 München 86 (DE)

(54) **Cold-rolled steel strip having excellent combined press formability and method of producing same.**

(57) A steel strip of a specific composition has tensile strength in 45° direction of 28.5 to 31.0 kgf/mm² and r value in 45° direction of not less than 1.90.

The steel strip exhibits excellent combined press formability. This steel strip is produced by continuous annealing.

FIG. 1**EP 0 484 960 A3**



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 91 11 9058

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	EP-A-0 295 697 (KAWASAKI STEEL CORPORATION) * page 3, line 56 - page 14, line 36; claims 1-5; examples 1,3,5; tables 1-4,6,7,11 *	1-4	C21D8/04 C22C38/14
A	EP-A-0 108 268 (NIPPON STEEL CORPORATION) * page 4, line 20 - page 23, line 11; claims 1-6; example 1; tables 1,2 *	1,2	
A	EP-A-0 171 208 (KAWASAKI STEEL CORPORATION) * page 3, line 12 - page 12, line 21; claims 1-4,6; examples 1-4; tables 1-5,7 *	1,2	
A	GB-A-2 234 985 (SUMITOMO METAL INDUSTRIES LTD) & WO-A-9 008 202 * page 5, line 18 - page 17, line 23; claims 1,3-6; examples 3-7; tables 2,4 *	1,2	
A	US-A-4 956 025 (K. KOYAMA ET AL) * column 2, line 47 - column 6, line 68; claims 1,5,7-10; examples 1-3; tables 1-4 *	1,2	TECHNICAL FIELDS SEARCHED (Int. Cl.5) C21D C22C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15 DECEMBER 1992	Examiner BLASBAND I.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document			