



(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **93305836.4**

(51) Int. Cl.⁵ : **C09J 7/04**

(22) Date of filing : **23.07.93**

(30) Priority : **30.07.92 US 922280**

(72) Inventor : **Van Vleck, Gordon Thomas**
88 North Lake Avenue
Troy, New York 12180 (US)

(43) Date of publication of application :
02.02.94 Bulletin 94/05

(74) Representative : **Pratt, Richard Wilson et al**
London Patent Operation G.E. Technical
Services Co. Inc. Essex House 12/13 Essex
Street
London WC2R 3AA (GB)

(84) Designated Contracting States :
DE FR GB

(71) Applicant : **GENERAL ELECTRIC COMPANY**
1 River Road
Schenectady, NY 12345 (US)

(54) **Silicone release composition.**

(57) The aged release stability of epoxy-functional W-curable polysiloxane release coating compositions on various substrates is enhanced by treating the substrate with a weak acid, such as acetic acid.

The present invention relates to silicone release coatings. More particularly, the present invention relates to epoxy functional ultraviolet (UV) radiation-curable polysiloxane release coatings. Most particularly, the present invention relates to a method for improving the aging stability of epoxy-functional UV-curable polysiloxane release coatings.

5

BACKGROUND OF THE PRESENT INVENTION

10

Silicone compositions have become widely accepted as release coatings, which are useful to provide a surface or material which is relatively nonadherent to other materials which would normally adhere closely thereto. Silicone release compositions may be used as coatings which release pressure sensitive adhesives for labels, decorative laminates, transfer tapes, etc. Silicone release coatings on paper, polyethylene, Mylar® and other such substrates are also useful to provide non-stick surfaces for food handling and industrial packaging.

15

Silicone release compositions are generally either heat-curable or UV-curable. The ultraviolet (UV) curable compositions have become more commercially acceptable for various applications due in part to the high energy costs and strict environmental regulations on solvent emissions which are attendant with the heat-curable compositions. Ultraviolet radiation is one of the most widely used types of radiation because of its low cost, ease of maintenance, and low potential hazard to industrial users. Typical curing times are much shorter, and heat-sensitive substrates can be safely coated and cured under UV radiation whereas thermal energy might damage the substrate.

20

Several UV-curable silicone systems are known in the art, including, Viventi, United States Patent No. 3,816,282, Bokerman et al., United States Patent No. 4,052,059 and Colquhoun et al., United States Patent No. 4,070,526. These patents describe compositions where ω -mercaptoalkyl substituted polysiloxanes react with vinyl-functional siloxanes when exposed to UV radiation in the presence of certain photosensitizers.

25

UV-curable silicone resins with epoxy or acrylic functionality are also known in the art. These resins are found to have the degree of activity necessary to make them especially suitable for release applications. Illustrative of these compositions are Eckberg et al., United States Patent No., 4,279,717; and Crivello et al., United States Patent No. 4,026,705, as well as others.

30

It has been found that while these compositions give excellent stable aged release properties in most applications, there still exists room for improvement in employing the silicone release compositions on kraft paper and machine refined paper substrates. It would therefore represent a notable advance in the state of the art if a novel silicone release composition could be developed which provided further improvements of stable aged release properties on these substrates.

35

To this end, the present applicant has now found that if the substrate, such as kraft paper, is treated with a weak acid, improved aged release properties are obtained.

SUMMARY OF THE PRESENT INVENTION

40

According to the present invention there is provided a method of improving the age releasing properties of a silicone release composition comprising applying an effective amount of a weak acid to a substrate.

Also according to the present invention there is provided a novel adhesive release composition comprising a silicone release composition, an adhesive and an effective amount of a weak acid.

45

Still further, according to the present invention there is provided a novel adhesive release system comprising a substrate, an effective amount of a weak acid applied to the substrate, a silicone release composition and an adhesive.

In preferred embodiments, the substrate is a Kraft paper, the weak acid is acetic acid, the silicone release composition comprises an ultra-violet light curable epoxy silicone and the adhesive is an acrylic adhesive.

DETAILED DESCRIPTION OF THE PRESENT INVENTION

50

The silicone release compositions useful in the practice of the present invention are UV radiation curable compositions and are well known in the art and described in the patent literature, for example, Eckberg et al., United States Patent No., 4,279,717; Crivello et al., United States Patent No. 4,026,705; Eckberg et al., United States Patent No. 4,421,904; Eckberg, United States Patent No. 4,547,431; Eckberg, United States Patent No. 4,576,999; Eckberg, United States Patent No. 4,640,967; Hayes et al., United States Patent No. 4,370,358; Eckberg, United States Patent No. 4,558,082; and Eckberg, United States Patent No. 4,977,198.

55

These silicone release compositions generally comprise a catalytic amount of a photocatalyst and an epoxy functional organopolysiloxane.

Particularly suitable for use with the present invention is a silicone release composition comprising a catalytic amount of an onium salt photocatalyst and an epoxy functional organopolysiloxane comprising in sufficient number to crosslink and cure the composition units of the formula:



5 wherein R is hydrogen, C₍₁₋₈₎ alkyl, or aryl, R¹ is a monovalent epoxy functional organic radical of from 2 to 20 carbon atoms, a is 0, 1 or 2; b is 1, 2 or 3; and a+b is 1, 2 or 3.

The epoxy functional organopolysiloxanes are easily and simply manufactured. By one method they are produced by reacting organopolysiloxane hydrides with unsaturated epoxy monomers in the presence of a platinum catalyst. The hydride may be present in the organopolysiloxane as H₂SiO_{2/2} units, HSiO_{3/2} units, (CH₃)₂HSiO_{1/2} units, and/or preferably (CH₃)HSiO_{2/2} units. The number of hydrides will determine the maximum number of epoxy functions present since the hydride will react with the unsaturation of the epoxy monomer and be replaced thereby.


Suitable unsaturated epoxy groups for use herein include vinyl or allylic functional epoxy compounds containing olefinic moieties such as allylglycidylether, glycidyl acrylate, vinyl norbornene monoxide, dicyclopentadiene monoxide and 4-vinylcyclohexeneoxide. Cyclohexeneoxide compounds are preferred. Epoxy functional organopolysiloxanes and the production thereof are taught in United States Patent Nos. 4,576,999 and 4,279,717.

The epoxy functional organopolysiloxane should have from about 2% to about 40% by number units with epoxy functions based on total silicone units, and preferably from about 3 to 25% by number. It is also contemplated that the epoxy functional organopolysiloxane be modified by modifying the epoxy functionalities by an epoxy esterification reaction with HOOC-R³ where R³ is a C₁₋₂₀ substituted or unsubstituted hydrocarbon radical. Generally from about 5% to about 60% by number of the epoxy functions and preferably from about 10% to 35% should be modified by such modifying reaction. Such a modifying reaction is described more fully in United States Patent No. 4,977,198.

25 The epoxy functional organopolysiloxane may be blended or compounded with optional substances as desired. Fillers, pigments, crosslinking agents or promoters, catalysts, UV absorbers etc. will all find utility in compositions containing epoxy functional organopolysiloxanes.


The photocatalysts useful in the practice of the present invention, particularly for use with epoxy functional materials are onium salt photocatalysts. Generally, the onium salt photocatalyst can be divided into three classes, namely the halonium photocatalysts, the sulfonium photocatalysts and the phosphonium photocatalysts.

The halonium salts are represented by the general formula:




35 where R⁶ is a monovalent aromatic organic radical; R⁷ is the same or a different monovalent aromatic organic radical; X is a halogen, such as I, Br, Cl, etc.; M is a metal or a metalloid; Q is a halogen radical, such as Cl, F, Br, I, etc.; e is a whole number equal to 0, 1 or 2; f is a whole number equal to 0, 1 or 2; e+f=2; g=h-i; i is the valence of M and is an integer from 2 to 7 inclusive; and h is greater than i and has a value up to and including 8. Preferred halonium salts are iodonium salts and are exemplified by 3-methoxyphenylphenyl-I⁺ BF₄⁻, 2-nitrophenyl-phenyl-I⁺ BF₄⁻, etc. The halonium salts are well known and are discussed further in United States Patent Nos. 4,026,705 and 3,981,897.

40 Similarly, the sulfonium salts are represented by the general formula:



45 where R⁸ is a monovalent aromatic organic radical; R⁹ is a monovalent organic aliphatic radical selected from alkyl, cycloalkyl, and substituted alkyl; R¹⁰ is a polyvalent organic radical forming a heterocyclic or fused ring structure selected from aliphatic radicals and aromatic radicals; X' is a group VIa element selected from sulfur, selenium and tellurium; M' is a metal or metalloid; Q' is a halogen radical, j is a whole number of 0, 1, 2 or 3; k is a whole number of 0, 1 or 2; l is a whole number of 0 or 1; j+k+l = 3 or the valence of X; m = n-p; p is the valence of M' and is an integer of from 2 to 7 inclusive; and n is greater than p and is an integer having a value up to 8. Consistent with the name given herein, it is preferred that X' be sulfur. Suitable sulfonium salts include triphenyl-S⁺ SbF₆⁻, 4-thiophenoxyphenyl-di-phenyl-S⁺ SbF₆⁻, tricyclodiphenylenephenyl-S⁺ BF₄⁻, benzoylmethyl-cyclo-butylene-S⁺ PF₆⁻. Further sulfonium salts are disclosed in United States Patent No. 4,161,478.

The phosphonium salts may be represented by the formula:



55 where R¹¹ is a monovalent aromatic organic radical selected from carbocyclic radicals and heterocyclic radicals; R¹² is a monovalent organic aliphatic radical selected from alkyl, alkoxy, cycloalkyl and substituted derivatives thereof; R¹³ is a polyvalent organic radical forming an aromatic heterocyclic or fused ring structure with X''; X'' is a group Va element selected from N, P, As, Sb, and Bi; M'' is a metal or metalloid, Q'' is a halogen radical; q is a whole number equal to 0 to 4 inclusive; r is a whole number equal to 0 to 2 inclusive; s is a whole number

equal to 0 to 2 inclusive. $q+r+s$ is a value equal to 4 or the valence of X'' ; $t = u-v$; v is the valence of M'' and is an integer of from 2 to 7 inclusive; and u is greater than v and is an integer having a value up to 8. X'' is preferably phosphorus as understood from the term phosphonium salt. Phosphonium salts are represented by, for example, tetraphenyl- $P^+ BF_4^-$, triphenylbenzoylmethyl- $P^+ AsF_6^-$, dimethyl-phenylbenzoylmethyl- $N^+ BF_4^-$. Phosphonium salts are further described in United States Patent No. 4,069,055.

Dye photosensitizers may also be added to the silicone release compositions of the present invention. These are generally added to increase the effectiveness of the photocatalyst and are understood to generally function by absorbing light of a spectrum which has little or no effect on the catalyst and releasing the absorbed light in a form to effect the photocatalyst. Thus, the use of the dye photosensitizer results in better utilization of the energy available from the light source. Dyes which can be used in combination with the above described onium salts are cationic dyes, such as shown in Vol. 20, p. 194-97 of the Kirk-Othmer Encyclopedia, 2nd Edition, 1965, John Wiley & Sons, New York. Some of the cationic dyes which can be used are, for example,

Acridine orange; C.I. 46005;

Acridine yellow; C.I. 46035;

Phosphine R; C.I. 46045;

Benzoflavin; C.I. 46065;

Setoflavin T; C.I. 49005.

In addition to the above, basic dyes can also be used as photosensitizers. Some of these basic dyes are shown in Vol. 7, p. 532-34 of Kirk-Othmer Encyclopedia, as cited above, and include:

Hematoporphyrin;

4,4'-bisdimethylaminobenzophenone and

4,4'-bisdiethylaminobenzophenone.

Also, suitable are xanthenes, such as thioxanthone, 2-isopropyl thioxanthone, and aminoxanthene, as described in Eckberg et al., United States Patent Application Serial No. 07/710,266, filed , 1991. Specific instances where dye photosensitizers are employed are also detailed in United States Patent No. 4,026,705.

Epoxy functional organic compounds which are miscible with epoxysilicones may also commonly be utilized in the epoxy functional organopolysiloxanes and onium salt photocatalyst compositions of the instant invention to modify cure performance and adhesion. These epoxy functional organic compounds include limoneneoxide, 4-vinylcyclohexeneoxide, allyl glycidyl ether, 7-epoxy-1-octene, vinylcyclohexenedioxide, bis(2,3-epoxycyclopentyl)ether, 3,4-epoxycyclohexylmethyl-3,4-cyclohexanecarboxylate, cresylglycidyl ether, butanedioldiglycidyl ether and the like. Mixtures of such epoxides are also suitable. These compounds may also be useful as reactive diluents.

The silicone release compositions are conveniently prepared into UV-curable compositions by simply mixing epoxy functional organopolysiloxanes with the onium salt photocatalyst and other ingredients as the skill in the art dictates. Of the onium photocatalysts there is generally required from about 0.1 % to about 15% by weight based on the weight of curable composition. Of the dye photosensitizers there may be employed any effective amount but generally from about 0.01 % to about 1.5% by weight, again based on the total curable composition. The epoxy functional organic compound where employed is generally present in an amount of from about 1% to about 50% and preferably from about 2% to about 20% by weight based on the epoxy functional organopolysiloxane present.

A curable silicone coating useful in the practice of the present invention may comprise about 100 parts by weight epoxy functional organopolysiloxane which is linear with a viscosity of from about 10 to about 500,000 centipoise at 25° C; optionally from about 1 to about 100 parts by weight of a reinforcing or extending filler, optionally from about 1 to about 50 parts by weight of an epoxy functional organic compound; from about 0.1 to about 15% by weight based on total composition an onium salt photocatalyst; and from about 0.01 to about 1.5% by weight of a dye photosensitizer based on total composition.

The silicone release compositions are known to be employed with a wide variety of adhesives to form coatings for pressure sensitive adhesives. In preferred embodiments the adhesives for use in the practice of the present invention are acrylic adhesives, although rubbery and other adhesives known to those skilled in the art may be used. These adhesives are available commercially and include but are not limited to, for example, GELVA® 263 self crosslinking adhesive available from Monsanto, Inc., and Ashland® 1085 available from Ashland Chemicals, Inc.

In the prior art, the silicone release coating compositions and the pressure sensitive adhesives were applied directly to a substrate by methods known to those skilled in the art, such as by coating, spraying, brushing and application by blade or gravure processes. Typical substrates included, but were not limited to, glass, metal, paper, polyethylene coated kraft (PEK) paper, super-calendered kraft (SCK) paper, machined finished paper, polyethylene films, polypropylene films, polyester films and the like.

The present applicant has now found that by pretreating the substrate with a weak acid, improved aged

release stability of the adhesive is obtained. Accordingly, essential to the practice of the present invention is the use of a weak acid. A weak acid, as used hereinabove and throughout the instant specification, is an acid having a pKa of 10^{-3} or below. Also contemplated for use herein are acids having a pKa of 10^{-5} or below.

Exemplary of acids useful in the practice of the present invention are saturated and unsaturated carboxylic acids, such as formic, acetic, acrylic, methacrylic, butyric, valeric, hexanoic, heptanoic, octanoic, palmitic, stearic, oleic, linoleic, halo- or cyano-substituted carboxylic acids such as chloroacetic acid or cyanoacetic acid, and aromatic acids such as benzoic acid or naphthoic acids and the corresponding halo or cyano or nitro substituted aromatic acids. Also useful are carbonic acid, phosphoric acid, boric acid and the like. Most preferred is acetic acid.

The acid, such as acetic acid, can be applied in any effective amount to the substrate by methods known to those of ordinary skill in the art. Typically coatings of solutions containing from about 1 to about 50% by weight acid is added, preferably from about 5 to about 25% by weight acid and most preferably from about 5 to about 10% by weight acid. Generally, a relatively thin and continuous coating is applied to the substrate, such as by means of a wire rod.

It is believed, although the inventor does not wish to be bound by any theory, that the weak acid simultaneously catalyzes the acid-triggered cure reaction of the silicone release composition and the rate of the cure reaction. The increased rate of cure is thought to be caused since the acid on the paper sets up a weak acid surface which catalyzes the reaction of the silicone composition. Without the acid present, the reaction must start first and generate acid to drive the reaction to completion. This increase in rate of cure prevents penetration of the silicone into the porous paper surface. The weak acid also neutralizes materials on the surface which might retard the cure of the compositions.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The following examples illustrate the present invention. They are not to be construed to limit the scope of the appended claims in any manner whatsoever.

EXAMPLES 1-3

Solutions of 1%, 5% and 10% acetic acid are prepared. These solutions are then respectively coated on SCK paper with a #5 Meyer rod and cured in a forced air oven for 20 seconds at 300°F. The acid coated SCK paper is then further coated with an epoxy functional silicone release composition comprising UV9300 epoxysilicone polymer and UV9310c photocatalyst, available from General Electric Company, using a Euclid Tool & Machine Co. Laboratory Coater at 100% solids to coat a continuous, defect free silicone coating of about 1.2 g/m² at 100% solids, and cured in an RPC model 1202 AN Lab UV processor equipped with 2 Hanovia 200 watt/inch UV lamps at 100 feet per minute. These sheets are then coated with a coating weight of 15 lbs/ream (3000 ft²) of GELVA® 263 acrylic adhesive by a laboratory 2 roll coater with feeler gauges and laminates are prepared therefrom by setting a sheet of paper facestock on the adhesive.

For comparison purposes, a non-acid treated sheet of SCK paper, a sheet of parchment and non-acid coated sheets coated with UV 9300 and UV 9310c on a commercial coater at Black Clawson, Fulton, NY are also prepared.

These sheets are tested for release values at different aging periods as the laminates aged at 25°C. The release values represent the amount of force necessary to separate the facestock or substrate containing the adhesive from the release liner or silicone coated substrate, for 2 inch wide laminates pulled at 400 inch/minute at a 180° angle.

The results are set forth in Table 1 below.

50

55

TABLE 1

<u>Example</u>	<u>A*</u>	<u>B*</u>	<u>C*</u>	<u>1^a</u>	<u>2^b</u>	<u>3^c</u>
Release data, g/in ²						
Initial same day release	45	65	15	25	25	25
1 Day	65	75	15	25	25	25
3 Day	125	115	15	30	30	25
10 Day	140	170	20	40	40	40

- * = Comparative Example
- A = Untreated paper
- B = Non-acid treated paper
- C = Parchment
- ^a = 1% Acetic Acid treated
- ^b = 5% Acetic Acid treated
- ^c = 10% Acetic Acid treated

From the data in Table 1 above, it can be seen that the acetic acid treated SCK paper provides significantly better aged release stability than untreated paper.

EXAMPLES 4-37

5 and 10% acetic acid was coated by a Meyer rod onto #42 SCK paper from Otis Specialty Papers. The coated paper was in turn coated with UV9300/3% UV9310c silicone release system at 200 and 400 feet per minute at two different silicone weights by means of a 3 roll offset gravure coating machine at Black Clawson Machine Co. Cure was then effected by exposure to 2 banks of focused Fusion Systems 375 watt/inch micro-wave-fired mercury vapor H lamps. The samples were then tested and the laminates were aged against the Gelva® 263 solvent acrylic adhesive at 70°C (Table 2) and at 25°C (Table 3), the Ashland® 1085 solvent acrylic adhesive at 25°C (Table 4) and at 70°C (Table 5) and the Flexacryl® 1625 emulsion acrylic adhesive at 25°C (Table 6). The release data from these tests is set forth below in Tables 2 - 6 along with comparative data.

5
10
15
20
25
30
35
40
45
50
55

TABLE 2 - Galva® 263 at 70°C

Example	4A*	4	5A*	5	6A*	6	7A*	7	8	9	10	11
% Acetic Acid	0	5	0	5	0	5	0	5	10	10	10	10
Line Speed	200	200	200	200	400	400	400	400	200	200	400	400
Coat Weight	0.78	0.89	1.06	1.0	1.0	0.80	0.75	1.0	0.80	0.97	0.76	1.04
Release Data, g/in ²												
Initial at 25°C	65	50	40	35	35	55	65	35	50	35	50	35
3 day at 70°C	>500	180	340	70	340	250	>500	70	140	60	230	70
1 week at 70°C	>500	120	300	40	350	180	>500	40	80	40	160	50
2 weeks at 70°C	>500	190	>500	50	>500	280	>500	40	100	40	180	60

* = Comparative Example

TABLE 3 - Galva® 263 at 25°C

Example	12A*	12	13A*	13	14A*	14	15A*	15	16	17	18	19
% Acetic Acid	0	5	0	5	0	5	0	5	10	10	10	10
Line Speed	200	200	200	200	400	400	400	400	200	200	400	400
Coat Weight	0.78	0.89	1.06	1.0	1.0	0.80	0.75	1.0	0.80	0.97	0.76	1.04
Release Data, g/in ²												
Initial at 25°C	110	85	60	60	50	95	90	55	85	55	100	50
1 week at 70°C	>500	90	130	50	120	120	>500	40	70	40	100	40
2 weeks at 70°C	>500	70	150	40	150	120	>500	40	60	60	100	40

* = Comparative Example

5
10
15
20
25
30
35
40
45
50
55

TABLE 4 - Anbland[®] 1085 at 70°C

Example	20A*	20	21A*	21	22A*	22	23A*	23	24	25	26	27
% Acetic Acid	0	5	0	5	0	5	0	5	10	10	10	10
Line Speed	200	200	200	200	400	400	400	400	200	200	400	400
Coat Weight	0.78	0.89	1.06	1.0	1.0	0.80	0.75	1.0	0.80	0.97	0.76	1.04
Release Data, g/in ²												
Initial at 25°C	90	75	60	50	55	75	85	45	80	55	80	60
1 week at 25°C	>250	90	100	60	90	90	240	45	85	60	90	60
2 weeks at 25°C	470	80	100	50	100	70	375	40	75	50	75	55

* - Comparative Example

TABLE 5 - Ashland® 1085 at 25°C

<u>Example</u>	<u>28A*</u>	<u>28</u>	<u>29A*</u>	<u>29</u>
% Acetic Acid	0	5	0	5
Line Speed	200	200	400	200
Coat Weight	0.78	0.89	1.0	1.0
Release Data, g/in ²				
Initial at 25°C	80	80	50	60
1 day at 70°C	450	100	130	70
1 week at 70°C	>500	220	>500	120

* = Comparative Example

5

10

15

20

25

30

35

40

45

50

55

5
10
15
20
25
30
35
40
45

TABLE 6 - Flexocryl® 1625 Emulsion Acrylic at 25°C

Example	30A*	10	31A*	31	32A*	32	33A*	33	34	35	36	37
% Acetic Acid	0	5	0	5	0	5	0	5	10	10	10	10
Line Speed	200	200	200	200	400	400	400	400	200	200	400	400
Coat Weight	0.78	0.69	1.06	1.0	1.0	0.60	0.75	1.0	0.60	0.97	0.76	1.04
Release Data, g/in ²												
Initial at 25°C	200	195	110	100	100	250	155	125	190	110	225	125
1 week at 25°C	240	200	120	120	120	240	200	125	190	130	225	135
2 weeks at 25°C	230	180	120	110	110	200	180	110	160	100	170	110

* = Comparative Example

50 From the data above it can be seen that all of the samples with the untreated paper had unstable release values regardless of the type of the adhesive, coating line speed or silicone coat weights. However, stable release values were obtained when the paper was treated with acetic acid, in accordance with the appended claims.

55 **COMPARATIVE EXAMPLES 38A* AND 39A***

The procedure of Example 1 was repeated except that 1% and 5% aqueous solutions of hydrochloric acid was substituted for acetic acid. After drying the hydrochloric acid coated paper, the paper turned color and

became brittle to the point it was unusable as a silicone liner. Therefore no silicone adhesive was applied and tested for aging. It can therefore be seen that adhesive systems employing acids outside the scope of the present invention do not provide the significant improvements in aged release stability of the adhesive systems of the present invention.

5 The above-mentioned patents are all hereby incorporated by reference.

Many variations of the present invention will suggest themselves to those of ordinary skill in the art in light of the above-detailed description. For example, adhesives other than acrylic adhesives may be employed. Further, other weak acids such as boric acid, benzoic acid, formic acid, acrylic acid, palmaric acid, oleic acid and the like may be used instead of acetic acid. Still further the invention may be practiced on other substrates, including but not limited to PEK paper, machine finished paper and films such as polyethylene films. All such obvious modifications are within the full intended scope of the appended claims.

Claims

15

1. A method for improving the age releasing stability of a silicone release composition on a substrate comprising applying to said substrate an effective amount of a weak acid.

2. A method as defined in Claim 1 wherein said silicone release composition comprises an epoxy functional organopolysiloxane having units of the formula:



wherein R is hydrogen, C₍₁₋₈₎ alkyl, or aryl, R¹ is a monovalent epoxy functional organic radical of from 2 to 20 carbon atoms, a is 0, 1 or 2; b is 1, 2 or 3; and a+b is 1, 2 or 3.

3. A method as defined in Claim 2 wherein said silicone release composition further comprises a photocatalyst.

4. A method as defined in any preceding claim wherein said weak acid is applied to the substrate as a relatively thin continuous coating.

5. A method as defined in any preceding claim wherein said weak acid has a pKa of less than about 10⁻⁵.

6. A method as defined in Claim 5 wherein said weak acid is selected from a substituted or unsubstituted saturated or unsaturated carboxylic acid, a substituted or unsubstituted aromatic acid, carbonic acid, boric acid, phosphoric acid and mixtures of any of the foregoing.

7. An adhesive release composition comprising a silicone release composition, an adhesive and an effective amount of a weak acid.

8. An adhesive release composition as defined in Claim 7 wherein said silicone release composition comprises an epoxy functional organopolysiloxane having units of the formula:



wherein R is hydrogen, C₍₁₋₈₎ alkyl, or aryl, R¹ is a monovalent epoxy functional organic radical of from 2 to 20 carbon atoms, a is 0, 1 or 2; b is 1, 2 or 3; and a+b is 1, 2 or 3; and a photocatalyst selected from halonium photocatalysts, sulfonium photocatalysts, phosphonium photocatalysts and mixtures of any of the foregoing.

9. An adhesive release composition wherein said adhesive is an acrylic based adhesive.

10. An adhesive release system having improved aged release stability comprising a substrate, a relatively thin continuous coating of a weak acid applied to said substrate, a silicone release composition and an adhesive.

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 93 30 5836

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	WO-A-9 203 233 (PATTERSON) * page 1, line 25 - page 2, line 6 * * page 5, line 19 - line 23 * ---	1-10	C09J7/04
A	EP-A-0 089 279 (INST NAT DE RECHERCHE CHIM) * claim 1 * ---	1	
A	US-A-4 313 988 (3M) * claims 1,19 * -----	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C09J C09D
Place of search		Date of completion of the search	Examiner
THE HAGUE		14 SEPTEMBER 1993	LENTZ J.C.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1503 01.92 (P0401)