

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 600 727 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
25.02.1998 Bulletin 1998/09

(51) Int. Cl.⁶: **C07C 67/333**, C07C 69/54

(21) Application number: **93309613.3**

(22) Date of filing: **01.12.1993**

(54) Depolymerisation

Depolymerisierung

Dépolymérisation

(84) Designated Contracting States:
AT BE DE ES FR GB IT NL PT

(30) Priority: **04.12.1992 GB 9225461**

(43) Date of publication of application:
08.06.1994 Bulletin 1994/23

(73) Proprietor: **DU VERGIER LIMITED**
Hoddesdon, Herts. EN11 0DW (GB)

(72) Inventors:
• **Highgate, Donald James**
Holmbury St Mary, Dorking RH5 6NS (GB)
• **Vaughan, Patrick William**
Menai Bridge, Anglesey LL59 5NP (GB)

(74) Representative:
Perry, Robert Edward
GILL JENNINGS & EVERY
Broadgate House
7 Eldon Street
London EC2M 7LH (GB)

(56) References cited:
EP-A- 0 046 183

- **JOURNAL OF ANALYTICAL AND APPLIED PYROLYSIS**, no.19, 1991, AMSTERDAM NL pages 311 - 318 W. KAMINSKY AND J. FRANCK 'Monomer recovery by pyrolysis of poly(methyl methacrylate) (PMMA)'
- **CHEMICAL ABSTRACTS**, vol. 87, no. 2, 11 July 1977, Columbus, Ohio, US; abstract no. 6399e, ANON. 'Method of depolymerising thermoplastics.' page 2 ;column 2 ; & **RESEARCH DISCLOSURE**, no.157, 1977, HAVANT GB page 18

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 600 727 B1

Description

Field of the Invention

This invention relates to a depolymerisation process.

Background of the Invention

Monomer can often be recovered from polymer waste by depolymerisation. In particular, PMMA, i.e. poly(methyl methacrylate), gives methyl methacrylate at elevated temperature. For many years, PMMA has been successfully depolymerised by contact with molten lead at about 500°C; the monomer MMA can be obtained in a purity of more than 98% (here and throughout, percentages are given by weight unless otherwise specified).

Although this process gives MMA of high purity, the use of lead is undesirable, from an environmental viewpoint. Further, small amounts of lead as a contaminant are extremely difficult to remove from the monomer, reducing the range of commercial products for which the recovered monomer is acceptable. Higher purity would be desirable, and in particular substantial freedom from by-products such as methyl isobutyrate which is non-polymerisable, smelly and difficult to separate from MMA.

Kaminsky *et al.*, J. Anal. App. Pyrolysis **19** (1991) 311-318, disclose the recovery of MMA by pyrolysing PMMA in an indirectly-heated fluidised-bed process. At 450°C, more than 97% of the PMMA was recovered as monomer.

Research Disclosure 157:18, No. 15743 (May 1977) discloses the depolymerisation of polymeric material in particulate form by heating on the surface of a fluidised bed. Optimum results are obtained by depolymerisation of PMMA at a temperature of at least 400°C and preferably at least 500°C.

EP-A-0046183 discloses the recovery of caprolactam from caprolactam oligomers by heating in an alumina bed, and introducing steam, at 290-400°C.

Summary of the Invention

It has now been found, according to the present invention as set out in claim 1, that effective depolymerisation of PMMA and other depolymerisable polymers can be achieved in a fluidised-bed process at a relatively low temperature, by maintaining a fluidising gas flow, initially at least of inert gas and subsequently of monomer vapour, such that the heat transfer coefficient is maintained at a value sufficient to ablate the polymer particles. In particular, the temperature is below the autoignition point of the monomer (c. 425°C for MMA), thereby making the process not only potentially more economical but also much safer than the process described by Kaminsky *et al.* Despite the lower temper-

ature, e.g. from 300°C or 350°C up to 400°C or 420°C, the reaction rate remains high, the purity is significantly higher, and the process is thus of commercial importance.

On the simplest level, the novel process overcomes an apparent prejudice against operating the depolymerisation of PMMA at temperatures much below 500°C. The results that are thus achieved are surprising, since very high grade monomer is obtained under intrinsically safe conditions, in a bed which is apparently self-regulating and limited by heat-transfer coefficient (HTC) rather than absolute temperature. Further, the content of volatiles in the monomer vapour is surprisingly low. This combination of effects could not be expected, on the basis of the given prior art.

In a conventional gas-fluidised bed it is difficult to achieve heat transfer coefficients which exceed 500-600 W/m².K. On this basis it would be expected that many of the larger polymer particles would heat until they soften and therefore foam prior to depolymerisation into MMA vapour. In this condition, they would float to the top of the bed where the HTC would decrease still further and the bed would choke unless the working temperature was very much increased. In the present invention, the polymer particles have been shown to ablate and depolymerise from the surface without foaming. This process allows the particles to remain within the body of the bed where the necessary high HTC can be maintained, contributing to high output levels.

Although this invention will be described by way of illustration with respect to the production of MMA by the depolymerisation of PMMA, other depolymerisation processes may be so operated. The process is particularly applicable to the production of those monomers including a CH₂=CR-group, i.e. in which a polymer of the acrylate type has no α -H atom. Specific polymers that may be depolymerised are polyethylene terephthalate (that has been pre-treated with alcohol), isoprene and styrene.

Brief Description of the Drawings

The accompanying drawings illustrate, schematically, embodiments of apparatus suitable for use in a process according to the invention. The essential components of a recycling system are a fluidised bed chamber (1) and a recycling line (2) for gas via a cyclone (3) and a condenser (4). Entrained solids are removed in the cyclone. Circulation is driven by a fan (5). An inlet (6) for polymer and an outlet (7) for monomer are provided. The bed height is h_1 when static, h_2 when fluidised by inert gas, and h_3 when fluidisation is additionally driven by vapour of reaction, as described in more detail below.

Description of the Invention

The fluidised bed may be of known type. It preferably comprises particles of an inert material such as SiC,

silica or alumina. Alumina is preferred with respect to, say, silica; notwithstanding its greater density which requires increased gas circulation pressures, there does not appear to be any adverse effect on the heat transfer or throughput rates once vapour-driven fluidisation has become established. The particles are, for example, 50-1000 μm , e.g. 50-300 μm , in diameter.

The bed may be heated by any suitable means, directly or indirectly. For example, heating elements may be provided in the reaction chamber. Alternatively or in addition, quartz-iodine lamps may be used, or mercury-emitting discharge lamps that may emit in the visible spectrum and in the UV at wavelengths of 200 to 300 nm, to enhance depolymerisation. Indirect heating may be particularly suitable for low temperature depolymerisation.

An inert gas such as nitrogen may be used to initiate fluidisation of the bed in which the polymer is depolymerised. A characteristic of the depolymerisation of PMMA at least is that, following fluidisation of the bed by inert gas (which provides for the very high heat transfer coefficients needed by heating elements, and to initiate the depolymerisation of the PMMA first added to the bed), fluidisation is soon augmented by vapour evolved from the depolymerisation process. In the depolymerisation phase, when the bed is effectively driven by the evolved vapour, it has been found that the bed is essentially self-stabilising and therefore quite controllable. The inert gas flow helps to control the residence time of the vapour at high temperature, e.g. at a superficial velocity of 1 to 10 cm/sec for a given bed particle diameter.

Accordingly, the novel process involves gas circulation with a superimposed vapour flow, comprising generation in the bed and vapour removal as condensate in the condenser. During vapour-driven fluidisation, there exists the possibility of controlling the fluidisation and depolymerisation process by control of vapour pressure. Both the quality of fluidisation and the activity of the depolymerisation process are largely dependent upon the vapour cycle during vapour-driven fluidisation, and it has been found that if a low temperature vapour "trap" is included as the last stage of the condenser system, then very small changes in the temperature of this stage, e.g. by about 1.5°C, from -4 to -2.5°C, have a profound effect upon the throughput as measured by the rate of condensation in the primary condenser sections. For example, as the temperature of a cold vapour control stage increases from -4 to -2.5°C, the rate of depolymerisation falls sharply; as the temperature decreases, the rate of depolymerisation rises rapidly and immediately.

Since the volume of the bed is expanded enormously when depolymerisation is occurring, some means may be required in order to remove particles of the bed entrained with the flow of monomer vapour. For example, a cyclone may be provided; the separated particles can then be returned directly to the reaction

chamber. A suitable cyclone may be provided with an impeller. The exit temperature of the inert gas stream plus monomer vapour may be less than 250°C, so that a simple pressed metal or cast aluminium impeller may be used.

In one embodiment of apparatus for use in the present invention, the reaction chamber is modified so that it has a variable area throat, in order to make it fully self-regulating in the region where evolved vapour from the depolymerisation process is driving the fluidisation. A suitable design of chamber is generally cylindrical, its diameter increasing towards the top, e.g. trumpet-shaped. Additional control functions are variation of the inert gas flow, the rate of polymer input, and possibly also temperature conditions in the condenser.

In another embodiment of apparatus for use in the invention, the bed particles passing to the top of the reaction chamber are recirculated. In a circulating bed, a significant proportion of the bed material is kept constantly in transit out of the bed through a cyclone and back into the bed via a valve. This embodiment allows the polymer input to be combined with the return flow of bed material.

These two alternative embodiments will now be described by way of example only with reference to the accompanying, schematic drawings. The embodiments are respectively shown in Figures 1 and 2.

In the apparatus shown in Fig. 1, the cross-section of the bed container 1 is designed to match the increasing vapour flow from the process. This is an active part of the bed-fluidising region, not a transport disengagement device. The principle is to provide a parallel cross-section for the gas fluidised bed operation, and an exponentially increasing cross-section for the depolymerisation phase to operate in.

The apparatus of Fig. 2 provides for particle circulation and for a circulating bed in which a controlled part of the bed material leaves the reactor and is recirculated through a hydrodynamic valve 8. This may be incorporated into a bed material treatment process for the removal of waste products.

Accordingly, whether or not all such apparatus features as are shown in the drawings are adopted, a satisfactory rate of depolymerisation can be controllably maintained while polymer is introduced up to 40, e.g. 20-30, kg/h per 0.1 m² of active bed. The polymer is suitably introduced into the reaction chamber, e.g. a stainless steel vessel, by means of a screw feed. This feed is preferably above the normal height of the bed, in order to prevent the screw being heated by contact with the bed, thus preheating the polymer and causing the heated polymer to adhere to the screw. This and other potential problems are also minimised by the addition of a nitrogen entrainment flushing system to prevent back-flow of vapour along the screw. Using apparatus of this type, in a reaction chamber having internal base dimensions of 40 cm x 40 cm and a PMMA scrap feed of 30 kg/h, it has been demonstrated that the bed is stable

both in the initial phase and in the presence of depolymerisation. The heaters have been operated at full load for many hours, with an operating temperature only 5-50°C above a mean bed temperature of 385°C. The bed itself shows very small temperature variations, in the region of only 5°C across its width and from top to bottom. It is therefore essentially isothermal. Most importantly, the degree of fluidisation judged by the variation in temperature within the system actually improves as the evolved vapour from the depolymerisation process takes over from the nitrogen flow as the principal fluidisation mechanism.

The following Example illustrates the invention, using apparatus as described immediately above.

Example

Using approx. 90 kg of sand having a mean particle size of 120 µm, providing a non-fluidised bed height of 300 mm, PMMA was depolymerised.

Calculations based upon the theory of conventional fluidised beds show that the maximum depolymerisation rate for the experimental bed would be approximately 30 kg/h, provided that the necessary heat could be transferred to the particles of polymer. This limit is set by the superficial velocity at which bed material would be carried away and does not depend upon any temperature depolymerisation rate characteristics.

An average depolymerisation rate of 32.3 kg/h was observed for periods exceeding one hour, with peak activities estimated to be equivalent to 35-40 kg/h at a mean bed temperature of 410°C. The resulting monomer had a purity (by GLC) of 99.25-99.48%.

Calculations suggest that vapour-driven fluidisation becomes significant when a critical minimum polymer burden (equivalent to vapour sources spaced at 20-30 mm separations within bed) is exceeded in the bed; after which both the fluidisation process and most importantly the heat transfer coefficient achieved between the particles of the bed cease to be conventional functions of superficial gas flow as predicted by standard theories.

In a further test sequence, the temperature of the bed was allowed to decrease from an initial value of 350-315°C while the PMMA input was maintained at 16-20 kg/h.

On the basis of this and similar trials, it appears that the throughput is essentially independent of bed temperature at least in the range 460-315°C provided that the HTC is maintained at a value sufficient to achieve ablation of the particles of polymer.

Claims

1. A depolymerisation process, which comprises heating particles of a depolymerisable polymer in a fluidised bed comprising particles of an inert material of at least 50 µm diameter, characterised in that

the process is conducted at a temperature below the autoignition point of the monomer, while maintaining a fluidising gas flow, initially at least of inert gas and subsequently of monomer vapour, such that the heat transfer coefficient is at a value sufficient to ablate the polymer particles.

2. A process according to claim 1, in which the monomer is methyl methacrylate.
3. A process according to claim 1 or claim 2, in which the temperature is 300-420°C.
4. A process according to any preceding claim, in which the particles of inert material are 50 to 1000 µm in diameter.
5. A process according to claim 4, in which the inert material is alumina.
6. A process according to any preceding claim, in which the fluidising gas is circulated from the upper part of the bed to the lower part, via a condenser where entrained monomer is separated.
7. A process according to any preceding claim, which comprises means for continuously and controllably recycling bed material.
8. A process according to any preceding claim, in which the cross-section of the reaction chamber increases upwardly.

Patentansprüche

1. Depolymerisationsverfahren, welches umfaßt das Erwärmen von Teilchen eines depolymerisierbaren Polymers in einem Fließbett, das Teilchen eines inerten Materials mit einem Durchmesser von mindestens 50 µm umfaßt, dadurch gekennzeichnet, daß das Verfahren bei einer Temperatur unter dem Selbstentzündungspunkt des Monomers durchgeführt wird, während man einen verwirbelnden Gasstrom, am Anfang zumindest von Inertgas und anschließend von Monomerdampf, derart aufrechterhält, daß der Wärmeübertragungskoeffizient bei einem Wert liegt, der ausreicht, um die Polymerteilchen abzutragen.
2. Verfahren nach Anspruch 1, in welchem das Monomer Methylmethacrylat ist.
3. Verfahren nach Anspruch 1 oder Anspruch 2, in welchem die Temperatur 300 - 420°C beträgt.
4. Verfahren nach irgendeinem vorangehenden Anspruch, in welchem die Teilchen aus inertem Material einen Durchmesser von 50 - 1000 µm auf-

weisen.

5. Verfahren nach Anspruch 4, in welchem das inerte Material Aluminiumoxid ist.

5

6. Verfahren nach irgendeinem vorangehenden Anspruch, in welchem das verwirbelnde Gas vom oberen Teil des Bettes zum unteren Teil über einen Kühler, in welchem mitgeschlepptes Monomer abgetrennt wird, im Kreis geführt wird.

10

7. Verfahren nach irgendeinem vorangehenden Anspruch, welches Mittel zur kontinuierlichen und steuerbaren Recyclisierung von Bett-Material umfaßt.

15

8. Verfahren nach irgendeinem vorangehenden Anspruch, in welchem der Querschnitt der Reaktionskammer nach oben hin zunimmt.

20

Revendications

1. Procédé de dépolymérisation, qui comprend l'étape consistant à chauffer des particules d'un polymère dépolymérisable dans un lit fluidisé comprenant des particules d'un matériau inerte, d'au moins 50 µm de diamètre, caractérisé en ce que le procédé est conduit à une température inférieure au point d'inflammation spontanée du monomère, pendant que l'on maintient un courant de gaz de fluidisation, au départ au moins d'un gaz inerte et ensuite de vapeur de monomère, de telle sorte que le coefficient de transfert de chaleur ait une valeur suffisante pour soumettre à ablation les particules de polymère.

25

30

35

2. Procédé selon la revendication 1, dans lequel le monomère est le méthyl méthacrylate.

3. Procédé selon la revendication 1 ou la revendication 2, dans lequel la température est de 300-420°C.

40

4. Procédé selon l'une quelconque des revendications précédentes, dans lequel les particules de matériau inerte ont un diamètre de 50 à 1000 µm.

45

5. Procédé selon la revendication 4, dans lequel le matériau inerte est l'alumine.

50

6. Procédé selon l'une quelconque des revendications précédentes, dans lequel le gaz de fluidisation circule de la partie supérieure du lit vers la partie inférieure, en passant par un condenseur dans lequel est séparé le monomère entraîné.

55

7. Procédé selon l'une quelconque des revendications précédentes, qui comprend des moyens pour recy-

cler en continu et de manière commandée le matériau du lit.

8. Procédé selon l'une quelconque des revendications précédentes, dans lequel la section transversale de la chambre de réaction croît vers le haut.