

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 622 353 B1**

(12)

## EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention  
of the grant of the patent:  
**10.09.1997 Bulletin 1997/37**

(51) Int. Cl.<sup>6</sup>: **C07C 69/653**, C07C 67/08,  
C08F 20/24, C09D 133/16

(21) Application number: **94106375.2**

(22) Date of filing: **25.04.1994**

### (54) **Coatings based on perfluoropolyethers containing acrylic groups**

Beschichtungen basierend auf Acrylgruppen enthaltenden Perfluorpolyethern

Revêtements à base de perfluoropolyéthers contenant des groupes acryliques

(84) Designated Contracting States:  
**AT BE CH DE DK ES FR GB GR IE IT LI LU NL PT  
SE**

(30) Priority: **28.04.1993 IT MI930837**

(43) Date of publication of application:  
**02.11.1994 Bulletin 1994/44**

(73) Proprietor: **AUSIMONT S.p.A.**  
**I-20121 Milano (IT)**

(72) Inventors:  
• **Simeone, Giovanni**  
**Solaro, Milano (IT)**  
• **Tonelli, Claudio**  
**Concorezzo, Milano (IT)**  
• **Strepparola, Ezio**  
**Treviglio, Bergamo (IT)**  
• **Mutta, Fabrizio**  
**Caronno Pertusella, Varese (IT)**

(74) Representative: **Sama, Daniele, Dr. et al**  
**Sama Patents**  
**Via Morgagni, 2**  
**20129 Milano (IT)**

(56) References cited:  
**EP-A- 0 373 385** **EP-A- 0 394 927**

- **DATABASE WPI Section Ch, Week 8818, Derwent Publications Ltd., London, GB; Class A41, AN 88-123665 'Fluorinated methacrylate ester deriv. - used as flexible coating agent, prepd. from correspond. acid chloride and fluoro alcohol' & JP-A-63 068 542 (SHINETSU CHEM IND KK) 28 March 1988**
- **POLYM. PREPR. (AM. CHEM. SOC., DIV. POLYM. CHEM.) vol. 34, no. 1, 5 March 1993 pages 405 - 406 HWANG, F.S. & HOGEN-ESCH, T.E. 'Effects of water-soluble spacers on the hydrophobic association of fluorocarbon modified polyacrylamide'**

#### Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).


**EP 0 622 353 B1**

## Description

The present invention relates to coatings based on PFPE (perfluoropolyethers) having high mechanical properties, in particular hardness, combined with high resistance to photooxidative degradation and resistance to hydrolysis.

These properties are required in all applications as top-coat, for instance in the car industry.

A fluorinated methacrylic ester having the general formula:



is known from Derwent Abstract of JP-A-63068542.


Fluorinated polyacrylates from perfluoropolyethers, in particular Galden<sup>(R)</sup> acrylates, are known (see US Patent 5,011,979).

Experiments carried out from the Applicant have pointed out that resins obtained therefrom have such poor resistance properties to hydrolysis, as to make them unsuitable to the application as top-coat.

It has been unexpectedly found that it is possible to prepare coatings based on PFPE having the above indicated properties by utilizing the PFPE of the invention as hereinafter specified.

Object of the present invention are perfluoropolyethers containing (meth)acrylic groups obtainable by copolymerization of:

a) 1 - 50% by weight of a monomer having general formula:



wherein Y = F, Cl, CF<sub>3</sub>, C<sub>2</sub>F<sub>5</sub>, C<sub>3</sub>F<sub>7</sub>, C<sub>4</sub>F<sub>9</sub>; and X = F, CF<sub>3</sub>; p is an integer from 1 to 5; R<sub>f</sub> represents a radical having perfluoropolyetheral structure of average molecular weight of from 400 to 3000, formed by sequence of oxyfluoroalkylenic units; and R = H, CH<sub>3</sub>;

b) 40 - 90% by weight of one or more monomer(s) of formula




wherein R<sub>1</sub> = H, CH<sub>3</sub>, F, Cl; A is an alkyl radical having from 1 to 12 carbon atoms or a fluoroalkyl radical having from 1 to 10 carbon atoms, or an aliphatic or aromatic cyclic group having from 6 to 8 carbon atoms; and

c) 2 - 30% by weight of one or more monomer(s) of formula:



wherein R<sub>1</sub> has the same meaning described above; W = O, NH; B = H, (CH<sub>2</sub>)<sub>s</sub>B<sub>1</sub> with s = 1 - 5, B<sub>1</sub> = -COOH, -OH, -CH=CH<sub>2</sub>, NCO, -CO-CH<sub>2</sub>CO-CH<sub>3</sub>, -Si(OR<sub>2</sub>)<sub>3</sub> with alkylic R<sub>2</sub> groups having from 1 to 5 carbon atoms; the sum of the monomers a), b) and c) being equal to 100.

R<sub>f</sub> consists of sequences of oxyfluoroalkylenic units, such as for instance the units: -CF<sub>2</sub>O-, -CF<sub>2</sub>CF<sub>2</sub>O-, -CF<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>O-,



-CF<sub>2</sub>CF<sub>2</sub>CH<sub>2</sub>O-; R=H, CH<sub>3</sub>.


The acrylated perfluoropolyethers of formula (I) can be obtained by using the method indicated in the US Patent 5,011,979 which is here wholly incorporated.

The methods to prepare the precursors are largely known in the art, see for instance US Patents 3,513,203; 3,847,978; 3,810,874.

In particular suitable perfluoropolyethers to obtain the perfluoropolyethers acrylates of formula (I) are the ones formed

by sequences of perfluoroxyalkylenic units of the following types:


IA)



(CFXO) with X = F or CF<sub>3</sub>,

said units being randomly distributed along the perfluoropolyether chain;


IIA) (CF<sub>2</sub>CF<sub>2</sub>O),



(CFXO) with X = F or CF<sub>3</sub>,

said units being randomly distributed along the perfluoropolyether chain;

IIIA)



IVA) (CH<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>O);

VA) (CF<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>O);

VIA) (CF<sub>2</sub>CF<sub>2</sub>O).

The perfluoroetheral compounds containing the indicated units are preferably selected among the following classes:

IB) A'O (C<sub>3</sub>F<sub>6</sub>O)<sub>m</sub>(CFXO)<sub>n</sub>-

where X is -F, -CF<sub>3</sub>;

A' is = -CF<sub>3</sub>, -C<sub>2</sub>F<sub>5</sub>, -C<sub>3</sub>F<sub>7</sub> the C<sub>3</sub>F<sub>6</sub>O and CFXO units are randomly distributed along the perfluoropolyether chain, m and n are integers, the ratio m/n is ≥ 2.

These perfluoropolyethers are obtained by photooxidation of hexafluoropropene according to the process described in GB Patent 1,104,482.

IIB) C<sub>3</sub>F<sub>7</sub>O(C<sub>3</sub>F<sub>6</sub>O)<sub>m</sub>-, where m is a positive integer whereby the molecular weight has the above indicated value. They are obtained by ionic telomerization of the hexafluoropropene epoxide. See for instance US Patent 3,242,218.

IIIB) (C<sub>3</sub>F<sub>6</sub>O)<sub>m</sub>(C<sub>2</sub>F<sub>4</sub>O)<sub>n</sub>(CFXO)<sub>q</sub> where

X is equal to -F, -CF<sub>3</sub>; m, n and q, different from zero, are integers whereby the average molecular weight is at least 400.

These products are obtained by photooxidations of mixtures of C<sub>3</sub>F<sub>6</sub> and C<sub>2</sub>F<sub>4</sub> according to the process described in US Patent 3,665,041.

The Applicant has unexpectedly and surprisingly found that the (CH<sub>2</sub>CH<sub>2</sub>O)<sub>p</sub> group of the unsaturated ester, introduced in the formula of the starting alcohol (III) reported below, confers a surprising stability to the ester itself, mainly as regards the non hydrolyzability. Moreover a better reactivity in synthesis phase has been found.

The perfluoropolyetheral part has preferably the following formula:



where Y = F, Cl, CF<sub>3</sub>, C<sub>2</sub>F<sub>5</sub>; X = F, CF<sub>3</sub>; m and n have the above indicated meaning in (IIIB)

When Y is different from F or perfluoroalkyl, it can be obtained for instance according to EP Patent 0393230.

5 The acrylate or methacrylate (I) is prepared by reacting the fluorinated alcohol of formula



10 where X and Y have the meaning indicated, obtained by ethoxylation with ethylene oxide, for instance according to the process of the US Patent 3,810,874, with acrylic or methacrylic acid according to US Patent 5,011,979.

This preparation method is applicable to all alcohols with the other above indicated R<sub>f</sub> groups.

15 The esterification is carried out at a temperature between 30° and 150°C, preferably between 60° and 100°C in the presence of an usual esterification catalyst as p-toluenesulphonic acid, sulphuric acid, borotrifluoride, phosphoric acid or phosphoric anhydride, in an inert solvent as benzene, toluene, xylene. It is preferable to operate in the presence of polymerization inhibitors such as hydroquinone, di-ter-butyl-p-cresol, ter-butylcatechol, p-methoxy-phenol, etc. in amounts from 0.5 to 3% by weight on the total weight of the reactants.

20 Alternatively, the acrylate or methacrylate (I) can be prepared by direct reaction of the fluorinated alcohol (III) with acryloyl chloride or methacryloyl chloride, respectively. The reaction is carried out at a temperature comprised between 5 and 60°C in the presence of a polymerization inhibitor, as reported above. As acid acceptor it can be used a basic substance such as triethyl amine, pyridine, etc. Alternatively, the acrylate or methacrylate (I) can be prepared by reacting the fluorinated alcohol (III) with acrylic or methacrylic anhydride, respectively, at a temperature between 5 and 60°C in the presence of a polymerization inhibitor and of an acid acceptor.

The polymer of the present invention to be utilized as coating is obtained by radicalic polymerization in mass, in solution, in suspension or in emulsion.

25 Examples of usual solvents for the polymerization in solution are fluorinated solvents such as m-hexafluoroxylene, trifluorotoluene and the like, hydrogenated solvents as acetone, methylethylketone, methylisobutylketone (MIBK), ethyl acetate, isobutylacetate, toluene, xylene and the like. The polymer obtained by polymerization in solution can be used under the form of solution prepared by separating the polymer from the reaction solvent and by redissolving the polymer in the same or in another solvent or mixture of solvents, or under the form of solution merely prepared by diluting the resulting reaction mixture with the same or with another solvent or mixture of solvents.

30 The polymer obtained by polymerization in mass is used by dissolving it in a solvent or mixture of solvents after drying to remove the possibly remaining monomers.

35 Examples of usual radical polymerization initiators for polymerization in mass, solution or suspension are organic peroxides such as benzoyl peroxide, dicumyl peroxide, lauryl peroxide and the like, azocompounds such as azobisisobutyronitrile (AIBN), azobisisovaleronitrile and the like.

Examples of usual polymerization initiators for polymerization in emulsion are oxidizing agents, such as ammonium persulphate and potassium persulphate, and redox initiators comprising such an oxidizing agent, sodium sulphite or the like as reducing agent and FE (III) sulphate or similar transition metals salts.

40 The polymerization initiator is used in amounts from 0.1 to 5% by weight on the weight of all the monomers. Examples of usual emulsifying agents for polymerization in emulsion are of the anionic type, such as sodium lauryl sulphate, ammonium perfluorooctanoate and the like, of cationic type such as dodecyl trimethyl ammonium bromide, hexadecyl trimethyl ammonium bromide and the like, of non-ionic type such as polyethylenoxide lauryl ether and the like; the emulsifying agents are used in amounts of about 0.001 to 5% by weight with respect to the water amount.

45 If the solvent itself or other features are not sufficient to control the molecular weight, small amounts of chain controlling agents, such as alkanthiols having from 4 to 12 carbon atoms, can be used.

The polymerization temperature is preferably comprised between 30 and 150°C. The fluorinated polymer of the present invention has a molecular weight between 2,000 and 50,000, measured by GPC by using polystyrene as standard.

50 The polymer of the present invention, containing one or more monomers represented by the structure (V), is submitted to crosslinking to increase the adhesion to the substrate and its mechanical properties.

55 Examples of crosslinking agents generally used when the functional group of the monomer (V) is the -COOH group, are compounds having at least two aminic groups such as ethylene diamine, hexamethylenediamine, triethylenediamine, diamino-diphenylmethane and the like; compounds with at least two epoxidic groups such as butylenediglycidyl ether, bisphenol A diglycidyl ether and the like. Examples of crosslinking agents generally used when the functional group of the monomer (V) is the -OH group, are compounds with at least two isocyanic groups such as hexamethylene diisocyanate, isophoronediiisocyanate and their trimers or biurets; moreover, there can be used "blocked" polyisocyanates where the blocking agent can be of phenolic, alcoholic, mercaptan, oxime, imino type, etc.; compounds of the type alkyl etherated amino resins, such as alkyl etherated derivatives of melaminic, ureic benzoguanaminic resins, of the methyl ether, butyl ether, isobutyl ether type, methyl-butyl mixed ethers and the like.

When an alkyl etherated amino resin is used as cross-linking agent, the ratio between the fluorinated polymer of the present invention and the amino resin is preferably between 55/45 and 95/5, more preferably between 60/40 and 90/10 by weight.

When a polyisocyanate is used as crosslinking agent, the ratio between the fluorinated polymer of the present invention and the polyisocyanate is preferably between 0.5 and 2, more preferably between 0.8 and 1.2 in terms of equivalents ratio between isocyanate groups and hydroxy groups.


Examples of crosslinking agents generally used when the functional group of the monomer (V) is the -NCO group, are compounds with at least two amino groups or two acid groups or two hydroxy groups.

Crosslinking occurs in any case at a temperature between the room temperature and 200°C, for a time about 30 minutes up to 24 hours.

In Table 1 hereinafter, the OH value is determined according to ASTM E222 standards, expressed by mg of KOH per gram of final resin. The acid value is determined according to ASTM D1639 standards.

**EXAMPLE 1: preparation of I) wherein  $R_f$  has formula II**


In a 1 l flask 245 ml of methacrylic anhydride (1.54 moles), 0.5 g of hydroquinone, 1 ml of pyridine are charged and heated up to 80°C, then 820 g of fluorinated alcohol (III) with M.W. 709 (1.16 moles) are dripped in, the temperature being kept at the same value for 14 hours. The mixture is cooled to 50°C, 50 ml of methanol are introduced and stirring is continued for one hour. One distils at atmospheric pressure and then under vacuum (about 1 mm Hg) at 70°C; 913 g of a cloudy liquid product are obtained. After filtration through a 0.45 micron membrane of PTFE, a limpid product is obtained, still containing, at 1H-NMR examination, hydrogenated impurities. The product is treated with perfluoroheptane and methanol; there are two phases: the lower phase mainly contains the methacrylate, without hydrogenated product, of formula



with  $m/n = 27.6$  and M.W. = 777 ( $^{19}F$  and  $^1H$  NMR analysis), obtained as residue at 50-55°C/5 mbar.

**EXAMPLE 2: preparation of I) wherein  $R_f$  has formula II**


In a 500 ml flask 0.5 moles of a fluorinated alcohol (III) of M.W. 550 are added in 4 hours to a mixture of 1 mole of methacryloyl chloride and 0.5 ml of pyridine, kept at 50°C. Gaseous HCl develops immediately. Reaction is continued still 30 minutes after the dripping is over, then methacryloyl chloride in excess is distilled with the boiler at 50-60°C under vacuum (about 10 mm Hg). 305 g of a slightly cloudy product are obtained, which are filtered through 0.45 micron membrane of PTFE: a colourless limpid product is obtained, represented by the formula



with  $m/n = 40$  and M.W. 618 ( $^1H$  and  $^{19}F$  NMR analysis).

**EXAMPLE 3: preparation of I) wherein  $R_f$  has formula II)**


With the same technique of Example 2, one operates with a fluorinated alcohol (3) at M.W. 600; a colourless limpid product is obtained, represented by the formula



with  $m/n = 40$  and M.W. 654 ( $^1H$  and  $^{19}F$  NMR analysis).

**EXAMPLE 4: preparation of I) wherein  $R_f$  has formula II)**

With the same technique of Example 2, one operates with a fluorinated alcohol (III) at M.W. 650; a colourless limpid product is obtained, represented by the formula



with  $m/n = 40$  and M.W. 702 ( $^1H$  and  $^{19}F$  NMR analysis).

**EXAMPLE 5: Polymers of I)**

100 g of methacrylate I of Example 2, 200 g of m-hexafluoroxylene and 0.1 g of AIBN are charged in a glass vial, cooled in a dry ice-acetone bath, degassed and sealed. The sealed vial is maintained in a thermostatic bath at the constant temperature of 60°C for 8 hours; then the reaction mixture is poured into oil ether and the resulting precipitate is filtered and dried at 50°C for 24 hours at a pressure of 10 mm Hg. 95 g of a transparent polymer are recovered.

**EXAMPLE 6: Polymers of I)**

With the same process of Example 5, 100 g of methacrylate of Example (IV) are polymerized; 93 g of transparent polymer are recovered.

**EXAMPLE 7 (comparative) Polymers of I)**

With the same modalities of Example 5, 100 g of methacrylate of the fluorinated alcohol (III) with p=O, with M.W. = 550, are polymerized; 75 g of transparent polymer are recovered.  
The yield is lower compared with Example 5.

**EXAMPLE 8 (comparative) Polymers of I)**

With the same modalities of Example 5, 100 g of methacrylate of the fluorinated alcohol (III) with p=O, with M.W. = 650, are polymerized; 72 g of transparent polymer are recovered.  
Same considerations for the yield as in Example 7 are valid.

**EXAMPLE 9: Copolymers of I)**

63 g (0.105 moles) of the methacrylate of Example 5, 27 g of MMA (0.27 moles), 200 g of MIBK and 1 g of AIBN are charged in a glass vial, cooled in a dry ice-acetone bath, degassed and sealed. The sealed vial is maintained in a thermostatic bath at the constant temperature of 60°C for 8 hours. The reaction mixture is then poured into ligroin and the resulting precipitate is filtered and dried at 50°C for 24 hours at the pressure of 10 mm Hg. 97 g of transparent polymer are recovered. The polymer is analyzed by <sup>19</sup>F-NMR revealing that the molar composition between methacrylate of the fluorinated alcohol and MMA is 23/77. The polymer has an intrinsic viscosity of 0.98 dl/g, measured at the temperature of 35°C by using m-hexafluoroxylene as solvent.

**EXAMPLES 10-19: Preparation of the resins**

100 g of MIBK solvent are heated under nitrogen flow up to 105°C; the polymerization initiator (AIBN) and the monomers mixture (100 g) having the composition shown in Table 1 are then added, in a period of 4 hours; and the polymerization is carried out at the same temperature for 2 hours.

**EXAMPLES 20(1) to 20(10): Preparation of coatings**

On an aluminium support, treated with zinc phosphate, the compositions by grams reported in Table 2A are applied, left at room temperature for 5 minutes and then crosslinked according to the following modalities: for 30' at T = 150°C for examples 20(1), 20(4), 20(7) and 20(8); for 60' at T = 80°C for the remaining examples. Films of a 30 micron thickness are obtained. On the so obtained films the following evaluation tests reported in Table 2 B are carried out:

- MEK test: the surface of the coated sample is submitted to repeated rubbing by a pad soaked in MEK; the number of double strokes not causing removal of the film is reported;
- Adhesion according to ASTM D 3359 standard;
- Pencil hardness according to ASTM D 3363 standard;
- Bending test according to ASTM D 552 standard;
- Gloss according to ASTM D 523 standard;
- QUV test according to ASTM D 53 standard: UV cycles of 8 h at T = 60°C, 4 h of condensation at T = 40°C. The measurement is carried out after 1000 hours of exposure.

TABLE 1

Composition	Examples									
	10	11	12	13	14	15	16	17	18	19
MMA (methylmethacrylate)	26	51	41	41	38	58.5	40	40	40	40
BMA (butylmethacrylate)								43.4		44.4
HEMA (hydroxy-ethylmethacrylate)	11	11	9	9	8	7.5	15	15.6	15.6	15.6
MAA (methacrylic acid)							1	1		
(I) (of Example 2)	63	58	50	50	54	34	34	-	44.4	
AIBN	1	1	1	2	3	3	2	2	2	2
OH Value (KOH mg/resin g)	45	44	38	38	34	32	72	67	68	67
Acid Value (KOH mg/resin g)	0	0	0	0	0	0	7.2	8	0	0
Mn (GPC) (number average molecular weight)	2000	16000	14500	9000	6300	8800	7200	8400	7000	8500

TABLE 2 A: Preparation

Components	Examples									
	20 (1)	20 (2)	20 (3)	20 (4)	20 (5)	20 (6)	20 (7)	20 (8)	20 (9)	20 (10)
Example 10	70									
Example 11		86.8								
Example 12			88							
Example 13				70						
Example 14					89.4					
Example 15						90				
Example 16							70			
Example 17								70		
Example 18									81	
Example 19										81
HMTM	15			15			15	15		
N 3300		6.6	6		5.3	5			9.5	9.5
Xylene	15	6.6	6	15	5.3	5	15	15	9.5	9.5

HMTM= hexamethoxymethylmelamine

N3300= hexamethylendiisocyanatetrimer




TABLE 2 B: Properties

	Examples									
	20 (1)	20 (2)	20 (3)	20 (4)	20 (5)	20 (6)	20 (7)	20 (8)	20 (9)	20 (10)
Composition										
MEK Test	>100	> 100	>100	>100	>100	>100	>100	>100	>100	>100
Adhesion	100	100	100	100	100	100	100	95	100	95
Hardness	F-2H	H-4H	F-3H	H-4H	F-2H	H-4H	H-5H	2H-3H	HB-4H	2H-3H
Bending test	passes	passes	passes	passes	passes	passes	passes	passes	passes	passes
Gloss	80	83	86	85	80	85	85	86	84	85
QUV: gloss retention %	100	100	100	100	100	100	100	75	100	80

## Claims

1. A Perfluoropolyether containing (meth)acrylic groups obtainable by copolymerization of:

a) 1 - 50% by weight of a monomer having general formula:



wherein Y = F, Cl, CF<sub>3</sub>, C<sub>2</sub>F<sub>5</sub>, C<sub>3</sub>F<sub>7</sub>, C<sub>4</sub>F<sub>9</sub>; and X = F, CF<sub>3</sub>; p is an integer from 1 to 5; R<sub>f</sub> represents a radical having perfluoropolyether structure of average molecular weight of from 400 to 3000, formed by sequence of oxyfluoroalkylenic units; and R = H, CH<sub>3</sub>;

b) 40 - 90% by weight of one or more monomer(s) of formula




wherein R<sub>1</sub> = H, CH<sub>3</sub>, F, Cl; A is an alkyl radical having from 1 to 12 carbon atoms or a fluoroalkyl radical having from 1 to 10 carbon atoms, or an aliphatic or aromatic cyclic group having from 6 to 8 carbon atoms; and

c) 2 - 30% by weight of one or more monomer(s) of formula:



wherein R<sub>1</sub> has the same meaning described above; W = O, NH; B = H, (CH<sub>2</sub>)<sub>s</sub>B<sub>1</sub> with s = 1 - 5, B<sub>1</sub> = -COOH, -OH, -CH=CH<sub>2</sub>, NCO, -CO-CH<sub>2</sub>CO-CH<sub>3</sub>, -Si(OR<sub>2</sub>)<sub>3</sub> with alkylic R<sub>2</sub> groups having from 1 to 5 carbon atoms; the sum of the monomers a), b) and c) being equal to 100.

2. The perfluoropolyether according to claim 1, wherein R<sub>f</sub> is formed by the



and (CFXO) units wherein X has the meaning of claim 1.

3. The perfluoropolyether according to claim 2, wherein R<sub>f</sub> is (C<sub>3</sub>F<sub>6</sub>)<sub>m</sub> (CFXO)<sub>n</sub> where m/n is  $\leq 2$ , m and n being integers.

4. Coatings obtainable by the perfluoropolyether according to anyone of the preceding claims from 1 to 3.


5. Coatings according to claim 4 wherein the perfluoropolyether is crosslinked.

6. Use of the coating according to claim 5 as top-coat.

## Patentansprüche

1. Perfluoropolyether, welcher (Meth)Acryl-Gruppen enthält, erhältlich durch Copolymerisation von:

a) 1 - 50 Gew.-% eines Monomeren mit der allgemeinen Formel:



wobei Y = F, Cl, CF<sub>3</sub>, C<sub>2</sub>F<sub>5</sub>, C<sub>3</sub>F<sub>7</sub>, C<sub>4</sub>F<sub>9</sub>; und X = F, CF<sub>3</sub>; p eine ganze Zahl von 1 bis 5 ist; R<sub>f</sub> für einen Rest mit Perfluoropolyetheral-Struktur mit einem mittleren Molekulargewichts von 400 bis 3000 steht, welcher durch eine Sequenz von Oxyfluoralkylen-Einheiten gebildet ist; und R = H, CH<sub>3</sub>;

b) 40 bis 90 Gew.-% eines oder mehrerer Monomere(n) der Formel:




wobei R<sub>1</sub> = H, CH<sub>3</sub>, F, Cl; A ein Alkylrest mit 1 bis 12 Kohlenstoffatomen oder ein Fluoralkylrest mit 1 bis 10 Kohlenstoffatomen oder eine aliphatische oder aromatische cyclische Gruppe mit 6 bis 8 Kohlenstoffatomen ist; und

c) 2 - 30 Gew.-% eines oder mehrerer Monomere(n) der Formel:



wobei  $\text{R}_1$  dieselbe Bedeutung wie oben hat;  $\text{W} = \text{O}, \text{NH}$ ;  $\text{B} = \text{H}, (\text{CH}_2)_s\text{B}_1$  mit  $s = 1 - 5$ ,  $\text{B}_1 = -\text{COOH}, -\text{OH}, -\text{CH}=\text{CH}_2, \text{NCO}, -\text{CO}-\text{CH}_2\text{CO}-\text{CH}_3, -\text{Si}(\text{OR}_2)_3$  mit alkyischen  $\text{R}_2$ -Gruppen mit 1 bis 5 Kohlenstoffatomen, wobei die Summe der Monomeren a), b) und c) gleich 100 ist.

2. Perfluoropolyether gemäß Anspruch 1, wobei  $\text{R}_f$  aus den



(CFXO)-Einheiten gebildet ist, wobei X die Bedeutung aus Anspruch 1 hat.

3. Perfluoropolyether gemäß Anspruch 2, wobei  $\text{R}_f$  gleich  $(\text{C}_3\text{F}_6)_m(\text{CFXO})_n$  ist, wobei  $m/n \geq 2$ , wobei m und n ganze Zahlen sind.

4. Beschichtungen, welche mittels des Perfluoropolyethers gemäß einem der vorhergehenden Ansprüche 1 bis 3 erhältlich sind.


5. Beschichtungen gemäß Anspruch 4, wobei der Perfluoropolyether quervernetzt ist.

6. Verwendung der Beschichtung gemäß Anspruch 5 als Deckschicht.

## Revendications

1. Perfluoropolyéther contenant des groupes (méth)acryliques, pouvant être obtenu par copolymérisation de :

(a) 1-50% en poids d'un monomère ayant la formule générale :



dans laquelle :

- $\text{Y} = \text{F}, \text{Cl}, \text{CF}_3, \text{C}_2\text{F}_5, \text{C}_3\text{F}_7, \text{C}_4\text{F}_9$  ; et
- $\text{X} = \text{F}, \text{CF}_3$  ;
- p est un entier de 1 à 5 ;
- $\text{R}_f$  représente un radical ayant une structure perfluoropolyéthérée de masse moléculaire moyenne de 400 à 3000, formée par une succession d'unités oxyfluoroalkyléniques ; et
- $\text{R} = \text{H}, \text{CH}_3$  ;

(b) 40-90% en poids d'un ou plusieurs monomère(s) de formule :



dans laquelle :

- $\text{R}_1 = \text{H}, \text{CH}_3, \text{F}, \text{Cl}$  ;
- A est un radical alkyle ayant de 1 à 12 atomes de carbone ou un radical fluoroalkyle ayant de 1 à 10 atomes de carbone, ou un groupe cyclique aliphatique ou aromatique ayant de 6 à 8 atomes de carbone ; et

(c) 2-30% en poids d'un ou plusieurs monomère(s) de formule :




dans laquelle :

- $\text{R}_1$  a la même signification que celle décrite ci-dessus ;

- W = O, NH ;
- B = H, (CH<sub>2</sub>)<sub>s</sub>B<sub>1</sub> avec s = 1-5, B<sub>1</sub> = -COOH, -OH, -CH=CH<sub>2</sub>, NCO, -CO-CH<sub>2</sub>CO-CH<sub>3</sub>, -Si(OR<sub>2</sub>)<sub>3</sub> avec des groupes R<sub>2</sub> alkyls ayant de 1 à 5 atomes de carbone ;

la somme des monomères (a), (b) et (c) étant égale à 100.

2. Perfluoropolyéther selon la revendication 1, dans lequel R<sub>f</sub> est formé par les unités



et (CFXO), où X a la signification de la revendication 1.

3. Perfluoropolyéther selon la revendication 2, dans lequel R<sub>f</sub> représente (C<sub>3</sub>F<sub>6</sub>)<sub>m</sub>(CFXO)<sub>n</sub>, où m/n est ≥ 2, m et n étant des entiers.

4. Revêtements pouvant être obtenus par le perfluoropolyéther tel que défini à l'une quelconque des revendications précédentes 1 à 3.

5. Revêtements selon la revendication 4, dans lesquels le perfluoropolyéther est réticulé.

6. Utilisation du revêtement tel que défini à la revendication 5 comme couche de finition.