Europäisches Patentamt European Patent Office Office européen des brevets



EP 0 715 209 A3 (11)

(12)

EUROPEAN PATENT APPLICATION

- (88) Date of publication A3: 18.09.1996 Bulletin 1996/38
- (43) Date of publication A2: 05.06.1996 Bulletin 1996/23
- (21) Application number: 95118565.1
- (22) Date of filing: 24.11.1995
- (84) Designated Contracting States: **DE FR GB**
- (30) Priority: 25.11.1994 JP 314226/94
- (71) Applicant: FUJI PHOTO FILM CO., LTD. Kanagawa-ken (JP)

(51) Int. Cl.⁶: **G03C 1/498**, G03C 8/40, G03C 5/16

- (72) Inventor: Sawada, Satoru Minami Ashigara-shi, Kanagawa-ken (JP)
- (74) Representative: Grünecker, Kinkeldey, Stockmair & Schwanhäusser Anwaltssozietät Maximilianstrasse 58 80538 München (DE)

(54)Heat-developable color light-sensitive material

(57) Described is a heat developable color lightsensitive material comprising a support having provided thereon at least two layers having a spectral sensitivity peak in a different wavelength range of 700 nm or more, in which the at least two layers are each combined with a compound which provides a dye having a different hue, wherein the layer having a spectral sensitivity peak in the longest wavelength and/or a light-insensitive interlayer adjusted thereto comprises (a) a high silver chloride emulsion of fine grains having a silver chloride content of 80 mol% or more and an average size of 0.15 μm or less or (b) an easily soluble silver salt compound.



EUROPEAN SEARCH REPORT

Application Number EP 95 11 8565

B		
DIEL DO		
DIEL DO		
DIEL DO		
FIELDS (Int.Cl.6)		
~		
T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons		