

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 735 151 B2

(12)

NEW EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the opposition decision:
31.08.2005 Bulletin 2005/35

(51) Int Cl.7: **C22C 16/00, G21C 3/07**

(45) Mention of the grant of the patent:
21.04.1999 Bulletin 1999/16

(21) Application number: **96300381.9**

(22) Date of filing: **19.01.1996**

(54) **Alloy for improved corrosion resistance of nuclear reactor components**

Legierung zur Verbesserung der Korrosionsbeständigkeit von Kernreaktorbauteile

Alliage à résistance à la corrosion améliorée pour composants de réacteur nucléaire

(84) Designated Contracting States:
DE FR SE

(30) Priority: **28.03.1995 US 412499**

(43) Date of publication of application:
02.10.1996 Bulletin 1996/40

(73) Proprietor: **GENERAL ELECTRIC COMPANY**
Schenectady, NY 12345 (US)

(72) Inventors:
• **Adamson, Ronald B.**
Fremont, California 94536 (US)
• **Cheng, Bo-Ching**
Cupertino, California 95014 (US)

(74) Representative: **Tomlinson, Edward James et al**
Frohwitter
Patent- und Rechtsanwälte
Possartstrasse 20
81679 München (DE)

(56) References cited:
EP-A- 0 405 172 DE-B- 1 161 694
US-A- 4 992 240

• **B.T.K. BARRY AND C.J. THWAITES: "Tin and its**
Alloys and Compounds", ELLIS HORWOOD
LIMITED , CHICHESTER, GB XP002007543
Zircalloys * page 232 *

EP 0 735 151 B2

DescriptionField of the Invention

[0001] This invention generally relates to alloys useful in making nuclear reactor components. In particular, the invention relates to zirconium-based alloys useful in making components such as fuel channels, fuel cladding and fuel rod spacers in a light water nuclear reactor.

Background of the Invention

[0002] A boiling water reactor (BWR) has nuclear fuel assemblies comprising bundles of fuel rods made of fissionable materials capable of releasing a finite number of neutrons. Neutrons are released due to fission at high speed and then moderated by the water to a lower speed at which the neutrons can produce a chain reaction of fission events. Each fuel assembly is surrounded by a tubular flow channel (hereinafter "fuel channel") made of metal. These fuel channels are elongated tubular components which can parasitically absorb neutrons. In accordance with conventional practice, the preferred material is a zirconium-based alloy on the order of 125 mils thick. Zirconium-based alloys are used in nuclear reactors because of their low neutron absorption cross section, adequate strength and good corrosion resistance in reactor water and steam.

[0003] In-reactor dimensional stability and corrosion resistance are important attributes of reactor components such as fuel channels, fuel cladding and fuel rod spacers. To minimize parasitic absorption of neutrons, fuel channels, fuel cladding and fuel rod spacers are typically fabricated from Zircaloy, which is an alloy of zirconium with small amounts of iron, tin and other alloy metals. In particular, Zircaloy-2 contains, by weight, about 1.5% tin, 0.15% iron, 0.1% chromium, 0.05% nickel and 0.1% oxygen, whereas Zircaloy-4 contains substantially no nickel and about 0.2% iron, but otherwise is similar to Zircaloy-2. High corrosion resistance for the Zircaloys is conventionally obtained by heating the channel material to an elevated temperature followed by fast quenching, e.g., by inductive heating and water quenching.

[0004] As reactor designs are changed to require longer lives of core components such as fuel channels and fuel cladding, there is a need to use alloys having improved properties, particularly resistance to corrosion and hydriding (absorption of hydrogen) in a boiling water reactor, as compared to the Zircaloys and other zirconium-based alloys conventionally used. A tendency toward hydriding in zirconium alloys is known to be detrimental due to embrittlement.

Summary of the Invention

[0005] The present invention is an alloy as defined by the accompanying claim. This alloy has an improved combination of resistance to corrosion and hydriding, and good strength and fabricability. These properties make the new alloy exceptionally suited for use in BWR components such as fuel channels, fuel cladding and fuel rod spacers.

[0006] The alloys of this invention are zirconium-based alloys according to the claim. The term "remainder zirconium" as used herein means zirconium is the predominant element comprising the remaining weight percentage. However, other elements which do not interfere with the achievement of the improved corrosion and hydriding resistance and good strength and ductility of the inventive alloys may be present either as impurities normally occurring in reactor grade sponge zirconium or at non-interfering levels. For example, the impurities occurring in reactor grade sponge zirconium consist of the following substances in the contents stated: aluminum, 75 ppm or less; boron, 0.4 ppm or less; cadmium, 0.4 ppm or less; carbon, 270 ppm or less; chromium, 200 ppm or less; cobalt, 20 ppm or less; copper, 50 ppm or less; hafnium, 100 ppm or less; hydrogen, 25 ppm or less; iron, 1500 ppm or less; magnesium, 20 ppm or less; manganese, 50 ppm or less; molybdenum, 50 ppm or less; nickel, 70 ppm or less; niobium, 100 ppm or less; nitrogen, 80 ppm or less; silicon, 120 ppm or less; tin, 50 ppm or less; tungsten, 100 ppm or less; titanium, 50 ppm or less; and uranium, 3.5 ppm or less. Preferably, the alloys of this invention have 500-2000 ppm O₂ and are substantially nickel free. The term "substantially nickel free" as used herein means that the alloys contain only trace amounts of nickel, i. e., 70 ppm Ni or less.

Detailed Description of the Preferred Embodiments

[0007] An alloy of this invention comprised of 1.0% Sn, 1.2% Cr and 0.1% Fe. Further preferred alloys have 500-2000 ppm O₂. Still further preferred alloys are substantially nickel free.

Examples

[0008] A number of zirconium-based alloys were formed having the compositions given in Table 1 below

TABLE 1

Alloy	Elemental Composition* (wt.%)		
	Sn	Cr	Fe
V	0	1.2	0.1
VA	1.0	1.2	0.1
VB	0.5	1.0	0.5
Zirc-2†	1.5	0.1	0.15

* O₂ in each alloy was 500-2000 ppm.

† Also includes 0.05% Ni.

[0009] The foregoing alloys were fabricated into flat sheets, cut into coupons and irradiated in a boiling water reactor for two full reactor cycles. The fluence achieved by the coupons was $(2-4) \times 10^{25}$ neutrons/m². Corrosion performance data for alloys V, VA and VB are given below. Comparison is also given to Zircaloy-2, which is the standard material used for BWR fuel components such as cladding and channels.

[0010] The weight gain in the coupons as the result of irradiation in the reactor for two full cycles was measured and is shown in Table 2 below.

TABLE 2

Alloys of This Invention	Alloys Not of This Invention	Corrosion Weight Gain (mg/dm ²)
-	V	70-783
VA	-	41-54
VB	-	45-55
-	Zirc-2	54-113

[0011] The weight gain is a measure of corrosion performance, with increasing weight gain showing an increase in corrosion and therefore poorer resistance to corrosion. The data in Table 2 illustrate that the corrosion resistance of alloys VA and VB made in accordance with the present invention was superior to that of Zircaloy-2 and other alloys outside the scope of the present invention.

[0012] In addition, the level of hydriding in two of the irradiated Zircaloy-2 coupons was 23 and 133 ppm H₂ respectively. In contrast, one of the irradiated coupons made from alloy VB of this invention had a level of <10 ppm H₂. Low weight gain and low hydriding are good attributes for zirconium-based alloys subjected to the environment in a nuclear reactor core.

[0013] The corrosion weight gain data in Table 2 further shows that coupons of alloy V (not of this invention) have high and variable corrosion in high-temperature water in a boiling water reactor. The addition of tin to alloy V in amounts of 0.1 to 1.0 wt.%, as in the alloy of this invention, decreases the magnitude and variability of corrosion, as demonstrated by the lower corrosion weight gain data for alloys VA and VB of this invention.

[0014] Table 3 lists data from measurements of various mechanical properties of unirradiated and irradiated specimens made from sheets of Zircaloy-2, alloy VA and alloy VB. The data in Table 3 show that irradiated alloy VA and irradiated alloy VB are stronger (UTS) and have higher ductility (UE and TE) than Zircaloy-2.

TABLE 3

Specimen No.	Fluence (10^{25} n/m ²)	UTS*(MPa)	UE †(%)	TE‡ (%)	Flow Stress Drop
Alloy VA					
3A	0	406.5	6.2	32.4	Gradual
3B	0	390.7	8.9	33.9	Gradual
3C	2.65	751.0	2.4	16.1	Rapid
3D	2.65	736.5	2.2	15.5	Rapid
Alloy VB					
BA	0	388.6	8.3	36.5	Gradual
BB	0	385.2	7.9	33.2	Gradual
BC	3.95	828.2	3.9	18.4	Gradual
BD	3.95	828.2	3.9	17.6	Gradual
Zircaloy-2					
2-110	2.48	725.0	2.6	20.6	Gradual
2-112	2.48	654.0	0.4	14.8	Rapid
2-114	2.48	683.0	1.1	16.9	Rapid

*UTS = ultimate tensile strength.

† UE = uniform elongation.

‡ TE = total elongation.

[0015] In summary, the alloy of the invention has an improved combination of resistance to corrosion and hydriding, and improved post-irradiation strength and ductility, as compared to Zircaloy-2. Accordingly, alloys having an elemental composition in accordance with the invention are suitable for use in BWR components which are exposed to high levels of neutron fluence, such as fuel channels, fuel cladding and fuel rod spacers.

Claims

1. A zirconium-based alloy having a composition consisting of, by weight, 1.0% tin, 1.2% chromium and 0.1% iron, optionally 500-2000 ppm O₂ and the remainder zirconium and inevitable impurities.

Patentansprüche

1. Legierung auf Zirkoniumgrundlage mit einer Zusammensetzung, bestehend aus, bezogen auf das Gewicht, 1,0% Zinn, 1,2% Chrom und 0,1% Eisen, gegebenenfalls 500-2.000 ppm O₂, Rest Zirkonium und unvermeidbare Verunreinigungen

Revendications

1. Alliage à base de zirconium présentant une composition, exprimée en poids, qui comprend de 1,0% d'étain, de 1,2% de chrome, et 0,1% de fer, éventuellement de 500-2000 ppm d'O₂, et des impuretés inévitables, le reste étant constitué de zirconium.