



(11) **EP 0 743 047 B9**

(12) **CORRECTED NEW EUROPEAN PATENT SPECIFICATION**

Note: Bibliography reflects the latest situation

(15) Correction information:
Corrected version no 1 (W1 B2)
Corrections, see
Claims EN

(51) Int Cl.:
A61F 2/01 (2006.01) **A61B 17/12** (2006.01)
B29C 53/60 (2006.01) **B29C 61/00** (2006.01)

(48) Corrigendum issued on:
19.12.2007 Bulletin 2007/51

(45) Date of publication and mention
of the opposition decision:
27.06.2007 Bulletin 2007/26

(45) Mention of the grant of the patent:
19.11.2003 Bulletin 2003/47

(21) Application number: **96302744.6**

(22) Date of filing: **19.04.1996**

(54) **Anatomically shaped vasoocclusive device and method of making same**

Anatomisch geformte Vorrichtung zur Gefäßokklusion sowie deren Herstellungsverfahren

Dispositif de vaso-occlusion de forme anatomique, et son procédé de fabrication

(84) Designated Contracting States:
DE FR GB NL

(30) Priority: **20.04.1995 US 425106**

(43) Date of publication of application:
20.11.1996 Bulletin 1996/47

(60) Divisional application:
03078597.6 / 1 402 847

(73) Proprietor: **Micrus Corporation**
Mountain View,
California 94043 (US)

(72) Inventor: **Horton, Joseph A.**
Charleston,
South Carolina 29401-1725 (US)

(74) Representative: **McLeish, Nicholas Alistair**
Maxwell et al
Boult Wade Tennant
Verulam Gardens
70 Gray's Inn Road
London WC1X 8BT (GB)

(56) References cited:
EP-A- 0 747 013 **EP-A- 0 765 636**
WO-A-94/09705 **WO-A-94/10936**
WO-A1-93/16650 **DE-A- 3 203 410**
DE-U- 9 205 797 **JP-A- 7 000 406**
US-A- 5 108 407 **US-A- 5 217 484**
US-A- 5 334 210

- **Arterioembolization with shape memory angioembolus. Experimental study and clinical application - C.C. Zhang Zhonghua Waike Zazhi [Chinese Journal of Surgery], February 1992, vol. 30, no.2, pages 111-4.**

EP 0 743 047 B9

Description

Field of the Invention

[0001] This invention relates to the field of vasoocclusive devices. More particularly, it relates to a vasoocclusive device which, as used, is in the approximate shape of an anatomical cavity. The devices may be ultimately deployed through a catheter.

Background of the Invention

[0002] Vasoocclusion devices are surgical implants that are placed within the vasculature of the human body, typically via a catheter, either to block the flow of blood through a vessel making up that portion of the vasculature through the formation of an embolus or to form such an embolus within an aneurysm stemming from the vessel. One widely used vasoocclusive device is a helical wire coil having windings which may be dimensioned to engage the walls of the vessels. Other less stiff helically coiled devices have been described, as well as those involving woven braids.

[0003] For instance, U.S. Patent No. 4,994,069, to Ritchart et al., describes a vasoocclusive coil that assumes a linear helical configuration when stretched, and assumes a folded, convoluted configuration when relaxed. The stretched configuration is used in placing the coil at the desired site, eg. by its passage through a catheter. Once the device is so placed, the coil assumes a relaxed configuration, which is better suited to occlude the vessel. Ritchart et al describes a variety of shapes. The secondary shapes of the disclosed coils include "flower" shapes and double vortices. A random shape is described, as well. These prior vasoocclusive devices do not maintain a three-dimensional conformation for a satisfactory period of time; the coils collapsing in upon themselves to form mere rings. A useful substantially spherical vasoocclusive device has heretofore not been made available.

[0004] DE 32 03 410A describes an occlusive device comprising one member or strand (1) of a flexible material such that the device is moveable between an inoperable elongated configuration (Fig. 1) for insertion into and through a means for delivering the device to a cavity, and an operable substantially cylindrical coil configuration (Fig. 7) of variable diameter in which the member forms a supporting frame to a hollow chamber and in which the device is capable of occluding at least a portion of said cavity. However, the cylindrical coil is open at each of its opposite axial ends.

[0005] In contrast, in the device of the present invention, when distended to its operative configuration takes the form of a skeletal cage-like structure of substantially spherical form.

[0006] Vasoocclusive coils having attached fibrous elements in a variety of secondary shapes are shown in US Patent No 5,304,194 to Chee et al. Chee et al de-

scribes a helically wound device having a secondary shape in which the fibrous elements extend in a sinusoidal fashion down the length of the coil. These coils, as with Ritchart et al, are produced in such a way that they will pass through the lumen of a catheter in a generally straight configuration, and when released from the catheter, form a relaxed and folded shape in the lumen or cavity chosen within the human body. The fibrous elements shown in Chee et al enhance the ability of the coil to fill the space within the vasculature and to facilitate formation of embolus and subsequent allied tissue.

[0007] There are a variety of ways of discharging shaped coils and linear coils into the human vasculature. In addition to those patents which apparently describe only the physical pushing of a coil out into the vasculature (eg. Ritchart et al), there are a number of other ways to release the coil at a specifically chosen time and site. US Patent No. 5,354,295 and its parent, 5,122,136, both to Guglielmi et al, describe an electrolytically detachable embolic device.

[0008] A variety of mechanically detachable devices are also known. For instance, U.S. Patent No. 5,234,437, to Sepetka, shows a method of unscrewing a helically wound coil from a pusher having interlocking surfaces. U.S. Patent No 5,250,071, to Palermo, shows an embolic coil assembly using interlocking clasps mounted both on the pusher and on the embolic coil. U.S. Patent No. 5,261,916, to Engelson, shows a detachable pusher-vasoocclusive coil assembly having an interlocking ball and keyway-type coupling. U.S. Patent No. 5,304,195, to Twyford et al., shows a pusher-vasoocclusive coil assembly having an extending wire carrying a ball on its proximal end and a pusher having a similar end. The two ends are interlocked and disengage when expelled from the distal tip of the catheter. U.S. Patent No. 5,312,415, to Palermo, also shows a method for discharging numerous coils from a single pusher by use of a guidewire which has a section capable of interconnecting with the interior of the helically wound coil. U.S. Patent No. 5,350,397, to Palermo et al., shows a pusher having a throat at its distal end and a pusher through its axis. The pusher sheath will hold onto the end of an embolic coil and will then be released upon pushing the axially placed pusher wire against the member found on the proximal end of the vasoocclusive coil.

[0009] Vasoocclusive coils having little or no inherent secondary shape have also been described. For instance, in U.S. Patent No. 5,690,666 by Berenstein et al., is found a coil having little or no shape after introduction into the vascular space.

[0010] Common to all of these devices above is the characteristic of lacking a spheroid shape when relaxed. Additionally, the concept of a plurality of concentrically nested spherical vasoocclusive devices is lacking in the prior art.

SUMMARY OF THE INVENTION

[0011] One aspect of the present invention provides an occlusive device having the features of claim 1.

[0012] According to a feature of this aspect of the invention, the strand may be helical in shape and optionally, further may comprise a safety strand inserted longitudinally through said helical shape. The device may comprise a first strand and a second strand which second strand is co-woven along at least a portion of the length of the first strand.

[0013] According to another feature of this aspect of the invention, the flexible material may comprise one of the following:

- (i) a metal selected from platinum, palladium, rhodium, gold, tungsten, and alloys thereof;
- (ii) an alloy of platinum and tungsten;
- (iii) an alloy selected from a stainless steel and a super-elastic alloy;
- (iv) a polymer;
- (v) an alloy of titanium and nickel; or
- (vi) an alloy of platinum.

[0014] The device may further comprise fibres attached to at least a portion of said strand. It is also preferred that said second portion is disposed concentrically within said first portion. Preferably, at least a portion of said second portion of said strand comprises a means for increasing the thrombogenicity of the device.

[0015] According to another feature of this aspect of the invention, the device further comprises a plurality of additional strand portions disposed within said cage-like structure of the first portion optionally, at least a portion of said plurality of strand portions comprises fibres attached thereto. In such constructions, said plurality of additional strand portions may be either:

- (i) concentrically disposed with each other within said cage-like structure of the first portion; or
- (ii) non-concentrically disposed with each other within said cage-like structure of the first portion.

[0016] Preferably, the means for increasing the thrombogenicity comprises fibres attached to at least a portion of said strand. The fibres may further comprise a radio-paque marker.

[0017] Yet another aspect of the invention provides a method for producing a vasoocclusive device as claimed in claim 11.

[0018] According to a feature of the method for producing the device, said first core may further comprise a circumferentially continuous groove recessed therein for releasably maintaining said strand in a substantially spherical or spheroidal configuration, and wherein heating is at about 593 degrees Celsius (1100 degrees Fahrenheit).

[0019] According to a further feature of this aspect of

the invention, wherein said second portion of said strand is disposed concentrically within the cage-like structure of the first portion and/or there are a plurality of additional portions, the additional portions optionally being disposed concentrically within each other. Preferably, means is provided on at least one portion of said strand for increasing the thrombogenicity of the device and/or the feature(s) recited in an appropriate one or more of claims 1 and 10.

[0020] The device is used simply by temporarily straightening the device into the inoperable configuration and introducing it into a suitable catheter, the catheter already having been situated so that its distal opening is within the mouth of the vascular crevice or opening to be filled. The device is then pushed through the catheter and, upon its emanation at the distal end of the catheter into the vascular cavity, assumes its relaxed operable configuration.

[0021] The device of the invention can be used in a method of occluding a desired portion of a vesicle in a patient comprising inserting into at least a portion of the vesicle the vasoocclusive device. Preferably, the method further comprises inserting into the desired portion of said vesicle a plurality of vasoocclusive devices concentrically nesting with each other when in the operably substantially spherical configuration. Said plurality of vasoocclusive devices are longitudinally attached in tandem when in the inoperable substantially elongate configuration, and preferably concentrically nesting with each other when in the operable substantially spherical configuration. Preferably, at least one said vasoocclusive device concentrically nesting within another vasoocclusive member comprises thrombogenic fibres attached to at least a portion thereof. Preferably, the vesicle is an artery and the desired portion is an aneurysm.

[0022] Embodiments of the invention will now be described, by way of example, with reference to the accompanying drawings, in which:-

Figure 1 shows a side view of a spherical device.

Figure 2 shows a side view of a device having an oval cross-section

Figure 3 shows a side view of a device using a thrombogenic fibre

Figure 4 shows a magnified section of a helical coil as could be used in the inventive device having filamentary material attached through the loop of the device.

Figure 5 shows a magnified section of a helical coil covered by an outer fibrous braided covering

Figure 6A shows a central cross-section of an embodiment having a vasoocclusive sphere covered with fibres positioned within a first vasoocclusive

sphere as it would appear when deployed within a portion of vesicle.

Figure 6B shows a side view of the embodiment shown in Figure 6A in the wound configuration, but not deployed in a vesicle.

Figure 7 shows a mandrel suitable for winding making a device according to the invention.

DETAILED DESCRIPTION OF THE INVENTION

[0023] Figure 1 shows a substantially spherical occlusive device (100) in the operable configuration. The occlusive device (100) comprises at least one strand (102) of flexible material movable between an inoperable substantially linear configuration for insertion into and through a means for delivering the device to a desired portion of a vesicle, and an operable, substantially spherical configuration for occluding at least a portion of said vesicle. Preferably, the vesicle is an artery and the desired portion is an aneurysm, however, the invention contemplates that any bodily vesicle or cavity may be occluded by the device. The strand (102) shown is wound in a tertiary substantially spherical structure so as to have multiple loops spaced generally equally to form a cavity, or cage-like structure. The rear side strand (102) loops are shown as dotted lines for clarity, however, these would be visible through the open areas of the cage. It is clearly not necessary that the tertiary shape be precisely a sphere, but it is desirable from a mechanical point of view that such a spacing be approached. The invention contemplates that the occlusive device (100) is wound into and is self-forming into a substantially spherical or distorted spherical form.

[0024] In one arrangement, it is intended that the device (100) in the operable configuration be in a roughly spherical cavity or cage-like structure where at least 90-95% of the strand (102) is in the outer 10-15 % of the diameter of the device (100). The precise number of loops of the strand will vary and depends upon the type of vesicle or cavity to be filled, and upon the length of catheter tubing necessary for deployment in the extended, linear position.

[0025] Figure 2 shows a variation in side view in which the shape of the anatomically conforming vasoocclusive device (104) is oval or egg-shaped, yet still substantially spherical in the operable configuration. Other than the final shape of the Figure 2 device (104), it is similar to that shown in Figure 1. It is of little importance which axis of the ovoid structure is the major axis and which is the minor axis. In general, it is desirable that the device (104) be constructed in such a way that the resulting relaxed device (104) have a shape similar to the cavity into which it is placed. Somewhat less spherical configurations of the device are permissible and, in many instances, even desired, depending upon the anatomical shape of the vesicle or cavity to be occluded. The substantially spher-

ical shape prevents the vasoocclusive device from collapsing upon itself. By the term "substantially spherical" is meant a shape which includes spherical as well as other distorted shapes, such as ovate, ovoid, or ellipsoid, but in any event having two orthogonal cross sections which are closed shapes having no substantially straight sides.

[0026] The material used in the occlusive device (100) may be any of a wide variety of materials. Preferably, the strand (102) is a wire constructed of a radiopaque material such as a metal or a polymer. Suitable metals and alloys for the wiring include Platinum Group metals, especially platinum rhodium, palladium, as well as tungsten, gold, silver, tantalum, and alloys of these metals. Highly preferred is a platinum/tungsten alloy.

[0027] The wire may also be of any of a wide variety of stainless steels if some sacrifice of radiopacity may be tolerated. Very desirable materials of construction, from a mechanical point of view, are materials which maintain their shape despite being subjected to high stress. Certain "super-elastic alloys" include nickel/titanium alloys (48-58 atomic % nickel, and optionally containing modest amounts of iron); copper/zinc alloys (38-42 weight % zinc); copper/zinc alloys containing 1-10 weight % of beryllium, silicon, tin, aluminum, or gallium; or nickel/aluminum alloys (36-38 atomic % aluminum). Particularly preferred are the alloys described in U.S. Patent Nos. 3,174,851; 3,351,463; and 3,753,700. Especially preferred is the titanium/nickel alloy known as nitinol. These are very sturdy alloys which will tolerate significant flexing without deformation even when used as a very small diameter wire. Additionally, the strand may be constructed of a polymer, such as polyvinyl alcohol foam, for example.

[0028] Generally speaking, when the device (100) is formed of a metal such as platinum or a super-elastic alloy such as nitinol, the diameter of the wire used in the production of the coil will be in the range of 0.0127mm to 0.1524mm (0.0005 and 0.006 inches). The wire of such diameter is typically then wound into a coil having a primary diameter of between 0.127mm and 0.4572mm (0.005 and 0.018 inches). The preferable diameter is 0.254mm to 0.4572mm (0.010 to 0.018 inches). The wire should be of sufficient diameter to provide a hoop strength to the resulting device sufficient to hold the device (100) in place within the chosen body cavity without distending the wall of the cavity and without moving from the cavity as a result of the repetitive fluid pulsing found in the vascular system. Obviously, should a super-elastic alloy such as nitinol be used, the diameter of the coil wire can be significantly smaller than that used when the relatively ductile platinum or platinum/tungsten alloy is used as the material of construction. Finally, as regards Figure 1, the overall diameter of the device (100) in the operable configuration is generally between 3 and 40 millimeters. Most aneurysms within the cranial vasculature can be treated by one or more devices having those diameters.

[0029] As can be seen in Figure 3, the occlusive strand (107) may be adapted with fibers (108) such as synthetic

radiolucent fibers or polymers (or metallic threads coated with radiolucent or radiopaque fibers) such as dacron (polyester), polyglycolic acid, polylactic acid, fluoropolymers (polytetrafluoro-ethylene), nylon (polyamide), or even silk. Natural fibers such as silk, cotton or wool may also be employed. Should a fiber be used as the major component of the strand (102), it is desirably filled with some amount of a known radiopaque material such as powdered tantalum, powdered tungsten, bismuth oxide, barium sulfate, and the like.

[0030] The fibrous elements incorporated into the braid may be a bundle of individual fibers, e.g., between 5 and 100 fibers per fibrous bundle, preferably 20-30 fibers per bundle, or may be monofilaments. As was noted above, it may be desirable in certain circumstances to add fibrous materials outlying the vasoocclusive core so to provide additional bulk and area for creation of thrombosis.

[0031] Figure 4 shows a magnified side view of a helically coiled vasoocclusive strand (110) as may be used in the variations of the invention. Shown attached to the coiled vasoocclusive strand (110) are fibrous polymeric materials (112, 114) attached to the member (110) by distinct two methods. First is a series of looping fibers (112), which are looped through or tied to the strand (110) and continue axially down the coil. Another variation is the tuft (114) shown tied or otherwise affixed to the strand (110). Tufts (114) are tied at multiple sites through the coiled strand (110) so to provide a vast area of thrombus forming sites

[0032] The occlusive strand (110) in Figure 4 is shown to have a secondary structure of helically wound flexible material. The helixes provide further support to the substantially spherical form when in the operable configuration. In another variation of the invention in which the device can comprise a plurality of small, braided strands (not shown). The strands can be braided elements made partially of regularly or randomly included radiopaque wires. Again, the braid may optionally be partially woven of, or co-woven with, fibers. The wire or fibers used in the production of the braid will typically be fairly small, e.g., in the range of 0.0127mm to 0.0381 mm (0.0005 to 0.0015 inches). The resulting woven braid diameter will normally be 0.2032mm to 0.4572mm (0.008 to 0.018 inches). The braided structure is typically not as compliant as is that of a coiled secondary structure. Consequently, a more ductile material such as platinum may be preferable in such a device. The braid structure permits introduction of natural or synthetic fibrous materials such as Dacron and the other filaments noted below which promote formation of a thrombus.

[0033] Additionally, the invention contemplates that a safety wire (not shown) may be inserted through the longitudinal axis of the helically coiled strand to provide structural support. Alternatively, the safety wire may be first formed to be flexibly disposed in a substantially spherical form, and then inserted through the longitudinal axis of a helically coiled strand which has not been pre-

formed in a substantially spherical form.

[0034] Figure 5 shows still another variation and method for increasing the thrombogenic capability and rate of the device. Figure 5 shows an embolic, helically shaped strand (116) co-woven with and covered by a fibrous braid (118). One method for producing the variation shown in Figure 5 is described in U.S. Patent Nos. 5,226,911 and 5,304,194 to Chee. One manner of producing the variation shown in Figure 5 is described in U.S. Patent No. 5,382,259 to Phelps and Vann. One manner of making a co-woven braid using radiopaque fibers is shown in U.S. Patent No. 5,423,849 to Engelson and Samson. Each of these techniques may be used in making the vasoocclusive devices described herein, however, other similar techniques will be known to the skilled artisan.

[0035] Procedures for incorporating first substantially spherical occlusive devices of this invention into an aneurysm or other vascular vesicle can be followed by introduction of other occlusive devices into the center of the cavity formed by the first occlusive device to produce superior physical stability.

[0036] Figure 6A shows a cross-section of such an embodiment of the invention, wherein two vasoocclusive strand portions (142, 144) are provided to nest concentrically with each other in the operable configuration. The larger vasoocclusive strand portion (142) can serve as a cavity in which to concentrically house the other smaller vasoocclusive strand portion (144). When the device (140) is unwound in the inoperable configuration, each vasoocclusive strand portion (142, 144) is aligned longitudinally in tandem. Such a vasoocclusive device (140) with a plurality of concentric vasoocclusive portions can be made from the same metallic strand along different portions thereof, or separate strands can be prepared and then fused together at their ends in longitudinal tandem. Figure 6B shows this embodiment in a partially unwound position to demonstrate that the spheres are arranged in tandem along the same strand. The aligned vasoocclusive strand portions (142, 144) can each be wound on the same or slightly different sized mandrel in order to form a multiple-layered sphere when positioned in the wound, operable configuration

[0037] The invention contemplates that a plurality of concentrically nesting occlusive strand portions may be employed. Each spherical occlusive strand portion may have a unique size, so that the device is capable of concentric nesting with the other occlusive members. The invention also contemplates that a plurality of substantially spherical strand portions, or other known vasoocclusive devices, can be inserted in a non-concentric manner inside a substantially spherical cavity created by the first strand portion. To protect flowing blood from a thrombogenic surface, the outermost coils may be bare, or unfibered. Providing natural or synthetic fibers (146) to the innermost strand portion (144) increases the thrombogenicity therein and protects the vesicle from flowing blood. In this way, blood clotting begins in the center of

the vasoocclusive device and proceeds outward, stopping at the arterial lumen.

[0038] Figure 7 depicts a mandrel (120) suitable for making a substantially spherical vasoocclusive device. As shown, the mandrel (120) can primarily consist of a core (124). The core (124) is typically made of a refractory material, such as alumina or zirconia. The function of the core (124) is simply to form a support for winding that will not pollute the vasoocclusive device during the heat-treatment step to be described below, and will provide a specific substantially spherical form for the vasoocclusive device during the heat-treatment step. Circumferentially continuous grooves (122) on the surface of the core (124) may be preferably provided to assist in regularly aligning the strand as it is being wound about the core (124). Additionally, a small strand receptacle (126) may be provided to insert and hold the end or ends of the strand in place when performing the heating step. Other methods of winding a strand around a core will be apparent to one skilled in the art. The continuous grooves (122) are preferably provided to permit the strand to be wound about the core (124) with minimal kinking or angulation of the coils.

[0039] If the entire then-wound vasoocclusive device is metallic, it may be placed in an oven at an appropriate temperature to "set" or impart the substantially spherical form to the device. If the device is a platinum alloy or of nitinol, such a temperature is 593 degrees Celsius (1100 degrees Fahrenheit), for 4 hours to provide a modest amount of preshaping to the resulting vasoocclusive device. Should the make-up of the vasoocclusive device not be solely metal, in that it contains readily meltable plastic or the like, the temperature at which the heat treatment takes place is significantly lower and typically for a significantly shorter period of time. The flexural modulus of most plastics being significantly lower than that of metals, the bulk of the polymer-based device will be significantly larger than that of the metal-based device.

[0040] After cooling, the device is removed from the core (124). Any filamentary fibrous material may then be attached to the strand as described above. The vasoocclusive device is then placed in a cannula or catheter for delivery in the inoperable substantially linear configuration into a selected body cavity or vesicle, where it then assumes the operable substantially spherical configuration.

[0041] Practitioners in this medical device area will undoubtedly have other ways of producing the noted anatomically shaped occlusive and vasoocclusive devices. The vasoocclusive devices of this invention may be used in a manner similar to those methods described in U.S. Patent No 4,994,069. Briefly, the inventive devices are typically—supplied in a prepackaged form in a sterile cannula which is adapted to engage the proximal end of a catheter. Once the catheter is in place within a vessel and the distal end of the catheter is placed into, e.g., a mouth of an aneurysm, the vasoocclusive device is inserted into the aneurysm, where it assumes its relaxed

shape. Although the device may be used with a flexible pusher without connection to the vasoocclusive device described here, much more desirable is the use of a mechanically detachable coupling on the vasoocclusive device and the pusher. Any of the mechanically detachable couplings described above in the Background of the Invention would be suitable in this instance.

[0042] The examples herein are intended to illustrate, but not limit, the present invention. While they are typical of those that might be used, other procedures known to those skilled in the art may alternatively be employed.

EXAMPLE

[0043] Transparent, elastic, vesicle models were constructed with two rows of lateral wall aneurysms for comparison: two each at diameters of 10, 8, 6, and 4 millimeters. One row had narrow necks (less than 50% of aneurysm diameter), the other had wide necks (greater than 50% of aneurysm diameter). The models were perfused with both Newtonian and with non-Newtonian fluids flowing at physiologic volumes and pulse profiles. Isobaric dyes were injected and the flow dynamics observed. Various sizes and kinds of previously known coils, such as the Guglielmi Detachable Coil, were delivered to the aneurysms, in addition to various sizes of the devices of the present invention, and the changes in flow dynamics were observed and compared.

[0044] The angular velocities within the aneurysm were observed to vary inversely with aneurysm diameter. That is to say that smaller aneurysms had a faster angular flow velocities, however, both small-neck aneurysms and wide-neck aneurysms were observed to have high angular flow velocities. Aneurysms with wider necks were observed to have more rapid peripheral flow than those with smaller necks.

[0045] The spherical vasoocclusive devices of the present invention introduced into the aneurysms markedly decreased the angular and peripheral velocity by creating more internal friction and/or by better insulating the fluid in the aneurysm from that section of the parent artery. Such an improved stasis of blood flow is critical to the success of the invention to promote blood clot formation. As compared to other available coils tested, the vasoocclusive devices of the present invention were very surprisingly successful and yielded unexpectedly improved results.

[0046] The vasoocclusive devices remained stable and in a substantially spherical form within the aneurysms, especially that made from 0.1016mm (0.004-inch) platinum wire and inserted into the smaller aneurysms. This was in contrast to the other available coil devices tested, which had a tendency to collapse into ring forms when disturbed, as by the introducing catheter tip. In larger aneurysms, especially those with wide necks, the greater hoop strength of the vasoocclusive devices of the present invention provided the desirable physical stability within the aneurysm.

Claims

1. An occlusive device (140) comprising at least one strand (142,144) of a flexible material, the device (140) being formed such that it is self-forming to be distensible from an inoperable elongate configuration, for insertion into and through a means for delivering the device to a desired portion of a vesicle into an operable, substantially spherical, skeletal cage-like structure defining a shape having two orthogonal cross-sections which are closed shapes having no substantially straight sides wherein said strand (142,144) of flexible material comprises a first portion (142) and a second portion (144), said first and second portions being aligned longitudinally in tandem when said device (140) is in the inoperable elongate configuration, and wherein the first portion (142) forms said substantially spherical, skeletal cage-like structure when in its distended configuration and said second portion (144) is disposed within said cage-like structure of the first portion (142). 5
2. The device according to claim 1 wherein said strand (142,144) is helical in shape and optionally, further comprises a safety strand inserted longitudinally through said helical shape. 10
3. The device of any of the preceding claims which comprises a first strand (110) and a second strand (112) is co-woven along at least a portion of the length of the first strand. 15
4. The device of any of the preceding claims, wherein said flexible material comprises one of the following: 20
 - (i) a metal selected from platinum, palladium, rhodium, gold, tungsten and alloys thereof;
 - (ii) an alloy of platinum and tungsten;
 - (iii) an alloy selected from a stainless steel and a super-elastic alloy;
 - (iv) a polymer;
 - (v) an alloy of titanium and nickel; or
 - (vi) an alloy of platinum. 25
5. The device of any preceding claim wherein said second portion (144) is disposed concentrically within said first portion (142). 30
6. The device of any preceding claim wherein at least a portion (146) of said second portion (144) of said strand (142,144) comprises a means for increasing the thrombogenicity of the device (140). 35
7. The device of any preceding claim further comprising a plurality of additional strand portions disposed within said cage-like structure of the first portion (142), optionally, at least a portion of said plurality of strand portions comprises fibres attached thereto. 40
8. The device of claim 7 wherein said plurality of additional strand portions are either: 45
 - (i) concentrically disposed with each other within said cage-like structure of the first portion (142); or
 - (ii) non-concentrically disposed with each other within said cage-like structure of the first portion (142). 50
9. A device of claim 6 wherein said means for increasing the thrombogenicity comprises fibres (146) attached to at least a portion of said strand (142,144). 55
10. A device of claim 7 or claim 9, wherein said fibres (146) further comprise a radiopaque marker.
11. A method for producing a vasoocclusive device (140) comprising at least one strand (142,144) of a flexible material which device (140) is self-forming to be distensible from an inoperable elongate configuration, for insertion into and through a means for delivering the device to a desired portion of a vesicle into an operable, substantially spherical, skeletal cage-like structure defining a shape having two orthogonal cross-sections which are closed shapes having no substantially straight sides wherein said strand (142,144) of flexible material comprises a first portion (142) and a second portion (144), said first and second portions being aligned longitudinally in tandem when said device (140) is in the inoperable elongate configuration, and wherein the first portion (142) forms said substantially spherical, skeletal cage-like structure when in its distended configuration and said second portion (144) is disposed within said cage-like structure of the first portion (142) which method comprises the steps of:
 - (a) winding said first portion (142) of said at least one strand (142,144) of flexible material onto a first core (124) having a substantially spherical form;
 - (b) winding said second portion (144) of said at least one strand (142,144) of flexible material onto a second core;
 - (c) heating the first and second cores (124) and the strand (142,144) to a temperature such as to impart to said strand (142,144) a substantially spherical form when it is relaxed with the first portion (142) forming said cage-like structure and said second portion (144) being disposed within said cage-like structure, and
 - (d) removing said strand (142,144) from said cores (124), thereby producing said vasoocclusive device (140). 60
12. The method of claim 11 which further comprises one or both of the following features: 65

- (i) said first core (124) further comprises a circumferentially continuous groove (122) recessed therein, for releasably maintaining said strand (142,144) in a substantially spherical configuration;
- (ii) wherein said step of heating is at about 593 degrees Celsius (1100 degrees Fahrenheit).
13. A method of claim 11 or claim 12 wherein the device (140) comprises the features recited in one or more of claims 2 to 4 and claims 9 and 10.
14. The method of claim 11 wherein said second portion (144) of said strand (142, 144) is disposed concentrically within the cage-like structure of the first portion and/or there are a plurality of additional portions, the additional portions optionally being disposed concentrically within each other.
15. The method of claim 14 further comprising means (146) on at least one portion of said strand (142, 144) for increasing the thrombogenicity of the device (140) and/or the features recited in one or more of claims 1 and 10.

Patentansprüche

1. Okklusionsvorrichtung (140), umfassend wenigstens einen Strang (142, 144) aus flexiblem Material, wobei die Vorrichtung (140) derart ausgebildet ist, dass sie selbstformend ist, um von einer nicht betriebsmäßigen, länglichen Konfiguration für das Einführen in und durch ein Mittel zum Ausgeben der Vorrichtung zu einem gewünschten Abschnitt eines Gefäßes in eine betriebsmäßige, im wesentlichen kugelartige skelettartige, käfigartige Struktur ausgedehnt werden zu können, die eine Form mit zwei orthogonalen Querschnitten definiert, die geschlossene Formen ohne im wesentlichen gerade Linien sind, wobei der Strang (142, 144) aus flexiblem Material einen ersten Abschnitt (142) und einen zweiten Abschnitt (144) aufweist, wobei die ersten und zweiten Abschnitte längs im Tandem ausgerichtet sind, wenn die Vorrichtung (140) in der nicht betriebsmäßigen länglichen Konfiguration ist, und wobei der erste Abschnitt (142) die im wesentlichen kugelartige, skelettartige, käfigartige Struktur bildet, wenn sie sich in der ausgedehnten Konfiguration befindet und der zweite Abschnitt (144) innerhalb der käfigartigen Struktur des ersten Abschnitts (142) angeordnet ist.
2. Vorrichtung nach Anspruch 1, wobei der Strang (142, 144) schraubenförmig ist und optional darüber hinaus einen in Längsrichtung durch die Schraubenform eingeführten Sicherheitsstrang umfasst.
3. Vorrichtung nach einem der vorangehenden Ansprüche, die einen ersten Strang (110) umfasst, und ein zweiter Strang (112) entlang wenigstens einem ersten Abschnitt der Länge des ersten Strangs mitgewebt ist.
4. Vorrichtung nach einem der vorangehenden Ansprüche, wobei das flexible Material eines der folgenden umfasst:
 - (i) ein Metall aus der Gruppe Platin, Palladium, Rhodium, Gold, Wolfram und Legierungen davon;
 - (ii) eine Legierung aus Platin und Wolfram;
 - (iii) eine Legierung, die aus einem Edelstahl und einer superelastischen Legierung ausgewählt ist;
 - (iv) ein Polymer;
 - (v) eine Legierung aus Titan und Nickel; oder
 - (vi) eine Platinlegierung.
5. Vorrichtung nach einem der vorangehenden Ansprüche, wobei der zweite Abschnitt (144) konzentrisch in dem ersten Abschnitt (142) angeordnet ist.
6. Vorrichtung nach einem der vorangehenden Ansprüche, wobei wenigstens ein Teil (146) des zweiten Abschnitts (144) des Strangs (142, 144) ein Mittel zum Erhöhen der Thrombogenität der Vorrichtung (140) umfasst.
7. Vorrichtung nach einem der vorangehenden Ansprüche, welche darüber hinaus eine Vielzahl zusätzlicher, in der käfigartigen Struktur des ersten Abschnitts (142) angeordneter Strangabschnitte umfasst, wobei optional wenigstens ein Teil der Vielzahl von Strangabschnitten daran befestigte Fasern aufweist.
8. Vorrichtung nach Anspruch 7, wobei die Vielzahl zusätzlicher Strangabschnitte entweder:
 - (i) in der käfigartigen Struktur des ersten Abschnitts (142) zueinander konzentrisch angeordnet ist; oder
 - (ii) in der käfigartigen Struktur des ersten Abschnitts (142) zueinander nicht konzentrisch angeordnet ist.
9. Vorrichtung nach Anspruch 6, wobei das Mittel zum Erhöhen der Thrombogenität an wenigstens einem Teil des Strangs (142, 144) befestigte Fasern (146) umfasst.
10. Vorrichtung nach Anspruch 7 oder Anspruch 9, wobei die Fasern (146) darüber hinaus einen Röntgenstrahlen absorbierenden Marker aufweisen.
11. Verfahren zur Herstellung einer Gefäßokklusions-

vorrichtung (140), umfassend zumindest einen Strang (142, 144) aus flexiblem Material, wobei die Vorrichtung (140) selbstformend ist, sodass sie von einer nicht betriebsmäßigen, länglichen Konfiguration zum Einführen in und durch ein Mittel zum Ausgeben der Vorrichtung zu einem gewünschten Abschnitt eines Gefäßes in eine betriebsmäßige, im wesentlichen kugelartige, skelettartige, käfigartige Struktur ausdehnbar ist, die eine Form mit zwei orthogonalen Querschnitten definiert, die geschlossene Formen ohne im wesentlichen gerade Linien sind, wobei der Strang (142, 144) aus flexiblem Material einen ersten Abschnitt (142) und einen zweiten Abschnitt (144) aufweist, wobei die ersten und zweiten Abschnitte längs im Tandem ausgerichtet werden, wenn die Vorrichtung (140) in der nicht betriebsmäßigen länglichen Konfiguration ist, und wobei der erste Abschnitt (142) die im wesentlichen kugelartige, skelettartige, käfigartige Struktur bildet, wenn sie in ihrer ausgedehnten Konfiguration ist und der zweite Abschnitt (144) innerhalb der käfigartigen Struktur des ersten Abschnitts (142) angeordnet ist, wobei das Verfahren die Schritte umfasst:

(a) Wickeln des ersten Abschnitts (142) des zumindest einen Strangs (142, 144) aus flexiblem Material auf einen ersten Kern (124) mit im Wesentlichen kugelartiger Form;

(b) Wickeln des zweiten Abschnitts (144) des zumindest einen Strangs (142, 144) aus flexiblem Material auf einen zweiten Kern;

(c) Erhitzen der ersten und zweiten Kerne (124) und des Strangs (142, 144) auf eine solche Temperatur, die dem Strang (142, 144) eine im wesentlichen kugelartige Form verleiht, wenn er losgelassen wird, wobei der erste Abschnitt (142) die käfigartige Struktur bildet und der zweite Abschnitt (144) innerhalb der käfigartigen Struktur angeordnet ist, und

(d) Entfernen des Strangs (142, 144) von den Kernen (124), um hierdurch die Gefäßokklusivvorrichtung (140) herzustellen.

12. Verfahren nach Anspruch 11, welches darüber hinaus eines oder beide der folgenden Merkmale aufweist:

(i) der Kern (124) umfasst darüber hinaus eine darin ausgesparte, umfangmäßig fortlaufende Rille (122) zum lösbaren Halten des Strangs (102, 107, 142, 144) in einer im Wesentlichen kugelartigen Konfiguration;

(ii) wobei der Schritt des Erhitzens eine Temperatur von ungefähr 593 ° C (1100 °F) umfasst.

13. Verfahren nach Anspruch 11 oder Anspruch 12, wobei die Vorrichtung (140) die in einem oder mehreren der Ansprüche 2 bis 4 und der Ansprüche 9 und 10

genannten Merkmale aufweist.

14. Verfahren nach Anspruch 11, wobei der zweite Abschnitt (144) des Strangs (142, 144) konzentrisch in der käfigartigen Struktur des ersten Abschnitts angeordnet wird und/oder es eine Vielzahl von zusätzlichen Abschnitten gibt, wobei die zusätzlichen Abschnitte optional konzentrisch ineinander angeordnet werden.

15. Verfahren nach Anspruch 14, welches darüber hinaus Mittel (146) an wenigstens einem Abschnitt des Strangs (142, 144) umfasst, um die Thrombogenität der Vorrichtung (140) zu erhöhen und/oder welches die in einem oder mehreren der Ansprüche 1 und 10 genannten Merkmale aufweist.

Revendications

1. Dispositif d'occlusion (140) comprenant au moins un brin (142, 144) d'un matériau flexible, le dispositif (140) étant formé de telle manière qu'il est auto-adaptable pour être distensible d'une configuration allongée et inutilisable, pour l'insertion dans et à travers un moyen pour acheminer le dispositif jusqu'à une partie désirée d'une vésicule, à une structure utilisable, sensiblement sphérique, semblable à une cage squelettique, définissant une forme ayant deux sections orthogonales qui sont des formes fermées n'ayant sensiblement pas de côtés droits, dans lequel ledit brin (142, 144) d'un matériau flexible comprend une première partie (142) et une seconde partie (144), lesdites première et seconde parties étant aligées longitudinalement en couple lorsque ledit dispositif (140) est dans une configuration allongée inutilisable, et dans lequel ladite première partie (142) forme ladite structure sensiblement sphérique, semblable à une cage squelettique lorsqu'il se trouve dans sa configuration distendue, et ladite seconde partie (144) est disposée à l'intérieur de ladite structure semblable à une cage de la première partie (142).

2. Dispositif selon la revendication 1, dans lequel ledit brin (142, 144) est de forme hélicoïdale et facultativement, comprend en outre un brin de sécurité inséré de manière longitudinale dans ladite forme hélicoïdale.

3. Dispositif selon l'une quelconque des revendications précédentes, qui comprend un premier brin (110), et un second brin (112) est co-tissé le long d'au moins une partie de la longueur du premier brin.

4. Dispositif selon l'une quelconque des revendications précédentes, dans lequel ledit matériau flexible comprend l'un de ce qui suit :

- (i) un métal choisi entre le platine, le palladium, le rhodium, l'or, le tungstène, et des alliages de ceux-ci ;
- (ii) un alliage de platine et de tungstène ;
- (iii) un alliage choisi entre un acier inoxydable et un alliage super-élastique ;
- (iv) un polymère ;
- (v) un alliage de titane et de nickel ; ou
- (vi) un alliage de platine.
- 5
- 10
- 15
- 20
- 25
- 30
- 35
- 40
- 45
- 50
- 55
5. Dispositif selon l'une quelconque des revendications précédentes, dans lequel ladite seconde partie (144) est disposée de manière concentrique à l'intérieur de ladite première partie (142).
6. Dispositif selon l'une quelconque des revendications précédentes, dans lequel au moins une partie (146) de ladite seconde partie (144) dudit brin (142, 144) comprend un moyen destiné à augmenter la thrombogénicité du dispositif (140).
7. Dispositif selon l'une quelconque des revendications précédentes, comprenant en outre une pluralité de parties de brins supplémentaires disposées à l'intérieur de ladite structure semblable à une cage de la première partie (142), facultativement, et au moins une partie de ladite pluralité des parties de brin comprend des fibres attachées à celles-ci.
8. Dispositif selon la revendication 7, dans lequel ladite pluralité de parties de brins supplémentaires sont soit :
- (i) disposées de manière concentrique les unes par rapport aux autres à l'intérieur de ladite structure semblable à une cage de la première partie (142) ; soit
- (ii) disposées de manière non concentrique les unes par rapport aux autres à l'intérieur de ladite structure semblable à une cage de la première partie (142).
9. Dispositif selon la revendication 6, dans lequel lesdits moyens destinés à augmenter la thrombogénicité comprennent des fibres (146) attachées à au moins une partie dudit brin (142, 144).
10. Dispositif selon la revendication 7 ou la revendication 9, dans lequel lesdites fibres (146) comprennent en outre un marqueur radio-opaque.
11. Procédé de production d'un dispositif d'occlusion vasculaire (140) comprenant au moins un brin (142, 144) d'un matériau flexible, lequel dispositif (140) est auto-adaptable pour être distensible d'une configuration allongée et inutilisable, pour l'insertion dans et à travers un moyen pour acheminer le dispositif jusqu'à une partie désirée d'une vésicule, à une structure utilisable, sensiblement sphérique, semblable à une cage squelettique, définissant une forme ayant deux sections orthogonales qui sont des formes fermées n'ayant sensiblement pas de côtés droits, dans lequel ledit brin (142, 144) d'un matériau flexible comprend une première partie (142) et une seconde partie (144), lesdites première et seconde parties étant alignées longitudinalement en couple lorsque ledit dispositif (140) est dans une configuration allongée inutilisable, et dans lequel ladite première partie (142) forme ladite structure sensiblement sphérique, semblable à une cage squelettique lorsqu'il se trouve dans sa configuration distendue, et ladite seconde partie (144) est disposée à l'intérieur de ladite structure semblable à une cage de la première partie (142), lequel procédé comprend les étapes suivantes :
- (a) enrouler ladite première partie (142) dudit au moins un brin (142, 144) de matériau flexible sur un premier noyau (124) ayant une forme sensiblement sphérique ;
- (b) enrouler ladite deuxième partie (144) dudit au moins un brin (142, 144) de matériau flexible sur un deuxième noyau ;
- (c) chauffer les premier et deuxième noyaux (124) et le brin (142, 144) à une température de manière à impartir audit brin (142, 144) une forme sensiblement sphérique lorsqu'il est relâché avec la première partie (142) formant la structure semblable à une cage et la seconde partie (144) étant disposée à l'intérieur de ladite structure semblable à une cage, et
- (d) retirer ledit brin (142, 144) desdits noyaux (124), produisant ainsi ledit dispositif d'occlusion vasculaire (140).
12. Procédé selon la revendication 11, qui comprend en outre une des caractéristiques suivantes ou les deux :
- (i) ledit premier noyau (124) comprend en outre un sillon continu de manière circonférentielle (122), encastré à l'intérieur de celui-ci pour maintenir de manière libérable ledit brin (142, 144) dans une configuration sensiblement sphérique;
- (ii) dans lequel ladite étape de chauffage est à environ 593 degrés Celsius (1100 degrés Fahrenheit).
13. Procédé selon la revendication 11 ou la revendication 12, dans lequel le dispositif (140) comprend les caractéristiques citées dans une ou plus des revendications 2 à 4 et des revendications 9 et 10.
14. Procédé selon la revendication 11, dans lequel ladite deuxième partie (144) dudit brin (142, 144) est dis-

posée de manière concentrique à l'intérieur de la structure semblable à une cage de la première partie, et/ou il y a une pluralité de parties supplémentaires, les parties supplémentaires étant disposées facultativement de manière concentrique les unes à l'intérieur des autres. 5

15. Procédé selon la revendication 14, comprenant en outre des moyens (146) sur au moins une partie dudit brin (142, 144) destinés à augmenter la thrombogénicité du dispositif (140) et/ou les caractéristiques citées dans une ou plus des revendications 1 et 10. 10

15

20

25

30

35

40

45

50

55




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6A




FIG. 6B




FIG. 7

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 4994069 A [0003] [0041]
- DE 3203410 A [0004]
- US 5304194 A [0006] [0034]
- US 5354295 A [0007]
- US 5122136 A, Guglielmi [0007]
- US 5234437 A, Sepetka [0008]
- US 5250071 A, Palermo [0008]
- US 5261916 A, Engelson [0008]
- US 5304195 A, Twyford [0008]
- US 5312415 A, Palermo [0008]
- US 5350397 A, Palermo [0008]
- US 5690666 A, Berenstein [0009]
- US 3174851 A [0027]
- US 3351463 A [0027]
- US 3753700 A [0027]
- US 5226911 A [0034]
- US 5382259 A, Phelps and Vann [0034]
- US 5423849 A, Engelson and Samson [0034]