



(11) **EP 0 773 258 B9**

(12) **CORRECTED NEW EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B2)
Corrections, see
Description Paragraph(s) 7

(51) Int Cl.:
C08L 23/08 ^(2006.01) **C08J 5/18** ^(2006.01)
C08L 23/16 ^(2006.01)

(48) Corrigendum issued on:
16.09.2009 Bulletin 2009/38

(45) Date of publication and mention
of the opposition decision:
15.10.2008 Bulletin 2008/42

(45) Mention of the grant of the patent:
31.03.2004 Bulletin 2004/14

(21) Application number: **96308065.0**

(22) Date of filing: **06.11.1996**

(54) **Film extruded from a blend of ethylene copolymers**

Extrudierter Film aus aethylencopolymeren Mischungen

Feuille extrudée à partir d'un mélange de copolymères d'éthylène

(84) Designated Contracting States:
AT BE DE ES FR GB GR IT NL SE

(30) Priority: **07.11.1995 US 6269**
03.07.1996 US 675602

(43) Date of publication of application:
14.05.1997 Bulletin 1997/20

(73) Proprietor: **Union Carbide Chemicals & Plastics
Technology
Corporation
Midland, MI 48674 (US)**

(72) Inventors:
• **Moy, Francis H.
Belle Mead,
New Jersey 08502 (US)**
• **Michie, Williams James
Raritan,
New Jersey 08869-1659 (US)**

(74) Representative: **Hayes, Adrian Chetwynd et al
Boulton Wade Tennant,
Verulam Gardens
70 Gray's Inn Road
London WC1X 8BT (GB)**

(56) References cited:
EP-A- 0 369 436 EP-A- 0 450 276
WO-A-95/30713 US-A- 3 125 547
US-A- 3 914 342 US-A- 4 438 238
US-A- 4 705 829 US-A- 4 770 912
US-A- 5 210 142 US-A- 5 405 901

- "Chemical Additives for the Plastics Industry", Radian Corporation, McLean, Virginia, Noyes Data Corp.p. 105, 1987
- E.Flick "Plastics Additives", An Industrial Guide, Noyes Publications, p.722, 1986
- Journal of Rheology 30(2), pp. 337-357, 1986, A.V. Ramamurthy

EP 0 773 258 B9

Description**Technical Field**

5 [0001] This invention relates to film extruded from a blend of (i) conventional linear low density polyethylene and (ii) an in situ blend of ethylene copolymers prepared in a series of polymerization reactors.

Background Information

10 [0002] There has been a rapid growth in the market for linear low density polyethylene (LLDPE), particularly resin made under mild operating conditions, typically at pressures of 0.7 to 2.1 MPa (100 to 300 psi) and reaction temperatures of less than 100° C. This low pressure process provides a broad range of LLDPE products for blown and cast film, injection molding, rotational molding, blow molding, pipe, tubing, and wire and cable applications. LLDPE has essentially a linear backbone with only short chain branches, about 2 to 6 carbon atoms in length. In LLDPE, the length and frequency
15 of branching, and, consequently, the density, is controlled by the type and amount of comonomer used in the polymerization. Although the majority of the LLDPE resins on the market today have a narrow molecular weight distribution, LLDPE resins with a broad molecular weight distribution are available for a number of non-film applications.

[0003] LLDPE resins designed for commodity type applications typically incorporate 1-butene as the comonomer. The use of a higher molecular weight alpha-olefin comonomer produces resins with significant strength advantages relative
20 to those of ethylene/1-butene copolymers. The predominant higher alpha-olefin comonomers in commercial use are 1-hexene, 4-methyl-1-pentene, and 1-octene. The bulk of the LLDPE is used in film products where the excellent physical properties and drawdown characteristics of LLDPE film makes this film well suited for a broad spectrum of applications. Fabrication of LLDPE film is generally effected by the blown film and slot casting processes. The resulting film is characterized by excellent tensile strength, high ultimate elongation, good impact strength, and excellent puncture resistance.

25 [0004] LLDPE, however, due to an inherent molecular structure/melt rheology characteristic, is highly susceptible to melt fracture, a phenomenon, whereby, on exiting an extruder die, the extrudate has a highly irregular surface. LLDPE is particularly vulnerable to melt fracture at die rates in excess of 0.71 kg per hour per centimetre (4 pounds per hour per inch) of die circumference and at die gaps in the range of 0.508 mm to 1.905 mm (0.020 to 0.75 inch).

30 [0005] US-A-5 210 142 discloses a method of reducing melt fracture in melt processing a linear polyethylene. The article formed by the method can be a film.

Disclosure of the Invention

35 [0006] An object of this invention, therefore, is to provide a film containing a defined weight proportion of LLDPE, which has been extruded at the die rate and die gap mentioned above with essentially no melt fracture.

[0007] Other objects and advantages will become apparent hereinafter. According to the present invention such a film and a process for preparing the same has been discovered. The present invention provides a film which has been extruded to a gauge in the range of from 12.5 to 150 micrometres (0.5 to 6 mils), comprising a blend of (i) a linear low density polyethylene having a melt index in the range of from 0.3 to 3 grams per 10 minutes and a density in the range
40 of from 0.900 to 0.940 gram per cubic centimeter and (ii) a multimodal resin consisting of an in situ blend of copolymers of ethylene and one or more alpha-olefins having 3 to 8 carbon atoms, said resin having a flow index in the range of 40 to 150 grams per 10 minutes; a melt flow ratio in the range of 50 to 150; an Mw/Mn ratio of 8 to 22; and a density in the range of 0.908 to 0.930 gram per cubic centimeter wherein (a) the weight ratio of component (i) to component (ii) is in the range of from 1:1 to 3:1; (b) the blend has been extruded, under extrusion conditions, at a die rate in the range of
45 from 1.4 to 2.7 kg per hour per centimeter (8 to 15 pounds per hour per inch) of die circumference and at a die gap in the range of from 0.088 to 0.125 cm (0.035 to 0.050 inch); and (c) the film exhibits essentially no melt fracture, component (ii) having been produced in situ by contacting the ethylene and one or more alpha-olefins with a magnesium/titanium based catalyst system in each of two reactors connected in series, under polymerisation conditions, wherein the relatively high molecular weight polymer formed in one reactor has a flow index in the range of from 0.2 to 6 grams per 10 minutes
50 and a density in the range of from 0.900 to 0.940 gram per cubic centimeter and the relatively low molecular weight polymer formed in the other reactor has a melt index in the range of from 100 to 1500 grams per 10 minutes and a density in the range of from 0.905 to 0.970 gram per cubic centimeter, the weight ratio of high molecular weight polymer to the low molecular weight polymer being in the range of from 0.67:1 to 1.5:1.

Description of the Preferred Embodiment(s)

55 [0008] The gauge or thickness of the film can be in the range of 0.013 to 0.15 mm (0.5 to 6 mils) and is preferably in the range of 0.019 to 0.064 mm (0.75 to 2.5 mils). The optimum gauge is about 0.038 mm (1.5 mil).

[0009] As noted, the film is formed by extrusion. The extruder is a conventional one using a die, which will provide the desired gauge. Examples of various extruders, which can be used in forming the film are the single screw type modified with a blown film die and air ring and continuous take off equipment. A typical single screw type extruder can be described as one having a hopper at its upstream end and a die at its downstream end. The hopper feeds into a barrel, which contains a screw. At the downstream end, between the end of the screw and the die, is a screen pack and a breaker plate. The screw portion of the extruder is considered to be divided up into three sections, the feed section, the compression section, and the metering section, and multiple heating zones from the rear heating zone to the front heating zone, the multiple sections and zones running from upstream to downstream. If it has more than one barrel, the barrels are connected in series. The length to diameter ratio of each barrel is in the range of 16:1 to 30:1. The extrusion can take place at temperatures in the range of 150 to 280 degrees C, and is preferably carried out at temperatures in the range of 190 to 250 degrees C.

[0010] The blend, which is used in the extruder, is a mixture of a conventional linear low density polyethylene and an in situ blend produced in two staged reactors connected in series wherein a mixture of resin and catalyst precursor is transferred from the first reactor to the second reactor in which another copolymer is prepared and blends in situ with the copolymer from the first reactor.

[0011] The conventional linear low density polyethylene (LLDPE) can be a copolymer of ethylene and one or more alpha-olefins having 3 to 12 carbon atoms, and preferably 3 to 8 carbon atoms. These polymers can be produced by processes described in United States Patents 4,101,445; 4,302,565; and 4,508,842. LLDPE, typically, has a density in the range of 0.900 to 0.940 gram per cubic centimeter, and preferably 0.915 to 0.925 gram per cubic centimeter; a melt index in the range of 0.3 to 3 grams per 10 minutes; and an Mw/Mn ratio in the range of 3 to 8.

[0012] With regard to the in situ blend:

[0013] Component (ii) is produced in situ by contacting ethylene and at least one alpha-olefin comonomer with a magnesium/titanium based catalyst system in each of two reactors connected in series, under polymerization conditions, wherein a relatively high molecular weight polymer is formed in the first reactor and has a flow index in the range of 0.2 to 6 grams per 10 minutes and a density in the range of 0.900 to 0.940 gram per cubic centimeter and a relatively low molecular weight polymer is formed in the second reactor and has a melt index in the range of 100 to 1500 grams per 10 minutes and a density in the range of 0.905 to 0.970 gram per cubic centimeter, the weight ratio of high molecular weight polymer to low molecular weight polymer being in the range of 0.67:1 to 1.5:1.

[0014] More particularly, the copolymers produced in each of the reactors are copolymers of ethylene and one or more alpha-olefin comonomers having 3 to 8 carbon atoms, preferably one or two alpha-olefins. The relatively high molecular weight copolymer is produced in what is referred to as the high molecular weight reactor, and the relatively low molecular weight copolymer is produced in what is referred to as the low molecular weight reactor. The alpha-olefins are exemplified by propylene, 1-butene, 1-hexene, 4-methyl-1-pentene, or 1-octene. Any of the aforementioned comonomers can be used in either reactor.

[0015] Preferred comonomer combinations (first reactor/second reactor) are 1-hexene/1-butene; 1-butene/1-butene; 1-butene/1-hexene; and 1-hexene/1-hexene combinations.

[0016] It will be understood that generally the in situ blend can be characterized as a multimodal resin, usually bimodal or trimodal. In some cases, however, the two components making up the blend are sufficiently close in average molecular weight that there is no discernible discontinuity in the molecular weight curve.

[0017] The properties of these resins are strongly dependent on the proportion of the high molecular weight component, i.e., the low melt index component. For a staged reactor system, the proportion of the high molecular weight component is controlled via the relative production rate in each reactor. The relative production rate in each reactor can, in turn, be controlled by a computer application program, which monitors the production rate in the reactors (measured by heat balance) and then manipulates the ethylene partial pressure in each reactor and catalyst feed rate in order to meet the production rate, the production rate split, and catalyst productivity requirements.

[0018] The magnesium/titanium based catalyst system, which is used to produce the in situ blend can be exemplified by the catalyst system described in United States patent 4,302,565 although the precursor is preferably unsupported. Another preferred catalyst system is one where the precursor is formed by spray drying and used in slurry form. Such a catalyst precursor, for example, contains titanium, magnesium, and an electron donor, and, optionally an aluminum halide. The precursor is introduced into a hydrocarbon medium such as mineral oil to provide the slurry form. See United States patent 5,290,745.

[0019] The electron donor, if used in the catalyst precursor, is an organic Lewis base, liquid at temperatures in the range of 0°C to 200°C, in which the magnesium and titanium compounds are soluble. The electron donor can be an alkyl ester of an aliphatic or aromatic carboxylic acid, an aliphatic ketone, an aliphatic amine, an aliphatic alcohol, an alkyl or cycloalkyl ether, or mixtures thereof, each electron donor having 2 to 20 carbon atoms. Among these electron donors, the preferred are alkyl and cycloalkyl ethers having 2 to 20 carbon atoms; dialkyl, diaryl, and alkylaryl ketones having 3 to 20 carbon atoms; and alkyl, alkoxy, and alkylalkoxy esters of alkyl and aryl carboxylic acids having 2 to 20 carbon atoms. The most preferred electron donor is tetrahydrofuran. Other examples of suitable electron donors are

methyl formate, ethyl acetate, butyl acetate, ethyl ether, dioxane, di-n-propyl ether, dibutyl ether, ethyl formate, methyl acetate, ethyl anisate, ethylene carbonate, tetrahydropyran, and ethyl propionate.

[0020] While an excess of electron donor is used initially to provide the reaction product of titanium compound and electron donor, the reaction product finally contains 1 to 20 moles of electron donor per mole of titanium compound and preferably 1 to 10 moles of electron donor per mole of titanium compound.

[0021] An activator compound, which is generally used with any of the titanium based catalyst precursors, can have the formula $AlR_aX_bH_c$ wherein each X is independently chlorine, bromine, iodine, or OR'; each R and R' is independently a saturated aliphatic hydrocarbon radical having 1 to 14 carbon atoms; b is 0 to 1.5; c is 0 or 1; and $a+b+c = 3$. Preferred activators include alkylaluminum mono- and dichlorides wherein each alkyl radical has 1 to 6 carbon atoms and the trialkylaluminums. A particularly preferred activator is a mixture of diethylaluminum chloride and tri-n-hexylaluminum. 0.10 to 10 moles, and preferably 0.15 to 2.5 moles, of activator are used per mole of electron donor. The molar ratio of activator to titanium is in the range of 1:1 to 10:1 and is preferably in the range of 2:1 to 5:1.

[0022] The hydrocarbyl aluminum cocatalyst can be represented by the formula R_3Al or R_2AlX wherein each R is independently alkyl, cycloalkyl, aryl, or hydrogen; at least one R is hydrocarbyl; and two or three R radicals can be joined to form a heterocyclic structure. Each R, which is a hydrocarbyl radical, can have 1 to 20 carbon atoms, and preferably has 1 to 10 carbon atoms. X is a halogen, preferably chlorine, bromine, or iodine. Examples of hydrocarbyl aluminum compounds are as follows: triisobutylaluminum, tri-n-hexylaluminum, di-isobutyl-aluminum hydride, dihexylaluminum dihydride, di-isobutyl-hexylaluminum, isobutyl dihexylaluminum, trimethylaluminum, triethylaluminum, tripropylaluminum, triisopropylaluminum, tri-n-butylaluminum, trioctylaluminum, tridecylaluminum, tridodecylaluminum, tribenzylaluminum, triphenylaluminum, trinaphthylaluminum, tritolylaluminum, dibutylaluminum chloride, diethylaluminum chloride, and ethylaluminum sesquichloride. The cocatalyst compounds can also serve as activators and modifiers.

[0023] As noted above, it is preferred not to use a support. However, in those cases where it is desired to support the precursor, silica is the preferred support. Other suitable supports are inorganic oxides such as aluminum phosphate, alumina, silica/alumina mixtures, silica modified with an organoaluminum compound such as triethylaluminum, and silica modified with diethyl zinc. A typical support is a solid, particulate, porous material essentially inert to the polymerization. It is used as a dry powder having an average particle size of 10 to 250 μm (microns) and preferably 30 to 100 μm (microns); a surface area of at least 200 square meters per gram and preferably at least 250 square meters per gram; and a pore size of at least 10 nm (100 angstroms) and preferably at least 20 nm (200 angstroms). Generally, the amount of support used is that which will provide 0.1 to 1.0 millimole of titanium per gram of support and preferably 0.4 to 0.9 millimole of titanium per gram of support. Impregnation of the above mentioned catalyst precursor into a silica support can be accomplished by mixing the precursor and silica gel in the electron donor solvent or other solvent followed by solvent removal under reduced pressure. When a support is not desired, the catalyst precursor can be used in liquid form.

[0024] Activators can be added to the precursor either before and/or during polymerization. In one procedure, the precursor is fully activated before polymerization. In another procedure, the precursor is partially activated before polymerization, and activation is completed in the reactor. Where a modifier is used instead of an activator, the modifiers are usually dissolved in an organic solvent such as isopentane and, where a support is used, impregnated into the support following impregnation of the titanium compound or complex, after which the supported catalyst precursor is dried. Otherwise, the modifier solution is added by itself directly to the reactor. Modifiers are similar in chemical structure and function to the activators. For variations, see, for example, United States patent 5,106,926. The cocatalyst is preferably added separately neat or as a solution in an inert solvent, such as isopentane, to the polymerization reactor at the same time as the flow of ethylene is initiated.

[0025] United States patent 5,106,926 provides another example of a magnesium/titanium based catalyst system comprising:

(a) a catalyst precursor having the formula $Mg_dTi(OR)_eX_f(ED)_g$ wherein R is an aliphatic or aromatic hydrocarbon radical having 1 to 14 carbon atoms or COR' wherein R' is a aliphatic or aromatic hydrocarbon radical having 1 to 14 carbon atoms; each OR group is the same or different; X is independently chlorine, bromine or iodine; ED is an electron donor; d is 0.5 to 56; e is 0, 1, or 2; f is 2 to 116; and g is $1.5d+2$;

(b) at least one modifier having the formula BX_3 or $AlR_{(3-e)}X_e$ wherein each R is alkyl or aryl and is the same or different, and X and e are as defined above for component (a)

wherein components (a) and (b) are impregnated into an inorganic support; and

(c) a hydrocarbyl aluminum cocatalyst.

[0026] The precursor is prepared from a titanium compound, a magnesium compound, and an electron donor. Titanium compounds, which are useful in preparing these precursors, have the formula $Ti(OR)_eX_h$ wherein R, X, and e are as defined above for component (a); h is an integer from 1 to 4; and $e+h$ is 3 or 4. Examples of titanium compounds are $TiCl_3$, $TiCl_4$, $Ti(OC_2H_5)_2Br_2$, $Ti(OC_6H_5)Cl_3$, $Ti(OCOCH_3)Cl_3$, and $Ti(OCOC_6H_5)Cl_3$. The magnesium compounds include magnesium halides such as $MgCl_2$, $MgBr_2$, and MgI_2 . Anhydrous $MgCl_2$ is a preferred compound. 0.5 to 56, and preferably

1 to 10, moles of the magnesium compounds are used per mole of titanium compounds.

[0027] The electron donor, the support, and the cocatalyst are the same as those described above. As noted, the modifier can be similar in chemical structure to the aluminum containing activators. The modifier has the formula BX_3 or $AlR_{(3-e)}X_e$ wherein each R is independently alkyl having 1 to 14 carbon atoms; each X is independently chlorine, bromine, or iodine; and e is 1 or 2. One or more modifiers can be used. Preferred modifiers include alkylaluminum mono- and dichlorides wherein each alkyl radical has 1 to 6 carbon atoms; boron trichloride; and the trialkylaluminums. 0.1 to 10 moles, and preferably 0.2 to about 2.5 moles, of modifier can be used per mole of electron donor. The molar ratio of modifier to titanium can be in the range of 1:1 to 10:1 and is preferably in the range of 2:1 to about 5:1.

[0028] The entire catalyst system, which includes the precursor or activated precursor and the cocatalyst, is added to the first reactor. The catalyst is admixed with the copolymer produced in the first reactor, and the mixture is transferred to the second reactor. Insofar as the catalyst is concerned, only cocatalyst is added to the second reactor from an outside source.

[0029] The polymerization in each reactor is, preferably, conducted in the gas phase using a continuous fluidized process. A typical fluidized bed reactor is described in United States patent 4,482,687.

[0030] A relatively low melt index (or high molecular weight) copolymer is preferably prepared in the first reactor, and the relatively high melt index (or low molecular weight) copolymer is prepared in the second reactor. This can be referred to as the forward mode. Alternatively, the relatively low molecular weight copolymer can be prepared in the first reactor and the relatively high molecular weight copolymer can be prepared in the second reactor. This can be referred to as the reverse mode.

[0031] The first reactor is generally smaller in size than the second reactor because only a portion of the final product is made in the first reactor. The mixture of polymer and an active catalyst is usually transferred from the first reactor to the second reactor via an interconnecting device using nitrogen or second reactor recycle gas as a transfer medium.

[0032] In the high molecular weight reactor:

[0033] Because of the low values, instead of melt index, flow index is determined and those values are used in this specification. The flow index is in the range of 0.2 to 6 grams per 10 minutes. The molecular weight of this polymer is, generally, in the range of 400,000 to 480,000. The density of the copolymer is in the range of 0.900 to 0.940 gram per cubic centimeter. The melt flow ratio of the polymer can be in the range of 20 to 70, and is preferably 22 to 45.

[0034] Melt index is determined under ASTM D-1238, Condition E. It is measured at 190°C and 2.16 kilograms and reported as grams per 10 minutes. Flow index is determined under ASTM D-1238, Condition F. It is measured at 190°C and 10 times the weight used in determining the melt index, and reported as grams per 10 minutes. Melt flow ratio is the ratio of flow index to melt index.

[0035] In the low molecular weight reactor:

[0036] A relatively high melt index (or low molecular weight) copolymer is prepared in this reactor. The high melt index is in the range of 100 to 1500 grams per 10 minutes. The molecular weight of the high melt index copolymer is, generally, in the range of 14,000 to 30,000. The density of the copolymer prepared in this reactor is in the range of 0.905 to 0.970 gram per cubic centimeter. The melt flow ratio of this copolymer can be in the range of about 20 to about 70, and is preferably 20 to 45.

[0037] The blend or final product, as removed from the second reactor, has a flow index in the range of 40 to 150 grams per 10 minutes, and preferably has a flow index in the range of 45 to 145 grams per 10 minutes. The melt flow ratio is in the range of 50 to 150. The molecular weight of the final product is, generally, in the range of 90,000 to 250,000. The density of the blend is at least 0.908 gram per cubic centimeter, and is preferably in the range of 0.910 to 0.930 gram per cubic centimeter.

[0038] The broad molecular weight distribution is reflected in an Mw/Mn ratio of 8 to 22, preferably 9 to 20. Mw is the weight average molecular weight; Mn is the number average molecular weight; and the Mw/Mn ratio can be referred to as the polydispersity index, which is a measure of the breadth of the molecular weight distribution.

[0039] The magnesium/titanium based catalyst system, ethylene, alpha-olefin, and hydrogen are continuously fed into the first reactor; the polymer/catalyst mixture is continuously transferred from the first reactor to the second reactor; ethylene, alpha-olefin, and hydrogen, as well as cocatalyst are continuously fed to the second reactor. The final product is continuously removed from the second reactor.

[0040] In the low melt index, as reflected in flow index, reactor:

[0041] The mole ratio of alpha-olefin to ethylene can be in the range of 0.05:1 to 0.4:1, and is preferably in the range of 0.09:1 to 0.26:1. The mole ratio of hydrogen (if used) to ethylene can be in the range of 0.0001:1 to 0.3:1, and is preferably in the range of 0.001:1 to 0.18:1. The operating temperature is generally in the range of 60° C to 100° C. Preferred operating temperatures vary depending on the density desired, i.e., lower temperatures for lower densities and higher temperatures for higher densities.

[0042] In the high melt index reactor:

[0043] The mole ratio of alpha-olefin to ethylene can be in the range of 0.1:1 to 0.6:1, and is preferably in the range of 0.2:1 to 0.45:1. The mole ratio of hydrogen to ethylene can be in the range of 1:1 to 3:1, and is preferably in the range

of 1.6:1 to 2.2:1. The operating temperature is generally in the range of 70° C to 100° C. As mentioned above, the temperature is preferably varied with the desired density.

[0044] The pressure is generally the same in both the first and second reactors. The pressure can be in the range of 1.4 to 3.15 MPa (200 to 450 psi) and is preferably in the range of 1.96 to 2.45 MPa gauge (280 to 350 psig).

[0045] A typical fluidized bed reactor can be described as follows:

[0046] The bed is usually made up of the same granular resin that is to be produced in the reactor. Thus, during the course of the polymerization, the bed comprises formed polymer particles, growing polymer particles, and catalyst particles fluidized by polymerization and modifying gaseous components introduced at a flow rate or velocity sufficient to cause the particles to separate and act as a fluid. The fluidizing gas is made up of the initial feed, make-up feed, and cycle (recycle) gas, i.e., comonomers and, if desired, modifiers and/or an inert carrier gas.

[0047] The essential parts of the reaction system are the vessel, the bed, the gas distribution plate, inlet and outlet piping, a compressor, cycle gas cooler, and a product discharge system. In the vessel, above the bed, there is a velocity reduction zone, and, in the bed, a reaction zone. Both are above the gas distribution plate.

[0048] Conventional additives, which can be introduced into the blend, are exemplified by antioxidants, ultraviolet absorbers, antistatic agents, pigments, dyes, nucleating agents, fillers, slip agents, fire retardants, plasticizers, processing aids, lubricants, stabilizers, smoke inhibitors, viscosity control agents, and crosslinking agents, catalysts, and boosters, tackifiers, and anti-blocking agents. Aside from the fillers, the additives can be present in the blend in amounts of 0.1 to 10 parts by weight of additive for each 100 parts by weight of polymer blend. Fillers can be added in amounts up to 200 parts by weight and more for each 100 parts by weight of the blend.

[0049] A typical process for the preparation of the in situ blend, blending the in situ blend with LLDPE, and extruding the in situ blend/LLDPE mixture is as follows:

[0050] The preferred catalyst system is one where the precursor is formed by spray drying and is used in slurry form. Such a catalyst precursor, for example, contains titanium, magnesium, an electron donor, and an aluminum halide. The precursor is then introduced into a hydrocarbon medium such as mineral oil to provide the slurry form. For the catalyst composition and the method of preparing same, see United States patent 5,290,745.

[0051] The in situ polyethylene blend can be produced using the following typical procedure:

[0052] Ethylene is copolymerized with 1-hexene and 1-butene. Trimethylaluminum (TMA) cocatalyst is added to each reactor during polymerization. The pressure in each reactor is 2.1 MPa absolute (300 psia). Each polymerization is continuously conducted after equilibrium is reached.

[0053] Polymerization is initiated in the first reactor by continuously feeding the above catalyst precursor and cocatalyst, TMA, into a fluidized bed of polyethylene granules together with ethylene, 1-hexene, and hydrogen. The TMA is first dissolved in isopentane (5 percent by weight TMA). The resulting copolymer mixed with active catalyst is withdrawn from the first reactor and transferred to the second reactor using nitrogen as a transfer medium. The second reactor also contains a fluidized bed of polyethylene granules. Ethylene, 1-butene, and hydrogen are introduced into the second reactor where they come into contact with the copolymer and catalyst from the first reactor. Additional cocatalyst is also introduced. The product blend is continuously removed.

[0054] The in situ blend is blended in a conventional mixer with (i) a 1-butene LLDPE having a density of 0.918 gram per cubic centimeter and a melt index of 1 gram per 10 minutes or (ii) a 1-hexene LLDPE having a density of 0.918 gram per cubic centimeter and a melt index of 1 gram per 10 minutes in weight ratios of 40/60, 30/70, and 20/80 (in situ blend/LLDPE) and extruded at die rates of 2.5, 1.8, 1.1, 0.71 and 0.54 kg per hour per centimetre (14, 10, 6, 4 and 3 pounds per hour per inch) of die circumference and a die gap of 0.91 mm (0.036 inch).

[0055] The in situ blend/LLDPE mixtures in the various ratios and the aforementioned die gap are extruded in a 88.9 mm (3.5 inch) Gloucester™ blown film extruder having a 9.14 mm (0.036 inch) die gap; a 152.4 mm (6 inch) die; and a L/D ratio of 24:1. The extruder is operated at a die rate of 0.54 to 2.5 kg per hour per centimetre (3 to 14 pounds/hour linch) of die circumference; at a melt temperature of 213°C (415° F); and a blow up ratio of 3:1. 0.0254 mm (One mil) films are produced.

[0056] Density is measured by producing a plaque in accordance with ASTM D-1928, procedure C, and then testing as is via ASTM D-1505.

[0057] Melt flow ratio is the ratio of flow index to melt index.

[0058] The molecular weight distribution is determined via Size Exclusion Chromatography using a Waters™ 150C with trichlorobenzene as solvent at 140 degrees C with a broad molecular weight distribution standard and broad molecular weight distribution calibration method.

[0059] Die rate is defined as kg per hour per centimetre (pounds per hour per inch) of die circumference.

[0060] Blow up ratio is the ratio of the bubble diameter to the die diameter.

[0061] Melt fracture is determined by visually examining the film. Each film is given a value from 1 to 9 with the value 1 being the worst case of melt fracture and the value 9 representing essentially no melt fracture as follows:

1 = severely gross

- 2 = gross
- 3 = gross shark skin
- 4 = severe shark skin
- 5 = shark skin
- 6 = rough surface
- 7 = slightly rough surface
- 8 = minor imperfection, but acceptable
- 9 = essentially no melt fracture

[0062] The 40/60 films exhibit essentially no melt fracture (9); the 30/70 films exhibit minor imperfections, but are acceptable (8); 20/ 80 films exhibit values in the range of (3) to (7) and are unacceptable. Films consisting essentially of LLDPE exhibit values of (1) and (2), which represent heavy melt fracture even at very low die rates, e.g., of 0.54 to 0.71 kg per hour per centimetre (3 or 4 pounds per hour per inch) of die circumference.

[0063] The primary advantage of the film of the invention is that the film is essentially free of melt fracture. Another advantage is ease of extrudability due to lower extruder head pressures.

[0064] The invention is illustrated by the following examples.

Examples

[0065] The process for the preparation of the in situ blend used in the examples is carried out in the reverse mode, i.e., the low molecular weight copolymer is prepared in the first reactor; transferred together with active catalyst to the second reactor; and blended in situ with the high molecular weight copolymer, which is prepared in the second reactor.

[0066] The catalyst precursor is formed by spray drying and is used in slurry form. It contains titanium, magnesium, and aluminum halides, and an electron donor, and is attached to the surface of silica. The precursor is then introduced into a hydrocarbon medium such as mineral oil to provide the slurry form. See United States patent 5,290,745 (' 745). The catalyst precursor and method of preparing same used in the examples is the same composition and preparation method as example 1 of ' 745. For low density operation, such as that described herein, a reduced catalyst precursor is used. Typically, the molar ratio of diethylaluminum chloride (DEAC) to tetrahydrofuran (THF) is 0.45 and the molar ratio of tri-n-hexylaluminum to tetrahydrofuran is 0.20. The addition of diethylaluminum chloride and tri-n-hexylaluminum (TnHAL) is achieved by an in-line reduction system in which the diethylaluminum chloride and tri-n-hexylaluminum are fed to the reactor concurrently with the catalyst precursor in order to produce a reduced catalyst.

[0067] Ethylene is copolymerized with a comonomer in each of two fluidized bed reactors. Each polymerization is continuously conducted after equilibrium is reached.

[0068] Polymerization is initiated in the first reactor by continuously feeding the above catalyst precursor and cocatalyst, trimethylaluminum (TMA), into a fluidized bed of polyethylene granules together with ethylene, a comonomer, and hydrogen. The cocatalyst is first dissolved in isopentane (5 percent by weight cocatalyst). Higher concentrations of cocatalyst in solution can also be used as well as using the cocatalyst neat. The resulting copolymer mixed with active catalyst is withdrawn from the first reactor and transferred to the second reactor using either nitrogen or second reactor cycle gas as a transfer medium. The second reactor also contains a fluidized bed of polyethylene granules. Again, ethylene, a comonomer, and hydrogen are introduced into the second reactor where the gases come into contact with the copolymer and catalyst from the first reactor. Additional cocatalyst is also introduced. The product blend is continuously removed. This in situ blend is referred to as Resin A.

[0069] Resin B and Resin C are each blended with Resin A. Resin B is a linear low density polyethylene (LLDPE). It is a copolymer of ethylene and 1-butene prepared by a conventional low pressure process. Resin B has a melt index of 1 gram per 10 minutes; a flow index of 26 grams per 10 minutes; a melt flow ratio of 26; and a density of 0.920 gram per cubic centimeter. Resin C is also an LLDPE. It is a copolymer of ethylene and 1-hexene prepared by a conventional low pressure process. Resin C has a melt index of 0.9 gram per 10 minutes; a flow index of 23 grams per 10 minutes; a melt flow ratio of 25.6 and a density of 0.920 gram per cubic centimeter.

[0070] In addition to polymerization conditions for Resin A in Table I, resin properties of the blend of Resins A and B and Resins A and C, film extrusion conditions, and film properties are given in Tables II to V.

[0071] The equipment for extruding the blends into film is a 90 millimeter (3 1/2 inches) Gloucester™ extruder having a DSB II screw; a 150 millimeter (6 inch) die; and a 0.9 millimeter (35 mil) die gap. The screw revolutions per minute (rpm) is 35 in Table II; 36 in Table IV; and variable in Tables III and V.

Table I

reaction conditions	reactor I	reactor II
temperature (° C)	85	72

EP 0 773 258 B9

(continued)

	reaction conditions	reactor I	reactor II
5	pressure (MPa absolute) ((psia))	2.09 (298)	1.76 (251)
	C2 partial pressure (MPa absolute) ((psia))	0.47 (66.7)	0.37 (53)
	H2/C2 molar ratio	1.96	0.018
	C4/C2 molar ratio	0.28	0
	C6/C2 molar ratio	0	0.166
10	C2 feed (kg/h) ((lbs/hr))	6917 (15250)	4826 (10639)
	H2 feed (kg/h) ((lbs/hr))	8.8 (19.3)	0.029 (0.065)
	C4 feed (kg/h) ((lbs/hr))	538 (1186)	0 (0)
	C6 feed (kg/h) ((lbs/hr))	0 (0)	1344 (2964)
	cocatalyst	10% TMA	10% TMA
15	catalyst feed rate (kg/h) ((lbs/hr))	4.02 (8.87)	
	production rate (kg/h) ((lbs/hr))	7290 (1672)	5772 (12725)
	total production rate (kg/h) ((lbs/hr))	----	13062 (28797)
	ethylene split	0.589	0.411
20	titanium split	0.591	0.409
	fluidized bulk density (kg/m ³) ((lbs/cu ft))	248.93 (15.54)	23.7 (14.4)
	bed weight (kg) ((lbs))	28218 (62210)	27318 (60225)
	bed level (m) ((ft))	12.0 (39.3)	11.3 (37.2)
	bed volume (m ³) ((cu ft))	113 (4003)	118 (4182)
25	residence time (hrs)	3.871	2.091
	STY (kg/hr/m ³) ((lbs/hr/cu ft))	64.23 (4.01)	48.70 (3.04)

Table II

Percent by weight Resin A/Resin B	100 A	90/10 A/B	70/30 A/B	50/50 A/B	10/90 A/B
MI (gm/10 min)	1.2	0.9	0.95	1.0	0.98
35 HLMI (gm/10 min)	122.0	71.0	60.0	45.0	34.0
MFR	99.0	82.0	61.0	44.0	35.0
Density (gm/eu cm)	0.921	0.921	0.920	0.920	0.923
40 Extrusion Conditions, Bubble Stability, and Melt Fracture:					
Melt Temperature (C°)	214	216	217	217	229
Head Pressure MPa(psi)	23(3350)	26(3700)	31(4400)	36(5150)	48(6800)
45 % Amps	95	100	120	130	170
Die Rate (kg/h/cm) (lbs/hr/in)	1.5 (8.2)	1.5 (8.2)	1.6 (9.0)	1.6 (9.0)	1.9 (10.5)
50 Specific Output Rate 1(kg)/h/rpm) (lbs/hr/rpm)	1.95(4.3)	1.95(4.3)	2.09(4.6)	2.13(4.7)	2.50(5.5)
Bubble Stability	GOOD	GOOD	GOOD	GOOD	GOOD
55 Melt Fracture	NONE	NONE	NONE	NONE	SLIGHT-CLEARED AFTER 45 MIN.

EP 0 773 258 B9

(continued)

Percent by weight Resin A/Resin B		100 A	90/10 A/B	70/30 A/B	50/50 A/B	10/90 A/B		
5	Film Properties: [25.4 μm (1 mil) film, 3:1 BUR (blow up ratio)]							
10	Tensile Strength (MPa)((psi))	MD	44(6300)	40(5700)	37(5300)	40(5700)	41(5800)	34(4900)
		TD	29.4(4200)	32(4500)	29.7(4100)	34(4800)	36(5200)	33(4800)
	Elongation at break (%)	MD	500	600	550	600	600	650
		TD	700	800	700	800	700	800
15	Secant Modulus (MPa)((psi))	MD	245(35000)	264(37700)	231(33000)	214(30500)	273 (39000)	224(32000)
		TD	307(43900)	285(40700)	287(41000)	238(34000)	245 (35000)	245(35000)
20	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD	15759 (1900)	14929 (1800)	14929 (1800)	14929 (1800)	14100 (1700)	13270 (1600)
		TD	14100 (1700)	10782 (1300)	8294(1000)	9123(1100)	8294 (1000)	8087 (975)
25	Elmendorf Tear (gm/μm) ((gm/mil))	MD	5.5(140)	8(200)	10(250)	10(250)	11(270)	8(200)
		TD	39(1000)	32 (800)	28 (700)	24 (600)	17 (440)	16 (400)
30	Puncture (load/μm) (load/mil)		0.26(6.5)	0.24 (6.0)	0.24(6.0)	0.20 (5.0)	0.28 (7.0)	0.24 (6.0)
	Dart Drop (gm/μm) ((gm/mil))		4.53(115)	4.92 (125)	4.57(116)	4.65(118)	3.94 (100)	3.74 (95)
35	Film Properties: (50.8μm (2 mil) film, 2:1 BUR)							
40	Tensile Strength (MPa)((psi))	MD	32(4600)	37(5300)	33.6(4800)	34.3(4900)	33(4700)	34.3(4900)
		TD	26(3700)	25(3600)	29 (4200)	28.7(4100)	31(4400)	31(4400)
	Elongation at break (%)	MD	700	700	700	700	700	900
		TD	900	900	900	800	800	900
45	Secant Modulus (MPa) ((psi))	MD	256(36400)	263(37600)	252(36000)	217(31000)	245 (35000)	235(33600)
		TD	294(42000)	315(45000)	287(41000)	266(38000)	266 (30000)	273(39000)
50	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD	10782 (1300)	13270 (1600)	14100 (1700)	13270 (1600)	14100 (1700)	13270 (1600)
		TD	5806(700)	6635(800)	6635(800)	5806(700)	6635(800)	6221(750)
55	Elmendorf Tear (gm/μm) ((gm/mil))	MD	6.93(176)	6.89(175)	7.87(200)	6.69(170)	6.89(175)	7.87(200)
		TD	21.7(550)	27.6(700)	17.7(450)	18.1(460)	14.8(375)	12.8(325)
	Puncture (load/μm) ((load/mil))		0.21(5.4)	0.24(6.0)	0.24(6.0)	0.20(5.0)	0.24(6.0)	0.24(6.0)

EP 0 773 258 B9

(continued)

Percent by weight Resin A/Resin B		100 A	90/10 A/B	70/30 A/B	50/50 A/B	10/90 A/B	
5	Dart Drop (gm/μm) ((gm/mil))	3.62(92)	3.94(100)	4.17(106)	4.06(103)	3.74(95)	3.46(88)
Film Properties: (50.8 μm (2 mil) film, 3:1 BUR)							
10	Tensile Strength (MPa)((psi))	MD 29(4100) TD 24.5(3500)	31(4400) 25(3600)	32 (4500) 29(4100)	32 (4500) 28(4000)	32(4600) 32(4600)	34(4900) 33(4700)
15	Elongation at break (%)	MD 700 TD 800	700 800	700 800	700 800	700 800	800 900
20	Secant Modulus (Mpa) ((psi))	MD 252(36000) TD 282(40300)	259(37000) 273(39000)	245(35000) 266(38000)	231(33000) 238(34000)	224 (32000) 238 (34000)	231(33000) 245 (35000)
25	Tensile Impact (x 10 ⁴ N/m ²) (10782 (1300))((ft lbs/cu in))	MD 10782 (1300) TD 10782 (1300)	14100 (1700) 10782 (1300)	14100 (1700) 8294(1000)	13270 (1600) 8294(1000)	12441 (1500) 7465(900)	11612 (1400) 7465 (900)
30	Elmendorf Tear (gm/μm) ((gm/mil))	MD 10.2(260) TD 21.7(550)	9.84(250) 19.7(500)	10.2(260) 15.7(400)	10.8(275) 15.7(400)	9.06(230) 13.8(350)	8.66(220) 12.8(326)
	Puncture (load/μm) ((load/mil))	0.24(6.0)	0.24(6.0)	0.24(6.0)	0.20(5.0)	0.24(6.0)	0.24(6.0)
35	Dart Drop (gm/μm) ((gm/mil))	5.43(138)	5.43(138)	4.49(114)	4.41(112)	3.74(95)	3.54(90)
Film Properties: (25.4μm (1 mil) film, 2:1 BUR)							
40	Tensile Strength (MPa) ((psi))	MD 38(5400) TD 27(3800)	46(6600) 28(4000)	36(5100) 28(4000)	40 (5700) 30(4300)	40(5700) 34(4800)	35(5000) 33 (4700)
45	Elongation at break (%)	MD 550 TD 800	500 800	500 700	600 800	600 800	800 900
50	Secant Modulus (Mpa) ((psi))	MD 259(37000) TD 322(46000)	256(36500) 336(48000)	252(36000) 287(41000)	234(33500) 263(37500)	243 (34700) 279 (39800)	245(35000) 271(38700)
55	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD 14929 (1800) TD 6635(800)	14929 (1800) 5806(700)	14100 (1700) 5806(700)	14100 (1700) 4976(600)	19929 (1800) 5806(700)	12441 (1500) 5806(700)
	Elmendorf Tear (gm/μm) ((gm/mil))	MD 4.33(110) TD 38.6(980)	3.54(90) 43.3(1100)	6.69(170) 27.6(700)	7.87(200) 27.6(700)	7.87(200) 19.7(500)	8.46(215) 11.8(300)

EP 0 773 258 B9

(continued)

Percent by weight Resin A/Resin B	100 A	90/10 A/B	70/30 A/B	50/50 A/B	10/90 A/B
Puncture (load/ μm) ((load/mil))	0.24(6.0)	0.24(6.0)	0.24(6.0)	0.20(5.0)	0.26(6.5)
Dart Drop (gm/ μm) ((gm/mil))	4.72(120)	3.03(77)	3.74(95)	3.86(98)	3.54(90)

Table III

Percent by weight Resin A/Resin B	50/50 A/B	30/70 A/B	15/85 A/B	100 B
MI (gm/10 min)	0.95	1.0	1.0	1.0
HLMI (gm/10 min)	60.0	45.0	40.0	26.0
MFR	61.0	44.0	30.5	24.0
Density (gm/cu cm)	0.920	0.920	0.920	0.920
Extrusion Characteristics, Bubble Stability, and Melt Fracture:				
Screw RPM	45	45	45	10
Melt Temperature ($^{\circ}\text{C}$)	225	231	229	232
Head Pressure (MPa) ((psi))	39 (5600)	45 (6400)	47 (6700)	25 (3500)
Amps	140	160	165	80
Die Rate (kg/hr/cm) ((lbs/hr/in))	1.9 (10.7)	2.2 (12.5)	2.1 (12.0)	1.2 (6.8)
Specific Output Rate (kg/h/rpm) ((lbs/hr/rpm))	2.04 (4.5)	2.36 (5.2)	2.27 (5.0)	2.72 (6.0)
Bubble Stability	GOOD	GOOD	GOOD	GOOD
Melt Fracture	NONE	NONE	NONE	GROSS

Table IV

Percent by weight Resin A/ ResinC	100 A	90/10 A/C	70/30 A/C	50/50 A/C	30/70 A/C	10/90 A/C
MI (gm/10 min)	1.2	0.8	0.8	0.8	0.8	0.8
HLMI (gm/10 min)	122	67.0	42	39	29.5	24.0
MFR	99	87.0	52	48	37	29.0

EP 0 773 258 B9

(continued)

	Percent by weight		100	90/10	70/30	50/50	30/70	10/90
5	Resin A/ ResinC		A	A/C	A/C	A/C	A/C	A/C
	Density (gm/cu cm)		0.921	0.921	0.921	0.920	0.920	0.920.
	Extrusion Conditions, Bubble Stability, and Melt Fracture:							
10	Melt Temperature (°C)		211	222	227	221	222	226
15	Head Pressure (MPa) ((psi))		23(3350)	27(3900)	35(4950)	38(5400)	44(6250)	49(7000)
	% Amps		95	100	120	130	150	180
20	Die Rate (Rg/hr/rpm) ((lbs/hr/in))		1.5(8.2)	1.5(8.3)	1.6(8.8)	1.6(8.8)	1.7(9.4)	1.89(10.57)
	Specific Output Rate (Rg/hr/rpm) ((lbs/hr/rpm))		1.95(4.3)	1.95(4.3)	1.68(3.7)	2.09(4.6).	2.22(4.9)	2.54(5.6)
25	Bubble Stability		GOOD	GOOD	GOOD	GOOD	GOOD	GOOD
	Melt Fracture		NONE	NONE	NONE	NONE	NONE	GROSS
30	Film Properties: (25.4µm (1mil) film, 2:1 BUR)							
	Tensile Strength (MPa) ((psi))	MD	38(5400)	43(6200)	41(5800)	44(6300)	47(6700)	44(6300)
35		TD	27(3800)	30(4300)	32(4600)	41(5800)	41.3(5900)	43(6200)
	Elongation at break (%)	MD	550	500	550	600	600	600
		TD	800	750	800	800	800	800
40	Secant Modulus (MPa)((psi))	MD	259(37000)	273(39000)	271(38700)	280(40000)	252(36000)	266(38000)
		TD	322(46000)	315(45000)	329(97000)	336(48000)	308(444000)	308(44000)
45	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD	14929 (1800)	14929 (1800)	15759 (1900)	15759(1900)	16588(2000)	16588 (2000)
		TD	6635(800)	7465(900)	9953(1200)	10782(1300)	11612(1400)	11612 (1400)
50	Elmendorf Tear (gm/µm)((gm (mil))	MD	4.33(110)	6.89(175)	7.87 (200)	7.87(200)	9.06(230)	13.8(350)
		TD	38.6(980)	35.0 (890)	35.4 (900)	31.5 (800)	29.5(750)	27.6(700)
55	Puncture (load/µm) ((load/mil))		0.24(6.0)	0.28(7.0)	0.30(7.5)	0.31(8.0)	0.28(7.0)	0.33(8.5)

EP 0 773 258 B9

(continued)

	Percent by weight		100	90/10	70/30	50/50	30/70	10/90
5	Resin A/ ResinC		A	A/C	A/C	A/C	A/C	A/C
	Dart Drop (gm/ μ m) ((gm/mil))		4.72(120)	4.57(116)	4.09(104)	4.92(125)	5.0(127)	3.23(82)
10	Film Properties: (50.8 μ m (2 mil) film, 2:1 BUR)							
	Tensile Strength (MPa)((psi))	MD	32(4600)	33(4700)	27.3(3900)	42(6000)	39(5600)	45(6400)
15		TD	26(3700)	27(3800)	28(4000)	37(5300)	37(5300)	41(5800)
	Elongation at break (%)	MD	700	700	600	800	800	800
20		TD	900	800	850	900	900	850
	Secant Modulus (MPa)((psi))	MD	255(36400)	278(39700)	266(38000)	266(38000)	256(36500)	238(34000)
25		TD	294(42000)	306 (43700)	313 (44700)	335(47800)	301(43000)	294(42000)
	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD	13270 (1600)	14100 (1700)	15759 (1900)	16588(2000)	15759(1900)	16588 (2000)
30		TD	5806(700)	8294(1000)	10782 (1300)	12441(1500)	12441(1500)	12441 (1500)
	Elmendorf Tear (gm/ μ m) ((gm/mil))	MD	6.93(176)	9.06(230)	9.84(250)	11.8(300)	11.8(300)	15.7(400)
35		TD	21.7(550)	21.7(55)	27.6 (700)	23.6(600)	25.6(650)	23.6 (600)
	Puncture (load/ μ m) ((load/mil))		0.21(5.4)	0.24(6.0)	0.26(6.5)	0.28(7.0)	0.28(7.0)	0.28(7.0)
40	Dart Drop (gm/ μ m) ((gm/mil))		3.62(92)	4.21(107)	4.41(112)	4.92(125)	5.0(127)	4.17(106)
	Film Properties: (50.8 μ m (2 mil) film, 3:1 BUR)							
	Tensile Strength (MPa) ((psi))	MD	44(6300)	43(6100)	46(6500)	48(6800)	49(7000)	50(7200)
45		TD	29(4200)	34(4800)	36(5200)	35(5000)	41 (5800)	49(7000)
	Elongation at break (%)	MD	500	500	600	600	600	650
50		TD	700	700	700	775	750	775
	Secant Modulus (MPa)((psi))	MD	245(35000)	266(38000)	245(35000)	272(38800)	259(37000)	245(35000)
55		TD	307(43900)	291(41600)	298(42500)	312(44600)	301(43000)	273(39000)
	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD	17417 (2100)	15759 (1900)	14929 (1800)	16588(2000)	16588(2000)	15759 (1900)
		TD	14100 (1700)	10782 (1300)	14100 (1700)	13270(1600)	13270(1600)	14929 (1800)

EP 0 773 258 B9

(continued)

Percent by weight Resin A/ ResinC		100	90/10	70/30	50/50	30/70	10/90
		A	A/C	A/C	A/C	A/C	A/C
5	Elmendorf Tear	MD	5.51(140)	7.28(185)	13.8(350)	10.8(275)	15.7(400)
	(gm/μm)(gm/mil)	TD	39.4(1000)	39.4(1000)	27.6(700)	29.5(750)	27.6(700)
10	Puncture (load/mil)((load/μm))		0.26(6.5)	0.28(7.0)	0.28(7.0)	0.28(7.0)	0.28(7.0)
15	Dart Drop (gm/μm)((gm/mil))		4.53(115)	4.69(119)	5.28(134)	5.24(133)	5.91(150)
Film Properties: (50.8μm (2 mil) film, 3:1 BUR)							
20	Tensile Strength (MPa) ((psi))	MD	29(4100)	33(4700)	39(5500)	40(5700)	43(6100)
		TD	25(3500)	29(4100)	33 (4700)	36(5100)	37(5300)
25	Elongation at break (%)	MD	700	700	800	800	800
		TD	800	800	800	900	850
30	Secant Modulus (Mpa)((psi))	MD	252(36000)	245(35000)	263(37500)	280(40000)	259(37000)
		TD	282(40300)	301(43000)	271(38700)	300(42900)	273(39000)
35	Tensile Impact (x 10 ⁴ N/m ²) ((ft lbs/cu in))	MD	14100 (1700)	14929 (1800)	15759 (1900)	15759(1900)	14929(1800)
		TD	10782 (1300)	10782 (1300)	13270 (1600)	12441(1500)	13270(1600)
40	Elmendorf Tear (gm/μm)((gm/mil))	MD	10.2(260)	10.8(275)	13.8(350)	17.7(450)	17.7(450)
		TD	21.7(550)	23.6(600)	23.6(600)	23.6(600)	23.6(600)
45	Puncture (load/mil)((load/μm))		0.24(6.0)	0.24(6.0)	0.26(6.7)	0.28(7.0)	0.28(7.0)
	Dart Drop (gm/μm)((gm/mil))		5.43(138)	4.80(122)	5.83(148)	5.91(150)	6.14(156)

Table V

Percent	50/50	15/85	100
Resin A/Resin C	A/C	A/C	C
MI (gm/10 min)	0.8	1.0	0.9
HLMI (gm/10 min)	39	31.0	23.0
MFR	48	32.0	27.0
Density (gm/cu cm))	0.920	0.920	0.920

EP 0 773 258 B9

(continued)

Percent	50/50	15/85	100
Resin A/Resin C	A/C	A/C	C
Extrusion Conditions, Bubble Stability, and Melt Fracture:			
Screw RPM	36	45	10
Melt Temperature (°C)	221	231	226
Head Pressure (MPa) ((psi))	38 (5400)	41 (5900)	28 (4000)
Amps	130	155	95
Die Rate (kg/hr/cm) (lbs/hr/in))	1.6 (8.8)	2.0 (10.9)	0.6 (3.3)
Specific Output Rate (kg/hr/rpm) (lbs/hr/rpm)	2.09 (4.6)	2.09 (4.6)	2.86 (6.3)
Bubble Stability	GOOD	GOOD	GOOD
Melt Fracture	NONE	NONE	GROSS
<p>Notes to examples: 1. MI = melt index 2. HLMI = flow index 3. MFR = melt flow ratio 4. Bubble stability is determined by the speed of the line. The faster the speed (prior to failure) the better the bubble stability. 5. Blow-up ratio is the ratio of die diameter to bubble diameter. The bubble diameter is determined as follows: $2 \times \text{layflat} / \pi$. The "layflat" refers to the width of a flattened bubble. 6. Film gauge is the thickness of the film. The value is given in μm (mils) or (microns). 7. Dart impact (dart drop) is determined under ASTM D-1709, methods A and B. It is given in grams. 8. Elmendorf Tear is determined under ASTM D-1992. It is given in $9/\mu\text{m}$ (grams per mil). 9. MD = machine direction 10. TD = transverse direction 11. Tensile Strength is measured in accordance with ASTM D-882. 12. Elongation is measured in accordance with ASTM D-882. 13. Secant Modulus is measured in accordance with ASTM D-882. 14. Puncture resistance: the test is carried out with a metal cylinder, open at both ends, having a diameter of 75 millimeters and a length of 100 millimeters. One open end is covered with the sample film, which is held taut by a metal band surrounding that end of the cylinder (similar to a drum). The cylinder is placed in a vertical position with the film covered end up. Then, the film is pressed with the sharp point of a nail-like rod (5 millimeters in diameter and 150 millimeters in length) and a force is exerted against the film. When the film is broken, the force exerted is measured in grams. 15. STY kg/h ((lbs/hr/cu ft)) is the space time yield defined as the (pounds per hour) of polymer produced per cubic metre (per cubic foot) of fluidized bed.</p>			

Claims

1. A film which has been extruded to a gauge in the range of from 12.5 to 150 micrometres (0.5 to 6 mils), comprising a blend of (i) a linear low density polyethylene having a melt index in the range of from 0.3 to 3 grams per 10 0 minutes and a density in the range of from 0.900 to 0.940 gram per cubic centimeter and (ii) a multimodal resin

consisting of an in situ blend of copolymers of ethylene and one or more alpha-olefins having 3 to 8 carbon atoms, said resin having a flow index in the range of 40 to 150 grams per 10 minutes; a melt flow ratio in the range of 50 to 150; an Mw/Mn ratio of 8 to 22; and a density in the range of 0.908 to 0.930 gram per cubic centimeter wherein (a) the weight ratio of component (i) to component (ii) is in the range of from 1:1 to 3:1; (b) the blend has been
 5 extruded, under extrusion conditions, at a die rate in the range of from 1.4 to 2.7 kg per hour per centimeter (8 to 15 pounds per hour per inch) of die circumference and at a die gap in the range of from 0.088 to 0.125 cm (0.035 to 0.050 inch); and (c) the film exhibits essentially no melt fracture, component (ii) having been produced in situ by contacting the ethylene and one or more alpha-olefins with a magnesium/titanium based catalyst system in each of two reactors connected in series, under polymerisation conditions,
 10 wherein the relatively high molecular weight polymer formed in one reactor has a flow index in the range of from 0.2 to 6 grams per 10 minutes and a density in the range of from 0.900 to 0.940 gram per cubic centimeter and the relatively low molecular weight polymer formed in the other reactor has a melt index in the range of from 100 to 1500 grams per 10 minutes and a density in the range of from 0.905 to 0.970 gram per cubic centimeter, the weight ratio of high molecular weight polymer to the low molecular weight polymer being in the range of from
 15 0.67:1 to 1.5:1.

2. A film as claimed in claim 1 wherein component (ii) is produced under the following conditions:
 - (i) in the reactor in which the high molecular weight polymer is made: the mole ratio of alpha-olefin to ethylene is in the range of from 0.05:1 to 0.4:1 and the mole ratio of hydrogen, if used, to ethylene is in the range of from 0.0001:
 20 1 to 0.3:1; and
 - (ii) in the reactor in which the low molecular weight polymer is made: the mole ratio of alpha-olefin to ethylene is in the range of from 0.1:1 to 0.6:1 and the mole ratio of hydrogen to ethylene is in the range of from 1:1 to 2.5:1.
3. A process for preparing a film comprising a blend of (i) a linear low density polyethylene and (ii) an in situ blend of
 25 copolymers of ethylene and one or more alpha olefins having 3 to 8 carbon atoms as defined in claim 1 or 2 wherein the blend is extruded under extrusion conditions, at a die rate in the range of from 1.4 to 2.7 kg per hour per centimeter (8 to 15 pounds per hour per inch) of die circumference and at a die gap in the range of from 0.088 to 0.125 cm (0.035 to 0.050 inch).

Patentansprüche

1. Folie, die zu einer Dicke im Bereich von 12,5 bis 150 Micrometern (0,5 bis 6 mils) extrudiert wurde, umfassend eine
 35 Mischung aus (i) einem linearen Polyethylen geringer Dichte mit einem Schmelzindex im Bereich von 0,3 bis 3 Gramm pro 10 Minuten und einer Dichte im Bereich von 0,900 bis 0,940 Gramm pro Kubikzentimeter und (ii) ein multimodales Harz, bestehend aus einer in situ Mischung von Copolymeren von Ethylen und einem oder mehreren alpha-Olefinen mit 3 bis 8 Kohlenstoffatomen, wobei das Harz einen Flussindex im Bereich von 40 bis 150 Gramm pro 10 Minuten, ein Schmelzflussverhältnis im Bereich von 50 bis 150, ein Mw/Mn-Verhältnis von 8 bis 22 und eine Dichte im Bereich von 0,908 bis 0,930 Gramm pro Kubikzentimeter aufweist, wobei (a) das Gewichtsverhältnis von
 40 Verbindung (i) zu Verbindung (ii) im Bereich von 1:1 bis 3:1 liegt; (b) die Mischung unter Extrusionsbedingungen mit einer Düsenaustrittsrate im Bereich von 1,4 bis 2,7 kg pro Stunde pro Zentimeter (8 bis 15 Pfund pro Stunde pro Inch) des Düsenumfangs und bei einem Düsenpalt im Bereich von 0,088 bis 0,125 cm (0,035 bis 0,050 Inch) extrudiert wurde; und (c) die Folie im Wesentlichen keinen Schmelzbruch aufweist, Verbindung (ii) in situ hergestellt wurde, durch in Kontakt bringen des Ethylens und eines oder mehrerer alpha-Olefine mit einem Katalysatorsystem auf Magnesium/Titan-Basis in jedem von zwei in Serien verbundenen Reaktorsystemen unter Polymerisationsbedingungen, wobei das in einem Reaktor gebildete Polymer mit relativ hohem Molekulargewicht einen Flussindex im Bereich von 0,2 bis 6 Gramm pro 10 Minuten und eine Dichte im Bereich von 0,900 bis 0,940 Gramm pro Kubikzentimeter aufweist und das in dem anderen Reaktor gebildete Polymer mit relativ geringem Molekulargewicht einen Schmelzindex im Bereich von 100 bis 1500 Gramm pro 10 Minuten und
 50 eine Dichte im Bereich von 0,905 bis 0,970 Gramm pro Kubikzentimeter aufweist, wobei das Gewichtsverhältnis des Polymers mit hohem Molekulargewicht zu dem Polymer mit niedrigerem Molekulargewicht im Bereich von 0,67:1 bis 1,5:1 liegt.
2. Folie nach Anspruch 1, worin Verbindung (ii) unter folgenden Bedingungen hergestellt wird:
 55
 - (i) in dem Reaktor, in welchem das Polymer mit hohem Molekulargewicht hergestellt wird: das Molverhältnis von alpha-Olefin zu Ethylen liegt im Bereich von 0,05:1 bis 0,4:1 und das Molverhältnis von Wasserstoff, wenn verwendet, zu Ethylen liegt im Bereich von 0,0001:1 bis 0,3:1; und

(ii) in dem Reaktor, in welchem das Polymer mit niedrigem Molekulargewicht hergestellt wird: das Molverhältnis von alpha-Olefin zu Ethylen liegt im Bereich von 0,1:1 bis 0,6:1 und das Molverhältnis von Wasserstoff zu Ethylen liegt im Bereich von 1:1 bis 2,5:1.

- 5 3. Verfahren zur Herstellung einer Folie, umfassend eine Mischung aus (i) einem linearen Polyethylen geringer Dichte und (ii) einer in situ Mischung von Copolymeren von Ethylen und einem oder mehreren alpha-Olefinen mit 3 bis 8 Kohlenstoffatomen wie in Anspruch 1 oder 2 definiert, wobei die Mischung unter Extrusionsbedingungen mit einer Düsenaustrittsrate im Bereich von 1,4 bis 2,7 kg pro Stunde pro Zentimeter (8 bis 15 Pfund pro Stunde pro Inch) des Düsenumfangs und bei einem Düsenpalt im Bereich von 0,088 bis 0,125 cm (0,035 bis 0,050 Inch) extrudiert wurde.

Revendications

- 15 1. Film qui a été extrudé en une épaisseur de 12,5 à 150 micromètres (0,5 à 6 millièmes de pouce), qui comprend un alliage

i) d'un polyéthylène basse densité linéaire présentant un indice de fluidité à chaud de 0,3 à 3 grammes par 10 minutes et une masse volumique de 0,900 à 0,940 gramme par centimètre cube,

20 ii) et d'une résine multimodale qui consiste en un mélange formé *in situ* de copolymères d'éthylène et d'une ou plusieurs alpha-oléfines comportant de 3 à 8 atomes de carbone, ladite résine présentant un indice d'écoulement de 40 à 150 grammes par 10 minutes, un rapport de vitesses d'écoulement de 50 à 150, un rapport Mw/Mn de 8 à 22, et une masse volumique de 0,908 à 0,930 gramme par centimètre cube,

25 dans lequel film

a) le rapport pondéral du composant (i) au composant (ii) vaut de 1/1 à 3/1,

30 b) l'alliage a été extrudé dans les conditions suivantes : un débit de filière de 1,4 à 2,7 kilogrammes par heure et par centimètre de pourtour de filière (8 à 15 livres par heure et par pouce), et un écartement de filière de 0,088 à 0,125 cm (0,035 à 0,050 pouce),

c) et il n'y a pratiquement pas de rupture d'extrudat,

35 et pour lequel film on a produit le composant (ii) *in situ* en mettant de l'éthylène et une ou plusieurs alpha-oléfines servant de comonomère(s) en contact avec un système catalyseur à base de magnésium et de titane, dans l'un et l'autre de deux réacteurs raccordés en série, dans des conditions de polymérisation, le polymère à masse moléculaire relativement élevée, formé dans l'un de ces réacteurs, présentant un indice d'écoulement de 0,2 à 6 grammes par 10 minutes et une masse volumique de 0,900 à 0,940 gramme par centimètre cube, et le polymère à masse moléculaire relativement faible, formé dans l'autre réacteur, présentant un indice de fluidité à chaud de 100 à 1500 grammes par 10 minutes et une masse volumique de 0,905 à 0,970 gramme par centimètre cube,

40 le rapport pondéral du polymère à masse moléculaire élevée au polymère à faible masse moléculaire valant de 0,67/1 à 1,5/1.

2. Film conforme à la revendication 1, pour lequel le composant (ii) a été produit dans les conditions suivantes :

45 i) dans le réacteur dans lequel se forme le polymère à masse moléculaire élevée, le rapport molaire alpha-oléfine/éthylène vaut de 0,05/1 à 0,4/1, et si l'on emploie de l'hydrogène, le rapport molaire hydrogène/éthylène vaut de 0,0001/1 à 0,3/1 ;

50 ii) dans le réacteur dans lequel se forme le polymère à faible masse moléculaire, le rapport molaire alpha-oléfine/éthylène vaut de 0,1/1 à 0,6/1, et le rapport molaire hydrogène/éthylène vaut de 1/1 à 2,5/1.

3. Procédé de fabrication d'un film comprenant un alliage

i) d'un polyéthylène basse densité linéaire

55 ii) et d'un mélange formé *in situ* de copolymères d'éthylène et d'une ou plusieurs alpha-oléfines comportant de 3 à 8 atomes de carbone,

conforme à la revendication 1 ou 2,

dans lequel procédé l'on extrude l'alliage dans les conditions suivantes : un débit de filière de 1,4 à 2,7 kilogrammes

EP 0 773 258 B9

par heure et par centimètre de pourtour de filière (8 à 15 livres par heure et par pouce), et un écartement de filière de 0,088 à 0,125 cm (0,035 à 0,050 pouce).

5

10

15

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 5210142 A [0005]
- US 4101445 A [0011]
- US 4302565 A [0011] [0018]
- US 4508842 A [0011]
- US 5290745 A [0018] [0050] [0066]
- US 5106926 A [0024] [0025]
- US 4482687 A [0029]