

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 796 947 B9

(12)

CORRECTED EUROPEAN PATENT SPECIFICATION

Note: Bibliography reflects the latest situation

(15) Correction information:

Corrected version no 1 (W1 B1)
Corrections, see page(s) 8

(51) Int Cl.7: **D21H 19/36, B41M 5/00**

(48) Corrigendum issued on:

05.11.2003 Bulletin 2003/45

(45) Date of publication and mention
of the grant of the patent:

04.06.2003 Bulletin 2003/23

(21) Application number: **97301943.3**

(22) Date of filing: **21.03.1997**

(54) **Cast-coated paper and production method thereof**

Giessbeschichtetes Papier und Verfahren zur Herstellung

Papier couché par moulage et procédé de fabrication

(84) Designated Contracting States:

DE FI FR GB

(30) Priority: **22.03.1996 JP 9181896**

(43) Date of publication of application:

24.09.1997 Bulletin 1997/39

(73) Proprietor: **NIPPON PAPER INDUSTRIES CO., LTD.**

Kita-ku, Tokyo (JP)

(72) Inventors:

- **Omura, Tomonobu, Nippon Paper Industries Co. Ltd. Shinjuku-ku, Tokyo (JP)**
- **Ueno, Takashi, Nippon Paper Industries Co. Ltd. Shinjuku-ku, Tokyo (JP)**
- **Teramasa, Toshikazu, Nippon Paper Ind. Co. Ltd. Shinjuku-ku, Tokyo (JP)**
- **Kuroyama, Yoshihiro, Nippon Paper Ind. Co. Ltd. Shinjuku-ku, Tokyo (JP)**

(74) Representative: **Bubb, Antony John Allen et al**

**Wilson Gunn Gee,
Chancery House,
Chancery Lane
London WC2A 1QU (GB)**

(56) References cited:

- **DATABASE WPI Section Ch, Week 9719 Derwent Publications Ltd., London, GB; Class F09, AN 97-209872 XP002031323 & JP 09 059 897 A (NIPPON SEISHI KK) , 4 March 1997**
- **DATABASE WPI Section Ch, Week 9709 Derwent Publications Ltd., London, GB; Class E16, AN 97-095013 XP002031324 & JP 08 332 771 A (NIPPON SEISHI KK) , 17 December 1996**
- **DATABASE WPI Section Ch, Week 9614 Derwent Publications Ltd., London, GB; Class A82, AN 96-135081 XP002031321 & JP 08 025 799 A (NIPPON SEISHI KK) , 30 January 1996**
- **DATABASE WPI Section Ch, Week 8723 Derwent Publications Ltd., London, GB; Class A14, AN 87-160425 XP002031322 & JP 62 095 285 A (SANYO KOKUSAKU PULP CO) , 1 May 1987**
- **DATABASE WPI Section Ch, Week 9648 Derwent Publications Ltd., London, GB; Class A82, AN 96-482803 XP002031325 & JP 08 246 392 A (OJI PAPER CO) , 24 September 1996**
- **DATABASE WPI Section Ch, Week 9051 Derwent Publications Ltd., London, GB; Class F09, AN 90-379954 XP002031326 & JP 02 274 587 A (SANYO KOKUSAKU PULP CO) , 8 November 1990**
- **DATABASE WPI Section Ch, Week 9140 Derwent Publications Ltd., London, GB; Class A97, AN 91-291899 XP002031327 & JP 03 193 995 A (SANYO KOKUSAKU PULP CO) , 23 August 1991**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 796 947 B9

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Description

[0001] The present invention relates to a cast-coated paper.

[0002] A cast-coated paper is generally obtained by applying a coating solution containing a pigment and an aqueous binder to at least one side of a raw paper and pressing the resultant coating to a heated specular metal surface while it is in a wet state to copy the specular metal surface on the coating and at the same time to dry the coated paper. The cast-coated paper thus obtained has a feature of high gloss and high smoothness, compared with general coated papers which are finished with a super calender. Accordingly, it gives very excellent printing effect when used in printing and high-quality feeling when used for packaging material.

[0003] Further, in the field of full color image recording paper and the like whose market are developing now, the recording paper having high gloss has been produced by using a film as substrate or by adopting a wet-type lamination technique or a multilayer coating technique. In comparison with those production methods, a cast coating method is favorable in terms of cost and simplicity of processes. However, it has a drawback of being inferior in productivity to the method for producing a general coated paper.

[0004] More specifically, in the cast coating method, a coated paper requires to be dried while the wet coating is pressed to the specular surface of metal. Consequently, the water contained in the coating should pass through a raw paper and evaporate on the back side of the paper. In case where a general coated paper is produced, on the other hand, water is evaporated on the front side or both sides of the coating. Therefore, drying efficiency in the cast coating method is far lower than that in the preparation of a general coated paper; as a result, a cast-coated paper should be produced at a low speed, and thereby the productivity thereof becomes low.

[0005] For the purpose of improving drying efficiency in the cast coating method, it was proposed to increase the permeability of a raw paper in, e.g., Japanese Tokkai Sho 56-26094 and Japanese Tokkai Hei 3-193995 (The term "Tokkai" as used herein means an "unexamined published patent application"). However, the coatings of the cast-coated papers disclosed therein have a high coverage rate of from 10 to 30 g/m², so that a lot of water to be evaporated is present therein. On this account, the aforementioned means cannot sufficiently improve the productivity.

[0006] Further, the inferiority of the cast coating method in productivity is due to low capability in continuous operation, too.

[0007] More specifically, in the production of a cast-coated paper, the releasability of paper web from a specular metal surface gradually deteriorates with the passage of time; as a result, the coating is partially picked off by the metal surface, namely the so-called "drum pick" is caused.

[0008] When the drum pick occurs, the paper web is broken in a short time and at the same time the specular metal surface becomes dirty in most cases. Consequently, the operation is interrupted for a long period of time for cleaning the specular metal surface.

[0009] In this connection, the specular surface of metal has so far been coated with a release agent, such as vegetable hardened oil, vegetable oxidized oil, tributyl phosphate, xylene, terpene, monochlorobenzene and their derivatives, to maintain good releasability of the specular metal surface from paper web.

[0010] Further, there has been added a release agent, such as stearic acid, polyethylene, polypropylene, paraffin, silicone oil and their derivatives, to a coating solution, a coagulating solution or a re-wetting solution to obtain good releasability of paper web.

[0011] However, even when the above treatments for enhancing the releasability are carried out, the releasability of paper and that of specular metal surface are gradually deteriorated with a lapse of time.

[0012] Reasons therefor are considered as follows:

- a) A release agent applied to the specular surface of metal gradually shifts into the coating to lose its effect, and
- b) A slight portion of the coating remains on a specular metal surface every time paper web is released from the specular surface, and its accumulation on the specular surface makes it impossible to copy the specular surface and at the same time to lose the releasability from each other.

[0013] In an ink-jet recording system, on the other hand, images are formed on a recording paper by jetting droplets of ink in various ways, and such a recording system has features that it makes less noise than dot impact recording system and enables easy full color recording and high-speed recording.

[0014] Usually, an ink-jet recording system uses a water-base ink in most cases, and so it has a disadvantage of being inferior in drying properties of ink.

[0015] Therefore, it is required for the recording paper used for ink-jet recording system to have the following characteristics:

- a) high drying speed of ink,
- b) neither feathering nor overflow of ink,

- c) high recording density, and
- d) no cockle generation due to absorption of ink.

[0016] It has already been proposed to produce ink-jet recording papers having all of those characteristics using a cast coating method (Japanese Tokkai Sho 62-95258, Japanese Tokkai Sho 62-264391, Japanese Tokkai Hei 2-274587 and Japanese Tokkai Hei 5-59684).

[0017] However, the cast-coated papers for ink-jet recording contain as the main pigment component a porous synthetic silica of large specific surface area, so that they absorb a great amount of release accelerating material to cause frequent paper break, thereby suffering a great drop in productivity, compared with cast-coated papers using other pigments as their main pigment component.

[0018] JP-A-08025799 discloses a cast-coated paper for ink-jet recording, which comprises a base paper at least one surface of which is coated with a recording layer comprising a binder and a pigment containing synthetic silica as a main component and dried by pressing the recording layer surface against a hot specular surface while the recording layer is in a wet condition. The base paper has a basis weight of from 80 to 150 g/m², a freeness of from 290 to 450 ml and a filler content in the range $28 - (\text{freeness}/20) \leq \text{filler content (\%)} \leq 32 - (\text{freeness}/20)$.

[0019] Therefore, a first object of the present invention is to provide a cast coated paper which not only has good quality but also ensures high productivity.

[0020] A second object of the present invention is to provide a method of producing a cast-coated paper which can realize a continuous operation of a long duration to ensure high productivity.

[0021] The above objects of the present invention are attained by a cast-coated paper according to claim 1, and a method of producing the cast coated paper according to claim 6.

DETAILED DESCRIPTION OF THE INVENTION

[0022] The method of the present invention belongs to a coagulating process among cast coating processes. This coagulating process means a process comprising the steps of applying a coating composition to a raw paper, coagulating the resultant coating into a gel state having no fluidity, pressing the coagulated coating to a hot specular surface of metal to copy the specular metal surface on the surface of the coating. In this process, the coating coagulates through the salting-out of a water base binder contained therein, such as casein, by the use of a salt solution (coagulant).

[0023] Hitherto, in cases where cast-coated papers are produced adopting a coagulating process, metal salts of formic acid such as calcium formate and zinc formate have been prevalently used as coagulant because they have high solubility in water and excellent salting-out effect; while ammonium salts have never been used because of their low coagulability.

[0024] However, the present inventors have carefully studied to find the following:

[0025] In case where a metal salt conventionally used as the coagulant is employed, the metal salt accumulates on the specular surface of metal to lose good releasability of the metal surface from paper web; as a result, the breaking of paper web occurs in high frequency. In contrast to the above case, when an ammonium salt is used as coagulant, the ammonium salt decomposes on heating to discharge its base moiety in the form of ammonia into the atmosphere, so that it cannot be present in the form of salt at the time of the release of paper web from the specular surface of metal.

[0026] Accordingly, when an ammonium salt is used as coagulant, the salt will never accumulate on the specular surface of metal to maintain good releasability of paper from the specular surface of metal, and thereby the breaking of paper occurs in a reduced frequency.

[0027] Specific examples of an ammonium salt usable as a coagulant in the present invention includes the ammonium salts of formic acid, acetic acid, sulfuric acid, hydrochloric acid, nitric acid and phosphoric acid. In the present invention, at least one ammonium salt selected from the above-recited salts can be used.

[0028] Since an ammonium salt has less ability to coagulate a coating than conventionally used metal formates, the coagulation treatment performed with the ammonium salt cannot achieve the same gel state as usual so long as the ammonium salt is used in the same concentration as conventional metal formates, and so the product quality will be deteriorated. However, the gel state equivalent to the hitherto attained gel state can be accomplished by heightening the concentration of an ammonium salt as coagulant to ensure as good surface gloss and high surface strength as the conventional coagulants.

[0029] The concentration of an ammonium salt or ammonium salts used as the coagulant should be changed depending on the usage of a cast coated paper produced, and on the recipe for a coating composition used, the solids concentration therein, the coverage rate thereof and so on. In the present invention, the ammonium salt concentration in the coagulating solution is chosen so as not to adversely affect the product quality, the shelf stability and the capability in a continuous operation during the production. Specifically, the ammonium salt concentration is adjusted to the range of 2 to 40 % by weight, preferably 5 to 30 % by weight.

[0030] In other words, the use of an ammonium salt within the above concentration range can give the surface of a

coating and the interior of a paper the same structures and properties as those obtained respectively in the case of using the conventional metal salts of formic acid and so on, thereby ensuring good properties with respect to surface gloss, surface strength and so on.

[0031] When the ammonium salt used is less than 2 % by weight, the coating composition cannot coagulate sufficiently, so that part or all of the coating remaining uncoagulated will be squeezed out upon press of the resultant coating to the specular surface of metal. Accordingly, the layer having a high gloss surface, which is one of the great advantages of a cast-coated paper, cannot be obtained.

[0032] When the concentration of an ammonium salt as the coagulant exceeds 40 % by weight, on the other hand, the pyrolysis of the ammonium salt cannot proceed sufficiently in the drying step to leave some portion of ammonium salt on the dried coating surface. Consequently, not only productivity will be lowered as described before but also ammonia will be discharged progressively from a product to considerably deteriorate the quality of the product. Further, the increase in an amount of the coagulant adhering to a paper lowers the pH of the paper to give rise to a fear of deteriorating shelf stability of the product.

[0033] In addition, conventional coagulants can be used together with the ammonium salt of the present invention, if desired.

[0034] Specific examples of a coagulant usable together with the present ammonium salt includes acids, such as formic acid, acetic acid, citric acid, lactic acid, hydrochloric acid, sulfuric acid, carbonic acid and boric acid; the salts of those acids and metals such as calcium, zinc, barium, lead, potassium, sodium, cadmium and aluminum; and borax. When these coagulants are used together with an ammonium salt, however, the capability in continuous operation is somewhat shortened in some cases, compared with the independent use of the ammonium salt.

[0035] Specific examples of a water base binder used in the present invention include starch such as oxidized starch or esterified starch; cellulose derivatives such as carboxymethyl cellulose and hydroxyethyl cellulose; polyvinyl alcohol resin; polyvinyl pyrrolidone; casein; gelatin; soybean protein; styrene-acrylic resin; styrene-butadiene latex; acrylic resin; vinyl acetate resin; vinyl chloride resin; urea resin; alkyd resin; urethane resin; polyethylene; and the derivatives of those resins. In the present invention, one or more of a water base binder selected properly from the above-recited ones can be used.

[0036] The coating composition employed in the present invention, wherein at least the aforementioned pigment and water base binder are contained, is generally prepared in the form of an aqueous coating composition. An appropriate ratio between those ingredients is different depending on the binder composition, the pigment composition, the coating condition and so on, but it has no particular limitation as far as the cast-coated paper produced can satisfy the quality required for the intended use thereof. Further, the coating composition according to the present invention can optionally contain additives, such as a dispersant, a water retaining agent, a thickening agent, an anti-foaming agent, a preservative, a colorant, a waterproofing agent, a wetting agent, a drying agent, an initiator, a plasticizer, a fluorescent dye, an ultraviolet absorbent, a release agent, a lubricant and a cationic polyelectrolyte.

[0037] The suitable coating system for the present invention can be selected from among conventional coating systems, such as those using a blade coater, an air-knife coater, a roll coater, a comma coater, a bar coater, a gravure coater or so on.

[0038] When the present coating has a low coverage rate, it may fail to provide a good cast-coated surface. Oppositely, the excessive coverage rate may cause defects on the cast-coated surface due to the poor coagulation of the wetted coating, or it may require a reduction of the coating speed because the amount of water to be evaporated is large. Accordingly, it is desirable for the coverage rate to be in the range of 10 to 30 g/m², but the present cast-coated paper can also be produced choosing the coverage rate from a range beyond the foregoing limits under some particular conditions concerning the sizing degree, permeability, smoothness and basis weight of a raw paper used, and the composition, viscosity and solids concentration of a coating composition used.

[0039] In accordance with the present invention, a cast-coated paper can be produced by preparing a coating composition containing a pigment and a water base binder, applying the coating composition to at least one side of a raw paper, treating the resultant coating with a coagulating solution containing ammonium salt (s) as a coagulant, pressing the coating treated to the cylindrical specular metal surface of a drum heated to about 100°C while the treated coating is in a wet condition.

[0040] Additionally, it will be understood without any further explanation that the aforementioned coating can be provided on both sides of a raw paper to prepare a double-sided recording paper.

[0041] The cast-coated paper of the present invention, has good quality, and can be produced with excellent productivity because it has remarkably improved capability in the continuous operation during the production thereof.

[0042] The present invention will now be illustrated in more detail by reference to the following examples. Unless otherwise indicated all percentages and all parts are by weight.

EP 0 796 947 B9 (W1B1)

Preparation of Coating Compositions:

Coating Composition A;

5 **[0043]** 100 parts of kaolin as a pigment, 15 parts of styrene-butadiene latex (made by Japan Synthetic Rubber CO., Ltd., trade name: JSR-0617) and 10 parts of casein (a product of New Zealand) as a binder, 5 parts of calcium stearate (made by San Nopco Ltd., trade name: Nopcoat SYC) as a release agent and 0.5 part of anti-foaming agent were mixed to prepare an aqueous Coating Composition A having a solids concentration of 45 %.

10 Coating Composition B;

15 **[0044]** 100 parts of kaolin as a pigment, 30 parts of styrene-butadiene latex (made by Japan Synthetic Rubber CO., Ltd., trade name: JSR-0617) and 10 parts of casein (a product of New Zealand) as a binder, 5 parts of calcium stearate (made by San Nopco Ltd., trade name: Nopcoat SYC) as a release agent and 0.5 part of anti-foaming agent were mixed to prepare an aqueous Coating Composition B having a solids concentration of 45 %.

Coating Composition C;

20 **[0045]** A mixture of 80 parts of kaolin and 20 parts of calcium carbonate as a pigment, 15 parts of styrene-butadiene latex (made by Japan Synthetic Rubber CO., Ltd., trade name: JSR-0617) and 10 parts of casein (a product of New Zealand) as a binder, 5 parts of calcium stearate (made by San Nopco Ltd., trade name: Nopcoat SYC) as a release agent and 0.5 part of anti-foaming agent were mixed to prepare an aqueous Coating Composition C having a solids concentration of 45 %.

25 Preparation of Coagulating Solution:

Coagulating Solution (1);

30 **[0046]** A coagulating solution containing 10% of ammonium sulfate as a coagulant and 0.5% of a release agent (Nopcoat SYC) was prepared.

Coagulating Solution (2);

35 **[0047]** A coagulating solution containing 10% of ammonium formate as a coagulant and 0.5% of a release agent (Nopcoat SYC) was prepared.

Coagulating Solution (3);

40 **[0048]** A coagulating solution containing 20% of ammonium sulfate as a coagulant and 0.5% of a release agent (Nopcoat SYC) was prepared.

Coagulating solution (4);

45 **[0049]** A coagulating solution containing 10% of calcium formate as a coagulant and 0.5% of a release agent (Nopcoat SYC) was prepared.

Coagulating Solution (5);

50 **[0050]** A coagulating solution containing 20% of zinc sulfate as a coagulant and 0.5% of a release agent (Nopcoat SYC) was prepared.

EXAMPLE 1

55 **[0051]** The Coating Composition A was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (1). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

EXAMPLE 2

[0052] The Coating Composition B was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (1). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

EXAMPLE 3

[0053] The Coating Composition C was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (1). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

EXAMPLE 4

[0054] The Coating Composition A was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (2). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

EXAMPLE 5

[0055] The Coating Composition A was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (3). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

COMPARATIVE EXAMPLE 1

[0056] The Coating Composition A was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (4). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

COMPARATIVE EXAMPLE 2

[0057] The Coating Composition C was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (4). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

COMPARATIVE EXAMPLE 3

[0058] The Coating Composition A was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (5). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

COMPARATIVE EXAMPLE 4

[0059] The Coating Composition C was coated on one side of a raw paper at a coverage rate of 18 g/m² by means of a comma coater, and then treated with Coagulating Solution (5). The thus treated coating was pressed to the specular metal surface heated to 100°C while the coating was in a wet condition, and dried to produce a cast-coated paper.

[0060] Each of Examples 1 to 5 and Comparative Examples 1 to 4 were examined for the capability in a continuous operation, the surface gloss of the coating formed and the pH on the surface of the coating. The criteria employed for evaluation of those properties are as follows:

i) Capability in Continuous Operation:

[0061] A comparison of the capability of cast-coated paper samples in continuous operation is made by examining a duration of the coating operation (or the length of paper web coated without any break). The data set forth in Table 1 are relative values, taking the cast-coated paper produced in Comparative Example 1 as the standard. The larger the value, the higher the capability in continuous operation. The value of no smaller than 1.4 indicates a remarkable improvement in the capability of a cast-coated paper in continuous operation.

ii) Surface Gloss of Coating:

[0062] The surface gloss, which is one of the most prominent features of a cast-coated paper, is evaluated by the 75° gloss on the coating surface determined in accordance with JIS P-8142.

iii) pH on Surface of Coating:

[0063] A coagulant applied in excess may leave an acid on or inside the coating after the production of a cast-coated paper. The acid, as mentioned hereinbefore, adversely affects on shelf stability of the cast coated paper produced. Therefore, pH on the surface of the coating is examined, and evaluated in accordance with TAPPI UM-471. If the pH on the surface of a coating is from 6 to 8, the resultant cast-coated paper causes no trouble in self stability.

[0064] The results obtained are shown in Table 1.

Table 1

	Coating Composition	Coagulating Solution	Capability in Continuous Operation	Surface of Coating	
				surface Gloss (%)	pH
Example 1	A	(1)	3.0	89.1	6.5
Example 2	B	(1)	3.2	93.0	6.5
Example 3	C	(1)	3.0	88.5	6.5
Example 4	A	(2)	3.1	87.7	6.7
Example 5	A	(3)	2.9	90.3	6.3
Compar.Ex.1	A	(4)	1.0	90.1	6.9
Compar.Ex.2	C	(4)	1.1	89.3	6.9
Compar.Ex.3	A	(5)	1.0	89.0	6.9
Compar.Ex.4	C	(5)	1.0	88.4	6.9

[0065] The data shown in Table 1 demonstrate the effectiveness of the present invention. ~~[deletion(s)]~~

Claims

1. A cast coated paper which comprises a raw paper having on at least one side thereof a layer of a coating composition consisting of a pigment selected from kaolin, talc, calcium carbonate, calcium acetate, titanium dioxide, clay, zinc oxide, alumina, aluminium hydroxide and mixtures thereof, a water base binder and optionally one or more of a dispersant, a water retaining agent, a thickening agent, an anti foaming agent, a preservative, a colorant, a waterproofing agent, a wetting agent, a drying agent, an initiator, a plasticizer, a fluorescent dye, an ultraviolet absorbent, a release agent, a lubricant and a cationic polyelectrolyte, and having a surface treated with a coagulating solution containing a coagulant and smoothened by pressing the treated surface to a hot specular surface of metal while the layer is in a wet condition, wherein the coagulant is one or more of an ammonium salt.
2. A cast-coated paper according to Claim 1, wherein the coagulant is at least one ammonium salt selected from a group consisting of ammonium formate, ammonium acetate, ammonium, sulfate, ammonium chloride, ammonium nitrate and ammonium phosphate.
3. A cast-coated paper according to either Claim 1 or 2, wherein the coagulant is ammonium formate, ammonium sulfate or a mixture thereof.
4. A cast-coated paper according to any preceding claim, wherein the coagulating solution has an ammonium salt concentration of from 2 to 40% by weight.
5. A cast-coated paper according to any preceding claim, wherein the coagulating solution is free of water proofing

agents.

6. A method of producing a cast coated paper comprising the steps of

applying a coating composition consisting of a pigment selected from kaolin, talc, calcium carbonate, calcium acetate, titanium dioxide, clay, zinc oxide, alumina, aluminium hydroxide and mixtures thereof a water base binder and optionally one or more of a dispersant, a water retaining agent, a thickening agent, an anti foaming agent, a preservative, a colorant, a waterproofing agent, a wetting agent, a drying agent, an initiator, a plasticizer, a fluorescent dye, an ultraviolet absorbent, a release agent, a lubricant and a cationic polyelectrolyte, to at least one side of a raw paper to form a layer, treating the layer with a coagulating solution containing one or more of an ammonium salt in a proportion of from 2 to 40% by weight, and pressing the treated layer surface to a hot specular surface of metal while the layer is in a wet condition.

7. A method according to Claim 6, wherein the coagulating solution is free of water proofing agent.

Patentansprüche

1. Gießbeschichtetes Papier, bestehend aus einem Rohpapier mit einer an wenigstens einer Seite davon vorgesehenen Schicht einer Beschichtungszusammensetzung bestehend aus einem Pigment gewählt aus Kaolin, Talk, Kalziumkarbonat, Kalziumazetat, Titandioxid, Ton, Zinkoxid, Aluminiumoxid, Aluminiumhydroxid und Mischungen davon, einem Binder auf Wasserbasis und optional einem oder mehreren von einem Dispergiermittel, einem Wasserhaltemittel, einem Verdickungsmittel, einem Antischaummittel, einem Konservierungsmittel, einem Färbemittel, einem wassersperrenden Mittel, einem Benetzungsmittel, einem Trockenmittel, einem Initiator, einem Weichmacher, einem Fluoreszenzfarbstoff, einem Ultraviolettabsorptionsmittel, einem Trennmittel, einem Schmiermittel und einem kationischen Polyelektrolyten, und mit einer Oberfläche, die mit einer Koagulierlösung enthaltend ein Koagulationsmittel behandelt und durch Pressen der behandelten Oberfläche gegen eine heiße spiegelnde Metallfläche, während die Schicht im nassen Zustand ist, geglättet wurde, wobei das Koagulationsmittel eines oder mehrere eines Ammoniumsalzes ist.

2. Gießbeschichtetes Papier nach Anspruch 1, wobei das Koagulationsmittel wenigstens ein Ammoniumsalz aus einer Gruppe bestehend aus Ammoniumformiat, Ammoniumazetat, Ammoniumsulfat, Ammoniumchlorid, Ammoniumnitrat und Ammoniumphosphat ist.

3. Gießbeschichtetes Papier nach Anspruch 1 oder 2, wobei das Koagulationsmittel Ammoniumformiat, Ammoniumsulfat oder eine Mischung davon ist.

4. Gießbeschichtetes Papier nach einem der vorangehenden Ansprüche, wobei die Koagulationslösung eine Ammoniumsalzkonzentration von 2 - 40 Gewichts-% aufweist.

5. Gießbeschichtetes Papier nach einem der vorangehenden Ansprüche, wobei die Koagulationslösung frei von wassersperrenden Mitteln ist.

6. Verfahren zur Herstellung eines gießbeschichteten Papiers, umfassend die Schritte:

Aufbringen einer Beschichtungszusammensetzung bestehend aus einem Pigment gewählt aus Kaolin, Talk, Kalziumkarbonat, Kalziumazetat, Titandioxid, Ton, Zinkoxid, Aluminiumoxid, Aluminiumhydroxid und Mischungen davon, einem Binder auf Wasserbasis und optional einem oder mehreren von einem Dispergiermittel, einem Wasserhaltemittel, einem Verdickungsmittel, einem Antischaummittel, einem Konservierungsmittel, einem Färbemittel, einem wassersperrenden Mittel, einem Benetzungsmittel, einem Trockenmittel, einem Initiator, einem Weichmacher, einem Fluoreszenzfarbstoff, einem Ultraviolettabsorptionsmittel, einem Trennmittel, einem Schmiermittel und einem kationischen Polyelektrolyten, auf wenigstens eine Seite eines Rohpapiers zur Ausbildung einer Schicht, Behandeln der Schicht mit einer Koagulierlösung enthaltend eines oder mehrere eines Ammoniumssalzes in einem Verhältnis von 2 - 40 Gewichts-%, und Pressen der behandelten Oberflächenschicht auf eine heiße spiegelnde Metalloberfläche, während die Schicht im nassen Zustand ist.

7. Verfahren nach Anspruch 6, wobei die Koagulierlösung frei von einem wassersperrenden Mittel ist.

Revendications

1. Papier couché à haut brillant qui comprend un papier brut ayant sur au moins une de ses faces une couche d'une composition de revêtement consistant en un pigment choisi parmi le kaolin, le talc, le carbonate de calcium, l'acétate de calcium, le dioxyde de titane, l'argile, l'oxyde de zinc, l'alumine, l'hydroxyde d'aluminium et des mélanges de ceux-ci, un liant à base aqueuse et en option un ou plusieurs parmi un dispersant, un agent de rétention d'eau, un épaississant, un agent anti-mousse, un conservateur, un colorant, un agent imperméabilisant, un mouillant, un agent siccatif, un initiateur, un plastifiant, un colorant fluorescent, un absorbant ultraviolet, un agent anti-adhésif, un lubrifiant et un polyélectrolyte cationique, et ayant une surface traitée avec une solution coagulante contenant un coagulant et lissée en pressant la surface traitée contre une surface de métal spéculaire chaude alors que la couche est à l'état humide, dans lequel le coagulant est un ou plusieurs d'un sel d'ammonium.
2. Papier couché à haut brillant selon la revendication 1, dans lequel le coagulant est au moins un sel d'ammonium choisi parmi un groupe constitué du formate d'ammonium, de l'acétate d'ammonium, du sulfate d'ammonium, du chlorure d'ammonium, du nitrate d'ammonium et du phosphate d'ammonium.
3. Papier couché à haut brillant selon l'une des revendications 1 et 2, dans lequel le coagulant est du formate d'ammonium, du sulfate d'ammonium ou un mélange de ceux-ci.
4. Papier couché à haut brillant selon l'une quelconque des revendications précédentes, dans lequel la solution coagulante a une concentration en sel d'ammonium de 2 à 40 % en poids.
5. Papier couché à haut brillant selon l'une quelconque des revendications précédentes, dans lequel la solution coagulante est exempte d'agents imperméabilisants.
6. Procédé de production d'un papier couché à haut brillant comprenant les étapes consistant à :
- appliquer une composition de revêtement consistant en un pigment choisi parmi le kaolin, le talc, le carbonate de calcium, l'acétate de calcium, le dioxyde de titane, l'argile, l'oxyde de zinc, l'alumine, l'hydroxyde d'aluminium et des mélanges de ceux-ci, un liant à base aqueuse et en option un ou plusieurs parmi un dispersant, un agent de rétention d'eau, un épaississant, un agent anti-mousse, un conservateur, un colorant, un agent imperméabilisant, un mouillant, un agent siccatif, un initiateur, un plastifiant, un colorant fluorescent, un absorbant ultraviolet, un agent anti-adhésif, un lubrifiant et un polyélectrolyte cationique, sur au moins une face d'un papier brut pour former une couche,
- traiter la couche avec une solution coagulante contenant un ou plusieurs d'un sel d'ammonium dans une proportion de 2 à 40 % en poids, et
- presser la surface traitée de la couche contre une surface de métal spéculaire chaude alors que la couche est à l'état humide.
7. Procédé selon la revendication 6 dans lequel la solution coagulante est exempte d'agent imperméabilisant.