

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 798 599 B9

(12)

CORRECTED EUROPEAN PATENT SPECIFICATION

Note: Bibliography reflects the latest situation

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see page(s) 37, 38

(51) Int Cl.7: **G03G 5/147**

(48) Corrigendum issued on:
07.08.2002 Bulletin 2002/32

(45) Date of publication and mention
of the grant of the patent:
05.12.2001 Bulletin 2001/49

(21) Application number: **97302027.4**

(22) Date of filing: **25.03.1997**

(54) **Electrophotographic photosensitive member, and electrophotographic apparatus and process cartridge including same**

Elektrophotographisches photoempfindliches Element, elektrophotographischer Apparat und Prozesskassette unter Verwendung desselben

Elément photosensible électrophotographique, cartouche de traitement l'utilisant et appareil électrophotographique

(84) Designated Contracting States:
DE FR GB IT

- **Hirano, Hidetoshi**
Ohta-ku, Tokyo (JP)
- **Kitamura, Wataru**
Ohta-ku, Tokyo (JP)

(30) Priority: **27.03.1996 JP 9585096**

(74) Representative:
Beresford, Keith Denis Lewis et al
BERESFORD & Co.
2-5 Warwick Court,
High Holborn
London WC1R 5DH (GB)

(43) Date of publication of application:
01.10.1997 Bulletin 1997/40

(73) Proprietor: **CANON KABUSHIKI KAISHA**
Tokyo (JP)

(56) References cited:

EP-A- 0 501 517	WO-A-95/02853
GB-A- 2 025 079	US-A- 4 455 205
US-A- 4 923 775	

(72) Inventors:

- **Tanaka, Takakazu**
Ohta-ku, Tokyo (JP)
- **Anayama, Hideki**
Ohta-ku, Tokyo (JP)
- **Yoshida, Akira**
Ohta-ku, Tokyo (JP)

EP 0 798 599 B9

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionFIELD OF THE INVENTION AND RELATED ART

5 [0001] The present invention relates to an electrophotographic photosensitive member (hereinafter simply referred to as "photosensitive member") including a specific protective layer and also relates to an electrophotographic apparatus and a process cartridge respectively including the photosensitive member.

10 [0002] Photosensitive members used in an electrophotographic process are generally required to have a given (photo-)sensitivity, electrical characteristics and optical characteristics suitable for the electrophotographic process applied.

15 [0003] Particularly, in the case where a photosensitive member is used repetitively, on the photosensitive member, electrically and/or mechanically external force is directly exerted in respective steps, such as a charging step, an imagewise exposure step, a developing step with a toner, a transfer step onto a paper, and a cleaning step. Accordingly, the photosensitive member is required to have a durability with respect to such external forces.

20 [0004] More specifically, the photosensitive member is required to have resistances to abrasion or marring of its surface due to friction at the time of the transfer or cleaning and resistance to deterioration thereof and in electrical characteristics due to ozone generated at the time of corona charging. Further, the photosensitive member is accompanied with a problem such that toner particles are attached to its surface due to repetition of the development with a toner and the cleaning of the toner, thus being required to provide a good cleaning characteristic.

25 [0005] In order to satisfy the above-mentioned requirements, there has been proposed a surface protective layer formed on a photosensitive layer and principally containing a resin in, e.g., Japanese Laid-Open Patent Applications (JP-A) 56-42863 and 53-103741. In the protective layer, a curable resin is used as a main component so as to improve a hardness and abrasion (or wear) resistance thereof.

30 [0006] Further, in order to obtain excellent images, the protective layer is also required to have an appropriate electrical resistance or resistivity in itself in addition to a high hardness and an excellent abrasion resistance. In the case where the protective layer has a too high (electrical) resistance, the protective layer is liable to cause an increase in residual potential, i.e., a charge accumulation within the protective layer. As a result, an electric potential is not stabilized at the time of repetitive use of the photosensitive member, thus resulting in an unstable image quality. In the case where the resistance of the protective layer is too low, an electrostatic latent image flows or moves in a planar direction within the protective layer, thus leading to an occurrence of image blur. In order to solve these problems, there has been proposed a method wherein metal oxide particles are added as electroconductive fine particles in a protective layer to appropriately control an electrical resistance of the resultant layer in, e.g., JP-A 57-30843. On the other hand, it has been generally known that an appropriate resistivity of the protective layer for the photosensitive member is in the range of $10^{10} - 10^{15}$ ohm. cm.

35 [0007] However, with respect to a conventional protective layer having a resistivity (electrical resistance) within the above range, the resistance is liable to be largely changed depending on a change in environmental condition. Particularly, in a high-humidity environment, a lowering in resistivity of the protective layer is readily caused, thus resulting in image blur leading to lowered image quality as described above.

40 [0008] Thus, in the circumstances, there still has not been provided a satisfactory protective layer for the photosensitive layer.

45 [0009] There have been proposed a curable acrylic resin for use in a protective layer of a photosensitive member in, e.g., JP-A 61-5253 and 1-178972. However, in such a protective layer, an electrical resistance thereof is liable to be largely affected by a change in environmental conditions since the acrylic resin has a polar group, such as carbonyl group susceptible to humidity. Particularly, in a high humidity environment, a lowering in resistance of the protective layer is readily caused, thus resulting in an occurrence of image flow.

50 [0010] Further, there has also been proposed a protective layer containing colloidal silica in, e.g., JP-A 60-57847. However, the protective layer has a polar group, such as hydroxyl group, so that the protective layer is readily affected by humidity similarly as in the case of the acrylic resin described above, thus leading to a problem of image flow.

55 [0011] In EP-A-0501517, an electrographic apparatus is disclosed comprising an electrographic photosensitive member comprising a support, a photosensitive layer and a protective layer.

SUMMARY OF THE INVENTION

[0012] An object of the present invention is to provide a photosensitive member excellent in a stability against a change in environmental conditions, providing a high durability and low transfer memory and photo-memory, and free from an accumulation of residual potential in a repetitive electrographic (image forming) process.

55 [0013] Embodiments of the present invention provide an electrophotographic apparatus and process cartridge each including the photosensitive layer described above.

[0014] According to the present invention, there is provided an electrophotographic photosensitive member, com-

prising: at least a support, a photosensitive layer disposed on the support, and a protective layer disposed on the photosensitive layer, characterized in that the protective layer comprises a cured product obtained from a condensation product between a silyl acrylate compound and colloidal silica.

[0015] According to an embodiment of the present invention, there is also provided an electrophotographic apparatus, comprising: the electrophotographic photosensitive member described above, charging means for charging said photosensitive member, imagewise exposure means for exposing imagewise the charged photosensitive member to form an electrostatic latent image on the photosensitive member, and developing means for developing the latent image with a toner.

[0016] According to another embodiment the present invention, there is provided a process cartridge, comprising: the electrophotographic photosensitive member described above and charging means for charging the photosensitive member.

[0017] These and other objects, features and advantages of the present invention will become more apparent upon a consideration of the following description of the preferred embodiments of the present invention taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0018] Figure 1 is a schematic sectional view of an embodiment of an electrophotographic apparatus using the photosensitive member according to the present invention.

[0019] Figures 2 - 4 are schematic sectional views each illustrating another embodiment of the electrophotographic apparatus of the present invention, respectively.


DETAILED DESCRIPTION OF THE DRAWINGS

[0020] The photosensitive member according to the present invention including at least a support, a photosensitive layer disposed on the support and a protective layer disposed on the photosensitive layer is characterized by including a cured product constituting the protective layer. The cured product is obtained from a condensation product between a silyl acrylate compound and colloidal silica.

[0021] In the present invention, the silyl acrylate compound may have at least one alkoxy silyl group and at least one double bond in its molecular structure.

[0022] The alkoxy silyl group of the silyl acrylate compound may preferably contain 1 - 3 alkoxy group, more preferably two or three alkoxy groups connected with silicon (Si) atom. The silyl acrylate compound may preferably have an weight-average molecular weight of 200 - 500.

[0023] The silyl acrylate compound may preferably be represented by the following formula (1):



wherein R¹ denotes an alkyl group; R² denotes an alkyl group, an alkoxy group or an aryl group; R³, R⁴, R⁵ and R⁶ independently denote hydrogen atom, an alkyl group, an alkoxy group or an aryl group; R⁷ denotes an alkylene group; m is an integer of 0 - 2 and n is an integer of 1 - 3 satisfying 0 < m+n ≤ 3; and p and q independently denotes an integer of at least 0.

[0024] Each of the above groups for R¹ to R⁷ including an alkyl group, an alkoxy group, an aryl group and an alkylene group may be substituted by a substituent. More specifically, examples of such a substituent may preferably include: an alkyl group, such as methyl, ethyl, propyl or butyl; an alkoxy group, such as methoxy, ethoxy, propoxy or butoxy; and a halogen atom, such as fluorine, chlorine or bromine.

[0025] Specific examples of the alkyl group for R¹-R⁶ may preferably include methyl, ethyl, propyl and butyl. Specific examples of the alkoxy group for R²-R⁶ may preferably include methoxy, ethoxy, propoxy and butoxy. Further, the aryl group for R² - R⁶ may preferably be phenyl or naphthyl. The alkylene group for R⁷ may preferably be methylene, ethylene or trimethylene.

[0026] Preferred examples of the silyl acrylate compound used in the present invention are shown below but the silyl acrylate compound usable in the present invention is not restricted to the following compounds.


Ex.Comp.No.

[0027]

5

(1)


10



15

(2)

20




25

(3)

30

(4)

35




40

(5)

45

(6)


50



55

(7)


5



10

(8)


15



20

(9)


25



35

(10)


30



40

(11)


45




50

(12)

55




(14)




10

(15)




20

(16)




30

(17)




35

(18)




45

(19)




55

(20)




10

(21)




20

(22)




30

(23)




35

(24)



45


(25)



55

5

(26)




10

15

(27)


15



20

(28)


25



30

(29)

35




40

(30)

(31)

50



55 [0028] The colloidal silica used in the present invention comprises an aqueous dispersion liquid of silica (SiO_2) particles having hydroxyl groups at their surfaces due to hydration as is well known in the art. Such silica particles may preferably have an average particle size of 1nm - 1 μm .

[0029] In the present invention, the condensation product between the silyl acrylate compound and colloidal silica





may be produced at room temperature or under heating through a condensation reaction after hydrolysis of the silyl acrylate compound in the presence of the (hydrous) colloidal silica and a water-miscible (soluble) alcohol or after the addition of the (hydrous) colloidal silica to a hydrolyzed product of the silyl acrylate compound. At that time, the silyl acrylate compound and the colloidal silica may preferably used in a ratio (silyl acrylate:colloidal silica) of 1:5 to 1:20 by weight.

[0030] The above-prepared condensation product may generally be a photocurable (light-curable) monomer containing an acrylic monomer portion modified by a water-repellent siloxane structure and hydrophobic silica. Accordingly, the cured product, obtained by curing such a photocurable monomer (condensation product), constituting the protective layer of the photosensitive member according to the present invention has an improved water-repellency and is little affected by humidity based on the condensation structure between the hydroxyl group located at the colloidal silica surface and the alkoxy silane portion. Further, the resultant protective layer is very effective in improving a transfer memory characteristic (i.e., a lowering in transfer memory specifically described hereinafter) of the photosensitive member of the present invention.

[0031] Incidentally, there has been known that a hydrolysis product between colloidal silica and a silyl acrylate can be used as a component of a coating composition (U.S. Patent No. 4455205). On the other hand, in the present invention, the cured product obtained from the above-described condensation product between the silyl acrylate compound and colloidal silica is used for constituting a protective layer of a photosensitive member, whereby the resultant photosensitive member is improved in transfer memory characteristic as described above.

[0032] When the condensation product described above is cured, a photopolymerization initiator may generally be used in an appropriate amount, preferably 0.1 - 40 wt. %, particularly 0.5 - 20 wt. %, based on the entire condensation product.

[0033] Preferred examples of the photopolymerization initiator may include those shown below.




5




R'' = isopropyl, methyl or ethyl

10

15




20



25

30



In the present invention, it is preferred that a polyfunctional acrylic monomer is cured together with the condensation product in view of a densed structure of a resultant film (cured product) in a mixing ratio (silyl acrylate: polyfunctional acrylic monomer) of 1:0.1 - 1:9 by mole.


35 [0034] Specific but non-exhaustive examples of the polyfunctional acrylic monomer may include those shown below.

Monomer No.

40 [0035]

<1>


45




50


<2>

55





10 <4>



15




20 <7>



25


<8>



35




40 <10>



45


<11>



55

<12>


5



10

<13>


15



20

<14>


25



30

<15>


35



40

<16>


45



50


<17>

55



<18>

5




10

<19>

15

20

25



<20>


30

35

40

<21>


45



50


<22>

55



<23>

5




10

15

<24>

20




25

30

<25>


35



40

<26>

45




50

55

<27>

5




10

15

20

<28>

25



30

<29>


35

40

45

50

55



<30>

5

10

15

20

<31>

25

30

35




<32>

40

45


50

55



<33>

5




10

15

20

<34>




25

30

<35>

35




40

<36>

45


50



55

<37>

5




10

15

<38>

20



25

[0036] In the photosensitive member of the present invention, the protective layer may preferably have a volume resistivity of $10^{10} - 10^{15}$ ohm.cm. In order to control the volume resistance of the protective layer so as to provide a value within the above range, electroconductive particles may be added in an appropriate amount, preferably 10 - 70 wt. %, per the protective layer.

[0037] Examples of the electroconductive particles may include particles of metal oxides, such as zinc oxide, titanium oxide, tin oxide, antimony oxide, bismuth oxide, tin-doped indium oxide, antimony-doped tin oxide, and zirconium oxide.

[0038] These metal oxide particles may be used singly or in combination of two or more species.

[0039] The electroconductive particles may have an average particle size of at most 0.3 μm , preferably at most 0.1 μm . The particle size of the electroconductive particles may preferably be as small as possible but may generally be 10 nm or above.

[0040] The protective layer used in the present invention may further contain various coupling agents and antioxidants in order to further improve, e.g., a dispersibility, an adhesiveness and an environmental resistance.

[0041] The protective layer may preferably have a thickness of 0.1 - 10 μm , particularly 0.5 - 7 μm .

[0042] The photosensitive layer of the photosensitive member of the present invention may have a single layer structure and a lamination layer structure of two or more layers. In the present invention, the photosensitive layer may preferably have a lamination structure including a lower charge generation layer (disposed on the support) and an upper charge transport layer (disposed on the charge generation layer) since such a lamination structure is effective in improving a (photo-)sensitivity and memory characteristics, such as a photomemory, of the resultant photosensitive member. Further, the photosensitive layer may have a lamination structure including a lower charge transport layer and an upper charge generation layer.

[0043] The charge generation layer may be formed by applying a dispersion of a charge generation material in a binder resin together with an appropriate solvent, followed by drying.

[0044] The thus-formed charge generation layer may preferably have a thickness of at most 5 μm , particularly 0.05 - 2 μm .

[0045] Examples of the charge generation material for the charge generation layer may include: azo pigments, quinone pigments, such as pyrenequinone and anthoanthrone; quinocyanine pigments; perylene pigments; indigo pigments, such as indigo and thioindigo; azulene salt pigments; and phthalocyanine pigments, such as copper phthalocyanine and titanyl phthalocyanine. Examples of the binder resin for the charge generation layer may include polyvinyl butyral, polystyrene, polyvinyl acetate, acrylic resin, cellulose acetate and ethyl cellulose.

[0046] The charge generation material may preferably be contained in the charge generation layer in an amount of

20 - 80 wt. %, more preferably 30 - 70 wt. %.

[0047] The charge transport layer may be formed by applying a dispersion of a charge transport material in a binder resin together with an appropriate solvent, followed by drying.

[0048] The thus-formed charge transport layer may preferably have a thickness of at most 5 - 40 μm , particularly 5 - 30 μm .


[0049] Examples of the charge transport material for the charge transport layer may include: polycyclic aromatic compounds having a cyclic structure, such as biphenylene, anthracene or phenanthrene, in a main or side chain; nitrogen-containing cyclic compounds, such as indoles, carbazoles, oxadiazoles and pyrazolines; hydrazone compounds; styryl compounds; and triarylamine compounds. Examples of the binder resin for the charge transport layer may include polyester, polycarbonate, polystyrene, and polymethacrylate.

[0050] The charge transport material may preferably be contained in the charge transport layer in an amount of 20 - 80 wt. %, more preferably 30 - 70 wt. %.

[0051] The charge transport layer may be formed by using a coating liquid comprising a solution of a polysilane preferably represented by the formula (2) shown below in an appropriate solvent (e.g., dichloromethane, chloroform).

15

Formula (2)



[0052] In the formula (2), R⁸, R⁹ and R¹⁰ independently denote an alkyl group or an aryl group each optionally having a substituent; each X independently denotes an alkyl group optionally having a substituent, an alkoxy group optionally having a substituent, an aryl group optionally having a substituent, or a halogen atom; and r, s and t independently denote an integer of at least 0 satisfying r+s+t > 10.


[0053] Specific examples of the alkyl group for R⁸, R⁹, R¹⁰ and X may preferably include methyl, ethyl and propyl. Specific examples of the aryl group for R⁸, R⁹, R¹⁰ and X may preferably include phenyl and naphthyl. Further, the alkoxy group for X may preferably be methoxy, ethoxy, and propoxy. Further, the halogen atom for X may preferably be fluorine, chlorine or bromine.

[0054] Examples of the substituent for R⁸ - R¹⁰ and X may preferably include: an alkyl group, such as methyl, ethyl or propyl; an alkoxy group, such as methoxy, ethoxy or propoxy and a halogen atom, such as fluorine, chlorine or bromine.

[0055] Specific some examples of the polysilane represented by the above formula (2) usable in the charge transport layer are shown below.


40

[1]




55


[2]




[3]




[4]



[5]



[6]



10

[0056] The polysilane of the formula (2) may generally be prepared through, e.g., Wurtz synthesis.

[0057] The polysilane has a high mobility, whereby it is effective for enhancing memory characteristics, such as a photomemory characteristic.

[0058] In the present invention, the protective layer of the photosensitive member has a relatively higher density of an acrylic portion, so that a somewhat insufficient cure can be caused therein in some cases if a charge transport layer is constituted by an ordinary charge transport material and a binder resin. In this regard, the polysilane does not cause migration of a low-molecular component leading to the insufficient cure state, so that the polysilane-based charge transport layer is effective in combination with the protective layer containing colloidal silica modified so as to have a high density of an acrylic portion at its surface as used in the present invention.

[0059] In the case where the photosensitive member of the present invention includes a photosensitive layer having a single layer structure, the photosensitive layer may, e.g., be formed by dissolving or dispersing a charge generation material (e.g., oxytitanium phthalocyanine or bisazo pigment), a charge transport material and a binder resin in an appropriate solvent, applying the solution or dispersion by a known coating method, and drying the wet coating. The thus-formed photosensitive layer having a single layer structure may preferably have a thickness of 5 - 40 μm , more preferably 10 - 30 μm .

[0060] The support constituting the photosensitive member according to the present invention may include any electroconductive material. Examples of the material for the support may include: a drum or sheet-shaped metal or alloy comprising aluminum, aluminum alloy, copper, chromium, nickel, zinc and/or stainless steel; a laminated plastic film covered with a metal foil of aluminum, copper, etc.; an plastic film covered with aluminum, indium oxide, tin oxide, etc., by vapor deposition; and metal, plastic film or paper each covered with an electroconductive layer formed by applying a coating liquid comprising an electroconductive substance and an optional appropriate binder and/or solvent as desired.

[0061] In the present invention, the support may preferably be in the form of a cylinder or drum, or a belt but may be formed in any shape suitable for an electrophotographic apparatus used.

[0062] In the present invention, it is possible to dispose an undercoat (or primer) layer having a barrier function controlling charge injection and an adhesive function at a boundary between the support and the photosensitive layer.

[0063] The undercoat layer principally comprises a binder resin and may optionally contain metal, alloy, their oxides, salts and a surfactant. Examples of such binder resin for the undercoat layer may include polyester, polyurethane, polyacrylate, polyethylene, polybutadiene, polycarbonate, polyamide, polypropylene, polyimide, phenolic resin, acrylic resin, silicone resin, epoxy resin, urea resin, allyl resin, alkyd resin, polyamide-imide, polysulfone, polyarylether, polyacetal and butyral resin.

[0064] The undercoat layer used in the present invention may preferably have a thickness of 0.05 - 7 μm , particularly 0.1 - 2 μm .

[0065] In the present invention, the above-mentioned various layers constituting the photosensitive member may generally be formed by vapor deposition or coating method. The coating method may preferably be used since the method allows a desired layer thickness (from a thin film to a thick film) and various layer compositions. Examples of such a coating method may include dipping, spray coating, beam coating, (wire) bar coating, and blade coating.

[0066] The photosensitive member according to the present invention can be applied to not only an ordinary electrophotographic apparatus such as copying machine, but also a laser beam printer, a light-emitting diode (LED) printer, a cathode-ray tube (CRT) printer, a liquid crystal printer, a facsimile machine, and other fields of applied electrophotography including, e.g., laser plate making.

[0067] The photosensitive member according to the present invention may be prepared, e.g., as follows.

[0068] Onto an aluminum cylinder, a solution of a material for an undercoat layer in an appropriate solvent is applied to form an undercoat layer. On the undercoat layer, a charge generation layer and a charge transport layer are successively formed in the above-described manner.

[0069] Then, a mixture of a silyl acrylate compound, colloidal silica and water-miscible solvent (e.g., butanol) is heated and thereafter cooled to effect condensation reaction. The condensation product is further mixed with a poly-functional acrylic monomer and electroconductive particles to prepare a coating liquid for a protective layer.

[0070] The coating liquid is applied onto the above-formed charge transport layer, followed by curing of the coating (e.g., by irradiation of light using a high-pressure mercury lamp) to prepare a photosensitive member according to the present invention.

[0071] Hereinbelow, an electrophotographic apparatus using the photosensitive member according to the present invention will be described.

[0072] Figure 1 shows a schematic structural view of an embodiment of the electrophotographic apparatus using the photosensitive member of the invention. Referring to Figure 1, a drum-shaped photosensitive member (photosensitive drum) 1 is rotated about an axis 1a at a prescribed peripheral speed in the direction of the arrow shown inside of the photosensitive drum 1. The surface of the photosensitive drum 1 is uniformly charged by means of a charger (charging means) 2 to have a prescribed positive or negative potential. Then, the photosensitive drum 1 is exposed to light L (as by slit exposure or laser beam-scanning exposure) by using an imagewise-exposure means (not shown), whereby an electrostatic latent image corresponding to an exposure image is successively formed on the surface of the photosensitive drum 1. The electrostatic latent image is developed with a toner by a developing means 4 to form a toner image. The toner image is successively transferred to a recording material 9 which is supplied from a supply part (not shown) to a position between the photosensitive drum 1 and a transfer corona charger (transfer means) 5 in synchronism with the rotating speed of the photosensitive drum 1, by means of the transfer means 5. The recording material 9 with the transferred toner image thereon is separated from the photosensitive drum 1 to be conveyed to an image-fixing device (image-fixing means) 8, followed by image fixation to print out the recording material 9 as a copy product outside the electrophotographic apparatus. Residual toner particles remaining on the surface of the photosensitive drum 1 after the transfer are removed by means of a cleaner (cleaning means) 6 to provide a cleaned surface, and residual charge on the surface of the photosensitive drum 1 is erased by a pre-exposure means 7 to be subjected to next image formation.

[0073] In an electrophotographic apparatus shown in Figure 2, at least three members comprising a photosensitive member 1, a charging means 2 and a developing means 4 are integrally supported to form a process cartridge 20, being attachable to or detachable from an apparatus body by using a guiding means 12 such as a rail within the apparatus body. In this case, a cleaning means 6 may be disposed within the cartridge 20.

[0074] In Figures 3 and 4, a direct charging means 10 as a charging means is used for directly charging the photosensitive drum (member) 1. Specifically, the direct charging means 10 supplied with a voltage is caused to be come in contact with the photosensitive member 1 directly to effect direct charging of the photosensitive member 1. In electrophotographic apparatus shown in Figures 3 and 4, toner images formed on the photosensitive member 1 are transferred to a recording member 9 by a direct charging member 23. Specifically, a voltage-applied direct charging member 23 is caused to be in contact with the recording member 9 directly, thus transferring the toner images formed on the photosensitive member 1 onto the recording material 9.

[0075] In an electrophotographic apparatus shown in Figure 4, a first process cartridge comprising at least two members of a photosensitive member 1 and a direct charging member 10 installed in a container 21 and a second process cartridge comprising at least a developing means 7 installed in a container 22 are respectively disposed attachably to or detachably from an apparatus body. In this case, a cleaning means 6 may be disposed within the first process cartridge 21.


[0076] In a case where the electrophotographic apparatus is used as a copying machine or a printer, imagewise exposure to light L may be performed by using reflection light or transmitted light from an original or by reading data on the original, converting the data into a signal and then effecting a laser beam scanning, a drive of LED array or a drive of a liquid crystal shutter array in accordance with the signal.

[0077] Hereinbelow, the present invention, will be explained more specifically with reference to examples. In the following, "part(s)" means "weight part(s)".

Example 1


[0078] A solution of 10 parts of an alcohol-soluble nylon copolymer (weight-average molecular weight (Mw) = 28000) and 30 parts of a methoxymethylated 6-nylon (Mw = 30000) in a mixture solvent of 260 parts of methanol and 40 parts of butanol was applied onto an aluminum cylinder (outer diameter = 30 mm, length = 260 mm) by dipping, followed by drying for 10 minutes at 90 °C to form a 1 µm-thick undercoat layer.

[0079] A coating liquid for a charge generation layer was prepared by dispersing a mixture of 4 parts of a bisazo pigment of the formula:



10 and 2 parts of a butyral resin (butyral degree = 65 mole %, Mw = 24000) in 100 parts of cyclohexanone by means of a sand mill for 30 hours and by adding 100 parts of tetrahydrofuran (THF) to the above mixture. The thus prepared coating liquid was applied onto the above prepared undercoat layer by dipping, followed by drying for 20 minutes at 80 °C to form a 0.3 µm-thick charge generation layer.

15 [0080] Onto the charge generation layer, a solution of 10 parts of a styryl compound of the formula:



25 and 10 parts of a polycarbonate resin (Mw = 40000) in a mixture solvent of 20 parts of dichloromethane and 60 parts of chlorobenzene was applied by dipping, followed by drying for 60 minutes at 120 °C to form a 20 µm-thick charge transport layer.

[0081] Then, a coating liquid for a protective layer was prepared as follows.

30 [0082] A mixture of 10 parts of a silyl acrylate compound (Ex. Comp. No. (1)), 100 parts of a colloidal silica ("Nalcoag 1034A", mfd. by Nalco Chemical Company) and 300 parts of t-butanol was heat-refluxed for 5 min. After cooling, 25 parts of a mixture liquid of 1,4-butanediol diacrylate/propylene oxide-modified trimethylolpropane triacrylate (1/1) was added to the above-refluxed mixture, followed by distilling-off of the solvent under reduced pressure to obtain a clear solution. In 100 parts of the solution (mixture), 2 parts of 2,2-diethoxyacetophenone and 50 parts of 10 wt. %-antimony-containing tin oxide fine particles (average particle size = 0.02 µm) were added and mixed to prepare a coating liquid.

35 [0083] The thus prepared coating liquid was applied onto the charge transport layer by spray coating and dried, followed by ultraviolet ray irradiation for 30 seconds with a high-pressure mercury lamp at a light intensity of 80 mW/cm² to form a 3 µm-thick protective layer, thus preparing a photosensitive member according to the present invention.

40 [0084] The thus prepared photosensitive member was installed in a copying machine ("NP-3825", mfd. by Canon K. K.) remodeled so as to evaluate electrophotographic characteristics, thus measuring several electrophotographic properties including dark part potential V_D (V), sensitivity E_{Δ500} (lux.sec) and residual potential V_r (V) in a normal temperature/normal humidity environment (23 °C/50 %RH: abbreviated s "N/N condition").

45 [0085] In this regard, a larger "dark part potential" represents a better chargeability. Further, "sensitivity" is evaluated as a quantity of light (E_{Δ500}; lux.sec) required for decreasing (or attenuating) a surface potential of -700 V to a surface potential of -200 V.

[0086] The results are shown in Table 1 appearing hereinafter.

50 [0087] Then, the copying machine including the photosensitive member was subjected to image formation at an initial stage under environmental conditions including N/N condition (23 °C/50 %RH), low-temperature/low-humidity environment (10°C/15 %RH) (abbreviated as "L/L" condition), and high-temperature/high-humidity environment (35 °C/85 %RH) (abbreviated as "H/H condition") to evaluate image forming properties by eyes. Further, the copying machine was subjected to successive image formation of 100,000 sheets (a durability test) under N/N condition. The results are shown in Table 2 appearing hereinafter.

55 [0088] Separately, a photosensitive member was prepared in the same manner as in the above-prepared photosensitive member and was subjected to successive image formation of 100,000 sheets under N/N condition to measure dark part potentials (V_D) and light part potentials (V_L) at an initial stage (initial V_D = -1010 V, initial V_L = -200 V) and after the copying of 10⁵ sheets thus evaluating differences therebetween respectively, as a fluctuation in dark part potential (ΔV_D) and a fluctuation in light part potential (ΔV_L). The results are also shown in Tables 1 and 2.

[0089] As apparent from the results shown in Tables 1 and 2 (appearing hereinafter), good images free from image irregularity and black spots were obtained. Further, the potential fluctuations ΔV_D and ΔV_L were decreased and stable

images were retained even after the copying of 10^5 sheets.

[0090] Further, with respect to the photosensitive member prepared in this example, a photomemory characteristic and a transfer memory characteristic were evaluated in the following manners, respectively.

[0091] Measurement of a photomemory was performed under N/N condition as follows.

[0092] A part of the photosensitive member surface was covered with a masking (light-intercepting) member and the photosensitive member was exposed to (irradiated by) a white fluorescent lamp (illuminance = 2000 lux) for 15 min. Thereafter, the photosensitive member was left standing for 10 min., followed by measurement of a voltage at the irradiated portion and a voltage at the covered (unexposed) portion.

[0093] A photomemory (V) was evaluated as a difference between the voltages at the irradiated and covered portions.

[0094] Measurement of a transfer memory was performed under N/N condition as follows.

[0095] With respect to the photosensitive member, a primary-charge voltage V_{d1} under no transfer current application and a primary-charge voltage V_{d2} under application of a transfer current were measured to determine a difference therebetween (as absolute value) as a transfer memory (V).

[0096] The results are also shown in Table 1.

Examples 2 - 5

[0097] Four photosensitive members were prepared and evaluated in the same manner as in Example 1 except for using silyl acrylate compounds (Ex. Comp. Nos. (3), (5), (10) and (23) for Examples 2 - 5, respectively) instead of the silyl acrylate compound (Ex. Comp. No. (1)), respectively.

[0098] The results are shown in Tables 1 and 2.

Comparative Example 1

[0099] A photosensitive member was prepared and evaluated in the same manner as in Example 1 except that the protective layer was not formed.

[0100] The results are shown in Tables 1 and 2.

[0101] The photosensitive member showed good electrophotographic properties at an initial stage but lowered its chargeability, thus failing to provide good image due to an occurrence of black spots at the time of the copying of about 5×10^4 sheets.

Comparative Example 2

[0102] A photosensitive member was prepared and evaluated in the same manner as in Example 1 except that a 3 μm -thick protective layer was formed in the following manner.

[0103] A coating liquid for the protective layer was prepared by mixing a mixture of 10 parts of an acrylic monomer ($\text{CH}_2=\text{CH}-\text{COO}-\text{CH}_2-\text{CH}_3$), 100 parts of a colloidal silica ("Nalcoag 1034A", the same as in Example 1), 2 parts of 2,2-diethoxyacetophenone, 100 parts of 0.02 μm -dia. antimony-containing tin oxide fine particles (the same as in Example 1) and 300 parts of t-butanol in a sand mill for 48 hours.

[0104] The results are shown in Tables 1 and 2.

[0105] The photosensitive member caused image flow in H/H condition and, in the successive image forming test (durability test), provided a larger ΔV_L (light part potential charge) and caused fogs.

Table 1:

Electrophotographic properties								
Ex.	No.	V_D (-V)	$E_{\Delta 500}$ (lux.sec)	V_r (-V)	ΔV_D (V)	ΔV_L (V)	Photo- memory (V)	Transfer memory (V)
Ex.	1	1010	1.8	20	0	10	10	10
	2	1020	1.8	20	10	15	20	5
	3	1020	1.9	15	10	10	10	10
	4	1020	1.8	25	0	10	20	15
	5	1015	1.8	15	5	20	15	15
Comp. Ex.	1	980	1.6	10	*	*	15	10
	2	1020	1.9	30	20	100	50	60

*: charging failure occurred.

Table 2:

Ex.	No.	Image forming properties			
		(N/N)	(L/L)	(H/H)	
		Initial	10^5 sheets	Initial	Initial
Ex.	1	Good	Good	Good	Good
	2	"	"	"	"
	3	"	"	"	"
	4	"	"	"	"
	5	"	"	"	"
Comp. Ex.	1	Good	"	Good	Image flow
	2	"	Fog	"	"

Example 6


[0106] A coating liquid for an electroconductive layer was prepared as follows.

[0107] A mixture of 50 parts of electroconductive titanium oxide powder coated with 10 wt. %-antimony oxide-containing tin oxide (average primary particle size (of the powder) = 0.3 μm , coating amount = 35 wt. %), 25 parts of a phenolic resin, 20 parts of methyl cellosolve, 20 parts of methanol and 0.002 part of a silicone oil (polydimethylsiloxane-polyoxyalkylene copolymer, $M = 3000$) was dispersed in a sand mill using 1 mmø-glass beads.

[0108] The thus prepared coating liquid was applied onto an aluminum cylinder (outer diameter = 30 mm, length = 260 mm) by dipping, followed by drying for 30 min. at 140 °C to form a 20 μm -thick electroconductive layer.

[0109] On the electroconductive layer, a 1 μm -thick undercoat layer was formed in the same manner as in Example 1.

[0110] Then, a coating liquid for a charge generation layer was prepared by dispersing a mixture of 4 parts of a bisazo pigment of the formula:



and 2 parts of polyvinylbenzal (benzal degree = 80 mole %, $M_w = 12000$) in 30 parts of cyclohexanone in a sand mill using 1 mmø-glass beads for 25 hours and by adding 60 parts of methylethylketone to the above mixture. The thus prepared coating liquid was applied onto the above prepared undercoat layer by dipping, followed by drying for 10 minutes at 80 °C to form a 0.3 μm -thick charge generation layer.

[0111] On the charge generation layer, a 20 μm -thick charge transport layer was prepared in the same manner as in Example 1.

[0112] Thereafter, on the charge transport layer, a protective layer was formed in the same manner as in Example 1 except that the thickness (3 μm) of the protective layer was changed to 5 μm , thus preparing a photosensitive member according to the present invention.

[0113] The thus prepared photosensitive member was installed in a laser beam printer ("Laser Shot 4 plus", mfd. by Hewlett-Packard Company) remodeled so as to evaluate electrophotographic characteristics and evaluated in the same manner as in Example 1.

[0114] The results are shown in Tables 3 and 4 appearing hereinafter.

[0115] As a result, the photosensitive member provided stable images free from image flow and image irregularity even in H/H condition and was excellent in potential stability due to decreased fluctuations in potentials in the successive image forming test.

Examples 7 - 10

[0116] Four photosensitive members were prepared and evaluated in the same manner as in Example 6 except for using silyl acrylate compounds (Ex. Comp. Nos. (4), (7), (11) and (22) for Examples 7 - 10, respectively) instead of the silyl acrylate compound (Ex. Comp. No. (1)), respectively.

[0117] The results are shown in Tables 3 and 4.

Table 3:

Electrophotographic properties								
Ex.	No.	V_D (-V)	$E_{\Delta 500}$ (lux.sec)	V_r (-V)	ΔV_D (V)	ΔV_L (V)	Photo- memory (V)	Transfer memory (V)
Ex.	6	850	1.6	25	10	0	15	10
	7	860	1.7	30	0	-10	10	15
	8	860	1.8	20	0	-10	20	10
	9	850	1.7	25	5	-15	20	20
	10	850	1.6	25	10	-10	10	15

Table 4:

Image forming properties					
Ex.	No.	(N/N)		(L/L)	(H/H)
		Initial	10^5 sheets	Initial	Initial
Ex.	6	Good	Good	Good	Good
	7	"	"	"	"
	8	"	"	"	"
	9	"	"	"	"
	10	"	"	"	"

Example 11

[0118] On an aluminum cylinder (outer diameter = 30 mm, length = 260 mm), a 1 μm -thick undercoat layer was formed in the same manner as in Example 1.

[0119] Then, on the undercoat layer, a 18 μm -thick charge transport layer was formed in the same manner as in Example 1.

[0120] A 0.4 μm -thick charge generation layer was formed on the charge transport layer in the same manner as in Example 1.

[0121] Thereafter, on the charge generation layer, a 3 μm -thick protective layer was formed in the same manner as in Example 1, thus preparing a photosensitive member according to the present invention.

[0122] The thus prepared photosensitive member was evaluated in the same manner as in Example 1 by using a copying machine ("NP-3825", mfd. by Canon K.K.) remodeled so as to positively charge the photosensitive member.

[0123] The results are shown in Tables 5 and 6 appearing hereinafter.

[0124] As a result, the photosensitive member provided stable images free from image irregularity and black spots and decreased potential fluctuations (ΔV_D and ΔV_L) and retained the stable images even when subjected to the copying of 10^5 sheets.

Example 12

[0125] A photosensitive member was prepared and evaluated in the same manner as in Example 11 except that the silyl acrylate compound for forming the coating liquid for the protective layer was changed to a silyl acrylate compound (Ex. Comp. No. (6)).

[0126] The results are shown in Tables 5 and 6.

Example 13

[0127] A photosensitive member was prepared and evaluated in the same manner as in Example 11 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (16)) and the (electroconductive) fine particles were changed to zinc oxide fine particles (average particle size of 0.1 μm) each for forming the coating liquid for the protective layer.

[0128] The results are shown in Tables 5 and 6.

Example 14

[0129] A photosensitive member was prepared and evaluated in the same manner as in Example 11 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (17)) and the (electroconductive) fine particles were changed to titanium oxide fine particles (average particle size of 0.1 μm) each for forming the coating liquid for the protective layer.

[0130] The results are shown in Tables 5 and 6.

Example 15

[0131] A photosensitive member was prepared and evaluated in the same manner as in Example 11 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (21)) and the (electroconductive) fine particles were changed to tin oxide fine particles (average particle size of 0.2 μm) each for forming the coating liquid for the protective layer.

[0132] The results are shown in Tables 5 and 6.

Comparative Example 3

[0133] A photosensitive member was prepared and evaluated in the same manner as in Example 11 except that the protective layer was not formed.

[0134] The results are shown in Tables 5 and 6.

[0135] The photosensitive member showed good electrophotographic properties at an initial stage but caused an occurrence of abrasion of the charge generation layer at the time of the copying of 400 sheets, thus failing to retain good images.

Table 5:

Electrophotographic properties								
Ex.	No.	V_D (-V)	$E_{\Delta 500}$ (lux.sec)	V_r (-V)	ΔV_D (V)	ΔV_L (V)	Photo- memory (V)	Transfer memory (V)
Ex.	11	1010	1.9	15	0	20	20	30
	12	1015	1.8	20	0	15	30	20
	13	1020	1.9	20	10	15	30	20
	14	1020	1.9	20	10	10	20	30
	5	1020	1.8	15	10	20	20	25
Comp. Ex.	3	970	1.6	15	*	*	30	30

*: charging failure occurred.

Table 6:

Image forming properties					
Ex.	No.	(N/N)		(L/L)	(H/H)
		Initial	10^5 sheets	Initial	Initial
Ex.	11	Good	Good	Good	Good
	12	"	"	"	"
	13	"	"	"	"

Table 6: (continued)

Image forming properties					
Ex.	No.	(N/N)		(L/L)	(H/H)
		Initial	10^5 sheets	Initial	Initial
	14	"	"	"	"
	15	"	"	"	"
10	Comp. Ex.	13	Good	-	Good
					Image flow

-: Image defect occurred at the time of the copying of 400 sheets.


Example 16

[0136] On an aluminum cylinder (outer diameter = 30 mm, length = 260 mm), a 1 μm -thick undercoat layer was formed in the same manner as in Example 1.

[0137] A coating liquid for a charge generation layer was prepared by mixing 4 parts of oxytitanium phthalocyanine (showing four main peaks at bragg angles ($2\theta \pm 0.2$ degree) of 9.0 degrees, 14.2 degrees, 23.9 degrees and 27.1 degrees in X-ray diffraction pattern based on $\text{CuK}\alpha$ characteristic X-ray), 2 parts of a polyvinyl butyral ("S-LEC BM2", mfd. by Sekisui Kagaku Kogyo K.K.) and 60 parts of cyclohexanone in a sand mill using 1 mmØ-glass beads for 4 hours and by adding 100 parts of ethyl acetate to the mixture.

[0138] The thus prepared coating liquid was applied onto the undercoat layer by dipping to form a 0.3 μm -thick charge generation layer.

[0139] A coating liquid for a charge transport layer was prepared by dissolving 10 parts of a polysilane (viscosity-average molecular weight = 13000) of the formula:



in a mixture solvent of 30 parts of toluene and 30 parts of THF and was applied onto the charge generation layer followed by drying for 1 hour at 120 °C to form a 10 μm -thick charge transport layer.

[0140] On the charge transport layer, a 3 μm -thick protective layer was formed in the same manner as in Example 1, thus preparing a photosensitive member according to the present invention.

[0141] The thus prepared photosensitive member was installed in a digital copying machine ("GP-55", mfd. by Canon K.K.) remodeled so as to evaluate electrophotographic characteristics and was evaluated in the same manner as in Example 1 except for evaluating a sensitivity in the following manner.

[0142] In this example, "sensitivity" was evaluated as a light energy ($E_{\Delta 400}$; $\mu\text{J}/\text{cm}^2$) required for decreasing (or attenuating) a surface potential of -500 V to a surface potential of -100 V.

[0143] The results are shown in Tables 7 and 8 appearing hereinafter.

[0144] As a result, the photosensitive member provided stable images free from image irregularity and black spots and decreased potential fluctuations (ΔV_D and ΔV_L) and retained the stable images even when subjected to the copying of 10^5 sheets.

Examples 17 - 20

[0145] Four photosensitive members were prepared and evaluated in the same manner as in Example 16 except for using silyl acrylate compounds (Ex. Comp. Nos. (3), (5), (10) and (23) for Examples 17 - 20, respectively) instead of the silyl acrylate compound (Ex. Comp. No. (1)), respectively.

[0146] The results are shown in Tables 7 and 8.

Comparative Example 4

[0147] A photosensitive member was prepared and evaluated in the same manner as in Example 16 except that the protective layer was not formed.

5 [0148] The results are shown in Tables 7 and 8.

[0149] The photosensitive member showed good electrophotographic properties at an initial stage but lowered its chargeability, thus failing to provide good image due to an occurrence of black spots at the time of the copying of about 2000 sheets.

10

Table 7:

Electrophotographic properties								
Ex.	No.	V_D (-V)	$E_{\Delta 400}$ (μ J/cm 2)	V_r (-V)	ΔV_D (V)	ΔV_L (V)	Photo- memory (V)	Transfer memory (V)
Ex.	16	650	1.3	20	0	10	30	10
	17	620	1.4	20	10	15	20	10
	18	550	1.6	15	0	10	20	20
	19	570	1.5	15	0	10	25	10
	20	580	1.4	15	5	20	20	15
Comp. Ex.	4	450	1.1	10	*	*	25	20

*: charging failure occurred.

15

20

25

25

Table 8:

Image forming properties					
Ex.	No.	(N/N)		(L/L)	(H/H)
		Initial	10^5 sheets	Initial	Initial
Ex.	16	Good	Good	Good	Good
	17	"	"	"	"
	18	"	"	"	"
	19	"	"	"	"
	20	"	"	"	"
Comp. Ex.	4	Good	-	Good	Good

Example 21

40


[0150] On an aluminum cylinder (outer diameter = 30 mm, length = 260 mm), a 20 μ m-thick electroconductive layer was formed in the same manner as in Example 6 and thereon a 1 μ m-thick undercoat layer was formed in the same manner as in Example 16.

[0151] On the undercoat layer, a 0.3 μ m-thick charge generation layer was formed in the same manner as in Example 16.

[0152] A coating liquid for a charge transport layer was prepared by dissolving 10 parts of a polysilane (viscosity-average molecular weight = 12500) of the formula:

50

55



in a mixture solvent of 30 parts of toluene and 30 parts of THF and was applied onto the charge generation layer followed by drying for 1 hour at 120 °C to form a 12 μm -thick charge transport layer.

[0153] On the charge transport layer, a 5 μm -thick protective layer was formed in the same manner as in Example 16 except for changing the layer thickness, thus preparing a photosensitive member according to the present invention.

5 [0154] The thus prepared photosensitive member was evaluated in the same manner as in Example 16.

[0155] The results are shown in Tables 9 and 10 appearing hereinafter.

[0156] As a result, the photosensitive member provided stable images free from image irregularity and black spots even in H/H condition and decreased potential fluctuations (ΔV_D and ΔV_L), thus being excellent in potential stability.

10 Example 22

[0157] A photosensitive member was prepared and evaluated in the same manner as in Example 21 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (4)) and the (electroconductive) fine particles were changed to tin-doped indium oxide fine particles (average particle size of 0.1 μm) each for forming the coating liquid for the protective layer.

15 [0158] The results are shown in Tables 9 and 10.

Example 23

20 [0159] A photosensitive member was prepared and evaluated in the same manner as in Example 21 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (7)) and the (electroconductive) fine particles were changed to tin oxide fine particles (average particle size of 0.3 μm) each for forming the coating liquid for the protective layer.

25 [0160] The results are shown in Tables 9 and 10.

Example 24

30 [0161] A photosensitive member was prepared and evaluated in the same manner as in Example 21 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (11)) and the (electroconductive) fine particles were changed to antimony oxide fine particles (average particle size of 0.1 μm) each for forming the coating liquid for the protective layer.

35 [0162] The results are shown in Tables 9 and 10.

Example 25

40 [0163] A photosensitive member was prepared and evaluated in the same manner as in Example 21 except that the silyl acrylate compound was changed to a silyl acrylate compound (Ex. Comp. No. (27)) and the (electroconductive) fine particles were changed to zirconium oxide fine particles (average particle size of 0.2 μm) each for forming the coating liquid for the protective layer.

[0164] The results are shown in Tables 9 and 10.

Table 9:


Electrophotographic properties								
Ex.	No.	V_D (-V)	$E_{\Delta 400}$ ($\mu\text{J}/\text{cm}^2$)	V_r (-V)	ΔV_D (V)	ΔV_L (V)	Photo- memory (V)	Transfer memory (V)
Ex.	21	650	1.1	25	10	0	20	10
	22	650	1.2	30	0	0	25	10
	23	620	1.1	20	0	0	20	20
	24	630	1.2	25	5	0	20	10
	25	640	1.3	25	10	0	20	15

Table 10:

Image forming properties					
Ex.	No.	(N/N)		(L/L)	(H/H)
		Initial	10^5 sheets	Initial	Initial
Ex.	21	Good	Good	Good	Good
	22	"	"	"	"
	23	"	"	"	"
	24	"	"	"	"
	25	"	"	"	"


Claims

1. An electrophotographic photosensitive member, comprising: at least a support, a photosensitive layer disposed on the support, and a protective layer disposed on the photosensitive layer,
characterized in that said protective layer comprises a cured product obtained from a condensation product between a silyl acrylate compound and colloidal silica.
2. A member according to Claim 1, wherein said silyl acrylate compound has at least one alkoxy silyl group and at least one double bond.
3. A member according to Claim 1, wherein said silyl acrylate compound is represented by the following formula (1):




wherein R¹ denotes an alkyl group; R² denotes an alkyl group, an alkoxy group or an aryl group; R³, R⁴, R⁵ and R⁶ independently denote hydrogen atom, an alkyl group, an alkoxy group or an aryl group; R⁷ denotes an alkylene group; m is an integer of 0 - 2 and n is an integer of 1 - 3 satisfying 0 < m+n ≤ 3; and p and q independently denotes an integer of at least 0.

4. A member according to Claim 1, wherein said cured product is obtained from said condensation product and a polyfunctional acrylic monomer.
5. A member according to Claim 1, wherein said protective layer comprises electroconductive particles.
6. A member according to Claim 5, wherein said electroconductive particles comprise a metal oxide.
7. A member according to claim 1 wherein said photosensitive layer comprises a charge generation layer disposed on the support and a charge transport layer disposed on the charge generation layer, the charge transport layer comprising a polysilane.
8. A member according to Claim 7, wherein said silyl acrylate compound has at least one alkoxy silyl group and at least one double bond.
9. A member according to Claim 7, wherein said silyl acrylate compound is represented by the formula (1) shown below and said polysilane is represented by the formula (2) shown below:



10 wherein R^1 denotes an alkyl group; R^2 denotes an alkyl group, an alkoxy group or an aryl group; R^3 , R^4 , R^5 and R^6 independently denote hydrogen atom, an alkyl group, an alkoxy group or an aryl group; R^7 denotes an alkylene group; m is an integer of 0 - 2 and n is an integer of 1 - 3 satisfying $0 < m+n \leq 3$; and p and q independently denotes an integer of at least 0; and



25 wherein R^8 , R^9 and R^{10} independently denote an alkyl group or an aryl group each optionally having a substituent; each X independently denotes an alkyl group optionally having a substituent, an alkoxy group optionally having a substituent, an aryl group optionally having a substituent, or a halogen atom; and r , s and t independently denote an integer of at least 0 satisfying $r+s+t > 10$.

30 10. A member according to Claim 7, wherein said cured product is obtained from said condensation product and a polyfunctional acrylic monomer.

11. A member according to Claim 7, wherein said protective layer comprises electroconductive particles.

12. A member according to Claim 11, wherein said electroconductive particles comprise a metal oxide.

35 13. An electrophotographic apparatus, comprising: an electrophotographic photosensitive member according to Claim 1 or 7, charging means for charging said photosensitive member, imagewise exposure means for exposing imagewise the charged photosensitive member to form an electrostatic latent image on said photosensitive member, and developing means for developing the latent image with a toner.

40 14. A process cartridge, comprising: an electrophotographic photosensitive member according to Claim 1 or 7 and charging means for charging said photosensitive member.

15. A process cartridge according to Claim 14, which comprises developing means for developing an electrostatic image formed on said photosensitive member.

45

Patentansprüche

50 1. Elektrophotographisches lichtempfindliches Element, das die nachstehenden Bestandteile umfaßt: mindestens einen Träger, eine auf dem Träger angeordnete lichtempfindliche Schicht, und eine auf der lichtempfindlichen Schicht angeordnete Schutzschicht,

dadurch gekennzeichnet, daß

die Schutzschicht ein gehärtetes Produkt umfaßt, das aus einem Kondensationsprodukt zwischen einer Silylacrystallverbindung und kolloidalem Siliciumdioxid erhalten wurde.

55


2. Element nach Anspruch 1,

dadurch gekennzeichnet, daß

die Silylacrystallverbindung mindestens eine Alkoxsilylgruppe und mindestens eine Doppelbindung aufweist.

3. Element nach Anspruch 1,
dadurch gekennzeichnet, daß
die Silylacrylatverbindung durch die nachstehende Formel (1) wiedergegeben wird:

5



10

(1),

worin R¹ eine Alkylgruppe bezeichnet; R² eine Alkylgruppe, eine Alkoxygruppe oder eine Arylgruppe bezeichnet; R³, R⁴, R⁵ und R⁶ unabhängig ein Wasserstoffatom, eine Alkylgruppe, eine Alkoxygruppe oder eine Arylgruppe bezeichnen; R⁷ eine Alkylengruppe bezeichnet; m eine ganze Zahl von 0 bis 2 und n eine ganze Zahl von 1 bis 3 ist, die der Beziehung $0 < m+n \leq 3$ genügen; und p und q unabhängig eine ganze Zahl von mindestens 0 bezeichnet.

4. Element nach Anspruch 1,
dadurch gekennzeichnet, daß
das gehärtete Produkt aus dem Kondensationsprodukt und einem polyfunktionellen Acrylmonomer erhalten wird.

5. Element nach Anspruch 1,
dadurch gekennzeichnet, daß
die Schutzschicht elektrisch leitende Teilchen umfaßt.

6. Element nach Anspruch 5,
dadurch gekennzeichnet, daß
die elektrisch leitenden Teilchen ein Metalloxid umfassen.

30


7. Element nach Anspruch 1,
dadurch gekennzeichnet, daß
die lichtempfindliche Schicht eine auf dem Träger angeordnete Ladungserzeugungsschicht und eine auf der Ladungserzeugungsschicht angeordnete Ladungstransportschicht umfaßt, wobei die Ladungstransportschicht ein Polyzellen umfaßt

8. Element nach Anspruch 7,
dadurch gekennzeichnet, daß
die Silvacyrlyatverbindung mindestens eine Alkoxysilylgruppe und mindestens eine Doppelbindung aufweist.

40


9. Element nach Anspruch 7,
dadurch gekennzeichnet, daß
die Silylacrylatverbindung durch die nachstehend gezeigte Formel (1) wiedergegeben wird und das Polysilan durch
die nachstehend gezeigte Formel (2) wiedergegeben wird:

45



worin R¹ eine Alkylgruppe bezeichnet; R² eine Alkylgruppe, eine Alkoxygruppe oder eine Arylgruppe bezeichnet; R³, R⁴, R⁵ und R⁶ unabhängig ein Wasserstoffatom, eine Alkylgruppe, eine Alkoxygruppe oder eine Arylgruppe bezeichnen; R⁷ eine Alkylengruppe bezeichnet; m eine ganze Zahl von 0 bis 2 und n eine ganze Zahl von 1 bis 3 ist, die der Beziehung 0 < m+n ≤ 3 genügen; und p und q unabhängig eine ganze Zahl von mindestens 0 bezeich-

net; und



worin R⁸, R⁹ und R¹⁰ unabhängig eine Alkylgruppe oder eine Arylgruppe bezeichnen, die jeweils wahlweise mit einem Substituenten versehen sind; jedes X unabhängig eine Alkylgruppe, die wahlweise mit einem Substituenten versehen ist, eine Alkoxygruppe, die wahlweise mit einem Substituenten versehen ist, eine Arylgruppe, die wahlweise mit einem Substituenten versehen ist, oder ein Halogenatom bezeichnet; und r, s und t bezeichnen unabhängig eine ganze Zahl von mindestens 0, die der nachstehenden Beziehung genügen: r+s+t > 10.

20

10. Element nach Anspruch 7,
dadurch gekennzeichnet, daß
 das gehärtete Produkt aus dem Kondensationsprodukt und einem polyfunktionellen Acrylmonomer erhalten wird.

25

11. Element nach Anspruch 7,
dadurch gekennzeichnet, daß
 die Schutzschicht elektrisch leitende Teilchen umfaßt.

12. Element nach Anspruch 11,
dadurch gekennzeichnet, daß
 die elektrisch leitenden Teilchen ein Metalloxid umfassen.

30

13. Elektrophotographisches Gerät, das die nachstehenden Bestandteile umfaßt: ein elektrophotographisches lichtempfindliches Element nach Anspruch 1 oder Anspruch 7, eine Ladeeinrichtung zum Laden des lichtempfindlichen Elements, eine Belichtungseinrichtung zur bildweisen Belichtung des geladenen lichtempfindlichen Elements, um auf dem lichtempfindlichen Element ein latentes elektrostatisches Bild zu erzeugen, und eine Entwicklungseinrichtung zur Entwicklung des latenten Bildes mit einem Toner.

35

14. Prozesskassette, die die nachstehenden Bestandteile umfaßt: ein elektrophotographisches lichtempfindliches Element nach Anspruch 1 oder Anspruch 7 und eine Ladeeinrichtung zum Laden des lichtempfindlichen Elements.

40

15. Prozesskassette nach Anspruch 14, die eine Entwicklungseinrichtung zum Entwickeln eines auf dem lichtempfindlichen Element erzeugten elektrostatischen Bildes umfaßt.

Revendications


45

1. Élément photosensible électrophotographique, comprenant : au moins un support, une couche photosensible disposée sur le support, et une couche protectrice disposée sur la couche photosensible,
caractérisé en ce que ladite couche protectrice comprend un produit durci obtenu à partir d'un produit de condensation entre un silyl-acrylate et de la silice colloïdale.

50

2. Élément suivant la revendication 1, dans lequel le silyl-acrylate a au moins un groupe alkoxy-silyle et au moins une double liaison.

3. Élément suivant la revendication 1, dans lequel le silyl-acrylate est représenté par la formule (1) suivante :



10 dans laquelle R^1 représente un groupe alkyle ; R^2 représente un groupe alkyle, un groupe alkoxy ou un groupe aryle ; R^3 , R^4 , R^5 et R^6 représentent, indépendamment, un atome d'hydrogène, un groupe alkyle, un groupe alkoxy ou un groupe aryle ; R^7 représente un groupe alkylène ; m représente un nombre entier de 0 à 2 et n représente un nombre entier de 1 à 3 satisfaisant la relation $0 < m+n \leq 3$; et p et q représentent, indépendamment, un nombre entier d'au moins 0.

15 4. Elément suivant la revendication 1, dans lequel le produit durci est obtenu à partir du produit de condensation et d'un monomère acrylique polyfonctionnel.


20 5. Elément suivant la revendication 1, dans lequel la couche protectrice comprend des particules électroconductrices.

6. Elément suivant la revendication 5, dans lequel les particules électroconductrices comprennent un oxyde métallique.

25 7. Elément suivant la revendication 1, dans lequel la couche photosensible comprend une couche de production de charges disposée sur le support, et une couche de transport de charges disposée sur la couche de production de charges, la couche de transport de charges comprenant un polysilane.


8. Elément suivant la revendication 7, dans lequel le silyl-acrylate a au moins un groupe alkoxy-silyle et au moins une double liaison.

30 9. Elément suivant la revendication 7, dans lequel le silyl-acrylate est représenté par la formule (1) illustrée ci-dessous et le polysilane est représenté par la formule (2) illustrée ci-dessous.



40

dans laquelle R^1 représente un groupe alkyle ; R^2 représente un groupe alkyle, un groupe alkoxy ou un groupe aryle ; R^3 , R^4 , R^5 et R^6 représentent, indépendamment, un atome d'hydrogène, un groupe alkyle, un groupe alkoxy ou un groupe aryle ; R^7 représente un groupe alkylène, m représente un nombre entier de 0 à 2 et n représente un nombre entier de 1 à 3 satisfaisant la relation $0 < m+n \leq 3$; et p et q représentent, indépendamment, un nombre entier d'au moins 0 ; et



dans laquelle R^8 , R^9 et R^{10} représentent, indépendamment, un groupe alkyle ou un groupe aryle portant chacun

facultativement un substituant ; chaque groupe X représente, indépendamment, un groupe alkyle portant facultativement un substituant, un groupe alkoxy portant facultativement un substituant, un groupe aryle portant facultativement un substituant, ou un atome d'halogène ; et r, s et t représentent, indépendamment, un nombre entier d'au moins 0 satisfaisant la relation $r+s+t > 10$.

5 **10.** Élément suivant la revendication 7, dans lequel le produit durci est obtenu à partir du produit de condensation et d'un monomère acrylique polyfonctionnel.

10 **11.** Élément suivant la revendication 7, dans lequel la couche protectrice comprend des particules électroconductrices.

15 **12.** Élément suivant la revendication 11, dans lequel les particules électroconductrices comprennent un oxyde métallique.

20 **13.** Appareil électrophotographique, comprenant : un élément photosensible électrophotographique suivant la revendication 1 ou 7, un moyen de charge pour charger ledit élément photosensible, un moyen d'exposition à des fins de formation d'images pour exposer à des fins de formation d'images l'élément photosensible chargé afin de former une image latente électrostatique sur ledit élément photosensible, et un moyen de développement pour développer l'image latente au moyen d'un toner.

25 **14.** Cartouche de traitement, comprenant : un élément photosensible électrophotographique suivant la revendication 1 ou 7 et un moyen de charge pour charger ledit élément photosensible.

30 **15.** Cartouche de traitement suivant la revendication 14, qui comprend un moyen de développement pour développer une image électrostatique formée sur ledit élément photosensible.

25

30

35

40

45

50

55




FIG. I




FIG. 2




FIG. 3




FIG. 4