



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 846 150 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

Note: Bibliography reflects the latest situation

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see page(s) 7

(51) Int Cl.7: **C10G 11/05**, B01J 23/00,
B01J 23/10

(48) Corrigendum issued on:
05.11.2003 Bulletin 2003/45

(86) International application number:
PCT/US95/14020

(45) Date of publication and mention
of the grant of the patent:
14.05.2003 Bulletin 2003/20

(87) International publication number:
WO 96/035762 (14.11.1996 Gazette 1996/50)

(21) Application number: **95938978.4**

(22) Date of filing: **27.10.1995**

(54) **USE OF La/Nd-SPINEL COMPOSITIONS FOR METALS PASSIVATION IN FCC PROCESSES**

VERWENDUNG VON La/Nd-SPINELZUSAMMENSETZUNGEN FÜR PASSIVATION VON
METAILEN IM FCC-VERFAHREN

UTILISATION DE COMPOSITIONS La/Nd - SPINELLE POUR LA PASSIVATION DE METAUX DANS
DES PROCEDES DE CRAQUAGE CATALYTIQUE FLUIDE

(84) Designated Contracting States:
DE ES FR GB IT NL

(74) Representative: **Muth, Heinz-Peter**
Uexküll & Stolberg
Patentanwälte
Beselerstrasse 4
22607 Hamburg (DE)

(30) Priority: **12.05.1995 US 440281**

(43) Date of publication of application:
10.06.1998 Bulletin 1998/24

(56) References cited:
EP-A- 0 110 703 **EP-A- 0 554 968**
WO-A-87/06156 **WO-A-94/19427**
US-A- 4 497 902

(73) Proprietor: **W.R. Grace & Co.-Conn.**
New York, New York 10036 (US)

(72) Inventor: **KIM, Gwan**
Columbia, MD 21045 (US)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 846 150 B9

Description

Background of the Invention

[0001] Poisoning (or deactivation) of fluid catalytic cracking (FCC) catalysts is a persistent problem especially as petroleum refiners often work with hydrocarbon feedstocks which contain substantial amounts of vanadium and/or nickel. Premature catalyst deactivation leads to added refining cost both in terms of the amount of catalyst consumed and in terms of down time for the refinery.

[0002] In the past, various additives have been proposed to passivate poisoning metals such that their deactivating effect is lessened. Examples of compositions which have been proposed for this purpose include magnesium aluminate spinel (U.S. Patent 5,057,205), hydrotalcite (U.S. Patent 4,889,625), rare earth compounds in clay/alumina matrix (U.S. Patent 5,304,299), rare earth compounds in acid-reacted metakaolin matrix (U.S. Patent 5,248,642), co-precipitated non-spinel ternary oxides (U.S. Patent 5,407,878), etc.

[0003] In general, the use of any additive may present issues for the refiner in practice. The additive content in the catalyst inventory may require separate monitoring. Additives may cause the creation of undesired effluents in the regenerator. Additives may require or create altered conditions in the FCC unit. Additives are often more expensive than the cracking catalyst itself. Thus, it is often desired to minimize the amount and/or number of additives used.

[0004] While known metals passivation additives often produce satisfactory results, there is a continued need for improved additives for metals passivation, especially additives which are more suitable for manufacture on a commercial scale..

Summary of the Invention

[0005] The invention is directed to the use of particles containing a metals passivation composition which comprises a component containing a combination of MgO-Al₂O₃ spinel and La/Nd oxides as vanadium passivators in a FCC process. These compositions are capable of providing superior metals passivation performance.

[0006] The metals passivation composition contains:

15-60 parts by weight MgO,
30-60 parts by weight Al₂O₃, and
10-30 parts by weight rare earth compound selected from the group consisting La oxide, Nd oxide, and mixtures thereof,

wherein at least a portion of the MgO and Al₂O₃ are present as an Mg-Al spinel phase. The La/Nd compound may optionally be present as a compound which forms the corresponding oxide in the course of use in the FCC

process.

[0007] The invention further encompasses the use of fluid catalytic cracking catalysts including the metals passivation composition of the invention either as a particulate admixture or as an integral part of the catalyst particles. The invention further encompasses the use of the metals passivation compositions of the invention in any form in an FCC process whereby the catalyst poisoning effects of metals such as vanadium and/or nickel are diminished. These and other aspects of the invention are described in further detail below.

Brief Description of the Drawings

[0008]

Figure 1 is a plot of vanadium pickup as a function of La oxide content.

Detailed Description of the Invention

[0009] The invention encompasses the use of compositions in FCC processes involving hydrocarbon feedstocks which contain metals such as vanadium and/or nickel. The compositions are characterized by the fact that they contain a metals passivation component which contains:

15-60 parts by weight MgO,
30-60 parts by weight Al₂O₃, and
10-30 parts by weight rare earth compound selected from the group consisting La oxide, Nd oxide, and mixtures thereof.

wherein at least a portion of the MgO and Al₂O₃ is present as an Mg-Al spinel phase.

[0010] The amount of MgO present in the metals passivation component may be varied extensively within the 15-60 parts by weight range depending on the amount of free MgO desired in the product. Preferably, the metals passivation component contains about 25-50 parts by weight MgO, more preferably 35-40 parts by weight.

[0011] The amount of Al₂O₃ in the metals passivation component may also be varied to any level within the 30-60 parts by weight range. Preferably, the metals passivation component contains about 35-55 parts by weight alumina, more preferably 40-50 parts by weight.

[0012] The La/Nd oxide present in the metals passivation component may be varied from all La oxide to all Nd oxide. Preferably, the molar ratio of La/Nd oxides used is greater than 1, more preferably greater than 4. Sources of La and/or Nd which also contain other rare earth oxides may be used if desired. Examples of such rare earth sources are La and/or Nd rich rare earth materials such as those disclosed in U.S. Patent 5,407,878, the disclosure of which is incorporated herein by reference. Referring to Figure 1, it can be seen that the amount of La/Nd present in the composition can have a

significant effect on the metals passivation ability as determined by the vanadium pick-up factor (discussed below). Thus, the metals passivation component preferably contains about 12-25 parts by weight total of La/Nd oxide, more preferably about 15-23 parts by weight.

[0013] The metals passivation component may contain minor amounts (preferably less than 10 parts by weight) of other materials which preferably do not adversely affect the metals passivation function. More preferably, however, the metals passivation component consists essentially of MgO, Al₂O₃, and La/Nd oxide.

[0014] Where the composition is used as an additive particle for an FCC process, the metals passivation component may be combined with fillers and/or binders to form particles suitable for use in an FCC process. Any known filler (e.g. clays, silica, alumina and other non-zeolitic oxides) may also be used in the composition. Preferably, any filler selected will not have a significant adverse effect on the performance of the metals passivation component. Any known binders may be used as long as they do not significantly adversely affect the performance of the metals passivation component. For example, binders such as alumina sols, silica sols, etc. may be used. In some cases, it may be possible to incorporate other functional components into the additive particles.

[0015] Where the metals passivation composition is used as an additive particulate (as opposed to being integrated into the FCC catalyst particles themselves), the amount of metals passivation component in the additive particles is preferably at least 50 wt.%, more preferably at least 75 wt.%. Most preferably, the additive particles consist entirely of the metals passivation component. The additive particles are preferably of a size suitable for circulation with the catalyst inventory in an FCC process. The additive particles preferably have an average particle size of about 20-200 µm. The additive particles preferably have a Davison attrition index (DI) value of about 0-45, more preferably about 0-15.

[0016] If desired, the metals passivation composition may be integrated into the FCC catalyst particles themselves. In such case, any conventional FCC catalyst particle components may be used in combination with the metals passivation composition. If integrated into the FCC catalyst particles, the metals passivation composition is preferably represents at least about 0.2 wt.% of the FCC catalyst particle, more preferably about 0.5 - 15 wt.%.

[0017] The metal passivation component of the compositions of the invention can be made by a variety of techniques whereby the appropriate amounts of MgO, Al₂O₃ and La/Nd oxide are assembled into the composition. Preferably, the metals passivation component is prepared by a method which does not involve coprecipitation.

[0018] In one preferred method, an aqueous alumina slurry is combined with an aqueous magnesia slurry and an La and/or Nd salt. The resulting mixture is then dried

and calcined. If desired, the mixture can be milled before drying. The drying may be performed by any conventional means such as oven drying or spray drying, spray drying being most preferable. The calcination is preferably conducted at about 450-750°C in air.

[0019] The alumina used may be neat Al₂O₃ particles or may be a hydrated form of alumina such as pseudo-boehmite. If desired, dispersants such as tetra sodium pyrophosphate (TSPP) and peptizing agents such as formic acid may be added to the alumina slurry. Other known expedients for slurry processing may also be added to the alumina slurry assuming that do not result in any excessive adverse effect. Where the metals passivation component is to be used directly as an additive particle (i.e. without an added binder), preferably the alumina slurry is peptized by the addition of about 1-2 moles of formic acid per mole of alumina in the slurry. The amount of solids in the slurry may be varied as desired depending on the selected drying/particle formation techniques used. Typically, about 4-6 parts by weight of water are used per part of solids in the slurry.

[0020] The magnesia used may be neat MgO particles or may be any composition known to yield MgO on calcination. If desired, dispersants such as tetra sodium pyrophosphate (TSPP) or other expedients may be added to the MgO slurry. Typically, about 4-6 parts by weight of water are used per part of solids in the slurry.

[0021] The La and/or Nd salt may be any salt which can be suitably dispersed in the overall slurry and resulting composition. The salt is preferably one which yields La and/or Nd oxide either on calcination or on use of the composition in the FCC reactor/regenerator. Nitrate salts generally give the best dispersion and best metals passivation performance. The amount of La and/or Nd salt should be such that the ultimate metals passivation component produced contains the desired amount of La and/or Nd on an oxide basis.

[0022] The metals passivation composition may be used as a separate additive particle or as an integral part of an FCC catalyst particle. If used as an additive, the metals passivation component may itself be formed into particles suitable for use in an FCC process. Alternatively, the metals passivation component may be combined with binders, fillers, etc. by any conventional technique. See for example, the process described in U.S. Patent 5,194,413, the disclosure of which is incorporated herein by reference.

[0023] Incorporation of the metals passivation composition directly into FCC catalyst particles may be accomplished by any known technique. Examples of suitable techniques for this purpose are disclosed in U.S. Patents 3,957,689; 4,499,197; 4,542,118 and 4,458,023, the disclosures of which are incorporated by reference.

[0024] The compositions of the invention may be used in any conventional FCC process. Typical FCC processes are conducted reaction temperatures of 450 to 650°C with catalyst regeneration temperatures of 600 to

850°C. The amount of the composition used is preferably about 1-20 parts by weight per 100 parts of FCC catalyst used. The compositions of the invention may be used in FCC processing of any typical hydrocarbon feedstock. Preferably, the compositions of the invention are used in FCC processes involving the cracking of hydrocarbon feedstocks which contain at least 2 ppm vanadium, more preferably at least 5 to 100 ppm or more of V and/or Ni. The presence of the compositions of the invention during the FCC process passivates the adverse effects of metals such as vanadium and decreases the formation of hydrogen and coke.

[0025] The invention is further illustrated by the following examples. It should be understood that the invention is not limited to the details of these examples.

Example 1

[0026] An alumina slurry was prepared by vigorously mixing 2498 g (1773 g on a dry basis) of CATAPAL-B alumina powder, a kind of pseudo-boehmite, and 14600 g of deionized (DI) - water containing 3.5 g of tetra-sodium-pyrophosphate (TSPP), in a Myers mixer (a high-shear mixer). The alumina in the slurry was then peptized for 10 minutes by adding 3000 g of 45 weight % formic acid to the slurry. To the resulting slurry was added a magnesia slurry which was readied by high-shear mixing 1630 g (1402 g on a dry basis) of MgO powder and 6200 g of DI-water containing 6.4 g of TSPP. After allowing the slurry to mix for 10 minutes, the slurry was two-pass Drais milled, and then was spray dried. A portion of the spray dried material was dried in a 204°C preheated oven for 45 minutes, and then was air calcined in a 718°C preheated muffle furnace for 45 minutes. The resulting material showed the following properties: Chemical composition (weight %): 43.2% MgO, 0.21% La₂O₃, 0.21% RE₂O₃ (total rare earth oxide), 0.40% Na₂O, 0.63% SO₄, 51.6% Al₂O₃ and 2.26% SiO₂. Physical properties: 7 DI (Davison Attrition Index), 116 m/g S.A. (N₂), and a powder XRD pattern revealing the presence of microcrystalline MgAl₂O₄ and (MgO)₂Al₂O₃ spinel, and some free MgO.

Example 2

[0027] A slurry of peptized alumina was prepared in exactly the same manner as in Example 1, using 1900 g (1300 g on a dry basis) of CATAPAL-B alumina powder, 9500 g of DI-water, 2.7 g of TSPP, and 2016 g of 45% formic acid solution. In the meantime, a magnesia slurry was readied by high-shear mixing 1208.5 g (1051.4 g on a dry basis) of MgO powder and 3519 g of DI-water containing 5 g of TSPP. The magnesia slurry was added to the above-peptized alumina slurry, and the batch was allowed to mix for 10 minutes. To the resulting slurry was added 1234.4 g of La/Nd-nitrate solution bearing 306.1 g of La₂O₃ and 32.1 g of Nd₂O₃. After mixing the batch for 5 minutes, the slurry was one-pass

Drais milled, and then was spray dried. A portion of the spray dried material was air calcined in a muffle furnace, ramping up to 718°C and allowing 45-minute soak at this temperature. The resulting material had the following properties: Chemical composition (weight %): 38.5% MgO, 12.67% La₂O₃, 0.96% Nd₂O₃, 13.70% RE₂O₃, 0.21% Na₂O, 0.45% SO₄, 45.3% Al₂O₃, and 0.32% SiO₂. Physical properties: 6 DI, 111 m²/g S.A. (N₂), and a powder XRD pattern showing the presence of microcrystalline (MgO)₂Al₂O₃ spinel, microcrystalline La₂O₃, and some free MgO.

Example 3

[0028] A slurry of peptized alumina was prepared in exactly the same manner as in Example 1, using 1629 g (1140 g on a dry basis) of CATAPAL-B alumina powder, 8145 g of DI-water containing 2.7 g of TSPP, and 2016 g of 45% formic acid solution. To this was added a magnesia slurry which was readied in the same manner in Example 2, using 1035.8 g (901 g on a dry basis) of MgO powder and 3107 g of DI-water containing 5 g of TSPP. After allowing the batch to mix for 10 minutes, 2469 g of La/Nd-nitrate solution bearing 611.7 g of La₂O₃ and 64.3 g of Nd₂O₃ was added to the batch. The slurry was mixed for 5 minutes, one-pass milled, and spray dried. The resulting material had the following properties: Chemical composition (weight %): 33.7% MgO, 22.15% La₂O₃, 2.28% Nd₂O₃, 24.43% RE₂O₃, 0.13% Na₂O, 0.45% SO₄, 41.1% Al₂O₃, and 0.32% SiO₂. Physical properties: 9 DI, 88 m²/g S.A. (N₂), and a powder XRD pattern showing the presence of microcrystalline (MgO)₂Al₂O₃ spinel, microcrystalline La₂O₃, and some free MgO.

Example 4

[0029] In order to demonstrate the superiority of the materials of this invention for trapping vanadium in FCC operation, the following study was carried out: a 100 g (on a dry basis) blend was prepared by mixing one of the traps prepared above with an ORION® family of GRACE-Davison FCC catalyst at a weight ratio of 1 part trap to 9 parts FCC catalyst. An unblended, 100 g of FCC catalyst was taken as a base case. Each sample spread over a dish in a shallow bed was then treated according to the following protocol: Heated in a muffle furnace to 204°C air, allowed to soak for one hour at this temperature; raised to 503° C, allowed to soak for 3 hours at this temperature; and then allowed to cool to room temperature; impregnated with a desired level - 5000 ppm in this study - of vanadium naphthenate in pentane to completely and uniformly cover all particles with vanadium; allowed pentane to evaporate away in muffle furnace at room temperature; heated to 204°C and held for one hour; raised to 593°C, and allowed to soak at this temperature for 3 hours; and then allowed to cool to room temperature; charged into an Inconel flu-

id-bed reactor; allowed the bed temperature to reach 771°C in flowing nitrogen over a period of approximately 3 hours; and then subjected to 20-hour/771°C cyclic-propylene-steaming (CPS), an accelerated catalyst deactivation protocol involving redox cycles (40 minutes/cycle) and 50 weight % steam (10 g H₂O/hour) throughout each cycle as follows: 10 minutes of nitrogen (137 ml/min.), 10 minutes of nitrogen containing 5 vol.% propylene, 10 minutes of nitrogen, and 10 minutes of air containing 4000 ppm SO₂ finally, the reactor was allowed to cool to room temperature in flowing nitrogen for discharging the sample.

[0030] In the course of the above deactivation treatment, FCC catalysts are attacked by vanadium. In the presence of a metals trap, however, the degree of vanadium attack on FCC catalysts can be significantly lessened as a result of vanadium capture by the metals trap. In order to prove this, each of the above deactivated samples was divided into two fractions - approximately 10 weight % of sink (metals trap) and approximately 90 weight % of float (FCC catalyst) fractions - by means of so-called "sink-float" or density separation, using tetrabromoethane having a density of 2.96 g/ml, tetrachloroethane having a density of 1.58 g/ml, and a centrifuge. All the samples, before and after the sink-float separation, were analyzed by using an Inductively Coupled Plasma Spectrometer. Figure 1 shows the so-called vanadium pick-up factor (V-PUF) data for each of the compositions of examples 1-3 as a function of La/Nd oxide content in the metals trap composition. The V-PUF, defined by the ratio of vanadium concentration in the trap (i.e., in the sink fraction) to that in the FCC catalyst (i.e., in the float fraction), is a measure of vanadium trapping efficiency.

Claims

1. Use of particles containing a metal passivation component containing:

15 to 60 parts by weight MgO,
30 to 60 parts by weight Al₂O₃, and
10 to 30 parts by weight rare earth compound selected from the group consisting of La oxide, Nd oxide, and mixtures thereof,

wherein at least a portion of said MgO and Al₂O₃ in said particles is present as an Mg-Al oxide spinel phase as vanadium passivators in a FCC process.

2. Use according to claim 1 wherein said particles consist essentially of:

15 to 60 parts by weight MgO,
30 to 60 parts by weight Al₂O₃, and
10 to 30 parts by weight rare earth compound selected from the group consisting of La

oxide, Nd oxide, and mixtures thereof.

3. Use according to claim 1 or 2 wherein substantially all of said MgO and Al₂O₃ is in the form of a magnesium aluminate spinel.
4. Use according to anyone of claims 1 to 3 wherein said metals passivation component contains 15 to 25 parts by weight of said rare earth compound.
5. Use according to anyone of claims 1 to 4 wherein said rare earth compound consists essentially of lanthan oxide.
6. Use according to anyone of claims 1 to 5 wherein said particles contain at least 50 wt.% of said passivation component.
7. Use according to claim 6 wherein said particles contain at least 75 wt.% of said metals passivation component.
8. Use according to anyone of claims 1 to 7 wherein said particles have a Davison attrition index of 0-15.
9. Use according to anyone of claims 1 to 8 wherein said passivation component is integrated into FCC catalyst particles.
10. Use according to claim 9 wherein said FCC catalyst particles contain 0.5 to 15 wt.% of said metals passivation component.

Patentansprüche

1. Verwendung von Teilchen, die eine Metallpassivierungskomponente enthalten, die

15 bis 60 Gewichtsteile MgO,
30 bis 60 Gewichtsteile Al₂O₃, und
10 bis 30 Gewichtsteile Seitenerdverbindung ausgewählt aus der Gruppe bestehend aus La-Oxid, Nd-Oxid und Mischungen derselben

enthält, wobei mindestens ein Teil des MgO und Al₂O₃ in den Teilchen als Mg-Al-Oxidspinnellphase vorliegt, als Vanadiumpassivatoren in einem katalytischen Wirbelschicht-Crack-(FCC)-Verfahren.

2. Verwendung nach Anspruch 1, bei der die Teilchen im Wesentlichen aus

15 bis 60 Gewichtsteilen MgO,
30 bis 60 Gewichtsteilen Al₂O₃, und
10 bis 30 Gewichtsteilen Seltenerdverbindung ausgewählt aus der Gruppe bestehend aus La-Oxid, Nd-Oxid und Mischungen derselben

bestehen.

3. Verwendung nach Anspruch 1 oder 2, bei der im Wesentlichen das gesamte MgO und Al_2O_3 in Form eines Magnesiumaluminat-Spinells vorliegt. 5
4. Verwendung nach einem der Ansprüche 1 bis 3, bei der die Metallpassierungskomponente 15 bis 25 Gewichtsteile der Seltenerdverbindung enthält. 10
5. Verwendung nach einem der Ansprüche 1 bis 4, bei der die Seltenerdverbindung im Wesentlichen aus Lanthanoxid besteht.
6. Verwendung nach einem der Ansprüche 1 bis 5, bei der die Teilchen mindestens 50 Gew.% der Passivierungskomponente enthalten. 15
7. Verwendung nach Anspruch 6, bei der die Teilchen mindestens 75 Gew.% der Metallpassivierungskomponente enthalten. 20
8. Verwendung nach einem der Ansprüche 1 bis 7, bei der die Teilchen einen Davison-Abriebindex von 0 bis 15 haben. 25
9. Verwendung nach einem der Ansprüche 1 bis 8, bei der die Passivierungskomponente in FCC-Katalysatorteilchen integriert ist. 30
10. Verwendung nach Anspruch 9, bei der die FCC-Katalysatorteilchen 0,5 bis 15 Gew.% der Metallpassivierungskomponente enthalten. 35

Revendications

1. Utilisation de particules contenant un composant de passivation des métaux contenant : 40
 - 15 à 60 parties en poids de MgO ,
 - 30 à 60 parties en poids de Al_2O_3 , et
 - 10 à 30 parties en poids de dérivé de terre rare choisi dans le groupe consistant en oxyde de La, oxyde de Nd et leurs mélanges, 45

où au moins une partie desdits MgO et Al_2O_3 dans lesdites particules est présente sous forme de phase de spinel d'oxyde de Mg-Al, en tant qu'agent de passivation du vanadium dans un procédé FCC. 50
2. Utilisation selon la revendication 1, dans laquelle lesdites particules consistent sensiblement en : 55
 - 15 à 60 parties en poids de MgO ,
 - 30 à 60 parties en poids de Al_2O_3 , et
 - 10 à 30 parties en poids de dérivé de terre rare choisi dans le groupe consistant en oxyde de

La, oxyde de Nd et leurs mélanges,

3. Utilisation selon la revendication 1 ou 2, dans laquelle sensiblement la totalité desdits MgO et Al_2O_3 est sous la forme d'une spinel d'aluminate de magnésium.
4. Utilisation selon l'une quelconque des revendications 1 à 3, dans laquelle ledit composant de passivation des métaux contient 15 à 25 parties en poids dudit dérivé de terre rare.
5. Utilisation selon l'une quelconque des revendications 1 à 4, dans laquelle ledit dérivé de terre rare consiste essentiellement en oxyde de lanthane.
6. Utilisation selon l'une quelconque des revendications 1 à 5, dans laquelle lesdites particules contiennent au moins 50 % en poids dudit composant de passivation.
7. Utilisation selon la revendication 6, dans laquelle lesdites particules contiennent au moins 75 % en poids dudit composant de passivation des métaux.
8. Utilisation selon l'une quelconque des revendications 1 à 7, dans laquelle lesdites particules ont un indice d'attrition Davison de 0-15.
9. Utilisation selon l'une quelconque des revendications 1 à 8, dans laquelle ledit composant de passivation fait partie intégrante des particules de catalyseur de FCC.
10. Utilisation selon la revendication 9, dans laquelle lesdites particules de catalyseur de FCC contiennent 0,5 à 15 % en poids dudit composant de passivation des métaux.

Figure 1

