

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 896 053 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**10.02.1999 Bulletin 1999/06**

(51) Int. Cl.<sup>6</sup>: **C11D 17/00**

(21) Application number: **97870166.2**

(22) Date of filing: **27.10.1997**

(84) Designated Contracting States:  
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC  
NL PT SE**  
Designated Extension States:  
**AL LT LV RO SI**

(30) Priority: **08.08.1997 EP 97870116**

(71) Applicant:  
**THE PROCTER & GAMBLE COMPANY**  
**Cincinnati, Ohio 45202 (US)**

(72) Inventors:  
• **Tcheou, Eric (NMN)**  
**1040 Brussel (BE)**  
• **Ongena, Steven René Martha**  
**9170 Sint-Gillis-Waas (BE)**

(74) Representative:  
**Mather, Peter Geoffrey et al**  
**BVBA Procter & Gamble Europe SPRL,**  
**Temselaan 100**  
**1853 Strombeek-Bever (BE)**

(54) **Detergent tablet**

(57) The present invention relates a detergent tablet comprising a core and a coating, the core having a diametral fracture stress of less than 15 kPa, and the core comprising a non-gelling binder, wherein the coated detergent tablet has a diametral fracture stress of at least 20 kPa.

In a further aspect of the invention there is provided a detergent tablet having a diametral fracture stress of at least 20 kPa, the tablet giving less than 18g residue at the end of the washing machine cycle under stressed test, the stressed test consisting of three tablets, each tablet weighing 60g, being placed in the bottom of the drum of a Miele® W831 washing machine, 2.5 kg of mixed fabric load being placed in the drum on top of the tablets, and the machine being run using a "whites/colours" short cycle of 30°C.

**EP 0 896 053 A1**

## Description

[0001] The present invention relates to detergent tablets, especially those adapted for use in washing.

[0002] Although cleaning compositions in tablet form have often been proposed, these have not (with the exception of soap bars for personal washing) gained any substantial success, despite the several advantages of products in a unit dispensing form. One of the reasons for this may be that detergent tablets usually dissolve slower than the constituent powders from which they are made, simply because the constituent powders are forced close together in the tablet, with comparatively little opportunity for water to permeate between them. This gives rise to the problem that slow dissolving tablets cause residues which may be visible through the door of the washing machine during the wash cycle, or which stick to the fabrics at the end of the wash cycle, or both.

[0003] EP-A-0 716 144, published on 12th June 1996, discloses laundry detergent tablets with water-soluble coatings which may be organic polymers including acrylic/maleic co-polymer, polyethylene glycol, PVPVA, and sugar. It states that the tablets of the invention preferably have a diametral fracture stress of at least 5 kPa. The speed of disintegration of the tablets is measured by means of a test using a metal gauze.

[0004] However, in certain front loading washing machines, problems of tablet residues appearing visibly at the window of the washing machine have still been encountered.

[0005] The object of the present invention is to provide tablets with a core which is formed by compressing a particulate material, the particulate material comprising surfactant and detergent builder, the tablet being suitable for storing, shipping and handling without breakage.

[0006] A further object of the invention is to provide a tablet comprising a soft core which breaks up easily and rapidly, releasing the active ingredients into the wash solution and which completely disintegrates and disperses in alkaline or surfactant-rich solutions such as the wash liquor.

## Summary of the Invention

[0007] The object of the invention is achieved by providing a detergent tablet comprising a core and a coating, the core having a diametral fracture stress of less than 15 kPa, and the core comprising a non-gelling binder, wherein the coated detergent tablet has a diametral fracture stress of at least 20 kPa.

[0008] In a further aspect of the invention there is provided a detergent tablet having a diametral fracture stress of at least 20 kPa, the tablet giving less than 18g residue at the end of the washing machine cycle under stressed test, the stressed test consisting of three tablets, each tablet weighing 60g, being placed in the bottom of the drum of a Miele® W831 washing machine, 2.5 kg of mixed fabric load being placed in the drum on top of the tablets, and the machine being run using a "whites/colours" short cycle of 30°C.

[0009] In a further aspect of the invention a method is provided for dispensing a detergent tablet from the dispensing drawer of a front loading washing machine.

## Detailed Description of the Invention

[0010] Detergent tablets of the present invention can be prepared simply by mixing the solid ingredients together and compressing the mixture in a conventional tablet press as used, for example, in the pharmaceutical industry. Preferably the principal ingredients, in particular gelling surfactants, are used in particulate form. Any liquid ingredients, for example the surfactant or suds suppressor, can be incorporated in a conventional manner into the solid particulate ingredients.

[0011] In particular for laundry tablets, the ingredients such as builder and surfactant can be spray-dried in a conventional manner and then compacted at a suitable pressure.

The detergent tablets can be made in any size or shape and can, if desired, be surface treated before coating, according to the present invention. In the core of the tablet is included a surfactant and a builder which normally provides a substantial part of the cleaning power of the tablet. The term "builder" is intended to mean all materials which tend to remove calcium ion from solution, either by ion exchange, complexation, sequestration or precipitation.

[0012] The particulate material used for making the tablet of this invention can be made by any particulation or granulation process. An example of such a process is spray drying (in a co-current or counter current spray drying tower) which typically gives low bulk densities 600g/l or lower. Particulate materials of higher density can be prepared by granulation and densification in a high shear batch mixer/granulator or by a continuous granulation and densification process (e.g. using Lodige® CB and/or Lodige® KM mixers). Other suitable processes include fluid bed processes, compaction processes (e.g. roll compaction), extrusion, as well as any particulate material made by any chemical process like flocculation, crystallisation, sintering, etc. Individual particles can also be any other particle, granule, sphere or grain.

[0013] The particulate materials may be mixed together by any conventional means. Batch is suitable in, for example,

a concrete mixer, Nauta mixer, ribbon mixer or any other. Alternatively the mixing process may be carried out continuously by metering each component by weight on to a moving belt, and blending them in one or more drum(s) or mixer(s). The non-gelling binder can be sprayed on to the mix of some, or all of, the particulate materials. Other liquid ingredients may also be sprayed on to the mix of particulate materials either separately or premixed. For example perfume and slurries of optical brighteners may be sprayed. A finely divided flow aid (dusting agent such as zeolites, carbonates, silicas) can be added to the particulate materials after spraying the binder, preferably towards the end of the process, to make the mix less sticky.

**[0014]** The tablets may be manufactured by using any compacting process, such as tableting, briquetting, or extrusion, preferably tableting. Suitable equipment includes a standard single stroke or a rotary press (such as Courtoy<sup>®</sup>, Korch<sup>®</sup>, Manesty<sup>®</sup>, or Bonals<sup>®</sup>). The tablets prepared according to this invention preferably have a diameter of between 40mm and 60mm, and a weight between 25 and 100 g. The ratio of height to diameter (or width) of the tablets is preferably greater than 1:3, more preferably greater than 1:2. The compaction pressure used for preparing these tablets need not exceed 5000 kN/m<sup>2</sup>, preferably not exceed 3000 kN/m<sup>2</sup>, and most preferably not exceed 1000 kN/m<sup>2</sup>.

**[0015]** Suitable non-gelling binders include synthetic organic polymers such as polyethylene glycols, polyvinylpyrrolidones, polyacrylates and water-soluble acrylate copolymers. The handbook of Pharmaceutical Excipients second edition, has the following binders classification: Acacia, Alginic Acid, Carbomer, Carboxymethylcellulose sodium, Dextrin, Ethylcellulose, Gelatin, Guar gum, Hydrogenated vegetable oil type I, Hydroxyethyl cellulose, Hydroxypropyl methylcellulose, Liquid glucose, Magnesium aluminum silicate, Maltodextrin, Methylcellulose, polymethacrylates, povidone, sodium alginate, starch and zein. Most preferable binders also have an active cleaning function in the laundry wash such as cationic polymers, i.e. ethoxylated hexamethylene diamine quaternary compounds, bis-hexamethylene triamines, or others such as pentaamines, ethoxylated polyethylene amines, maleic acrylic polymers.

**[0016]** The non-gelling binder materials are preferably sprayed on and hence have an appropriate melting point temperature below 70°C and preferably below 50°C so as not to damage or degrade the other active ingredients in the matrix. Most preferred are non-aqueous liquid binders (i.e. not in aqueous solution) which may be sprayed in molten form. However, they may also be solid binders incorporated into the matrix by dry addition but which have binding properties within the tablet.

**[0017]** The non-gelling binder materials are preferably used in an amount within the range from 0.1 to 15% of the composition, more preferably below 5% and especially if it is a non laundry active material below 2% by weight of the tablet.

**[0018]** It is preferred that gelling binders, such as nonionic surfactants are avoided in their liquid or molten form. Non-ionic surfactants and other gelling binders are not excluded from the compositions, but it is preferred that they be processed into the detergent tablets as components of particulate materials, and not as liquids.

**[0019]** In one embodiment of the present invention, the tablets may then be coated so that the tablet does not absorb moisture, or absorbs moisture at only a very slow rate. The coating is also strong so that moderate mechanical shocks to which the tablets are subjected during handling, packing and shipping result in no more than very low levels of breakage or attrition. Finally the coating is preferably brittle so that the tablet breaks up when subjected to stronger mechanical shock. Furthermore it is advantageous if the coating material is dissolved under alkaline conditions, or is readily emulsified by surfactants. This contributes to avoiding the problem of visible residue in the window of a front-loading washing machine during the wash cycle, and also avoids deposition of undissolved particles or lumps of coating material on the laundry load.

**[0020]** Water solubility is measured following the test protocol of ASTM E1148-87 entitled, "Standard Test Method for Measurements of Aqueous Solubility".

**[0021]** Suitable coating materials are dicarboxylic acids. Particularly suitable dicarboxylic acids are selected from the group consisting of oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, undecanedioic acid, dodecanedioic acid, tridecanedioic acid and mixtures thereof.

**[0022]** The coating material has a melting point preferably of from 40 °C to 200 °C.

The coating can be applied in a number of ways. Two preferred coating methods are a) coating with a molten material and b) coating with a solution of the material.

In a), the coating material is applied at a temperature above its melting point, and solidifies on the tablet. In b), the coating is applied as a solution, the solvent being dried to leave a coherent coating. The substantially insoluble material can be applied to the tablet by, for example, spraying or dipping.

**[0023]** Normally when the molten material is sprayed on to the tablet, it will rapidly solidify to form a coherent coating. When tablets are dipped into the molten material and then removed, the rapid cooling again causes rapid solidification of the coating material. Clearly substantially insoluble materials having a melting point below 40 °C are not sufficiently solid at ambient temperatures and it has been found that materials having a melting point above about 200 °C are not practicable to use. Preferably, the materials melt in the range from 60 °C to 160 °C, more preferably from 70 °C to 120 °C.

By "melting point" is meant the temperature at which the material when heated slowly in, for example, a capillary tube becomes a clear liquid.

[0024] A coating of any desired thickness can be applied according to the present invention. For most purposes, the coating forms from 1% to 10%, preferably from 1.5% to 5%, of the tablet weight.

[0025] The tablet coatings of the present invention are very hard and provide extra strength to the tablet.

5 [0026] In a preferred embodiment of the present invention the fracture of the coating in the wash is improved by adding a disintegrant in the coating. This disintegrant will swell once in contact with water and break the coating in small pieces. This will improve the dissolution of the coating in the wash solution. The disintegrant is suspended in the coating melt at a level of up to 30%, preferably between 5% and 20%, most preferably between 5 and 10% by weight. Possible disintegrants are described in Handbook of Pharmaceutical Excipients (1986). Examples of suitable disintegrants include starch: natural, modified or pregelatinized starch, sodium starch gluconate; gum: agar gum, guar gum, locust  
10 bean gum, karaya gum, pectin gum, tragacanth gum; croscarmylose Sodium, crospovidone, cellulose, carboxymethyl cellulose, alginic acid and its salts including sodium alginate, silicone dioxide, clay, polyvinylpyrrolidone, soy polysaccharides, ion exchange resins and mixtures thereof.

15 [0027] Depending on the composition of the starting material, and the shape of the tablets, the used compaction force will be adjusted to not affect the strength (Diametral Fracture Stress), and the disintegration time in the washing machine. This process may be used to prepare homogenous or layered tablets of any size or shape.

[0028] Diametral Fracture Stress (DFS) is a way to express the strength of a tablet, it is determined by the following equation :

$$20 \quad = \frac{2F}{\mu Dt}$$

25 [0029] Where F is the maximum force (Newton) to cause tensile failure (fracture) measured by a VK 200 tablet hardness tester supplied by Van Kell industries, Inc. D is the diameter of the tablet, and t the thickness of the tablet. (Method Pharmaceutical Dosage Forms : Tablets Volume 2 Page 213 to 217). A tablet having a diametral fracture stress of less than 20 kPa is considered to be fragile and is likely to result in some broken tablets being delivered to the consumer. A  
30 diametral fracture stress of at least 25 kPa is preferred.

[0030] The rate of disintegration of a detergent tablet can be determined in two ways :

a) In a "VAN KEL" Friabilator with "Vankel Type" drums.

- 35
- Put 2 tablets with a known weight and D.F.S in the Friabilator drum.
  - Rotate the drum for 20 rotations.
  - Collect all product and remaining tablet pieces from the Friabilator drum, and screen it on 5 mm, and through 1.7 mm
  - Express as % residue on 5 mm and through 1.7 mm.
- 40
- The higher the % of material through 1.7 mm the better the disintegration.

b) In a washing machine according to the following method

Three tablets, nominally 60 grams each, are weighed, and then placed in at the bottom of the wash drum of a front loading Miele® W831 washing machine. The machine is then filled with a 2.5kg clean ballast which comprises 8  
45 terry towels, 5 T-shirts, and 5 kitchen towels. The washing machine wash temperature is set to 30°C, the water supplied to the washing machine is set to a hardness of 21 grains per gram, and the wash cycle set to the wash program "Whites/Colors, short cycle".

50 [0031] At the end of the full cycle the residues are spun out of the wash load, and the residues which are stuck at the front window porthole are collected and the total is weighed. The level of residues is determined by repeating the procedure 10 times and an average residue level is calculated based on the ten individual measurements. In this stressed test a residue of 18g (i.e. corresponding to 10% of the starting tablet weight) is considered to be acceptable. A residue of less than 10g is preferred, and less than 5g is more preferred.

55 [0032] In a more stressed test the washing machine is stopped after ten minutes of the wash cycle and the residues are collected and weighed.

[0033] In another preferred embodiment of the present invention the tablets further comprises an effervescent. Effervescency as defined herein means the evolution of bubbles of gas from a liquid, as the result of a chemical reaction between a soluble acid source and an alkali metal carbonate, to produce carbon dioxide gas,



**[0034]** Further examples of acid and carbonate sources and other effervescent systems may be found in : (Pharmaceutical Dosage Forms : Tablets Volume 1 Page 287 to 291)

5 An effervescent may be added to the tablet mix in addition to the detergent ingredients. The addition of this effervescent to the detergent tablet improves the disintegration time of the tablet. The amount will preferably be between 5 and 20 % and most preferably between 10 and 20% by weight of the tablet. Preferably the effervescent should be added as an agglomerate of the different particles or as a compact, and not as separated particles.

10 Due to the gas created by the effervescency in the tablet, the tablet can have a higher D.F.S. and still have the same disintegration time as a tablet without effervescency. When the D.F.S. of the tablet with effervescency is kept the same as a tablet without, the disintegration of the tablet with effervescency will be faster.

#### Detersive surfactants

15 **[0035]** Nonlimiting examples of surfactants useful herein typically at levels from about 1% to about 55%, by weight, include the conventional  $\text{C}_{11}\text{-C}_{18}$  alkyl benzene sulfonates ("LAS") and primary, branched-chain and random  $\text{C}_{10}\text{-C}_{20}$  alkyl sulfates ("AS"), the  $\text{C}_{10}\text{-C}_{18}$  secondary (2,3) alkyl sulfates of the formula  $\text{CH}_3(\text{CH}_2)_x(\text{CHOSO}_3\text{M}^+)\text{CH}_3$  and  $\text{CH}_3(\text{CH}_2)_y(\text{CHOSO}_3\text{M}^+)\text{CH}_2\text{CH}_3$  where x and (y + 1) are integers of at least about 7, preferably at least about 9, and M is a water-solubilizing cation, especially sodium, unsaturated sulfates such as oleyl sulfate, the  $\text{C}_{10}\text{-C}_{18}$  alkyl alkoxy sul-

20 fates ("AE<sub>x</sub>S"; especially EO 1-7 ethoxy sulfates),  $\text{C}_{10}\text{-C}_{18}$  alkyl alkoxy carboxylates (especially the EO 1-5 ethoxycarboxylates), the  $\text{C}_{10}\text{-C}_{18}$  glycerol ethers, the  $\text{C}_{10}\text{-C}_{18}$  alkyl polyglycosides and their corresponding sulfated polyglycosides, and  $\text{C}_{12}\text{-C}_{18}$  alpha-sulfonated fatty acid esters. If desired, the conventional nonionic and amphoteric surfactants such as the  $\text{C}_{12}\text{-C}_{18}$  alkyl ethoxylates ("AE") including the so-called narrow peaked alkyl ethoxylates and  $\text{C}_6\text{-C}_{12}$  alkyl phenol alkoxyates (especially ethoxylates and mixed ethoxy/propoxy),  $\text{C}_{12}\text{-C}_{18}$  betaines and sulfobetaines ("sultaines"),  $\text{C}_{10}\text{-C}_{18}$  amine oxides, and the like, can also be included in the overall compositions. The  $\text{C}_{10}\text{-C}_{18}$  N-alkyl polyhydroxy fatty acid amides can also be used. Typical examples include the  $\text{C}_{12}\text{-C}_{18}$  N-methylglucamides. See WO 9,206,154. Other sugar-derived surfactants include the N-alkoxy polyhydroxy fatty acid amides, such as  $\text{C}_{10}\text{-C}_{18}$  N-(3-methoxypropyl) glucamide. The N-propyl through N-hexyl  $\text{C}_{12}\text{-C}_{18}$  glucamides can be used for low sudsing.  $\text{C}_{10}\text{-C}_{20}$  conventional soaps may also be used. If high sudsing is desired, the branched-chain  $\text{C}_{10}\text{-C}_{16}$  soaps may be used. Mixtures of an-

25 ionic and nonionic surfactants are especially useful. Other conventional useful surfactants are listed in standard texts.

#### Builders

35 **[0036]** Detergent builders can optionally be included in the compositions herein to assist in controlling mineral hardness. Inorganic as well as organic builders can be used. Builders are typically used in fabric laundering compositions to assist in the removal of particulate soils.

The level of builder can vary widely depending upon the end use of the composition.

Inorganic or P-containing detergent builders include, but are not limited to, the alkali metal, ammonium and alkanolammonium salts of polyphosphates (exemplified by the tripolyphosphates, pyrophosphates, and glassy polymeric metaphosphates), phosphonates, phytic acid, silicates, carbonates (including bicarbonates and sesquicarbonates), sul-

40 phates, and aluminosilicates. However, non-phosphate builders are required in some locales. Importantly, the compositions herein function surprisingly well even in the presence of the so-called "weak" builders (as compared with phosphates) such as citrate, or in the so-called "underbuilt" situation that may occur with zeolite or layered silicate builders.


45 Examples of silicate builders are the alkali metal silicates, particularly those having a  $\text{SiO}_2\text{:Na}_2\text{O}$  ratio in the range 1.6:1 to 3.2:1 and layered silicates, such as the layered sodium silicates described in U.S. Patent 4,664,839, issued May 12, 1987 to H. P. Rieck. NaSKS-6 is the trademark for a crystalline layered silicate marketed by Hoechst (commonly abbreviated herein as "SKS-6"). Unlike zeolite builders, the Na SKS-6 silicate builder does not contain aluminum. NaSKS-6 has the delta- $\text{Na}_2\text{SiO}_5$  morphology form of layered silicate. It can be prepared by methods such as those described in

50 German DE-A-3,417,649 and DE-A-3,742,043. SKS-6 is a highly preferred layered silicate for use herein, but other such layered silicates, such as those having the general formula  $\text{NaMSi}_x\text{O}_{2x+1} \cdot y\text{H}_2\text{O}$  wherein M is sodium or hydrogen, x is a number from 1.9 to 4, preferably 2, and y is a number from 0 to 20, preferably 0 can be used herein. Various other layered silicates from Hoechst include NaSKS-5, NaSKS-7 and NaSKS-11, as the alpha, beta and gamma forms. As noted above, the delta- $\text{Na}_2\text{SiO}_5$  (NaSKS-6 form) is most preferred for use herein. Other silicates may also be useful

55 such as for example magnesium silicate, which can serve as a crispening agent in granular formulations, as a stabilizing agent for oxygen beaches, and as a component of suds control systems.


Examples of carbonate builders are the alkaline earth and alkali metal carbonates as disclosed in German Patent Application No. 2,321,001 published on November 15, 1973.

Aluminosilicate builders are useful in the present invention. Aluminosilicate builders are of great importance in most currently marketed heavy duty granular detergent compositions, and can also be a significant builder ingredient in liquid detergent formulations. Aluminosilicate builders include those having the empirical formula:



wherein z and y are integers of at least 6, the molar ratio of z to y is in the range from 1.0 to about 0.5, and x is an integer from about 15 to about 264.

Useful aluminosilicate ion exchange materials are commercially available. These aluminosilicates can be crystalline or amorphous in structure and can be naturally-occurring aluminosilicates or synthetically derived. A method for producing aluminosilicate ion exchange materials is disclosed in U.S. Patent 3,985,669, Krummel, et al, issued October 12, 1976. Preferred synthetic crystalline aluminosilicate ion exchange materials useful herein are available under the designations Zeolite A, Zeolite P (B), Zeolite MAP and Zeolite X. In an especially preferred embodiment, the crystalline aluminosilicate ion exchange material has the formula:



wherein x is from about 20 to about 30, especially about 27. This material is known as Zeolite A. Dehydrated zeolites (x = 0 - 10) may also be used herein. Preferably, the aluminosilicate has a particle size of about 0.1-10 microns in diameter.

Organic detergent builders suitable for the purposes of the present invention include, but are not restricted to, a wide variety of polycarboxylate compounds. As used herein, "polycarboxylate" refers to compounds having a plurality of carboxylate groups, preferably at least 3 carboxylates. Polycarboxylate builder can generally be added to the composition in acid form, but can also be added in the form of a neutralized salt. When utilized in salt form, alkali metals, such as sodium, potassium, and lithium, or alkanolammonium salts are preferred.

Included among the polycarboxylate builders are a variety of categories of useful materials. One important category of polycarboxylate builders encompasses the ether polycarboxylates, including oxydisuccinate, as disclosed in Berg, U.S. Patent 3,128,287, issued April 7, 1964, and Lamberti et al, U.S. Patent 3,635,830, issued January 18, 1972. See also "TMS/TDS" builders of U.S. Patent 4,663,071, issued to Bush et al, on May 5, 1987. Suitable ether polycarboxylates also include cyclic compounds, particularly alicyclic compounds, such as those described in U.S. Patents 3,923,679; 3,835,163; 4,158,635; 4,120,874 and 4,102,903.

Other useful detergency builders include the ether hydroxypolycarboxylates, copolymers of maleic anhydride with ethylene or vinyl methyl ether, 1, 3, 5-trihydroxy benzene-2, 4, 6-trisulphonic acid, and carboxymethyloxysuccinic acid, the various alkali metal, ammonium and substituted ammonium salts of polyacetic acids such as ethylenediamine tetraacetic acid and nitrilotriacetic acid, as well as polycarboxylates such as mellitic acid, succinic acid, oxy-disuccinic acid, polymaleic acid, benzene 1,3,5-tricarboxylic acid, carboxymethyloxysuccinic acid, and soluble salts thereof.

Citrate builders, e.g., citric acid and soluble salts thereof (particularly sodium salt), are polycarboxylate builders of particular importance for heavy duty liquid detergent formulations due to their availability from renewable resources and their biodegradability. Citrates can also be used in granular compositions, especially in combination with zeolite and/or layered silicate builders. Oxydisuccinates are also especially useful in such compositions and combinations.

Also suitable in the detergent compositions of the present invention are the 3,3-dicarboxy-4-oxa-1,6-hexanedioates and the related compounds disclosed in U.S. Patent 4,566,984, Bush, issued January 28, 1986. Useful succinic acid builders include the C<sub>5</sub>-C<sub>20</sub> alkyl and alkenyl succinic acids and salts thereof. A particularly preferred compound of this type is dodecenylsuccinic acid. Specific examples of succinate builders include: laurylsuccinate, myristylsuccinate, palmitylsuccinate, 2-dodecenylsuccinate (preferred), 2-pentadecenylsuccinate, and the like. Laurylsuccinates are the preferred builders of this group, and are described in European Patent Application 86200690.5/0,200,263, published November 5, 1986.

Other suitable polycarboxylates are disclosed in U.S. Patent 4,144,226, Crutchfield et al, issued March 13, 1979 and in U.S. Patent 3,308,067, Diehl, issued March 7, 1967. See also Diehl U.S. Patent 3,723,322.

**[0037]** Fatty acids, e.g., C<sub>12</sub>-C<sub>18</sub> monocarboxylic acids, can also be incorporated into the compositions alone, or in combination with the aforesaid builders, especially citrate and/or the succinate builders, to provide additional builder activity. Such use of fatty acids will generally result in a diminution of sudsing, which should be taken into account by the formulator.

In situations where phosphorus-based builders can be used, and especially in the formulation of bars used for hand-laundering operations, the various alkali metal phosphates such as the well-known sodium tripolyphosphates, sodium pyrophosphate and sodium orthophosphate can be used. Phosphonate builders such as ethane-1-hydroxy-1,1-diphosphonate and other known phosphonates (see, for example, U.S. Patents 3,159,581; 3,213,030; 3,422,021; 3,400,148 and 3,422,137) can also be used.

## Bleach

[0038] The detergent compositions herein may optionally contain bleaching agents or bleaching compositions containing a bleaching agent and one or more bleach activators. When present, bleaching agents will typically be at levels of from about 1% to about 30%, more typically from about 5% to about 20%, of the detergent composition, especially for fabric laundering. If present, the amount of bleach activators will typically be from about 0.1% to about 60%, more typically from about 0.5% to about 40% of the bleaching composition comprising the bleaching agent-plus-bleach activator.

The bleaching agents used herein can be any of the bleaching agents useful for detergent compositions in textile cleaning, hard surface cleaning, or other cleaning purposes that are now known or become known. These include oxygen bleaches as well as other bleaching agents. Perborate bleaches, e.g., sodium perborate (e.g., mono- or tetra-hydrate) can be used herein.

Another category of bleaching agent that can be used without restriction encompasses percarboxylic acid bleaching agents and salts thereof. Suitable examples of this class of agents include magnesium monoperoxyphthalate hexahydrate, the magnesium salt of metachloro perbenzoic acid, 4-nonylamino-4-oxoperoxybutyric acid and diperoxydecanedioic acid. Such bleaching agents are disclosed in U.S. Patent 4,483,781, Hartman, issued November 20, 1984, U.S. Patent Application 740,446, Burns et al, filed June 3, 1985, European Patent Application 0,133,354, Banks et al, published February 20, 1985, and U.S. Patent 4,412,934, Chung et al, issued November 1, 1983. Highly preferred bleaching agents also include 6-nonylamino-6-oxoperoxydecanoic acid as described in U.S. Patent 4,634,551, issued January 6, 1987 to Burns et al.


Peroxygen bleaching agents can also be used. Suitable peroxygen bleaching compounds include sodium carbonate peroxyhydrate and equivalent "percarbonate" bleaches, sodium pyrophosphate peroxyhydrate, urea peroxyhydrate, and sodium peroxide. Persulfate bleach (e.g., OXONE, manufactured commercially by DuPont) can also be used.

A preferred percarbonate bleach comprises dry particles having an average particle size in the range from about 500 micrometers to about 1,000 micrometers, not more than about 10% by weight of said particles being smaller than about 200 micrometers and not more than about 10% by weight of said particles being larger than about 1,250 micrometers. Optionally, the percarbonate can be coated with silicate, borate or water-soluble surfactants. Percarbonate is available from various commercial sources such as FMC, Solvay and Tokai Denka.

Mixtures of bleaching agents can also be used.

Peroxygen bleaching agents, the perborates, the percarbonates, etc., are preferably combined with bleach activators, which lead to the *in situ* production in aqueous solution (i.e., during the washing process) of the peroxy acid corresponding to the bleach activator. Various nonlimiting examples of activators are disclosed in U.S. Patent 4,915,854, issued April 10, 1990 to Mao et al, and U.S. Patent 4,412,934. The nonanoyloxybenzene sulfonate (NOBS) and tetraacetyl ethylene diamine (TAED) activators are typical, and mixtures thereof can also be used. See also U.S. 4,634,551 for other typical beaches and activators useful herein.

Highly preferred amido-derived bleach activators are those of the formulae:



wherein  $R^1$  is an alkyl group containing from about 6 to about 12 carbon atoms,  $R^2$  is an alkylene containing from 1 to about 6 carbon atoms,  $R^5$  is H or alkyl, aryl, or alkaryl containing from about 1 to about 10 carbon atoms, and L is any suitable leaving group. A leaving group is any group that is displaced from the bleach activator as a consequence of the nucleophilic attack on the bleach activator by the perhydrolysis anion. A preferred leaving group is phenyl sulfonate.

Preferred examples of bleach activators of the above formulae include (6-octanamido-caproyl)oxybenzenesulfonate, (6-nonanamidocaproyl)oxybenzene-sulfonate, (6-decanamidocaproyl)oxybenzenesulfonate, and mixtures thereof as described in U.S. Patent 4,634,551, incorporated herein by reference.

Another class of bleach activators comprises the benzoxazin-type activators disclosed by Hodge et al in U.S. Patent 4,966,723, issued October 30, 1990, incorporated herein by reference. A highly preferred activator of the benzoxazin-type is:



15



25

30

35

45

## 50

55



Enzymes are normally incorporated at levels sufficient to provide up to about 5 mg by weight, more typically about 0.01 mg to about 3 mg, of active enzyme per gram of the composition. Stated otherwise, the compositions herein will typically comprise from about 0.001% to about 5%, preferably 0.01%-1% by weight of a commercial enzyme preparation. Protease enzymes are usually present in such commercial preparations at levels sufficient to provide from 0.005 to 0.1 Anson units (AU) of activity per gram of composition.

**[0041]** Suitable examples of proteases are the subtilisins which are obtained from particular strains of *B. subtilis* and *B. licheniformis*. Another suitable protease is obtained from a strain of *Bacillus*, having maximum activity throughout the pH range of 8-12, developed and sold by Novo Industries A/S under the registered trade name ESPERASE. The preparation of this enzyme and analogous enzymes is described in British Patent Specification No. 1,243,784 of Novo. Proteolytic enzymes suitable for removing protein-based stains that are commercially available include those sold under the tradenames ALCALASE and SAVINASE by Novo Industries A/S (Denmark) and MAXATASE by International Bio-Synthetics, Inc. (The Netherlands). Other proteases include Protease A (see European Patent Application 130,756, published January 9, 1985) and Protease B (see European Patent Application Serial No. 87303761.8, filed April 28, 1987, and European Patent Application 130,756, Bott et al, published January 9, 1985).

Amylases include, for example,  $\alpha$ -amylases described in British Patent Specification No. 1,296,839 (Novo), RAPIDASE, International Bio-Synthetics, Inc. and TERMAMYL, Novo Industries.

The cellulase usable in the present invention include both bacterial or fungal cellulase. Preferably, they will have a pH optimum of between 5 and 9.5. Suitable cellulases are disclosed in U.S. Patent 4,435,307, Barbesgoard et al, issued March 6, 1984, which discloses fungal cellulase produced from *Humicola insolens* and *Humicola* strain DSM1800 or a cellulase 212-producing fungus belonging to the genus *Aeromonas*, and cellulase extracted from the hepatopancreas of a marine mollusk (*Dolabella Auricula Solander*). Suitable cellulases are also disclosed in GB-A-2.075.028; GB-A-2.095.275 and DE-OS-2.247.832. CAREZYME (Novo) is especially useful.

Suitable lipase enzymes for detergent usage include those produced by microorganisms of the *Pseudomonas* group, such as *Pseudomonas stutzeri* ATCC 19.154, as disclosed in British Patent 1,372,034. See also lipases in Japanese Patent Application 53,20487, laid open to public inspection on February 24, 1978. This lipase is available from Amano Pharmaceutical Co. Ltd., Nagoya, Japan, under the trade name Lipase P "Amano," hereinafter referred to as "Amano-P." Other commercial lipases include Amano-CES, lipases ex *Chromobacter viscosum*, e.g. *Chromobacter viscosum* var. *lipolyticum* NRRLB 3673, commercially available from Toyo Jozo Co., Tagata, Japan; and further *Chromobacter viscosum* lipases from U.S. Biochemical Corp., U.S.A. and Disoynth Co., The Netherlands, and lipases ex *Pseudomonas gladioli*. The LIPOLASE enzyme derived from *Humicola lanuginosa* and commercially available from Novo (see also EPO 341,947) is a preferred lipase for use herein.

Peroxidase enzymes are used in combination with oxygen sources, e.g., percarbonate, perborate, persulfate, hydrogen peroxide, etc. They are used for "solution bleaching," i.e. to prevent transfer of dyes or pigments removed from substrates during wash operations to other substrates in the wash solution. Peroxidase enzymes are known in the art, and include, for example, horseradish peroxidase, ligninase, and haloperoxidase such as chloro- and bromo-peroxidase. Peroxidase-containing detergent compositions are disclosed, for example, in PCT International Application WO 89/099813, published October 19, 1989, by O. Kirk, assigned to Novo Industries A/S.

A wide range of enzyme materials and means for their incorporation into synthetic detergent compositions are also disclosed in U.S. Patent 3,553,139, issued January 5, 1971 to McCarty et al. Enzymes are further disclosed in U.S. Patent 4,101,457, Place et al, issued July 18, 1978, and in U.S. Patent 4,507,219, Hughes, issued March 26, 1985, both. Enzyme materials useful for liquid detergent formulations, and their incorporation into such formulations, are disclosed in U.S. Patent 4,261,868, Hora et al, issued April 14, 1981. Enzymes for use in detergents can be stabilized by various techniques. Enzyme stabilization techniques are disclosed and exemplified in U.S. Patent 3,600,319, issued August 17, 1971 to Gedge, et al, and European Patent Application Publication No. 0 199 405, Application No. 86200586.5, published October 29, 1986, Venegas. Enzyme stabilization systems are also described, for example, in U.S. Patent 3,519,570.

**[0042]** Other components which are commonly used in detergent compositions and which may be incorporated into the detergent tablets of the present invention include chelating agents, soil release agents, soil antiredeposition agents, dispersing agents, brighteners, suds suppressors, fabric softeners, dye transfer inhibition agents and perfumes.

**[0043]** It is known to place laundry detergent tablets in the washing drum together with the laundry. However, this method tends to result in unsightly residues appearing visibly at the window, especially in certain types of washing machine which have been designed to operate with a lower water consumption. In extreme cases visible residues can also be left on clothes at the end of the wash cycle.

**[0044]** The present invention also relates to a method of washing which significantly avoids this problem. The new method comprises the preparation of an aqueous solution of a laundry detergent for use in a front-loading washing machine, the front-loading washing machine having a dispensing drawer and a washing drum, wherein the aqueous solution of laundry detergent is formed by dissolving a detergent tablet in water, characterised in that the detergent tablet is placed in the dispensing drawer and water is passed through the dispensing drawer so that the tablet is dispensed

as an aqueous solution of a laundry detergent, the aqueous solution subsequently being passed in the washing drum.

**[0045]** Whilst any detergent tablet may be used in the method of the invention, it has been found that the tablets described herein are most completely dispensed from the dispenser drawer without leaving residues in the dispenser drawer. It is further preferred that the density of the tablet is from 0.9 to 1.1 g/cc, and more preferably from 0.95 to 1.05 g/cc.

5

10

15

20

25

30

35

40

45

50

55

## EXAMPLES

		Comp. 1	Comp. 2	Comp. 3
5	Anionic Agglomerates	28.69	28.99	34.80
	Nonionic Agglomerate	5.93	5.93	-
	Cationic Agglomerate	-	-	5.51
10	Bleach Activator Agglomerates	6.10	6.10	4.53
	Zinc Phthalocyanine sulphonate	0.03	0.03	0.03
	encapsulate			
15	Suds Supressor	3.46	3.46	1.89
	Dried Zeolite	6.75	6.75	-
20	Layered Silicate	14.67	14.67	10.68
	Dye transfer Inhibitor Agglomerate	0.14	0.14	-
	Perfume Encapsulates	0.25	0.25	-
25	AE7/PEG4000 spray on	5.82	5.82	-
	PEG200	-	1.20	-
	Diamine quat	1.50	-	1.08
30	Fluorescer	0.28	0.28	0.183
	Sodium carbonate	5.02	5.02	13.96
	Sodium perborate monohydrate	17.80	17.80	-
35	Sodium percarbonate	-	-	14.33
	Sodium HEDP	0.85	0.85	0.74
40	Soil Release polymer	0.19	0.19	0.33
	Perfume	0.35	0.35	0.46
	Protease	0.92	0.92	0.89
45	Cellulase	0.27	0.27	0.21
	Lipase	0.23	0.23	0.275
	Amylase	0.75	0.75	1.04
50	Citric acid	-	-	7.16
	Soap	-	-	1.90
	TOTAL	100.00	100.00	100.00
55				

[0046]

Anionic agglomerates comprise 38% anionic surfactant, 22% zeolite and 40% carbonate.

Nonionic agglomerates comprise 26% nonionic surfactant, 48% zeolite and 26% carbonate.

Cationic agglomerates comprise 24% cationic surfactant (alkyl hydroxyethyl dimethyl ammonium chloride), 64% zeolite, and 12% sulphate.

Bleach activator agglomerates comprise 81% TAED, 17% acrylic/maleic copolymer (acid form) and 2% water.

Zinc Phthalocyanine sulphonate encapsulates are 10% active.

Suds suppressor comprises 11.5% silicone oil (ex Dow Corning), and 88.5% starch.

Layered silicate comprises 78% SKS-6, ex Hoechst, 22% citric acid.

Dye transfer inhibitor agglomerates comprise 21% PVNO/PVPVI, 61% zeolite and 18% carbonate.

Perfume encapsulates comprise 50% perfume and 50% starch.

AE7/PEG4000 spray-on comprises 83% C12-C15 AE7 (alcohol with an average of 7 ethoxy groups per molecule), 17% polyethylene glycol with an average molecular weight of 4000.

PEG200 is polyethylene glycol with an average molecular weight of 200

Diamine quat is ethoxylated hexa methylenediamine quaternary compound.

#### Example 1

**[0047]** A detergent base powder of Composition 1 is prepared by the following steps:

Nonionic AE7/PEG4000 mixture is sprayed on the sodium perborate in a mixing drum. After spray on zeolite is used to dust the perborate impregnated with nonionic to eliminate its potential to bind the other powders;

Ethoxylated hexamethylenediamine quat (the non-gelling binder) is sprayed on to the layered silicate, the bleach activator agglomerates and the carbonate; the contents of these two mixing drums are then mixed together with the remaining particulate materials of Composition 1 to form a homogeneous particulate.

**[0048]** 80 parts of the Composition 1 are then mixed in a mixing drum with 15 parts of sodium acetate and 5 parts of an effervescent mix consisting of 54.5% sodium bicarbonate and 45.5% citric acid.

**[0049]** Tablets are then made by introducing 55g of the mixture into a circular mold (diameter 54mm) and compressed to give tablets of 21 mm height and a density of 1.1 g/cc. The diametral fracture stress is 6 kPa.

**[0050]** The tablets are then dipped into a coating bath containing 90 parts of dodecanedioic acid mixed with 10 parts of Nymcel z6b16 heated to 140°C. The tablets are left in the bath for just long enough for 5g of coating to be applied,

after which the tablets are removed and left to cool at 25°C for 24 hours. The diametral fracture stress is increased by the coating to greater than 20 kPa.

#### Example 2

**[0051]** A detergent base powder of Composition 2 is prepared by the following steps:

Nonionic AE7/PEG4000 mixture is sprayed on the sodium perborate in a mixing drum. After spray on zeolite is used to dust the perborate impregnated with nonionic to eliminate its potential to bind the other powders;

PEG200 (the non-gelling binder) is sprayed on to the layered silicate, the bleach activator agglomerates and the carbonate;

and thereafter the process of Example 1 is repeated except that 45 g of the composition are compressed into 45mm diameter tablet having a height of 23mm and a density of 1.1 g/cc.

**[0052]** The uncoated tablet has a diametral fracture stress of 10.2 kPa.

**[0053]** Detergent tablets having the following characteristics are produced:

	Example 1	Example 2
Diameter (mm)	55	45
Diametral Fracture Stress	24kPa	30kPa
Residue after 10 mins (g)	17	7
Residue at end of washing machine cycle (g)	7	2

**[0054]** In Examples 1 and 2 the tablets are used to wash a laundry load, by placing three tablets into the drum of a Miele<sup>®</sup> W831 washing machine together with the laundry.

#### Example 3

**[0055]**

i) Detergent composition 3 is prepared as follows : all the particulate materials of base composition 3, except for diamine quat and the perfume were mixed together in a mixing drum to form a homogeneous particulate mixture. During this mixing, the spray-ons of the diamine quat and perfume were carried out.

ii) Tablets were then made the following way : 45 g of the mixture was introduced into a mould of circular shape with a diameter of 4.5 cm and compressed to give tablets of 2.3 cm height and a density of 1.0 g/cc. The tensile strength (or diametrical fracture stress) of the tablet was 10.2 kPa.

**[0056]** In Examples 4, 5 and 6, the same tablets were prepared as in Examples 1, 2 and 3, however in Examples 4, 5 and 6, the tablet density is 1 g/cc. The tablets are placed into the dispensing drawer of the Miele<sup>®</sup> W831 washing machine, the laundry is placed into the drum, and the washing machine cycle is run.

#### Claims

1. Detergent tablet comprising a core and a coating, the core having a diametral fracture stress of less than 15 kPa, and the core comprising a non-gelling binder, characterised in that the coated detergent tablet has a diametral fracture stress of at least 20 kPa.

2. Detergent tablet according to claim 1 wherein the detergent core has a diametral fracture stress of less than 10 kPa, and preferably less than 5 kPa.

3. Detergent tablet having a diametral fracture stress of at least 20 kPa, the tablet giving less than 18g residue at the end of the washing machine cycle under stressed test, the stressed test consisting of three tablets, each tablet weighing 60g, being placed in the bottom of the drum of a Miele® W831 washing machine, 2.5 kg of mixed fabric load being placed in the drum on top of the tablets, and the machine being run using a "whites/colours" short cycle of 30°C.
4. Detergent tablet according to claim 3 wherein the tablet has a diametral fracture stress of at least 25 kPa.
5. Detergent tablet according to claim 3 wherein the residue in the stressed test is less than 10g, and preferably less than 5g.
6. Detergent tablet comprising a core and a coating, the core having a diametral fracture stress of less than 15 kPa, and the core comprising a non-gelling binder, characterised in that the coated detergent tablet has a diametral fracture stress of at least 20 kPa, and wherein the tablet gives less than 18g residue at the end of the washing machine cycle under stressed test, the stressed test consisting of three tablets, each tablet weighing 60g, being placed in the bottom of the drum of a Miele® W831 washing machine, 2.5 kg of mixed fabric load being placed in the drum on top of the tablets, and the machine being run using a "whites/colours" short cycle of 30°C.
7. A method of preparing an aqueous solution of a laundry detergent for use in a front loading washing machine, the front loading washing machine having a dispensing drawer and a washing drum, wherein the aqueous solution of laundry detergent is formed by dissolving a detergent tablet in water, characterised in that the detergent tablet is placed in the dispensing drawer and water is passed through the dispensing drawer so that the tablet is dispensed as an aqueous solution of a laundry detergent, the aqueous solution subsequently being passed into the washing drum.
8. A method according to claim 7 wherein the detergent tablet is a coated detergent tablet according to either of claims 1 or 2.
9. A method according to claim 8 wherein the coated detergent tablet comprises a coating which is insoluble in water.
10. A method according to either of claims 8 or 9 wherein the coated detergent tablet comprises a coating and wherein the coating comprises a dicarboxylic acid.
11. A method according to any of claims 7 to 10, the tablet having a density of from 0.9 g/cc to 1.1 g/cc.



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 97 87 0166

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 522 766 A (UNILEVER) 13 January 1993 * page 3, line 5 - page 5, line 42; claims; examples 1-3 *	1,3-6	C11D17/00
D,A	EP 0 716 144 A (UNILEVER) 12 June 1996 * page 7, line 5 - page 8, line 54; claim 1 *	1,6	
A	EP 0 711 827 A (UNILEVER) 15 May 1996 * page 6, line 27 - page 7, line 40; claims; example 2 *	1,6	
A	DATABASE WPI Section Ch, Week 8745 Derwent Publications Ltd., London, GB; Class D25, AN 87-317677 XP002031238 & JP 62 225600 A (LION CORP) ; 3 October 1987 * abstract *	1	
A	DATABASE WPI Section Ch, Week 9403 Derwent Publications Ltd., London, GB; Class D16, AN 94-023143 XP002051794 & JP 05 331497 A (LION CORP) , 14 December 1993 * abstract *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C11D
X	DE 195 00 936 A (WEBER RUDOLF DIPL ING) 18 July 1996 * page 3, line 49 - line 60 *	7	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 16 November 1998	Examiner Grittern, A
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (P04C01)