



(19)

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 097 915 A1

(12)

## EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

09.05.2001 Bulletin 2001/19

(51) Int. Cl.<sup>7</sup>: C07C 37/20, C07C 39/16,

B01J 31/10

(21) Application number: 99926773.5

(86) International application number:

PCT/JP99/03348

(22) Date of filing: 23.06.1999

(87) International publication number:

WO 00/00454 (06.01.2000 Gazette 2000/01)

(84) Designated Contracting States:

DE FR

(30) Priority: 26.06.1998 JP 19654098

(71) Applicant:

Nippon Steel Chemical Co., Ltd.  
Tokyo 141-0031 (JP)

(72) Inventors:

- SAKURA, Katsuhiko  
Nippon Steel Chemical Co., Ltd.  
Tobata Kitakyushu Fukuoka 804-850 (JP)
- UEDA, Shingo  
Nippon Steel Chemical Co., Ltd.  
Tobata Kitakyushu Fukuoka 804-850 (JP)
- TAKEUCHI, Genki  
Nippon Steel Chemical Co., Ltd.  
Oita-shi Oita-ken 870-0111 (JP)

• SHIRASAKA, Shyouta

Nippon Steel Chemical Co., Ltd.

Oita-shi Oita-ken 870-0111 (JP)

• MARUYAMA, Toshikazu

Nippon St. Chemical Co., Ltd.

Tobata Kitakyushu Fukuoka-ken 804-8503 (JP)

• HUKUDA, Yasuharu

Nippon Steel Chemical Co., Ltd.

Tobata Kitakyushu Fukuoka-ken 804-8503 (JP)

• KITO, Taketoshi

Kitakyushu-shi Fukuoka-ken 807-1111 (JP)

• KIMURA, Morio

Kitakyushu-shi Fukuoka-ken 803-0835 (JP)

(74) Representative:

Calamita, Roberto et al

Frank B. Dehn & Co.,

European Patent Attorneys,

179 Queen Victoria Street

London EC4V 4EL (GB)

### (54) PROCESS FOR PRODUCING BISPHENOL A

(57) This invention relates to a process for preparing bisphenol A by the condensation of phenol with acetone in the presence of cation exchange resin obtained by sulfonating copolymers of monovinyl monomers mainly consisting of styrenes and divinyl monomers as crosslinking agent while using divinylbiphenyl and divinylbenzene mainly as said divinyl monomers and controlling the molar ratio of divinylbiphenyl to divinylbenzene at 10/0-2/8. The cation exchange resin to be used as catalyst in the condensation reaction shows a long life, maintains the production of bisphenol A over a long period of time, possesses high strength and is useful for economical and advantageous production of bisphenol A.

EP 1 097 915 A1

**Description**Field of Technology

5 [0001] This invention relates to a process for preparing 2,2-bis(4-hydroxyphenyl)propane (hereinafter referred to as bisphenol A).

Background Technology

10 [0002] In recent years, there is an increasing demand for bisphenol A as a principal raw material for engineering plastics such as polycarbonates and epoxy resins. Bisphenol A is usually obtained by the reaction of excess phenol with acetone in the presence of an acidic catalyst. Cation exchange resins are most common for such catalyst and those containing sulfonic acid groups are normally used. Of cation exchange resins containing sulfonic acid groups, sulfonated styrene-divinylbenzene copolymers are put to practical use most widely.

15 [0003] Sulfonated styrene-divinylbenzene copolymers are resins obtained by copolymerizing styrene and divinylbenzene in the presence of a polymerization initiator and introducing sulfonic acid groups to the aromatic rings of the styrene and divinylbenzene in the resulting copolymers with the aid of sulfuric acid and the like. The copolymers in question are considered to have a complex three-dimensional network in which divinylbenzene bridges polystyrene chains to form an irregularly intertwined structure. An increase in the amount of divinylbenzene leads to increased 20 branching of the polystyrene chain and a denser network. Conversely, a decrease in the amount of divinylbenzene leads to decreased branching and a coarser network. The divinylbenzene here plays the role of a knot in the network and is referred to as crosslinking agent. The ratio of the amount of crosslinking agent added to the amount of total monomers used is generally designated as degree of crosslinking.

25 [0004] The aforementioned copolymers ranging widely in the degree of crosslinking have been used as a catalyst for the preparation of bisphenol A and the existence of a significant correlation has been reported between the degree of crosslinking and the catalyst life. For example, Japan Kokai Tokkyo Koho Hei 6-32755 (1994) teaches the use of cation exchange resins with a degree of crosslinking of 6 wt.% or less since the life of a cation exchange resin catalyst becomes longer as the degree of crosslinking becomes lower. However, a cation exchange resin catalyst with a lower degree of crosslinking generally contains less sulfonic acid groups per unit volume of catalyst and leads to reduced output 30 of bisphenol A. Moreover, a cation exchange resin catalyst with a lower degree of crosslinking is more susceptible to elastic deformation when subjected to a stress from the outside and, when used in a fixed-bed reactor, may occasionally cause such pressure loss as to render the production difficult on a commercial scale. Thus, elongation of the catalyst life by reducing the degree of crosslinking causes another problem and an improved procedure is desired for development of cation exchange resin catalysts which maintain the production of bisphenol A over a long period of time, 35 resist elastic deformation and possess high strength without decreasing the number of sulfonic acid groups per unit volume of catalyst.

40 [0005] An object of this invention is to provide cation exchange resin catalysts which show high productivity per unit volume of catalyst, have a long life, maintain high productivity of bisphenol A over a long period of time, resist elastic deformation and possess high strength. Another object of this invention is to provide an efficient process for preparing bisphenol A.

Disclosure of the Invention

45 [0006] The present inventors have conducted intensive studies to accomplish the aforementioned objective, found that divinylbiphenyl is appropriate for use as crosslinking agent for cation exchange resin catalysts and arrived at this invention.

50 [0007] Accordingly, this invention relates to a process for preparing 2,2-bis(4-hydroxyphenyl)propane by the condensation of phenol with acetone in the presence of a cation exchange resin catalyst obtained by sulfonating copolymers of monovinyl monomers mainly comprising of styrenes and divinyl monomers as crosslinking agent which comprises using divinyl monomers containing 20 mol% or more of divinylbiphenyl. This invention also relates to the aforementioned cation exchange resin catalysts to be used in the condensation reaction.

55 [0008] The sulfonated copolymers of styrene and divinyl monomers to be used as cation exchange resin catalyst in this invention are prepared in accordance with a known procedure by copolymerizing a mixture of monovinyl monomers mainly comprising of styrenes and divinyl monomers mainly comprising of divinylbiphenyl or divinylbenzene and divinylbiphenyl in the presence of a polymerization initiator and sulfonating the resulting copolymers with sulfuric acid or the like to introduce sulfonic acid groups to the aromatic rings of the styrenes and divinyl monomers.

56 [0009] Styrenes include monovinyl derivatives of aromatic compounds such as styrene, vinyltoluene,  $\alpha$ -methylstyrene, vinylxylene, vinylethylbenzene, vinylbiphenyl, methylvinylbiphenyl. Monovinyl monomers other than styrenes

include aliphatic olefins. Monovinyl monomers here mainly consist of styrenes, that is, they consist of 50 mol% or more, preferably 80 mol% or more, of styrenes.

**[0010]** Divinyl monomers may be 100% divinylbiphenyl or a mixture of divinylbiphenyl with other divinyl monomers if the latter are less than 20 mol%. Such other divinyl monomers include divinylbenzene and divinyltoluene, divinylbenzene being preferable. Divinylbiphenyl accounts for 20 mol% or more, preferably 50 mol% or more, of divinyl monomers. Moreover, divinyl monomers mainly consist of divinylbiphenyl and divinylbenzene and the two together desirably account for 50 mol% or more, preferably 80 mol% or more, of divinyl monomers.

**[0011]** Of several isomers of divinylbiphenyl, 4,4'-divinylbiphenyl or a mixture of isomers mainly consisting of 4,4'-divinylbiphenyl is preferable. Depending on the procedure used for its preparation, 4,4'-divinylbiphenyl occasionally contains the unreacted starting material and intermediates such as 4,4'-diethylbiphenyl, 4,4'-vinylethylbiphenyl and 4-vinylbiphenyl and it can be used together with such intermediates without ill effect. Rather, it is desirable that 4,4'-divinylbiphenyl contains 10-60 mol% of monovinylbiphenyls such as 4,4'-vinylethylbiphenyl and 4-vinylbiphenyl. Monovinylbiphenyls are counted as monovinyl monomer. Likewise, of the isomers of divinylbenzene, 1,4-divinylbenzene or a mixture mainly consisting of 1,4-divinylbenzene is preferable.

**[0012]** As for the ratio of divinylbenzene to divinylbiphenyl in use, more divinylbiphenyl gives a longer catalyst life and higher catalyst strength, which makes it desirable to use as high a proportion of divinylbiphenyl as possible. Concretely, the molar ratio of divinylbiphenyl to divinylbenzene is 10/0-8/2, preferably 10/0-5/5.

**[0013]** The degree of crosslinking, as designated by the weight ratio of divinyl monomers as crosslinking agent to a mixture of all monomers, is not restricted, but it is 0.1-20 wt.%, preferably 1-15 wt.%, more preferably 2-8 wt.%, in consideration of the catalyst life, productivity of bisphenol A and catalyst strength. The degree of crosslinking as designated by the molar ratio of divinyl monomers to the total monomers is 2-50 mol%, preferably 2-40 mol%, more preferably 3-10 mol%. A decrease in this degree of crosslinking lowers the catalyst strength and performance.

**[0014]** A known procedure can be adopted for the copolymerization of monovinyl monomers mainly consisting of styrenes and divinyl monomers. Normally, the copolymerization is carried out at 50-90 °C for 3-30 hours in accordance with a procedure, for example, of introducing water and a dispersant in specified amounts to the polymerization reactor, adding a mixture of monomers in which a polymerization initiator has been dissolved to the water with stirring to form an oil-in-water suspension, and carrying out the polymerization at a specified temperature in a nitrogen atmosphere.

**[0015]** A concrete procedure for the polymerization is as follows. A polymerization initiator is added to a mixture of monovinyl monomers and divinyl monomers and the resulting mixture is subjected to mass, solution or suspension polymerization. Suspension polymerization is preferable for the preparation of resin beads suitable for use in a fixed bed. In this case, water in an amount 1-10 times that of the monomer mixture is used as dispersing medium and a dispersant such as polyvinyl alcohol and carboxymethylcellulose is used in an amount 0.05-5 wt.% of the monomer mixture. As for polymerization initiator, a known substance such as benzoyl peroxide and an azo compound can be used in an amount 0.01-15 wt.% of the monomer mixture.

**[0016]** Those copolymers which are prepared by merely copolymerizing monovinyl monomers mainly consisting of styrenes and divinyl monomers as crosslinking agent are transparent and gel-like in structure and they are called gel type resins. The copolymers in question form a two-dimensional network in which bifunctional divinyl monomers bridge polystyrene chains to form an irregularly intertwined structure and the interstices in the network are called micropores.

**[0017]** On the other hand, copolymers may be prepared in another way by copolymerizing a solution of monovinyl monomers mainly consisting of styrenes and divinyl monomers as crosslinking agent in an organic solvent which is a good solvent of these monovinyl and divinyl monomers and insoluble in water (for example, toluene, ethylbenzene and n-hexane) and stripping the organic solvent. A large space nearly free of intertwinement is created inside the resulting copolymers or the copolymers are porous. Such copolymers are generally called macroporous resins and the large space is called macropore.

**[0018]** Gel type or macroporous copolymers prepared in the aforementioned manner normally occur as crack-free spherical beads with a particle diameter in the range 100-1,000 µm. The beads are sulfonated by a given sulfonating agent in the presence of a swelling agent to yield cation exchange resin catalysts.

**[0019]** Preferable as a swelling agent is an organic solvent that swells the aforementioned copolymers well and is inert to the sulfonating agent; for example, dichloromethane and nitrobenzene. Such a solvent is normally used in an amount 0.1-10 times that of the copolymers on a weight basis.

**[0020]** The sulfonation is effected by stirring the swollen copolymer particles in 95-100% sulfuric acid. The amount of sulfuric acid is normally 3-30 times that of the copolymers on a weight basis. The temperature for the treatment is 50-150°C, preferably 90-110 °C, and the period is 3-30 hours.

**[0021]** The sulfonated styrene-divinyl monomer copolymers, that is, cation exchange resins, obtained in the aforementioned manner are used as catalyst in this invention. This cation exchange resin catalyst is generally used in a fixed-bed reactor, but it may be used in a fluidized-bed reactor.

**[0022]** For the preparation of bisphenol A, a known procedure involving the use of cation exchange resin as catalyst may be adopted. The raw materials for the reaction are usually acetone and excess phenol and, if necessary, a reaction

accelerator may be additionally used. As for the raw material acetone, a commercially available material is used as it is here but the acetone remaining unreacted in the reaction mixture may be recovered by such means as distillation and used.

**[0023]** As for the raw material phenol, phenol of industrial grade available on the market is used as it is or the mother liquor obtained by crystallizing the adduct of bisphenol A with phenol from the reaction mixture and separating the crystals by filtration may be used. Useful as reaction accelerator are thiols such as methylmercaptan, ethylmercaptan, mercaptoethanol and mercaptopropionic acid.

**[0024]** In case the aforementioned cation exchange resin is used as catalyst in a fixed-bed reactor according to the process of this invention, the liquid hourly space velocity (LHSV) is 0.1-20 hr<sup>-1</sup>, preferably 0.3-5 hr<sup>-1</sup>. As for the reaction temperature, the formation of impurities originating from side reactions becomes pronounced at high temperatures and such impurities adversely affect the quality of bisphenol A while the rate of reaction drops to cause a decrease in the output of bisphenol A at low temperatures. Concretely, the reaction temperature is preferably 45-140 °C, more preferably 55-100°C. The molar ratio of acetone to phenol is normally 0.005-0.5, preferably 0.01-0.3. A reaction accelerator may be added at a rate of 0.01-2% of the raw materials.

**[0025]** A general procedure for recovering bisphenol A from the reaction mixture is to separate low-boiling substances such as acetone, water, and reaction accelerator from the reaction mixture by such means as distillation, crystallize the adduct of bisphenol A with phenol separate the crystalline adduct from the mother liquor by such means as filtration, and remove the phenol from the adduct.

## 20 Preferred Embodiments of the Invention

### Example 1

**[0026]** Into a 500-ml three-necked separable flask fitted with a stirrer and a condenser was introduced 0.1 g of polyvinyl alcohol, then was introduced a mixture of 44.1 g of styrene, 5.9 g of crosslinking agents containing 52% of divinylbiphenyl (mainly consisting of the 4,4'-isomer; % by weight here and hereafter), 30% of vinylmethylethylbiphenyl and 18% of vinylbiphenyl and 0.1 g of benzoyl peroxide, and the mixture was allowed to polymerize with stirring at 80 °C for 10 hours while passing nitrogen through the system.

**[0027]** Particles of the copolymers were recovered from the mixture after polymerization, 30 g of the air-dried particles was placed in a 300-ml four-necked flask fitted with a stirrer and a condenser, 60 g of water and 150 g of nitrobenzene were added, and the resulting mixture was stirred at 70°C for 2 hours to swell the copolymers. The swollen copolymers were recovered and air-dried, placed in whole in a 300-ml four-necked flask fitted with a stirrer and a condenser, 150 g of concentrated sulfuric acid was added to the flask, and the mixture was heated at 80°C for 10 hours with stirring to effect sulfonation. After the reaction, the sulfonated copolymers were collected by filtration and washed with 1,200 g of water.

**[0028]** The cation exchange resin containing sulfonic acid groups obtained in this manner showed a total exchange capacity of 1.31 meq/ml-R. The chatillon value was 440 g/particle as a result of the crushing test conducted on 100 resin particles with a diameter of 600 µm.

**[0029]** Using the aforementioned cation exchange resin containing sulfonic acid groups as a catalyst, the reaction for the preparation of bisphenol A was carried out as follows. Phenol was allowed to react with acetone in the presence of ethylmercaptan as a reaction accelerator to yield a mixture containing bisphenol A. Low-boiling substances such as acetone, water and ethylmercaptan were distilled off from the mixture, the adduct of bisphenol A with phenol was crystallized out and filtered off to give the mother liquor (composed of 85% of phenol, 8% of bisphenol A, 5% of 2,4-isomer, and 2% of other impurities), 1,000 parts by weight of which was mixed with 30 parts by weight of acetone and 2 parts by weight of ethylmercaptan and fed continuously at a rate of 50 ml/hr at 70 °C to a flow reactor that is made of stainless steel, 1 cm in inside diameter and filled with 50 ml of the aforementioned cation exchange resin. Table 1 shows the change in conversion of acetone with time in terms of conversion of acetone vs. number of days of feeding to the flow reactor and also the pressure loss in the reactor after 150 days of feeding.

## 50 Example 2

**[0030]** The procedure of Example 1 was followed to prepare cation exchange resin containing sulfonic acid groups except using a feedstock containing 44.6 g of styrene, 4.7 g of crosslinking agents composed of 52% of divinylbiphenyl, 30% of vinylmethylethylbiphenyl and 18% of vinylbiphenyl and 0.7 g of crosslinking agents composed of 57% of divinylbenzene and 43% of vinylmethylethylbenzene in the step for preparing the copolymers. The resin showed a total exchange capacity of 1.29 meq/ml-R and also a chatillon value of 430 g/particle as a result of the crushing test conducted on 100 resin particles with a diameter of 600 µm.

## Example 3

**[0031]** The procedure of Example 1 was followed to prepare cation exchange resin containing sulfonic acid groups except using a feedstock containing 45.5 g of styrene, 2.4 g of crosslinking agents composed of 52% of divinylbiphenyl, 5 30% of vinylethylbiphenyl and 18% of vinylbiphenyl and 2.1 g of crosslinking agents composed of 57% of divinylbenzene and 43% of vinylethylbenzene, in the step for preparing the copolymers. The resin showed a total exchange capacity of 1.28 meq/ml-R and also a chatillon value of 420 g/particle as a result of the crushing test conducted on 100 resin particles with a diameter of 600  $\mu\text{m}$ .

## 10 Example 4

**[0032]** The procedure of Example 1 was followed to prepare cation exchange resin containing sulfonic acid groups except using a feedstock containing 45.9 g of styrene, 1.3 g of crosslinking agents composed of 52% of divinylbiphenyl, 15 30% of vinylethylbiphenyl and 18% of vinylbiphenyl and 2.8 g of crosslinking agents composed of 57% of divinylbenzene and 43% of vinylethylbenzene in the step for preparing the copolymers. The resin showed a total exchange capacity of 1.27 meq/ml-R and also a chatillon value of 440 g/particle as a result of the crushing test conducted on 100 resin particles with a diameter of 600  $\mu\text{m}$ .

## Comparative Example 1

**[0033]** The procedure of Example 1 was followed to prepare cation exchange resin containing sulfonic acid groups except using a feedstock containing 46.2 g of styrene, 0.6 g of crosslinking agents composed of 52% of divinylbiphenyl, 20 30% of vinylethylbiphenyl and 18% of vinylbiphenyl and 3.2 g of crosslinking agents composed of 57% of divinylbenzene and 43% of vinylethylbenzene in the step for preparing the copolymers. The resin showed a total exchange capacity of 1.25 meq/ml-R and also a chatillon value of 390 g/particle as a result of the crushing test conducted on 100 resin particles with a diameter of 600  $\mu\text{m}$ .

## Comparative Example 2

**[0034]** The procedure of Example 1 was followed to prepare cation exchange resin containing sulfonic acid groups except using a feedstock containing 46.5 g of styrene and 3.5 g of crosslinking agents composed of 57% of divinylbenzene and 43% of vinylethylbenzene in the step for preparing the copolymers. The resin showed a total exchange capacity of 1.24 meq/ml-R and also a chatillon value of 380 g/particle as a result of the crushing test conducted on 100 resin particles with a diameter of 600  $\mu\text{m}$ .

**[0035]** The cation exchange resins containing sulfonic acid groups obtained in Examples 2 to 4 and Comparative Examples 1 and 2 were respectively used as catalyst in the reaction in the manner described in Example 1.

**[0036]** Table 1 shows the molar ratio of divinylbiphenyl to divinylbenzene (DVBP/DVB), chatillon value, total exchange capacity per 1 ml of swollen resin of the cation exchange resins and the reaction results in the aforementioned Examples and Comparative Examples

40

Table 1

	DVBP/DVB Molar ratio	Chatillon value g/parti- cle	Total exchange capacity meq/ml-R	Conversion of acetone %			Pressure loss kg/cm <sup>2</sup>	
				0 day	30 days	150 days		
45	Example 1	10/0	440	1.31	93.1	92.2	88.5	4.5
50	Example 2	8/2	430	1.29	92.4	90.1	81.4	4.6
	Example 3	4/6	420	1.28	91.1	86.3	66.5	4.8
55	Example 4	2/8	400	1.27	90.5	84.3	59.1	5.0
	Comparative example 1	1/9	390	1.25	90.1	83.4	55.6	5.5

Table 1 (continued)

	DVBP/DVB Molar ratio	Chatillon value g/parti- cle	Total exchange capacity meq/ml-R	Conversion of acetone %			Pressure loss kg/cm <sup>2</sup>	
				0 day	30 days	150 days		
10	Comparative example 2	0/10	380	1.24	89.7	82.0	52.4	5.6

Industrial Applicability

**[0037]** Catalysts based on the cation exchange resins containing sulfonic acid groups developed by this invention show not only a longer life than those based on cation exchange resins containing sulfonic acid groups derived from the conventional styrene-divinylbenzene copolymers but also a reduced pressure loss when used in a flow reactor and they are capable of improving further the productivity of bisphenol A.

**Claims**

1. A process for preparing 2,2-bis(4-hydroxyphenyl)propane by the condensation of phenol with acetone in the presence of cation exchange resin obtained by sulfonating copolymers of monovinyl monomers mainly comprising of styrenes and divinyl monomers as crosslinking agent which comprises using divinylbiphenyl or divinylbiphenyl and divinylbenzene mainly as said divinyl monomers and controlling the molar ratio of divinylbiphenyl to divinylbenzene at 10/0-2/8.
2. Catalysts for preparing 2,2-bis(4-hydroxyphenyl)propane which are composed of cation exchange resins useful for the condensation of phenol with acetone to yield 2,2-bis(4-hydroxyphenyl)propane and are prepared by sulfonating copolymers of monovinyl monomers mainly comprising of styrenes and divinyl monomers as crosslinking agent while using divinylbiphenyl or divinylbiphenyl and divinylbenzene mainly as said divinyl monomers and controlling the molar ratio of divinylbiphenyl to divinylbenzene at 10/0-2/8.

35

40

45

50

55

<b>INTERNATIONAL SEARCH REPORT</b>		International application No. <b>PCT/JP99/03348</b>															
<b>A. CLASSIFICATION OF SUBJECT MATTER</b> Int.Cl <sup>6</sup> C07C37/20, C07C39/16, B01J31/10																	
According to International Patent Classification (IPC) or to both national classification and IPC																	
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) Int.Cl <sup>6</sup> C07C37/20, C07C39/16, B01J31/10, C07C15/50																	
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched																	
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) CA (STN), REGISTRY (STN)																	
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left; padding: 2px;">Category*</th> <th style="text-align: left; padding: 2px;">Citation of document, with indication, where appropriate, of the relevant passages</th> <th style="text-align: left; padding: 2px;">Relevant to claim No.</th> </tr> </thead> <tbody> <tr> <td style="padding: 2px;">A</td> <td style="padding: 2px;">JP, 6-32755, A (Idemitsu Petrochemical Co., Ltd.), 8 February, 1994 (08. 02. 94), Page 2, column 1, line 1 to column 2, line 23 (Family: none)</td> <td style="padding: 2px;">1, 2</td> </tr> <tr> <td style="padding: 2px;">A</td> <td style="padding: 2px;">JP, 6-320009, A (Bayer AG.), 22 November, 1994 (22. 11. 94), Page 2, column 1, line 1 to column 2, line 48 &amp; DE, 4312039, A1 &amp; EP, 621252, B1 &amp; US, 5395857, A</td> <td style="padding: 2px;">1, 2</td> </tr> <tr> <td style="padding: 2px;">A</td> <td style="padding: 2px;">JP, 10-139696, A (Nippon Steel Chemical Co., Ltd.), 26 May, 1998 (26. 05. 98), Page 2, column 1, lines 24 to 37 (Family: none)</td> <td style="padding: 2px;">2</td> </tr> <tr> <td style="padding: 2px;">A</td> <td style="padding: 2px;">JP, 8-269137, A (Nippon Steel Chemical Co., Ltd.), 15 October, 1996 (15. 10. 96), Page 2, column 1, lines 1 to 47 ; page 3, column 4, line 26 to page 4, column 5, line 11 (Family: none)</td> <td style="padding: 2px;">2</td> </tr> </tbody> </table>			Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	A	JP, 6-32755, A (Idemitsu Petrochemical Co., Ltd.), 8 February, 1994 (08. 02. 94), Page 2, column 1, line 1 to column 2, line 23 (Family: none)	1, 2	A	JP, 6-320009, A (Bayer AG.), 22 November, 1994 (22. 11. 94), Page 2, column 1, line 1 to column 2, line 48 & DE, 4312039, A1 & EP, 621252, B1 & US, 5395857, A	1, 2	A	JP, 10-139696, A (Nippon Steel Chemical Co., Ltd.), 26 May, 1998 (26. 05. 98), Page 2, column 1, lines 24 to 37 (Family: none)	2	A	JP, 8-269137, A (Nippon Steel Chemical Co., Ltd.), 15 October, 1996 (15. 10. 96), Page 2, column 1, lines 1 to 47 ; page 3, column 4, line 26 to page 4, column 5, line 11 (Family: none)	2
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.															
A	JP, 6-32755, A (Idemitsu Petrochemical Co., Ltd.), 8 February, 1994 (08. 02. 94), Page 2, column 1, line 1 to column 2, line 23 (Family: none)	1, 2															
A	JP, 6-320009, A (Bayer AG.), 22 November, 1994 (22. 11. 94), Page 2, column 1, line 1 to column 2, line 48 & DE, 4312039, A1 & EP, 621252, B1 & US, 5395857, A	1, 2															
A	JP, 10-139696, A (Nippon Steel Chemical Co., Ltd.), 26 May, 1998 (26. 05. 98), Page 2, column 1, lines 24 to 37 (Family: none)	2															
A	JP, 8-269137, A (Nippon Steel Chemical Co., Ltd.), 15 October, 1996 (15. 10. 96), Page 2, column 1, lines 1 to 47 ; page 3, column 4, line 26 to page 4, column 5, line 11 (Family: none)	2															
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.																	
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed																	
"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family																	
Date of the actual completion of the international search 17 September, 1999 (17. 09. 99)		Date of mailing of the international search report 28 September, 1999 (28. 09. 99)															
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer															
Facsimile No.		Telephone No.															

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP99/03348

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, 2-32032, A (Showa Denko K.K.), 1 February, 1990 (01. 02. 90), Page 1, left column, lines 1 to 16 (Family: none)	2

Form PCT/ISA/210 (continuation of second sheet) (July 1992)