(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication: **05.09.2001 Bulletin 2001/36**

(51) Int CI.7: **H01M 6/50**, H01M 10/42

(21) Application number: 01301511.0

(22) Date of filing: 20.02.2001

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 22.02.2000 JP 2000044101

(71) Applicants:


- MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD. Kadoma-shi, Osaka 571-8501 (JP)
- TOYOTA JIDOSHA KABUSHIKI KAISHA Aichi-ken 471-8571 (JP)
- (72) Inventors:
 - Onishi, Masato Toyohashi-shi, Aichi 441-8106 (JP)

- Osawa, Michio Toyohashi-shi, Aichi 440-0026 (JP)
- Tomioka, Katsuyuki Toyohashi-shi, Aichi 441-8112 (JP)
- Fujioka, Noriyuki Kosai-shi, Shizuoka 431-0452 (JP)
- Saito, Tomoharu
 Toyohashi-shi, Aichi 440-0856 (JP)
- (74) Representative: Rackham, Stephen Neil GILL JENNINGS & EVERY, Broadgate House, 7 Eldon Street London EC2M 7LH (GB)

(54) Battery sealing inspection method

(57) A battery (1) which has undergone initial charging and discharging is placed inside a sealed vessel (3), which is evacuated by a vacuum pump (9). After this evacuated state has been maintained for a while, the

density of hydrogen gas within the sealed vessel (3) is measured by a hydrogen density sensor (11), based on which the presence or absence of a gas escape from the battery is determined. The battery may be heated instead of subjecting it to charging and discharging.



Description

[0001] The present invention relates to a method of inspecting sealing property of battery.

[0002] Figure 2 illustrates a conventional battery sealing inspection method for verifying the sealing properties of a sealed battery case. The battery case 21 is closed with a sealing plate, in which a hole 22 is formed for mounting a safety vent or the like. Compressed gas is introduced from a high-pressure gas source 23 via a valve 24 into the battery case 21, and the pressure inside the battery case 21 is measured by a pressure gauge 25. When the pressure inside the battery case 21 has reached a predetermined value, the valve 24 is closed, and pressure change thereafter inside the battery case 21 is measured by the pressure gauge 25. If a fall in pressure is observed, then the battery is identified to be a defective battery in which gas is leaking out from the battery case.

[0003] Another prior art battery sealing inspection method as disclosed in Japanese Laid-open Patent Application No. 4-25738 includes introducing of compressed hydrogen gas into a battery case, and detecting the hydrogen gas leaking out from the battery case by collector plates and a semiconductor gas sensor.

[0004] In the inspection method illustrated in Fig. 2, the amount of gas leaking from the battery case 21, if any, is fairly small relative to the volume of the battery case 21, and hence the pressure drop inside the battery case 21 due to gas leakage is very small. Therefore, detection accuracy is relatively low, because detection of gas leakage is possible only when there is a hole or a gap of more than 100 µm. In order to ensure accurate detection of gas leakage with this method, it takes at least 5 to 10 minutes per each battery, resulting in extremely poor efficiency. Moreover, since the compressed air is introduced into the battery case through the hole 22 for mounting a safety vent or the like prior to the actual mounting of such parts, it was necessary to inspect the sealing properties of the battery after the safety vent has been mounted on the battery case by welding. Thus the method involves a further leakage test with respect to the welds.

[0005] In the method disclosed in Japanese Laidopen Patent Application No. 4-25738, since there is no assurance that the leaked gas will always be collected accurately by the collector plates, there are variations in detection accuracy. Also, similarly to the former method, this method involves a further inspection of sealing properties of the battery case with respect to the portion through which compressed air is introduced into the battery case.

[0006] In view of the foregoing problems of the prior art, an object of the present invention is to provide a battery sealing inspection method whereby gas leakage from any location on a battery case is detected with a high degree of accuracy, good efficiency, and high reliability.

[0007] In a method for inspecting sealing properties of a battery according to the present invention, the battery is made to undergo charging and discharging before being placed within a sealed vessel. The sealed vessel is then evacuated, and a certain low pressure inside thereof is maintained for a predetermined period of time. The density of a gas within the sealed vessel, the gas being a gas generated within the battery, is measured, based on which it is determined whether there is a gas leak from the battery, by comparing the measured gas density with a preliminarily obtained reference value

[0008] The characteristic feature of the invention is that the battery is charged and discharged prior to inspection so as to raise the internal pressure of the battery. Moreover, the sealed vessel in which the battery is placed is evacuated so as to make the internal pressure of the battery even higher relative to its ambient pressure. Since the battery is housed within the sealed vessel, a gas leak, even in a slightest amount, from any location of the battery is detected by the measurement of gas density within the sealed vessel. Thus the inspection method ensures detection of a hole or a crack as small as about 10 μm with good efficiency and high reliability.

[0009] The inspection should preferably be performed immediately after the battery has undergone initial charging and discharging, where the internal pressure of the battery is particularly high.

[0010] In another embodiment of the invention, a battery which has been filled with electrolyte and has been sealed is placed within a sealed vessel, and is heated to a predetermined temperature. The sealed vessel is then evacuated, and a certain low pressure inside thereof is maintained for a predetermined period of time. The density of a gas within the sealed vessel, the gas being a gas generated within the battery, is measured, based on which it is determined whether there is a gas leak from the battery, by comparing the measured gas density with a preliminarily obtained reference value.

[0011] In this embodiment, the battery is heated instead of subjected to charging and discharging in order to raise the internal pressure thereof. Therefore the inspection is performed with good efficiency and high reliability similarly to the above described embodiment. This embodiment is also effective for the inspection of batteries that have been stored for a long period of time after initial charging and discharging.

[0012] The battery should preferably be heated to a temperature between 45 °C and 80 °C, and more preferably to 65 °C plus or minus 5 °C. This temperature range enables the battery internal pressure to be a level optimal for accurate detection of gas leakage, while preventing degradation of other members which will not withstand high heat such as separators.

[0013] The gas generated within the battery is hydrogen, and the reference value is obtained by measuring hydrogen density in an ambient atmosphere prior to

evacuation of the sealed vessel. In this way, the inspection is performed without being affected by the initial hydrogen density of ambient atmosphere, and gas leakage is accurately detected.

[0014] Preferred embodiments of the present invention will be hereinafter described with reference to the accompanying drawings, in which:

Fig. 1 is a schematic diagram showing one embodiment of a battery sealing inspection method according to the present invention; and

Fig. 2 is a schematic diagram showing a conventional battery sealing inspection method.

[0015] In Fig. 1, reference numeral 1 denotes a battery, such as a nickel metal hydride battery which is the object of inspection. The battery includes a safety vent 2 for discharging hydrogen gas externally in the event that the internal pressure has reached a predetermined value or above. Reference numeral 3 denotes a hermetically sealed vessel for accommodating therein the battery 1 to perform sealing inspection. The vessel 3 is connected to a vacuum exhaust tube 4 and is provided with an air inlet 5 which can be opened or closed by means of a valve 6.

[0016] A pressure gauge 7, a valve 8, a vacuum pump 9, a switching valve 10, and a hydrogen density sensor 11, are serially connected to the vacuum exhaust tube 4 in this order from the sealed vessel side. The switching valve 10 connected between the vacuum pump 9 and the hydrogen density sensor 11 has an air inlet 12, and switches from one to another of three states: In a first state, the outlet of the vacuum pump 9 is connected to the air inlet 12 of the switching valve 10; in a second state, the outlet of the vacuum pump 9 is connected to the hydrogen density sensor 11; and in a third state, the air inlet 12 of the switching valve 10 is connected to the hydrogen density sensor 11.

[0017] Before inspecting the sealing property of the battery 1, the battery 1 is filled with electrolyte, sealed, and made to undergo initial charging and discharging, so that the battery 1 is activated and an internal pressure generated therein. Meanwhile, the switching valve 10 is switched to the third state where the air inlet 12 of the switching valve 10 is communicated with the hydrogen density sensor 11, for measuring the hydrogen density in the atmosphere. The value thus obtained is taken as the atmospheric hydrogen density A.

[0018] Thereupon, the battery 1 which has completed charging and discharging is placed inside the sealed vessel 3, and the valve 6 of the air inlet 5 is closed, while the valve 8 of the vacuum exhaust tube 4 is opened. Meanwhile, the switching valve 10 is switched to the first state where the outlet of the vacuum pump 9 communicates with the air inlet 12 of the switching valve 10. The vacuum pump 9 is then operated, so as to reduce the pressure inside the sealed vessel 3 to 10 kPa.

[0019] After maintaining the internal pressure of the

sealed vessel 3 at 10 kPa for approximately 1 minute to several minutes, the switching valve 10 is switched to the second state where the outlet of the vacuum pump 9 is connected to the hydrogen density sensor 11, so as to introduce the air inside the sealed vessel 3 into the hydrogen density sensor 11, for measuring the hydrogen density inside the sealed vessel 3. The value thus measured is taken as the sealed vessel hydrogen density B. Thereupon, the presence or absence of a gas escape from the battery 1 is judged based on a difference between the atmospheric hydrogen density A and the sealed vessel hydrogen density B.

[0020] According to this embodiment of the invention, prior to inspection, the battery 1 is made to undergo initial charging and discharging, so as to increase the internal pressure of the battery. Moreover, the battery is placed in the sealed vessel 3 so that the battery ambient pressure is in a vacuum state, whereby the internal pressure of the battery is made even higher relative to the outside of the battery. Since the inspection of gas leakage is effected by detecting small molecules of hydrogen gas, even a slightest gas leakage is readily detected. Moreover, since the battery 1 is placed inside the sealed vessel 3, it is possible to detect gas escape from any location of the battery 1 by the hydrogen density sensor 11. Accordingly, the inspection is performed in a short time with high accuracy, good efficiency, and high reliability. Defective batteries are readily detected particularly when the inspection is performed on a battery immediately after the initial charging and discharging whereby the internal pressure of the battery has been increased. Also, the determination as to whether there is any gas leakage is not affected by the initial atmospheric gas density, because the judgment is made based on the difference between a reference value of the atmospheric hydrogen density A which is previously measured and the hydrogen density B in the sealed vessel 3.

[0021] A modification may be made to the above described arrangement for battery sealing inspection method. The arrangement is substantially the same as that shown in Figure 1, with the exception that a heater (not illustrated) such as an infrared lamp is provided within the sealed vessel 3 for heating the battery 1.

[0022] For the sealing inspection, the battery 1 is filled with electrolyte, sealed, and placed within the sealed vessel 3. Meanwhile, the switching valve 10 is switched to the third state where the air inlet 12 of the switching valve 10 is communicated with the hydrogen density sensor 11, for measuring the hydrogen density in the atmosphere. The value thus obtained is taken as the atmospheric hydrogen density A.

[0023] Thereupon, the battery 1 is heated to a temperature of approximately 65 °C, by means of the infrared lamp (not illustrated) disposed inside the sealed vessel 3. Preferably, the battery is heated to a temperature of 45 °C to 80 °C, and more preferably to 65 °C plus or minus 5 °C. This is because the equilibrium pressure

20

inside the battery at a temperature of 45 $^{\circ}$ C is 0.02 to 0.03 MPa, whereas it is 0.15 to 0.20 MPa at a temperature of 80 $^{\circ}$ C, and therefore, at a temperature below 45 $^{\circ}$ C, the internal pressure of the battery is too low to effect inspection to a desired degree of accuracy. On the other hand, if the temperature is above 80 $^{\circ}$ C, it will cause degradation of the other parts which will not withstand high heat such as separators.

[0024] Similarly to the aforementioned embodiment, the interior of the sealed vessel 3 is evacuated and after maintaining this state for a predetermined period of time, the hydrogen density inside the sealed vessel 3 is measured by the hydrogen density sensor 11, and hence a sealed vessel hydrogen density B is obtained. The presence or absence of a gas escape from the battery 1 is judged from the difference between the atmospheric hydrogen density A and the sealed vessel hydrogen density B.

[0025] According to this embodiment, the battery 1 is heated so that gas is generated inside the battery 1 and the internal pressure of the battery raised, in a similar manner to a case where a battery 1 is subjected to initial charging and discharging. Thus the inspection of sealing properties of the battery is efficiently and reliably performed.

[0026] This embodiment is particularly effective for the inspection of sealing property of batteries which have been stored for a long period of time after initial charging and charging.

[0027] According to the battery sealing inspection method of the present invention, the battery is either subjected to initial charging or discharging, or heated, to raise the internal pressure thereof, prior to the inspection of its sealing properties. The battery is placed in a sealed vessel, which is evacuated to obtain a substantial difference between the pressure within the battery and its ambient pressure. The gas density within the sealed vessel is measured after a certain period of time, whereby gas escape from any location on the battery is detected in a reliable manner. With this method, even a slightest amount of gas leaking from anywhere on the battery causes changes in the gas density within the sealed vessel, and therefore gas leakage is detected accurately for a short time with good efficiency and high reliability.

Claims

1. A method of inspecting sealing properties of a battery, comprising the steps of:

charging and discharging the battery (1); placing the battery within a sealed vessel (3); evacuating the interior of the sealed vessel and maintaining a predetermined low pressure level for a period of time;

measuring density of a gas within the sealed

vessel, the gas being a gas generated within the battery; and

determining whether there is a gas leak from the battery by comparing the measured gas density with a preliminarily obtained reference value.

- A method of inspecting sealing properties of a battery according to claim 1, wherein the battery is heated before the density of the gas in the sealed vessel is measured.
- **3.** A method of inspecting sealing properties of a battery, comprising the steps of:

placing the battery (1) which has been filled with electrolyte and has been sealed inside a sealed vessel (3);

heating the battery;

evacuating the interior of the sealed vessel and maintaining a predetermined low pressure level for a period of time;

measuring density of a gas within the sealed vessel, the gas being a gas generated within the battery; and

determining whether there is a gas leak from the battery by comparing the measured gas density with a preliminarily obtained reference value.

- **4.** A method of inspecting sealing properties of a battery according to claim 3, wherein the battery is heated to a temperature between 45°C and 80°C.
- 5. A method of inspecting sealing properties of a battery according to claim 4, wherein the battery is heated to a temperature of $60^{\circ}\text{C} \pm 5^{\circ}\text{C}$.
- 6. A method of inspecting sealing properties of a battery according to any preceding claim, wherein the inspection is performed immediately after the battery has undergone initial charging and discharging.
 - 7. A method of inspecting sealing properties of a battery according to any one of the preceding claims, wherein the reference value is obtained by measuring density of the gas in an ambient atmosphere prior to evacuation of the sealed vessel.
 - 8. A method of inspecting sealing properties of a battery according to any one of the preceding claims, wherein the gas generated within the battery is hydrogen.
- 55 **9.** An apparatus for inspecting sealing properties of a battery, comprising:

a vessel (3) for housing therein a battery (1) to

45

be inspected, provided with a vacuum pump (9) so as to be evacuated; a hydrogen density sensor (11) connected to the vacuum pump; and means (10) for switchably connecting the vacuum pump with the hydrogen density sensor, the vacuum pump with atmosphere, and the hydrogen density sensor with atmosphere.

10. An apparatus for inspecting sealing properties of a 10 battery according to Claim 9 further comprising a heater provided within the vessel.

15

20

25

30

35

40

45

50

55





Fig. 2 Prior Art





EUROPEAN SEARCH REPORT

Application Number

EP 01 30 1511

	Citation of document with india		·	Delevision	A. 100/E/A
Category	Citation of document with indic of relevant passage		riate,	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)
A	US 3 793 876 A (OSWAL 26 February 1974 (197 * claims 1,2 *		1	-10	H01 M6/5 0 H01 M 10/ 4 2
A	US 4 097 803 A (FELDM 27 June 1978 (1978-06 * claims 1-10 *		1	-10 [^]	
D,A	PATENT ABSTRACTS OF J. vol. 016, no. 189 (P-8 May 1992 (1992-05-0. JP 04 025738 A (MAT CO LTD), 29 January 1 * abstract *	1348), 8) SUSHITA ELEC	TRIC IND	-10	
					TECHNICAL FIELDS SEARCHED (Int.Cl.7)
					H01M
	The present search report has been				
	THE HAGUE	Date of completi		Bat	Examiner tistig, M
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background		E: D L:	T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons		
O : non-	-written disclosure mediate document	****	member of the same		

7

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 01 30 1511

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report			Publication date		Patent family member(s)	Publication date
US	3793876	Α	26-02-1974	BE	803403 A	03-12-19
				CA	984930 A	02-03-19
				DE	2339489 A	07-03-19
				FR	2195856 A	08-03-19
				IT	993723 B	30-09-19
				JP	49046786 A	04-05-19
				LU	68196 A	16-10-19
				NL	7311056 A	12-02-19
US	4097803	Α	27-06-1978	CA	1044325 A	12-12-19
JP	04025738	Α	29-01-1992	JP	3021545 B	15-03-20

FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82