

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 167 397 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

02.01.2002 Bulletin 2002/01

(51) Int Cl.7: **C08F 16/12, C08F 290/06**

// C08F299:02

(21) Application number: **00907985.6**

(86) International application number:

PCT/JP00/01453

(22) Date of filing: **10.03.2000**

(87) International publication number:

WO 00/53647 (14.09.2000 Gazette 2000/37)

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

(30) Priority: **11.03.1999 JP 6457799**

(71) Applicant: **Daikin Industries, Ltd.
Osaka-shi, Osaka 530-8323 (JP)**

(72) Inventors:

- **MORITA, Shigeru Yodogawa Works
Settsu-shi, Osaka 566-8585 (JP)**

- **SAKASHITA, Hirotoishi Yodogawa Works
Settsu-shi, Osaka 566-8585 (JP)**

- **ARAKI, Takayuki Yodogawa Works
Settsu-shi, Osaka 566-8585 (JP)**


- **SHIMIZU, Tetsuo Yodogawa Works
Settsu-shi, Osaka 566-8585 (JP)**

(74) Representative: **HOFFMANN - EITLE**

**Patent- und Rechtsanwälte Arabellastrasse 4
81925 München (DE)**

(54) **FLUORINATED ALLYL ETHER POLYMER**

(57) A fluorine-containing allyl ether polymer having a number average molecular weight of 1,000 to 1,000,000 and consisting of chains of at least one repeating unit of the formula:



wherein A is an organic group having 1 to 100 carbon atoms.

EP 1 167 397 A1

Description

FIELD OF THE INVENTION

[0001] The present invention relates to a fluorinated allyl ether polymer, in particular, a homo- or copolymer of 1,1,2-trifluoroallyl ether.

BACKGROUND ART

[0002] Hitherto, it is believed that hydrocarbon allyl compounds are hardly radically homopolymerized, and no homopolymer thereof having a high molecular weight can be obtained, and the reported molecular weight of the homopolymer is from about 300 to about 3,000 (see R. L. Shriner, L. Kelley ed. "Chemical Reviews" (USA), page 815, received by the National Diet Library (Japan) on December 13, 1962).

[0003] Thus, various improvements have been made on comonomers copolymerizable with the allyl compounds. However, no publications other than the above reference has reported the homo- and copolymerization of the allyl compounds.


DISCLOSURE OF THE INVENTION

[0004] An object of the present invention is to provide a polymer of a fluorinated allyl ether having a high molecular weight, which is prepared by radical homopolymerization.

[0005] This object is achieved by a fluorinated allyl ether polymer having a number average molecular weight of 1,000 to 1,000,000 and consisting of chains of at least one repeating unit of the formula:



wherein A is an organic group having 1 to 100 carbon atoms, and a fluorinated allyl ether polymer having a number average molecular weight of 1,000 to 1,000,000 and represented by the formula:



wherein X^1 is a hydrogen atom, a fluorine atom or a chlorine atom, X^2 is a hydrogen atom, a chlorine atom, a methyl group or a trifluoromethyl group, X^3 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group, x, y, z and w are the same or different and a number of 0 to 20 provided that the sum of x, y, z and w is from 1 to 20, and R is $-\text{COOH}$, $-\text{COOR}^1$ in which R^1 is a hydrocarbon group having 1 to 20 carbon atoms, $-\text{CH}_2\text{OH}$, $-\text{CONH}_2$, $-\text{CF}=\text{CF}_2$, a hydrocarbon group having 1 to 20 carbon atoms or a perfluoroalkyl group having 1 to 20 carbon atoms.

[0006] The present invention is based on the finding that the specific allyl ether structure has good homopolymerizability and provides a polymer having a high molecular weight. That is, a fluorine-containing allyl ether compound of the formula:




wherein A is an organic group having 1 to 100 carbon atoms has good homopolymerizability, in particular radical polymerizability, of the monomer of the formula (1a) due to the structure of the group: $\text{CH}_2=\text{CFCF}_2\text{O---}$ in the formula (1a), and provides a high molecular weight polymer. This is particularly different from other allyl compounds such as $\text{CF}_2=\text{CFCF}_2\text{OR}$, $\text{CF}_2=\text{CFCF}_2\text{R}$, etc. or vinyl ether compounds such as $\text{CF}_2=\text{CFOR}$, $\text{CH}_2=\text{CHOR}$, etc., which cannot be homopolymerized or which provide only low molecular weight products (oligomers), if they can be polymerized.

[0007] According to the present invention, insofar as the monomer has the group of the formula: $\text{CH}_2=\text{CFCF}_2\text{O---}$, it can be radically polymerized irrespective of the kind of the group A, and the polymer of the formula (1) can be obtained.

DETAILED DESCRIPTION OF THE INVENTION

[0008] The fluorinated allyl ether polymer of the present invention consists of the chains of the repeating unit of the formula (1), and includes, for example, a copolymer of the formula:



In this formula, the order of the repeating units may be random or block.

[0009] The above polymer may be copolymerized with less than 20 % by mole, preferably less than 10 % by mole of an ethylenically unsaturated compound copolymerizable with the above fluorinated allyl ether such as a fluorine-containing olefin.


[0010] The group A may be selected from any organic groups. In general, examples of the organic group include saturated or unsaturated aliphatic hydrocarbon groups having 1 to 50 carbon atoms, aromatic hydrocarbon groups having 4 to 30 carbon atoms, etc. At least one of hydrogen atoms of these hydrocarbon groups may be substituted with a fluorine atom.

[0011] Specific examples of the hydrocarbon groups include alkyl or fluoroalkyl groups having 1 to 50 carbon atoms, alkenyl or fluoroalkenyl groups having 2 to 50 carbon atoms, alkynyl or fluoroalkynyl groups having 2 to 50 carbon atoms, alkyl or fluoroalkyl groups having an ether bond and 1 to 60 carbon atoms, alkenyl or fluoroalkenyl groups having an ether bond and 2 to 60 carbon atoms, alkynyl or fluoroalkynyl groups having an ether bond and 2 to 60 carbon atoms, aryl or fluoroaryl groups having 4 to 30 carbon atoms, etc.

[0012] The hydrocarbon group may have a functional group. When the hydrocarbon group having the functional group is used, various functions are preferably imparted to the fluorinated allyl ether polymer obtained. A specific example of the repeating unit comprising the group A having the functional group is a repeating unit of the formula:



wherein A¹ is a divalent organic group having 1 to 60 carbon atoms, and Y¹ is -CH₂OH, -COOH, -COOR¹ in which R¹ is a hydrocarbon group having 1 to 20 carbon atoms,



in which R² and R³ are the same or different and a hydrogen atom or a hydrocarbon group having 1 to 20 carbon atoms, -O-CF=CF₂, or -OCO-CZ³=CZ¹Z² in which Z¹ and Z² are the same or different and a hydrogen atom or a fluorine atom, and Z³ is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group.

[0013] Besides the group -A¹-Y¹, examples of the group A having the functional group include an epoxy group, a glycidyl group, a cyano group (-CN), a sulfonic acid group (-SO₃H), -SO₃R' in which R' is a monovalent organic group, etc.


[0014] The group A¹ in the formula (2) maybe selected from divalent organic groups having 1 to 60 carbon atoms, preferably, divalent fluoroalkylene groups, divalent fluoroalkylene group having an ether bond, etc. These groups can impart various functions such as heat resistance, stain-proofing, non-tackiness, optical properties (e.g. low refractive index), chemical resistance, electrical insulation, etc. to the polymer.

[0015] Specific examples of the divalent fluoroalkylene group include -(CF₂)_m-(CH₂)_n-, -[CF₂CF(CF₃)]_m-(CH₂)_n-, -(CF₂CH₂)_m-(CH₂)_n-, and -[CF₂C(CF₃)₂]_m-(CH₂)_n- wherein m is a number of 1 to 20, and n is a number of 0 to 10.

[0016] Specific examples of the divalent fluoroalkylene group having the ether bond include -(CF₂CF₂O)_m-CF₂-, -(CF₂CF₂CF₂O)_m-CF₂CF₂-, -[CF(CF₃)CF₂O]_m-CF(CF₃)-, and -(CF₂O)_m-(CF₂)_k- wherein m and k are the same or different and a number of 1 to 20.


[0017] Besides the above fluoroalkylene groups and the like, the group A¹ in the formula (2) may be one of the

following hydrocarbon groups having 1 to 20 carbons: $-(CH_2)_m-$ wherein m is a number of 1 to 20, a cyclohexylene group, $-(Ph)_a-$ wherein Ph is a phenylene group and a is an integer of 1 to 3, $-(CH_2)_{m1}-(Ph)_a-(CH_2)_{m2}-$ in which Ph and a are the same as defined above, $m1$ is a number of 1 to 5 and $m2$ is a number of 0 to 5,




wherein m is a number of 1 to 20, $m3$ is a number of 0 to 10 and $m4$ is a number of 1 to 10, and the like.

[0018] One particularly preferable example of the repeating unit of the formula (1) is a repeating unit of the formula:



wherein X^1 is a hydrogen atom, a fluorine atom or a chlorine atom, X^2 is a hydrogen atom, a chlorine atom, a methyl group or a trifluoromethyl group, X^3 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group, x , y , z and w are the same or different and a number of 0 to 20 provided that the sum of x , y , z and w is from 1 to 20, and Y^2 is $-COOH$, $-COOR^4$ in which R^4 is a hydrocarbon group having 1 to 20 carbon atoms, $-CH_2OH$,



in which R^5 and R^6 are the same or different and a hydrogen atom or a hydrocarbon group having 1 to 20 carbon atoms, $-O-CF=CF_2$, or $-OCO-CZ^6=Z^4Z^5$ in which Z^4 and Z^5 are the same or different and a hydrogen atom or a fluorine atom, and Z^6 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group.

[0019] Preferable examples of the fluorinated allyl ether (3) include $CH_2=CFCF_2OCF(CF_3)CF_2OCF(CF_3)COOCH_3$, $CH_2=CFCF_2OCF(CF_3)CF_2OCF(CF_3)CF_2OCF(CF_3)COOCH_3$, $CH_2=CFCF_2OCF(CF_3)CF_2OCF(CF_3)COOH$, $CH_2=CFCF_2OCF(CF_3)CF_2OCF(CF_3)CF_2OCF(CF_3)COOH$, $CH_2=CFCF_2OCF(CF_3)CF_2OCF(CF_3)CH_2OH$, $CH_2=CFCF_2OCF(CF_3)CF_2OCF(CF_3)CF_2OCF(CF_3)CH_2OH$, etc.

[0020] The preparation method of the fluorinated allyl ether (3) of the present invention will be explained. To simplify the formulas, $-(CF_2O)_x-(CF_2CF_2O)_y-(CX^1_2CF_2CF_2O)_z-(CFX^2CF_2O)_w-CFX^3-$ will be represented by "Rf" in the following description.

[0021] The fluorinated allyl ether (3) of the present invention can be easily synthesized by defluoroiodination of a compound having a terminal iodine atom of the formula:



The fluoroiodination is preferably carried out in a solvent (e.g. dimethylformamide, dimethylsulfoxide, methanol, acetone, methyl ethyl ketone, ethyl acetate, etc.) in the presence of a catalyst (e.g. zinc, copper, etc.) at a temperature of -20 to 200°C , preferably 50 to 150°C .

[0022] The polymer consisting of the chains of the repeating unit of the formula (1) of the present invention may be prepared as follows:

[0023] The homopolymerization of the fluorinated allyl ether (1) of the present invention is carried out by a conventional radical polymerization method under conventional radical polymerization conditions. Preferably, the radical polymerization using a radical initiating source (e.g. a radical polymerization initiator, light, heat, etc.) is used, and the

polymerization mode may be bulk polymerization, solution polymerization, emulsion polymerization, suspension polymerization, etc.

[0024] The conditions employed in the radical polymerization are not limited and may include a temperature of 0 to 100°C and a pressure of atmospheric pressure, a reduced pressure down to about 760 mmHg or an elevated pressure up to about 100 kg/cm².

[0025] Alternatively, a functional group can be introduced in the polymer obtained by reacting the polymer with a compound having a functional group.

[0026] For example, when a polymer, which is obtained by polymerizing the fluorinated allyl ether (4) having the -CH₂OH group, is reacted with a compound of the formula: CZ¹Z²=CZ³COF wherein Z¹ and Z² are the same as defined above, a group of the formula: -CH₂OCO-CZ³=CZ¹Z² can be introduced in the polymer.

[0027] Alternatively, when a polymer obtained by polymerizing the fluorinated allyl ether (4) having the -OCF(CF₃)COOH group is treated with sodium hydroxide, etc. to change this group to an alkali salt and then heated to decarboxylate the polymer, the -OCF=CF₂ group can be introduced in the polymer.

[0028] The fluorinated allyl ether of the present invention can provide a high molecular weight product through the radical homopolymerization, and when the fluorinated allyl ether having the functional group is used, the polymer having the functional group in the molecule can be easily obtained. Such polymers have various properties depending on the functional groups contained therein, and they may be used as solvent-resistant polymers, water-soluble polymers, ion-exchange resins, reactive polymers, etc.

[0029] The present invention will be explained in detail by the following examples.

Example 1

[0030] CH₂=CF CF₂OCF(CF₃)CF₂OCF(CF₃)COOCH₃ (5 g) and a 8 wt. % solution of [H(CF₂CF₂)₃COO-]₂ (hereinafter referred to as "DHP") in trichlorotrifluoroethane (0.5 g) were charged in a glass vessel. When the internal atmosphere in the vessel was replaced with nitrogen and the mixture was stirred at room temperature for 24 hour, the viscosity of the mixture increased. Low boiling materials were distilled off from the reaction mixture under reduced pressure to obtain a colorless transparent polymer (4.67 g).

[0031] When a molecular weight was calculated on the assumption that the initiator efficiency was 1 (one), no chain transfer reaction took place, and the termination was only rebonding termination, it was 71,652. Hereinafter, the molecular weight calculated as above will be referred to as a "calculated molecular weight".

[0032] The polymer obtained was soluble in tetrahydrofuran (THF). The polymer was dissolved in THF, and its molecular weight was measured with GPC using polystyrene as a standard. A number average molecular weight was about 68,000. This number average molecular weight measured with GPC was in good agreement with the calculated molecular weight. Thus, in the following Examples, only calculated molecular weights are reported.

[0033] The polymer had Tg of -2°C and a refractive index of 1.3132.

[0034] Herein, Tg was measured with DSC (differential scanning calorimeter), and a refractive index was measured with an Abbe refractometer.

Example 2

[0035] CH₂=CF CF₂OCF(CF₃)CF₂OCF(CF₃)CF₂OCF(CF₃)CH₂OH was polymerized in the same manner as in Example 1, and a colorless transparent polymer (2.10 g) was obtained. It had a calculated molecular weight of 32,865, Tg of -4°C and a refractive index of 1.3416.

Example 3

[0036] CH₂=CF CF₂OCF(CF₃)CF₂OCF(CF₃)COOH was polymerized in the same manner as in Example 1, and a white polymer (4.77 g) was obtained. It had a calculated molecular weight of 74,651 and Tg of 13°C. This polymer was soluble in water, and pH of the aqueous solution (concentration: 1 wt. %) was about 2. The aqueous solution was foamable.

Example 4

[0037] Polymerization was carried out in the same manner as in Example 1 except that CH₂=CF CF₂OCF(CF₃)CF₂OCF(CF₃)CH₂OH (5.0 g) and DHP (0.51 g) were used, and a colorless transparent polymer (4.68 g) was obtained. This polymer was a hard solid at room temperature, and it had a calculated molecular weight of 80,730.

Example 5

[0038] Polymerization was carried out in the same manner as in Example 1 except that $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COOCH}_3$ (5.01 g) and DHP (0.53 g) were used, and a colorless transparent polymer (4.54 g) was obtained. This polymer was soft at room temperature, and it had a calculated molecular weight of 73,880.

Example 6

[0039] $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{CH}_2\text{OH}$ (Monomer A) (14. g), $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COOCH}_3$ (Monomer B) (6 g) and DHP (8.29 g; 8 wt. % solution in perfluorohexane) were mixed with HCFC-225 (a mixture of 1,1-dichloro-2,2,3,3,3-pentafluoropropane and 1,3-dichloro-1,2,2,3,3-pentafluoropropane) (5 g), and the mixture was stirred at 30°C for 24 hours.

[0040] The resulting solution was poured in petroleum benzine to precipitate the polymer formed.

[0041] The polymer precipitated was recovered, washed with petroleum benzine, and dried under reduced pressure to obtain a rubbery polymer (18 g).

[0042] According to NMR analysis, the polymer obtained was a copolymer containing Monomer A and Monomer B in a molar ratio of 81:19.

Example 7

[0043] The fluorine-containing copolymer obtained in Example 6 (13 g) was dissolved in HCFC-225 (30 g), and the pyridine (0.61 g) was added to the solution, followed by cooling to 0 to 5°C. Then, $\text{CH}_2=\text{CFCOF}$ (3.0 g) was gradually dropwise added to the solution while cooling with ice and stirring, and then the solution was stirred for additional 4 hours.

[0044] The polymer was precipitated washed and dried in the same manner as in Example 6 to obtain a rubbery polymer (10 g).

[0045] In the NMR chart of the obtained polymer, the absorption assigned to the OH groups disappeared, while the absorption assigned to $>\text{C}=\text{C}<$ appeared.

[0046] According to NMR analysis, in the polymer obtained, the molar ratio of the monomer having $-\text{COOCH}_3$ to the monomer having $-\text{OCO}-\text{CF}=\text{CH}_2$ was 80:20.

Claims

1. A fluorine-containing allyl ether polymer having a number average molecular weight of 1,000 to 1,000,000 and consisting of chains of at least one repeating unit of the formula:




wherein A is an organic group having 1 to 100 carbon atoms.

2. The fluorine-containing allyl ether polymer according to claim 1, wherein at least one of the repeating units is a repeating unit of the formula:




wherein A^1 is a divalent organic group having 1 to 60 carbon atoms, and Y^1 is $-\text{CH}_2\text{OH}$, $-\text{COOH}$, $-\text{COOR}^1$ in which R^1 is a hydrocarbon group having 1 to 20 carbon atoms,




in which R^2 and R^3 are the same or different and a hydrogen atom or a hydrocarbon group having 1 to 20 carbon atoms, $-\text{O}-\text{CF}=\text{CF}_2$, or $-\text{OCO}-\text{CZ}^3=\text{CZ}^1\text{Z}^2$ in which Z^1 and Z^2 are the same or different and a hydrogen atom or a fluorine atom, and Z^3 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group.

3. The fluorine-containing allyl ether polymer according to claim 2, wherein A^1 in the formula (2) is a fluoroalkylene group having 1 to 60 carbon atoms or a fluoroalkylene group having an ether bond and 1 to 60 carbon atoms.
4. The fluorine-containing allyl ether polymer according to claim 1, wherein at least one of the repeating units is a repeating unit of the formula:




wherein X^1 is a hydrogen atom, a fluorine atom or a chlorine atom, X^2 is a hydrogen atom, a chlorine atom, a methyl group or a trifluoromethyl group, X^3 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group, x , y , z and w are the same or different and a number of 0 to 20 provided that the sum of x , y , z and w is from 1 to 20, and Y^2 is $-\text{COOH}$, $-\text{COOR}^4$ in which R^4 is a hydrocarbon group having 1 to 20 carbon atoms, $-\text{CH}_2\text{OH}$,



in which R^5 and R^6 are the same or different and a hydrogen atom or a hydrocarbon group having 1 to 20 carbon atoms, $-\text{O}-\text{CF}=\text{CF}_2$, or $-\text{OCO}-\text{CZ}^6=\text{CZ}^4\text{Z}^5$ in which Z^4 and Z^5 are the same or different and a hydrogen atom or a fluorine atom, and Z^6 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group.

5. A fluorine-containing allyl ether polymer represented by the formula:



wherein X^1 is a hydrogen atom, a fluorine atom or a chlorine atom, X^2 is a hydrogen atom, a chlorine atom, a methyl group or a trifluoromethyl group, X^3 is a hydrogen atom, a fluorine atom, a chlorine atom or a trifluoromethyl group, x , y , z and w are the same or different and a number of 0 to 20 provided that the sum of x , y , z and w is from 1 to 20, and R is $-\text{COOH}$, $-\text{COOR}^1$ in which R^1 is a hydrocarbon group having 1 to 20 carbon atoms, $-\text{CH}_2\text{OH}$, $-\text{CONH}_2$, $-\text{CF}=\text{CF}_2$, a hydrocarbon group having 1 to 20 carbon atoms or a perfluoroalkyl group having 1 to 20 carbon atoms.

6. The fluorine-containing allyl ether polymer according to claim 5, which has a number average molecular weight of 1,000 to 1,000,000.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP00/01453

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl⁷ C08F16/12, C08F290/06, //C08F299/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl⁷ C08F16/12-16/32, C08F290/06, C08F299/02,
C08F116/12-116/20

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
CA (STN)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP, 10-237130, A (Daikin Industries, Ltd.), 08 September, 1998 (08.09.98), Claims 1 to 2, 4 to 5; Par. Nos. [0006] to [0008], [0014] to [0015] (Family: none)	1
X	WO, 95/33782, A1 (Daikin Industries, Ltd.), 14 December, 1995 (14.12.95), Claims; pages 9 to 38, pages 41 to 46, pages 96 to 137 & AU, 9525764, A & CN, 1129454, A & EP, 728776, A & US, 5670593, A	1-6
X	JP, 10-329282, A (Daikin Industries, Ltd.), 15 December, 1998 (15.12.98), Claims 1 to 3; Par. Nos. [0025], [0049] to [0053], [0058], [0069] (Family: none)	1-6
X	JP, 10-329281, A (Daikin Industries, Ltd.), 15 December, 1998 (15.12.98), Claims 1 to 3; Par. Nos. [0020], [0040] to [0041], [0050] to [0052], [0063] (Family: none)	1-6

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not
considered to be of particular relevance"E" earlier document but published on or after the international filing
date"L" document which may throw doubts on priority claim(s) or which is
cited to establish the publication date of another citation or other
special reason (as specified)"O" document referring to an oral disclosure, use, exhibition or other
means"P" document published prior to the international filing date but later
than the priority date claimed"T" later document published after the international filing date or
priority date and not in conflict with the application but cited to
understand the principle or theory underlying the invention"X" document of particular relevance; the claimed invention cannot be
considered novel or cannot be considered to involve an inventive
step when the document is taken alone"Y" document of particular relevance; the claimed invention cannot be
considered to involve an inventive step when the document is
combined with one or more other such documents, such
combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search
25 April, 2000 (25.04.00)Date of mailing of the international search report
16.05.00Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.