



(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

Note: Bibliography reflects the latest situation

- (15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see page(s) 5
- (48) Corrigendum issued on:
05.07.2006 Bulletin 2006/27
- (45) Date of publication and mention
of the grant of the patent:
08.03.2006 Bulletin 2006/10
- (21) Application number: **02786987.4**
- (22) Date of filing: **09.12.2002**
- (51) Int Cl.:
C04B 22/16 (2006.01) C04B 28/14 (2006.01)
- (86) International application number:
PCT/US2002/039362
- (87) International publication number:
WO 2003/053878 (03.07.2003 Gazette 2003/27)

(54) **GYPSUM-CONTAINING COMPOSITION HAVING ENHANCED RESISTANCE TO PERMANENT DEFORMATION**

GIPSZUSAMMENSETZUNG MIT VERBESSERTER DEFORMATIONSSTABILITÄT

COMPOSITION CONTENANT DU GYPSE, PRESENTANT UNE RESISTANCE AMELIOREE A LA DEFORMATION PERMANENTE

- | | |
|--|--|
| <p>(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SI SK TR</p> <p>(30) Priority: 11.12.2001 US 15066</p> <p>(43) Date of publication of application:
08.09.2004 Bulletin 2004/37</p> <p>(73) Proprietor: UNITED STATES GYPSUM COMPANY
Chicago,
Illinois 60606 (US)</p> <p>(72) Inventors:
• VEERAMASUNENI, Srinivas
Grayslake, IL 60030 (US)</p> | <ul style="list-style-type: none"> • YU, Qiang
Grayslake, IL 60030 (US) • FRANK, William, A.
Lindenhurst, IL 60046 (US) <p>(74) Representative: Pfenning, Meinig & Partner GbR
Patent- und Rechtsanwälte
Theresienhöhe 13
80339 München (DE)</p> <p>(56) References cited:
EP-A- 1 041 209 WO-A-00/06518
WO-A-99/08978 FR-A- 1 164 344</p> |
|--|--|

EP 1 453 772 B9

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

TECHNICAL FIELD OF THE INVENTION

5 **[0001]** The present invention relates generally to gypsum compositions. More particularly, the invention relates to set gypsum-containing compositions that exhibit enhanced strength, dimensional stability, and resistance to permanent deformation, and to methods, gypsum-containing compositions, and products related thereto.

BACKGROUND OF THE INVENTION

10 **[0002]** Set gypsum (calcium sulfate dihydrate) is a well-known material that is included commonly in many types of products. By way of example, set gypsum is a major component of end products created by the use of traditional plasters (e.g., plaster-surfaced internal building walls) and also in paper-faced gypsum boards employed in typical drywall construction of interior walls and ceilings of buildings. In addition, set gypsum is the major component of gypsum/cellulose fiber composite boards and products, and also is included in products that fill and smooth the joints between edges of gypsum boards. Also, many specialty materials, such as materials useful for modeling and mold-making, that are precisely machined, produce products that contain major amounts of set gypsum.

15 **[0003]** Typically, such gypsum-containing products are prepared by forming a mixture of calcined gypsum (calcium sulfate hemihydrate and/or calcium sulfate anhydrite) and water (and other components, as appropriate). The mixture is cast into a desired shape or onto a surface, and then allowed to harden to form set (i.e., rehydrated) gypsum by reaction of the calcined gypsum with the water to form a matrix of crystalline hydrated gypsum (calcium sulfate dihydrate). It is the desired hydration of the calcined gypsum that enables the formation of an interlocking matrix of set gypsum crystals, thus imparting strength to the gypsum structure in the gypsum-containing product. Mild heating is utilized to drive off the remaining free (i.e., unreacted) water to yield a dry product.

20 **[0004]** One problem with such gypsum-containing products is that they often are subject to permanent deformation (e.g., sag), especially under conditions of high humidity, temperature, or load. For example, the possibility of sag is particularly problematic where gypsum-containing boards and tiles are stored or employed in a manner in which they are positioned horizontally. In this respect, if the set gypsum matrix in these products is not sufficiently resistant to permanent deformation, the products may start to sag in areas between the points to which they are fastened, or supported by, an underlying structure. This can be unsightly and can cause difficulties during use of the products. Furthermore, in many applications, gypsum-containing products must be able to carry loads, e.g., insulation or condensation loads, without perceptible sag.

25 **[0005]** Another problem with such set gypsum-containing products is that dimensional stability can be compromised during their manufacture, processing, and commercial application. For example, in the preparation of set gypsum products, there is usually a significant amount of free (i.e., unreacted) water left in the matrix after the gypsum has set. Upon drying of the set gypsum in order to drive off the excess water, the interlocking set gypsum crystals in the matrix tend to move closer together as the water evaporates. In this respect, as the water leaves the crystal interstices of the gypsum matrix, the matrix tends to shrink from natural forces of the set gypsum that were resisting capillary pressure applied by the water on the gypsum crystals. As the amount of water in the aqueous calcined gypsum mixture increases, lack of dimensional stability becomes more of a problem.

30 **[0006]** Dimensional stability is also of concern even after the final dried product is realized, especially under conditions of changing temperature and humidity where set gypsum is susceptible to, for example, expansion and shrinkage. For example, moisture taken up in crystal interstices of a gypsum matrix of a gypsum board or tile exposed to high humidity and temperature can aggravate a sagging problem by causing the humidified board to expand.

35 **[0007]** If such dimensional instability could be avoided or minimized, various benefits would result. For example, existing gypsum board production methods would yield more product if the boards did not shrink during drying, and gypsum-containing products desired to be relied upon to hold a precise shape and dimensional proportions (e.g., for use in modeling and mold making) would serve their purposes better.

40 **[0008]** International Publication No. WO 99/08979 describes the use of polyphosphates as an enhancing material to achieve the goals of resistance to permanent deformation (e.g., sag) and enhanced dimensional stability. According to WO 99/08979, polyphosphates in general produce the benefits of resistance to permanent deformation and enhanced dimensional stability whether the polyphosphates are used to treat a calcium sulfate material before it rehydrates to form set gypsum (i.e., a "pre-set treatment") or to treat an already-set gypsum (i.e., a "post-set treatment"). In many situations, carrying out a post-set treatment is more complicated and difficult to achieve than a pre-set treatment because, for example, once the set gypsum is in place, it can be difficult to absorb the enhancing material into the set gypsum or to contact the set gypsum with the enhancing material (e.g., where the set gypsum is covered with paper). Thus, it generally is more desirable to impart resistance to permanent deformation and enhanced dimensional stability by way of a pre-set treatment of a calcium sulfate material. However, almost all of the polyphosphates described in WO 99/08979 have

45
50
55

a negative effect on the strength of the resulting set gypsum-containing product when used in a pre-set treatment.

[0009] Thus, there is a continuing need to impart resistance to permanent deformation and enhanced dimensional stability in a pre-set treatment while maintaining or, preferably, even increasing the strength (e.g., compressive strength) of the resulting set gypsum-containing product. Of the polyphosphate enhancing materials disclosed in WO 99/08979, only the trimetaphosphate compounds were found to actually increase strength upon addition in a pre-set treatment. It would be desirable to identify alternative enhancing materials for achieving resistance to permanent deformation and enhanced dimensional stability in a pre-set treatment of a calcium sulfate material while maintaining or, preferably, even increasing the strength of the resultant set gypsum product so as to afford flexibility in manufacture and in choosing raw materials.

[0010] Accordingly, it will be appreciated from the foregoing that there is a need in the art for an alternative pre-set treatment of a calcium sulfate material for increasing resistance to permanent deformation (e.g., sag) and dimensional stability while maintaining or, preferably, even increasing the strength of the resultant set gypsum product. The invention satisfies this need. These and other advantages of the present invention, as well as additional inventive features, will be apparent from the description of the invention provided herein.

BRIEF SUMMARY OF THE INVENTION

[0011] The present invention provides a composition comprising a calcium sulfate material, a set gypsum-containing product, and a method for producing a set gypsum-containing product having increased resistance to permanent deformation, while maintaining or increasing strength.

[0012] In accordance with the present invention, it has been found that the inclusion of 0.004 to 2.0 percent by weight of a tetrametaphosphate compound (e.g., salt or ion amount based on the weight of the calcium sulfate material) in a pre-set treatment of a calcium sulfate material enhances the resistance to permanent deformation (e.g., sag) while maintaining or, preferably, increasing compressive strength of the composition. Furthermore, it is expected that the addition of the tetrametaphosphate in a pre-set treatment will enhance the dimensional stability of the resulting set gypsum-containing product. It is to be noted that, although the singular is utilized for convenience to describe certain terms such as the tetrametaphosphate compound and the calcium sulfate material, it will be understood that singular terms such as "a," "an," and "the" are meant to cover both the singular and the plural (e.g., tetrametaphosphate compounds, calcium sulfate materials, or the like), unless otherwise indicated herein or clearly contradicted by context.

[0013] Thus, in one aspect, the present invention provides a composition comprising a mixture of a calcium sulfate material, water, and a tetrametaphosphate compound. As used herein, the term "calcium sulfate material" refers to calcium sulfate anhydrite, calcium sulfate hemihydrate, ions of calcium and sulfate, or mixtures of any of the foregoing, but is not meant to refer to calcium sulfate dihydrate (i.e., set gypsum). In some embodiments, an accelerator for increasing the rate of the hydration of the calcium sulfate material to produce calcium sulfate dihydrate (i.e., set gypsum) optionally is included in the composition, for example, when the composition is used to prepare a board. Some embodiments optionally also can include pregelatinized starch, aqueous foam, and/or other ingredients as will be appreciated readily by one of ordinary skill in the art.

[0014] The composition of the invention is useful to produce set gypsum-containing products that exhibit sag resistance while maintaining or increasing compressive strength. Desirably, when the composition is cast to form a $\frac{1}{2}$ inch (1.27 cm) board comprising an interlocking matrix of set gypsum, the board has a sag resistance, as determined according to ASTM C473-95, of less than about 0.1 inch (0.254 cm) per two-foot (0.6096 m) length of said board. Also, when the composition is used to prepare a product comprising an interlocking matrix of set gypsum, the product has at least as much strength, and preferably has more strength, than it would have if the tetrametaphosphate compound had not been included in the mixture.

[0015] ASTM C473-95 recites a method for sag resistance (e.g., humidified deflection) of gypsum panel products (e.g., gypsum boards). In accordance with the method set forth in ASTM C473-95, a one foot (0.3048 m) by two feet (0.6096 m) section of a gypsum board is supported on parallel and level bearing edges, said bearing edges being 23 inches (58.4 cm) apart and having 3.2 mm radii, with the resulting assembly enclosed within a cabinet maintained at a temperature of $32 \pm 1.7^\circ \text{C}$ and a relative humidity of $90 \pm 3\%$. After 48 h, the distance between the center of the top surface of the gypsum board from an imaginary horizontal plane extending between the top edges of the ends of the board is measured. In the context of < the present invention, sag resistance refers to the magnitude of the aforementioned distance.

[0016] In some embodiments, the composition comprises set gypsum and host particles such that at least a portion of the set gypsum is positioned in and about accessible voids in the host particles. As a result, in another aspect, the present invention provides a composition comprising a mixture of the host particles having the accessible voids therein; calcium sulfate hemihydrate, at least a portion of which is in the form of crystals in and about the voids of the host particles; and a tetrametaphosphate compound. When the composition is cast to form a $\frac{1}{2}$ inch (1.27 cm) board comprising an interlocking matrix of set gypsum, the board preferably has a sag resistance, as determined according to ASTM

C473-95, of less than about 0.1 inch (0.254 cm) per two-foot (0.6096 m) length of the board, and the board has at least as much strength, and preferably has more strength, than it would have if the tetrametaphosphate compound had not been included in the mixture.

5 [0017] In some embodiments of the invention, the composition is mixed with water to produce a machinable set gypsum-containing product or a joint compound. The machinable set gypsum-containing product comprises a mixture of a starch, particles of a water-redispersible polymer, calcium sulfate hemihydrate, and a tetrametaphosphate compound. The joint compound is useful for finishing joints between edges of gypsum boards, and comprises a mixture of a binder, a thickener, a non-leveling agent, calcium sulfate hemihydrate, and a tetrametaphosphate compound.

10 [0018] Some embodiments of the inventive composition are useful for producing an acoustical tile. Such compositions comprise a mixture of a calcium sulfate material, water, and a tetrametaphosphate compound, as well as one or more of a gelatinized starch, a mineral wool, expanded perlite particles, and/or a fiber reinforcing agent. By way of example, in some embodiments, the composition comprises a mixture of a gelatinized starch, a mineral wool, a calcium sulfate material, water, and a tetrametaphosphate compound. As another example, in some embodiments, the composition comprises a mixture of a gelatinized starch, expanded perlite particles, a fiber reinforcing agent, a calcium sulfate material, water, and a tetrametaphosphate compound.

15 [0019] In another aspect of the invention, a method for producing a set gypsum-containing product having increased resistance to permanent deformation is provided. The method comprises forming a mixture of a calcium sulfate material, water, and a tetrametaphosphate compound. The mixture is maintained under conditions sufficient for the calcium sulfate material to form an interlocking matrix of set gypsum material. The tetrametaphosphate compound is included in the mixture in an amount such that the set gypsum-containing product has greater resistance to permanent deformation than it would have if the tetrametaphosphate compound had not been included in the mixture.

20 [0020] In yet another aspect of the invention, a method for producing a set gypsum-containing product having enhanced strength is provided. The method comprises forming a mixture of a calcium sulfate material, water, and a tetrametaphosphate compound. The mixture is maintained under conditions sufficient for the calcium sulfate material to form an interlocking matrix of set gypsum material. The tetrametaphosphate compound is included in the mixture in an amount such that the set gypsum-containing product has greater strength than it would have if the tetrametaphosphate compound had not been included in the mixture.

25 [0021] In still another aspect, the present invention provides a set gypsum product. In some embodiments, the set gypsum product is a gypsum board. For example, the present invention provides gypsum board comprising an interlocking matrix of set gypsum formed from, i.e., using, at least calcined gypsum, water and a tetrametaphosphate compound. Preferably, the gypsum board has a sag resistance, as determined according to ASTM C473-95, of less than about 0.1 inch (0,254 cm) per two-foot (0,6096 mm) length of the board, while maintaining or increasing strength.

30 [0022] In some embodiments, the set gypsum product is a gypsum board comprising a core of material sandwiched between cover sheets. The core comprises an interlocking matrix of set gypsum. Preferably, the board is prepared by a method comprising forming or depositing a mixture between the cover sheets, wherein the mixture comprises a calcium sulfate material, water, and a tetrametaphosphate compound. The mixture is maintained under conditions sufficient for the calcium sulfate material to form the interlocking matrix of set gypsum. The tetrametaphosphate compound is included in the mixture in an amount such that the gypsum board has a sag resistance, as determined according to ASTM C473-95, of less than about 0.1 inch (0,254 cm) per two foot (0,6096 cm) length of the board, while maintaining or increasing strength.

35 [0023] The invention may best be understood in the following detailed description of the preferred embodiments.


DESCRIPTION OF THE PREFERRED EMBODIMENTS

40 [0024] The present invention provides tetrametaphosphate in a pre-set treatment of a calcium sulfate material. The invention can be practiced employing compositions and methods similar to those employed in the prior art to prepare various set gypsum-containing products. The essential difference in the compositions and methods of some preferred embodiments of this invention from compositions and methods employed in the prior art to prepare various set gypsum-containing products is that a tetrametaphosphate compound (such as a tetrametaphosphate salt) is included. It will be appreciated by those skilled in the art that while a tetrametaphosphate compound can be used to form the mixture described herein, the tetrametaphosphate may exist as the ion in the mixture, particularly with water present and prior to setting and drying. Thus, the term "tetrametaphosphate compound" is intended to mean such a compound itself or the tetrametaphosphate ion. Because the invention is particularly useful in a pre-set treatment, in practicing the methods of the invention, rehydration of calcined gypsum to form an interlocking matrix of set gypsum takes place in the presence of tetrametaphosphate ion and thereby produces the benefits of the invention. In other respects the compositions and methods of the invention can be the same as the corresponding compositions and methods of the prior art.


45 [0025] Tetrametaphosphate compounds, also referred to as cyclotetraphosphates, that are included in compositions of the invention can comprise any water-soluble tetrametaphosphate compound or ion that does not adversely interact with other components of the composition. Some examples of useful salts are sodium tetrametaphosphate, potassium

tetrametaphosphate, ammonium tetrametaphosphate, lithium tetrametaphosphate, aluminum tetrametaphosphate, and mixed salts thereof, among others. Sodium tetrametaphosphate is preferred.

[0026] The tetrametaphosphate compound can be prepared in any suitable manner. For example, in one embodiment, the tetrametaphosphate compound can be in the form of sodium tetrametaphosphate, which may be synthesized by



[0027] The acid is then reacted with sodium hydroxide to form the sodium tetrametaphosphate, which is a tetrahydrate, as follows:



Inasmuch as the sodium tetrametaphosphate is in a highly soluble form, a salt or solvent can be added to the solution product to precipitate sodium tetrametaphosphate. For example, ethanol or sodium chloride can be added for this purpose. In a similar way, tetrametaphosphate salts of potassium, lithium, aluminum, and the like, can be prepared. The synthesis of cyclotetraphosphates is described, for example, in Bell, R. N.; Audrieth, L. F.; Hill, O. F. *Industrial and Engineering Chemistry* 1952, 44, 568.

[0028] While not wishing to be bound by any particular theory, it is hypothesized that addition of the tetrametaphosphate compound in a pre-set treatment enhances the strength at each contact point in the crystalline gypsum structure after setting takes place. As a result, it is believed that the tetrametaphosphate compound imparts enhanced strength and dimensional stability to the set gypsum-containing product. With respect to dimensional stability, it is expected and preferred that the resulting gypsum product, e.g., board, exhibits a drying shrinkage of less than about 0.06 inch (0.1524 cm) per four foot (1.2192 m) width and less than about 0.30 inch (0.762 cm) per twelve foot (3.6576 m) length and/or that the gypsum product exhibits a drying shrinkage of less than about 0.13% across its width and less than about 0.26% across its length, wherein length and width are measured according to ASTM C473-95. As will be appreciated by one of ordinary skill in the art, drying shrinkage is the shrinkage that might occur when excess water is dried off after completion of setting (hydration). This is done, for example, by measuring length and width of board (e.g., in accordance with the ASTM C473-95) after completion of setting hydration but before drying off excess water (for example, in a kiln) and then measuring again after drying, and then calculating the difference.

[0029] ASTM C473-95 recites methods for evaluating the width and length of specimens of gypsum panel products (e.g., gypsum boards) having two edges defining a width and two ends defining a length. In accordance with ASTM C473-95, the width of a gypsum board is determined by placing a measuring device perpendicular to the edges of the gypsum board and measuring the distance between extremities of the edges. The width of an individual gypsum board is the maximum of two measurements taken not less than 48 inches (122 cm) apart and about 6 inches (15.2 cm) away from both ends of the gypsum board. The length of a gypsum board is determined by placing a measuring device parallel to the edges of the gypsum board and measuring the distance between extremities of the ends. The length of a gypsum board is the maximum of two measurements taken about 3 inches (7.6 cm) away from both edges of the gypsum board.

[0030] In preferred embodiments, a tetrametaphosphate salt is dissolved in an aqueous mixture of calcined gypsum in concentration of from about 0.004% to about 2.0% by weight, based on the weight of the calcined gypsum, to yield tetrametaphosphate ion in the mixture. A preferred concentration of tetrametaphosphate compound is from about 0.04% to about 0.16%. A more preferred concentration is about 0.08%. If desired, for easier storage and delivery in the practice of some embodiments of the invention, the tetrametaphosphate salt can be pre dissolved in water and inserted into the mixture in the form of an aqueous solution.

[0031] In accordance with a preferred embodiment of the invention, the tetrametaphosphate ion need only be present in the aqueous mixture of calcined gypsum during the hydration of the calcined gypsum to form set gypsum. Therefore, it is usually most convenient and thus preferred to add the tetrametaphosphate compound into the mixture at an early stage.

[0032] It is also sufficient to add the tetrametaphosphate compound to a mixture of calcined gypsum and water at a somewhat later stage. For example, in preparing typical gypsum boards, water and calcined gypsum are brought together in a mixing apparatus, are mixed thoroughly, and then are usually deposited onto a cover sheet on a moving belt, and a second cover sheet is placed over the deposited mixture before the major part of the rehydration of calcined gypsum to form set gypsum occurs. While it is most convenient to add the tetrametaphosphate compound to the gypsum-containing mix during its preparation in the mixing apparatus, it is also sufficient to add the tetrametaphosphate ion at a later stage, e.g., by spraying an aqueous solution of the ion onto the deposited aqueous mixture of calcined gypsum just before the second cover sheet is placed over the deposit, so that the aqueous tetrametaphosphate ion solution will soak into the deposited mixture and be present when the bulk of the hydration to form set gypsum occurs.

[0033] Other alternative methods of adding the tetrametaphosphate compound into the mixture will be apparent to those of ordinary skill in the art and are of course considered to be within the scope of the present invention. For example,

it may be possible to pre-coat one or both of the cover sheets with a tetrametaphosphate salt or salt solution, so that the salt will dissolve and cause tetrametaphosphate ion to migrate through the mixture when the deposit of aqueous mixture of calcined gypsum comes into contact with the cover sheet. Another alternative is to mix a tetrametaphosphate salt with raw gypsum even before it is heated to form calcined gypsum, so that the salt is already present when the calcined gypsum is mixed with water to cause rehydration.

[0034] The calcined gypsum employed in the invention can be in the form of concentrations typically found useful in the corresponding embodiments of the prior art. The calcined gypsum used in the practice of the invention can be alpha calcium sulfate hemihydrate, beta calcium sulfate hemihydrate, water-soluble calcium sulfate anhydrite, or mixtures of any and all thereof, from natural or synthetic sources. In some preferred embodiments alpha calcium sulfate hemihydrate is employed for its yield of set gypsum having relatively high strength. In other preferred embodiments beta calcium sulfate hemihydrate or a mixture of beta calcium sulfate hemihydrate and water-soluble calcium sulfate anhydrite are employed.

[0035] Other conventional additives can be employed in the practice of the invention in customary amounts to impart desirable properties and to facilitate manufacturing such as, for example, aqueous foam, set accelerators, set retarders, recalcination inhibitors, binders, adhesives, dispersing aids, leveling or nonleveling agents, thickeners, bactericides, fungicides, pH adjusters, colorants, reinforcing materials, fire retardants, water repellants, fillers and mixtures thereof.

[0036] In some preferred inventive embodiments wherein the method and composition are for preparing gypsum board comprising a core of set gypsum-containing material sandwiched between cover sheets, tetrametaphosphate compound is employed in the concentrations and manner described above. In other respects, the composition and method can be practiced with the same components and in the same manner as the corresponding compositions and methods for preparing gypsum board of the prior art, for example, as described in US Patents 4,009,062 and 2,985,219. Boards produced using this preferred inventive composition and method exhibit improved strength, resistance to permanent deformation, and dimensional stability.

[0037] In preferred methods and compositions for preparing gypsum board, wherein the surface sheets of the board comprise paper, a pregelatinized starch is also employed to avoid the otherwise slightly increased risk of paper delamination under conditions of extreme-moisture. Pregelatinizing of raw starch is achieved by cooking in water at temperatures of at least 185° F (85°C) or by other well known methods.

[0038] Some examples of readily available pregelatinized starches that serve the purposes of the present invention are (identified by their commercial names): PCF1000 starch, available from Lauhoff Grain Co.; and AMERIKOR 818 and HQM PREGEL starches, both available from Archer Daniels Midland Co.

[0039] To be used in a preferred practice of the invention, the pregelatinized starch is included in the aqueous mixture of calcined - gypsum at a concentration of from about 0.08 to about 0.5 percent by weight, based on the weight of the calcined gypsum. A preferred concentration of pregelatinized starch is from about 0.16 to about 0.4 percent. A more preferred concentration is about 0.3 percent. If the corresponding embodiment of the prior art also contains a starch that has not been pregelatinized (as many do), the pregelatinized starch in the inventive embodiment can also serve to replace all or a portion of the amount of that prior art starch normally employed.

[0040] In embodiments of the invention that employ a foaming agent to yield voids in the set gypsum-containing product to provide lighter weight, any of the conventional foaming agent known to be useful in preparing foamed set gypsum products can be employed. Many such foaming agents are well known and readily available commercially, e.g., from GEO Specialty Chemicals in Ambler, Pennsylvania. For further descriptions of useful foaming agent, see, for example: U.S. patents 4,676,835; 5,158,612; 5,240,639 and 5,643,510; and PCT International Application Publication WO 95/16515, published June 22, 1995.

[0041] In many cases it will be preferred to form relatively large voids in the gypsum product, in order to help maintain its strength. This can be accomplished by employing a foaming agent that generates foam that is relatively unstable when in contact with calcined gypsum slurry. Preferably, this is accomplished by blending a major amount of foaming agent known to generate relatively unstable foam, with a minor amount of foaming agent known to generate relatively stable foam.


[0042] Such a foaming agent mixture can be pre-blended "off-line", i.e., separate from the process of preparing foamed gypsum product. However, it is preferable to blend such foaming agents concurrently and continuously, as an integral "on-line" part of the process. This can be accomplished, for example, by pumping separate streams of the different foaming agents and bringing the streams together at, or just prior to, the foam generator that is employed to generate the stream of aqueous foam which is then inserted into and mixed with the calcined gypsum slurry. By blending in this manner, the ratio of foaming agents in the blend can be simply and efficiently adjusted (for example, by changing the flow rate of one or both of the separate streams) to achieve the desired void characteristics in the foamed set gypsum product. Such adjustment will be made in response to an examination of the final product to determine whether such adjustment is needed. Further description of such "on-line" blending and adjusting can be found in U.S. Patents 5,643,510 and 5,683,635.

[0043] An example of one type of foaming agent, useful to generate unstable foams, has the formula (Q)



wherein R is an alkyl group containing from 2 to 20 carbon atoms, and M is a cation. Preferably; R is an alkyl group containing from 8 to 12 carbon atoms.


[0044] An example of one type of foaming agent, useful to generate stable foams, has the formula (7)



wherein X is a number from 2 to 20, Y is a number from 0 to 10 and is greater than 0 in at least 50 weight percent of the foaming agent, and M is a cation.

[0045] In some preferred embodiments of the invention, foaming agents having the formulas (Q) and (J) above are blended together, such that the formula (Q) foaming agent and the portion of the formula (J) foaming agent wherein Y is 0, together constitute from 86 to 99 weight percent of the resultant blend of foaming agents.

[0046] In some preferred embodiments of the invention, the aqueous foam has been generated from a pre-blended foaming agent having the formula (Z)



wherein X is a number from 2 to 20, Y is a number from 0 to 10 and is 0 in at least 50 weight percent of the foaming agent, and M is a cation. Preferably, Y is 0 in from 86 to 99 weight percent of the formula (Z) foaming agent.

[0047] In some preferred inventive embodiments wherein the method and composition are for preparing a composite board comprising set gypsum and particles of a reinforcing material, tetrametaphosphate compound is employed in the concentrations and manner described above. It is particularly preferred that the composite product comprise set gypsum and host particles, at least a portion of the set gypsum being positioned in and about accessible voids in the host particles. The inventive composition comprises a mixture of: host particles having accessible voids therein; calcined gypsum, at least a portion of which is in the form of crystals in and about the voids in the host particles; and a water-soluble tetrametaphosphate salt. The composition can be mixed with water to produce an inventive mixture of water, host particles having accessible voids therein, calcined gypsum (at least a portion of which is in the form of crystals in and about the voids in the host particles), and tetrametaphosphate ion. The method comprises forming such a mixture, depositing it on a surface or into a mold, and allowing it to set and dry. In other respects, the composition and method can be practiced with the same components and in the same manner as the corresponding compositions and methods for preparing composite board of the prior art, for example, as described in U.S. Patent 5,320,677.

[0048] In some preferred embodiments wherein the method and composition are for preparing a machinable material, tetrametaphosphate compound is employed in the concentrations and manner described above. In some preferred forms of such embodiments the composition comprises a mixture of calcined gypsum, a water-soluble tetrametaphosphate salt, a starch, and particles of a water-redispersible polymer. The composition can be mixed with water to produce an inventive mixture of water, calcined gypsum, tetrametaphosphate ion, starch, and particles of water-redispersible polymer. The method comprises forming such a mixture, depositing it on a surface or into a mold, and allowing it to set and dry.

[0049] In respect to aspects other than the inclusion of tetrametaphosphate salts and ions, the composition and method can be practiced with the same components and in the same manner as the corresponding compositions and methods for preparing machinable plaster material of the prior art, for example, as described in U.S. Patent 5,534,059.

[0050] In some preferred inventive embodiments wherein the method and composition are for producing a material employed to finish a joint between edges of gypsum boards, tetrametaphosphate salt or ion is employed in the concentrations described above. In respect to aspects other than the inclusion of tetrametaphosphate salts and ions, the composition and method can be practiced with the same components and in the same manner as the corresponding compositions and methods for producing a joint finishing material in the prior art, for example, as described in U.S. Patent 3,297,601.

[0051] In some preferred forms of such embodiments, the composition comprises a mixture of calcined gypsum, a water-soluble tetrametaphosphate salt, a binder, a thickener, and a non-leveling agent. The composition can be mixed with water to produce an inventive mixture of calcined gypsum, tetrametaphosphate ion, binder, thickener, and a non-leveling agent. The method comprising forming such a mixture, inserting it into a joint between edges of gypsum boards, and allowing it to set and dry.

[0052] In such preferred joint finishing embodiments the binder, thickener, and non-leveling agent are chosen from the components well known to those skilled in the joint compound art. For example, the binder can be a conventional latex binder, with poly(vinyl acetate) and poly(ethylene-co-vinyl acetate) being preferred and being included in a range from about 1 to about 15 percent by weight of the composition. An example of a useful thickener is a cellulosic thickener, e.g., ethylhydroxy, ethylcellulose, hydroxypropyl methylcellulose, methylhydroxypropyl cellulose, or hydroxyethyl cellu-

lose, included in a range of from about 0.1 to about 2 percent by weight of the composition. Examples of suitable non-leveling agents are attapulgite, sepiolite, bentonite, and montmorillonite clays, included in a range of from about 1 to about 10 percent by weight of the composition.

[0053] In some preferred inventive embodiments wherein the method and composition are for preparing an acoustical tile, tetrametaphosphate compound is included in the concentrations described above. In some preferred forms of such embodiments the composition comprises a mixture of water, calcined gypsum, tetrametaphosphate ion, a gelatinized starch, and mineral wool or a mixture of water, calcined gypsum, tetrametaphosphate ion, a gelatinized starch, expanded perlite particles, and a fiber reinforcing agent. The method comprises forming such a mixture, casting it into a tray, and allowing it to set and dry. In respect to aspects other than the inclusion of tetrametaphosphate compound, the composition and method can be practiced with the same components and in the same manner as the corresponding compositions and methods for producing an acoustical tile of the prior art, for example, as described in U.S. Patents 5,395,438 and 3,246,063.

[0054] The following examples are presented to further illustrate some preferred embodiments of the invention but should not be construed as any limitation on the scope of the invention. Unless otherwise indicated, concentrations of materials in compositions and mixtures are given in percent by weight based upon the weight of calcined gypsum present. The abbreviation "STMP" stands for sodium trimetaphosphate, and the abbreviation "SC" stands for sodium cyclotetraphosphate (i.e., sodium tetrametaphosphate).

EXAMPLE 1: RESISTANCE TO PERMANENT DEFORMATION (LABORATORY GYPSUM BOARD SAG RESISTANCE)

[0055] Samples of set gypsum-containing boards were prepared in a laboratory in accordance with the invention and compared, in regard to resistance to permanent deformation, with sample boards prepared using methods and compositions that do not include sodium tetrametaphosphate.

[0056] Samples were prepared by mixing in a 4 liter WARING blender for 10 seconds at low speed: 0.7 kg of beta calcium sulfate hemihydrate (United States Gypsum Company's Southard plant); 1.0 g of a set accelerator powder comprising fine ground particles of calcium sulfate dihydrate coated with sugar to maintain efficiency and heated as described in U.S. Patent 3,573,947 herein referred to as a "climate stabilized accelerator" (CSA); 1 liter of tap water; and 0 g additive (control samples), 0.7 g (0.1%) of sodium trimetaphosphate, or 0.7 g (0.1 %) of sodium tetrametaphosphate. The slurries thus formed were cast into trays to prepare flat gypsum board samples, each having dimensions of about 6×24×1/2 inch 15,24 × 60,96 × 1,27 cm. After the calcium sulfate hemihydrate set to form an interlocking matrix of set gypsum (calcium sulfate dihydrate), the boards were dried in a 112°F (44,44°C) oven to constant weight. The final measured weight of each board was recorded. No paper facing was applied to these boards, in order to avoid the effect of paper covers on the sag performance of the gypsum board.

[0057] Each dried board was then laid in a horizontal position upon two 1/2-inch (1,27 cm) wide supports whose length extended the full width of the board, with one support at each end of the board. The boards remained in this position for a specified period of time (in this example, 2 weeks) under continuous surrounding conditions of 90°F (32,22°C) temperature and 90 percent relative humidity. The deflection (i.e., extent of sag) of the board was then determined by measuring the distance (in inches) of the center of the top surface of the board from the imaginary horizontal plane extending between the top edges of the ends of the board. The resistance to permanent deformation of the set gypsum matrix of the board is considered to be inversely proportional to the extent of the sag of the board. Thus, the greater the extent of the sag is, the lower is the relative resistance to permanent deformation of the set gypsum matrix comprising the board. The test of resistance to permanent deformation, measured as "deflection," is reported in Table 1.

Table 1

Additive	Deflection
Control	3.25" (8,255 cm)
STMP	0.02" (0,0508 cm)
Tetrametaphosphate precipitated using NaCl	0.01" (0,0254 cm)
Tetrametaphosphate precipitated using ethanol	0.03" (0,0762 cm)

[0058] As seen in Table 1, the two samples that included a tetrametaphosphate in the calcined gypsum slurry in a pre-set treatment exhibited significantly less deflection (i.e., sag) as compared with the control and comparable with that of the sample in which STMP was employed.

EP 1 453 772 B9

EXAMPLE 2: RATE OF HYDRATION

[0059] This Example illustrates the rate of hydration of calcined gypsum to calcium sulfate dihydrate with the presence of sodium cyclotetraphosphate in a pre-set treatment, in accordance with the present invention, as compared with the rate of hydration where no phosphate additive (control) is present, and where sodium trimetaphosphate is present.

[0060] Four batches were prepared. For each batch, 1200 grams of calcium sulfate hemihydrate (United States Gypsum Company's Southard plant) was measured and set aside. Three grams of CSA was blended with the calcium sulfate hemihydrate powder until all were thoroughly dispersed. A 1320 ml quantity of water at 75°F (23.88°C) was measured and poured into a 4 liter Waring blender with high shear blades.

[0061] In one of the batches, 1.2 g (0.1 %) of sodium cyclotetraphosphate, precipitated with ethanol, was added. In the second batch, 1.2 g (0.1 %) of sodium cyclotetraphosphate, precipitated with NaCl, was added. In the third batch, 1.2 g (0.1 %) of sodium trimetaphosphate (STMP) was added. In the fourth batch, no phosphate was added.

[0062] In each batch, the powdered mixture was allowed to soak for 10 seconds, and then blended on medium speed for 30 seconds to form a slurry. In each batch, the slurry was poured into molds to permit casting of 9 cubes (2 inches per side).

[0063] The remaining slurry was poured into an insulated test cell. The temperature was measured every 5 seconds with a temperature probe and recorded. Since the setting reaction is exothermic, the extent of the reaction was measured by the temperature rise. The Time to 50% hydration was determined to be the time in minutes to reach the temperature half way between the minimum and maximum temperatures recorded during the test. The results are provided in Table 2, which indicates hydration times for each batch.

Table 2

Additive	Total Time to 50% Hydration	Total Time to 98% Hydration
SC/Ethanol	6.8	10.0
SC/NaCl	6.6	9.6
STMP	6.2	9.3
Control	6.6	9.5

[0064] As seen in Table 2, each of the additives had little effect on rate of hydration. Thus, advantageously, the addition of the tetrametaphosphate in a pre-set treatment enhances sag resistance and compressive strength, without significantly adversely affecting hydration time.

EXAMPLE 3-LABORATORY CUBE COMPRESSIVE STRENGTH

[0065] This Example compares the compressive strength of cubes prepared with the inclusion of a tetrametaphosphate compound in a pre-set treatment with that of cubes prepared with no phosphate additive and with cubes prepared with the inclusion of sodium trimetaphosphate in a pre-set treatment. The test procedure employed was in accordance with ASTM C472-93.

[0066] After the calcium sulfate hemihydrate for the 9 cubes from each batch described in Example 2 set to form calcium sulfate dihydrate, the cubes were removed from the molds and dried in a ventilated oven at 112°F (44.44°C) for at least 72 hours to achieve a constant weight. The dried cubes had a density of about 50 pounds per cubic foot (pcf) (0.80 g/cm³).

[0067] The compressive strength of each dry cube was measured on a SATEC testing machine. Results are reported in Table 3, below, as average values of nine samples tested for each batch. Strength values for control samples varied, because various sources of beta calcium sulfate hemihydrate and/or different batches of beta calcium sulfate hemihydrate were employed. Results in the table are reported in the form of the measured compressive strength in pounds per square-inch (psi) and percent change in strength as compared with a theoretical expected value (identified as "normal" in Table 3) for the density of the cube.

Table 3

Cube Series	Wet Weight (g)	Dry Weight (g)	% H ₂ O LOST	P.S.I. (kPa)	P.S.I. (kPa) NORMAL	% NORMAL
SC/Ethanol	187.7	105.1	44.0 %	1286.3 (8868.73)	903.2 (6227.34)	142 %

Table continued

Cube Series	Wet Weight (g)	Dry Weight (g)	% H ₂ O LOST	P.S.I. (kPa)	P.S.I. (kPa) NORMAL	% NORMAL
SC/NaCl	188.1	105.3	44.0 %	1310.4 (9034.89)	911.7 (6285.95)	144 %
STMP	187.6	105.1	44.0 %	1410.1 (9722.30)	903.9 (6232.17)	156 %
None	187.2	104.8	44.0 %	1236.0 (8521.92)	893.3 (6159.09)	138 %

[0068] As seen in Table 3, the compressive strength of the cubes prepared with sodium tetrametaphosphate or sodium trimetaphosphate in the pre-set treatment increased as compared with the control. Thus, Table 3 illustrates that the cube has greater strength than it would have if the sodium tetrametaphosphate compound had not been included in a pre-set treatment in accordance with the invention. If the concentration of the sodium tetrametaphosphate added to the mixture had been significantly lower (e.g. as low as 0.004 %), although no measurable strength increase might be seen, there still would be no strength increase.

[0069] While this invention has been described with an emphasis open preferred embodiments, it will be apparent to those of ordinary skill in the art that variations of the preferred embodiments may be used and that it is intended that the invention may be practiced otherwise than as specifically described herein. Accordingly, this invention includes all modifications encompassed within the scope of the invention as defined by the following claims.

Claims

1. A composition comprising a mixture of a calcium sulfate material, water, and a tetrametaphosphate compound, wherein the concentration of the tetrametaphosphate compound in the mixture is from 0.004 to 2.0 percent by weight, based on the weight of the calcium sulfate material.
2. The composition of claim 1, wherein the mixture further comprises a pregelatinized starch.
3. The composition of claim 1, wherein the mixture further comprises aqueous foam.
4. The composition of claim 3, wherein the mixture further comprises a pregelatinized starch.
5. The composition of claim 1, wherein the composition further comprises a mixture of host particles having accessible voids therein; and wherein at least a portion of the calcium sulfate material is in the form of crystals in and about the voids of the host particles.
6. Use of a composition comprising a mixture of a starch, particles of a water-redispersible polymer, calcium sulfate material, and a tetrametaphosphate compound for producing a machinable set gypsum-containing product when mixed with water, wherein the concentration of the tetrametaphosphate compound in the mixture is from 0.004 to 2.0 percent by weight, based on the weight of the calcium sulfate material.
7. Use of a composition comprising a mixture of a binder, a thickener, a non-leveling agent, calcium sulfate material, and a tetrametaphosphate compound for finishing joints between edges of gypsum boards when mixed with water, wherein the concentration of the tetrametaphosphate compound in the mixture is from 0.004 to 2.0 percent by weight, based on the weight of the calcium sulfate material.
8. Use of a composition comprising a mixture of a gelatinized starch, a calcium sulfate material, water, and a tetrametaphosphate compound and either (i) a mineral wool or (ii) expanded perlite particles and a fiber reinforcing agent for producing an acoustical tile, wherein the concentration of the tetrametaphosphate compound in the mixture is from 0.004 to 2.0 percent by weight, based on the weight of the calcium sulfate material.
9. Use of a composition comprising a mixture of a calcium sulfate material, water, an accelerator, and a tetrametaphosphate compound for producing a gypsum board, wherein the concentration of the tetrametaphosphate com-

pound in the mixture is from 0.004 to 2.0 percent by weight, based on the weight of the calcium sulfate material.

10. The use of claim 9, wherein the mixture further comprises a pregelatinized starch.

5 11. The use of claim 9, wherein the mixture further comprises an aqueous foam.

12. The use of claim 11, wherein the mixture further comprises a pregelatinized starch.

10 13. A method for producing a set gypsum-containing product having increased resistance to permanent deformation and/or enhanced strength, comprising:

forming a mixture of a calcium sulfate material, water, and from 0.004 to 2.0 percent by weight, based on the weight of the calcium sulfate material, of a tetrametaphosphate compound, and maintaining the mixture under conditions sufficient for the calcium sulfate material to form an interlocking matrix of set gypsum material.

14. The method of claim 13, wherein the concentration of the tetrametaphosphate compound in the mixture is from 0.04 to 0.16 percent by weight, based on the weight of the calcium sulfate material.

20 15. The method of claim 13, wherein the concentration of the tetrametaphosphate compound in the mixture is 0.08 percent by weight, based on the weight of the calcium sulfate material.

16. The method of claim 13, wherein the mixture further comprises a pregelatinized starch.

25 17. The method of claim 13, wherein the calcium sulfate material comprises one or more of: calcium sulfate anhydrite; calcium sulfate hemihydrate; or ions of calcium and sulfate.

18. The method of claim 17, wherein the calcium sulfate material comprises calcium sulfate hemihydrate.

30 19. A set gypsum-containing product prepared by the method of claim 13.

35 20. Gypsum board comprising an interlocking matrix of set gypsum formed from at least calcined gypsum, water and at least one tetrametaphosphate compound, said gypsum board having a sag resistance such that when a one foot (0.3048 m) by two feet (0.6096 m) section of said board is supported on parallel and level bearing edges, said bearing edges being 23 inches (58.4 cm) apart and having 3.2 mm radii, at a temperature of $32 \pm 1.7^\circ \text{C}$ and a relative humidity of $90 \pm 3\%$ for 48 h, the distance between the center of the top surface of said board from an imaginary horizontal plane extending between the top edges of the ends of the board is less than 0.1 inch (0.254 cm), wherein the concentration of the tetrametaphosphate compound in the mixture is from 0.004 to 2.0 percent by weight, based on the weight of the calcined gypsum.

40 21. The gypsum board of claim 20, wherein said set gypsum is in the form of a core material sandwiched between cover sheets.

45 22. The gypsum board of claim 21, wherein said cover sheets comprise paper.

23. The gypsum board of claim 20, wherein said tetrametaphosphate compound is selected from the group consisting of sodium tetrametaphosphate, lithium tetrametaphosphate, potassium tetrametaphosphate, ammonium tetrametaphosphate, aluminum tetrametaphosphate, and mixtures thereof.

50 24. The gypsum board of claim 20, wherein said tetrametaphosphate is sodium tetrametaphosphate.

25. The gypsum board of claim 20 having two edges defining a width and two ends defining a length, wherein said gypsum board has a drying shrinkage of less than 0.06 inch (0.1524 cm) per four foot (1.219 m) width and less than 0.30 inch (0.762 cm) per twelve foot (3.6576 m) length.

55 26. The gypsum board of claim 20 having two edges defining a width and two ends defining a length, wherein said gypsum board has a drying shrinkage of less than 0.13% across its width and less than 0.26% across its length.

27. The gypsum board of claim 20, wherein said gypsum board further comprises a pregelatinized starch.
28. The gypsum board of claim 27, wherein the amount of pregelatinized starch is from 0.08 to 0.5 percent by weight of the gypsum.
29. The gypsum board of claim 27, wherein the amount of pregelatinized starch is from 0.16 to 0.4 percent by weight of the gypsum.
30. The gypsum board of claim 27, wherein the amount of pregelatinized starch is 0.3 percent by weight of the gypsum.
31. The gypsum board of claim 20, wherein said set gypsum has voids uniformly distributed therein.
32. The gypsum board of claim 31, wherein said set gypsum is further formed from at least one foaming agent, having the formula (J):



wherein X is a number from 2 to 20, Y is a number from 0 to 10 and is 0 in at least 50 weight percent of the foaming agent or blend of foaming agents, and M is a cation.

33. The gypsum board of claim 32, wherein Y is 0 in from 86 to 99 weight percent of the foaming agent.
34. The gypsum board of claim 31, wherein the set gypsum is formed from at least calcined gypsum, water, at least one tetrametaphosphate compound, and a pregelatinized starch.

Revendications

1. Composition comprenant un mélange d'un matériau à base de sulfate de calcium, d'eau et d'un composé de tétramétaphosphate, dans laquelle la concentration du composé de tétramétaphosphate dans le mélange est de 0,004 à 2,0 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.
2. Composition selon la revendication 1, dans laquelle le mélange comprend en outre un amidon pré-gélatinisé.
3. Composition selon la revendication 1, dans laquelle le mélange comprend en outre une mousse aqueuse.
4. Composition selon la revendication 3, dans laquelle le mélange comprend en outre un amidon pré-gélatinisé.
5. Composition selon la revendication 1, dans laquelle la composition comprend en outre un mélange de particules hôtes contenant des vides accessibles; et dans laquelle au moins une partie du matériau à base de sulfate de calcium se présente sous la forme de cristaux dans et autour des vides des particules hôtes.
6. Utilisation d'une composition comprenant un mélange d'un amidon, de particules d'un polymère redispersable dans l'eau, de matériau à base de sulfate de calcium et d'un composé de tétramétaphosphate pour produire un produit contenant du gypse durci usinable lorsqu'il est mélangé à de l'eau, dans laquelle la concentration du composé de tétramétaphosphate dans le mélange est de 0,004 à 2,0 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.
7. Utilisation d'une composition comprenant un mélange d'un liant, d'un épaississant, d'un agent non nivelant, de matériau à base de sulfate de calcium et d'un composé de tétramétaphosphate pour joints de finition entre les bords de panneaux de gypse par mélange avec de l'eau, dans laquelle la concentration du composé de tétramétaphosphate dans le mélange est de 0,004 à 2,0 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.
8. Utilisation d'une composition comprenant un mélange d'un amidon gélatinisé, d'un matériau à base de sulfate de calcium, d'eau, d'un composé de tétramétaphosphate et (i) d'une laine minérale ou (ii) de particules de perlite expansées et d'un agent de renforcement fibreux pour produire une tuile acoustique, dans laquelle la concentration du composé de tétramétaphosphate dans le mélange est de 0,004 à 2,0 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.

EP 1 453 772 B9

9. Utilisation d'une composition comprenant un mélange d'un matériau à base de sulfate de calcium, d'eau, d'un accélérateur et d'un composé de tétramétaphosphate pour produire un panneau de plâtre, dans laquelle la concentration du composé de tétramétaphosphate dans le mélange est de 0,004 à 2,0 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.
- 5
10. Utilisation selon la revendication 9, dans laquelle le mélange comprend en outre un amidon pré-gélatinisé.
11. Utilisation selon la revendication 9, dans laquelle le mélange comprend en outre une mousse aqueuse.
- 10
12. Utilisation selon la revendication 11, dans laquelle le mélange comprend en outre un amidon pré-gélatinisé.
13. Procédé pour produire un produit contenant du gypse durci ayant une résistance accrue à la déformation permanente et/ou une résistance renforcée, comprenant :
- 15
- la formation d'un mélange d'un matériau à base de sulfate de calcium, d'eau et de 0,004 à 2,0 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium, d'un composé de tétramétaphosphate, et le maintien du mélange dans des conditions suffisantes pour que le matériau à base de sulfate de calcium forme une matrice interpénétrante de matériau de gypse durci.
- 20
14. Procédé selon la revendication 13, dans lequel la concentration du composé de tétramétaphosphate dans le mélange est de 0,04 à 0,16 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.
15. Procédé selon la revendication 13, dans lequel la concentration du composé de tétramétaphosphate dans le mélange est de 0,08 pour-cent en poids, par rapport au poids du matériau à base de sulfate de calcium.
- 25
16. Procédé selon la revendication 13, dans lequel le mélange comprend en outre un amidon pré-gélatinisé.
17. Procédé selon la revendication 13, dans lequel le matériau à base de sulfate de calcium comprend un ou plusieurs des éléments suivants : anhydrite de sulfate de calcium; hémihydrate de sulfate de calcium; ou des ions de calcium et de sulfate.
- 30
18. Procédé selon la revendication 17, dans lequel le matériau à base de sulfate de calcium comprend un hémihydrate de sulfate de calcium.
- 35
19. Produit contenant du gypse durci préparé par le procédé selon la revendication 13.
20. Panneau de plâtre comprenant une matrice interpénétrante de gypse durci formé au moins de gypse calciné, d'eau et d'au moins un composé de tétramétaphosphate, ledit panneau de plâtre ayant une résistance à l'affaissement de sorte que, lorsqu'une section de 0,3048 m (un pied) par 0,6096 m (deux pieds) dudit panneau est supportée sur des bords de support parallèles et de niveau, lesdits bords de support étant séparés l'un de l'autre de 58,4 cm (23
- 40
- pouces) et ayant des rayons de 3,2 mm, à une température de $32 \pm 1,7^\circ \text{C}$ et une humidité relative de $90 \pm 3\%$ pendant 48 h, la distance du centre de la surface supérieure dudit panneau d'un plan horizontal imaginaire s'étendant entre les bords supérieurs des extrémités du panneau soit inférieure à 0,254 cm (0,1 pouce), dans lequel la concentration du composé de tétramétaphosphate dans le mélange est de 0,004 à 2,0 pour-cent en poids, par rapport au poids du gypse calciné.
- 45
21. Panneau de plâtre selon la revendication 20, dans lequel ledit gypse durci se présente sous la forme d'un matériau formant âme pris en sandwich entre des feuilles de couverture.
- 50
22. Panneau de plâtre selon la revendication 21, dans lequel lesdites feuilles de couverture comprennent du papier.
23. Panneau de plâtre selon la revendication 20, dans lequel ledit composé de tétramétaphosphate est choisi dans le groupe constitué du tétramétaphosphate de sodium, du tétramétaphosphate de lithium, du tétramétaphosphate de potassium, du tétramétaphosphate d'ammonium, du tétramétaphosphate d'aluminium et de leurs mélanges.
- 55
24. Panneau de plâtre selon la revendication 20, dans lequel ledit tétramétaphosphate est le tétramétaphosphate de sodium.

EP 1 453 772 B9

25. Panneau de plâtre selon la revendication 20 ayant deux bords définissant une largeur et deux extrémités définissant une longueur, dans lequel ledit panneau de plâtre a une rétraction au séchage de moins de 0,1524 cm (0,06 pouce) par 1,219 m (quatre pieds) de large et moins de 0,762 cm (0,30 pouce) par 3,6576 m (douze pieds) de long.
- 5 26. Panneau de plâtre selon la revendication 20, ayant deux bords définissant une largeur et deux extrémités définissant une longueur, dans lequel ledit panneau de plâtre a une rétraction au séchage de moins de 0,13% sur sa largeur et de moins de 0,26% sur sa longueur.
- 10 27. Panneau de plâtre selon la revendication 20, dans lequel ledit panneau de plâtre comprend en outre un amidon prégélatinisé.
28. Panneau de plâtre selon la revendication 27, dans lequel la quantité d'amidon prégélatinisé est de 0,08 à 0,5 pour-cent en poids du gypse.
- 15 29. Panneau de plâtre selon la revendication 27, dans lequel la quantité d'amidon prégélatinisé est de 0,16 à 0,4 pour-cent en poids du gypse.
30. Panneau de plâtre selon la revendication 27, dans lequel la quantité d'amidon prégélatinisé est de 0,3 pour-cent en poids du gypse.
- 20 31. Panneau de plâtre selon la revendication 20, dans lequel des vides sont distribués de manière uniforme dans ledit gypse durci.
- 25 32. Panneau de plâtre selon la revendication 31, dans lequel ledit gypse durci est en outre formé d'au moins un agent moussant ayant la formule (J) :
- $$\text{CH}_3 (\text{CH}_2)_x \text{CH}_2 (\text{OCH}_2 \text{CH}_2)_y \text{OSO}_3^- \text{M}^+$$
- 30 dans laquelle X est un nombre de 2 à 20, T est un nombre de 0 à 10 et est de 0 dans au moins 50 pour-cent en poids de l'agent moussant ou du mélange d'agents moussants, et M est un cation.
33. Panneau de plâtre selon la revendication 32, dans lequel T est de 0 dans 86 à 99 pour-cent en poids de l'agent moussant.
- 35 34. Panneau de plâtre selon la revendication 31, dans lequel le gypse durci est formé au moins de gypse calciné, d'eau, d'au moins un composé de tétraméthaphosphate et d'un amidon prégélatinisé.

Patentansprüche

- 40 1. Zusammensetzung enthaltend eine Mischung eines Calciumsulfat-Materials, Wasser und eine Tetramethaphosphat-Verbindung, wobei die Konzentration der Tetramethaphosphat-Verbindung in der Mischung im Bereich von 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, liegt.
- 45 2. Zusammensetzung nach Anspruch 1, **dadurch gekennzeichnet, dass** die Mischung zusätzlich Quellstärke enthält.
3. Zusammensetzung nach Anspruch 1, **dadurch gekennzeichnet, dass** die Mischung zusätzlich einen wasserhaltigen Schaum enthält.
- 50 4. Zusammensetzung nach Anspruch 3, **dadurch gekennzeichnet, dass** die Mischung zusätzlich Quellstärke enthält.
- 55 5. Zusammensetzung nach Anspruch 1, **dadurch gekennzeichnet, dass** die Zusammensetzung zusätzlich eine Mischung von Wirtspartikeln mit darin enthaltenen zugänglichen Hohlräumen enthält und dass zumindest ein Teil des Calciumsulfat-Materials in kristalliner Form in und um die Hohlräume der Wirtspartikel herum vorliegt.

- 5 6. Verwendung einer Zusammensetzung enthaltend eine Mischung aus Stärke, Partikel eines redispersierbaren Polymers, Calciumsulfat-Material und eine Tetramethaphosphat-Verbindung für die Herstellung eines abgebundenen, Gips enthaltenden Produkts, das maschinell verarbeitbar ist, wenn es mit Wasser gemischt wird, wobei die Konzentration der Tetramethaphosphat-Verbindung in der Mischung im Bereich von 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, liegt.
- 10 7. Verwendung einer Zusammensetzung enthaltend eine Mischung eines Binders, eines Verdickungsmittels, eines Nivellierungsmittels, eines Calciumsulfat-Materials und einer Tetramethaphosphat-Verbindung für die Endbearbeitung von Fugen zwischen Gipsplattenecken im mit Wasser gemischten Zustand, wobei die Konzentration der Tetramethaphosphat-Verbindungen in der Mischung im Bereich von 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, liegt.
- 15 8. Verwendung einer Zusammensetzung enthaltend eine Mischung von einer gelierten Stärke, einem Calciumsulfat-Material, Wasser und einer Tetramethaphosphat-Verbindung und entweder (i) einer Mineralwolle oder (ii) expandierten Perlit-Partikeln und einem Glasfaserstärkungsmittel zur Herstellung einer Akustikplatte, wobei die Konzentration der Tetramethaphosphat-Verbindung in der Mischung im Bereich von 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, liegt.
- 20 9. Verwendung einer Zusammensetzung enthaltend eine Mischung eines Calciumsulfat-Materials, Wasser, eines Beschleunigers und einer Tetramethaphosphat-Verbindung zur Herstellung einer Gipsplatte, wobei die Konzentration der Tetramethaphosphat-Verbindung in der Mischung im Bereich von 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, liegt.
- 25 10. Verwendung nach Anspruch 9,
dadurch gekennzeichnet, dass die Mischung zusätzlich eine Quellstärke enthält.
- 30 11. Verwendung nach Anspruch 9,
dadurch gekennzeichnet, dass die Mischung zusätzlich einen wasserhaltigen Schaum enthält.
- 35 12. Verwendung nach Anspruch 11,
dadurch gekennzeichnet, dass die Mischung zusätzlich eine Quellstärke enthält.
- 40 13. Verfahren zur Herstellung eines abgebundenen Gips enthaltenden Produkts mit erhöhter Beständigkeit gegen permanente Deformation und/oder erhöhter Stärke, umfassend:
Herstellung einer Mischung aus Calciumsulfat-Material, Wasser und 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, einer Tetramethaphosphat-Verbindung, und
Einhaltung von Bedingungen der Mischung, die geeignet sind, dass das Calciumsulfat-Material eine vernetzende Matrix von abgebundenem Gipsmaterial bildet.
- 45 14. Verfahren nach Anspruch 13,
dadurch gekennzeichnet, dass die Konzentration der Tetramethaphosphat-Verbindung in der Mischung im Bereich von 0,04 bis 0,16 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, liegt.
- 50 15. Verfahren nach Anspruch 13,
dadurch gekennzeichnet, dass die Konzentration der Tetramethaphosphat-Verbindung in der Mischung 0,08 Gew.-%, bezogen auf das Gewicht des Calciumsulfat-Materials, beträgt.
- 55 16. Verfahren nach Anspruch 13,
dadurch gekennzeichnet, dass die Mischung zusätzlich eine Quellstärke enthält.
17. Verfahren nach Anspruch 13,
dadurch gekennzeichnet, dass das Calciumsulfat-Material eine oder mehrere der folgenden Komponenten enthält: Calciumsulfat-Anhydrid, Calciumsulfat-Hemihydrat oder Ionen von Calcium und Sulfat.
18. Verfahren nach Anspruch 17,
dadurch gekennzeichnet, dass das Calciumsulfat-Material Calciumsulfat-Hemihydrat enthält.

EP 1 453 772 B9

19. Abgebundenes, Gips enthaltendes Produkt hergestellt nach dem Verfahren nach Anspruch 13.

20. Gipsplatte enthaltend eine vernetzende Matrix von abgeundenem Gips gebildet zumindest aus kalziniertem Gips, Wasser und mindestens einer Tetramethaphosphat-Verbindung, wobei die Gipsplatte eine Beständigkeit gegen Läuferbildung besitzt, sodass, wenn ein Bereich von 0,3048 m von 0,6096 m der Platte an parallelen und eben tragenden Ecken unterstützt ist, die tragenden Ecken 58,4 cm voneinander entfernt sind und Radii von 3,2 mm besitzen, bei einer Temperatur von $32 \pm 1,7$ °C und einer relativen Feuchtigkeit von 90 ± 3 % über 48 Stunden lang, die Entfernung zwischen dem Zentrum der oberen Oberfläche der Platte von einer imaginären horizontalen Fläche, die sich zwischen den oberen Enden der Plattenenden erstreckt, weniger als 0,254 cm beträgt, wobei die Konzentration der Tetramethaphosphat-Verbindung in der Mischung im Bereich von 0,004 bis 2,0 Gew.-%, bezogen auf das Gewicht des kalzinierten Gips, beträgt.

21. Gipsplatte nach Anspruch 20, **dadurch gekennzeichnet, dass** der abgebundene Gips in Form eines Kernmaterials sandwichartig zwischen Abdeckungen vorliegt.

22. Gipsplatte nach Anspruch 21, **dadurch gekennzeichnet, dass** die Abdeckungen Papier enthalten.

23. Gipsplatte nach Anspruch 20, **dadurch gekennzeichnet, dass** die Tetramethaphosphat-Verbindung ausgewählt ist aus der Gruppe bestehend aus Natrium-Tetramethaphosphat, Lithium-Tetramethaphosphat, Kalium-Tetramethaphosphat, Ammonium-Tetramethaphosphat, Aluminium-Tetramethaphosphat und Mischungen hiervon.

24. Gipsplatte nach Anspruch 20, **dadurch gekennzeichnet, dass** das Tetramethaphosphat Natrium-Tetramethaphosphat ist.

25. Gipsplatte nach Anspruch 20 mit zwei die Breite definierenden Ecken und zwei die Länge definierenden Enden, wobei die Gipsplatte eine Trocknungsschwindung von weniger als 0,1524 cm pro 1,219 m Breite und weniger als 0,762 cm pro 3,6576 m Länge aufweist.

26. Gipsplatte nach Anspruch 20 mit zwei die Breite definierenden Ecken und zwei die Länge definierenden Enden, wobei die Gipsplatte eine Trocknungsschwindung von weniger als 0,13 % über ihre Breite und weniger als 0,26 % über ihre Länge aufweist.

27. Gipsplatte nach Anspruch 20, **dadurch gekennzeichnet, dass** die Gipsplatte zusätzlich eine Quellstärke enthält.

28. Gipsplatte nach Anspruch 27, **dadurch gekennzeichnet, dass** die Menge der Quellstärke im Bereich von 0,08 bis 0,5 Gew.-% des Gips liegt.

29. Gipsplatte nach Anspruch 27, **dadurch gekennzeichnet, dass** die Menge der Quellstärke im Bereich von 0,16 bis 0,4 Gew.-% des Gips liegt.

30. Gipsplatte nach Anspruch 27, **dadurch gekennzeichnet, dass** die Menge der Quellstärke 0,3 Gew.-% des Gips beträgt.

31. Gipsplatte nach Anspruch 20, **dadurch gekennzeichnet, dass** der abgebundene Gips hierin gleichförmig verteilte Hohlräume aufweist.

32. Gipsplatte nach Anspruch 31, **dadurch gekennzeichnet, dass** der abgebundene Gips zusätzlich aus mindestens einem Schaumbildner mit der Formel (J) gebildet ist:



mit X eine Zahl von 2 bis 20, Y eine Zahl von 0 bis 10 und in mindestens 50 Gew.-% des Schaumbildners oder der Blends von Schaumbildnern 0 ist und M ein Kation ist.

EP 1 453 772 B9

33. Gipsplatte nach Anspruch 32,
dadurch gekennzeichnet, dass Y in 86 bis 99 Gew.-% des Schaumbildners 0 ist.

5 **34.** Gipsplatte nach Anspruch 31,
dadurch gekennzeichnet, dass der abgebundene Gips zumindest aus kalziniertem Gips, Wasser, mindestens
einer Tetramethaphosphat-Verbindung und Quellstärke gebildet ist.

10

15

20

25

30

35

40

45

50

55