(19) Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) **EP 1 484 432 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:
25.08.2010 Bulletin 2010/34

(21) Application number: **03708593.3**

(22) Date of filing: **13.03.2003**

(51) Int Cl.:
C23C 22/53 *(2006.01)*

(86) International application number:
PCT/JP2003/002994

(87) International publication number:
WO 2003/076686 (18.09.2003 Gazette 2003/38)

(54) **TREATING SOLUTION FOR FORMING BLACK HEXAVALENT CHROMIUM-FREE CHEMICAL COATING ON ZINC OR ZINC ALLOY PLATED SUBSTRATE, AND METHOD FOR FORMING BLACK HEXAVALENT CHROMIUM-FREE CHEMICAL COATING ON ZINC OR ZINC ALLOY PLATED SUBSTRATE**

BEHANDLUNGSLÖSUNG ZUR HERSTELLUNG EINES SCHWARZEN, KEIN SECHSWERTIGES CHROM ENTHALTENDEN CHEMISCHEN ÜBERZUGS AUF MIT ZINK ODER ZINKLEGIERUNG PLATTIERTEM SUBSTRAT UND VERFAHREN ZUR HERSTELLUNG EINES SCHWARZEN, KEIN SECHSWERTIGES CHROM ENTHALTENDEN CHEMISCHEN ÜBERZUGS AUF MIT ZINK ODER ZINKLEGIERUNG PLATTIERTEM SUBSTRAT

SOLUTION DE TRAITEMENT POUR LA FORMATION D'UN REVETEMENT CHIMIQUE EXEMPT DE CHROME HEXAVALENT NOIR SUR UN SUBSTRAT RECOUVERT DE ZINC OU D'ALLIAGE DE ZINC, ET PROCEDE DE FORMATION DE REVETEMENT CHIMIQUE EXEMPT DE CHROME HEXAVALENT NOIR SUR UN SUBSTRAT RECOUVERT DE ZINC OU D'ALLIAGE DE ZINC

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PT RO SE SI SK TR

(30) Priority: **14.03.2002 JP 2002070175**

(43) Date of publication of application:
08.12.2004 Bulletin 2004/50

(73) Proprietor: **DIPSOL CHEMICALS CO., LTD.**
Tokyo 104-0061 (JP)

(72) Inventors:
- **INOUE, Manabu**
  Dipsol Chemicals Co., Ltd.
  Tokyo 124-0025 (JP)
- **NAKAJIMA, Ryo**
  Dipsol Chemicals Co., Ltd.
  Tokyo 124-0025 (JP)
- **WATANABE, Kazuhiro**
  Dipsol Chemicals Co., Ltd.
  Tokyo 124-0025 (JP)
- **WATANABE, Kimitaka**
  Dipsol Chemicals Co., Ltd.
  Tokyo 124-0025 (JP)

(74) Representative: **Hayes, Adrian Chetwynd et al**
Boult Wade Tennant
Verulam Gardens
70 Gray's Inn Road
London WC1X 8BT (GB)

(56) References cited:
WO-A2-02/07902
DE-A1- 19 615 664
JP-A- 2001 107 273
JP-A- 2002 069 660
US-A- 4 578 122

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 484 432 B1

Description

Field of Technology

[0001] The present invention relates to a processing solution for forming a hexavalent chromium free, black conversion film on zinc or zinc alloy plating layers, and a method for forming the hexavalent chromium free, black conversion film on zinc or zinc alloy plating layers.

Technical Background

[0002] As methods for rust preventing the surface of a metal, there has been known a zinc or zinc alloy-plating method. However, it is not possible to ensure sufficient corrosion resistance of the metal by such plating alone. For this reason, there has widely been adopted, in this industrial field, the treatment with chromic acid containing hexavalent chromium or the so-called chromate treatment after the plating. Nevertheless, it has recently been pointed out that the hexavalent chromium may adversely affect the human body and the environment and there has correspondingly been such a strong and active trend that the use of hexavalent chromium should be controlled.

[0003] As one of the substituent techniques therefor, the formation of a corrosion resistant conversion film, in which trivalent chromium is used, has been known. For instance, Japanese Examined Patent Publication (hereunder referred to as "J.P. KOKOKU") No. Sho 63-015991 discloses a method, which comprises the step of treating the surface of a metal with a bath containing a mixture of trivalent chromium and a fluoride, an organic acid, an inorganic acid and/or a metal salt such as cobalt sulfate. However, a fluoride is used in this plating bath and therefore, a problem of environmental pollution would arise. In addition, J.P. KOKOKU No. Hei 03-010714 discloses a method, which makes use of a plating bath comprising a mixture of trivalent chromium and an oxidizing agent, an organic acid, an inorganic acid and/or a metal salt such as a cerium salt. However, this method makes use of an oxidizing agent and cerium and therefore, the trivalent chromium may possibly be oxidized into hexavalent chromium, during the processing and/or the storage of the bath.

[0004] Japanese Un-Examined Patent Publication (hereunder referred to as "J.P. KOKAI") No. Hei 10-183364 discloses a method which comprises the step of treating the surface of a metal with a bath containing a phosphoric acid, a salt of metal such as Mo, Cr^{3+} and Ti, and an oxidizing agent to provide the surface with a hexavalent chromium free, corrosion resistant conversion film. This method uses a large quantity of the oxidizing agent and therefore, the trivalent chromium may possibly be oxidized into a hexavalent chromium, during the processing and/or the storage of the bath.

[0005] J.P. KOKAI No. 2000-54157 discloses a method which comprises the step of chemical conversion treating the surface of a metal with a bath containing phosphorus, a metal such as Mo, and trivalent chromium, but no fluoride. However, as a result of our experiments to confirm the effects produced by the method, acceptable corrosion resistance could not be obtained.

[0006] Furthermore, J.P. KOKAI No. 2000-509434 discloses a method, which comprises the step of treating the surface of a metal using a plating bath comprising 5 to 100 g/L of trivalent chromium and nitrate residues, an organic acid and/or a metal salt such as a cobalt salt. This method uses, for instance, trivalent chromium in a high concentration and the plating operation is carried out at a high temperature. Therefore, this method is advantageous in that it can form a thick film and ensure good corrosion resistance. However, the method suffers from a problem in that it is difficult to stably form a dense film and that the method cannot ensure the stable corrosion resistance of the resulting film. Moreover, the processing bath contains trivalent chromium in a high concentration and also contains a large amount of an organic acid. This makes the post-treatment of the waste water difficult and results in the formation of a vast quantity of sludge after the processing. Although one can recognize that it is advantageous to use a processing solution free of any hexavalent chromium for ensuring the environmental protection, the method suffers from a serious problem in that it may give a new burden to the environment such that the method generates a vast quantity of waste.

[0007] In addition, there could be obtained only films having colorless or an interference color appearances. In this connection, with regard to a black conversion film containing a trivalent chromium on zinc-nickel alloy plating layers (containing 8% or more of nickel in the layers) and zinc-iron alloy plating layers, U.S. Patent No. 5415702 discloses a method which comprises the step of treating the surface of a metal with an acidic bath containing a phosphate compound and trivalent chromium. Also, with regard to a chemical conversion interference color film containing a trivalent chromium on zinc-nickel alloy plating layers (containing 8% or more of nickel in the layers), U.S. Patent No. 5407749 discloses a method, which comprises the step of treating the surface of a metal with an acidic bath similar to that disclosed in U.S. Patent No. 5415702 containing a phosphorus compound, trivalent chromium and oxy-halogen acid ions.

[0008] However, in many cases, a Ni eutectoid rate in zinc-nickel alloy plating layers actually produced is less than 8%, and thus it is difficult to obtain a black feature from a practical standpoint. Furthermore, the black conversion film on zinc-iron alloy plating layers does not have enough corrosion resistivity.

[0009] Moreover, there have been proposed a method for processing the surface of a metal with a bath containing

trivalent chromium in a low concentration and an organic acid and a metal salt such as a nickel salt (U.S. Patent No. 4,578,122) and a processing method, which makes use of a bath containing trivalent chromium in a low concentration and an organic acid (U.S. Patent No. 5,368,655). However, these methods never ensure sufficient corrosion resistance of the resulting film as compared with the conventional hexavalent chromate treatment.

[0010] It is thus an object of the present invention to provide a processing solution used for forming a hexavalent chromium free, black conversion film, which is applied onto the surface of zinc or zinc alloy plating layers, and which has corrosion resistance identical to or higher than that achieved by the conventional hexavalent chromium-containing conversion film.

[0011] Another object of the present invention is to provide a method for forming such a hexavalent chromium free, black conversion film.

Summary of The Invention

[0012] The present invention has been completed on the basis of such finding that the foregoing problems associated with the conventional techniques can effectively be solved by depositing a zinc or zinc alloy plating layer(s) on a substrate and then subjecting the plating layer to a trivalent chromate treatment using a processing solution having a specific composition, i.e. containing a low concentration of nitrate ions, cobalt ions and nickel ions.

[0013] According to an aspect of the present invention, there is provided a processing solution for forming a hexavalent chromium free, black conversion film on zinc or zinc alloy plating layers and the processing solution comprises:

nitrate ions and trivalent chromium in a mole ratio (NO^{3-}/Cr^{3+}) of less than 0.5/1, wherein the trivalent chromium is present in the form of a water-soluble complex with a chelating agent; and
cobalt ions and / or nickel ions, wherein cobalt ions and / or nickel ions are stably present in the processing solution without causing any precipitation by forming a hardly soluble metal salt with the chelating agent; wherein the solution reacts with zinc when it is brought into contact with the zinc or zinc alloy plating to form a hexavalent chromium free, black conversion film containing zinc, chromium, cobalt and / or nickel, and the chelating agent on the plating.

[0014] According to a further aspect of the present invention, there is provided a method for forming a hexavalent chromium free, black conversion film, which comprises the step of bringing zinc or zinc alloy plating into contact with the foregoing processing solution.

[0015] The substrates used in the present invention may be a variety of metals such as iron, nickel and copper, alloys thereof and metals or alloys such as aluminum, which have been subjected to zincate treatment and the substrate may have a variety of shapes such as plate-like, rectangular prism-like, column-like, cylindrical and spherical shapes.

[0016] The foregoing substrate is plated with zinc or a zinc alloy according to the usual method. The zinc-plating layer may be deposited on the substrate using either, for instance, acidic baths such as a sulfuric acid bath, an ammonium chloride bath or a potassium chloride bath, and alkaline baths such as an alkaline non-cyanide bath and an alkaline cyanide bath, but an alkaline non-cyanide bath (NZ-98 available from Dipsol Chemicals Co., Ltd.) is preferable.

[0017] In addition, examples of zinc alloy plating are zinc-iron alloy plating, zinc-nickel alloy plating having a rate of nickel-co-deposition ranging from 5 to 20% by mass, zinc-cobalt alloy plating and tin-zinc alloy plating. The thickness of the zinc or zinc alloy plating to be deposited on the substrate may arbitrarily be selected, but it is desirably not less than 1 μm and preferably 5 to 25 μm.

[0018] In the present invention, after the zinc or zinc alloy plating is deposited on a substrate according to the foregoing method, if desired, the plated substrate is water-rinsed or subjected to nitrate activation processing after being water-rinsed, and then brought into contact with a processing solution for forming a hexavalent chromium free, black conversion film according to the present invention. For instance, the zinc or zinc alloy plating subjected to a dipping treatment using this processing solution.

[0019] In the foregoing processing solution of the present invention, the source of the trivalent chromium may be any chromium compound containing trivalent chromium, but preferred examples thereof usable herein are trivalent chromium salts such as chromium chloride, chromium sulfate, chromium nitrate, chromium phosphate and chromium acetate or it is also possible to reduce hexavalent chromium such as chromic acid or dichromic acid into trivalent chromium using a reducing agent. Particularly preferable trivalent chromium source is chromium phosphate ($Cr(H_nPO_4)_{(3/3\cdot n))}$). The foregoing sources of trivalent chromium may be used alone or in any combination of at least two of them. The trivalent chromium concentration in the processing solution is not limited. It is preferably as low as possible from the viewpoint of the easiness of the wastewater treatment, but it is preferably 0.5 to 10 g/L and most preferably 0.8 to 5 g/L, while taking into account the corrosion resistance. In the present invention, the use of trivalent chromium in such a low concentration falling within the range specified above is also quite advantageous from the viewpoint of the wastewater treatment and the processing cost.

[0020] The processing solution of the present invention comprises nitrate ions in a mole ratio of nitrate ions to a trivalent

chromium (NO^{3-}/Cr^{3+}) of less than 0.5/1, and preferably in a range of from 0.02/1 to 0.25/1. The nitrate ion concentration in the processing solution preferably ranges from 0.1 to 1 g/L. Examples of the nitrate ion source include nitric acid or a salt thereof.

[0021] Examples of the chelating agent used in the processing solution of the present invention include a hydroxycarboxylic acid such as tartaric acid and malic acid, a monocarboxylic acid, a polyvalent carboxylic acid such as a dicarboxylic acid such as oxalic acid, malonic acid, succinic acid, citric acid and adipic acid, or a tricarboxylic acid, aminocarboxylic acid such as glysinic acid. Moreover, the chelating agent may be used alone or in any combination of at least two of these acids or salts thereof (e.g. salt of sodium, potassium, ammonium or the like). The chelating agent concentration in the processing solution preferably ranges from 1 to 40 g/L, and more preferably 5 to 35 g/L in total.

[0022] The molar ratio of the chelating agent to the trivalent chromium (the chelating agent / Cr^{3+}) present in the processing solution of the present invention preferably ranges from 0.2 / 1 to 4/1 and more preferably 1/1 to 4 /1.

[0023] The processing solution of the present invention comprises cobalt ions and / or nickel ions. As the sources of the cobalt ions and / or nickel ions, there may be used any metallic compounds containing either of these metals. One of these metallic compounds or any combination of at least two of them may be used, but one or more of each of metal salt, cobalt and nickel, is preferably used. The metallic salt concentration in the processing solution preferably ranges from 0.1 to 2 g/L, and more preferably 0.5 to 1.5 g/L in total.

[0024] In addition, the processing solution of the present invention may comprise monovalent to hexavalent metal ions, for example silicon, iron, titan, zirconium, tungsten, vanadium, molybdenum, strontium, niobium, tantalum, manganese, calcium, barium, magnesium, aluminum and the like. Said metal ions may be added alone or in any combination of at least two of them to the processing solution of the present invention. Moreover, as the sources of said metal ions, there may be used any metallic compounds containing either of these metals, but nitrate, sulfate or chloride are preferably used. These metallic compounds may be used alone or in any combination of at least two of them. The concentration in the processing solution preferably ranges from 0.05 to 3.0 g/L, and more preferably 0.1 to 2.0 g/L in total.

[0025] The trivalent chromium and a chelating agent such as oxalic acid should be present in the processing solution in the form of a stable water-soluble complex formed therebetween, which is supposed to have a structure represented by the following general formula, while the metal ions such as cobalt ions should stably exist in the solution without causing any precipitation by forming a hardly soluble metal salt with the chelating agent.

$$[(Cr)_1 \cdot (A)_m]^{+3l-mn},$$

wherein A represents a chelating agent, and n represents a valence of the chelating agent.

[0026] For instance, if the foregoing stable complex is not formed in the solution or excess chelating agents such as oxalic acid ions are present in the processing solution, metal ions such as cobalt ions react with chelating agents present in the processing solution in its free state to thus form precipitates of a hardly soluble metal salt. As a result, the processing solution cannot form any chemical conversion film (coating) having excellent corrosion resistance.

[0027] In order to obtain an excellent black film, the molar ratio of the chelating agent to the trivalent chromium (m/l) in the processing solution of the present invention preferably ranges from 0.2/1 to 4/1.

[0028] In addition, an even more excellent black film can be obtained by adding phosphate ions to the foregoing processing solution. The sources of phosphate ions include oxyacid of phosphorus such as phosphoric acid or phosphorous acid and a salt thereof. One of these sources or any combination of at least two of them may be used. The concentration of phosphate ions in the processing solution preferably ranges from 0.1 to 50 g/L, and more preferably 5 to 25 g/L.

[0029] In addition, sulfate ions, halogen ions and/or borate ions may be added to the foregoing processing solution. Examples of the sources of these ions include sulfuric acid, hydrochloric acid, boric acid and an inorganic salt thereof and the like. The concentration of ions of these inorganic acids in the processing solution preferably ranges from 1 to 50 g/L, and more preferably 1 to 20 g/L in total.

[0030] The pH value of the processing solution of the present invention is preferably adjusted to the range of 0.5 to 4 and more preferably 2 to 3. In this respect, it is possible to use ions of the foregoing inorganic acids or an alkaline agent such as an alkali hydroxide or aqueous ammonia in order to adjust the pH value thereof to the range specified above.

[0031] The rest (balance) of the processing solution used in the present invention, except for the foregoing components, is water.

[0032] If zinc or zinc alloy plating is brought into contact with the processing solution according to the present invention, the components of the solution react with zinc to thus form a hexavalent chromium free, black conversion film on the zinc or zinc alloy plating, as is presumed below.

[0033] As the method for bringing the zinc or zinc alloy plating into contact with the foregoing processing solution according to the present invention, it is usual to immerse an article plated with zinc or zinc alloy in the foregoing processing solution. For instance, such an article is immersed in the solution maintained at a temperature ranging from 10 to 80°C and more preferably 40 to 60°C for preferably 5 to 600 seconds and more preferably 30 to 120 seconds.

[0034] In this connection, the subject to be treated may be immersed in a dilute nitric acid solution in order to activate the surface of the zinc or zinc alloy plating layers, before it is subjected to the trivalent chromate treatment.

[0035] The conditions and processing operations other than those described above may be determined or selected in accordance with the conventional hexavalent chromate processing.

[0036] In addition, further improvement of the corrosion resistance of the film can be achieved by subjecting the trivalent chromate treated film to aging treatment (heat treatment). In cases where it is applied to zinc-nickel alloy plating layers, particularly good effects are obtained. The aging treatment is conducted at 100 to 250°C for 10 to 300 minutes, preferably at 150 to 200°C for 10 to 300 minutes, and more preferably at 200°C for 4 hours.

[0037] Moreover, a topcoat film may be applied onto the hexavalent chromium free, black conversion film and this would permit the further improvement of the corrosion resistance of the film. In other words, this is a quite effective means for imparting more excellent corrosion resistance to the film. For instance, the zinc or zinc alloy plating is first subjected to the foregoing trivalent chromate treatment, followed by washing the plating with water, subjecting the plating to immersion or electrolyzation in a topcoating solution and then drying the processed article. Alternatively, the article is subjected to immersion or electrolyzation in a topcoating solution after the trivalent chromate treatment and the subsequent drying treatment, and then dried. The term "topcoat" effectively used herein means not only an inorganic film of, for instance, a silicate or a phosphoric acid salt, but also an organic film of, for instance, polyethylene, polyvinyl chloride, polystyrene, polypropylene, methacrylic resin, polycarbonate, polyamide, polyacetal, fluorine plastic, urea resin, phenolic resin, unsaturated polyester resin, polyurethane, alkyd resin, epoxy resin or melamine resin.

[0038] The topcoating liquids for forming such an topcoat film usable herein may be, for instance, DIPCOAT W or CC445 available from Dipsol Chemicals Co., Ltd.. The thickness of the topcoat film may arbitrarily be selected, but it desirably ranges from 0.1 to 30 μm.

Reaction Mechanism of Film-Formation

[0039] The reaction mechanism of the hexavalent chromium free, black conversion film-formation according to the present invention can be supposed to be as follows:

(i) A dissolution reaction of Zn, Fe, Ni or the like from a plating film by the action of hydrogen ions and an oxidizing agent such as nitric acid, a supply of metal ions such as zinc to the plating film and re-dissolution reaction of deposits;
(ii) Consumption of hydrogen ions and an increase of the pH value at the interface to be plated subsequent to the dissolution reaction:

$$Zn \rightarrow Zn^{2+} + 2e^-,\ 2H^+ + 2e^- \rightarrow 2H,\ 2H + 1/2\ O_2 \rightarrow H_2O \text{ (an increase in the pH value)};$$

(iii) The reduction of the stability of a chelating agent, the formation and deposition of Cr hydroxide, and the generation and supply of excess oxalic acid, due to the increase in the pH value:
(iv) Formation and deposition of a hardly soluble metal salt through the reaction of the excess chelating agent with metal ions in the solution. For example, in a case where a chelating agent is an oxalic acid and a metal is cobalt:

$$[CrC_2O_4 \cdot (H_2O)_4]^+ \rightarrow Cr(OH)_3 \downarrow + C_2O_4^{2-} + 3\ H^+ + H_2O;$$

$$C_2O_4^{2-} + Co^{2-}\ CoC_2O_4 \downarrow;$$

(v) Formation and deposition of a hardly soluble metal salt through the reaction of the anions such as phosphoric acid in the solution with metal ions such as zinc, Fe and Ni dissolved from the plating film into the solution or Ni, Co and / or Fe added into the solution, and the deposition of another hardly soluble substance produced when the plating film is dissolved onto the zinc or zinc alloy plating film.
For example, in a case where phosphate ions are added into the solution:

$$X_mY_n(H_2PO_4)_2 \rightarrow X_mY_n \cdot (PO_4)_2 \cdot 4H_2O \downarrow;$$

M + n = 3, X, Y: metal ions such as zinc, iron, nickel and / or manganese.
(vi) These reactions are repeated to thus cause the growth of the chemical conversion film.

[0040] In this connection, it would appear that the black conversion film is a composite film of (iii), (iv) and (v).

[0041] In the concentration of nitrate ions being within a suitable range (0.1g/L to 1 g/L), it would appear that the re-dissolution reaction of the hardly soluble metal salt in (v) is inhibited and the hardly soluble metal salt in (v) is incorporated into the chemical conversion film, so that the film exhibits a black feature.

Description of the Preferred Embodiments

Examples 1 to 6

[0042] A steel plate, which had been plated with zincates using a NZ-98 solution available from Dipsol Chemicals Co., Ltd. to form a Zn plating layer having a thickness of 8 μm, was immersed in a trivalent chromate-containing processing solution having a composition as shown in the following Table 1.

Table 1

Ex. No.	1	2	3	4	5	6
Cr^{3+} (g/L)	4.5	4.5	4.5	4.5	4.5	2
NO_3^- (g/L)	0.2	0.4	0.1	0.4	0.6	0.4
Mole ratio of NO_3^- /Cr^{3+}	0.04/1	0.07/1	0.02/1	0.07/1	0.11/1	0.17/1
PO_4^{3-} (g/L)	12	12	0	15	12	12
SO_4^{2-} (g/L.)	15	0	0	2	0	2
Cl^- (g/L)	10	10	10	0	15	0
Oxalic acid (g/L)	15	15	7	0	0	0
Malonic acid (g/L)	0	0	7	15	12	12
Succinic acid (g/L)	0	10	20	0	0	0
Adipic acid (g/L)	0	0	0	20	0	0
Molar ratio of the chelating agent / Cr^{3+}	2.0/1	3.0/1	3.7/1	3.4/1	1.4/1	1.4/1
Co (g/L)	1	1.5	0.5	1	1	1
Ni (g/L)	0.1	0	1.0	0	0.3	0.5
Other metal salt	Si	Si	Ti	Si	Si	Si
pH of Processing Soln.	2.3	2.3	2.3	2.4	2.6	2.5
Processing Temp. (°C)	50	50	60	50	40	30
Processing time (sec.)	30	60	120	60	60	60

[0043] In Table 1, Cr^{3+} sources used were $CrCl_3$ (in Examples 1, 2, 3 and 5), $CrPO_4$ (in Examples 4 and 6) and $Cr(NO_3)_3$ (in Example 5). The concentrations of NO_3. were adjusted by $Cr(NO_3)_3$ (in Example 5) or by adding HNO_3 (in Examples 1, 2 and 3) or $NaNO_3$ (in Examples 4 and 6). Further, the SO_4^{2-} source used was Na_2SO_4 and the PO_4^{3-} source used was NaH_2PO_4. The balance of each processing solution was water. The metallic salts used such as Co and Ni were its sulfate (in Examples 1, 4 and 6) and chloride (in Examples 2, 3 and 5). The Si source used was colloidal silica and the Ti source used was titanium trichloride. The concentration of metal ions other than Co and Ni was 1g/L. The pH value of each solution was adjusted using NaOH.

Examples 7 to 10

[0044] A steel plate, which had been plated with alkaline zinc-nickel alloy (Ni%: 5 to 15%) or zinc-iron alloy (Fe%: 0.3 to 2.0%) in a thickness of 8 μm, was immersed in a trivalent chromate-containing processing solution having a composition as shown in the following Table 2.

Table 2

Ex. No.	7	8	9	10
Cr^{3+} (g/L)	4.5	4.5	4.5	4.5
NO_3^- (g/L)	0.6	0.4	0.2	0.4
Mole ratio of NO_3^-/Cr^{3+}	0.11/1	0.07/1	0.04/1	0.07/1

(continued)

Ex. No.	7	8	9	10
PO_4^{3-} (g/L)	12	12	12	15
SO_4^{2-} (g/L)	10	0	15	2
Cl^- (g/L)	0	10	0	0
Oxalic acid (g/L)	15	7	15	15
Malonic acid (g/L)	0	7	0	0
Succinic acid (g/L)	10	0	0	0
Adipic acid (g/L)	0	0	0	20
Molar ratio of the chelating 3.0/1 agent / Cr^{3+}	3.0/1	1.7/1	2.0/1	3.7/1
Co (g/L)	1	1	1	1
Ni (g/L)	0.3	0	0.1	0
Other metal salt	Si	Si	Si	Si
pH of Processing Soln.	2.6	2.0	2.3	2.5
Processing Temp. (°C)	35	50	50	40
Processing time (sec.)	60	60	60	60
Plating Eutectoid rate (%)	Zn-Ni 6.5	Zn-Ni 15	Zn-Fe 0.5	Zn-Fe 2.0

[0045] In Table 2, the Cr^{3+} sources used were $CrCl_3$ (in Example 8) and $CrPO_4$ (in Examples 7, 9 and 10).

[0046] The concentrations of NO_3 were adjusted by adding HNO_3 (in Example 8) or_$NaNO_3$ (in Examples 7, 9 and 10). Further, the SO_4^{2-} source used was Na_2SO_4 and the PO_4^{3-} source used was NaH_2PO_4. The balance of each processing solution was water. The metal salts used such as Co and Ni were its sulfate (in Examples 7 and 9) and chloride (in Example 8). The Si source used was colloidal silica and the concentration thereof was 1g/L. The pH value of each solution was adjusted using NaOH.

Examples 11 to 14

[0047] After the trivalent chromate treatment in Examples 1, 8 and 9, the steel plate was subjected to a topcoating treatment. The conditions for the topcoating treatment used herein are summarized in the following Table 3.

Table 3

Ex. No.	11	12	13	14
Trivalent chromate treatment	Example 1	Example 8	Example 9	Example 9
Kind of Topcoat	Silicate type inorganic film	Silicate type inorganic film	Polyurethane type organic film	Methacrylic resin type organic film
Concn. Of Processing Soln.	200 mL/L	200 mL/L	100 mL/L	Stock solution was used as such
Processing Conditions	45°C - 45 sec	45°C - 45 sec	25°C - 60 sec	25°C - 60 sec
Name and Origin of Reagent	CC-445 available from Dipsol Chemicals Co., Ltd.	CC-445 available from Dipsol Chemicals Co., Ltd.	SUPERFLEX R3000 available from Dai-ichi Kogyo Seiyaku Co., Ltd.	DIPCOAT W available from Dipsol Chemicals Co., Ltd.

Comparative Example 1

[0048] A steel plate, which had been plated with zinc in a thickness of 8 μm, as a comparative example, was subjected to a hexavalent chromate treatment. The hexavalent chromate bath used herein was ZB-535A (200 mL/L) and ZB-535B (10 mL/L) available from Dipsol Chemicals Co., Ltd.

Comparative Example 2

[0049] A steel plate, which had been plated with zinc in a thickness of 8 μm, as a comparative example, was subjected to a trivalent chromate treatment using a processing solution having the following composition: 15 g/L (3.3 g/L as expressed in terms of Cr^{3+}) of $Cr(NO_3)_3$; 10 g/L of $NaNO_3$; and 10 g/L of oxalic acid (pH: 2.0). In this respect, the processing was carried out at 30°C for 40 seconds.

Comparative Example 3

[0050] A steel plate, which had been plated with zinc in a thickness of 8 μm, as a comparative example, was subjected to a trivalent chromate treatment using a processing solution having the following composition as disclosed in the example of J.P. KOKAI No. 2000-509434: 50 g/L (9.8 g/L as expressed in terms of Cr^{3+}) of $CrCl_3 \cdot 6H_2O$; 3 g/L (0.6 g/L as expressed in terms of Co) of $Co(NO_3)_2$; 100 g/L of $NaNO_3$; and 31.2 g/L of malonic acid (pH: 2.0). In this respect, the processing was carried out at 30°C for 40 seconds.

Processing Steps:

[0051] In these Examples and Comparative Examples, the details of the processing steps are as follows:

Plating → Water Rinsing → Activation with Dilute Nitric Acid → Water Rising → Trivalent Chromate Treatment → Water Rinsing → (Topcoating Treatment)[1] → Drying[2] → (Heat Treatment)[3]
Note 1: This step was used only when the steel plate was subjected to a topcoating treatment.
Note 2: The drying step was carried out at a temperature ranging from 60 to 80°C for 10 minutes.
Note 3: When carrying out the test for the corrosion resistance after heating, each steel plate was treated at 200°C for 2 hours.

Salt Spray Test:

[0052] The zinc plated steel plates obtained in Examples 1 to 14 and Comparative Examples 1 to 3 and each provided thereon with a trivalent chromate film were inspected for the appearance and subjected to the salt spray test (JIS-Z-2371). The results thus obtained are summarized in the following Table 4.

[0053] As will be clear from the data listed in Table 4, it is found that the films obtained in Examples 1 to 10 show the corrosion resistance almost identical or superior to those observed for the chromate film obtained in Comparative Examples 1 to 3. In addition, the films of Examples 11 to 14, which were subjected to a topcoating treatment, especially at the time required for the formation of red rust, show corrosion resistance superior to that observed for the conventional chromate film.

Table 4: Results of Salt Spray Test (JIS-Z-2371)

Ex. No.	Appearance of Film	Corrosion Resistance (1) (hr.)	Corrosion Resistance After Heating (2) (hr.)
1	Black	120/600	240
2	Black	72/500	240
3	Black	72/400	120
4	Black	96/500	240
5	Black	120/500	240
6	Black	120/500	240
7	Black	120/800	240
8	Black	120/1500	240

(continued)

Ex. No.	Appearance of Film	Corrosion Resistance (1) (hr.)	Corrosion Resistance After Heating (2) (hr.)
9	Black	240/1000	240
10	Black	240/1000	240
11	Black	240/1000	
12	Black	300/2000	
13	Black	300/1200	
14	Black	300/1200	
1*	Black	120/500	12
2*	Pale Blue	24/250	24
3*	Interference Color	72/300	48

(1) Time (hour) required for the formation of white rust / red rust (5% by mass).
(2) Time (hour) required for the formation of white rust (5% by mass).
*: Comparative Example

Effect of the Invention

[0054] As has been described above in detail, the present invention permits the formation of a hexavalent chromium free, black conversion film directly on zinc or zinc alloy plating layers. The plated article obtained according to this method has not only the corrosion resistance due to the zinc or zinc alloy plating as such, but also the excellent corrosion resistance due to the presence of the trivalent chromate film. Moreover, the processing solution used in the present invention comprises trivalent chromium in a low concentration and therefore, the present invention is quite advantageous from the viewpoint of the wastewater treatment and production and processing cost. The film obtained by directly forming trivalent chromate on the plating possesses not only corrosion resistance, resistance to salt water and after heating resistance identical or superior to those observed for the conventional hexavalent chromium-containing film, but also expresses a black feature, and therefore, the film of the present invention can widely be used in a variety of fields in the future.

Claims

1. A processing solution for forming a hexavalent chromium free, black conversion film on a zinc or zinc alloy plating layer(s), the processing solution comprising:

   nitrate ions and trivalent chromium in a mole ratio (NO_3^-/Cr^{3+}) of less than 0.5/1, wherein the trivalent chromium is present in the form of a water-soluble complex with a chelating agent; and
   cobalt ions and / or nickel ions, wherein cobalt ions and / or nickel ions are stably present in the processing solution without causing any precipitation by forming a hardly soluble metal salt with the chelating agent; wherein the solution reacts with zinc when it is brought into contact with the zinc or zinc alloy plating to form a hexavalent chromium free, black conversion film containing zinc, chromium, cobalt and / or nickel, and the chelating agent on the plating layer(s).

2. The processing solution according to claim 1 wherein the trivalent chromium concentration ranges from 0.5 to 10g/L and a molar ratio of the chelating agent to the trivalent chromium (the chelating / Cr^{3+}) ranges from 0.2/1 to 4/1.

3. The processing solution according to claim 1 or 2 wherein the trivalent chromium source is chromium phosphate ($(Cr(H_nPO_4)_{(3/(3-n))}$).

4. The processing solution according to any of claims 1 to 3 wherein the chelating agent is one or more members selected from the group consisting of monocarboxylic acids, dicarboxylic acids, tricarboxylic acids, hydroxycarboxylic acids, aminocarboxylic acids and salts thereof.

5. The processing solution according to any of claims 1 to 4 wherein the chelating agent is one or more members selected from the group consisting of oxalic acid, malonic acid, succinic acid and a salt thereof.

6. The processing solution according to any of claims 1 to 5, which further comprises one or more metal ions selected from the group consisting of silicon, iron, titan, zirconium, tungsten, vanadium, molybdenum, strontium, niobium, tantalum, manganese, calcium, barium, magnesium and aluminum.

7. The processing solution according to any of claims 1 to 6 wherein the nitrate ion concentration ranges from 0.1 to 1 g/L.

8. The processing solution according to any of claims 1 to 7, which further comprises phosphate ions.

9. The processing solution according to any of claims 1 to 8, which further comprises one or more ions selected form the group consisting of a sulfate ion, a halogen ion and a borate ion.

10. A method for forming a hexavalent chromium free, black conversion film, which comprises the step of bringing a zinc or zinc alloy plating layer(s) into contact with the processing solution of any of claims 1 to 9.

11. The method according to claim 10, which comprises the step of subjecting a hexavalent chromium free, black conversion film to an aging treatment at 100 to 250°C for 30 to 300 minutes.

12. The method according to claim 11 wherein the aging treatment is applied at 200°C for 60 to 300 minutes.

13. A method for rust-proofing zinc and zinc alloy plating, which comprises the step of subjecting a hexavalent chromium free, black conversion film formed by the method according to any of claims 10 to 12 to an overcoating treatment.

Patentansprüche

1. Verarbeitungslösung zur Bildung eines hexavalenten Chrom-freien, schwarzen Umwandlungsfilms auf einer Zink- oder Zinklegierungs-Plattierungsschicht(en), wobei die Verarbeitungslösung umfasst:

   Nitrationen und trivalentes Chrom in einem Molverhältnis (NO_3^-/Cr_3^+) von weniger als 0,5/1, wobei das trivalente Chrom in Form eines Wasserlöslichen Komplexes mit einem Chelatbildner vorliegt; und
   Kobaltionen und / oder Nickelionen, wobei Kobaltionen und / oder Nickelionen stabil in der Verarbeitungslösung vorliegen, ohne irgendeine Präzipitation durch Bildung eines schwer löslichen Metallsalzes mit dem Chelatbildner zu verursachen; wobei die Lösung mit Zink reagiert, wenn sie in Kontakt mit der Zink- oder Zinklegierungs-Plattierung gebracht wird, um einen hexavalenten Chrom-freien, schwarzen Umwandlungsfilm zu bilden, der Zink, Chrom, Kobalt und / oder Nickel und den Chelatbildner auf der/den Plattierungsschicht(en) enthält.

2. Verarbeitungslösung nach Anspruch 1, wobei die Konzentration des trivalenten Chroms von 0,5 bis 10g/L reicht und ein Molverhältnis des Chelatbildners zum trivalenten Chrom (der Chelatbildner / Cr_3^+) von 0,2/1 bis 4/1 reicht.

3. Verarbeitungslösung nach Anspruch 1 oder 2, wobei die Quelle des trivalenten Chroms Chromphosphat ($Cr(H_nPO_4)_{(3/(3-n))}$) ist.

4. Verarbeitungslösung nach einem der Ansprüche 1 bis 3, wobei der Chelatbildner ein oder mehrere Mitglieder ausgewählt aus der Gruppe bestehend aus Monocarbonsäuren, Dicarbonsäuren, Tricarbonsäuren, Hydroxycarbonsäuren, Aminocarbonsäuren und Salze davon ist.

5. Verarbeitungslösung nach einem der Ansprüche 1 bis 4, wobei der Chelatbildner ein oder mehrere Mitglieder ausgewählt aus der Gruppe bestehend aus Oxalsäure, Malonsäure, Bernsteinsäure und ein Salz davon ist.

6. Verarbeitungslösung nach einem der Ansprüche 1 bis 5, die weiter ein oder mehrere Metallionen ausgewählt aus der Gruppe bestehend aus Silicium, Eisen, Titan, Zirkonium, Wolfram, Vanadium, Molybdän, Strontium, Niob, Tantal, Mangan, Calcium, Barium, Magnesium und Aluminium umfasst.

7. Verarbeitungslösung nach einem der Ansprüche 1 bis 6, wobei die Konzentration des Nitrations von 0,1 bis 1 g/L reicht.

8. Verarbeitungslösung nach einem der Ansprüche 1 bis 7, die weiter Phosphationen umfasst.

9. Verarbeitungslösung nach einem der Ansprüche 1 bis 8, die weiter ein oder mehrere Ionen ausgewählt aus der Gruppe bestehend aus einem Sulfation, einem Halogenion und einem Boration umfasst.

10. Verfahren zur Bildung eines hexavalenten Chrom-freien, schwarzen Umwandlungsfilms, das den Schritt in-Kontaktbringen einer Zink- oder Zinklegierungs-Plattierungsschicht(en) mit der Verarbeitungslösung nach einem der Ansprüche 1 bis 9 umfasst.

11. Verfahren nach Anspruch 10, das den Schritt Unterwerfen eines hexavalenten Chrom-freien, schwarzen Umwandlungsfilms einer Alterungsbehandlung bei 100 bis 250°C für 30 bis 300 Minuten umfasst.

12. Verfahren nach Anspruch 11, wobei die Alterungsbehandlung bei 200°C für 60 bis 300 Minuten angewendet wird.

13. Verfahren zum Rostschutz einer Zink- und Zinklegierungs-Plattierung, das den Schritt Unterwerfen eines hexavalenten Chrom-freien, schwarzen Umwandlungsfilms, der durch das Verfahren nach einem der Ansprüche 10 bis 12 gebildet wurde, einer Beschichtungsbehandlung umfasst.

Revendications

1. Solution de traitement pour la formation d'un film de conversion noir exempt de chrome hexavalent sur une/des couche (s) de placage au zinc ou en alliage de zinc, la solution de traitement comprenant :

   des ions nitrate et du chrome trivalent en un rapport molaire (NO_3/Cr^{3+}) inférieur à 0,5/1, où le chrome trivalent est présent sous la forme d'un complexe soluble dans l'eau avec un chélateur ; et
   des ions cobalt et/ou des ions nickel, où les ions cobalt et/ou les ions nickel sont présents de manière stable dans la solution de traitement sans entraîner de précipitation en formant un sel métallique à peine soluble avec le chélateur ; où la solution réagit avec du zinc lorsqu'elle est mise en contact avec le placage de zinc ou en alliage de zinc pour former un film de conversion noir exempt de chrome hexavalent contenant du zinc, du chrome, du cobalt et/ou du nickel, et le chélateur sur la/les couche(s) de placage.

2. Solution de traitement selon la revendication 1 où la concentration de chrome trivalent se trouve dans la plage de 0,5 à 10 g/L et un rapport molaire du chélateur rapporté au chrome trivalent (le chélateur/Cr^{3+}) se trouve dans la plage de 0,2/1 à 4/1.

3. Solution de traitement selon la revendication 1 ou 2 où la source de chrome trivalent est du phosphate de chrome ($Cr(H_nPO_4)_{3/(3-n))}$).

4. Solution de traitement selon l'une quelconque des revendications 1 à 3 où le chélateur est un élément ou plusieurs éléments sélectionnés du groupe constitué d'acides monocarboxyliques, d'acides dicarboxyliques; d'acides tricarboxyliques, d'acides hydrocarboxyliques, d'acides aminocarboxyliques et de leurs sels.

5. Solution de traitement selon l'une quelconque des revendications 1 à 4 où le chélateur est un élément ou plusieurs éléments sélectionnés du groupe constitué d'acide oxalique, d'acide malonique, d'acide succinique et de leur sel.

6. Solution de traitement selon l'une quelconque des revendications 1 à 5 qui comprend en outre un ou plusieurs ions métalliques sélectionnés du groupe constitué de silicium, de fer, de titane, de zirconium, de tungstène, de vanadium, de molybdène, de strontium, de niobium, de tantale, de manganèse, de calcium, de baryum, de magnésium et d'aluminium.

7. Solution de traitement selon l'une quelconque des revendications 1 à 6 où la concentration en ions nitrate se trouve dans la plage de 0,1 à 1 g/L.

8. Solution de traitement selon l'une quelconque des revendications 1 à 7, qui comprend en outre des ions phosphate.

9. Solution de traitement selon l'une quelconque des revendications 1 à 8, qui comprend en outre un ou plusieurs ions sélectionnés du groupe constitué d'un ion sulfate, d'un ion halogène et d'un ion borate.

10. Procédé de formation d'un film de conversion noir exempt de chrome hexavalent, qui comprend l'étape consistant à mettre en contact une/des couche(s) de placage au zinc ou en alliage de zinc avec la solution de traitement de l'une quelconque des revendications 1 à 9.

11. Procédé selon la revendication 10, qui comprend en outre l'étape consistant à soumettre un film de conversion noir exempt de chrome hexavalent à un traitement de vieillissement à 100 jusqu'à 250°C pendant 30 à 300 minutes.

12. Procédé selon la revendication 11 où le traitement de vieillissement est appliqué à 200°C pendant 60 à 300 minutes.

13. Procédé de protection contre la rouille d'un placage au zinc ou en alliage de zinc, qui comprend l'étape consistant à soumettre un film de conversion noir exempt de chrome hexavalent formé par le procédé selon l'une quelconque des revendications 10 à 12 à un traitement de revêtement.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP SHO63015991 B **[0003]**
- JP HEI03010714 B **[0003]**
- JP 2000054157 A **[0005]**
- JP 2000509434 A **[0006] [0050]**
- US 5415702 A **[0007]**
- US 5407749 A **[0007]**
- US 4578122 A **[0009]**
- US 5368655 A **[0009]**