



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 609 922 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
28.12.2005 Bulletin 2005/52

(51) Int Cl.7: **E04B 1/94**

(21) Application number: **05076290.5**

(22) Date of filing: **02.06.2005**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU MC NL PL PT RO SE SI SK TR**
Designated Extension States:
AL BA HR LV MK YU

(30) Priority: **04.06.2004 NL 1026339**

(71) Applicant: **OPSTALAN B.V.**
5061 KD Oisterwijk (NL)

(72) Inventor: **Van Bergen, Josephus Joannes
Henricus**
5061 BC Oisterwijk (NL)

(74) Representative:
Dohmen, Johannes Maria Gerardus et al
Algemeen Octrooi- en Merkenbureau
P.O. Box 645
5600 AP Eindhoven (NL)

(54) **Compound plate-shaped insulation material, method for producing the same as well as a wall, facade and roof construction**

(57) The present invention relates to a compound plate-shaped insulation material comprising a base layer and a layer of insulation material present thereon, which base layer may be provided with ribs in the longitudinal direction thereof, between which ribs the insula-

tion material is present. The present invention furthermore relates to a method for producing a compound plate-shaped material, as well as to a wall, facade and roof construction provided with insulation material.

EP 1 609 922 A1

Description

[0001] The present invention relates to a compound plate-shaped insulation material comprising a base layer and a layer of insulation material present thereon, which base layer may be provided with ribs in the longitudinal direction thereof, between which ribs the insulation material is present. The present invention furthermore relates to a method for producing a compound plate-shaped material, as well as to a wall, facade and roof construction provided with insulation material.

[0002] From Japanese patent publication JP 02 209 229 there is known an insulation panel comprising a hard-foam thermally insulating layer sandwiched between a rigid base part, e.g. a metal panel or gypsum board, and a back part, e.g. an aluminium foil. Polyisocyanurate is mentioned as the hard foam. A certain amount of ground graphite is contacted with a mixture of concentrated sulphuric acid and hydrogen peroxide, after which the whole is dried and processed as a coating.

[0003] From French patent application FR 2 764 679 there is known a rigid panel comprising a plate having a thickness of about 10 mm, on which a fabric layer of graphite and/or carbon is present, which is in turn provided with a layer of a polystyrene insulation material, on which polystyrene layer a thin layer having a thickness of 3 mm is present, which is finished with a top coat.

[0004] British patent application GB 2 357 111 relates to a fire door or partition wall, in which a rigid polyurethane foam is used as the insulation material, which foam comprises graphite in an amount of 10-75 wt. %.

[0005] From Dutch laid-open publication No. 8801468 in the name of the present inventor there is known a compound plate-shaped material suitable for use as a constructional insulation material in buildings, which insulation material is built up of, successively, a layer of a mineral material, a layer of polyurethane foam material and a coating. Such an insulation material is known to exhibit a fire resistance of more than 30 minutes, according to TNO report B-88-005.

[0006] In recent years there has been an increasing demand for insulation materials that are noncombustible or at least exhibit a reduced combustibility in comparison with the known materials. Such materials are much in demand especially for insulating walls, facades and roofs. In addition to that, current legislation is aimed at achieving safe and durable construction methods, in which connection increasingly stringent requirements are being made especially as regards fire safety.

[0007] In the past, the inflammable polystyrene was frequently used, which was coated with a bituminous layer. To reduce the fire hazard, mineral wool such as rock wool or glass wool is currently being used instead of polystyrene. The use of such materials has certain drawbacks, such as the fact that they are not very suitable for being walked on, their low resistance against wind loads and their undesirably high specific weight.

Moreover, the insulating properties of such roof insulation materials are still capable of improvement.

[0008] It is an object of the present invention to provide a compound plate-shaped insulation material which exhibits a good dimensional stability, good insulation properties and which, in addition, is easy to use.

[0009] Another object of the present invention is to provide a compound plate-shaped material which, in addition to the aforesaid properties, exhibits a high fire resistance in combination with a favourable smoke behaviour.

[0010] Yet another object of the present invention is to provide a compound plate-shaped material designed to minimise the propagation of fire into the insulation material in case of a fire.

[0011] The invention as referred to in the introduction is according to the present invention characterized in that graphite is present in the insulation material.

[0012] The incorporation of graphite in the insulation material has made it possible to achieve one or more of the above objects. The present inventors do not wish to be bound by any explanation, but they assume that the graphite that is present in the insulation material will expand in case of a fire, thus forming a so-called carbon shield, which has a positive effect on the fire and smoke behaviour of the plate-shaped insulation material having the present composition.

[0013] The term "compound plate-shaped insulation material" is to be understood to mean: single-shell roof and facade elements to be described hereinafter and sandwiched roof and facade elements to be described hereinafter, in particular the insulation elements that are known from Dutch patents NL 1009801, NL 1015351 and NL 1009885.

[0014] Preferably, the graphite that is used in the present compound plate-shaped insulation material is a granular graphite having an average particle size of 0.1-3 mm, in particular 0.2-2 mm. If graphite particles having a particle size of less than 0.1 mm are used, a very large amount of graphite is needed to obtain a satisfactory fire and smoke behaviour, whilst a particle size of more than 3 mm will cause problems in forming the required carbon shield, which shield protects the insulation material against further combustion. In addition to this it can be mentioned that graphite particles having a particle size of 0.2-2 mm will form a slightly dense layer in the insulation material, so that such grains only need to exhibit a low degree of "swelling" in order to form a closed carbon shield, as a result of which the required fire resistance is reached sooner. The present inventors have found that when the temperature is further increased, the larger grains in the aforesaid range will build up a somewhat heavy carbon shield and cross-link in the already activated smaller grains.

[0015] To obtain a favourable fire and smoke behaviour, the graphite may be spread through the insulation material, in a specific embodiment, however, it may be desirable for the graphite to be present mainly in an up-

per layer of the insulation material, which upper layer can be considered to be a layer remote from the base layer, having a thickness of 0-70%, in particular 0-40%, more in particular 0-10%, based on the total thickness of the layer of insulation material. The term "substantially" is understood to mean at least 50%, in particular at least 70%, more in particular at least 90% of the total amount of graphite.

[0016] Preferably, the graphite grains are incorporated in the compound plate-shaped insulation material at a location where the fire load is to be expected, viz. mainly on the side of the compound plate-shaped insulation material that is used on the inner side of the construction, viz. the building, the shed, the hall and the like. Thus it is possible to concentrate the graphite mainly in the upper layer, which, if designed to have a thickness of 0-10%, will provide a satisfactory result as regards improving the fire and smoke behaviour, with the graphite particles cross-linking in the insulation material. The carbon shield thus formed protects the underlying insulation material against fire, with a further increase of the temperature forcing the underlying graphite to cross-link and the carbon shield thus created forming a new barrier against fire penetrating and harmful smoke being formed.

[0017] Preferably, the graphite that is used in the present compound plate-shaped insulation material has been pre-treated with an acid, for example nitric acid. Washing with an acid has a positive influence on the required swelling effect of graphite, so that the carbon shield will be formed when the graphite particles are exposed to a temperature increase, for example caused by fire.

[0018] The insulation material that is used in the present invention can be selected from the group consisting of PU, PIR, EPS and mineral wool. Chipboard, plywood and OSB are suitable materials for the base layer, on which a number of longitudinal ribs may be mounted, for example by glueing, as is known from Dutch patent No. 1009801, or ribs may be provided first, whereupon a foam layer is applied to the base layer, as is known from Dutch patent No. 1015351.

[0019] The present invention also relates to a method for producing a compound plate-shaped insulation material comprising a base layer and a layer of insulation material present thereon, which method comprises the following steps:

- i) providing a base layer material,
- ii) applying a slurry of graphite and insulation material to the base layer material, and
- iii) causing the slurry of step ii) to react into a foam.

[0020] Although the above method is aimed at obtaining a foam as the insulation material, it should be understood that also other insulation materials as mentioned above may be used, which insulation materials comprise graphite.

[0021] In a special embodiment, preferably the graphite as used in a slurry according to step ii) has been pre-treated with an acid, and preferably the acid-treated graphite is washed and dried before being worked into a slurry according to step ii). Different amounts of graphite may be used in the slurry, with the graphite being spread over the entire thickness of the insulation material.

[0022] To effect an optimum fire and smoke behaviour, step iii) is preferably carried out in such a manner that the graphite is distributed over the insulation material. In a specific embodiment it is also possible, however, to concentrate the graphite mainly in an upper layer of the insulation material, which upper layer can be considered to be a layer remote from the base layer, with step iii) being carried out in such a manner that the upper layer is provided in a thickness of 0-70%, in particular a 0-40%, more in particular 0-10%.

[0023] The aforesaid step ii), in which the graphite grains are incorporated in the insulation material by means of the so-called slurry system, takes place by making use of computer-controlled recipes, wherein the amount and the position of the graphite grains are determined for varying insulation material thicknesses.

[0024] The present invention further relates to a wall, facade and/or roof construction comprising one or more compound plates of insulation material as described above. Single-shell roof and facade elements comprise a baseplate or base layer material consisting of chipboard, plywood, OSB or other plate materials, in which and/or on which a number of longitudinal ribs are mounted, for example by glueing, and on which an insulation material is present. Sandwiched roof and facade elements consist of two plate materials with an insulation material present therebetween, which may be provided with wooden ribs on both longitudinal sides thereof.

Claims

1. A compound plate-shaped insulation material comprising a base layer and a layer of insulation material present thereon, which base layer may be provided with ribs in the longitudinal direction thereof, between which ribs the insulation material is present, **characterized in that** graphite is present in the insulation material.
2. A compound plate-shaped insulation material according to claim 1, **characterized in that** the graphite is a granular graphite having an average particle size of 0.1-3 mm.
3. A compound plate-shaped insulation material according to claim 2, **characterized in that** the graphite is a granular graphite having an average particle size of 0.2-2 mm.

4. A compound plate-shaped insulation material according to any one or more of the claims 1-3, **characterized in that** the graphite is distributed over the insulation material. 5
5. A compound plate-shaped insulation material according to any one or more of the claims 1-4, **characterized in that** the graphite is present mainly in an upper layer of the insulation material, which upper layer can be considered to be a layer remote from the base layer. 10
6. A compound plate-shaped insulation material according to claim 5, **characterized in that** the base layer has a thickness of 0-70%, based on the total thickness of the layer of insulation material. 15
7. A compound plate-shaped insulation material according to claim 5, **characterized in that** the base layer has a thickness of 0-40%, based on the total thickness of the layer of insulation material. 20
8. A compound plate-shaped insulation material according to claim 5, **characterized in that** the base layer has a thickness of 0-10%, based on the total thickness of the layer of insulation material. 25
9. A compound plate-shaped insulation material according to any one or more of the preceding claims, **characterized in that** the graphite has been pre-treated with an acid 30
10. A method for producing a compound plate-shaped insulation material comprising a base layer and a layer of insulation material present thereon, **characterized in that** the method comprises the following steps: 35
 - i) providing a base layer material,
 - ii) applying a slurry of graphite and insulation material to the base layer material, and 40
 - iii) causing the slurry of step ii) to react into a foam.
11. A method according to claim 10, **characterized in that** the graphite as used in a slurry according to step ii) has been pre-treated with an acid. 45
12. A method according to claim 11, **characterized in that** the acid-treated graphite is washed and dried before being worked into a slurry according to step ii). 50
13. A method according to any one or more of the claims 10-12, **characterized in that** step iii) is carried out in such a manner that the graphite is distributed over the insulation material. 55
14. A method according to any one or more of the claims 10-12, **characterized in that** step iii) is carried out in such a manner that the graphite is present mainly in an upper layer of the insulation material, which upper layer can be considered to be a layer remote from the base layer
15. A roof construction comprising one or more compound plates of insulation materials as defined in any one or more of the claims 1-9.
16. A wall construction comprising one or more compound plates of insulation materials as defined in any one or more of the claims 1-9.
17. A facade construction comprising one or more compound plates of insulation materials as defined in any one or more of the claims 1-9.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 05 07 6290

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	PATENT ABSTRACTS OF JAPAN vol. 014, no. 506 (M-1044), 6 November 1990 (1990-11-06) & JP 02 209229 A (M D KASEI KK), 20 August 1990 (1990-08-20)	1-3, 5-12,14	E04B1/94
A	* abstract *	15-17	
X	FR 2 764 679 A (LMCA LES MATERIAUX COMPOSITES) 18 December 1998 (1998-12-18)	1,5-8, 10,14,16	
A	* the whole document *	2,3	
X	GB 2 357 111 A (ENVIRONMENTAL SEALS LTD) 13 June 2001 (2001-06-13)	1,4,10, 16	
A	* the whole document *	2,3	
D,A	EP 0 450 731 A (OPSTALAN B V) 9 October 1991 (1991-10-09)	1,10, 15-17	
A	* the whole document *		
A	EP 0 694 372 A (UCAR CARBON TECH) 31 January 1996 (1996-01-31)	1,10	
	* the whole document *		
A	FR 2 553 084 A (COMMISSARIAT ENERGIE ATOMIQUE) 12 April 1985 (1985-04-12)		
	* abstract *		
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 4 October 2005	Examiner Vrugt, S
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

1
EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 05 07 6290

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-10-2005

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 02209229	A	20-08-1990	AU 5039890 A	05-09-1990
			WO 9009277 A1	23-08-1990

FR 2764679	A	18-12-1998	NONE	

GB 2357111	A	13-06-2001	NONE	

EP 0450731	A	09-10-1991	NL 9000797 A	01-11-1991

EP 0694372	A	31-01-1996	AU 687170 B2	19-02-1998
			AU 1778195 A	08-02-1996
			CA 2151538 A1	30-01-1996
			DE 69525490 D1	28-03-2002
			DE 69525490 T2	11-07-2002
			FI 952072 A	30-01-1996
			JP 2891899 B2	17-05-1999
			JP 8060764 A	05-03-1996
			NO 951655 A	30-01-1996
			US 5443894 A	22-08-1995

FR 2553084	A	12-04-1985	NONE	
