



(12) **CORRECTED EUROPEAN PATENT APPLICATION**

published in accordance with Art. 158(3) EPC

Note: Bibliography reflects the latest situation

- (15) Correction information:
Corrected version no 1 (W1 A1)
INID code(s) 72
- (48) Corrigendum issued on:
18.10.2006 Bulletin 2006/42
- (43) Date of publication:
28.06.2006 Bulletin 2006/26
- (21) Application number: **04792617.5**
- (22) Date of filing: **13.10.2004**
- (51) Int Cl.:
C08L 21/00^(2006.01) C08K 5/45^(2006.01)
C07D 341/00^(2006.01)
- (86) International application number:
PCT/JP2004/015451
- (87) International publication number:
WO 2005/035647 (21.04.2005 Gazette 2005/16)

(84) Designated Contracting States:
DE FR IT

(30) Priority: **14.10.2003 JP 2003353974**
24.10.2003 JP 2003364613
13.11.2003 JP 2003383808
13.11.2003 JP 2003383849
13.11.2003 JP 2003383943
14.11.2003 JP 2003385220
17.11.2003 JP 2003386800
18.11.2003 JP 2003388197
20.11.2003 JP 2003390979
27.11.2003 JP 2003397146

(71) Applicant: **THE YOKOHAMA RUBBER CO., LTD.**
Tokyo 105-8685 (JP)


(72) Inventors:
• **CHOI, Wonmun;**
c/o The Yokohama Rubber Co., Ltd.
Hiratsuka-shi, Kanagawa 254-8601 (JP)

- **MATSUMURA, Tomoyuki c/o The Yokohama Rubber Co Ltd**
Hiratsuka-shi, Kanagawa 254-8601 (JP)
- **AMINO, Naoya;**
c/o The Yokohama Rubber Co., Ltd.
Hiratsuka-shi, Kanagawa 254-8601 (JP)
- **TAKASE, Kazuhiro c/o The Yokohama Rubber Co., Ltd.**
Hiratsuka-shi, Kanagawa 254-8601 (JP)
- **KANENARI, Daisuke**
c/o The Yokohama Rubber Co. Ltd.
Hiratsuka-shi, Kanagawa 254-8601 (JP)
- **HOTAKA, Takeshi;**
c/o The Yokohama Rubber Co., Ltd.
Hiratsuka-shi, Kanagawa 254-8601 (JP)
- **NATORI, Junichirou c/o The Yokohama Rubber Co Ltd.**
Hiratsuka-shi, Kanagawa 254-8601 (JP)

(74) Representative: **HOFFMANN EITL**
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(54) **RUBBER COMPOSITION CONTAINING CYCLIC POLYSULFIDE AS VULCANIZER AND PNEUMATIC TIRE MADE THEREFROM**

(57) A rubber composition containing 100 parts by weight a sulfur-vulcanizable rubber (A) and 0.1 to 30 parts by weight of a vulcanization agent of a cyclic polysulfide (B) having the formula (I):



(I)

wherein R is a substituted or unsubstituted C₂ to C₂₀ alkylene group, substituted or unsubstituted C₂ to C₂₀ oxyalkylene group or alkylene group having an aromatic ring, n is an integer of 1 to 20, x is a number of 2 to 6 on average.

Fig. 1

