



(11) **EP 1 693 194 A8**

(12) **CORRECTED EUROPEAN PATENT APPLICATION**

Note: Bibliography reflects the latest situation

(15) Correction information:

Corrected version no 1 (W1 A1)
INID code(s) 71,72

(51) Int Cl.:

B32B 27/32 (2006.01)

(48) Corrigendum issued on:

21.02.2007 Bulletin 2007/08

(43) Date of publication:

23.08.2006 Bulletin 2006/34

(21) Application number: **06114929.0**

(22) Date of filing: **27.02.1998**

(84) Designated Contracting States:

AT BE DE ES FR GB IE IT

Designated Extension States:

AL BA HR MK YU

(30) Priority: **28.02.1997 US 808093**

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:

98908781.2 / 0 963 288

(71) Applicant: **CURWOOD, INC.**

Oshkosh,

Wisconsin 54904 (US)

(72) Inventors:

• **Wilhoit, Darrel Loel**

Plainfield, Illinois 60544 (US)

• **Georgelos, Paul Nick**

Naperville, Illinois 60540 (US)

(74) Representative: **Eddowes, Simon**

W P Thompson & Co

Eastcheap House

Central Approach

Letchworth Garden City

Hertfordshire SG6 3DS (GB)

Remarks:

This application was filed on 02 - 06 - 2006 as a divisional application to the application mentioned under INID code 62.

(54) **Thermoplastic C2-alpha-olefin copolymer blends and films**

(57) There is provided a thermoplastic film of at least two layers comprising:

a first layer comprising:

a third polymer having a melting point between 115 to 130°C, and

a second layer in direct contact with said first layer without any interposed thermoplastic film layer, said second layer

comprising:

a first polymer having a melting point between 55 to 75°C, comprising a copolymer of ethylene and at least one α -olefin, and

a second polymer having a melting point between 85 to 110°C, comprising a copolymer of ethylene and at least one α -olefin.

EP 1 693 194 A8