



(11) **EP 1 723 089 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Claims EN 1, 8, 15

(51) Int Cl.:
C04B 28/02 (2006.01)

(86) International application number:
PCT/NL2004/000182

(48) Corrigendum issued on:
23.03.2011 Bulletin 2011/12

(87) International publication number:
WO 2005/087687 (22.09.2005 Gazette 2005/38)

(45) Date of publication and mention
of the grant of the patent:
19.05.2010 Bulletin 2010/20

(21) Application number: **04720290.8**

(22) Date of filing: **12.03.2004**

(54) **CONSTRUCTION COMPOSITION AND METHOD FOR MAKING A CONSTRUCTION PRODUCT**
BAUMASSE UND VERFAHREN ZUR HERSTELLUNG EINES BAUPRODUKTS
COMPOSITION ET PROCEDE DE FABRICATION D'UN PRODUIT POUR LA CONSTRUCTION

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PL PT RO SE SI SK TR
Designated Extension States:
AL LT LV MK

(56) References cited:
WO-A-02/48067 GB-A- 1 069 657
GB-A- 1 312 079 GB-A- 1 592 001
US-A- 5 242 603 US-A- 5 577 865

(43) Date of publication of application:
22.11.2006 Bulletin 2006/47

(60) Divisional application:
10075063.7 / 2 218 700

(73) Proprietor: **Mega-Tech Holding B.V.**
4782 SK Moerdijk (NL)

(72) Inventor: **DE LA ROIJ, Robin**
NL-3335 BE Zwijndrecht (NL)

(74) Representative: **op den Brouw-Sprakel, Vera**
Stefanie Irene et al
Algemeen Octrooi- en Merkenbureau
P.O. Box 645
5600 AP Eindhoven (NL)

- **DATABASE WPI Section Ch, Week 199834**
Derwent Publications Ltd., London, GB; Class
L02, AN 1998-396820 XP002306623 & RU 2 101
251 C1 (KANSK-ACHINSK FUEL POWER
COMPLEX) 10 January 1998 (1998-01-10)
- **PATENT ABSTRACTS OF JAPAN vol. 0171, no.**
24 (C-1035), 16 March 1993 (1993-03-16) & JP 4
305044 A (KUBOTA CORP), 28 October 1992
(1992-10-28)
- **DATABASE WPI Section Ch, Week 200119**
Derwent Publications Ltd., London, GB; Class
L02, AN 2001-183489 XP002306624 & CN 1 271
698 A (LU J) 1 November 2000 (2000-11-01)
- **DATABASE WPI Section Ch, Week 197946**
Derwent Publications Ltd., London, GB; Class
D15, AN 1979-83154B XP002306625 & JP 54
128477 A (EBARA INFILCO KK) 5 October 1979
(1979-10-05)

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 723 089 B9

Description

[0001] This invention is related to a construction composition and a method for making a construction product.

[0002] In plants utilizing coal as a power source, such as black coal-fired burners, powder coal electricity plants, etc. large amounts of fly ash are generated and escape to the atmosphere, and thus, may cause polluting effects. Accordingly, it has been tried to solve this pollution problem by reusing industrial waste materials and measures have been undertaken to reuse as much fly ash as possible. Ashes, depending upon the kind of ash, can be reused, e.g. as filler material in cement, as filler material in dykes etc.

[0003] However, a disadvantage is that only limited amounts of fly ash can be used in such applications. For example, in order not to lose the construction properties of cement (like strength, etc.), fly ash can only be added to an amount of 30 wt% of the cement As described in e.g. US 487283 (for injection a limo-fly ash composition) and WO0248067 (immobilizing fly ash with cement), in order to obtain the desired properties, cement always has to be present When used as asphalt filler, only about 30 wt.% of this filler may consist of fly ash, next to cement.

[0004] A further disadvantage is that when fly ash is used (only fly ash or in combination with cement), usually large amounts of lime are necessary, as described in e.g. US 487283 (10-300 wt.% lime) and US 5951751 (30-50 wt.% lime). When e.g. stabilizing bottom materials like sludge, peat etc. (especially those bottom materials containing large amounts of water), with fly ash and cement, or with fly ash and large amounts of lime, bad construction properties may be obtained or e.g. long setting times are required.

[0005] RU 2101251 C1 relates to a heavy concrete mixture containing high calcium containing fly ash from burning brown cole, rubble, sand, a chloride containing additive and water.

[0006] GB 1 592 001 relates to cement composition using a pozzolan material preferably fly ash. The composition includes materials for supplying alkali metal and ionic constituents including sodium chloride.

[0007] GB 1 069 657 relates to a cementitious dry mix for inclusion In concrete articles comprising an accelerator, for example sodium chloride and a method for preparing such a dry mix comprising the steps of mixing fly ash and lime with an accelerator, and a dispersion agent.

[0008] It is therefor an object of the invention to provide a composition that can be used in construction applications, e.g. in combination with bottom materials, wherein this composition allows the use of the large amounts of ash, especially fly ash, while nonetheless maintaining good construction properties, In another aspect of the invention, it is an object of the invention to provide a construction product, based on bottom material and this construction composition. In yet another aspect of the invention, it is an object of the invention to provide a method for making a construction product with large amounts of ash, while having good construction properties.

[0009] Surprisingly, it has been found that a construction composition comprising ash and an additive, wherein the additive comprises chlorides and oxides, has very good construction properties, even in the complete absence of cement. In some cases, this construction composition may even provide better construction properties than state of the art compositions based on cement (cement only or cement and ash). This means, that by applying this construction composition, it is now possible to use ash as a construction material, with the some or better properties then with only cement, or with cement and ash as filler material. Hence, according to the invention, ash is not merely a filler material, but, in combination with an additive, ash can provide a construction composition, which can e.g. be used for consolidating bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay, etc.

[0010] According to the invention, the construction composition can be used as mortar (mortar concrete), for consolidating radioactive material, breaker sand, furnace slags (like high blast furnace slags) and minerals, Examples are o.g. asphalt granulate cement (AGRAC), asphalt granulate emulsion (AGRBM), asphalt granulate emulsion cement (AGREC or as mixture of milled porous asphalt granulate (porous asphalt, i.e asphalt that effectively drains off rain water), natural sand, cement and water (FAGREC application).

[0011] According to the invention, there is provided a construction composition comprising:

an ash in an amount of 90.0-99.9 wt.%, based on the total weight of the construction composition, wherein the ash is fly ash or bottom ash;

an additive composition in an amount of 0.1-10.0 wt.%, based on the total weight of the construction composition, wherein the additive composition comprises a component from group (2a) and a component from group (2b), wherein group (2a) consists of metal chlorides and wherein group (2b) consists of amorphous silica, zeolite and apatite, and wherein group (2a) comprises 70.0-99.0 wt.% of the total additive composition and group (2b) comprises 1.0-30.0 wt.% of the total additive composition, wherein group (2a) comprises at least one component from group (2a1) and a component from group (2a2), wherein group (2a1) consists of sodium chloride, potassium chloride, magnesium chloride, calcium chloride, strontium chloride, barium chloride, and ammonium chloride, and wherein the group (2a2) consists of aluminum chloride; and

cement, in an amount of 0.0-5.0 wt.%, based on the total weight of the construction composition.

[0012] The use of a similar additive composition as used in the invention is known from WO0248067 as cement improver. WO0248067 discloses that cement products based on cement and such an additive composition have superior characteristics with respect to prior cement products (without such an additive composition). It is also taught in WO0248067 that such cement can bind polluted soil or fly ash. When immobilizing fly ash, 1.7-3 kg of additive composition is used per m³ of material to be treated, in combination with the addition of 100-250 kg of cement per m³ of material. Assuming a density of the ash of about 800-1500 kg/m³, this means that, based on the amount of ash, cement has to be added in an amount of about 6.5-30 wt. % (since cement is the basic building component) and 0.1-0.4 wt. % of the additive composition of WO0248067.

[0013] However, according to the present invention, ash, especially ash from incineration plants, in combination with a small amount of additive composition, is used as construction material itself and cement is not necessarily present anymore, or is at least present in substantially smaller amounts (0.0-5.0 wt. %, based on the total weight of the construction composition) than according to the state of the art methods (6.5-30 wt. %). In an embodiment of the invention, the invention is directed to a construction composition, wherein the amount of cement is 0.0 -3.0 wt. % of the total construction composition. In a variation on this embodiment, the composition according to the invention is a construction composition, containing no cement.

[0014] The ash of the invention can e.g. be a fly ash or bottom ash, e.g. from incineration plants. For example, the ash can be E-bottom ash, an ash that is released from electricity plants based on powder coal. This bottom ash is released as "heavy" ash particles. The material is a burnt, dehydrated clay, having a brown-black color. One can distinguish between porous (sintered) and dense (molten) E-bottom ash granules. The density is about 780-800 kg/m³ for loosely poured ash and 950-1500 kg/m³ for densified E-bottom ash. The elasticity modulus is about 100-200 N/mm². The ash can also be E-fly ash, also released from electricity plants based on powder coal. With electrostatic filters, E-fly ash (and E-bottom ash) is separated from the exhaust. The density is about 800-1150 kg/m³ for loosely poured ash and 1100-1500 kg/m³ for densified E-fly ash. In an embodiment of the invention, the invention is directed to a construction composition, wherein the ash comprises fly ash, and especially a construction composition, wherein the ash comprises powder coal fly ash (PFA). When using PFA, a construction product with excellent properties like strength etc. can be obtained.

[0015] With construction composition in the context of the invention is referred to a composition that can be used for making constructions or construction products like consolidations, roads, etc. The construction composition can however also be used to make smaller construction products like granules, blocks, bricks, kerbs etc. Further, the construction composition can also be used e.g. as filler for mining binder, for waste material, for binding toxic materials, like e.g. those present in slag, as grout for injection or inoculation.

[0016] In an embodiment of the invention, the construction composition comprises an additive composition according to claim 1. In an embodiment of the invention, the invention is directed to a construction composition comprising an additive composition, wherein the metal chloride comprises sodium chloride, potassium chloride, magnesium chloride, calcium chloride, ammonium chloride and aluminium chloride.

[0017] In another embodiment of the invention, the construction composition comprises an additive composition, wherein group (2b) comprises zeolite, or a combination of zeolites. For example, this can be a zeolite selected from the group consisting of fibrous zeolites, zeolites with doubly-connected 4-ring chains, zeolites with 6-rings, zeolites with 8, 10 and/or 12 rings, like those of the mordenite group, zeolites of the Heulandite Group, Coislesite, Goosecreekite, Partleite, etc. The person skilled in the art can find other zeolites than those mentioned above, for application in the construction composition. Zeolites may be of natural or synthetic origin. Preferably, synthetic zeolite is used. Combinations of zeolites are also possible.

[0018] In yet another embodiment of the invention, the construction composition comprises an additive composition, wherein group (2b) comprises amorphous silion. Also combinations of amorphous silica and zeolite can be used. In a further embodiment, next to the chlorides of group (2a) and the oxides of group (2b), the additive composition may further comprise a component selected from the group consisting of magnesium oxide and calcium oxide.

[0019] The additive composition of the invention may for example be a composition similar to the composition which is intended for use as an additive for cement according to WO0248067, which contains:

- a. sodium chloride, potassium chloride, magnesium chloride, calcium chloride, strontium chloride, barium chloride and/or ammonium chloride;
- b. aluminum chloride; and
- c. amorphous silica and/or zeolite and/or apatite.

[0020] Group a. of components in the composition relates to the known alkali metal and alkaline earth metal chlorides. Of these, a combination of sodium chloride and calcium chloride is most preferred. In particular, the composition according to the invention contains a combination of sodium chloride, potassium chloride, magnesium chloride, calcium chloride and ammonium chloride. Group b. is composed of aluminum chloride. Aluminum chloride is preferred, but may also be

partially replaced by other chlorides of trivalent metals, such as iron (III) chloride. Group c. is composed of amorphous silica or zeolite. The zeolites used are preferably zeolites based on a combination of aluminum and silicon.

[0021] According to a preferred embodiment the group (2a) also comprises at least one compound from group (2a3), wherein the group (2a3) consists of chlorides of trivalent metals.

[0022] If appropriate, the amorphous SiO₂ can be replaced by apatite or a combination of zeolites or a zeolite composite, in particular a zeolite composite comprising natural zeolite (45%), alkali feldspar (32%), agriniauxite (10%), wollastonite (9%), calcite (1%), gotzenite (1%), melanite, apatite, titanite (2%).

[0023] In addition to the components from groups a., b. and c. referred to above, components from group d., namely magnesium oxide and/or calcium oxide, are preferably also present in the mixture. A preferred composition comprises at least sodium chloride, potassium chloride, magnesium chloride, calcium chloride, ammonium chloride, aluminum chloride, magnesium oxide, amorphous silica and/or zeolite.

[0024] Furthermore, there may also be present a component from group c. magnesium hydrogen phosphate and/or a component from group f., consisting of magnesium sulfate and sodium carbonate. The overall composition advantageously may contain a combination of components comprising:

- a. sodium chloride, potassium chloride, ammonium chloride, magnesium chloride and calcium chloride
- b. aluminum chloride
- c. amorphous silica
- d. magnesium oxide
- e. magnesium monohydrogen phosphate
- f. magnesium sulfate and sodium carbonate.

[0025] When these components are combined, the result is a composition which contains the following components in quantities, based on the total quantity of these components in the additive composition:

- 10 to 55% by weight of sodium chloride
- 5 to 40% by weight of potassium chloride
- 0.5 to 5% by weight of ammonium chloride
- 5 to 40% by weight of magnesium chloride
- 5 to 45% by weight of calcium chloride
- 1 to 15% by weight of aluminum chloride
- 0.5 to 10% by weight of amorphous silica
- 0.2 to 8% by weight of magnesium oxide
- 1.5 to 10% by weight of magnesium hydrogen phosphate
- 1.5 to 8% by weight of magnesium sulfate
- 1 to 10% by weight of sodium carbonate,

based on the total weight of the composition, and wherein the metal chlorides in the composition comprise about 70.0-99.0 wt.% of the total additive composition, and wherein the oxides (where applicable magnesium oxide, amorphous silica) of the composition comprise about 1.0-30.0 wt.% of the total additive composition.

[0026] In another embodiment, the invention is directed to a construction composition, wherein the additive composition comprise 80.0-99.0 wt% metal chlorides of the total additive composition, and the oxides of the composition comprise about 1.0-20.0 wt.% of the total additive composition. In yet another embodiment, the metal chlorides comprises 85.0-99.0 wt.% of the total additive composition, and the oxides of the composition comprise about 1.0-15.0 wt.% of the total additive composition.

[0027] When these components are combined, the result is a composition which contains the following components in quantities, based on the total quantity of these components in the additive composition:

- 10 to 55% by weight of sodium chloride
- 5 to 40% by weight of potassium chloride
- 0.5 to 5% by weight of ammonium chloride
- 5 to 40% by weight of magnesium chloride
- 5 to 45% by weight of calcium chloride
- 1 to 15% by weight of aluminum chloride
- 0.5 to 10% by weight of zeolite (or combination of zeolites)
- 0.2 to 8% by weight of magnesium oxide
- 1.5 to 10% by weight of magnesium hydrogen phosphate
- 1.5 to 8% by weight of magnesium sulfate

1 to 10% by weight of sodium carbonate,

based on the total weight of the composition, and wherein the metal chlorides in the composition comprise about 70.0-99.0 wt.% of the total additive composition, and wherein the oxides (where applicable magnesium oxide, zeolite) of the composition comprise about 1.0-30.0 wt.% of the total additive composition.

[0028] In another embodiment, the invention is directed to a construction composition, wherein the additive composition comprise 80.0-99.0 wt.% metal chlorides of the total additive composition, and the oxides of die composition comprise about 1.0-20.0 wt.% of the total additive composition. In yet another embodiment, the metal chlorides comprises 85.0-99.0 wt.% of the total additive composition, and the oxides of the composition comprise about 1.0-15.0 wt% of the total additive composition.

[0029] The additive composition for the construction composition of the invention can be prepared by combining the above-mentioned components and dry-mixing them. The additive composition according to the invention is preferably assembled from the abovementioned components in pure form (> 97%). If appropriate, salts including bound water of crystallization, are incorporated to facilitate processing. Suspensions based on the composition described above have a pH of between approx. 8-13.5 (1 part composition and 20 parts water, T - 16.8°C. This high pH is highly advantageous if soil which is contaminated with organic acids is to be stabilized or immobilized.

[0030] In another aspect, the invention is directed to a method for making a construction composition comprising:

providing an ash, wherein the ash is fly ash or bottom ash;

providing an additive composition, wherein the additive composition comprises a component from group (2a) and a component from group (2b), wherein group (2a) consists of metal chlorides and wherein group (2b) consists of amorphous silica, zeolite and apatite, and wherein group (2a) comprises 70.0-99.0 wt.% of the total additive composition and group (2b) comprises 1.0-30.0 wt% of the total additive composition, wherein group (2a) comprises at least one component from group (2a1) and a component from group (2a2), wherein group (2a1) consists of sodium chloride, potassium chloride, magnesium chloride, calcium chloride, strontium chloride, barium chloride, and ammonium chloride, and wherein the group (2a2) consists of aluminum chloride; such that the weight of the ash is 90.0-99.9 wt%, based on the total weight of the construction composition and the weight of the additive composition is 0.1-10.0 wt.%, based on the total weight of the construction composition;

mixing the ash and the additive composition.

[0031] This method advantageously provides a construction composition according to the invention. This construction composition, which is obtainable by this above-mentioned method, may further be used to make a construction product according to the invention, e.g. by a method for making a construction product, comprising:

providing a bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay; providing a construction composition according to any one of claims 1-8 in an amount such that the weight of the construction composition comprises 10-95 wt.% (wet weight) of the bottom material; mixing the bottom material and the construction composition; drying the mixture obtained in step (3).

[0032] In an embodiment of the method for making a construction product, before or during mixing, one may also add a small amount of cement. This may e.g. be used to obtain a faster consolidation or hardening of the of construction product. Hence, the invention is also directed to a method for making a construction product, wherein cement is added to the mixture obtained in step (3) in an amount such that the weight of the cement comprises 0.5-10 wt.% (wet weight) of the mixture obtained in step (3), for example wherein the weight of the cement comprises 3-5 wt.% (wet weight) of the mixture obtained in step (3). This method provides a construction product, comprising a mixture of the construction composition, and a bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay. This construction product, e.g. obtainable by above-mentioned method for making a construction product, may be a construction product having a compressive strength of at least 1.2 N/mm² (which was e.g. obtained in the field. In the lab, a value of even 1,5 N/mm² was obtained).

[0033] In a preferred embodiment, the construction composition is added in the method for making a construction product, such that the weight of the construction composition comprises 10-90 wt% (wet weight) of the bottom material, e.g. 10-80 wt.%.

[0034] Hence, the invention provides a construction composition and a construction product, which can advantageously be used for consolidating bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay, thereby not only binding fly ash, but also using fly ash in the substantial absence of cement as construction material, providing physical properties of the resulting construction product which are similar, or better, or are obtained in a shorter time frame than when making construction product based on e.g. cement according to state of the art

methods. Further, pollutants in the ash, or in the bottom material, are advantageously bound.

[0035] The person skilled in the art will understand that in the method for making a construction composition and in the method for making a construction product, one may vary the sequence of adding the chlorides of group (2a), the oxides of group (2b), and where applicable cement and bottom material respectively. One may also have a number of mixing steps, e.g. before the addition of a new component, etc.

Example 1: peat/sandy soil

[0036] Peat (wet) 1750.00 gram (Lab 70 wt.% = mass /mass) (field quantity is slight different and is determined on 70 vol.% = volume mass = 0.7m³) and sandy loam (wet) 750.00 gram (Lab 30 wt.%) (field quantity is slight different and is determined on 30 vol.% = volume mass = 0.3m³) are mixed. This makes a peat/loam bottom material sample (wet) of 2500.00 gram (approx. 1.8 dm³).

[0037] To the bottom material sample, an additive composition of 16.2 gram was added, the additive composition comprising a composition according to example 5b, and 450.00 gram PFA (18 wt.% related to wet base material) (PFA = Powder coal fly ash). The additive composition and the bottom material are mechanically mixed for a few minutes. A proctor cylinder sample was made. The proctor sample had a wet density of 1220g/dm³ and was extremely plastic after preparation due to the extreme high water content of the soil samples.

[0038] The wet density of both soil samples in composition (70:30) was determined at approx. 1360 g/dm³. Mechanical compaction was only partly possible and to a certain extend. The water content in the mixed peat sample (70 vol.% peat : 30 vol.% sandy loam) is 67 wt.% due to 100 wt.% sample. The water content is determined in an incubator by 110°C during 1 hour. The solid "organically" fraction is 33 wt.%. The wet density of the construction composition modified soil mix is determined at 1220 g/dm³. The mixed material showed before adding the construction composition 17°C; afterwards, when mixing, the temperature raised up to 23°C.

[0039] The useful macro composition in this experiment is determined on about 0.5- 2.5 kg additive composition + 100-500 kg PFA /m³ bulk material. The bulk weight of 70 vol.% peat + 30 vol.% sandy loam is determined on 1300 kg/m³. Slight differences could be noticed referring soils from other spots due to the heterogeneous character of the soil and the specific different water content in the field.

[0040] The extreme high water content is an additional negative factor which delays the hydration time. It is possible to increase the hydration time by increasing PFA (30-50 vol.%) or a slight percentage of cement (3-5 wt.%). This are possibilities which may be taken into account when construction under disadvantageous circumstances, e.g. when using extreme wet and/or high organically bottom material. In normal sandy soil and under normal circumstances approx. 1-2 kg additive composition: 100-200 kg PFA can be used for obtaining the required strength due to RAW Standard 1995 - NL.

[0041] The end product will have excellent physically / mechanically characteristics after the hydration period. It is e.g. possible to make 5-10000 m² stabilization per day. When using for roads with an additional asphalt top, the asphalt on top can be diminished to about 2/3 or even about 1/3, referring to classical design with using large amounts of cement and only small amounts of fly ash as filler material.

[0042] Physical tests were performed by measuring UCS MTE Lab with compressing speed 0.1 MPa/sec. Axial compression strength in N/mm² and flexural strength in N/mm² were measured. These techniques are known to the person skilled in the art and are e.g. described in "Standaard RAW Bepalingen", from the "Centrum voor Regelgeving en Onderzoek in Grond-, Water- en Wegenbouw en de Verkeerstechniek" from 1995, e.g. pages 64-68).

[0043] A soak test was performed: After 24 hours complete water soak the 72 hour sample with a weight of 131.4 g showed after 24 hours (total age 96 hours) a weight of 136 g. An increase of 4.6 g (3.5 wt.%) caused by water absorption. The PFA-additive composition modified sample is stored completely under water for 24 hours soak after 3 day's of hardening. The normal soak test soak after 3, respectively 7 days whereby the sample is in contact with just the lower part and a membrane between. The size of the sample was 62.5mm x 40mm x 40mm. This sample is than subsequently disposed to frost test with -20°C / +20°C cycles of 24 hours for 9 days. It showed then a 5 vol% shrinking; usually such samples desintegrate after these test, but the sample according to the invention did not.

[0044] A proctor after a 14 days hardening (drying, in this case by 20°C/65% humidity), has a dry density of 985 g/dm³ (19.26 wt.% has been dehydrated). After soaking this proctor for 24 hours completely under water, a mass if found of 1215 g. The proctor has absorbed 23.3 wt.% water.

[0045] Below, results on some samples with respect to compressive strength and the flexural strength are given:

Product Code	UCS (N/mm ²)	Flexural strength(N/mm ²)	Density (g/dm ³)
Alfa-P1-01 (3 days)	0.6	-	1220 (wet)
Alfa-P1-02 (6 days)	0.8	-	-

EP 1 723 089 B9

(continued)

Product Code	UCS (N/mm ²)	Flexural strength(N/mm ²)	Density (g/dm ³)
Alfa-P1-03 (14 days)	1.2	0.3	985 (dry)

[0046] According the Dutch RAW Standard 1995 following minimum requirements for road infrastructure are applicable; in the laboratory 1.5 N/mm² after 28 days; drilled samples in the field 1.2 N/mm² after 28 days.

Example 2: peat/sandy soil

[0047] A mix of 50 vol.% peat : 50 vol.% sandy soil was made. The water content from the peat & the sandy soil were determined separately by taking from both samples of 25 gram and storing these samples in an incubator by a T=110°C during 4 hours. The peat finalized with a weight of 0.5 gram and the sandy soil with 8.1 gram. The peat contains 98 wt.% water and the sandy soil 67.6 wt.% on base of 100 wt.% base material. The water content of the both soils mixed with each other is determined at 82.8 wt.% with a solid partly "organically" fraction of 17.2 wt.%. The incubator is specially developed for this type of investigation and works on warm / heat air which circulates around by convection.

[0048] Peat (wet) 1830.00 gram (Lab 50 vol.% = Volume / mass) (the peat shows in wet condition containing 98 wt.% a density of 1830 g/dm³) and sandy loam (wet) 1050.00 gram (Lab 50 vol.%) (the sandy loam shows in wet condition containing 67.7 wt.% water a density of 1050 g/dm³) are mixed. This makes a peat/loam sample (wet) 2880.00 gram (1440 g/dm³ wet density mixed soils (50:50)). To the bottom material 18.00 additive composition and 864.00 gram (30 wt.%) PFA were added. The mixture obtained was mixed for a few minutes.

[0049] Other samples were made, based on peat (wet) 1830.00 gram (Lab 50 vol.% = Volume / mass) (the peat shows in wet condition containing 98 wt.% a density of 1830 g/dm³) and sandy loam (wet) 1050.00 gram (Lab 50 vol.%) (the sandy loam shows in wet condition containing 67.7 wt.% water a density of 1050 g/dm³) are mixed. This makes a peat/loam sample (wet) 2880.00 gram (1440 g/dm³ wet density mixed soils (50:50)). To the bottom material 18.00 gram additive composition and CEM I 32,5R (Portland Cement) 400.00 gram (13.8 wt.%). This was mixed for a few minutes.

[0050] Below, results on the samples with respect to compressive strength and the flexural strength are given:

Product	UCS (N/mm ²)	Flexural strength(N/mm ²)
with fly ash (7 days)	1.2	-
with cement (7 days) (state of the art construction)	0.4	-
with fly ash (28 days)	2.5	1.0
with cement (28 days) (state of the art construction)	1.6	0.5

Example 3: use of sludge as bottom material in a construction

[0051] In this experiment, laboratory tests on harbor sludge modified with additive composition / OPC / PFA are described. The sludge is obtained from the Jan Rietman sludge depot Boskalis.

[0052] The additive composition according to example 5b is added to the sludge. The additive composition is mixed (T=19 °C) and OPC is added and mixed T = 20.5 °C. After mixing, the mixture is compacted by vibration.

[0053] Procedure sludge sample fresh harbor sludge: decantation of the water 2415 g (sludge contains 64.3% water = 4885 g). The sludge is divided in three portions of 1628.3 g each. The sludge, particularly after decantation, shows a wet density of 1185 g/dm³. Samples are classified as alpha and beta. The alpha sample code HS-sedi 0-2PCEM/CEMI is treated with 0.2 wt.% additive composition and 20 wt.% Cem I 32,5R. Mixed after each additive for 2 minutes and compacted by vibration table. The beta sample code HS-sedi 0-2PCEM/PFA is treated with 0.2 wt.% additive composition and 50 wt.% Powder Coal Fly ash (PFA). Mixed after each additive for 2 minutes and compacted by vibration table.

[0054] All products shows already after 24 hours a fast hardening by increased stiffness. The sludge can be used in order to prepare prefab elements eventual reinforced by a fiber inlay. Strong physical / mechanical behavior can be obtained for construction purposes.

[0055] Below, results on the samples with respect to compressive strength and the flexural strength are given:

EP 1 723 089 B9

Product Code	UCS (N/mm ²)	Flexural strength(N/mm ²)
Alpha (28 d) (prior art)	2.8	1.0
Beta (28 d)	4.8	1.9

5

[0056] The sludge is highly contaminated and classified as dangerous:

10

- mineral oil contaminations of approx. 9600 mg/kg d.s. (d.s.: dry substance)
- zinc 2000 mg/kg d.s.
- lead 600 mg/kg d.s.
- Arsenic 46 mg/kg d.s.
- Chrome 150 mg/kg d.s.
- PCB's and PAH's are available in larger concentrations.

15

The leach out of PCB's and PAH's is greatly diminished when using the construction composition, e.g. when they are present in a construction product.

[0057] It appears that the physical properties of the prior art construction product, based on sludge, a cement additive composition and cement has worse properties than the new construction, based on fly ash but without cement.

20

[0058] Similar good properties were obtained with other additive compositions, like e.g. the one described in example 5a.

Example 4: examples of ashes used

25

[0059] Ash 1 (Fly ash): The fly ash used comprises 21.96 wt.% silicic acid, calculated with respect to SiO₂; 14.6 wt.% aluminum, calculated with respect to Al₂O₃; 0.9 wt.% iron, calculated with respect to Fe₂O₃; 39.75 wt.% calcium, calculated with respect to CaO; 23.54 wt.% free calcium, calculated with respect to CaO; 39.75 wt.% magnesium, calculated with respect to MgO; 6.21 wt.% silicic acid, calculated with respect to SO₃; 1.81 wt.% soda, calculated with respect to MgO; 1.21 wt.% potassium, calculated with respect to K₂O; and 0.02 wt.% chlorine, calculated with respect to Cl. When using a 0.0063mm sieve, about 89.8 wt% passes.

30

[0060] Ash 2 (Bottom ash) (Filter ash HP SDT (F100): This bottom ash contains (when dry) about 40 wt.% SiO₂; 20 wt.% Al₂O₃; 2 wt.% Fe₂O₃; 30 wt.% CaO of which 2 % free CaO; 5 wt.% MgO; <1 wt.% SO₃.

35

[0061] Ash 3 (Fly ash from coal plant; EFA-Füller S-B/F of "Werk Scholven"): This fly ash contains about 53 wt.% SiO₂; 28 wt.% Al₂O₃; 6.8 wt.% Fe₂O₃; 2.7 wt.% CaO (0.07 % free CaO); 1.8 wt.% MgO; 0.7 wt.% SO₃; 3.3 wt.% C; 3.4 wt.% K₂O; 1.2 TiO₂ and 0.4 wt.% P₂O₅.

Example 5: examples of additive compositions used

40

[0062] Below, some additive composition are described, that can be used in the construction composition of the invention.

a)

45

Component	Quantity (relative weights)
NaCl (techn. pure)	30
NH ₄ Cl (techn. pure)	1
AlCl ₃ .6H ₂ O (extra pure)	3
KCl (techn. pure)	16
CaCl ₂ .2H ₂ O (techn. pure)	15
MgCl ₂ .6H ₂ O (techn. pure)	16
MgO (pure)	2
MgHPO ₄ .3H ₂ O (techn. pure)	3
MgSO ₄ .7H ₂ O (techn. pure)	2.5
Na ₂ CO ₃ (techn. pure)	3
Amorphous SiO ₂ (5-40 μm)	1

50

55

[0063] Another example of an additive composition is given below:

b)

	Component	Quantity (relative weights)
5	NaCl (techn. pure)	31
	NH ₄ Cl (techn. pure)	1
	AlCl ₃ ·6H ₂ O (extra pure)	3
	KCl (techn. pure)	16
	CaCl ₂ ·2H ₂ O (techn. pure)	15
10	MgCl ₂ ·6H ₂ O (techn. pure)	16
	MgO (pure)	2
	MgSO ₄ ·7H ₂ O (techn. pure)	3
	Na ₂ CO ₃ (techn. pure)	3
15	Zeolite A4 (Natrolite)	2.5

[0064] The construction composition, comprising these additive compositions, may further comprise some cement, like e.g. Portland cement 52.5 R (Blain 530m²/kg) in an amount of e.g. 0.0-5.0 wt.%, based on the total weight of the construction composition.

20

Claims

1. A construction composition comprising:

25

(1) an ash in an amount of 90.0-99.9 wt.%, based on the total weight of the construction composition, wherein the ash is fly ash or bottom ash;

30

(2) an additive composition in an amount of 0.1-10.0wt.%, based on the total weight of the construction composition, wherein the additive composition comprises a component from group (2a) and a component from group (2b), wherein group (2a) consists of metal chlorides and wherein group (2b) consists of amorphous silica, zeolite and apatite, and wherein group (2a) comprises 70.0-99.0 wt.% of the total additive composition and group (2b) comprises 1.0-30.0 wt.% of the total additive composition, wherein group (2a) comprises at least one component from group (2a1) and a component from group (2a2), wherein group (2a1) consists of sodium chloride, potassium chloride, magnesium chloride, calcium chloride, strontium chloride, barium chloride, and ammonium chloride, and wherein the group (2a2) consists of aluminum chloride; and

35

(3) cement, in an amount of 0.0-5.0 wt.%, based on the total weight of the construction composition.

2. The construction composition according to claim 1, wherein the amount of cement is 0.0 -3.0 wt% of the total construction composition.

40

3. The construction composition according to any one of claims 1-2, wherein the ash composes fly ash.

4. The construction composition according to claim 3, wherein the ash comprises powder coal fly ash.

45

5. The construction composition according to any one of claims 1-4, wherein the metal chloride comprises sodium chloride, and calcium chloride.

6. The construction composition according to any one of claims 1-5, wherein the metal chloride comprises sodium chloride, potassium chloride, magnesium chloride, calcium chloride, ammonium chloride and aluminium chloride.

50

7. The construction composition according to any one of claims 1-6, wherein the additive composition further comprises a component selected from the group consisting of magnesium oxide and calcium oxide.

8. The construction composition according to anyone of claims 1-7, wherein the group (2a) also comprises at least one component from group (2a3), wherein the group (2a3) consists of chlorides of trivalent metals.

55

9. A construction product, comprising a mixture of the construction composition according to any one of claims 1-8, and a bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay.

10. A method for making a construction composition comprising:

- (1) providing an ash, wherein the ash is fly ash or bottom ash;
(2) providing an additive composition, wherein the additive composition comprises a component from group (2a) and a component from group (2b), wherein group (2a) consists of metal chlorides and wherein group (2b) consists of amorphous silica, zeolite and apatite, and wherein group (2a) comprises 70.0-99.0 wt.% of the total additive composition and group (2b) comprises 1.0-30.0 wt.% of the total additive composition, wherein group (2a) comprises at least one component from group (2a1) and a component from group (2a2), wherein group (2a1) consists of sodium chloride, potassium chloride, magnesium chloride, calcium chloride, strontium chloride, barium chloride, and ammonium chloride, and wherein the group (2a2) consists of aluminum chloride; such that the weight of the ash is 90.0-99.9 wt.%, based on the total weight of the construction composition and the weight of the additive composition is 0.1-10.0 wt.%, based on the total weight of the construction composition;
(3) mixing the ash and the additive composition.

11. A method for making a construction product, comprising:

- (1) providing a bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay;
(2) providing a construction composition according to any one of claims 1-8 in an amount such that the weight of the construction composition comprises 10-95 wt.% (wet weight) of the bottom material;
(3) mixing the bottom material and the construction composition;
(4) drying the mixture obtained in step (3).

12. The method according to claim 11, wherein cement is added to the mixture obtained in step (3) in an amount such that the weight of the cement comprises 0.5-10 wt.% (wet weight) of the mixture obtained in step (3).

13. The method according to any one of claims 11 or 12, wherein the weight of the cement comprises 3-5 wt.% (wet weight) of the mixture obtained in step (3).

14. The construction product according to claim 9, having a compressive strength of at least 1.2 N/mm².

15. Use of a construction composition according to any one of claims 1-8 for consolidating bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay.

16. Use of a construction product according to claim 9 for consolidating bottom material selected from the group consisting of soil, sand, sludge, gangue, mud, peat, loam and clay.

Patentansprüche

1. Baustoff enthaltend

- (1) eine Asche in einer Menge von 90,0-99,9 Gew.% auf der Basis des Gesamtgewichtes des Baustoffs, wobei es sich bei der Asche um Flugasche oder Bodenasche handelt;
(2) eine Additivzusammensetzung in einer Menge von 0,1-10,0 Gew.% auf der Basis des Gesamtgewichtes des Baustoffs, wobei die Additivzusammensetzung eine Komponente aus einer Gruppe (2a) und eine Komponente aus einer Gruppe (2b) enthält, die Gruppe (2a) aus Metallchloriden besteht und die Gruppe (2b) aus amorphem Siliciumdioxid, Zeolith und Apatit besteht, die Gruppe (2a) 70,0-99,0 Gew.% der gesamten Additivzusammensetzung umfasst und die Gruppe (2b) 1,0-30,0 Gew.% der gesamten Additivzusammensetzung umfasst und die Gruppe (2a) mindestens eine Komponente aus einer Gruppe (2a1) und eine Komponente aus einer Gruppe (2a2) enthält, wobei die Gruppe (2a1) aus Natriumchlorid, Kaliumchlorid, Magnesiumchlorid, Calciumchlorid, Strontiumchlorid, Bariumchlorid und Ammoniumchlorid besteht und die Gruppe (2a2) aus Aluminiumchlorid besteht, und
(3) Zement in einer Menge von 0,0-5,0 Gew.% auf der Basis des Gesamtgewichtes des Baustoffs.

2. Baustoff nach Anspruch 1, bei dem die Zementmenge 0,0-3,0 Gew.% des gesamten Baustoffs beträgt.

3. Baustoff nach einem der Ansprüche 1-2, bei dem die Asche Flugasche umfasst.

4. Baustoff nach Anspruch 3, bei dem die Asche Kohlenstaubflugasche umfasst.
5. Baustoff nach einem der Ansprüche 1-4, bei dem das Metallchlorid Natriumchlorid und Calciumchlorid umfasst.
- 5 6. Baustoff nach einem der Ansprüche 1-5, bei dem das Metallchlorid Natriumchlorid, Kaliumchlorid, Magnesiumchlorid, Calciumchlorid, Ammoniumchlorid und Aluminiumchlorid umfasst.
7. Baustoff nach einem der Ansprüche 1-6, bei dem die Additivzusammensetzung des Weiteren eine Komponente enthält, die aus der Gruppe ausgewählt ist, die aus Magnesiumoxid und Calciumoxid besteht.
- 10 8. Baustoff nach einem der Ansprüche 1-7, bei dem die Gruppe (2a) auch mindestens eine Komponente aus einer Gruppe (2a3) enthält, wobei die Gruppe (2a3) aus Chloriden von dreiwertigen Metallen besteht.
9. Bauprodukt enthaltend ein Gemisch aus dem Baustoff nach einem der Ansprüche 1-8 und einem Bodenmaterial, das aus der Gruppe ausgewählt ist, die aus Erde, Sand, Schlamm, Ganggestein, Schlick, Torf, Lehm und Ton besteht.
- 15 10. Verfahren zur Herstellung eines Baustoffs mit den folgenden Schritten:
- (1) Vorsehen einer Asche, bei der es sich um Flugasche oder Bodenmasche handelt;
- 20 (2) Vorsehen einer Additivzusammensetzung, die eine Komponente aus einer Gruppe (2a) und eine Komponente aus einer Gruppe (2b) enthält, wobei die Gruppe (2a) aus Metallchloriden besteht und die Gruppe (2b) aus amorphem Siliciumdioxid, Zeolith und Apatit besteht, die Gruppe (2a) 70,0-99,0 Gew.% der gesamten Additivzusammensetzung umfasst und die Gruppe (2b) 1,0-30,0 Gew.% der gesamten Additivzusammensetzung umfasst und die Gruppe (2a) mindestens eine Komponente aus einer Gruppe (2a1) und eine Komponente aus einer Gruppe (2a2) enthält, wobei die Gruppe (2a1) aus Natriumchlorid, Kaliumchlorid, Magnesiumchlorid, Calciumchlorid, Strontiumchlorid, Bariumchlorid und Ammoniumchlorid besteht und die Gruppe (2a2) aus Aluminiumchlorid besteht, so dass das Gewicht der Asche 90,0-99,9 Gew.% auf der Basis des Gesamtgewichtes des Baustoffs beträgt und das Gewicht der Additivzusammensetzung 0,1-10,0 Gew.% auf der Basis des Gesamtgewichtes des Baustoffs beträgt;
- 25 (3) Vermischen der Asche und der Additivzusammensetzung.
- 30 11. Verfahren zur Herstellung eines Baustoffs mit den folgenden Schritten:
- (1) Vorsehen eines Bodenmaterials, das aus der Gruppe ausgewählt ist, die aus Erde, Sand, Schlamm, Ganggestein, Schlick, Torf, Lehm und Ton besteht;
- 35 (2) Vorsehen eines Baustoffs nach einem der Ansprüche 1-8 in einer solchen Menge, dass das Gewicht des Baustoffs 10-95 Gew.% (Nassgewicht) des Bodenmaterials beträgt;
- (3) Mischen des Bodenmaterials und des Baustoffs;
- (4) Trocknen des in Schritt (3) erhaltenen Gemisches.
- 40 12. Verfahren nach Anspruch 11, bei dem dem in Schritt (3) erhaltenen Gemisch Zement in einer solchen Menge zugesetzt wird, dass das Gewicht des Zementes 0,5-10 Gew.% (Nassgewicht) des in Schritt (3) erhaltenen Gemisches beträgt.
- 45 13. Verfahren nach einem der Ansprüche 11 oder 12, bei dem das Gewicht des Zementes 3-5 Gew.% (Nassgewicht) des in Schritt (3) erhaltenen Gemisches beträgt.
14. Bauprodukt nach Anspruch 9, das eine Druckfestigkeit von mindestens 1,2 N/mm² besitzt.
- 50 15. Verwendung eines Baustoffs nach einem der Ansprüche 1-8 zum Konsolidieren von Bodenmaterial, das aus der Gruppe ausgewählt ist, die aus Erde, Sand, Schlamm, Ganggestein, Schlick, Torf, Lehm und Ton besteht.
16. Verwendung eines Bauproduktes nach Anspruch 9 zum Konsolidieren eines Bodenmaterials, das aus der Gruppe ausgewählt ist, die aus Erde, Sand, Schlamm, Ganggestein, Schlick, Torf, Lehm und Ton besteht.
- 55

Revendications

1. Composition pour la construction comprenant :

5 (1) une cendre en une quantité de 90,0 % à 99,9 % en poids, sur la base du poids total de la composition pour la construction, dans laquelle la cendre est une cendre volante ou un mâchefer ;
(2) une composition d'additifs en une quantité de 0,1 % à 10,0 % en poids, sur la base du poids total de la composition pour la construction, dans laquelle la composition d'additifs comprend un composant provenant du groupe (2a) et un composant provenant du groupe (2b), le groupe (2a) étant composé de chlorures métalliques et le groupe (2b) étant composé de silice amorphe, de zéolithe et d'apatite, et le groupe (2a) comprenant 70,0
10 % à 99,0 % en poids de la composition totale d'additifs et le groupe (2b) comprenant 1,0 % à 30,0 % en poids de la composition totale d'additifs et le groupe (2a) comprend au moins un composant provenant du groupe (2a1) et un composant provenant du groupe (2a2), le groupe (2a1) étant le chlorure de sodium, le chlorure de potassium, le chlorure de magnésium, le chlorure de calcium, le chlorure de strontium, le chlorure de barium et le chlorure d'ammonium, et le groupe (2a2) étant le chlorure d'aluminium ; et
15 (3) un ciment en une quantité de 0,0 % à 5,0 % en poids, sur la base du poids total de la composition pour la construction.

20 **2.** Composition pour la construction selon la revendication 1, dans laquelle la quantité de ciment est de 0,0 % à 3,0 % en poids de la composition totale pour la construction.

3. Composition pour la construction selon l'une quelconque des revendications 1 et 2, dans laquelle la cendre comprend une cendre volante.

25 **4.** Composition pour la construction selon la revendication 3, dans laquelle la cendre comprend une cendre volante de houille pulvérulente.

5. Composition pour la construction selon l'une quelconque des revendications 1 à 4, dans laquelle le chlorure métallique comprend le chlorure de sodium et le chlorure de calcium.

30 **6.** Composition pour la construction selon l'une quelconque des revendications 1 à 5, dans laquelle le chlorure métallique comprend le chlorure de sodium, le chlorure de potassium, le chlorure de magnésium, le chlorure de calcium, le chlorure d'ammonium et le chlorure d'aluminium.

35 **7.** Composition pour la construction selon l'une quelconque des revendications 1 à 6, dans laquelle la composition d'additifs comprend en outre un composant choisi dans le groupe constitué par l'oxyde de magnésium et l'oxyde de calcium.

40 **8.** Composition pour la construction selon l'une quelconque des revendications 1 à 7, dans laquelle le groupe (2a) comprend également au moins un composant provenant du groupe (2a3), le groupe (2a3) étant composé de chlorures de métaux trivalents.

45 **9.** Produit pour la construction, comprenant un mélange de la composition pour la construction selon l'une quelconque des revendications 1 à 8, et un matériau de fond choisi dans le groupe constitué par un sol, un sable, une vase, une gangue, une boue, une tourbe, une glaise et une argile.

10. Procédé de préparation d'une composition pour la construction, comprenant :

50 (1) la fourniture d'une cendre, dans laquelle la cendre est une cendre volante ou un mâchefer ;
(2) la fourniture d'une composition d'additifs, dans laquelle la composition d'additifs comprend un composant provenant du groupe (2a) et un composant provenant du groupe (2b), le groupe (2a) étant composé de chlorures métalliques et le groupe (2b) étant composé de silice amorphe, de zéolithe et d'apatite, et le groupe (2a) comprenant 70,0 % à 99,0 % en poids de la composition totale d'additifs et le groupe (2b) comprenant 1,0 % à 30,0 % en poids de la composition totale d'additifs ; et le groupe (2a) comprend au moins un composant
55 provenant du groupe (2a1) et un composant provenant du groupe (2a2), le groupe (2a1) étant le chlorure de sodium, le chlorure de potassium, le chlorure de magnésium, le chlorure de calcium, le chlorure de strontium, le chlorure de barium et le chlorure d'ammonium, et le groupe (2a2) étant le chlorure d'aluminium de sorte que le poids de la cendre est de 90,0 % à 99,9 % en poids, sur la base du poids total de la composition pour la

EP 1 723 089 B9

construction, et que le poids de la composition d'additifs est de 0,1 % à 10,0 % en poids, sur la base du poids total de la composition pour la construction ;

(3) le mélange de la cendre et de la composition d'additifs.

5 **11.** Procédé de préparation d'un produit pour la construction, comprenant :

(1) la fourniture d'un matériau de fond choisi dans le groupe constitué par un sol, un sable, une vase, une gangue, une boue, une tourbe, une glaise et une argile ;

10 (2) la fourniture d'une composition pour la construction selon l'une quelconque des revendications 1 à 8 en une quantité telle que le poids de la composition pour la construction comprend 10 % à 95 % en poids (poids humide) du matériau de fond ;

(3) le mélange du matériau de fond et de la composition pour la construction ;

(4) le séchage du mélange obtenu dans l'étape (3).

15 **12.** Procédé selon la revendication 11, dans lequel du ciment est ajouté au mélange obtenu dans l'étape (3) en une quantité telle que le poids du ciment comprend 0,5 % à 10 % en poids (poids humide) du mélange obtenu dans l'étape (3).

20 **13.** Procédé selon l'une quelconque des revendications 11 ou 12, dans lequel le poids du ciment comprend 3 % à 5 % en poids (poids humide) du mélange obtenu dans l'étape (3).

14. Produit pour la construction selon la revendication 9, présentant une résistance à la compression d'au moins 1,2 N/mm².

25 **15.** Utilisation d'une composition pour la construction selon l'une quelconque des revendications 1 à 8, pour consolider un matériau de fond choisi dans le groupe constitué par un sol, un sable, une vase, une gangue, une boue, une tourbe, une glaise et une argile.

30 **16.** Utilisation d'un produit pour la construction selon la revendication 9, pour consolider un matériau de fond choisi dans le groupe constitué par un sol, un sable, une vase, une gangue, une boue, une tourbe, une glaise et une argile.

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 487283 A [0003] [0004]
- WO 0248067 A [0003] [0012] [0019]
- US 5951751 A [0004]
- RU 2101251 C1 [0005]
- GB 1592001 A [0006]
- GB 1069657 A [0007]

Non-patent literature cited in the description

- Centrum voor Regelgeving en Onderzoek in Grond.
Water- en Wegenbouw en de Verkeerstechniek,
64-68 [0042]