



(11) **EP 1 739 110 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Description Paragraph(s) 90, 109, 120
Claims EN 3

(51) Int Cl.:
C08F 297/08 (2006.01) C08L 23/08 (2006.01)

(48) Corrigendum issued on:
15.09.2010 Bulletin 2010/37

(45) Date of publication and mention
of the grant of the patent:
01.04.2009 Bulletin 2009/14

(21) Application number: **05014216.5**

(22) Date of filing: **30.06.2005**

(54) **Polyethylene composition of improved processability**

Polyethylenzusammensetzung mit verbesserter Verarbeitbarkeit

Composition de polyéthylène avec processabilité améliorée

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU MC NL PL PT RO SE SI SK TR**

- **Eklind, Hans**
444 45 Stenungsund (SE)
- **Helland, Irene**
3912 Porsgrunn (NO)

(43) Date of publication of application:
03.01.2007 Bulletin 2007/01

(74) Representative: **Kador & Partner**
Corneliusstrasse 15
80469 München (DE)

(73) Proprietor: **Borealis Technology Oy**
06101 Porvoo (FI)

(56) References cited:
EP-A- 1 267 189 EP-A- 1 333 044
EP-A- 1 378 528 EP-A- 1 460 105
WO-A-97/47682 US-A1- 2002 045 711
US-B1- 6 185 349

(72) Inventors:
• **Carlsson, Roger**
423 70 Säve (SE)
• **Van Marion, Remko**
1100 Wien (AT)

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 739 110 B9

Description

[0001] The present invention relates to a multimodal polyethylene composition having an improved balance of processability and mechanical properties, and to articles comprising the polyethylene composition, in particular wires/cables as well as polymeric films.

[0002] For linear low density polyethylene (LLDPE), there is a broad range of possible applications such as for wire and cable applications (in particular as a layer material) and film applications (e.g. blown films, cast films). Linear low density polyethylene has essentially a linear backbone with only short chain branches. Since it provides a good balance of processability and mechanical properties, it has become an alternative to low density polyethylene (LDPE) prepared in a high pressure process and having a high number of long chain branches.

[0003] For instance cables, such as power or communication cables, usually comprise an inner core which comprises a conducting element, such as a metal wire or a glass fibre, and one or more layers for shielding, protecting and insulating purposes. The outermost of these layers having mainly protective purpose is usually referred to as outer sheath or outer jacket.

[0004] It is known to produce outermost protective sheath layers from polymer compositions comprising mainly polyolefins, in particular polyethylenes, e.g. LDPE and LLDPE. The diverse application fields for the various kinds of cables make it necessary that the outer jacket meets a number of requirements which at least partly may be contradictory to each other.

[0005] When preparing cable layers, e.g. jacketing layers, or films by extrusion, there are several parameters which are relevant for processability. These include output rate, melt pressure, extruder motor power and surface finish. For a specific extrusion temperature, it is desired to keep melt pressure as low as possible, thereby lowering the stress exerted on the extruder equipment. Furthermore, a material of low melt pressure would enable higher output rate. From an economical point of view, it is desired to have high output rate at low extruder motor power.

[0006] Particularly in case of jacketing layers and film applications also surface finish is another relevant property of low density polyethylene materials. It was known to lower melt flow rate for improving surface smoothness. However, low MFR values normally have a detrimental effect on processability, e.g. on melt pressure and output rate.

[0007] For improving processability, it was suggested to add low density polyethylene, prepared in a high pressure process, to linear low density polyethylene. However, this might adversely affect mechanical properties including heat deformation.

[0008] It is of crucial importance that an improvement in processability is not achieved on the expense of mechanical properties. Relevant mechanical properties that could be mentioned are e.g. tensile strength and environmental stress cracking resistance. Thus, when seeking for solutions to improve processability, these properties should be improved as well or at least be maintained on a sufficiently high level.

[0009] As already discussed above, low density polyethylene as well as linear low density polyethylene are frequently used e.g. as jacketing materials for telecommunication cables. To protect the copper or optical fibre core from water intrusion, filling compounds are normally used. Thus, the polymeric jacketing material should have high compatibility with filling compounds and the jacket should still have excellent mechanical properties after exposure to filling compounds. Commonly filling compounds consist of petroleum jellies.

[0010] Another aspect that has to be taken into account for wire and cable applications as well as film applications is shrinkage behaviour. It is desired that the polymeric compositions show low shrinkage.

[0011] In EP 0907682, a bimodal polyethylene composition is disclosed which can be used as a jacketing material for cables, in particular telecommunication cables. The material disclosed in the examples have a molecular weight distribution below 15.

[0012] It is an object of the present invention to provide a polyethylene composition which meets the requirements and overcomes the problems outlined above.

[0013] In particular, it has now surprisingly been found that the present combination of low density and broad molecular weight distribution provides a polyethylene composition which has a very advantageous processability-mechanical property balance for many end applications including wire and cable and film applications.

[0014] The polyethylene composition of the invention comprises a base resin comprising at least two different ethylene polymer fractions, namely a first fraction (i) of an ethylene homo- or copolymer and a second fraction (ii) of an ethylene copolymer, wherein

- the first fraction (i) has a lower weight average molecular weight than the second fraction (ii);
- the base resin: has a density of less than 0.940 g/cm³;
- the base resin has a shear thinning index $_{2.7/210}$ of at least 25; and

- the base resin has a flow rate ratio $FRR_{21/2}$ of at least 65.

[0015] The broad MWD, which contributes very desirably to the processability and provides feasible means for further tailoring the mechanical and/or processing properties of the polymer depending on the needs desired for the end-use application, can be measured by SEC (also known as GPC), whereby it is expressed as M_w/M_n , or by a rheological measurement, like Shear Thinning Index (SHI) - measurement, which is a very sensitive indicator of the MWD. Moreover, further indicators of the broad MWD of the invention are the melt flow rate (MFR) and the melt flow rate ratio (FRR) between two MFR's measured at different loadings. All these measurements are known and further defined below under "Definitions and Determination Methods".

[0016] Furthermore, by providing two fractions which differ in weight average molecular weight, a multimodal base resin is obtained.

[0017] Usually, a polyethylene composition comprising at least two polyethylene fractions, which have been produced under different polymerisation conditions resulting in different (weight average) molecular weights for the fractions, is referred to as "multimodal". The prefix "multi" relates to the number of different polymer fractions the composition is consisting of. Thus, for example, a multimodal composition consisting of two fractions only is called "bimodal".

[0018] The form of the molecular weight distribution curve, i.e. the appearance of the graph of the polymer weight fraction as function of its molecular weight, of such a multimodal polyethylene will show two or more maxima or at least be distinctly broadened in comparison with the curves for the individual fractions.

[0019] For example, if a polymer is produced in a sequential multistage process, utilising reactors coupled in series and using different conditions in each reactor, or when a polymer is produced in a process comprising a single stage in which two or more different catalysts are used, the polymer fractions produced in the different reactors, or by the different catalysts, respectively, will each have their own molecular weight distribution and weight average molecular weight. When the molecular weight distribution curve of such a polymer is recorded, the individual curves from these fractions are superimposed into the molecular weight distribution curve for the total resulting polymer product, usually yielding a curve with two or more distinct maxima.

[0020] The first fraction (i) of the polyethylene composition of the invention is either an ethylene homo- or copolymer. Within the context of the present invention, the homopolymer is defined as having a density 0.965 g/cm^3 or more.

[0021] When using a copolymer, it is preferably obtained by copolymerization of ethylene with at least one C_3 to C_{20} alpha-olefin comonomer. Preferred comonomers are propylene, 1-butene, 1-hexene, 1-octene or mixtures thereof.

[0022] The second fraction (ii) of the present invention is an ethylene copolymer. Preferred comonomers are those already mentioned above.

[0023] Accordingly, the fractions (i) and (ii) can also be multimodal with respect to the comonomer distribution. Preferably the comonomer content of the base resin is up to 5 mol-%. More preferably the low molecular weight fraction (i) has a comonomer content of 0.05 to 4.0 mol-%. Further preferably, the total comonomer content of the base resin is 1.0 to 5.0 mol-%.

[0024] The polyethylene composition of the invention comprises a base resin comprising at least

(i) a first fraction which is an ethylene homo- or copolymer, and

(ii) a second fraction which is an ethylene copolymer,

wherein the first fraction (i) has a lower weight average molecular weight than the second fraction (ii), and the base resin has a density of less than 0.940 g/cm^3 , a shear thinning index $SHI_{2.7/210}$ of at least 25 and a flow rate ratio $FRR_{21/2}$ of at least 65.

[0025] The base resin may further comprises a third fraction (iii) which is an ethylene homo- or copolymer having a weight average molecular weight which is higher than the weight average molecular weight of the first fraction (i) and is different from the weight average molecular weight of the second fraction (ii).

[0026] In a preferred embodiment, the third fraction (iii) has a higher weight average molecular weight than the second fraction (ii).

[0027] In addition to tailoring the fractions (i) and (ii), by introducing one or more further different polyethylene fraction (s) is one very feasible way of achieving the broad MWD.

[0028] In the composition of the present invention, the base resin has a density of less than 0.940 g/cm^3 , preferably a density of less than 0.935 g/cm^3 . Preferably, the base resin has a density of more than 0.910 g/cm^3 , more preferably more than 0.920 g/cm^3 , and even more preferably more than 0.922 g/cm^3 .

[0029] Furthermore, the base resin of the composition of the invention has a shear thinning index $SHI_{2.7/210}$ of at least 25. The SHI is the ratio of the viscosity of the polyethylene composition at different shear stresses. In the present invention, the shear stresses at 2.7 kPa and 210 kPa are used for calculating the $SHI_{2.7/210}$ which may serve as a measure of the broadness of the molecular weight distribution.

[0030] Preferably, in the inventive composition the $SHI_{2.27/210}$ of the base resin is at least 30, more preferably at least 40. The upper limit is typically less than 100.

[0031] Preferably, in the inventive composition the base resin has a flow rate ratio $FRR_{21/2}$, which is the ratio of melt flow rate $MFR_{2.16kg/190^{\circ}C}$ to melt flow rate $MFR_{2.16kg/190^{\circ}C}$ of at least 65. Flow rate ratio can be used as an estimation of molecular weight distribution, wherein high values indicate a broad molecular weight distribution. More preferably, the base resin has a flow rate ratio $FRR_{21/2}$ of more than 70, more than 80, more than 90, more than 95, or more than 100. Preferably, the base resin has a flow rate ratio $FRR_{21/2}$ of less than 200, more preferably less than 170.

[0032] Preferred $FRR_{21/2}$ ranges for instance for wire and cable applications and film applications are e.g. from 70 to 160. For wire and cable applications the lower limit of $FRR_{21/2}$ is preferably 100.

[0033] When present in the inventive composition, the third fraction (iii) has a weight average molecular weight of more than 90000, the upper limit being typically up to 2000000, typically up to 1000000, preferably 120000 to 600000, e.g. or more than 200000. In a preferred embodiment, the third fraction (iii) has a higher weight average molecular weight than the second fraction (ii).

[0034] When present in the inventive composition, the third fraction (iii) is preferably a homopolymer, whereby the term "homopolymer" is as defined above. In case the third fraction (iii) is a copolymer, it is preferably obtained by copolymerization of ethylene with at least one comonomer selected from C_3 to C_{20} alpha-olefins. Preferred alpha-olefins are those already mentioned above.

[0035] When present in the inventive composition, the third fraction (iii) can be blended with the first fraction (i). As will be explained below in greater detail, the blend can be obtained by mechanical blending or reactor blending, preferably preparing one of these fractions in a first reactor, transferring the reaction product to a second reactor and preparing the other fraction in the presence of the fraction prepared first.

[0036] The fraction (i) of the composition (1) and composition (2), has a density within the range of 0.900 to 0.970 g/cm³. Preferably, the density of fraction (i) is higher than 0.920 g/cm³, more preferably higher than 0.931 g/cm³, even more preferably higher than 0.935 g/cm³, or at least 0.940 g/cm³. Preferably, the density of the fraction (i) is less than 0.955 g/cm³, or 0.952 g/cm³ or less.

[0037] Preferably, the optional blend of the first fraction (i) and the third fraction (iii) of the inventive composition, has a density within the range of 0.900 to 0.970 g/cm³. Preferably, the density of the blend of the fractions (i) and (iii) is higher than 0.920 g/cm³, more preferably higher than 0.931 g/cm³, even more preferably higher than 0.935 g/cm³, or at least 0.940 g/cm³. Preferably, the density of the blend of fractions (i) and (iii) is less than 0.955 g/cm³, or 0.952 g/cm³ or less.

[0038] For the inventive composition, the fraction (i) or preferably, when present, the blend of the first fraction (i) and the third fraction (iii), typically has a melt flow rate $MFR_{2.16kg/90^{\circ}C}$ of more than 20 g/10 min. More preferably, $MFR_{2.16kg/190^{\circ}C}$ of the fraction (i) or of the blend of fractions (i) and (iii) is higher than 50, higher than 200, higher than 250, or even higher than 300 g/10 min. If the polyethylene composition shall be used for wire and cable applications, e.g. as a jacketing material, preferred ranges of $MFR_{2.16kg/190^{\circ}C}$ for both the fraction (i) and said blend of (i) and (iii) are 100 to 600, 200 to 500, 300 to 400, or 300 to 350 g/10 min. If the polyethylene composition shall be used for the preparation of films, preferred ranges of $MFR_{2.16kg/90^{\circ}C}$ for both the fraction (i) and said blend of (i) and (iii) are 20 to 700, 50 to 500, 250 to 350, or 300 to 350 g/10 min.

[0039] Preferably, the base resin of the inventive composition has a melt flow rate $MFR_{2.16kg/190^{\circ}C}$ of more than 40 g/10 min. More preferably, the melt flow rate $MFR_{2.16kg/190^{\circ}C}$ of the base resin is higher than 60 g/10 min, higher than 85 g/10 min, higher than 90 g/10 min. Preferred $MFR_{2.16kg/190^{\circ}C}$ ranges for wire and cable applications and film applications are e.g. 90 to 115 g/10 min or 90 to 110 g/10 min. The upper limit is preferably less than 150 g/10 min.

[0040] Typically, the base resin has a molecular weight distribution M_w/M_n of more than 10, preferably 15, more preferably more than 22, even more preferably more than 30. Preferably, the molecular weight distribution is less than 50, more preferably less than 45.

[0041] The base resin comprises at least fractions (i) and (ii) as defined above, preferably at least fractions (i), (ii) and (iii) as defined above. Thus, the inventive composition preferably comprises a third fraction (iii) as defined above. The amount of the third fraction (iii), if present, is 10 wt% or less, preferably 0.5 to 5 wt%, based on the total weight of the base resin. In wire and cable applications, it can be present even in amounts of 2.5 to 3.3 wt% of the total amount of the base resin depending on the desired wire or cable application.

[0042] Preferably fraction (i) is a copolymer.

[0043] Preferably, the low molecular weight fraction (i) is present in an amount of 40 to 70 wt%, preferably 40 to 65 wt%, more preferably 40 to 60 wt%, based on the total weight of the base resin. Preferably, the high molecular weight fraction (ii) is present in an amount of 60 to 30 wt%, preferable 60 to 45 wt%, more preferably 60 to 40 wt%, based on the total weight of the base resin.

[0044] Preferably, the base resin as defined above has a melt flow rate $MFR_{2.16kg/190^{\circ}C}$ of at least 0.05 g/10 min, more than 0.15 g/10 min, more than 0.2 g/10 min, or more than 0.5 g/10 min. As an upper limit, a $MFR_{2.16kg/190^{\circ}C}$ value of 4.0 g/10 min is preferably chosen. For wire and cable applications, preferred $MFR_{2.16kg/190^{\circ}C}$ ranges are e.g. 0.1 to

4.0 g/10 min, 0.3 to 2.0 g/10 min, or 0.6 to 1.5 g/10 min. For film applications, preferred $MFR_{2.16\text{kg}/190^\circ\text{C}}$ ranges are e.g. 0.05 to 4.0 g/10 min, 0.15 to 2.0 g/10 min, or 0.2 to 0.5 g/10 min.

[0045] Preferably, the base resin as defined above has a weight average molecular weight of up to 350 000, suitably 90000 to 250000, more preferably 120000 to 200000.

[0046] In case a third fraction (iii) is present, its weight average molecular weight is preferably higher than the weight average molecular weight of the second fraction (ii). Preferably, the second fraction (ii) has a melt flow rate $MFR_{2.16\text{kg}/190^\circ\text{C}}$ between 0.01 to 1 g/10 min.

[0047] Preferably, the second fraction (ii) has a density between 0.880 to 0.930 g/cm³. Even more preferably, the density of the second fraction is within the range of 0.890 to 0.910 g/cm³.

[0048] The composition of the invention covers the base resin as such or any blends with further components including other polymer components for forming a polymer blend as well as additives. Thus e.g. usual additives for utilization with polyolefins, such as pigments (for example carbon black), stabilizers (antioxidant agents), antacids and/or anti-UVs, antistatic agents, polymers as carriers for additives or as modification of the performance of e.g. extrudability and utilization agents (such as processing aid agents) may be present in the polyethylene composition. Preferably, the amount of these additives is 10 wt% or below, further preferred 8 wt% or below, of the total composition. The additives can be added as such or in master batches as known in the field.

[0049] In one advantageous embodiment, the present composition comprising the base resin has the given SHI range or any of the preferred SHI ranges as defined above for the base resin.

[0050] In another advantageous embodiment, the definitions given above for the base resin (including any optional features and preferable embodiments of the base resin) apply also for the polyethylene composition of the invention comprising the base resin.

[0051] The present invention also provides a process for preparing the polyethylene compositions as discussed above, comprising the following steps:

(a) polymerizing ethylene, optionally with at least one alpha-olefin comonomer, to obtain a first polyethylene homo- or copolymer fraction (i), and

(b) polymerizing ethylene with at least one alpha-olefin comonomer to obtain a second polyethylene copolymer fraction (ii),

wherein fractions (i) and (ii) are blended to obtain the base resin.

[0052] The process can be used to prepare the polyethylene composition of the present invention.

[0053] Blending of the fractions (i) and (ii) can be effected by mechanical blending or reactor blending in a multistage process, preferably preparing one of these fractions in a first reactor, transferring the reaction product to a second reactor and preparing the other fraction in the presence of the fraction prepared first.

[0054] Preferably, the base resin is produced in a multistage process wherein the process steps can be carried out in the sequence (a)→(b) or (b)→(a).

[0055] A multistage process is defined to be a polymerisation process in which a polymer comprising two or more fractions is produced by producing each or at least two polymer fraction(s) in a separate reaction stage, usually with different reaction conditions in each stage, in the presence of the reaction product of the previous stage which comprises a polymerisation catalyst.

[0056] Accordingly, it is preferred that fraction (i) and (ii) of the polyethylene composition are produced in different stages of a multistage process.

[0057] Preferably, the multistage process comprises at least one gas phase stage in which, preferably, fraction (ii) is produced. Further preferred, fraction (ii) is produced in a subsequent stage in the presence of fraction (i) which has been produced in a previous stage.

[0058] For example, in the production of, say, a bimodal polyethylene, a first ethylene polymer fraction is produced in a first reactor under certain conditions with respect to hydrogen-gas concentration, temperature, pressure, and so forth. After the polymerisation in the first reactor, the polymer fraction including the catalyst is separated from the reaction mixture and transferred to a second reactor, where further polymerisation takes place under other conditions.

[0059] It is previously known to produce multimodal, in particular bimodal, olefin polymers, such as multimodal polyethylene, in a multistage process comprising two or more reactors connected in series. As instance of this prior art, mention may be made of EP 517 868, which is hereby incorporated by way of reference in its entirety, including all its preferred embodiments as described therein, as a preferred multistage process for the production of the polyethylene composition according to the invention.

[0060] Preferably, the main polymerisation stages of the multistage process are such as described in EP 517 868, i.e. the production of fractions (i) and (ii) is carried out as a combination of slurry polymerisation for fraction (i) and gas-phase polymerisation for fraction (ii). The slurry polymerisation is preferably performed in a so-called loop reactor. Further

preferred, the slurry polymerisation stage preceeds the gas phase stage.

[0061] The resulting end product consists of an intimate mixture of the polymers from the two reactors, the different molecular-weight-distribution curves of these polymers together forming a molecular-weight-distribution curve having a broad maximum or at least two maxima, i.e. the end product is at least a bimodal polymer mixture.

[0062] In the preferred embodiment of the polymerisation in a loop reactor followed by a gas-phase reactor, the polymerisation temperature in the loop reactor preferably is 40 to 110°C, preferably between 70 to 110°C and the temperature in the gas-phase reactor is typically 50 to 130°C, preferably 60 to 115°C.

[0063] A chain-transfer agent, preferably hydrogen, is added as required to the reactors, and preferably 100 to 800 moles of H₂/kmoles of ethylene are added to the reactor, when the LMW fraction is produced in this reactor, and 0 to 50 moles of H₂/kmoles of ethylene are added to the gas phase reactor when this reactor is producing the HMW fraction.

[0064] Preferably, the comonomer is added to the low molecular weight fraction (i) mole ratio of α -olefin to ethylene being in the range of 0.1:1 to 1:1. More preferred is 0,3:1 to 0,8:1. The high molecular weight fraction (ii) is an ethylene copolymer. Preferred comonomers are those already mentioned above for the first fraction. Preferably, mole ratio of α -olefin to ethylene is in the range of 0.1:1 to 1:1. More preferred is 0,3:1 to 0,8:1.

[0065] As polymerisation catalysts, in principle any catalyst which is suitable for producing the present base resin of the invention can be used, including Ziegler-Natta, single site (including metallocene and non metallocene catalysts) or chromium catalysts, preferably Ziegler-Natta or metallocene catalysts.

[0066] The base resin of the polyethylene composition according to the invention preferably is produced using a Ziegler-Natta catalyst comprising a group 4 metal compound (of Periodic Table, IUPAC nomenclature of inorganic chemistry, 1989), preferably a Ti-compound, and a halogen-containing magnesium compound.

[0067] In one preferable embodiment, the catalyst is a non-silica supported catalyst, i.e. the active components are not supported to an external silica support. Preferably, the support material of the catalyst is a Mg-based support material.

[0068] Examples of such preferred Ziegler-Natta catalysts are described in EP 0 810 235. The content of this document in its entirety is incorporated herein by reference, in particular concerning the general and all preferred embodiments of the catalysts described therein as well as the methods for the production of the catalysts.

[0069] In another embodiment, the used Ziegler-Natta catalyst is a silica supported catalyst e.g. described in EP 0 688 794 A1. The content of this document in its entirety is incorporated herein by reference, in particular concerning the general and all preferred embodiments of the catalysts described therein as well as the methods for the production of the catalysts.

[0070] Preferably, the multistage process of the present invention further comprises a polymerisation step (c), in any order, for the preparation of the ethylene homo- or copolymer fraction (iii). Preferably step (c) is carried out first, preferably in the presence of a Ziegler-Natta catalyst, followed by reaction steps (a) and (b), and the split between step (c) and reaction steps (a) and (b) is from 0.1:99.9 to 10:90. Alternatively, as mentioned above, mechanical blending can also be used for blending the fraction (iii).

[0071] More preferably, the split between polymerization step (c) and reaction steps (a) and (b) is from 0.5 : 99.5 to 7 : 93.

[0072] The polymer is preferably an ethylene homopolymer, preferably a high density polyethylene (HDPE). However, it is also possible to use an ethylene copolymer, preferably obtained by copolymerization of ethylene with at least one C₃ to C₂₀ α -olefin comonomer. Preferred C₃ to C₂₀ α -olefin comonomers are those already mentioned above with regard to the first and second base resin fraction.

[0073] At the polymerisation step (c), preferably all of the catalyst is charged into a loop reactor and the polymerisation is performed as a slurry polymerisation.

[0074] For the polymerization step (c), the ratio of H₂ feed (in g/h) to C₂ feed (in g/h) is preferably in the range of 0 to 0.005.

[0075] For the process comprising a prepolymerization step (c), it is again preferred to use the Ziegler-Natta catalysts described above.

[0076] In case of a multimodal process, the product obtained in the last step, e.g. step (b), is a mixture of the products obtained from the previous steps. The above given definitions for the fractions, e.g. for fraction (ii) can in that case be calculated using the calculation methods described in the literature.

[0077] The present invention also provides an article comprising the polyethylene composition as described above. Preferably, the article is a wire or cable comprising at least one layer which comprises the polyethylene composition of the invention. The layer is preferably a jacketing layer. According to another preferred embodiment, the article is a film comprising at least one layer which comprises the polyethylene composition of the invention.

[0078] The composition for the outer sheath layer of the cable preferably is produced in a process comprising a compounding step, wherein the composition of the base resin, i.e. the blend, which is typically obtained as a base resin powder from the reactor, is extruded in an extruder and then pelletised to polymer pellets in a manner known in the art, and finally further processed, e.g. extruded in a known manner to form a wire or cable layer.

[0079] Optionally, additives or other polymer components can be added to the composition during the compounding step, e.g. during the extrusion step for forming the pellets and/or during the extrusion step for forming a layer, such as a cable or film layer.

[0080] The cables of the invention in addition to the outermost sheath layer comprise at least one or more power or information conducting elements.

[0081] Preferably, the polyethylene composition is used as the cable sheathing composition for producing outer sheath layers for cables, including power cables as well as communication cables. Amongst power cables, mention may be made of high-voltage cables, medium voltage cables, and low voltage cables. Amongst communication cables, mention may be made of pair cables, coaxial cables and optical cables.

Definitions and Determination methods

[0082] The terms and determination methods for the measured properties used for defining the invention apply generally both for the description part above and for the examples and claims below, unless otherwise stated:

a) Molecular weight/molecular weight distribution

The molecular weight averages and molecular weight distribution were measured on a Waters Alliance GPCV2000 SEC instrument with on-line viscometer at 140 degrees Celsius using 1,2,4-trichlorobenzene (TCB) stabilized with 2,6-di-tert-butyl-4-methylphenol (BHT) as an eluent. A set of two mixed beds and one 10^7 Å TSK-Gel columns from TosoHaas was used and the system was calibrated with NMWD polystyrene standards (from Polymer laboratories). The analyses were carried out following the principles of standard test methods ISO 16014-2:2003 and ISO 16014-4:2003.

b) Density

Density is measured according to ISO 1183D.

c) Melt Flow Rate/Flow Rate Ratio

The melt flow rate (MFR) is determined according to ISO 1133 and is indicated in g/10 min. The MFR is an indication of the flowability, and hence the processability, of the polymer. The higher the melt flow rate, the lower the viscosity of the polymer. The MFR is determined at 190°C and may be determined at different loadings such as 2.16 kg (MFR₂), 5 kg (MFR₅) or 21.6 kg (MFR₂₁).

The quantity FRR (flow rate ratio) is an indication of molecular weight distribution and denotes the ratio of flow rates at different loadings. Thus, FRR_{21/2} denotes the value of MFR₂₁/MFR₂.

d) Rheological parameters

Rheological parameters such as Shear Thinning Index SHI and Viscosity are determined by using a rheometer, preferably a Rheometrics Phisica MCR 300 Rheometer. The definition and measurement conditions are described in detail on page 8 line 29 to page 11, line 25 of WO 00/22040.

Shear thinning index (SHI), which is correlating with MWD and is independent of M_w , was calculated according to Heino ("Rheological characterization of polyethylene fractions" Heino, E.L., Lehtinen, A., Tanner J., Seppälä, J., Neste Oy, Porvoo, Finland, Theor. Appl. Rheol., Proc. Int. Congr. Rheol, 11th (1992), 1, 360-362, and "The influence of molecular structure on some rheological properties of polyethylene", Heino, E.L., Borealis Polymers Oy, Porvoo, Finland, Annual Transactions of the Nordic Rheology Society, 1995.)

SHI value is obtained by calculating the complex viscosities $\eta_{a(1)}$ and $\eta_{a(100)}$ at a constant shear stress of 1 kPa and 100 kPa, respectively. The shear thinning index SHI_(1/100) is defined as the ratio of the two viscosities $\eta_{a(1)}$ and $\eta_{a(100)}$. Correspondingly, the SHI_(2.7/210) is defined as the ratio of the two viscosities $\eta_{a(2.7)}$ and $\eta_{a(210)}$.

e) Environmental stress cracking resistance (ESCR)

ESCR was evaluated according to CTL: ISO 6259, with a notch applied according to ASTM F 1473. using CTL with different constant stress of 2, 3 and 4 MPa. A 10% Igepal solution was used as medium.

f) Cable samples for the evaluation are extruded as follows.

Conductor	3.0 mm Solid Al conductor
Wall thickness	1.0 mm
Temperature, die	+210°C
Distance between die and waterbath	35cm
Temperature, water bath	+23°C
Line velocity	75m/min
Die type	Semi-tube
Nipple	3.65 mm
Die	5.9 mm
Screw design	Elise

g) Shrinkage

The shrinkage in percent is measured after 24h in constant temperature (+23°C) as well as after 24h at a temperature of +100°C. Cable samples measuring approximately 40cm are measured. Conveniently, the samples is so marked that the measurement after the conditioning can be carried out at the same point on the cable sample.

Should the sample be found to shrink during measurement, marks of about 40cm first have to be made. Then the length is cut and remeasured. Double samples are taken of each cable that is to be analysed. The samples are placed in the room with constant temperature for 24h, whereupon they are measured, and shrinkage value in percent are calculated. All the samples are then placed on a talcum bed at 100°C for 24h. The samples are measured, and the total shrinkage in percent is calculated on the basis of the initial length.

h) Filler absorption

Filler absorption was measured on plaques, quenched in cool water according to the method as described below under "Compatibility with filling compounds".

i) Mechanical properties

Elongation at break and tensile strength at break were measured according to 22542/ISO 527-2/1A,B, either on plaques or on cables having a jacket of 1 mm in thickness applied on a 3 mm in diameter aluminium conductor.

j) Heat deformation

This was tested according to EN 60811-3-1:1995. This was tested on cables 3mm core and 1mm jacketing layer extruded directly on the conductor. This property is directly proportional to the density. In this test we have used cool waterbath during extrusion, therefore reproducing the worst case. When the molten plastics meet cold water the density is lower than if the crystallization takes place during slow cooling, see table for results. The indentation at 115°C after 4h is recorded and reported as how many % the egg is penetrating the sample thickness.

k) Melting temperature T_m , crystallization temperature T_{cr} , and the degree of crystallinity: measured with Mettler TA820 differential scanning calorimetry (DSC) on 3 ± 0.5 mg samples. Both crystallization and melting curves were obtained during 10°C/min cooling and heating scans between -10 - 200°C. Melting and crystallization temperatures were taken as the peaks of endotherms and exotherms. The degree of crystallinity was calculated by comparison with heat of fusion of a perfectly crystalline polyethylene, i.e. 290 J/g.

l) Comonomer content (wt%) can be determined in a known manner based on Fourier transform infrared spectroscopy (FTIR) determination calibrated with, C^{13} -NMR.

Tested Compositions

[0083] The following polymerisation procedure and catalyst were used in all the examples of the invention unless otherwise stated.

[0084] All the examples were produced in pilot plant multistage reaction comprising an optional first stage in slurry in a 50 dm³ loop reactor as the polymerization step (c) for producing the third fraction (iii), then followed by transferring the slurry to a 500 dm³ loop reactor wherein polymerisation step (a) was effected in slurry to produce the first fraction (i) and a polymerization step (b) in a gas phase reactor in the presence of the product from the second loop reactor containing optionally the product from step (c) to produce the comonomer containing the second fraction (ii). The reaction conditions are given in the tables below.

Examples 1-5

[0085] Two polyethylene compositions according to the present invention (Ex1 and Ex2) and three comparative polyethylene compositions have been prepared (CompEx 1-3) as described. The polymerisation steps (a) and (b) where effected to obtain bimodal examples, i.e. the step (c) was not included in examples 1-5.

[0086] The catalyst used in Ex 1-2 and CompEx 1-2 was a Ziegler-Natta type catalyst which corresponds to the one used in EP 6887794, Example 3.

[0087] All compositions are bimodal. Further information about each composition is given below:

Table 1: Properties of Ex 1-2 and CompEx 1-2

	Ex. 1	Ex.2	CompEx 1	CompEx 2
The final composition with additives given below				
Density (kg/cm ³)	921.8	924.4	923	923
MFR2 (g/10 min)	0.87	0.81	0.4	0.2
MFR21 (g/10 min)	87	96	40	22

(continued)

	Ex. 1	Ex.2	CompEx 1	CompEx 2
The final composition with additives given below				
FRR21/2	100	118	100	110
The step (a): Loop Conditions and the product of step (a)				
Temperature (°C)	85	85		
Pressure (bar)	60	60		
H ₂ /C ₂ ratio (mol/kmol)	282	275	330	350
C ₄ /C ₂ ratio (mol/kmol)	147	142	670	630
MFR2 (g/10 min)	520	520	300	300
Density (kg/cm ³)	952	951	951	945
Split	50	54	43	42
The step (b): Gasphase Conditions and product obtained after step (b)				
Temperature (°C)	80	80		
Pressure (bar)	20	20		
H ₂ /C ₂ ratio (mol/kmol)	8	8	10	3
C ₄ /C ₂ ratio (mol/kmol)	747	695	650	600
MFR2 (g/10 min)	0.85	0.7-1		
Density (kg/cm ³)	892	893	901	907
Split	50	46	57	58

[0088] As additives, 2400 ppm Irganox B225 and 1500 ppm calcium stearate was used.

Table 2: Molecular weight and molecular weight distribution of Ex 1-2

	Ex 1	Ex 2
Mw	149000	139000
Mn	9040	8070
Mz	845000	796000
MWD	16.5	17.3

[0089] In Ex 1 and 2, the melt flow rate MFR_{21.6kg/190°C} is significantly higher than in the comparative examples. Furthermore, as indicated by FRR21/2 and MWD values, the inventive examples have a broad molecular weight distribution.

[0090] CompEx 3 is a linear low density polyethylene (LLDPE) including 15 wt% low density polyethylene to improve processability. Properties of the blend are given in Table 3:

Table 3: Properties of CompEx 3

	Comp.Ex. 3
Density (g/cm ³)	0.920
MFR2 (g/10 min)	0.8
MFR21 (g/10min)	79

EP 1 739 110 B9

(continued)

	Comp.Ex. 3
FRR _{21/2}	65

[0091] In the following, relevant processing properties and mechanical properties of these compositions will be provided and discussed.

Processability

[0092] As already discussed above, the processability of a jacketing material includes several parameters e.g. surface finish, output, melt pressure, and extruder motor power. It is important that the processing window is wide since there are many different applications for a jacketing material.

[0093] To evaluate the processability, the compositions were extruded at a cable line. 1mm thick jacket were applied on a 3mm in diameter aluminum conductor. To stress the material in terms of shrinkage performance the temperature setting was not optimal. The conductor was not preheated, the melt temperature was 210°C and the cooling bath temperature was 23°C. The line speed was 75m/min.

Surface finish

[0094] Surface finish was evaluated by visual and hands on inspection.

[0095] Previous experience is that the lower the MFR the better is the surface finish. However, all cables produced showed a very smooth surface which is quite surprising considering the high MFR₂₁ values chosen for Ex 1-2.

Output and melt pressure

[0096] In Table 4, data from the cable line extrusion test are shown.

Table 4: Cable line extrusion test

	Ex 1	Ex 2	Comp Ex 2	Comp Ex 1	Comp Ex 3
Filter pressure (Bar)	243	235	332	300	255
RPM	61	61	65	59	58
Extruder power (amps)	55	55	67	65	62

[0097] The results of Table 4 clearly indicate that the inventive compositions can be extruded at lower pressure and extruder power.

[0098] The effect of MFR_{21.6kg/190°C} on extruder pressure is also shown in Fig. 1. Due to the lower MFR₂₁, CompEx 1-2 need a much higher extruder pressure to have the same output. By blending LDPE and LLDPE (i.e. CompEx 3), it is possible to have an extruder pressure comparable the one of Ex 1-2. However, adding LDPE adversely affects mechanical properties, heat deformation and shrinkage behaviour, as will be shown below.

Environmental stress cracking resistance (ESCR)

[0099] The environmental stress cracking was evaluated using CTL with different constant stress. A 10% igepal solution was used as medium. The results are shown in table 5.

Table 5 :ESCR results

	Ex 1	Ex 2	CompEx 1	CompEx 2	CompEx 3
CTL 2MPa (h)					
CTL 3MPa (h)	>3500	>3500	>3500	>3500	55.25
CTL 4MPa (h)	>3500	>3500	>3500	>3500	30.35
ESCR bell test (F0h)	>2000	>2000	>2000		>2000

Mechanical properties

[0100] Elongation at break and tensile strength are summarized in Table 6. The results demonstrate that the inventive examples have good mechanical properties. In other words, processability has been improved while keeping mechanical properties on a high level.

Table 6: Data about mechanical properties

	Ex 1	Ex 2	CompEx 2	CompEx 1	CompEx 3
Elongation at break (%)	711	703	661	804	829
Tensile strength at break (MPa)	26.1	25.8	30.5	31.8	22.0

Shrinkage

[0101] Shrinkage values are listed in Table 7.

Table 7: Shrinkage behaviour

	Ex 1	Ex2	CompEx 2	CompEx 1	CompEx 3
Shrinkage 24h 23°C (%)	0.04	0.04	0.05	0.00	0.24
Shrinkage 24h 100°C (%)	0.08	0.13	0.19	0.18	0.92

[0102] The data of Table 7 indicate that the compositions of the present invention show low shrinkage. In particular, it is evident that the improvement in processability of CompEx 3 (e.g. low extrusion pressure) adversely affects shrinkage behaviour.

Compatibility with filling compounds

[0103] The main application for LD and LLD jackets is in telecommunication cables. In many telecables, copper or fiber optical, filling compounds are used to protect them from water intrusion. A petroleum jelly based, Insojell 3332, is commonly used in copper cables. This filling compound is normally the filling compound that gives the highest absorption.

[0104] Two tests are performed, weight increase and the influence on the mechanical properties.

[0105] Dumbbells 2 mm thick from pressed plaques were put in Insojell 3332 for 7 days. The samples were put on aluminum rods to enable free access for the petroleum jelly from all sides. The ageing was done at 60°C. For the results see table 9.

Table 9: Influence of petroleum jelly

	Ex 1	Ex 2	CompEx 2	CompEx 1	CompEx 3
Weight increase (%)	14.5	12.2	10.5	9.0	7.9
Tensile strength at break (MPa)	20.7	21.4	25.4	25.7	16.4
Change in tensile strength (%)	-8.0	5	-23.3	-20.5	-11.4
Elongation at break (%)	717	778	639	736	756
Change in elongation (%)	-19.2	-14.8	-22.0	-13.9	-10.7

Examples 6-13

[0106] In these examples, three polyethylene compositions according to the present invention (Ex 3-5) and five reference materials (CompEx 4-8) were prepared in a pilot plant as described above. In case of examples 3-5 a polymerization step (c) in a first loop reactor was included to prepare the third fraction (iii). As a catalyst for the examples 3-5 a commercial Lynx 200™ catalyst as manufactured and supplied by Engelhard Corporation, Pasadena, USA.

[0107] Thus, the final composition of Ex.3-5 included three polymer fractions (i), (ii) and (iii).

[0108] For the CompEx 4-8 the same catalyst was used as for examples 1-5 above. For preparing CompEx 4-5 no polymerization step (c) was included. Thus, CompEx 4-5 were bimodal.

[0109] CompEx 4 was the same as comparative example 5 but compounded with 15% LDPE. CompEx 5 corresponds to CompEx 1. CompEx 6 is as CompEx5 but compounded with carbon black. All CompEx5, 7 and 8 were natural, i.e. no carbon black or LDPE was added. Further information about these compositions is provided in Table 10.

Table 10: Process conditions and properties for Ex 3-5

sample		Ex 3	Ex 4	Ex 5
Polymerisation step (c)				
Conditions and				
Product obtained after step (c)				
temperature	°C	60	60	60
pressure	bar	61	60	61
catalyst feed	g/h	1.4	1.4	2.3
cocatalyst feed	g/h	5.0	5.0	5.0
C ₂ feed	kg/h	1.9	1.7	2.0
H ₂ feed	g/h		0.6	
C ₃ feed	kg/h	36.8	35.7	38.7
split	wt-%	2.7	2.5	3.0
MFR2	g/(10 min)			
density	kg/cum			
Polymerisation step (a)				
conditions and				
Product obtained after step (a)				
temperature	°C	80	80	80
pressure	bar	56	56	56
catalyst feed	g/h	1.4	1.4	2.3
C ₂ feed	kg/h	32.9	33.0	31.7
C ₃ feed	kg/h	80.2	93.7	88.7
C ₂ concentration	mol%	3.9	4.5	4.3
H ₂ /C ₂ ratio	mol/kmol	399	360	390
C ₄ /C ₂ ratio	mol/kmol	469	388	421
ethane concentration	mol%	0.23	0.17	0.19
production rate	kg/h	32	31	30
productivity	kg/g	23	22	13
split	wt-%	50.9	51.6	51.5
MFR2	g/(10 min)	350	300	350
density	kg/cum	944	947	946
comonomer		1-butene	1-butene	1-butene
Polymerisation step (b)				
Conditions and				
product (b) obtained after step (b)				
temperature	°C	80	80	80
pressure	bar	20	20	20
C ₂ concentration	mol%	11	12	11
C ₂ partial pressure	bar	2.2	2.4	2.2
H ₂ /C ₂ ratio	mol/kmol	34	29	31
C ₄ /C ₂ ratio	mol/kmol	403	455	450
C ₆ /C ₂ ratio	mol/kmol			
C ₄ /C ₆ feed ratio	g/kg	270	324	321

(continued)

Polymerisation step (b)

Conditions and

product (b) obtained after step (b)

ethane concentration	mol%	0.03	0.03	0.03
production rate	kg/h	30.5	29.3	28.8
productivity (overall)	kg/g	45	42	25
split	wt-%	49.1	48.4	48.5
MFR2	g/(10min)	0.8	0.9	1.0
MFR21	g/(10 min)	87	94	106
FRR21/2	-	104	106	106
density	kg/cum	926	927	925
calculated density (HMW fraction)	kg/cum	907	906	903
comonomer		1-butene	1-butene	1-butene
The final compound after compounding				
MFR2	g/(10min)	0.8	0.9	1.0
MFR5	g/(10 min)	3.40	3.90	4.50
MFR21	g/(10 min)	90.0	102.0	111.0
FRR21/2	-	114	115	111
MWD	-	31.6	32.0	32.3
density	kg/cum	926.3	928.3	926.8
irganox B225	ppm	2640	2650	2690
Ca-stearate	ppm	1580	1580	1590

Table 11: Properties of reference materials

	CompEx 4	CompEx 5	CompEx 6	CompEx 7	CompEx 8
Final composition		natural	+carbon black 2.5 wt%	natural	natural
Density (kg/cm ³)	925	923	931*	920	921.5
MFR2 (g/10 min)	0.4	0.4	0.7	0.8	0.7
MFR21 (g/10 min)		40	79	79	46
FRR21/2		100	65	65	68
Step (a):loop					
Temperature					85
Pressure					57
H2/C2 ratio		330			202
C4/C2 ratio		670			609
MFR2 (g/10 min)		300			290
Density (kg/cm ³)		951			950
Split		43			43.5
Step (b):					
Temperature					80
Pressure					20

(continued)

Step (b):					
H2/C2 ratio		10			4.4
C4/C2 ratio		650			619
MFR2 (g/10 min)					0.7
Density (kg/cm ³)		901			897
Split		57			56.5

[0110] In Table 12, molecular weight and molecular weight distribution of Ex 3-5 and CompEx 5 and 8 are summarized. From Table 12, it is evident that the presence of a third fraction (iii) in the inventive compositions significantly broadens the molecular weight distribution, if compared to the reference materials.

Table 12: Molecular weight and molecular weight distribution

	Ex 3	Ex 4	Ex 5	CompEx 8	CompEx 5
Mw	136000	143000	136000	143000	185000
Mn	4330	4480	4220	10100	15000
Mz	808000	940000	901000	612000	
MWD	31.6	32	32.3	14.2	12.3

[0111] In Table 13, the shear thinning index SHI(2.7/210) of Ex 3-5 and CompEx 8 is given.

Table 13: Shear thinning index

Product	SHI(2.7/210)
Ex 3	65
Ex 4	60
Ex 5	58
CompEx 4	41
CompEx 5	35
CompEx 6	50
CompEx 8	25

[0112] As shown in Table 13, the inventive compositions have high shear thinning index, significantly exceeding the value of the reference material. As already discussed above, high SHI values indicate a broad molecular weight distribution.

[0113] The compositions have been subjected to tests for processability and mechanical properties. The results are shown and discussed below.

Surface finish

[0114] Surface finish was evaluated by visual and hands on inspection. Two different phenomena were observed, first the surface finish as such but also the shape of the insulation. At higher line speed a wave shape occurred at some of the materials. The former are due to the melt strength and the second is more due to extruder pumping and could possibly be corrected by increased melt temperature. However it indicates a more narrow processing window. Previous experience is that the lower the MFR the better is the surface finish. Although the inventive compositions have much higher MFR, they provide excellent results at these line speeds.

Table 14: Evaluation of surface properties

	Line speed	Ex 3	Ex 4	Ex.5 A2047	CompEx 8	CompEx 6	CompEx 5	CompEx 4
Surface smoothness	15	3	3	4	4	3	3	4
35	4	4	4	4	4	4	4	4
70	4	4	4	4	4	4	4	4
140	4	4	4	4	4	4	4	4
0-4 (4 is best)								
Waviness	15	4	4	4	4	4	4	4
35	4	4	4	4	4	4	4	4
70	4	4	4	4	4	4	4	4
140	4	4	4	4	3	3	2	2
1-4 (4 is best)								
Over all performance compared to CompEx 6		=/+	=/+	+/+	+/=		=/-	+/-

Melt pressure

[0115] Just like Ex 1-2, the inventive examples 3-5 have low melt pressure at a specific line speed. With CompEx 6-7 (i.e. blends of LLDPE and LDPE), a low melt tension can be obtained as well. However, as will be shown below, in these materials low-melt tension adversely affects tensile strength, heat deformation and shrinkage behaviour.

[0116] In CompEx 4, 5 and 8, melt tension is significantly higher.

[0117] Melt tension as a function of line speed is shown in Fig. 2.

Mechanical properties

[0118] Mechanical properties are summarized in Tables 15 and 16.

Table 15: Mechanical properties measured on plaques

Plaques	Ex 3	Ex 4	Ex 5	CompEx 8	CompEx 4	CompEx 5	CompEx 6
Elongation at break (%)	904	907	937	837	808	824.9	810
Tensile strength at break (MPa)	26.3	28.7	28.5	33.1	31.7	32.5	19.5

[0119] The data of Table 15 show that the inventive examples have good mechanical properties. In particular, when comparing Ex 3-5 with CompEx 6 it is evident that only the inventive examples have an improved balance between processability (e.g. low melt pressure) and mechanical properties.

Table 16: Mechanical properties measured on cables

Cables	Ex 3	Ex 4	Ex 5	CompEx 8	CompEx 4	CompEx 5	CompEx 6
Elongation at break (%)	597	631	620	576	500	551	527
Tensile strength at break (MPa)	17.1	17.6	17.3	18.8	17.9	17	17.6

Shrinkage

[0120] 24 h shrinkage was measured at 23°C and 100°C. The results are summarized in Table 17. The inventive examples show good shrinkage performance.

Table 17: Shrinkage behaviour

	Ex3	Ex 4	Ex5	CompEx 4	CompEx 5	CompEx 6	CompEx 8
Shrinkage 24h 23°C (%)	0.15	0.0	0.0	0.0	0.00	0.0	0.0
Shrinkage 24h 100°C (%)	0.34	0.08	0.15	0.45	0.07	0.4	0.01

Compatibility with filling compounds

[0121] Two compatibility tests were performed: weight increase and the influence on the mechanical properties.

[0122] Dumbbells 2 mm thick from pressed plaques were put in Insojell 3332 for 7 days. The samples were put on aluminum rods to enable free access for the petroleum jelly from all sides. The ageing was done at 70°C. The results are shown in Table 18.

Table 18: Results from compatibility tests

Jelly absorption	Ex 3	Ex 4	Ex 5	CompEx 8	CompEx 4	CompEx 5	CompEx 6
Change in Elongation at break (%)	-5.6	-2.9	-3.7	-12.2	-9	-8.8	-0.8
Stress at break (%)	-11.4	-10.3	-17.5	-19.0	-15.6	-13.6	-9.1
Absorption weight increase (%)	5.61	5.48	5.84	8.24	7.14	7.26	6.79

[0123] The materials prepared in a sequential multistage process (i.e. Ex 3-5 and CompEx 4, 5 and 8) have a more pronounced change in mechanical properties than the blend of LLDPE/LDPE. With regard to absorption weight increase, the inventive examples have the lowest values. Thus, considering both effects (i.e. change in mechanical properties as

well as change in weight), the inventive materials offer the best compromise.

Heat deformation

[0124]

	Ex 3	Ex 4	Ex 5	Comp 8	Comp 4	Comp 5	Comp 6
Heat deformation 4h at 115° (%)	14.9	13.1	10.6	10.9	15.4	14.6	65

Crystallization temperature

[0125] In Table 19, crystallization temperatures of Ex 3-5 and CompEx 5 are listed.

Table 19: Crystallization temperature

	Ex 1	Ex 2	Ex 3	CompEx5
Crystallization temperature (°C)	112.7	112.9	113.3	111.6

[0126] The increase in crystallization temperature is beneficial for processing, e.g. for film applications, since the high molecular weight fraction (iii) acts as a nucleator increasing the crystallization. This is advantageous for the cooling properties after processing the article.

Claims

1. A polyethylene composition, comprising a base resin which comprises

- (i) a first fraction which is an ethylene homo- or copolymer, and
- (ii) a second fraction which is an ethylene copolymer,

wherein the first fraction (i) has a lower weight average molecular weight than the second fraction (ii), and the base resin has a density of less than 0.940 g/cm³, a shear thinning index SHI_{2.7/210} of at least 25, and a flow rate ratio FRR_{21/2} of at least 65.

2. The polyethylene composition according to claim 1 wherein the base resin further comprises a third fraction (iii) which is an ethylene homo- or copolymer having a weight average molecular weight which is higher than the weight average molecular weight of the first fraction (i) and is different from the weight average molecular weight of the second fraction (ii).

3. The polyethylene composition according to one of the preceding claims, wherein the base resin has a melt flow rate MFR_{21.6kg/190°C} of more than 40 g/10 min.

4. The polyethylene composition according to one of the preceding claims, wherein the fraction (i) has a density of more than 0.931 g/cm³.

5. The polyethylene composition according to one of the preceding claims, wherein the base resin has a molecular weight distribution M_w/M_n of more than 15.

6. The polyethylene composition according to one of the preceding claims, wherein the base resin has a flow rate ratio FRR_{21/2} of more than 70.

7. The polyethylene composition according to one of the preceding claims, wherein the fraction (i) has a density of more than 0.935 g/cm³.
8. The polyethylene composition according to one of the preceding claims, wherein the third fraction (iii) has a higher weight average molecular weight than the second fraction (ii).
9. The polyethylene composition according to one of the preceding claims, wherein the blend of fraction (iii) with fraction (i) has a melt flow rate MFR_{2.16kg/190°C} within the range of 20 to 700 g/10 min.
10. The polyethylene composition according to one of the preceding claims, wherein the second fraction (ii) has a melt flow rate MFR_{2.16kg/190°C} of more than 0.01 g/10 min.
11. A process for preparing the polyethylene composition according to one of the claims 1 to 10, comprising the following steps:
 - (a) polymerizing ethylene, optionally with at least one alpha-olefin comonomer, to obtain a first ethylene homo- or copolymer fraction (i), and
 - (b) polymerizing ethylene with at least one alpha-olefin comonomer to obtain a second polyethylene copolymer fraction (ii),wherein the fractions (i) and (ii) are blended to obtain the base resin.
12. The process according to claim 11, the process being a multistage process wherein the process steps are carried out either in the sequence (a)→(b) or (b)→(a).
13. The process according to claim 11 or claim 12, wherein the process steps (a) and (b) are carried out in the presence of a Ziegler-Natta catalyst.
14. The process according to claim 12 or 13, wherein the process step (a) is carried out first in a slurry reactor, followed by process step (b) in a gas phase reactor to obtain a reactor blend of fractions (i) and (ii).
15. The process according to claim 14, further comprising a process step (c) for the preparation of the ethylene homo- or copolymer fraction (iii), wherein step (c) is carried out first in the presence of a Ziegler-Natta catalyst, followed by reaction steps (a) and (b), and the split between step (c) and reaction steps (a) and (b) is from 0.1:99.9 to 10:90.
16. An article, comprising a polyethylene composition according to one of the claims 1 to 10.
17. The article according to claim 16, wherein the article is a wire or cable comprising at least one layer which comprises the composition of any of the previous claims, preferably the layer is a jacketing layer.
18. The article according to claim 16, wherein the article is a film.
19. The use of the composition as defined in any of the previous claims for producing a layer for a wire or cable, preferably for producing a jacketing layer.
20. A method for producing a wire or cable, comprising a core element power or information conducting element and one or more layers formed by extrusion, wherein at least one layer is formed from a polymer composition comprising the polyethylene compositions as defined in any of the previous claims.

Patentansprüche

1. Polyethylenzusammensetzung, umfassend ein Grundharz, das folgendes aufweist:

- (i) einen ersten Anteil, der ein Ethylenhomo- oder -copolymer ist und
- (ii) einen zweiten Anteil, der ein Ethylencopolymer ist,

wobei der erste Anteil (i) ein geringeres Gewichtsmittel des Molekulargewichts als der zweite Anteil (ii) hat, und das

Grundharz eine Dichte von weniger als $0,940 \text{ g/cm}^3$, einen Strukturviskositätsindex $\text{SHI}_{2,7/210}$ von mindestens 25 und ein Verhältnis der Fließraten $\text{FRR}_{21/2}$ von mindestens 65 aufweist.

2. Polyethylenzusammensetzung nach Anspruch 1, wobei das Grundharz ferner einen dritten Anteil (iii) umfaßt, der ein Ethylenhomo- oder -copolymer ist, das ein Gewichtsmittel des Molekulargewichts hat, das höher als das Gewichtsmittel des Molekulargewichts des ersten Anteils (i) ist und vom Gewichtsmittel des Molekulargewichts des zweiten Anteils (ii) verschieden ist.

3. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei das Grundharz eine Schmelzfließrate $\text{MFR}_{21,6 \text{ kg}/190^\circ\text{C}}$ von mehr als 40 g/10 min aufweist.

4. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei der Anteil (i) eine Dichte von mehr als $0,931 \text{ g/cm}^3$ aufweist.

5. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei das Grundharz eine Molekulargewichtsverteilung M_w/M_n von mehr als 15 aufweist.

6. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei das Grundharz ein Verhältnis der Fließraten $\text{FRR}_{21/2}$ von mehr als 70 aufweist.

7. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei der Anteil (i) eine Dichte von mehr als $0,935 \text{ g/cm}^3$ aufweist.

8. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei der dritte Anteil (iii) ein höheres Gewichtsmittel des Molekulargewichts als der zweite Anteil (ii) aufweist.

9. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei das Gemisch aus dem Anteil (iii) und dem Anteil (i) eine Schmelzfließrate $\text{MFR}_{2,16 \text{ kg}/190^\circ\text{C}}$ im Bereich von 20 bis 700 g/10 min aufweist.

10. Polyethylenzusammensetzung nach einem der vorstehenden Ansprüche, wobei der zweite Anteil (ii) eine Schmelzfließrate $\text{MFR}_{2,16 \text{ kg}/190^\circ\text{C}}$ von mehr als 0,01 g/10 min aufweist.

11. Verfahren zur Herstellung der Polyethylenzusammensetzung nach einem der Ansprüche 1 bis 10, das die folgenden Schritte umfaßt:

- (a) Polymerisieren von Ethylen, gegebenenfalls mit zumindest einem Comonomer aus einem α -Olefin, so daß ein erster Anteil (i) aus einem Ethylenhomo- oder -copolymer erhalten wird, und
- (b) Polymerisieren von Ethylen mit zumindest einem Comonomer aus einem α -Olefin, so daß ein zweiter Anteil (ii) aus einem Polyethylenocopolymer erhalten wird,

wobei die Anteile (i) und (ii) gemischt werden, so daß das Grundharz erhalten wird.

12. Verfahren nach Anspruch 11, wobei das Verfahren ein mehrstufiges Verfahren ist, wobei die Verfahrensschritte entweder in der Folge (a)→(b) oder (b)→(a) durchgeführt werden.

13. Verfahren nach Anspruch 11 oder Anspruch 12, wobei die Verfahrensschritte (a) und (b) in Gegenwart eines Ziegler-Natta-Katalysators erfolgen.

14. Verfahren nach Anspruch 12 oder 13, wobei der Verfahrensschritt (a) zuerst in einem Suspensionsreaktor durchgeführt wird, gefolgt vom Verfahrensschritt (b) in einem Gasphasenreaktor, so daß ein Reaktorgemisch der Anteile (i) und (ii) erhalten wird.

15. Verfahren nach Anspruch 14, das ferner einen Verfahrensschritt (c) zur Herstellung des Anteils (iii) aus einem Ethylenhomo- oder -copolymer umfaßt, wobei der Schritt (c) zuerst in Gegenwart eines Ziegler-Natta-Katalysators durchgeführt wird, gefolgt von den Reaktionsschritten (a) und (b), und wobei die Aufteilung zwischen dem Schritt (c) und den Reaktionsschritten (a) und (b) 0,1:99,9 bis 10:90 beträgt.

16. Gegenstand, der eine Polyethylenzusammensetzung nach einem der Ansprüche 1 bis 10 umfaßt.

17. Gegenstand nach Anspruch 16, wobei der Gegenstand ein Draht oder Kabel ist, der bzw. das zumindest eine Schicht umfaßt, die die Zusammensetzung nach einem der vorstehenden Ansprüche aufweist, wobei die Schicht vorzugsweise eine Ummantelungsschicht ist.

18. Gegenstand nach Anspruch 16, wobei der Gegenstand eine Folie ist.

19. Verwendung der Zusammensetzung nach einem der vorstehenden Ansprüche für die Herstellung einer Schicht für einen Draht oder ein Kabel, vorzugsweise für die Herstellung einer Ummantelungsschicht.

20. Verfahren zur Herstellung eines Drahts oder eines Kabels, der bzw. das ein Kernelement aus einem Strom oder Informationen leitenden Element und eine oder mehrere Schichten umfaßt, die durch Extrusion erzeugt worden sind, wobei zumindest eine Schicht aus einer Polymerzusammensetzung hergestellt ist, die die Polyethylenzusammensetzungen nach einem der vorstehenden Ansprüche umfaßt.

Revendications

1. Composition à base de polyéthylène, comprenant une résine de base, qui comprend :

- (i) une première fraction qui consiste en un homo ou copolymère, et
- (ii) une deuxième fraction qui consiste en un copolymère d'éthylène,

dans laquelle la première fraction (i) a un poids moléculaire moyen en poids inférieur à celui de la deuxième fraction (ii), et la résine de base a une masse volumique inférieure à $0,940 \text{ g/cm}^3$, et un indice de fluidification par cisaillement $\text{SHI}_{2,7/210}$ d'au moins 25, et un rapport d'indices de fluidité $\text{FRR}_{21/2}$ d'au moins 65.

2. La composition à base de polyéthylène selon la revendication 1, dans laquelle la résine de base comprend, en outre, une troisième fraction (iii) qui consiste en un homo ou copolymère d'éthylène ayant un poids moléculaire moyen en poids qui est supérieur au poids moléculaire moyen en poids de la première fraction (i) et est différent du poids moléculaire moyen en poids de la deuxième fraction (ii).

3. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la résine de base a un indice de fluidité à l'état fondu $\text{MFR}_{21,6\text{kg}/190^\circ\text{C}}$ de plus de 40 g/10 min.

4. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la fraction (i) a une masse volumique de plus de $0,931 \text{ g/cm}^3$.

5. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la résine de base a une distribution de poids moléculaire M_w/M_n de plus de 15.

6. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la résine de base a un rapport d'indices de fluidité $\text{FRR}_{21/2}$ de plus de 70.

7. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la fraction (i) a une masse volumique de plus de $0,935 \text{ g/cm}^3$.

8. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la troisième fraction (iii) a un poids moléculaire moyen en poids supérieur à celui de la deuxième fraction (ii).

9. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle le mélange de la fraction (iii) avec la fraction (i) a un indice de fluidité à l'état fondu $\text{MFR}_{2,16 \text{ kg}/190^\circ\text{C}}$ dans la plage de 20 à 700 g/10 min.

10. La composition à base de polyéthylène selon l'une des revendications précédentes, dans laquelle la deuxième fraction (ii) a un indice de fluidité à l'état fondu $\text{MFR}_{2,16\text{kg}/190^\circ\text{C}}$ de plus de 0,01 g/10 min.

11. Procédé pour la préparation de la composition à base de polyéthylène selon l'une des revendications 1 à 10, comprenant les étapes suivantes :

(a) la polymérisation d'éthylène, éventuellement avec au moins un comonomère de type alpha-oléfine, pour obtenir une première fraction à base d'homo ou copolymère d'éthylène (i), et
 (b) la polymérisation d'éthylène avec au moins un comonomère de type alpha-oléfine, pour obtenir une deuxième fraction à base de copolymère de polyéthylène (ii),

dans laquelle les fractions (i) et (ii) sont mélangées pour obtenir la résine de base.

12. Le procédé selon la revendication 11, consistant en un procédé à plusieurs étapes, dans lequel les étapes de traitement sont effectuées soit selon la séquence (a) → (b) ou (b) → (a).

13. Le procédé selon la revendication 11 ou la revendication 12, dans lequel les étapes de traitement (a) et (b) sont effectuées en présence d'un catalyseur de Ziegler-Natta.

14. Le procédé selon la revendication de 12 ou 13, dans lequel l'étape de traitement (a) est d'abord effectuée dans un réacteur à suspension, et est suivie par l'étape de traitement (b) dans un réacteur à phase gazeuse pour obtenir un mélange réactif des fractions (i) et (ii).

15. Le procédé selon la revendication de 14, comprenant, en outre, une étape de traitement (c) pour la préparation de la fraction à base d'homo ou copolymère d'éthylène (iii), dans lequel l'étape (c) est d'abord effectuée en présence d'un catalyseur de Ziegler-Natta, et est suivie par les étapes de réaction (a) et (b), et le rapport de partage entre l'étape (c), et les étapes de réaction (a) et (b) est de 0,1 : 99,9 à 10 : 90.

16. Article comprenant une composition à base de polyéthylène selon l'une des revendications 1 à 10.


17. L'article selon la revendication 16, dans lequel l'article est un fil ou un câble comprenant au moins une couche qui contient la composition de l'une quelconque des revendications précédentes, la couche étant, de préférence, une couche de gainage.

18. L'article selon la revendication 16, dans lequel l'article est un film.

19. L'utilisation de la composition, telle que définie dans l'une quelconque des revendications précédentes, pour la production d'une couche pour un fil métallique ou un câble, de préférence, pour la production d'une couche de gainage.

20. Procédé pour la production d'un fil métallique ou d'un câble, comprenant un élément central conducteur d'énergie ou d'information, et une ou plusieurs couches formées par extrusion, dans lequel au moins une couche est formée à partir d'une composition à base de polymère, comprenant les compositions à base de polyéthylène, telles que définies dans l'une quelconque des revendications précédentes.

Fig. 1: Extruder pressure as a function of MFR 21



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- EP 0907682 A [0011]
- EP 517868 A [0059] [0060]
- EP 0810235 A [0068]
- EP 0688794 A1 [0069]
- WO 0022040 A [0082]
- EP 6887794 A [0086]

Non-patent literature cited in the description

- **HEINO ; HEINO, E.L. ; LEHTINEN, A. ; TANNER J. ; SEPPÄLÄ, J.** Rheological characterization of polyethylene fractions. *Theor. Appl. Rheol., Proc. Int. Congr. Rheol.*, 1992, vol. 1, 360-362 [0082]
- **HEINO, E.L.** The influence of molecular structure on some rheological properties of polyethylene. *Annual Transactions of the Nordic Rheology Society*, 1995 [0082]