



(11) **EP 1 764 407 A8**

(12) **CORRECTED EUROPEAN PATENT APPLICATION**

published in accordance with Art. 158(3) EPC

Note: Bibliography reflects the latest situation

(15) Correction information:

Corrected version no 1 (W1 A1)
INID code(s) 86

(48) Corrigendum issued on:

04.07.2007 Bulletin 2007/27

(43) Date of publication:

21.03.2007 Bulletin 2007/12

(21) Application number: **06715134.0**

(22) Date of filing: **03.03.2006**

(51) Int Cl.:

C10M 169/00 (2006.01)	C10M 107/38 (2006.01)
C10M 119/22 (2006.01)	C10M 129/34 (2006.01)
C10M 129/42 (2006.01)	C10M 135/10 (2006.01)
C10N 10/02 (2006.01)	C10N 10/04 (2006.01)
C10N 20/06 (2006.01)	C10N 30/06 (2006.01)
C10N 30/08 (2006.01)	C10N 30/12 (2006.01)
C10N 40/00 (2006.01)	C10N 40/02 (2006.01)
C10N 40/04 (2006.01)	C10N 40/14 (2006.01)
C10N 40/34 (2006.01)	C10N 50/10 (2006.01)

(86) International application number:

PCT/JP2006/304051

(87) International publication number:

WO 2006/095644 (14.09.2006 Gazette 2006/37)

(84) Designated Contracting States:

DE FR GB

(30) Priority: **07.03.2005 JP 2005061811**

(71) Applicant: **NOK KLÜBER CO., LTD.**

Minato-ku
Tokyo 105-8585 (JP)

(72) Inventors:

- **NONAKA, Takeshi,**
c/o NOK KLÜBER CO., LTD.
Kitaibaraki-shi,
Ibaraki 319-1541 (JP)
- **NITTA, Toshio,**
c/o NOK KLÜBER CO., LTD.
Kitaibaraki-shi,
Ibaraki 319-1541 (JP)

- **KITAHARA, Tetsuhiro,**
c/o NOK KLÜBER CO., LTD.
Kitaibaraki-shi,
Ibaraki 319-1541 (JP)
- **HASHIMOTO, Tatsuya,**
c/o NOK KLÜBER CO., LTD.
Kitaibaraki-shi,
Ibaraki 319-1541 (JP)

(74) Representative: **Albrecht, Thomas et al**

Kraus & Weisert
Patent- und Rechtsanwälte
Thomas-Wimmer-Ring 15
80539 München (DE)

(54) **LUBRICANT COMPOSITION**

(57) A lubricant composition, which comprises a fluoro-oil, a powdery fluororesin thickener, and Ca salt or Na salt of aromatic sulfonic acid or saturated aliphatic dicarboxylic acid as a rust-inhibitive additive, where the thickener is in a proportion of 10-40% by weight, and the additive is in a proportion of 0.3-10% by weight, on the basis of total weight of the composition, the balance being

the fluoro-oil. The lubricant composition containing the powdery fluororesin in an appropriate admixing proportion as a thickener in the fluoro oil has a distinguished rust inhibition, particularly even after having being subjected to heat hysteresis, where a perfluoropolyether oil is usually used as a fluoro-oil.

EP 1 764 407 A8