

(19)



(11)

**EP 1 907 442 B9**

(12)

**CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:

**Corrected version no 1 (W1 B1)**  
**Corrections, see**  
**Claims EN 2, 11**

(51) Int Cl.:

**C08G 63/199 (2006.01) C08L 67/02 (2006.01)**  
**B65D 1/02 (2006.01)**

(48) Corrigendum issued on:

**02.02.2011 Bulletin 2011/05**

(86) International application number:

**PCT/US2006/011937**

(45) Date of publication and mention of the grant of the patent:

**17.11.2010 Bulletin 2010/46**

(87) International publication number:

**WO 2007/001563 (04.01.2007 Gazette 2007/01)**

(21) Application number: **06749034.2**

(22) Date of filing: **30.03.2006**

(54) **BOTTLES COMPRISING POLYESTER COMPOSITIONS WHICH COMPRISE CYCLOBUTANEDIOL**

CYCLOBUTANDIOL ENTHALTENDE POLYESTERZUSAMMENSETZUNGEN UMFASSENDE FLASCHEN

BOUITEILLES FABRIQUEES A PARTIR DE COMPOSITIONS DE POLYESTER COMPRENANT DU CYCLOBUTANEDIOL

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI SK TR**

(72) Inventors:

- **CRAWFORD, Emmett, Dudley Kingsport, Tennessee 37663 (US)**
- **PECORINI, Thomas, Joseph Kingsport, TN 37663 (US)**
- **PORTER, David, Scott Blountville, TN 37617 (US)**
- **CONNELL, Gary, Wayne Church Hill, TN 37642-3101 (US)**
- **KEEGAN, Michael, James Kingsport, TN 37663 (US)**

(30) Priority: **17.06.2005 US 691567 P**

**28.10.2005 US 731389 P**

**28.10.2005 US 731454 P**

**22.11.2005 US 738869 P**

**22.11.2005 US 739058 P**

**15.12.2005 US 750547 P**

**15.12.2005 US 750682 P**

**15.12.2005 US 750692 P**

**15.12.2005 US 750693 P**

(74) Representative: **Ricker, Mathias**

**Wallinger Ricker Schlotter Foerstl Patent- und Rechtsanwälte**  
**Zweibrückenstrasse 5-7**  
**80331 München (DE)**

(43) Date of publication of application:

**09.04.2008 Bulletin 2008/15**

(60) Divisional application:

**10012570.7 / 2 272 888**

(56) References cited:

**EP-A- 0 698 631 FR-A- 1 278 284**

**GB-A- 1 044 015 US-A- 5 552 512**

**US-A- 5 705 575 US-A- 5 942 585**

**US-A- 6 011 124 US-A- 6 043 322**

**US-A- 6 096 854 US-A- 6 120 889**

(73) Proprietor: **EASTMAN CHEMICAL COMPANY Kingsport TN 37660 (US)**

**EP 1 907 442 B9**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**Description****FIELD OF THE INVENTION**

5 **[0001]** The present invention generally relates to bottles comprising a polyester composition made from terephthalic acid or an ester thereof, or mixtures thereof, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol, the polyester having a certain combination of two or more of high impact strengths, high glass transition temperature (T<sub>g</sub>), toughness, certain inherent viscosities, low ductile-to-brittle transition temperatures, good color and clarity, low densities, chemical resistance, hydrolytic stability, and long crystallization half-times, which allow them to be easily  
10 formed into articles.

**BACKGROUND OF THE INVENTION**

15 **[0002]** Poly(1,4-cyclohexylenedimethylene) terephthalate (PCT), a polyester based solely on terephthalic acid or an ester thereof and 1,4-cyclohexanedimethanol, is known in the art and is commercially available. This polyester crystallizes rapidly upon cooling from the melt, making it very difficult to form amorphous articles by methods known in the art such as extrusion, injection molding, and the like. In order to slow down the crystallization rate of PCT, copolyesters can be prepared containing additional dicarboxylic acids or glycols such as isophthalic acid or ethylene glycol. These ethylene glycol- or isophthalic acid-modified PCTs are also known in the art and are commercially available.

20 **[0003]** One common copolyester used to produce films, sheeting, and molded articles is made from terephthalic acid, 1,4-cyclohexanedimethanol, and ethylene glycol. While these copolyesters are useful in many end-use applications, they exhibit deficiencies in properties such as glass transition temperature and impact strength when sufficient modifying ethylene glycol is included in the formulation to provide for long crystallization half-times. For example, copolyesters made from terephthalic acid, 1,4-cyclohexanedimethanol, and ethylene glycol with sufficiently long crystallization half-  
25 times can provide for amorphous products that exhibit what is believed to be undesirably higher ductile-to-brittle transition temperatures and lower glass transition temperatures than the compositions revealed herein.

**[0004]** The polycarbonate of 4,4'-isopropylidenediphenol (bisphenol A polycarbonate) has been used as an alternative for polyesters known in the art and is a well known engineering molding plastic. Bisphenol A polycarbonate is a clear,  
30 high-performance plastic having good physical properties such as dimensional stability, high heat resistance, and good impact strength. Although bisphenol-A polycarbonate has many good physical properties, its relatively high melt viscosity leads to poor melt processability and the polycarbonate exhibits poor chemical resistance. It is also difficult to thermoform.

**[0005]** Polymers containing 2,2,4,4-tetramethyl-1,3-cyclobutanediol have also been generally described in the art. Generally, however, these polymers exhibit high inherent viscosities, high melt viscosities and/or high T<sub>g</sub>s (glass transition temperatures) such that the equipment used in industry can be insufficient to manufacture or post polymerization process  
35 these materials.

**[0006]** Thus, there is a need in the art for bottles comprising at least one polymer having a combination of two or more properties, chosen from the following: such as toughness, and high glass transition temperatures, high impact strength, hydrolytic stability, chemical resistance, long crystallization half-times, low ductile to brittle transition temperatures, good color and clarity, lower density and/or thermoformability of polyesters while retaining processability on the standard  
40 equipment used in the industry.

**SUMMARY OF THE INVENTION**

45 **[0007]** It is believed that certain bottles comprising polyester compositions formed from terephthalic acid, an ester thereof, or mixtures thereof, 1,4-cyclohexanedimethanol and 2,2,4,4-tetramethyl-1,3-cyclobutanediol with a certain monomer compositions, inherent viscosities, and/or glass transition temperatures are superior to polyesters known in the art and to polycarbonate with respect to one or more of high impact strengths, hydrolytic stability, toughness, chemical resistance, good color and clarity, long crystallization half-times, low ductile to brittle transition temperatures, at least one of hydrolytic stability, toughness, chemical resistance, lower specific gravity, and thermoformability. These bottles  
50 are believed to be similar to polycarbonate in heat resistance and are still processable on the standard industry equipment.

**[0008]** In one aspect, the invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

55

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 85 to 200°C.

**[0009]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

(c) residues from at least one branching agent;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C ; and wherein the polyester has a Tg of 85 to 200°C.

**[0010]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 85°C to 200°C.

**[0011]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

## EP 1 907 442 B9

- i) 40 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 125 to 200°C.

**[0012]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to less than 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) greater than 20 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 125 to 200°C.

**[0013]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 85 to 200°C.

**[0014]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 55 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 45 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component

is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 85 to 200°C.

**[0015]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 50 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 85 to 200°C.

**[0016]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 45 to 55 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 45 to 55 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/4.0 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 85 to 200°C.

**[0017]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 50 up to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to less than 50 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component, is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 85 to 200°C.

**[0018]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 50 up to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to less than 50 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 85°C to 200°C.

**[0019]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 51 up to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to less than 49 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 85°C to 200°C.

**[0020]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

(c) residues of at least one branching agent;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C ; and wherein the polyester has a Tg of 110 to 200°C.

**[0021]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 50 up to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to less than 50 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110°C to 200°C.

**[0022]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 51 up to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to less than 49 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110°C to 200°C.

**[0023]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 50 up to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to less than 50 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110°C to 200°C.

**[0024]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;

## EP 1 907 442 B9

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 51 up to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to less than 49 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110°C to 200°C.

**[0025]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110 to 200°C.

**[0026]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 110 to 200°C.

**[0027]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

## EP 1 907 442 B9

- i) 40 to less than 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) greater than 20 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 110 to 200°C.

**[0028]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 110 to 200°C.

**[0029]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 55 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 45 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 110 to 200°C.

**[0030]** . In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 50 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component

is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 110 to 200°C.

**[0031]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 45 to 55 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 45 to 55 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 110 to 200°C.

**[0032]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 110 to 200°C.

**[0033]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 and less than 0.70 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110 to 200°C.

**[0034]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at

least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 5           i) 70 to 100 mole % of terephthalic acid residues;  
           ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
           iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 10           i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
           ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

15           wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

          wherein the inherent viscosity of the polyester is greater than 0.76 up to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 110°C to 200°C.

**[0035]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

20           (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;  
           ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
           iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 30           i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
           ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

          wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

          wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 110 to 150°C.

**[0036]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

40           (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;  
           ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
           iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 45           i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
           ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

50           wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

          wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 110 to 150°C.

**[0037]** In one aspect; this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

55           (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

5 (b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

10 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 120 to 135°C.

15 **[0038]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 20 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 25 i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

30 wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 120 to 135°C:

**[0039]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

35 (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- 40 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 45 i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 127°C to 200°C.

50 **[0040]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 55 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 127°C to 200°C.

**[0041]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from greater than 148°C to 200°C.

**[0042]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from greater than 148°C to 200°C.

**[0043]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 64.9 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35.1 to 59.1 mole % of 1,4-cyclohexanedimethanol residues,

iii) 0.10 to less than 15 mole % ethylene glycol residues;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 85 to 200°C.

**[0044]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 85 to 200°C and optionally, wherein one or more branching agents is added prior to or during the polymerization of the polymer.

**[0045]** In one aspect, this invention relates to a bottle comprising:

(I) at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues; and

(II) at least one thermal stabilizer and/or reaction products thereof;

wherein the total mole% of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 85 to 200°C.

**[0046]** In one aspect, this invention relates to a bottle comprising:

(I) at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues; and

5

(II) at least one thermal stabilizer and/or reaction products thereof;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

10 wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 85 to 200°C.

**[0047]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

15

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

20

(b) a glycol component comprising:

- i) 40 to 64.9 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 59.9 mole % of 1,4-cyclohexanedimethanol residues,
- iii) 0.10 to less than 15 mole % ethylene glycol residues;

25

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

30 wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g or less as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 110 to 200°C.

**[0048]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

35

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

40

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues; and

45

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

50

wherein the polyester has a Tg of 110 to 200°C and optionally, wherein one or more branching agents is added prior to or during the polymerization of the polymer.

**[0049]** In one aspect, this invention relates to a bottle comprising:

55

(I) at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;

EP 1 907 442 B9

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues;

(II) at least one thermal stabilizer and/or reaction products thereof;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 110 to 200°C.

**[0050]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising:

(I) at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues; and

(II) at least one thermal stabilizer and/or reaction products thereof;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 110 to 200°C.

**[0051]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising:

(I) at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 64.9 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35.1 to 60 mole % of 1,4-cyclohexanedimethanol residues,
- iii) 0.10 to less than 15 mole % ethylene glycol residues;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g or less as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 110 to 200°C.

**[0052]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at

least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 5
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 10
- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

15 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 110 to 200°C and

optionally, wherein one or more branching agents is added prior to or during the polymerization of the polymer.

20 **[0053]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 25
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 30
- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

(c) residues of at least one branching agent;

35 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C ; and wherein the polyester has a Tg of 110 to 200°C.

40 **[0054]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 45
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 50
- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues; and

(II) at least thermal stabilizer and/or reaction products thereof;

55 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 110 to 200°C.

**[0055]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising:

(I) at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues; and

(II) at least one thermal stabilizer and/or reaction products thereof;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C;

wherein the polyester has a Tg of 110 to 200°C.

**[0056]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 40 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to less than 60 mole % of 1,4-cyclohexanedimethanol residues;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein the polyester has a Tg of 85 to 200°C; wherein the polyester is amorphous; wherein if ethylene glycol residues is present in the glycol component, it is present in the amount of 0.01 to less than 15 mole %.

**[0057]** In one aspect, this invention relates to a bottle comprising an amorphous polyester comprising:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 10 to 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 0 to 90 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %.

**[0058]** In one aspect, this invention relates to a bottle comprising an amorphous polyester comprising:

(a) a dicarboxylic acid component comprising:

- 5
- i) 90 to 100 mole % of terephthalic acid residues;
  - ii) up to 10 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) up to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 10
- i) from 25 to 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) up to 75 mole % of 1,4-cyclohexanedimethanol residues,

15 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the amorphous polyester has a glass transition temperature ( $T_g$ ) of greater than 120°C.

**[0059]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 20
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 25
- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

30 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.10 to less than 1 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a  $T_g$  of from 85 to 120°C.

**[0060]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 40
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 45
- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

50 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a  $T_g$  of from 85 to 120°C.

**[0061]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 55
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 5 i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
 ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

10 wherein the inherent viscosity of the polyester is 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 95°C to 115°C.

**[0062]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

15 (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;  
 ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

20

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
 ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

25

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is 0.35 to less than 1 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of from 95°C to 115°C.

30 **[0063]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 35 i) 70 to 100 mole % of terephthalic acid residues;  
 ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

40

- i) 5 to less than 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
 ii) greater than 50 to 95 mole % of 1,4-cyclohexanedimethanol residues,

45 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.50 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

wherein the polyester has a Tg of 85 to 120°C.

50 **[0064]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 55 i) 70 to 100 mole % of terephthalic acid residues;  
 ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

## EP 1 907 442 B9

- i) 10 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 70 to 90 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

wherein the polyester has a Tg of 85 to 120°C.

**[0065]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 3 to 10 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 90 to 97 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

wherein the polyester has a Tg of 60 to 120°C.

**[0066]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 3 to 10 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 90 to 97 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from greater than 0.60 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

wherein the polyester has a Tg of 60 to 120°C.

**[0067]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 3 to 9 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) 91 to 97 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0068]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 8 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 92 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0069]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 7 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 93 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0070]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 11 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 70 to 89 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

5 wherein the polyester has a Tg of 85 to 120°C.

**[0071]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

10

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

15

(b) a glycol component comprising:

- i) 12 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 70 to 88 mole % of 1,4-cyclohexanedimethanol residues,

20

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

wherein the polyester has a Tg of 85 to 120°C.

25

**[0072]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

30

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

35

- i) 13 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 70 to 87 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

40

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and

wherein the polyester has a Tg of 85 to 120°C.

45

**[0073]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

50

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

55

- i) 14 to 25 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 75 to 86 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component

is 100 mole %; and

wherein the inherent viscosity is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a T<sub>g</sub> of 85 to 120°C.

**[0074]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 5 to less than 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) greater than 50 to 95 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.50 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a T<sub>g</sub> of 95 to 115°C.

**[0075]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 10 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 70 to 90 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.50 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a T<sub>g</sub> of 95 to 115°C.

**[0076]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 14 to 25 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 75 to 86 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.50 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a T<sub>g</sub> of 95 to 115°C.

**[0077]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at

least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 5           i) 70 to 100 mole % of terephthalic acid residues;  
           ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
           iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

10           (b) a glycol component comprising:

- i) 5 to less than 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
           ii) greater than 50 to 95 mole % of 1,4-cyclohexanedimethanol residues,

15           wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

          wherein the inherent viscosity of the polyester is from 0.50 to less than 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 85 to 120°C.

20           **[0078]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

          (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;  
           ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
           iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

          (b) a glycol component comprising:

- i) 10 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
           ii) 70 to 90 mole % of 1,4-cyclohexanedimethanol residues,

          wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

35           wherein the inherent viscosity of the polyester is from 0.50 to less than 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 85 to 120°C.

**[0079]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

          (a) a dicarboxylic acid component comprising:

- 40           i) 70 to 100 mole % of terephthalic acid residues;  
           ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and  
           iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

45           (b) a glycol component comprising:

- i) 14 to 25 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and  
           ii) 75 to 86 mole % of 1,4-cyclohexanedimethanol residues,

50           wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

          wherein the inherent viscosity of the polyester is from 0.50 to less than 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 85 to 120°C.

55           **[0080]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

          (a) a dicarboxylic acid component comprising:

## EP 1 907 442 B9

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

5 (b) a glycol component comprising:

- i) 5 to less than 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) greater than 50 to 95 mole % of 1,4-cyclohexanedimethanol residues,

10 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.50 to less than 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 95 to 115°C.

15 **[0081]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 20 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 25 i) 10 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 70 to 90 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

30 wherein the inherent viscosity of the polyester is from 0.50 to less than 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 95 to 115°C.

**[0082]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

35 (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- 40 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 45 i) 14 to 25 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 75 to 86 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.50 to less than 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 95 to 115°C.

50 **[0083]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 55 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 14 to 25 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 75 to 86 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.6 to 0.72 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 95 to 115°C.

**[0084]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) optionally, 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0085]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 4.5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) optionally, 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0086]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 4 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) optionally, 1,4-cyclohexanedimethanol residues

5 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

10 **[0087]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 15 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 20 i) 0.01 to 3 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

25 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

30 **[0088]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 35 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 40 i) 0.01 to 2 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) optionally, 1,4-cyclohexanedimethanol residues

45 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

50 **[0089]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 55 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 1 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;

- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0090]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to less than 1 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and ,
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0091]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 15 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0092]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 15 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 70 to 99.98 mole % ethylene glycol residues, and

iii) 0.01 to 15 mole % of 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

5 wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0093]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

10 (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

15

(b) a glycol component comprising:

- i) 0.01 to 10 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

20

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

25 wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0094]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

30 (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

35

(b) a glycol component comprising:

- i) 0.01 to 10 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 80 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 10 mole % of 1,4-cyclohexanedimethanol residues

40

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

45 wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0095]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

50

(b) a glycol component comprising:

55

- i) 0.01 to 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

5 **[0096]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 10
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 15
- i) 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) ethylene glycol residues, and
  - iii) 1,4-cyclohexanedimethanol residues

20 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

25 **[0097]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 30
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 35
- i) 0.01 to 4.5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) ethylene glycol residues, and
  - iii) 1,4-cyclohexanedimethanol residues

40 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

45 **[0098]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 50
- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- 55
- i) 0.01 to 4 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) ethylene glycol residues, and
  - iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component

is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0099]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 3 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0100]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 2.0 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0101]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 1 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0102]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

5

(a) a dicarboxylic acid component comprising:

10

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

15

- i) 0.01 to less than 1 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) ethylene glycol residues, and
- iii) 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

20

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0103]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

25

(a) a dicarboxylic acid component comprising:

30

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

35

- i) 0.01 to 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 90 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

40

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/140 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0104]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

45

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

50

(b) a glycol component comprising:

- i) 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) greater than 90 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

55

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloro-

roethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0105]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

5 (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

10

(b) a glycol component comprising:

- i) 0.01 to 4 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 91 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

15

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

20

**[0106]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

25

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

30

(b) a glycol component comprising:

- i) 0.01 to 3 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 92 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

35

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

40

**[0107]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

45

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

50

(b) a glycol component comprising:

- i) 0.01 to 2 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 93 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

55

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0108]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to 1 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) 94 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0109]** In one aspect, this invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 0.01 to less than 1 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
- ii) greater than 94 to 99.98 mole % of ethylene glycol residues, and
- iii) 0.01 to 5 mole % of 1,4-cyclohexanedimethanol residues

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 60 to 120°C.

**[0110]** In one aspect, the invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of from 100

## EP 1 907 442 B9

to 190°C, or 100 to 180°C, or 100 to 160°C, or 100 to 150°C, or 100 to 140°C, or 100 to 130°C, or 100 to 120°C, or of 110 to 180°C, or of 110 to 160°C, or 110 to 150°C, or 110 to 140°C, or 110 to 130°C, or 110 to 120°C, or of 115 to 180°C, or 115 to 170°C, or 115 to 160°C, or 115 to 150°C, or 115 to 140°C, or 115 to 130°C, or 115 to 120°C, or 120 to 160°C, or 120 to 150°C, or 130 to 160°C, or 130 to 150°C, or 130 to 145°C.

5 **[0111]** In one aspect, the invention relates to a bottle comprising at least one polyesters composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 10 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- 15 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- 20 ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; wherein the inherent viscosity of said polyester is from 0.60 to 0.72 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of from 130 to 145°C.

25 **[0112]** In one aspect, the invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 30 i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- 35 iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- 40 ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; wherein the inherent viscosity of said polyester is from 0.35 to 1.0 dL/g, or 0.40 to 0.90 dL/g, or from greater than 0.42 to 0.80 dL/g, or from 0.45 to 0.75 dL/g, or from 0.50 to 0.68 dL/g, or from 0.35 to 0.75 dL/g, or from 0.35 to 0.80 dL/g, or from 0.35 to 0.70 dL/g, or from 0.35 to less than 0.70 dL/g, or from 0.35 to 0.68 dL/g, or from 0.35 to less than 0.68 dL/g, or from 0.50 to 0.75 dL/g, or from 0.50 to 0.70 dL/g, or from 0.50 to less than 0.70 dL/g, or from 0.50 to less than 0.68 dL/g, or from 0.55 to 0.80 dL/g, or from 0.55 to 0.75 dL/g, or from 0.55 to 0.70 dL/g, or from 0.55 to less than 0.70 dL/g, or from 0.55 to 0.68 dL/g, or from or from 0.60 to 0.80 dL/g, or from 0.60 to 0.75 dL/g, or from 0.60 to 0.70 dL/g, or from 0.60 to less than 0.70 dL/g, or from 0.60 to 0.68 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of from 85 to 200°C.

50 **[0113]** In one aspect, the invention relates to a bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- 55 i) 70 to 100 mole % of terephthalic acid residues;

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

5 (b) a glycol component comprising:

1 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 99 mole % 1,4-cyclohexanedimethanol, or  
 25 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 75 mole % 1,4-cyclohexanedimethanol, or  
 35 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 65 mole % 1,4-cyclohexanedimethanol, or  
 10 40 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 60 mole % 1,4-cyclohexanedimethanol, or  
 45 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 55 mole % 1,4-cyclohexanedimethanol, or  
 50 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 50 mole % 1,4-cyclohexanedimethanol, or  
 40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol, or  
 15 greater than 50 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to less than 50 mole % 1,4-cy-  
 clohexanedimethanol, or greater than 50 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to less  
 than 50 mole % 1,4-cyclohexanedimethanol, or greater 51 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclob-  
 utanediol and 20 to less than 49 mole % 1,4-cyclohexanedimethanol, or 30 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclob-  
 utanediol and 40 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclob-  
 utanediol and 50 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclob-  
 utanediol and 55 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclob-  
 utanediol and 60 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclob-  
 utanediol and 65 to 70 mole % 1,4-cyclohexanedimethanol,

25 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component  
 is 100 mole %; wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt)  
 phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of from 85  
 to 200°C.

**[0114]** In one aspect, the invention relates to a bottle comprising at least one polyester composition comprising at  
 least one polyester which comprises:

30

(a) a dicarboxylic acid component comprising:

i) 70 to 100 mole % of terephthalic acid residues;

35

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

40

(b) a glycol component comprising:

40 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 60 mole % 1,4-cyclohexanedimethanol, or  
 40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol,

45

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component  
 is 100 mole %; wherein the inherent viscosity of said polyester is from 0.60 to 0.72 dL/g as determined in 60/40 (wt/wt)  
 phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of from 85  
 to 200°C.

**[0115]** In one aspect, the invention relates to a bottle comprising at least one polyester composition comprising at  
 least one polyester which comprises:

50

(a) a dicarboxylic acid component comprising:

i) 70 to 100 mole % of terephthalic acid residues;

55

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol,

5 wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; wherein the inherent viscosity of said polyester is from 0.60 to 0.72 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> of from 130 to 145°C.

[0116] In one aspect, the polyester compositions useful in the bottles of the invention contain polycarbonate.

10 [0117] In one aspect, the polyester compositions useful in the bottles of the invention contain no polycarbonate.

[0118] In one aspect, the polyesters useful in the bottles of the invention contain from 0.01 to less than 15 mole % ethylene glycol residues.

[0119] In one aspect, the polyesters useful in the bottles of the invention contain no ethylene glycol residues.

15 [0120] In one aspect the polyester compositions useful in the bottles of the invention contain at least one thermal stabilizer and/or reaction products thereof.

[0121] In one aspect of the invention, the mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol useful in certain polyesters useful in the invention is greater than 50 mole % or greater than 55 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or greater than 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol; wherein the total mole percentage of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to a total of 100 mole %.

20 [0122] In one aspect of the invention, the mole % of the isomers of 2,2,4,4-tetramethyl-1,3-cyclobutanediol useful in certain polyesters useful in the invention is from 30 to 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or from 30 to 70 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol, or from 40 to 60 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or from 40 to 60 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol, wherein the total mole percentage of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to a total of 100 mole %.

[0123] In one aspect, the polyesters useful in the invention contain no branching agent, or alternatively, at least one branching agent is added either prior to or during polymerization of the polyester.

25 [0124] In one aspect, the polyesters useful in the invention contain at least one branching agent without regard to the method or sequence in which it is added.

[0125] In one aspect, the polyesters useful in the invention are made from no 1,3-propanediol, or, 1,4-butanediol, either singly or in combination. In other aspects, 1,3-propanediol or 1,4-butanediol, either singly or in combination, may be used in the making of the polyesters of this invention.

30 [0126] In one aspect, the polyester compositions are useful in bottles including but not limited to extruded and/or molded articles including but not limited to injection molded articles, thermoformed articles, extrusion molded articles, injection blow molded articles, injection stretch blow molded articles, extrusion blow molded articles and extrusion stretch blow molded articles. These bottles can include but are not limited to injection molded bottles, thermoformed bottles, extrusion molded bottles, injection blow molded bottles, injection stretch blow molded bottles, extrusion blow molded bottles and extrusion stretch blow molded bottles.

35 [0127] Also, in one aspect, use of these particular polyester compositions minimize and/or eliminates the drying step prior to melt processing and/or thermoforming.

[0128] In one aspect, the polyesters useful in the invention may be amorphous or semicrystalline. In one aspect, certain polyesters useful in the invention can have a relatively low crystallinity. Certain polyesters useful in the invention can thus have a substantially amorphous morphology, meaning that the polyesters comprise substantially unordered regions of polymer.

#### BRIEF DESCRIPTION OF THE DRAWINGS

40 [0129] Figure 1 is a graph showing the effect of comonomer on the fastest crystallization half-times of modified PCT copolyesters.

[0130] Figure 2 is a graph showing the effect of comonomer on the brittle-to-ductile transition temperature (T<sub>bd</sub>) in a notched Izod impact strength test (ASTM D256, 3.2 mm (1/8-in) thick, 254 μm (1 0-mil) notch).

[0131] Figure 3 is a graph showing the effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol composition on the glass transition temperature (T<sub>g</sub>) of the copolyester.

#### DETAILED DESCRIPTION OF THE INVENTION

45 [0132] The present invention may be understood more readily by reference to the following detailed description of

embodiments of the invention and the working examples. In accordance with the purpose(s) of this invention, certain embodiments of the invention are described in the Summary of the Invention and are further described herein below. Also, other embodiments of the invention are described herein.

5 [0133] The term "bottle" as used herein is understood to mean a receptacle containing plastic which is capable of storing or holding liquid.

[0134] It is believed that polyesters and/or polyester composition(s) which are included in the bottles of the invention can have a unique combination of two or more physical properties such as moderate or high impact strengths, high glass transition temperatures, chemical resistance, hydrolytic stability, toughness, low ductile-to-brittle transition temperatures, good color and clarity, low densities, and long crystallization half-times, and good processability thereby easily permitting them to be formed into articles. In some of the embodiments of the invention, the polyesters have a unique combination of the properties of good impact strength, heat resistance, chemical resistance, density and/or the combination of the properties of good impact strength, heat resistance, and processability and/or the combination of two or more of the described properties, that have never before been believed to be present in bottles comprising the polyester compositions which comprise the polyester(s) as disclosed herein.

15 [0135] Applications in the industry for these types of bottles include but are not limited to food, beverage, cosmetics and personal care applications.

[0136] The term "polyester", as used herein, is intended to include "copolyesters" and is understood to mean a synthetic polymer prepared by the reaction of one or more difunctional carboxylic acids and/or multifunctional carboxylic acids with one or more difunctional hydroxyl compounds and/or multifunctional hydroxyl compounds. Typically the difunctional carboxylic acid can be a dicarboxylic acid and the difunctional hydroxyl compound can be a dihydric alcohol such as, for example, glycols and diols. The term "glycol" as used herein includes, but is not limited to, diols, glycols, and/or multifunctional hydroxyl compounds, for example, branching agents. Alternatively, the difunctional carboxylic acid may be a hydroxy carboxylic acid such as, for example, p-hydroxybenzoic acid, and the difunctional hydroxyl compound may be an aromatic nucleus bearing 2 hydroxyl substituents such as, for example, hydroquinone. The term "residue", as used herein, means any organic structure incorporated into a polymer through a polycondensation and/or an esterification reaction from the corresponding monomer. The term "repeating unit", as used herein, means an organic structure having a dicarboxylic acid residue and a diol residue bonded through a carbonyloxy group. Thus, for example, the dicarboxylic acid residues may be derived from a dicarboxylic acid monomer or its associated acid halides, esters, salts, anhydrides, or mixtures thereof. Furthermore, as used herein, the term "diacid" includes multifunctional acids, for example, branching agents. As used herein, therefore, the term "dicarboxylic acid" is intended to include dicarboxylic acids and any derivative of a dicarboxylic acid, including its associated acid halides, esters, half-esters, salts, half-salts, anhydrides, mixed anhydrides, or mixtures thereof, useful in a reaction process with a diol to make polyester. As used herein, the term "terephthalic acid" is intended to include terephthalic acid itself and residues thereof as well as any derivative of terephthalic acid, including its associated acid halides, esters, half-esters, salts, half-salts, anhydrides, mixed anhydrides, or mixtures thereof or residues thereof useful in a reaction process with a diol to make polyester.

30 [0137] In one embodiment, terephthalic acid may be used as the starting material. In another embodiment, dimethyl terephthalate may be used as the starting material. In yet another embodiment, mixtures of terephthalic acid and dimethyl terephthalate may be used as the starting material and/or as an intermediate material.

[0138] The polyesters used in the bottles of the present invention typically can be prepared from dicarboxylic acids and diols which react in substantially equal proportions and are incorporated into the polyester polymer as their corresponding residues. The polyesters of the bottles of the present invention, therefore, can contain substantially equal molar proportions of acid residues (100 mole%) and diol (and/or multifunctional hydroxyl compound) residues (100 mole%) such that the total moles of repeating units is equal to 100 mole%. The mole percentages provided in the present disclosure, therefore, may be based on the total moles of acid residues, the total moles of diol residues, or the total moles of repeating units. For example, a polyester containing 30 mole% isophthalic acid, based on the total acid residues, means the polyester contains 30 mole% isophthalic acid residues out of a total of 100 mole% acid residues. Thus, there are 30 moles of isophthalic acid residues among every 100 moles of acid residues. In another example, a polyester containing 30 mole% 2,2,4,4-tetramethyl-1,3-cyclobutanediol, based on the total diol residues, means the polyester contains 30 mole% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues out of a total of 100 mole% diol residues. Thus, there are 30 moles of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues among every 100 moles of diol residues.

40 [0139] In other aspects of the invention, the T<sub>g</sub> of the polyesters useful in the bottles of the invention can be at least one of the following ranges: 60 to 200°C; 60 to 190°C; 60 to 180°C; 60 to 170°C; 60 to 160°C; 60 to 155°C; 60 to 150°C; 60 to 145°C; 60 to 140°C; 60 to 138°C; 60 to 135°C; 60 to 130°C; 60 to 125°C; 60 to 120°C; 60 to 115°C; 60 to 110°C; 60 to 105°C; 60 to 100°C; 60 to 95°C; 60 to 90°C; 60 to 85°C; 60 to 80°C; 60 to 75°C; 65 to 200°C; 65 to 190°C; 65 to 180°C; 65 to 170°C; 65 to 160°C; 65 to 155°C; 65 to 150°C; 65 to 145°C; 65 to 140°C; 65 to 138°C; 65 to 135°C; 65 to 130°C; 65 to 125°C; 65 to 120°C; 65 to 115°C; 65 to 110°C; 65 to 105°C; 65 to 100°C; 65 to 95°C; 65 to 90°C; 65 to 85°C; 65 to 80°C; 65 to 75°C; 70 to 200°C; 70 to 190°C; 70 to 180°C; 70 to 170°C; 70 to 160°C; 70 to 155°C; 70 to 150°C; 70 to 145°C; 70 to 140°C; 70 to 138°C; 70 to 135°C; 70 to 130°C; 70 to 125°C; 70 to 120°C; 70 to 115°C; 70 to













and 40 to less than 50 mole % 1,4-cyclohexanedimethanol.

**[0159]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 55 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 45 mole % 1,4-cyclohexanedimethanol; and 55 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 45 mole % 1,4-cyclohexanedimethanol.

**[0160]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 60 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 40 mole % 1,4-cyclohexanedimethanol; and 60 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 40 mole % 1,4-cyclohexanedimethanol.

**[0161]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 65 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 35 mole % 1,4-cyclohexanedimethanol; and 65 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 35 mole % 1,4-cyclohexanedimethanol.

**[0162]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 70 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 30 mole % 1,4-cyclohexanedimethanol.

**[0163]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 75 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 25 mole % 1,4-cyclohexanedimethanol; and 75 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 25 mole % 1,4-cyclohexanedimethanol.

**[0164]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 80 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 20 mole % 1,4-cyclohexanedimethanol; 80 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 20 mole % 1,4-cyclohexanedimethanol; 80 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 20 mole % 1,4-cyclohexanedimethanol.

**[0165]** In other aspects of the invention, the glycol component for the polyesters useful in the bottles of the invention include but are not limited to at least one of the following combinations of ranges: 37 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 63 mole % 1,4-cyclohexanedimethanol; 40 to less than 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 55 to 60 mole % 1,4-cyclohexanedimethanol; greater than 45 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to less than 55 mole % 1,4-cyclohexanedimethanol; and 46 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 54 mole % 1,4-cyclohexanedimethanol; and 46 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 54 mole % 1,4-cyclohexanedimethanol.

**[0166]** In other aspects of the invention where the mole percent of 2,2,4,4-tetramethyl-1,3-cyclobutanediol is present at 0.01 to less than 5 mole % based on the mole percentages for the diol component equaling 100 mole % and where the presence of CHDM is optional, the glycol component for the polyesters useful the bottles of the invention include

but are not limited to at least of the following combinations of ranges: 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 95 mole % of ethylene glycol residues, and 0 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 94.99 mole % of ethylene glycol residues, and 0.01 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 90 mole % of ethylene glycol residues, and 5 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 85 mole % of ethylene glycol residues, and 10 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 80 mole % of ethylene glycol residues, and 15 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 75 mole % of ethylene glycol residues, and 20 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 70 mole % of ethylene glycol residues, and 25 to 99.98 mole % of 1, 4-cyclohexanedimethanol; greater than 0.01 to 65 mole % of ethylene glycol residues, and 30 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole-% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 60 mole % of ethylene glycol residues, and 35 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 55 mole % of ethylene glycol residues, and 40 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 50 mole % of ethylene glycol residues, and 45 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 45 mole % of ethylene glycol residues, and 50 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 40 mole % of ethylene glycol residues, and 55 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 35 mole % of ethylene glycol residues, and 60 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 30 mole % of ethylene glycol residues, and 65 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 25 mole % of ethylene glycol residues, and 70 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 20 mole % of ethylene glycol residues, and 75 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 15 mole % of ethylene glycol residues, and 80 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 10 mole % of ethylene glycol residues, and 85 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, greater than 0.01 to 5 mole % of ethylene glycol residues, and 90 to 99.98 mole % of 1, 4-cyclohexanedimethanol; 0.01 to less than 5 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and greater than 0.01 to 5 mole % of ethylene glycol residues, and 90 to 99.98 mole % of 1, 4-cyclohexanedimethanol.

**[0167]** The glycol component may also contain one of the following ranges of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues: 0.01 to 4.5 mole %; 0.01 to 4 mole %; 0.01 to 3.5 mole %; 0.01 to 3 mole %; 0.01 to 2.5 mole %; 0.01 to 2.0 mole %; 0.01 to 2.5 mole %; 0.01 to 2 mole %; 0.01 to 1.5 mole %; 0.01 to 1.0 mole %; and 0.01 to 0.5 mole %. The remainder of the glycol component can be any amount of 1,4-cyclohexanedimethanol and/or ethylene glycol so long as the total amount of the glycol component equals 100 mole %.

**[0168]** In addition to the diols set forth above, the polyesters useful in the polyester compositions useful in the bottles of the invention may be made from 1,3-propanediol, 1,4-butanediol, or mixtures thereof. It is contemplated that compositions useful in the bottles of the invention made from 1,3-propanediol, 1,4-butanediol, or mixtures thereof can possess at least one of the Tg ranges described herein, at least one of the inherent viscosity ranges described herein, and/or at least one of the glycol or diacid ranges described herein. In addition or in the alternative, the polyesters made from 1,3-propanediol or 1,4-butanediol or mixtures thereof may also be made from 1,4-cyclohexanedimethanol in at least one of the following amounts: from 0.1 to 99 mole %; 0.1 to 90 mole %; from 0.1 to 80 mole %; from 0.1 to 70 mole %; from 0.1 to 60 mole %; from 0.1 to 50 mole %; from 0.1 to 40 mole %; from 0.1 to 35 mole %; from 0.1 to 30 mole %; from 0.1 to 25 mole %; from 0.1 to 20 mole %; from 0.1 to 15 mole %; from 0.1 to 10 mole %; from 0.1 to 5 mole %; from 1 to 99 mole %; from 1 to 90 mole %; from 1 to 80 mole %; from 1 to 70 mole %; from 1 to 60 mole %; from 1 to 50 mole %; from 1 to 40 mole %; from 1 to 35 mole %; from 1 to 30 mole %; from 1 to 25 mole %; from 1 to 20 mole %; from 1 to 15 mole %; from 1 to 10 mole %; from 1 to 5 mole %; from 5 to 99 mole %; from 5 to 90 mole %; from 5 to 80 mole %; from 5 to 70 mole %; from 5 to 60 mole %; from 5 to 50 mole %; from 5 to 40 mole %; from 5 to 35 mole %; from 5 to 30 mole %; from 5 to 25 mole %; from 5 to 20 mole %; and from 5 to 15 mole %; from 5 to 10 mole %; from 10 to 99 mole %; from 10 to 90 mole %; from 10 to 80 mole %; from 10 to 70 mole %; from 10 to 60 mole %; from 10 to 50 mole %; from 10 to 40 mole %; from 10 to 35 mole %; from 10 to 30 mole %; from 10 to 25 mole %; from 10 to 20 mole %; from 10 to 15 mole %; from 20 to 99 mole %; from 20 to 80 mole %; from 20 to 70 mole %; from 20 to 60 mole %; from 20 to 50 mole %; from 20 to 40 mole %; from 20 to 35 mole %; from 20 to 30 mole %; and from 20 to 25 mole %.

**[0169]** For embodiments of the invention, the polyesters useful in the bottles of the invention may exhibit at least one of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.10 to 1.2 dL/g; 0.10 to 1.1 dL/g; 0.10 to 1 dL/g; 0.10 to less than 1 dL/g; 0.10 to 0.98 dL/g; 0.10 to 0.95 dL/g; 0.10 to 0.90 dL/g; 0.10 to 0.85 dL/g; 0.10 to 0.80 dL/g; 0.10 to 0.75 dL/g; 0.10 to less than 0.75 dL/g; 0.10 to 0.72 dL/g; 0.10 to 0.70 dL/g; 0.10 to less than 0.70 dL/g; 0.10 to 0.68 dL/g; 0.10 to less than 0.68 dL/g; 0.10 to 0.65 dL/g; 0.10 to 0.6 dL/g; 0.10 to 0.55 dL/g; 0.10 to 0.5 dL/g; 0.10 to 0.4 dL/g; 0.10 to 0.35 dL/g; 0.20 to 1.2 dL/g; 0.20 to 1.1 dL/g; 0.20 to 1 dL/g; 0.20 to less than 1 dL/g; 0.20 to 0.98 dL/g; 0.20 to 0.95 dL/g; 0.20 to 0.90 dL/g; 0.20 to 0.85 dL/g; 0.20 to 0.80 dL/g; 0.20 to 0.75 dL/g; 0.20 to less than 0.75 dL/g; 0.20 to 0.72 dL/g; 0.20 to 0.70 dL/g; 0.20 to less than 0.70 dL/g; 0.20 to 0.68 dL/g; 0.20 to less than 0.68 dL/g; 0.20 to 0.65 dL/g; 0.20 to 0.6 dL/g; 0.20 to 0.55 dL/g; 0.20 to 0.5 dL/g; 0.20 to 0.4 dL/g; 0.20 to 0.35 dL/g; 0.35 to 1.2 dL/g; 0.35 to 1.1 dL/g; 0.35 to 1 dL/g; 0.35 to less than 1 dL/g; 0.35 to 0.98 dL/g; 0.35 to 0.95 dL/g; 0.35 to 0.90 dL/g; 0.35 to 0.85 dL/g; 0.35 to 0.80 dL/g; 0.35 to 0.75 dL/g; 0.35 to less than 0.75 dL/g; 0.35 to 0.72 dL/g; 0.35 to 0.70 dL/g; 0.35 to less than 0.70 dL/g; 0.35 to 0.68 dL/g; 0.35 to less than 0.68 dL/g; 0.35 to 0.65 dL/g; 0.40 to 1.2 dL/g; 0.40 to 1.1 dL/g; 0.40 to 1 dL/g; 0.40 to less than 1 dL/g; 0.40 to 0.98 dL/g; 0.40 to 0.95 dL/g; 0.40 to 0.90 dL/g; 0.40 to 0.85 dL/g; 0.40 to 0.80 dL/g; 0.40 to 0.75 dL/g; 0.40 to less than 0.75 dL/g; 0.40 to 0.72 dL/g; 0.40 to 0.70 dL/g; 0.40 to less than 0.70 dL/g; 0.40 to 0.68 dL/g; 0.40 to less than 0.68 dL/g; 0.40 to 0.65 dL/g; greater than 0.42 to 1.2 dL/g; greater than 0.42 to 1.1 dL/g; greater than 0.42 to 1 dL/g; greater than 0.42 to less than 1 dL/g; greater than 0.42 to 0.98 dL/g; greater than 0.42 to 0.95 dL/g; greater than 0.42 to 0.90 dL/g; greater than 0.42 to 0.85 dL/g; greater than 0.42 to 0.80 dL/g; greater than 0.42 to 0.75 dL/g; greater than 0.42 to less than 0.75 dL/g; greater than 0.42 to 0.72 dL/g; greater than 0.42 to 0.70 dL/g; greater than 0.42 to less than 0.70 dL/g; greater than 0.42 to 0.68 dL/g; and greater than 0.42 to 0.65 dL/g.

**[0170]** For embodiments of the invention, the polyesters useful in the bottles of the invention may exhibit at least one of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.45 to 1.2 dL/g; 0.45 to 1.1 dL/g; 0.45 to 1 dL/g; 0.45 to 0.98 dL/g; 0.45 to 0.95 dL/g; 0.45 to 0.90 dL/g; 0.45 to 0.85 dL/g; 0.45 to 0.80 dL/g; 0.45 to 0.75 dL/g; 0.45 to less than 0.75 dL/g; 0.45 to 0.72 dL/g; 0.45 to 0.70 dL/g; 0.45 to less than 0.70 dL/g; 0.45 to 0.68 dL/g; 0.45 to less than 0.68 dL/g; 0.45 to 0.65 dL/g; 0.50 to 1.2 dL/g; 0.50 to 1.1 dL/g; 0.50 to 1 dL/g; 0.50 to less than 1 dL/g; 0.50 to 0.98 dL/g; 0.50 to 0.95 dL/g; 0.50 to 0.90 dL/g; 0.50 to 0.85 dL/g; 0.50 to 0.80 dL/g; 0.50 to 0.75 dL/g; 0.50 to less than 0.75 dL/g; 0.50 to 0.72 dL/g; 0.50 to 0.70 dL/g; 0.50 to less than 0.70 dL/g; 0.50 to 0.68 dL/g; 0.50 to less than 0.68 dL/g; 0.50 to 0.65 dL/g; 0.55 to 1.2 dL/g; 0.55 to 1.1 dL/g; 0.55 to 1 dL/g; 0.55 to less than 1 dL/g; 0.55 to 0.98 dL/g; 0.55 to 0.95 dL/g; 0.55 to 0.90 dL/g; 0.55 to 0.85 dL/g; 0.55 to 0.80 dL/g; 0.55 to 0.75 dL/g; 0.55 to less than 0.75 dL/g; 0.55 to 0.72 dL/g; 0.55 to 0.70 dL/g; 0.55 to less than 0.70 dL/g; 0.55 to 0.68 dL/g; 0.55 to less than 0.68 dL/g; 0.55 to 0.65 dL/g; 0.58 to 1.2 dL/g; 0.58 to 1.1 dL/g; 0.58 to 1 dL/g; 0.58 to less than 1 dL/g; 0.58 to 0.98 dL/g; 0.58 to 0.95 dL/g; 0.58 to 0.90 dL/g; 0.58 to 0.85 dL/g; 0.58 to 0.80 dL/g; 0.58 to 0.75 dL/g; 0.58 to less than 0.75 dL/g; 0.58 to 0.72 dL/g; 0.58 to 0.70 dL/g; 0.58 to less than 0.70 dL/g; 0.58 to 0.68 dL/g; 0.58 to less than 0.68 dL/g; 0.58 to 0.65 dL/g; 0.60 to 1.2 dL/g; 0.60 to 1.1 dL/g; 0.60 to 1 dL/g; 0.60 to less than 1 dL/g; 0.60 to 0.98 dL/g; 0.60 to 0.95 dL/g; 0.60 to 0.90 dL/g; 0.60 to 0.85 dL/g; 0.60 to 0.80 dL/g; 0.60 to 0.75 dL/g; 0.60 to less than 0.75 dL/g; 0.60 to 0.72 dL/g; 0.60 to 0.70 dL/g; 0.60 to less than 0.70 dL/g; 0.60 to 0.68 dL/g; 0.60 to less than 0.68 dL/g; 0.60 to 0.65 dL/g; 0.65 to 1.2 dL/g; 0.65 to 1.1 dL/g; 0.65 to 1 dL/g; 0.65 to less than 1 dL/g; 0.65 to 0.98 dL/g; 0.65 to 0.95 dL/g; 0.65 to 0.90 dL/g; 0.65 to 0.85 dL/g; 0.65 to 0.80 dL/g; 0.65 to 0.75 dL/g; 0.65 to less than 0.75 dL/g; 0.65 to 0.72 dL/g; 0.65 to 0.70 dL/g; 0.65 to less than 0.70 dL/g; 0.68 to 1.2 dL/g; 0.68 to 1.1 dL/g; 0.68 to 1 dL/g; 0.68 to less than 1 dL/g; 0.68 to 0.98 dL/g; 0.68 to 0.95 dL/g; 0.68 to 0.90 dL/g; 0.68 to 0.85 dL/g; 0.68 to 0.80 dL/g; 0.68 to 0.75 dL/g; 0.68 to less than 0.75 dL/g; 0.68 to 0.72 dL/g; greater than 0.76 dL/g to 1.2 dL/g; greater than 0.76 dL/g to 1.1 dL/g; greater than 0.76 dL/g to 1 dL/g; greater than 0.76 dL/g to less than 1 dL/g; greater than 0.76 dL/g to 0.98dL/g; greater than 0.76 dL/g to 0.95 dL/g; greater than 0.76 dL/g to 0.90 dL/g; greater than 0.80 dL/g to 1.2 dL/g; greater than 0.80 dL/g to 1.1 dL/g; greater than 0.80 dL/g to 1 dL/g; greater than 0.80 dL/g to less than 1 dL/g; greater than 0.80 dL/g to 1.2 dL/g; greater than 0.80 dL/g to 0.98dL/g; greater than 0.80 dL/g to 0.95 dL/g; greater than 0.80 dL/g to 0.90 dL/g.

**[0171]** For the desired polyester, the molar ratio of cis/trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol can vary from the pure form of each or mixtures thereof. In certain embodiments, the molar percentages for cis and/or trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol are greater than 50 mole % cis and less than 50 mole % trans; or greater than 55 mole % cis and less than 45 mole % trans; or 30 to 70 mole % cis and 70 to 30 mole % trans; or 40 to 60 mole % cis and 60 to 40 mole % trans; or 50 to 70 mole % trans and 50 to 30 % cis; or 50 to 70 mole % cis and 50 to 30 % trans; or 60 to 70 mole % cis and 30 to 40 mole % trans; or greater than 70 mole % cis and less than 30 mole % trans; wherein the total sum of the mole percentages for cis- and trans- 2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to 100 mole %. The molar ratio of cis/trans 1,4-cyclohexandimethanol can vary within the range of 50/50 to 0/100, for example, between 40/60 to 20/80.

**[0172]** It is contemplated that compositions useful in the bottles of the invention can possess at least one of the inherent viscosity ranges described herein and at least one of the monomer ranges for the compositions described herein unless otherwise stated. It is also contemplated that compositions useful in the bottles of the invention can possess at least

one of the Tg ranges described herein and at least one of the monomer ranges for the compositions described herein unless otherwise stated. It is also contemplated that compositions useful in the bottles of the invention can possess at least one of the inherent viscosity ranges described herein, at least one of the Tg ranges described herein, and at least one of the monomer ranges for the compositions described herein unless otherwise stated.

5 **[0173]** In certain embodiments, terephthalic acid or an ester thereof, such as, for example, dimethyl terephthalate or a mixture of terephthalic acid residues and an ester thereof can make up a portion or all of the dicarboxylic acid component used to form the polyesters useful in bottles of the invention. In certain embodiments, terephthalic acid residues can make up a portion or all of the dicarboxylic acid component used to form the polyesters useful in the bottles of the invention at a concentration of at least 70 mole %, such as at least 80 mole %, at least 90 mole % at least 95 mole %, 10 at least 99 mole %, or even 100 mole %. In certain embodiments, higher amounts of terephthalic acid can be used in order to produce a higher impact strength polyester useful in the bottles of the invention. For purposes of this disclosure, the terms "terephthalic acid" and "dimethyl terephthalate" are used interchangeably herein. In one embodiment, dimethyl terephthalate is part or all of the dicarboxylic acid component used to make the polyesters useful in the present invention. For the purposes of this disclosure, the terms "terephthalic acid" and "dimethyl terephthalate" are used interchangeably 15 herein. In all embodiments, ranges of from 70 to 100 mole %; or 80 to 100 mole %; or 90 to 100 mole %; or 99 to 100 mole %; or 100 mole % terephthalic acid and/or dimethyl terephthalate and/or mixtures thereof may be used.

**[0174]** In addition to terephthalic acid, the dicarboxylic acid component of the polyester useful in the invention can comprise up to 30 mole %, up to 20 mole %, up to 10 mole %, up to 5 mole %, or up to 1 mole % of one or more modifying aromatic dicarboxylic acids. Yet another embodiment contains 0 mole % modifying aromatic dicarboxylic acids. Thus, 20 if present, it is contemplated that the amount of one or more modifying aromatic dicarboxylic acids can range from any of these preceding endpoint values including, for example, from 0.01 to 30 mole %, 0.01 to 20 mole %, from 0.01 to 10 mole %, from 0.01 to 5 mole % and from 0.01 to 1 mole. In one embodiment, modifying aromatic dicarboxylic acids that may be used in the present invention include but are not limited to those having up to 20 carbon atoms, and which can be linear, para-oriented, or symmetrical. Examples of modifying aromatic dicarboxylic acids which may be used in this 25 invention include, but are not limited to, isophthalic acid, 4,4'-biphenyldicarboxylic acid, 1,4-, 1,5-, 2,6-, 2,7-naphthalenedicarboxylic acid, and trans-4,4'-stilbenedicarboxylic acid, and esters thereof. In one embodiment, the modifying aromatic dicarboxylic acid is isophthalic acid.

**[0175]** The carboxylic acid component of the polyesters useful in the bottles of the invention can be further modified with up to 10 mole %, such as up to 5 mole % or up to 1 mole % of one or more aliphatic dicarboxylic acids containing 30 2-16 carbon atoms, such as, for example, malonic, succinic, glutaric, adipic, pimelic, suberic, azelaic and dodecanedioic dicarboxylic acids. Certain embodiments can also comprise 0.01 or more mole %, such as 0.1 or more mole %, 1 or more mole %, 5 or more mole %, or 10 or more mole % of one or more modifying aliphatic dicarboxylic acids. Yet another embodiment contains 0 mole % modifying aliphatic dicarboxylic acids. Thus, if present, it is contemplated that the amount of one or more modifying aliphatic dicarboxylic acids can range from any of these preceding endpoint values including, 35 for example, from 0.01 to 10 mole % and from 0.1 to 10 mole %. The total mole % of the dicarboxylic acid component is 100 mole %.

**[0176]** Esters of terephthalic acid and the other modifying dicarboxylic acids or their corresponding esters and/or salts may be used instead of the dicarboxylic acids. Suitable examples of dicarboxylic acid esters include, but are not limited to, the dimethyl, diethyl, dipropyl, diisopropyl, dibutyl, and diphenyl esters. In one embodiment, the esters are chosen 40 from at least one of the following: methyl, ethyl, propyl, isopropyl, and phenyl esters.

**[0177]** The 1,4-cyclohexanedimethanol may be cis, trans, or a mixture thereof, for example, a cis/trans ratio of 60:40 to 40:60. In another embodiment, the trans-1,4-cyclohexanedimethanol can be present in an amount of 60 to 80 mole %.

**[0178]** The glycol component of the polyester portion of the polyester composition useful in the bottles of the invention can contain 25 mole % or less of one or more modifying glycols which are not 2,2,4,4-tetramethyl-1,3-cyclobutanediol or 1,4-cyclohexanedimethanol; in one embodiment, the polyesters useful in the bottles of the invention may contain less 45 than 15 mole % or of one or more modifying glycols. In another embodiment, the polyesters useful in the bottles of the invention can contain 10 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the bottles of the invention can contain 5 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the bottles of the invention can contain 3 mole % or less of one or more modifying glycols. In 50 another embodiment, the polyesters useful in the bottles of the invention can contain 0 mole % modifying glycols. Certain embodiments can also contain 0.01 or more mole %, such as 0.1 or more mole %, 1 or more mole %, 5 or more mole %, or 10 or more mole % of one or more modifying glycols. Thus, if present, it is contemplated that the amount of one or more modifying glycols can range from any of these preceding endpoint values including, for example, from 0.01 to 15 mole % and from 0.1 to 10 mole %.

55 **[0179]** Modifying glycols useful in the polyesters useful in the bottles of the invention refer to diols other than 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1,4-cyclohexanedimethanol and can contain 2 to 16 carbon atoms. Examples of suitable modifying glycols include, but are not limited to, ethylene glycol, 1,2-propanediol, 1,3-propanediol, neopentyl glycol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, p-xylene glycol, or mixtures thereof. In one embodiment, the

modifying glycol is ethylene glycol. In another embodiment, the modifying glycols include, but are not limited to, 1,3-propanediol and 1,4-butanediol. In another embodiment, ethylene glycol is excluded as a modifying diol. In another embodiment, 1,3-propanediol and 1,4-butanediol are excluded as modifying diols. In another embodiment, 2,2-dimethyl-1,3-propanediol is excluded as a modifying diol.

5 **[0180]** The polyesters and/or the polycarbonates useful in the polyesters compositions of the bottles of the invention can comprise from 0 to 10 mole percent, for example, from 0.01 to 5 mole percent, from 0.01 to 1 mole percent, from 0.05 to 5 mole percent, from 0.05 to 1. mole percent, or from 0.1 to 0.7 mole percent, based the total mole percentages of either the diol or diacid residues; respectively, of one or more residues of a branching monomer, also referred to herein as a branching agent, having 3 or more carboxyl substituents, hydroxyl substituents, or a combination thereof. In certain embodiments, the branching monomer or agent may be added prior to and/or during and/or after the polymerization of the polyester. The polyester(s) useful in the bottles of the invention can thus be linear or branched. The polycarbonate can also be linear or branched. In certain embodiments, the branching monomer or agent may be added prior to and/or during and/or after the polymerization of the polycarbonate.

10 **[0181]** Examples of branching monomers include, but are not limited to, multifunctional acids or multifunctional alcohols such as trimellitic acid, trimellitic anhydride, pyromellitic dianhydride, trimethylolpropane, glycerol, pentaerythritol, citric acid, tartaric acid, 3-hydroxyglutaric acid and the like. In one embodiment, the branching monomer residues can comprise 0.1 to 0.7 mole percent of one or more residues chosen from at least one of the following: trimellitic anhydride, pyromellitic dianhydride, glycerol, sorbitol, 1,2,6-hexanetriol, pentaerythritol, trimethylolethane, and/or trimesic acid. The branching monomer may be added to the polyester reaction mixture or blended with the polyester in the form of a concentrate as described, for example, in U.S. Patent Nos. 5,654,347 and 5,696,176, whose disclosure regarding branching monomers is incorporated herein by reference.

15 **[0182]** The glass transition temperature ( $T_g$ ) of the polyesters useful in the bottles of the invention was determined using a TA DSC 2920 from Thermal Analyst Instrument at a scan rate of 20°C/min.

20 **[0183]** Because of the long crystallization half-times (e.g., greater than 5 minutes) at 170°C exhibited by certain polyesters useful in the bottles of the invention, it can be possible to produce injection blow molded bottles, injection stretch blow molded bottles, extrusion blow molded bottles and extrusion stretch blow molded bottles. The polyesters useful in the bottles of the invention can be "amorphous" or semicrystalline. In one aspect, certain polyesters useful in the invention can have a relatively low crystallinity. Certain polyesters useful in the bottles of the invention can thus have a substantially amorphous morphology, meaning that the polyesters comprise substantially unordered regions of polymer.

25 **[0184]** In one embodiment, an "amorphous" polyester can have a crystallization half-time of greater than 5 minutes at 170°C or greater than 10 minutes at 170°C or greater than 50 minutes at 170 °C or greater than 100 minutes at 170°C. In one embodiment, of the invention, the crystallization half-times can be greater than 1,000 minutes at 170°C. In another embodiment of the invention, the crystallization half-times of the polyesters useful in the invention can be greater than 10,000 minutes at 170°C. The crystallization half time of the polyester, as used herein, may be measured using methods well-known to persons of skill in the art. For example, the crystallization half time of the polyester,  $t_{1/2}$ , can be determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage. This measurement can be done by exposing the polymers to a temperature,  $T_{max}$ , and then cooling it to the desired temperature. The sample can then be held at the desired temperature by a hot stage while transmission measurements are made as a function of time. Initially, the sample can be visually clear with high light transmission and becomes opaque as the sample crystallizes. The crystallization half-time is the time at which the light transmission is halfway between the initial transmission and the final transmission.  $T_{max}$  is defined as the temperature required to melt the crystalline domains of the sample (if crystalline domains are present). The sample can be heated to  $T_{max}$  to condition the sample prior to crystallization half time measurements. The absolute  $T_{max}$  temperature is different for each composition. For example PCT can be heated to some temperature greater than 290°C to melt the crystalline domains.

30 **[0185]** As shown in Table 1 and Figure 1 of the Examples, 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than other comonomers such ethylene glycol and isophthalic acid at increasing the crystallization half-time, i.e., the time required for a polymer to reach half of its maximum crystallinity. By decreasing the crystallization rate of PCT, i.e. increasing the crystallization half-time, amorphous articles based on modified PCT may be fabricated by methods known in the art such as extrusion, injection molding, and the like. As shown in Table 1, these materials can exhibit higher glass transition temperatures and lower densities than other modified PCT copolyesters.

35 **[0186]** The polyesters can exhibit an improvement in toughness combined with processability for some of the embodiments useful in the bottles of the invention. For example, lowering the inherent viscosity slightly of the polyesters useful in the bottles of the invention results in a more processable melt viscosity while retaining good physical properties of the polyesters such as toughness and heat resistance.

40 **[0187]** Increasing the content of 1,4-cyclohexanedimethanol in a copolyester based on terephthalic acid, ethylene glycol, and 1,4-cyclohexanedimethanol can improve toughness which can be determined by the brittle-to-ductile transition temperature in a notched Izod impact strength test as measured by ASTM D256. This toughness improvement, by lowering of the brittle-to-ductile transition temperature with 1,4-cyclohexanedimethanol, is believed to occur due to the

flexibility and conformational behavior of 1,4-cyclohexanedimethanol in the copolyester. Incorporating 2,2,4,4-tetramethyl-1,3-cyclobutanediol into PCT is believed to improve toughness, by lowering the brittle-to-ductile transition temperature, as shown in Table 2 and Figure 2 of the Examples. This is unexpected given the rigidity of 2,2,4,4-tetramethyl-1,3-cyclobutanediol.

5 **[0188]** In one embodiment, the melt viscosity of the polyester(s) useful in the bottles of the invention is less than 3,000 Pa\*s (30,000 poise) as measured at 1 radian/second on a rotary melt rheometer at 290°C. In another embodiment, the melt viscosity of the polyester(s) useful in the bottles of the invention is less than 2,000 Pa\*s (20,000 poise) as measured at 1 radian/second on a rotary melt rheometer at 290°C.

10 **[0189]** In one embodiment, the melt viscosity of the polyester(s) useful in the bottles of the invention is less than 1,500 Pa\*s (15,000 poise) as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290°C. In one embodiment, the melt viscosity of the polyester(s) useful in the bottles of the invention is less than 1,000 Pa\*s (10,000 poise) as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290°C. In another embodiment, the melt viscosity of the polyester(s) useful in the bottles of the invention is less than 600 Pa\*s (6,000 poise) as measured at 1 radian/second on a rotary melt rheometer at 290°C. Viscosity at rad/sec is related to processability. Typical polymers have viscosities of less than 1,000 Pa\*s (10,000 poise) as measured at 1 radian/second when measured at their processing temperature. Polyesters are typically not processed above 290°C. Polycarbonate is typically processed at 290°C. The viscosity at 1 rad/sec of a typical 12 melt flow rate polycarbonate is 700 Pa\*s (7000 poise at 290°C).

15 **[0190]** In one embodiment, certain polyesters useful in the bottles of the invention can be visually clear. The term "visually clear" is defined herein as an appreciable absence of cloudiness, haziness, and/or muddiness, when inspected visually. In another embodiment, when the polyesters are blended with polycarbonate, including but not limited to, bisphenol A polycarbonates, the blends can be visually clear.

20 **[0191]** In other embodiments of the invention, the polyesters useful in the bottles of the invention may have a yellowness index (ASTM D-1925) of less than 50 or less than 20.

25 **[0192]** In one embodiment, the polyesters useful in the bottles of the invention and/or the polyester compositions useful in the bottles of the invention, with or without toners, can have color values  $L^*$ ,  $a^*$  and  $b^*$  which were determined using a Hunter Lab Ultrascan Spectra Colorimeter manufactured by Hunter Associates Lab Inc., Reston, Va. The color determinations are averages of values measured on either pellets of the polyesters or plaques or other items injection molded or extruded from them. They are determined by the  $L^*a^*b^*$  color system of the CIE (International Commission on Illumination) (translated), wherein  $L^*$  represents the lightness coordinate,  $a^*$  represents the red/green coordinate, and  $b^*$  represents the yellow/blue coordinate. In certain embodiments, the  $b^*$  values for the polyesters useful in the invention can be from -10 to less than 10 and the  $L^*$  values can be from 50 to 90. In other embodiments, the  $b^*$  values for the polyesters useful in the invention can be present in one of the following ranges: from -10 to 9; -10 to 8; -10 to 7; -10 to 6; -10 to 5; -10 to 4; -10 to 3; -10 to 2; from -5 to 9; -5 to 8; -5 to 7; -5 to 6; -5 to 5; -5 to 4; -5 to 3; -5 to 2; 0 to 9; 0 to 8; 0 to 7; 0 to 6; 0 to 5; 0 to 4; 0 to 3; 0 to 2; 1 to 10; 1 to 9; 1 to 8; 1 to 7; 1 to 6; 1 to 5; 1 to 4; 1 to 3; and 1 to 2. In other embodiments, the  $L^*$  value for the polyesters useful in the invention can be present in one of the following ranges: 50 to 60; 50 to 70; 50 to 80; 50 to 90; 60 to 70; 60 to 80; 60 to 90; 70 to 80; 79 to 90.

30 **[0193]** In some embodiments, use of the polyester compositions useful in the bottles of the invention minimizes and/or eliminates the drying step prior to melt processing and/or thermoforming.

35 **[0194]** The present polyesters useful in the bottles of this invention can possess one or more of the following properties. Notched Izod impact strength, as described in ASTM D256, is a common method of measuring toughness: The present polyesters useful in the bottles of the invention can possess one or more of the following properties. In one embodiment, the polyesters useful in the bottles of the invention exhibit a impact strength of at least 150 J/m (3 ft-lb/in) at 23°C with a 254  $\mu\text{m}$  (10-mil) notch in a 3.2mm (1/8-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the bottles of the invention exhibit a notched Izod impact strength of at least 400 J/m (7.5 ft-lb/in) at 23°C with a 254  $\mu\text{m}$  (10-mil) notch in a 3.2mm (1/8-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the bottles of the invention exhibit a notched Izod impact strength of at least 1000 J/m (18 ft-lb/in) at 23°C with a 254  $\mu\text{m}$  (10-mil) notch in a 3.2mm (1/8-inch) thick bar determined according to ASTM D256. In one embodiment, the polyesters useful in the bottles of the invention exhibit a notched Izod impact strength of at least 150 J/m (3 ft-lb/in) at 23°C with a 254  $\mu\text{m}$  (10-mil) notch in a 6.4mm (1/4-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the bottles of the invention exhibit a notched Izod impact strength of at least 400 J/m (7.5 ft-lb/in) at 23°C with a 254  $\mu\text{m}$  (10-mil) notch in a 6.4mm (1/4-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the bottles of the invention exhibit a notched Izod impact strength of at least 1000 J/m (18 ft-lb/in) at 23°C with a 254  $\mu\text{m}$  (10-mil) notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256.

40 **[0195]** In another embodiment, certain polyesters useful in the bottles of the invention can exhibit an increase in notched Izod impact strength when measured at 0°C of at least 3% or at least 5% or at least 10% or at least 15% as compared to the notched Izod impact strength when measured at -5°C with a 254  $\mu\text{m}$  (10-mil) notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256. In addition, certain other polyesters useful in the bottles of the

invention can also exhibit a retention of notched Izod impact strength within plus or minus 5% when measured at 0°C through 30°C with a 254 μm (10-mil) notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256.

**[0196]** In yet another embodiment, certain polyesters useful in the bottles of the invention can exhibit a retention in notched Izod impact strength with a loss of no more than 70% when measured at 23°C with a 254 μm (10-mil) notch in a 6.4 mm (1/4-inch) thick bar determined according to ASTM D256 as compared to notched Izod impact strength for the same polyester when measured at the same temperature with a 254 μm (10-mil) notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256.

**[0197]** In one embodiment, the polyesters useful in the bottles of the invention can exhibit a ductile-to-brittle transition temperature of less than 0°C based on a 254 μm (10-mil) notch in a 3.2 mm (1/8-inch) thick bar as defined by ASTM D256.

**[0198]** In one embodiment, the polyesters useful in the bottles of the invention can exhibit at least one of the following densities: a density of less than 1.3 g/ml at 23°C; a density of less than 1.2 g/ml at 23°C; a density of less than 1.18 g/ml at 23°C; a density of 0.70 to 1.3 g/ml at 23°C; a density of 0.70 to 1.2 g/ml at 23°C; a density of 0.70 to less than 1.2 g/ml at 23°C; a density of 0.75 to 1.3 g/ml at 23°C; a density of 0.75 to 1.2 at 23°C; a density of 0.75 g/ml to less than 1.2 at 23°C; a density of 0.80 g/ml to 1.3 at 23°C; a density of 0.80 g/ml to 1.2 at 23°C; a density of 0.80 to less than 1.2 g/ml at 23°C; a density of 0.90 g/ml to 1.3 at 23°C; a density of 0.90 to 1.2 g/ml at 23°C; a density of 0.90 to less than 1.2 g/ml at 23°C; a density of 1.0 to 1.3 g/ml at 23°C, a density of 1.0 to 1.2 g/ml at 23°C; a density of 1.1 to 1.3 g/ml at 23°C; a density of 1.1 to 1.2 g/ml at 23°C; a density of 1.13 to 1.3 g/ml at 23°C, a density of 1.13 to 1.2 g/ml at 23°C; a density of 0.80 to 1.18 at 23°C; a density of 0.80 to less than 1.18 g/ml at 23°C; a density of 1.0 to less than 1.18 g/ml at 23°C; and a density of 1.1 to less than 1.18 g/ml at 23°C.

**[0199]** In one embodiment, polyesters useful in the invention exhibit superior notched toughness in thick sections. Notched Izod impact strength, as described in ASTM D256, is a common method of measuring toughness. When tested by the Izod method, polymers can exhibit either a complete break failure mode, where the test specimen breaks into two distinct parts, or a partial or no break failure mode, where the test specimen remains as one part. The complete break failure mode is associated with low energy failure. The partial and no break failure modes are associated with high energy failure. A typical thickness used to measure Izod toughness is 3.2 mm (1/8"). At this thickness, very few polymers are believed to exhibit a partial or no break failure mode, polycarbonate being one notable example. When the thickness of the test specimen is increased to 6.4 mm (1/4"), however, no commercial amorphous materials exhibit a partial or no break failure mode. In one embodiment, compositions of the present example exhibit a no break failure mode when tested in Izod using a 6.4 mm (1/4") thick specimen.

**[0200]** In some embodiments, use of the polyester compositions useful in the bottles of the invention minimizes and/or eliminates the drying step prior to melt processing and/or thermoforming.

**[0201]** The polyester portion of the polyester compositions useful in the bottles of the invention can be made by processes known from the literature such as, for example, by processes in homogenous solution, by transesterification processes in the melt, and by two phase interfacial processes. Suitable methods include, but are not limited to, the steps of reacting one or more dicarboxylic acids with one or more glycols at a temperature of 100°C to 315°C at a pressure of 13.33 Pa to 101,308 Pa (0.1 to 760 mm Hg) for a time sufficient to form a polyester. See U.S. Patent No. 3,772,405 for methods of producing polyesters.

**[0202]** In another aspect, the invention relates to bottles comprising a polyester produced by a process comprising:

- (I) heating a mixture comprising the monomers useful in any of the polyesters useful in the invention in the presence of a catalyst at a temperature of 150 to 240°C for a time sufficient to produce an initial polyester;
- (II) heating the initial polyester of step (I) at a temperature of 240 to 320°C for 1 to 4 hours; and
- (III) removing any unreacted glycols.

**[0203]** Suitable catalysts for use in this process include, but are not limited to, organo-zinc or tin compounds. The use of this type of catalyst is well known in the art. Examples of catalysts useful in the present invention include, but are not limited to, zinc acetate, butyltin tris-2-ethylhexanoate, dibutyltin diacetate, and dibutyltin oxide. Other catalysts may include, but are not limited to, those based on titanium, zinc, manganese, lithium, germanium, and cobalt. Catalyst amounts can range from 10 ppm to 20,000 ppm or 10 to 10,000 ppm, or 10 to 5000 ppm or 10 to 1000 ppm or 10 to 500 ppm, or 10 to 300 ppm or 10 to 250 based on the catalyst metal and based on the weight of the final polymer. The process can be carried out in either a batch or continuous process.

**[0204]** Typically, step (I) can be carried out until 50% by weight or more of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol has been reacted. Step (I) may be carried out under pressure, ranging from atmospheric pressure to 689,475 Pa (100 psig). The term "reaction product" as used in connection with any of the catalysts useful in the invention refers to any product of a polycondensation or esterification reaction with the catalyst and any of the monomers used in making the polyester as well as the product of a polycondensation or esterification reaction between the catalyst and any other type of additive.

**[0205]** Typically, Step (II) and Step (III) can be conducted at the same time. These steps can be carried out by methods

known in the art such as by placing the reaction mixture under a pressure ranging, from 1.4 Pa (0.002 psig) to below atmospheric pressure, or by blowing hot nitrogen gas over the mixture.

**[0206]** The invention further relates to a polymer blend useful in the bottles of the invention. The blend comprises:

5 (a) from 5 to 95 wt % of at least one of the polyesters described above; and

(b) from 5 to 95 wt % of at least one of the polymeric components.

10 **[0207]** Suitable examples of the polymeric components include, but are not limited to, nylon; polyesters different than those described herein; polyamides such as ZYTEL® from DuPont; polystyrene; polystyrene copolymers; styrene acrylonitrile copolymers; acrylonitrile butadiene styrene copolymers; poly(methylmethacrylate); acrylic copolymers; poly(ether-imides) such as ULTEM® (a poly(ether-imide) from General Electric); polyphenylene oxides such as poly(2,6-dimethylphenylene oxide) or poly(phenylene oxide)/polystyrene blends such as NORYL 1000® (a blend of poly(2,6-dimethylphenylene oxide) and polystyrene resins from General Electric); polyphenylene sulfides; polyphenylene sulfide/sulfones; poly(ester-carbonates); polycarbonates such as LEXAN® (a polycarbonate from General Electric); polysulfones; polysulfone ethers; and poly(ether-ketones) of aromatic dihydroxy compounds; or mixtures of any of the foregoing polymers. The blends can be prepared by conventional processing techniques known in the art, such as melt blending or solution blending. In one embodiment, polycarbonate is not present in the polyester composition useful in the bottles of the invention. If polycarbonate is used in a blend in the polyester compositions of the bottles of the invention, the blends can be visually clear. However, polyester compositions useful in the bottles of the invention also contemplate the exclusion of polycarbonate as well as the inclusion of polycarbonate.

20 **[0208]** Polycarbonates useful in the bottles of the invention may be prepared according to known procedures, for example, by reacting the dihydroxyaromatic compound with a carbonate precursor such as phosgene, a haloformate or a carbonate ester, a molecular weight regulator, an acid acceptor and a catalyst. Methods for preparing polycarbonates are known in the art and are described, for example, in U.S. Patent 4,452,933, where the disclosure regarding the preparation of polycarbonates is hereby incorporated by reference herein.

25 **[0209]** Examples of suitable carbonate precursors include, but are not limited to, carbonyl bromide, carbonyl chloride, or mixtures thereof; diphenyl carbonate; a di(halophenyl)carbonate, e.g., di(trichlorophenyl) carbonate, di(tribromophenyl) carbonate, and the like; di(alkylphenyl)carbonate, e.g., di(tolyl)carbonate; di(naphthyl)carbonate; di(chloronaphthyl) carbonate, or mixtures thereof; and bis-haloformates of dihydric phenols.

30 **[0210]** Examples of suitable molecular weight regulators include, but are not limited to, phenol, cyclohexanol, methanol, alkylated phenols, such as octylphenol, para-tertiary-butyl-phenol, and the like. In one embodiment, the molecular weight regulator is phenol or an alkylated phenol.

35 **[0211]** The acid acceptor may be either an organic or an inorganic acid acceptor. A suitable organic acid acceptor can be a tertiary amine and includes, but is not limited to, such materials as pyridine, triethylamine, dimethylaniline, tributylamine, and the like. The inorganic acid acceptor can be either a hydroxide, a carbonate, a bicarbonate, or a phosphate of an alkali or alkaline earth metal.

40 **[0212]** The catalysts that can be used include, but are not limited to, those that typically aid the polymerization of the monomer with phosgene. Suitable catalysts include, but are not limited to, tertiary amines such as triethylamine, tripropylamine, N,N-dimethylaniline, quaternary ammonium compounds such as, for example, tetraethylammonium bromide, cetyl triethyl ammonium bromide, tetra-n-heptylammonium iodide, tetra-n-propyl ammonium bromide, tetramethyl ammonium chloride, tetra-methyl ammonium hydroxide, tetra-n-butyl ammonium iodide, benzyltrimethyl ammonium chloride and quaternary phosphonium compounds such as, for example, n-butyltriphenyl phosphonium bromide and methyltriphenyl phosphonium bromide.

45 **[0213]** The polycarbonates useful in the polyester compositions useful in the bottles of the invention also may be copolyestercarbonates such as those described in U.S. Patents 3,169,121; 3,207,814; 4,194,038; 4,156,069; 4,430,484, 4,465,820, and 4,981,898, where the disclosure regarding copolyestercarbonates from each of the U.S. Patents is incorporated by reference herein.

50 **[0214]** Copolyestercarbonates useful in bottles of the invention can be available commercially and/or may be prepared by known methods in the art. For example, they can be typically obtained by the reaction of at least one dihydroxyaromatic compound with a mixture of phosgene and at least one dicarboxylic acid chloride, especially isophthaloyl chloride, terephthaloyl chloride, or both.

55 **[0215]** In addition, the polyester compositions and the polymer blend compositions useful in the bottles of this invention may also contain from 0.01 to 25% by weight of the overall composition common additives such as colorants, dyes, mold release agents, flame retardants, plasticizers, nucleating agents, stabilizers, including but not limited to, UV stabilizers, thermal stabilizers and/or reaction products thereof, fillers, and impact modifiers. Examples of typical commercially available impact modifiers well known in the art and useful in this invention include, but are not limited to, ethylene/propylene terpolymers, functionalized polyolefins such as those containing methyl acrylate and/or glycidyl methacrylate,

styrene-based block copolymeric impact modifiers, and various acrylic core/shell type impact modifiers. Residues of such additives are also contemplated as part of the polyester composition

5 [0216] The polyesters useful in the bottles of the invention can comprise at least one chain extender. Suitable chain extenders include, but are not limited to, multifunctional (including, but not limited to, bifunctional) isocyanates, multifunctional epoxides, including for example, epoxylated novolacs, and phenoxy resins. In certain embodiments, chain extenders may be added at the end of the polymerization process or after the polymerization process. If added after the polymerization process, chain extenders can be incorporated by compounding or by addition during conversion processes such as injection molding or extrusion. The amount of chain extender used can vary depending on the specific monomer composition used and the physical properties desired but is generally from 0.1 percent by weight to 10 percent by weight, 10 such as 0.1 to 5 percent by weight, based on the total weight of the polyester.

15 [0217] Thermal stabilizers are compounds that stabilize polyesters during polyester manufacture and/or post polymerization, including but not limited to phosphorous compounds including but not limited to phosphoric acid, phosphorous acid, phosphonic acid, phosphinic acid, phosphonous acid, and various esters and salts thereof. These can be present in the polyester compositions useful in the bottles of the invention. The esters can be alkyl, branched alkyl, substituted alkyl, difunctional alkyl, alkyl ethers, aryl, and substituted aryl. In one embodiment, the number of ester groups present in the particular phosphorous compound can vary from zero up to the maximum allowable based on the number of hydroxyl groups present on the thermal stabilizer used. The term "thermal stabilizer" is intended to include the reaction product(s) thereof. The term "reaction product" as used in connection with the thermal stabilizers of the invention refers to any product of a polycondensation or esterification reaction between the thermal stabilizer and any of the monomers used in making the polyester as well as the product of a polycondensation or esterification reaction between the catalyst and any other type of additive.

20 [0218] Reinforcing materials may be useful in the compositions useful in the bottles of this invention. The reinforcing materials may include, but are not limited to, carbon filaments, silicates, mica, clay, talc, titanium dioxide, Wollastonite, glass flakes, glass beads and fibers, and polymeric fibers and combinations thereof. In one embodiment, the reinforcing materials include glass, such as, fibrous glass filaments, mixtures of glass and talc, glass and mica, and glass and polymeric fibers.

25 [0219] The invention further relates to bottles described herein. The methods of forming the polyesters into bottles are well known in the art. Examples of bottles include but are not limited to bottles such as baby bottles; water bottles; juice bottles; large commercial water bottles having a weight from 200 to 800 grams; beverage bottles which include but are not limited to two liter bottles, 0.567 kg (20 ounce) bottles, 0.479 kg (16.9 ounce) bottles; medical bottles; personal care bottles, carbonated soft drink bottles; hot fill bottles; water bottles; alcoholic beverage bottles such as beer bottles and wine bottles; and bottles comprising at least one handle. These bottles include but are not limited to injection blow molded bottles, injection stretch blow molded bottles, extrusion blow molded bottles, and extrusion stretch blow molded bottles. Methods of making bottles include but are not limited to extrusion blow molding, extrusion stretch blow molding, 30 injection blow molding, and injection stretch blow molding. In each case, the invention further relates to the preforms (or parisons) used to make each of said bottles.

35 [0220] These bottles include, but are not limited to, injection blow molded bottles, injection stretch blow molded bottles, extrusion blow molded bottles, and extrusion stretch blow molded bottles. Methods of making bottles include but are not limited to extrusion blow molding, extrusion stretch blow molding, thermoforming, injection blow molding, and injection stretch blow molding.

40 [0221] For the purposes of this invention, the term "wt" means "weight".

[0222] The following examples further illustrate how the bottles of the invention can be made and evaluated. Unless indicated otherwise, parts are parts by weight, temperature is in degrees C or is at room temperature, and pressure is at or near atmospheric.

## 45 EXAMPLES

### Measurement Methods

50 [0223] The inherent viscosity of the polyesters was determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C.

[0224] Unless stated otherwise, the glass transition temperature ( $T_g$ ) was determined using a TA DSC 2920 instrument from Thermal Analyst Instruments at a scan rate of 20°C/min according to ASTM D3418.

55 [0225] The glycol content and the cis/trans ratio of the compositions were determined by proton nuclear magnetic resonance (NMR) spectroscopy. All NMR spectra were recorded on a JEOL Eclipse Plus 600MHz nuclear magnetic resonance spectrometer using either chloroform-trifluoroacetic acid (70-30 volume/volume) for polymers or, for oligomeric samples, 60/40(wt/wt) phenol/tetrachloroethane with deuterated chloroform added for lock. Peak assignments for 2,2,4,4-tetramethyl-1,3-cyclobutanediol resonances were made by comparison to model mono- and dibenzoate esters of 2,2,4,4-

tetramethyl-1,3-cyclobutanediol. These model compounds closely approximate the resonance positions found in the polymers and oligomers.

**[0226]** The crystallization half-time,  $t_{1/2}$ , was determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage. This measurement was done by exposing the polymers to a temperature,  $T_{max}$ , and then cooling it to the desired temperature. The sample was then held at the desired temperature by a hot stage while transmission measurements were made as a function of time. Initially, the sample was visually clear with high light transmission and became opaque as the sample crystallized. The crystallization half-time was recorded as the time at which the light transmission was halfway between the initial transmission and the final transmission.  $T_{max}$  is defined as the temperature required to melt the crystalline domains of the sample (if crystalline domains are present). The  $T_{max}$  reported in the examples below represents the temperature at which each sample was heated to condition the sample prior to crystallization half time measurement. The  $T_{max}$  temperature is dependant on composition and is typically different for each polyester. For example, PCT may need to be heated to some temperature greater than 290°C to melt the crystalline domains.

**[0227]** Density was determined using a gradient density column at 23°C.

**[0228]** The melt viscosity reported herein was measured by using a Rheometrics Dynamic Analyzer (RDA II). The melt viscosity was measured as a function of shear rate, at frequencies ranging from 1 to 400 rad/sec, at the temperatures reported. The zero shear melt viscosity ( $\eta_0$ ) is the melt viscosity at zero shear rate estimated by extrapolating the data by known models in the art. This step is automatically performed by the Rheometrics Dynamic Analyzer (RDA II) software.

**[0229]** The polymers were dried at a temperature ranging from 80 to 100°C in a vacuum oven for 24 hours and injection molded on a Boy 22S molding machine to give 3.2x12.7x127-mm (1/8x1/2x5-inch) and 6.4x12.7x127-mm (1/4x1/2x5-inch) flexure bars. These bars were cut to a length of 63.5 mm (2.5 inch) and notched down the 12.7 mm (1/2 inch) width with a 254  $\mu$ m (10-mil) notch in accordance with ASTM D256. The average Izod impact strength at 23°C was determined from measurements on 5 specimens.

**[0230]** In addition, 5 specimens were tested at various temperatures using 5°C increments in order to determine the brittle-to-ductile transition temperature. The brittle-to-ductile transition temperature is defined as the temperature at which 50% of the specimens fail in a brittle manner as denoted by ASTM D256.

**[0231]** Color values reported herein were determined using a Hunter Lab Ultrascan Spectra Colorimeter manufactured by Hunter Associates Lab Inc., Reston, Va. The color determinations were averages of values measured on either pellets of the polyesters or plaques or other items injection molded or extruded from them. They were determined by the  $L^*a^*b^*$  color system of the CIE (International Commission on Illumination) (translated), wherein  $L^*$  represents the lightness coordinate,  $a^*$  represents the red/green coordinate, and  $b^*$  represents the yellow/blue coordinate.

**[0232]** In addition, 254  $\mu$ m (10-mil) films were compression molded using a Carver press at 240°C.

**[0233]** Unless otherwise specified, the cis/trans ratio of the 1,4 cyclohexanedimethanol used in the following examples was approximately 30/70, and could range from 35/65 to 25/75. Unless otherwise specified, the cis/trans ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol used in the following examples was approximately 50/50.

**[0234]** The following abbreviations apply throughout the working examples and figures:

TPA	Terephthalic acid
DMT	Dimethyl terephthalate
TMCD	2,2,4,4-tetramethyl-1,3-cyclobutanediol
CHDM	-1,4-cyclohexanedimethanol
IV	Inherent viscosity
$\eta_0$	Zero shear melt viscosity
$T_g$	Glass transition temperature
$T_{bd}$	Brittle-to-ductile transition temperature
$T_{max}$	Conditioning temperature for crystallization half time measurements

### Example 1

**[0235]** This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective at reducing the crystallization rate of PCT than ethylene glycol or isophthalic acid. In addition, this example illustrates the benefits of 2,2,4,4-tetramethyl-1,3-cyclobutanediol on the glass transition temperature and density.

**[0236]** A variety of copolyesters were prepared as described below. These copolyesters were all made with 200 ppm

dibutyl tin oxide as the catalyst in order to minimize the effect of catalyst type and concentration on nucleation during crystallization studies. The cis/trans ratio of the 1,4-cyclohexanedimethanol was 31/69 while the cis/trans ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol is reported in Table 1.

**[0237]** For purposes of this example, the samples had sufficiently similar inherent viscosities thereby effectively eliminating this as a variable in the crystallization rate measurements.

**[0238]** Crystallization half-time measurements from the melt were made at temperatures from 140 to 200°C at 10°C increments and are reported in Table 1. The fastest crystallization half-time for each sample was taken as the minimum value of crystallization half-time as a function of temperature, typically occurring around 170 to 180°C. The fastest crystallization half-times for the samples are plotted in Figure 1 as a function of mole% comonomer modification to PCT.

**[0239]** The data shows that 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than ethylene glycol and isophthalic acid at decreasing the crystallization rate (i.e., increasing the crystallization half-time). In addition, 2,2,4,4-tetramethyl-1,3-cyclobutanediol increases  $T_g$  and lowers density.

5

10

15

20

25

30

35

40

45

50

55

Table 1

Crystallization Half-times (min)												
Example	Comonomer (mol %) <sup>1</sup>	IV (dl/g)	Density (g/ml)	T <sub>g</sub> (°C)	T <sub>max</sub> (°C)	at 140 °C (min)	at 150 °C (min)	at 160°C (min)	at 170 °C (min)	at 180°0 (min)	at 190 °C (min)	at 200 °C (min)
1A	20.2 % A <sup>2</sup>	0.630	1.198	87.5	290	2.7	2.1	1.3	1.2	0.9	1.1	1.5
1B	19.8 % B	0.713	1.219	87.7	290	2.3	2.5	1.7	1.4	1.3	1.4	1.7
1C	20.0 % C	0.731	1.188	100.5	290	> 180	>60	35.0	23.3	21.7	23.3	25.2
1D	40.2 % A <sup>2</sup>	0.674	1.198	81.2	260	18.7	20.0	21.3	25.0	34.0	59.9	96.1
1E	34.5 % B	0.644	1.234	82.1	260	8.5	8.2	7.3	7.3	8.3	10.0	11.4
1F	40.1% C	0.653	1.172	122.0	260	>10 days	>5 days	>5 days	19204	> 5 days	>5 days	>5 days
1G	14.3 % D	0.646 <sup>3</sup>	1.188	103.0	290	55.0	28.8	11.6	6.8	4.8	5.0	5.5
1H	15.0 % E	0.728 <sup>4</sup>	1.189	99.0	290	25.4	17.1	8.1	5.9	4.3	2.7	5.1

1 The balance of the diol component of the polyesters in Table 1 is 1, 4-cyclohexanedimethanol; and the balance of the dicarboxylic acid component of the polyesters in Table 1 is dimethyl terephthalate; if the dicarboxylic acid is not described, it is 100 mole % dimethyl terephthalate.

2 100 mole % 1,4-cyclohexanedimethanol.

3 A film was pressed from the ground polyester of Example 1G at 240°C. The resulting film had an inherent viscosity value of 0.575 dL/g.

4 A film was pressed from the ground polyester of Example 1H at 240°C. The resulting film had an inherent viscosity value of 0.652 dL/g.

where:

A is Isophthalic Acid

B is Ethylene Glycol

C is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (approx. 50/50 cis/trans)

D is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (98/2 cis/trans)

E is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (5/95 cis/trans)

[0240] As shown in Table 1 and Figure 2-,2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than other comonomers, such ethylene glycol and isophthalic acid, at increasing the crystallization half-time, *i.e.*, the time required for a polymer to reach half of its maximum crystallinity. By decreasing the crystallization rate of PCT (increasing the crystallization half-time), amorphous articles based on 2,2,4,4-tetramethyl-1,3-cyclobutanediol-modified PCT as described herein may be fabricated by methods known in the art. As shown in Table 1, these materials can exhibit higher glass transition temperatures and lower densities than other modified PCT copolyesters.

[0241] Preparation of the polyesters shown on Table 1 is described below.

#### Example 1A

[0242] This example illustrates the preparation of a copolyester with a target composition of 80 mol% dimethyl terephthalate residues, 20 mol % dimethyl isophthalate residues, and 100 mol% 1,4-cyclohexanedimethanol residues (28/72 cis/trans).

[0243] A mixture of 56.63 g of dimethyl terephthalate, 55.2 g of 1,4-cyclohexanedimethanol, 14.16 g of dimethyl isophthalate, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 5 minutes and then the temperature was gradually increased to 290°C over 30 minutes. The reaction mixture was held at 290°C for 60 minutes and then vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 13,330 Pa (100 mm of Hg). The pressure inside the flask was further reduced to 40 Pa (0.3 mm of Hg) over the next 5 minutes. A pressure of 40 Pa (0.3 mm of Hg) was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 87.5°C and an inherent viscosity of 0.63 dl/g. NMR analysis showed that the polymer was composed of 100 mol% 1,4-cyclohexanedimethanol residues and 20.2 mol% dimethyl isophthalate residues.

#### Example 1B

[0244] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % ethylene glycol residues, and 80 mol% 1,4-cyclohexanedimethanol residues (32/68 cis/trans).

[0245] A mixture of 77.68 g of dimethyl terephthalate, 50.77 g of 1,4-cyclohexanedimethanol, 27.81 g of ethylene glycol, and 0.0433 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 200°C for 60 minutes and then the temperature was gradually increased to 210°C over 5 minutes. The reaction mixture was held at 210°C for 120 minutes and then heated up to 280°C in 30 minutes. Once at 280°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 13,330 Pa (100 mm of Hg). The pressure inside the flask was further reduced to 40 Pa (0.3 mm of Hg) over the next 10 minutes. A pressure of 40 Pa (0.3 mm of Hg) was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 87.7°C and an inherent viscosity of 0.71 dl/g. NMR analysis showed that the polymer was composed of 19.8 mol% ethylene glycol residues.

#### Example 1C

[0246] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and 80 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

[0247] A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 17.86 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. This polyester was prepared in a manner similar to that described in Example 1A. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 100.5°C and an inherent viscosity of 0.73 dl/g. NMR analysis showed that the polymer was composed of 80.5 mol% 1,4-cyclohexanedimethanol residues and 19.5 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

#### Example 1D

[0248] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 40 mol % dimethyl isophthalate residues, and 100 mol% 1,4-cyclohexanedimethanol residues

(28/72 cis/trans).

5 [0249] A mixture of 42.83 g of dimethyl terephthalate, 55.26 g of 1,4-cyclohexanedimethanol, 28.45 g of dimethyl isophthalate, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 5 minutes and then the temperature was gradually increased to 290°C over 30 minutes. The reaction mixture was held at 290°C for 60 minutes and then vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 13,330 Pa (100 mm of Hg). The pressure inside the flask was further reduced to 40 Pa (0.3 mm of Hg) over the next 5 minutes. A pressure of 40 Pa (0.3 mm of Hg) was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 81.2°C and an inherent viscosity of 0.67 dl/g. NMR analysis showed that the polymer was composed of 100 mol% 1,4-cyclohexanedimethanol residues and 40.2 mol% dimethyl isophthalate residues.

#### 15 Example 1E

[0250] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 40 mol % ethylene glycol residues, and 60 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

20 [0251] A mixture of 81.3 g of dimethyl terephthalate, 42.85 g of 1,4-cyclohexanedimethanol, 34.44 g of ethylene glycol, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 200°C for 60 minutes and then the temperature was gradually increased to 210°C over 5 minutes. The reaction mixture was held at 210°C for 120 minutes and then heated up to 280°C in 30 minutes. Once at 280°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 13,330 Pa (100 mm of Hg). The pressure inside the flask was further reduced to 40 Pa (0.3 mm of Hg) over the next 10 minutes. A pressure of 40 Pa (0.3 mm of Hg) was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 82.1°C and an inherent viscosity of 0.64 dl/g. NMR analysis showed that the polymer was composed of 34.5 mol% ethylene glycol residues.

#### 30 Example 1F

[0252] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 40 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and 60 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

35 [0253] A mixture of 77.4 g of dimethyl terephthalate, 36.9 g of 1,4-cyclohexanedimethanol, 32.5 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 3 minutes and then the temperature was gradually increased to 260°C over 30 minutes. The reaction mixture was held at 260°C for 120 minutes and then heated up to 290°C in 30 minutes. Once at 290°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 13,330 Pa (100 mm of Hg). The pressure inside the flask was further reduced to 40 Pa (0.3 mm of Hg) over the next 5 minutes. A pressure of 40 Pa (0.3 mm of Hg) was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 122°C and an inherent viscosity of 0.65 dl/g. NMR analysis showed that the polymer was composed of 59.9 mol% 1,4-cyclohexanedimethanol residues and 40.1 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

#### 50 Example 1G

[0254] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues (98/2 cis/trans), and 80 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

55 [0255] A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 20.77 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 3 minutes and then the temperature was gradually increased to 260°C over 30 minutes. The reaction mixture

was held at 260°C for 120 minutes and then heated up to 290°C in 30 minutes. Once at 290°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 13,330 Pa (100 mm of Hg) and the stirring speed was also reduced to 100 RPM. The pressure inside the flask was further reduced to 40 Pa (0.3 mm of Hg) over the next 5 minutes and the stirring speed was reduced to 50 RPM. A pressure of 40 Pa (0.3 mm of Hg) was maintained for a total time of 60 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 103°C and an inherent viscosity of 0.65 dl/g. NMR analysis showed that the polymer was composed of 85.7 mol% 1,4-cyclohexanedimethanol residues and 14.3 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

#### Example 1H

**[0256]** This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues (5/95 cis/trans), and 80 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

**[0257]** A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 20.77 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM at the beginning of the experiment. The contents of the flask were heated at 210°C for 3 minutes and then the temperature was gradually increased to 260°C over 30 minutes. The reaction mixture was held at 260°C for 120 minutes and then heated up to 290°C in 30 minutes. Once at 290°C, vacuum was gradually applied over the next 5 minutes with a set point of 100 mm of Hg and the stirring speed was also reduced to 100 RPM. The pressure inside the flask was further reduced to a set point of 40 Pa (0.3 mm of Hg) over the next 5 minutes and the stirring speed was reduced to 50 RPM. This pressure was maintained for a total time of 60 minutes to remove excess unreacted diols. It was noted that the vacuum system failed to reach the set point mentioned above, but produced enough vacuum to produce a high melt viscosity, visually clear and colorless polymer with a glass transition temperature of 99°C and an inherent viscosity of 0.73 dl/g. NMR analysis showed that the polymer was composed of 85 mol% 1,4-cyclohexanedimethanol residues and 15 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

#### Example 2

**[0258]** This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol improves the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol).

**[0259]** Copolyesters based on 2,2,4,4-tetramethyl-1,3-cyclobutanediol were prepared as described below. The cis/trans ratio of the 1,4-cyclohexanedimethanol was approximately 31/69 for all samples. Copolyesters based on ethylene glycol and 1,4-cyclohexanedimethanol were commercial polyesters. The copolyester of Example 2A (Eastar PCTG 5445) was obtained from Eastman Chemical Co. The copolyester of Example 2B was obtained from Eastman Chemical Co. under the trade name Spectar. Example 2C and Example 2D were prepared on a pilot plant scale (each a 6,804 g (15-lb) batch) following an adaptation of the procedure described in Example 1A and having the inherent viscosities and glass transition temperatures described in Table 2 below. Example 2C was prepared with a target tin amount of 300ppm (Dibutyltin Oxide). The final product contained 295 ppm tin. The color values for the polyester of Example 2C were  $L^* = 77.11$ ;  $a^* = -1.50$ ; and  $b^* = 5.79$ . Example 2D was prepared with a target tin amount of 300ppm (Dibutyltin Oxide). The final product contained 307 ppm tin. The color values for the polyester of Example 2D were  $L^* = 66.72$ ;  $a^* = -1.22$ ; and  $b^* = 16.28$ .

**[0260]** Materials were injection molded into bars and subsequently notched for Izod testing. The notched Izod impact strengths were obtained as a function of temperature and are also reported in Table 2.

**[0261]** For a given sample, the Izod impact strength undergoes a major transition in a short temperature span. For instance, the Izod impact strength of a copolyester based on 38 mol% ethylene glycol undergoes this transition between 15 and 20°C. This transition temperature is associated with a change in failure mode; brittle/low energy failures at lower temperatures and ductile/high energy failures at higher temperatures. The transition temperature is denoted as the brittle-to-ductile transition temperature,  $T_{bd}$ , and is a measure of toughness.  $T_{bd}$  is reported in Table 2 and plotted against mol% comonomer in Figure 2.

**[0262]** The data shows that adding 2,2,4,4-tetramethyl-1,3-cyclobutanediol to PCT lowers  $T_{bd}$  and improves the toughness, as compared to ethylene glycol, which increases  $T_{bd}$  of PCT.

**Table 2**

Notched Izod Impact Energy (ft-lb/in)															
Example	Comonomer (mol %) <sup>1</sup>	IV (dl/g)	T <sub>g</sub> (°C)	T <sub>bd</sub> (°C)	at -20 °C	at -15 °C	at -10 °C	at -5 °C	at 0 °C	at 5 °C	at 10 °C	at 15 °C	at 20 °C	at 25 °C	at 30 °C
2A	38.0 % B	0.68	86	18	NA	NA	NA	1.5	NA	NA	1.5	1.5	32	32	NA
2B	69.0 % B	0.69	82	26	NA	NA	NA	NA	NA	NA	2.1	NA	2.4	13.7	28.7
2C	22.0 % C	0.66	106	-5	1.5	NA	12	23	23	NA	23	NA	NA	NA	NA
2D	42.8 % C	0.60	133	-12	2.5	2.5	11	NA	14	NA	NA	NA	NA	NA	NA

1 The balance of the glycol component of the polyesters in the Table is 1,4-cyclohexanedimethanol. All polymers were prepared from 100 mole % dimethyl terephthalate. NA = Not available.

where: B is Ethylene glycol C is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (50/50 cis/trans)

**Example 3**

**[0263]** This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example comprise from 15 to 25 mol% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**[0264]** Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol were prepared as described below, having the composition and properties shown on Table 3. The balance up to 100 mol% of the diol component of the polyesters in Table 3 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

**[0265]** Materials were injection molded into both 3.2 mm and 6.4 mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23°C and are reported in Table 3. Density, T<sub>g</sub>, and crystallization half-time were measured on the molded bars. Melt viscosity was measured on pellets at 290°C.

15

20

25

30

35

40

45

50

55

**Table 3**

Compilation of various properties for certain polyesters useful in the invention										
Example	TMCD mole%	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt at 170°C (min)	Melt Viscosity at 1 rad/sec at 290°C in Pa*s (Poise)
A	15	48.8	0.736	0.707	1069	878	1.184	104	15	564.9 (5649)
B	18	NA	0.728	0.715	980	1039	1.183	108	22	662.1 (6621)
C	20	NA	0.706	0.696	1006	1130	1.182	106	52	632.1 (6321)
D	22	NA	0.732	0.703	959	988	1.178	108	63	716.1 (7161)
E	21	NA	0.715	0.692	932	482	1.179	110	56	616.2 (6162)
F	24	NA	0.708	0.677	976	812	1.180	109	58	628.2 (6282)
G	23	NA	0.650	0.610	647	270	1.182	107	46	317.2 (3172)
H	23	47.9	0.590	0.549	769	274	1.181	106	47	173.6 (1736)
I	23	48.1	0.531	0.516	696	352	1.182	105	19	129.2 (1292)
J	23	47.8	0.364	NA	NA	NA	NA	98	NA	16.7 (167)

NA = Not available.

**Example 3A**

5 [0266] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 14.34 lb (45.21 gram-mol) 1,4-cyclohexanedimethanol, and 4.58 lb (14.44 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and at a pressure of 137,895 Pa (20 psig). The pressure was then decreased to 0 Pa (0 psig) at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1 hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to < 133 Pa (1 mm of Hg). The reaction mixture was held at 290°C and at a pressure of < 133 Pa (1 mm of Hg) until the power draw to the agitator no longer increased (70 minutes). The pressure of the pressure vessel was then increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.736 dL/g and a Tg of 104 °C. NMR analysis showed that the polymer was composed of 85.4 mol% 1,4-cyclohexane-dimethanol residues and 14.6 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\* = 78.20, a\* = -1.62, and b\* = 6.23.

**Example 3B to Example 3D**

20 [0267] The polyesters described in Example 3B to Example 3D were prepared following a procedure similar to the one described for Example 3A. The composition and properties of these polyesters are shown in Table 3.

**Example 3E**

25 [0268] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb (19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 68 l (18-gallon) stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1 hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to < 133 Pa (1 mm of Hg). The reaction mixture was held at 290°C and at a pressure of < 133 Pa (1 mm of Hg) for 60 minutes. The pressure of the pressure vessel was then increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.715 dL/g and a Tg of 110°C. X-ray analysis showed that the polyester had 223 ppm tin. NMR analysis showed that the polymer was composed of 78.6 mol% 1,4-cyclohexane-dimethanol residues and 21.4 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\* = 76.45, a\* = -1.65, and b\* = 6.47.

**Example 3F**

45 [0269] The polyester described in Example 3F was prepared following a procedure similar to the one described for Example 3A. The composition and properties of this polyester are shown in Table 3.

**Example 3H**

50 [0270] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb (19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 68 l (18-gallon) stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1

hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to < 133 Pa (1 mm of Hg). The reaction mixture was held at 290°C and at a pressure of < 133 Pa (1 mm of Hg) for 12 minutes. The pressure of the pressure vessel was then increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.590 dL/g and a T<sub>g</sub> of 106°C. NMR analysis showed that the polymer was composed of 77.1 mol% 1,4-cyclohexane-dimethanol residues and 22.9 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\* = 83.27, a\* = - 1.34, and b\* = 5.08.

### Example 3I

**[0271]** 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb (19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 68 l (18-gallon) stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1 hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to 533 Pa (4 mm of Hg). The reaction mixture was held at 290°C and at a pressure of 533 Pa (4 mm of Hg) for 30 minutes. The pressure of the pressure vessel was then increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.531 dL/g and a T<sub>g</sub> of 105 °C. NMR analysis showed that the polymer was composed of 76.9 mol% 1,4-cyclohexane-dimethanol residues and 23.1 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\* = 80.42, a\* = - 1.28, and b\* = 5.13.

### Example 3J

**[0272]** 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb (19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1 hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to 533 Pa (4 mm of Hg). When the reaction mixture temperature was 290°C and the pressure was 533 Pa (4 mm of Hg), the pressure of the pressure vessel was immediately increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.364 dL/g and a T<sub>g</sub> of 98°C. NMR analysis showed that the polymer was composed of 77.5 mol% 1,4-cyclohexane-dimethanol residues and 22.5 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\* = 77.20, a\* = - 1.47, and b\* = 4.62.

### Example 4

**[0273]** This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example fall comprise more than 25 to less than 40 mol% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**[0274]** Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol (31/69 cis/trans) were prepared as described below, having the composition and properties shown on Table 4. The balance up to 100 mol% of the diol component of the polyesters in Table 4 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

**[0275]** Materials were injection molded into both 3.2mm and 6.4mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23°C and are reported in Table 4. Density, T<sub>g</sub>, and

## EP 1 907 442 B9

crystallization halftime were measured on the molded bars. Melt viscosity was measured on pellets at 290°C.

5

10

15

20

25

30

35

40

45

50

55

**Table 4**

Compilation of various properties for certain polyesters useful in the invention										
Example	TMCD mole%	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt at 170°C (min)	Melt Viscosity at 1 rad/sec at 290°C in Pa*s (Poise)
A	27	47.8	0.714	0.678	877	878	1.178	113	280	831.2 (8312)
B	31	NA	0.667	0.641	807	789	1.174	116	600	659.2 (6592)
NA = Not available.										

**Example 4A**

5 [0276] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 11.82 lb (37.28 gram-mol) 1,4-cyclohexanedimethanol, and 6.90 lb (21.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1 hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to < 133 Pa (1 mm of Hg). The reaction mixture was held at 290°C and at a pressure of < 133 (1 mm of Hg) until the power draw to the agitator no longer increased (50 minutes). The pressure of the pressure vessel was then increased to 101,330 (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.714 dL/g and a Tg of 113°C. NMR analysis showed that the polymer was composed of 73.3 mol% 1,4-cyclohexane-dimethanol residues and 26.7 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 4B**

20 [0277] The polyester of Example 4B was prepared following a procedure similar to the one described for Example 4A. The composition and properties of this polyester are shown in Table 4.

**Example 5**

25 [0278] This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example comprise 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues in an amount of 40 mol% or greater.

30 [0279] Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol were prepared as described below, having the composition and properties shown on Table 5. The balance up to 100 mol% of the diol component of the polyesters in Table 5 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

35 [0280] Materials were injection molded into both 3.2mm and 6.4mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23°C and are reported in Table 5. Density, Tg, and crystallization halftime were measured on the molded bars. Melt viscosity was measured on pellets at 290°C.

**Table 5**

Compilation of various properties for certain polyesters useful in the invention										
Example	TMCD mole%	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt at 170°C (min)	Melt Viscosity at 1 rad/sec at 290°C in Pa*s (Poise)
A	44	46.2	0.657	0.626	727	734	1.172	119	NA	975.1 (9751)
B	45	NA	0.626	0.580	748	237	1.167	123	NA	805.1 (8051)
C	45	NA	0.582	0.550	671	262	1.167	125	19782	583.5 (5835)
D	45	NA	0.541	0.493	424	175	1.167	123	NA	327.5 (3275)
E	59	46.6	0.604	0.576	456	311	1.156	139	NA	1,653.7 (16537)
F	45	47.2	0.475	0.450	128	30	1.169	121	NA	161.4 (1614)
NA = Not available.										

**Example 5A**

[0281] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 8.84 lb (27.88 gram-mol) 1,4-cyclohexanedimethanol, and 10.08 lb (31.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). Then the agitator speed was decreased to 15 RPM, the temperature of the reaction mixture was then increased to 290°C and the pressure was decreased to 267 Pa (2 mm of Hg). The reaction mixture was held at 290°C and at a pressure of 267 Pa (2 mm of Hg) until the power draw to the agitator no longer increased (80 minutes). The pressure of the pressure vessel was then increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.657 dL/g and a Tg of 119°C. NMR analysis showed that the polymer was composed of 56.3 mol% 1,4-cyclohexanedimethanol residues and 43.7 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\*= 75.04, a\*=-1.82, and b\*= 6.72.

**Example 5B to Example 5D**

[0282] The polyesters described in Example 5B to Example 5D were prepared following a procedure similar to the one described for Example 5A. The composition and properties of these polyesters are shown in Table 5.

**Example 5E**

[0283] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 6.43 lb (20.28 gram-mol) 1,4-cyclohexanedimethanol, and 12.49 lb (39.37 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 68 l (18-gallon) stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). Then the agitator speed was decreased to 15 RPM, the temperature of the reaction mixture was then increased to 290°C and the pressure was decreased to 267 Pa (2 mm of Hg). The reaction mixture was held at 290°C and at a pressure of < 133 Pa (1 mm of Hg) until the power draw to the agitator no longer increased (50 minutes). The pressure of the pressure vessel was then increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.604 dL/g and a Tg of 139°C. NMR analysis showed that the polymer was composed of 40.8 mol% 1,4-cyclohexanedimethanol residues and 59.2 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\*= 80.48, a\*=-1.30, and b\*= 6.82.

**Example 5F**

[0284] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 8.84 lb (27.88 gram-mol) 1,4-cyclohexanedimethanol, and 10.08 lb (31.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 68 l (18-gallon) stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 137,895 Pa (20 psig). The reaction mixture was held for 2 hours at 250°C and 137,895 Pa (20 psig) pressure. The pressure was then decreased to 0 Pa (0 psig) at a rate of 20,684 Pa/minute (3 psig/minute). The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 11,997 Pa (90 mm of Hg). After a 1 hour hold time at 270°C and 11,997 Pa (90 mm of Hg), the agitator speed was decreased to 15 RPM and the pressure was decreased to 4 mm of Hg. When the reaction mixture temperature was 270°C and the pressure was 4 mm of Hg, the pressure of the pressure vessel was immediately increased to 101,330 Pa (1 atmosphere) using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.475 dL/g and a Tg of 121°C. NMR analysis showed that the polymer was composed of 55.5 mol% 1,4-cyclohexane-dimethanol residues and 44.5 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\*= 85.63, a\*=- 0.88, and b\*= 4.34.

**Example 6-Comparative Example**

**[0285]** This example shows data for comparative materials are shown in Table 6. The PC was Makrolon 2608 from Bayer, with a nominal composition of 100 mole% bisphenol A residues and 100 mole% diphenyl carbonate residues. Makrolon 2608 has a nominal melt flow rate of 20 grams/10 minutes measured at 300°C using a 1.2 kg weight. The PET was Eastar 9921 from Eastman Chemical Company, with a nominal composition of 100 mole% terephthalic acid, 3.5 mole% cyclohexanedimethanol (CHDM) and 96.5 mole% ethylene glycol. The PETG was Eastar 6763 from Eastman Chemical Company, with a nominal composition of 100 mole% terephthalic acid, 31 mole% cyclohexanedimethanol (CHDM) and 69 mole % ethylene glycol. The PCTG was Eastar DN001 from Eastman Chemical Company, with a nominal composition of 100 mole% terephthalic acid, 62 mole% cyclohexanedimethanol (CHDM) and 38 mole % ethylene glycol. The PCTA was Eastar AN001 from Eastman Chemical Company, with a nominal composition of 65 mole% terephthalic acid, 35 mole% isophthalic acid and 100 mole% cyclohexanedimethanol (CHDM). The Polysulfone was Udel 1700 from Solvay, with a nominal composition of 100 mole% bisphenol A residues and 100 mole% 4,4-dichlorosulfonyl sulfone residues. Udel 1700 has a nominal melt flow rate of 6.5 grams/10 minutes measured at 343C using a 2.16 kg weight. The SAN was Lustran 31 from Lanxess, with a nominal composition of 76 weight % styrene and 24 weight % acrylonitrile. Lustran 31 has a nominal melt flow rate of 7.5 grams/10 minutes measured at 230C using a 3.8 kg weight. The examples of the invention show improved toughness in 6.4mm thickness bars compared to all of the other resins.

5  
10  
15  
20

25

30

35

40

45

50

55

**Table 6**

Compilation of various properties for certain commercial polymers								
Example	Polymer name	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt (min)
A	PC	12 MFR	NA	929	108	1.20	146	NA
B	PCTG	0.73	0.696	NB	70	1.23	87	30 at 170°C
C	PCTA	0.72	0.702	98	59	1.20	87	15 at 150°C
D	PETG	0.75	0.692	83	59	1.27	80	2500 at 130°C
E	PET	0.76	0.726	45	48	1.33	78	1.5 at 170°C
F	SAN	7.5 MFR	NA	21	NA	1.07	~110	NA
G	PSU	6.5 MFR	NA	69	NA	1.24	~190	NA
NA = Not available								

**Example 7**

**[0286]** This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example comprise from 15 to 25 mol% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 7A to Example 7G**

**[0287]** Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. NMR analysis on the 2,2,4,4-tetramethyl-1,3-cyclobutanediol starting material showed a cis/trans ratio of 53/47. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 40 Pa (0.3 mm of Hg) over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 20 mol%.

**[0288]** Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by <sup>1</sup>H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

**Example 7H to Example 7Q**

**[0289]** These polyesters were prepared by carrying out the ester exchange and polycondensation reactions in separate stages. The ester exchange experiments were conducted in a continuous temperature rise (CTR) reactor. The CTR was a 3000 ml glass reactor equipped with a single shaft impeller blade agitator, covered with an electric heating mantle and fitted with a heated packed reflux condenser column. The reactor was charged with 777g (4 moles) of dimethyl terephthalate, 230g (1.6 moles) of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, 460.8g (3.2 moles) of cyclohexane dimethanol and 1.12g of butyltin tris-2-ethylhexanoate (such that there will be 200ppm tin metal in the final polymer). The heating mantle was set manually to 100 % output. The set points and data collection were facilitated by a Camile process control system. Once the reactants were melted, stirring was initiated and slowly increased to 250 rpm. The temperature of the reactor gradually increased with run time. The weight of methanol collected was recorded via balance. The reaction was stopped when methanol evolution stopped or at a pre-selected lower temperature of 260°C. The oligomer was discharged with a nitrogen purge and cooled to room temperature. The oligomer was frozen with liquid nitrogen and broken into pieces small enough to be weighed into a 500 ml round bottom flask.

**[0290]** In the polycondensation reactions, a 500 ml round bottom flask was charged with approximately 150 g of the oligomer prepared above. The flask was equipped with a stainless steel stirrer and polymer head. The glassware was set up on a half mole polymer rig and the Camile sequence was initiated. The stirrer was positioned one full turn from the flask bottom once the oligomer melted. The temperature/pressure/stir rate sequence controlled by the Camile software for each example is reported in the following tables.

**[0291]**

Camile Sequence for Example 7H and Example 7I

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50

EP 1 907 442 B9

(continued)

5

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50
6	5	290	798 (6)	25
7	110	290	798 (6)	25

10

[0292]

Camile Sequence for Example 7N to Example 7Q

15

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50
6	5	290	399 (3)	25
7	110	290	399 (3)	25

20

25

[0293]

Camile Sequence for Example 7K and Example 7L

30

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50
6	5	290	266 (2)	25
7	110	290	266 (2)	25

35

40

45

[0294]

Camile Sequence for Example 7J and Example 7M

50

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50

55

(continued)

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
6	5	290	133 (1)	25
7	110	290	133 (1)	25

[0295] The resulting polymers were recovered from the flask, chopped using a hydraulic chopper, and ground to a 6 mm screen size. Samples of each ground polymer were submitted for inherent viscosity in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C, catalyst level (Sn) by x-ray fluorescence, and color ( $L^*$ ,  $a^*$ ,  $b^*$ ) by transmission spectroscopy. Polymer composition was obtained by  $^1\text{H}$  NMR. Samples were submitted for thermal stability and melt viscosity testing using a Rheometrics Mechanical Spectrometer (RMS-800).

[0296] The table below shows the experimental data for the polyesters of this example. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity. Figure 3 also shows the dependence of  $T_g$  on composition and inherent viscosity.

Table 7

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol% TMCD	% cis TMCD	IV (dL/g)	$T_g$ (°C)	$\eta_o$ at 260°C in Pa*s (Poise)	$\eta_o$ at 275°C in Pa*s (Poise)	$\eta_o$ at 290°C in Pa*s (Poise)
A	20	51.4	0.72	109	1,135.6 (11356)	1,950.3 (19503)	552.7 (5527)
B	19.1	51.4	0.60	106	689.1 (6891)	393.7 (3937)	205.1 (2051)
C	19	53.2	0.64	107	807.2 (8072)	474.5 (4745)	268.6 (2686)
D	18.8	54.4	0.70	108	1,493.7 (14937)	877.4 (8774)	461.0 (4610)
E	17.8	52.4	0.50	103	356.3 (3563)	122.5 (1225)	88.3 (883)
F	17.5	51.9	0.75	107	2,116.0 (21160)	1,087.7 (10877)	525.6 (5256)
G	17.5	52	0.42	98	NA	NA	NA
H	22.8	53.5	0.69	109	NA	NA	NA
I	22.7	52.2	0.68	108	NA	NA	NA
J	23.4	52.4	0.73	111	NA	NA	NA
K	23.3	52.9	0.71	111	NA	NA	NA
L	23.3	52.4	0.74	112	NA	NA	NA
M	23.2	52.5	0.74	112	NA	NA	NA
N	23.1	52.5	0.71	111	NA	NA	NA
O	22.8	52.4	0.73	112	NA	NA	NA
P	22.7	53	0.69	112	NA	NA	NA
Q	22.7	52	0.70	111	NA	NA	NA

NA = Not available

## Example 8

**[0297]** This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example fall comprise more than 25 to less than 40 mol% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**[0298]** Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. NMR analysis on the 2,2,4,4-tetramethyl-1,3-cyclobutanediol starting material showed a cis/trans ratio of 53/47. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 40 Pa (0.3 mm of Hg) over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 32 mol%.

**[0299]** Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by <sup>1</sup>H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

**[0300]** The table below shows the experimental data for the polyesters of this example. Figure 3 also shows the dependence of T<sub>g</sub> on composition and inherent viscosity. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity.

Table 8

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol% TMCD	% cis TMCD	IV (dL/g)	T <sub>g</sub> (°C)	η <sub>o</sub> at 260°C in Pa*s (Poise)	η <sub>o</sub> at 275°C in Pa*s (Poise)	η <sub>o</sub> at 290°C in Pa*s (Poise)
A	32.2	51.9	0.71	118	2,968.5 (29685)	1,607.4 (16074)	852.2 (8522)
B	31.6	51.5	0.55	112	519.5 (5195)	289.9 (2899)	208.8 (2088)
C	31.5	50.8	0.62	112	819.2 (8192)	413.3 (4133)	225.8 (2258)
D	30.7	50.7	0.54	111	434.5 (4345)	243.4 (2434)	115.4 (1154)
E	30.3	51.2	0.61	111	792.9 (7929)	438.3 (4383)	226.1 (2261)
F	30.0	51.4	0.74	117	3,147.6 (31476)	1,786.4 (17864)	863.0 (8630)
G	29.0	51.5	0.67	112	1,632.2 (16322)	878.7 (8787)	435.5 (4355)
H	31.1	51.4	0.35	102	NA	NA	NA
NA = Not available							

**Example 9**

**[0301]** This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example comprise 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues in an amount of 40 mol% or greater.

**Examples A to AC**

**[0302]** These polyesters were prepared by carrying out the ester exchange and polycondensation reactions in separate stages. The ester exchange experiments were conducted in a continuous temperature rise (CTR) reactor. The CTR was a 3000 ml glass reactor equipped with a single shaft impeller blade agitator, covered with an electric heating mantle and fitted with a heated packed reflux condenser column. The reactor was charged with 777g of dimethyl terephthalate, 375g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, 317g of cyclohexane dimethanol and 1.12g of butyltin tris-2-ethylhexanoate (such that there will be 200ppm tin metal in the final polymer). The heating mantle was set manually to 100 % output. The set points and data collection were facilitated by a Camile process control system. Once the reactants were melted, stirring was initiated and slowly increased to 250 rpm. The temperature of the reactor gradually increased with run time. The weight of methanol collected was recorded via balance. The reaction was stopped when methanol evolution stopped or at a pre-selected lower temperature of 260°C. The oligomer was discharged with a nitrogen purge and cooled to room temperature. The oligomer was frozen with liquid nitrogen and broken into pieces small enough to be weighed into a 500 ml round bottom flask.

**[0303]** In the polycondensation reactions, a 500 ml round bottom flask was charged with 150 g of the oligomer prepared above. The flask was equipped with a stainless steel stirrer and polymer head. The glassware was set up on a half mole polymer rig and the Camile sequence was initiated. The stirrer was positioned one full turn from the flask bottom once the oligomer melted. The temperature/pressure/stir rate sequence controlled by the Camile software for these examples is reported in the following table, unless otherwise specified below.

**Camile Sequence for Polycondensation Reactions**

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50
6	5	290	798 (6)	25
7	110	290	798 (6)	25

**[0304]**

Camile Sequence for Examples A, C, R, Y, AB, AC

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50
6	5	290	798 (6)	25
7	110	290	798 (6)	25

**[0305]** For Examples B, D, F, the same sequence in the preceding table was used, except the time was 80 min in Stage 7. For Examples G and J, the same sequence in the preceding table was used, except the time was 50 min in

**EP 1 907 442 B9**

Stage 7. For Example L, the same sequence in the preceding table was used, except the time was 140 min in Stage 7.  
**[0306]**

Camile Sequence for Example E

5  
  
10  
  
15

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	300	11,970 (90)	50
6	5	300	931 (7)	25
7	110	300	931 (7)	25

**[0307]** For Example I, the same sequence in the preceding table was used, except the vacuum was 1,064 Pa (8 torr) in Stages 6 and 7. For Example O, the same sequence in the preceding table was used, except the vacuum was 798 Pa (6 torr) in Stages 6 and 7. For Example P, the same sequence in the preceding table was used, except the vacuum was 532 Pa (4 torr) in Stages 6 and 7. For Example Q, the same sequence in the preceding table was used, except the vacuum was 665 Pa (5 torr) in Stages 6 and 7.

20

**[0308]**

Camile Sequence for Example H

25  
  
30  
  
35

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970(90)	50
5	110	280	11,970(90)	50
6	5	280	665 (5)	25
7	110	280	665 (5)	25

**[0309]** For Example U and AA, the same sequence in the preceding table was used, except the vacuum was 798 Pa (6 torr) in Stages 6 and 7. For Example V and X, the same sequence in the preceding table was used, except the vacuum was 798 Pa (6 torr) and stir rate was 15 rpm in Stages 6 and 7. For Example Z, the same sequence in the preceding table was used, except the stir rate was 15 rpm in Stages 6 and 7.

40

**[0310]**

Camile Sequence for Example K

45  
  
50  
  
55

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	300	11,970 (90)	50
6	5	300	798 (6)	15
7	110	300	798 (6)	15

## EP 1 907 442 B9

[0311] For Example M, the same sequence in the preceding table was used, except the vacuum was 1064 Pa (8 torr) in Stages 6 and 7. For Example N, the same sequence in the preceding table was used, except the vacuum was 931 Pa (7 torr) in Stages 6 and 7.

[0312]

Camile Sequence for Examples S and T

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	5	290	798 (6)	25
5	110	290	798 (6)	25

[0313] The resulting polymers were recovered from the flask, chopped using a hydraulic chopper, and ground to a 6 mm screen size. Samples of each ground polymer were submitted for inherent viscosity in 60/40 (wt/wt) phenol/tetra-chloroethane at a concentration of 0.5 g/100 ml at 25°C, catalyst level (Sn) by x-ray fluorescence, and color (L\*, a\*, b\*) by transmission spectroscopy. Polymer composition was obtained by 1H NMR. Samples were submitted for thermal stability and melt viscosity testing using a Rheometrics Mechanical Spectrometer (RMS-800).

### Examples AD to AK and AT

[0314] The polyesters of these examples were prepared as described above for Examples A to AC, except that the target tin amount in the final polymer was 150ppm for examples AD to AK and AT. The following tables describe the temperature/pressure/stir rate sequences controlled by the Camile software for these examples.

[0315]

Camile Sequence for Examples AD, AF, and AH

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	53,200 (400)	50
5	110	290	53,200 (400)	50
6	5	290	1064 (8)	50
7	110	295	1064 (8)	50

[0316] For Example AD, the stirrer was turned to 25 rpm with 95 min left in Stage 7.

[0317]

Camile Sequence for Example AE

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	10	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	283	101,080 (760)	50
4	3	283	23,275 (175)	50
5	5	283	665 (5)	50
6	5	283	159.6 (1.2)	50

**EP 1 907 442 B9**

(continued)

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
7	71	285	159.6 (1.2)	50

5

**[0318]** For Example AK, the same sequence in the preceding table was used, except the time was 75 min in Stage 7.  
**[0319]**

Camile Sequence for Example AG

Stage	Time (min)	Temp (°C)	Vacuum IN Pa (torr)	Stir (rpm)
1	10	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	285	101,080 (760)	50
4	3	285	23,275 (175)	50
5	5	285	665 (5)	50
6	5	285	532 (4)	50
7	220	290	532 (4)	50

10

15

20

**[0320]**

Camile Sequence for Example AI

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	285	11,970 (90)	50
6	5	285	798 (6)	50
7	70	290	798 (6)	50

25

30

35

**[0321]**

Camile Sequence for Example AJ

Stage	Time (min)	Temp (°C)	Vacuum in Pa (torr)	Stir (rpm)
1	5	245	101,080 (760)	0
2	5	245	101,080 (760)	50
3	30	265	101,080 (760)	50
4	3	265	11,970 (90)	50
5	110	290	11,970 (90)	50
6	5	290	798 (6)	25
7	110	295	798 (6)	25

40

45

50

55

**Examples AL to AS**

**[0322]** Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were

weighed into a 500-ml single neck round bottom flask. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 40 Pa (0.3 mm of Hg) over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 45 mol%.

**[0323]** Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by <sup>1</sup>H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

**[0324]** The table below shows the experimental data for the polyesters of this example. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity. Figure 3 also shows the dependence of T<sub>g</sub> on composition and inherent viscosity.

Table 9

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol% TMCD	% cis TMCD	IV (dL/g)	T <sub>g</sub> (°C)	η <sub>o</sub> at 260°C in Pa*s (Poise)	η <sub>o</sub> at 275°C in Pa*s (Poise)	η <sub>o</sub> at 290°C in Pa*s (Poise)
A	43.9	72.1	0.46	131	NA	NA	NA
B	44.2	36.4	0.49	118	NA	NA	NA
C	44	71.7	0.49	128	NA	NA	NA
D	44.3	36.3	0.51	119	NA	NA	NA
E	46.1	46.8	0.51	125	NA	NA	NA
F	43.6	72.1	0.52	128	NA	NA	NA
G	43.6	72.3	0.54	127	NA	NA	NA
H	46.4	46.4	0.54	127	NA	NA	NA
I	45.7	47.1	0.55	125	NA	NA	NA
J	44.4	35.6	0.55	118	NA	NA	NA
K	45.2	46.8	0.56	124	NA	NA	NA
L	43.8	72.2	0.56	129	NA	NA	NA
M	45.8	46.4	0.56	124	NA	NA	NA
N	45.1	47.0	0.57	125	NA	NA	NA
O	45.2	46.8	0.57	124	NA	NA	NA
P	45	46.7	0.57	125	NA	NA	NA
Q	45.1	47.1	0.58	127	NA	NA	NA
R	44.7	35.4	0.59	123	NA	NA	NA
S	46.1	46.4	0.60	127	NA	NA	NA
T	45.7	46.8	0.60	129	NA	NA	NA
U	46	46.3	0.62	128	NA	NA	NA

EP 1 907 442 B9

(continued)

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol% TMCD	% cis TMCD	IV (dL/g)	T <sub>g</sub> (°C)	η <sub>o</sub> at 260°C in Pa*s (Poise)	η <sub>o</sub> at 275°C in Pa*s (Poise)	η <sub>o</sub> at 290°C in Pa*s (Poise)
V	45.9	46.3	0.62	128	NA	NA	NA
X	45.8	46.1	0.63	128	NA	NA	NA
Y	45.6	50.7	0.63	128	NA	NA	NA
Z	46.2	46.8	0.65	129	NA	NA	NA
AA	45.9	46.2	0.66	128	NA	NA	NA
AB	45.2	46.4	0.66	128	NA	NA	NA
AC	45.1	46.5	0.68	129	NA	NA	NA
AD	46.3	52.4	0.52	NA	NA	NA	NA
AE	45.7	50.9	0.54	NA	NA	NA	NA
AF	46.3	52.6	0.56	NA	NA	NA	NA
AG	46	50.6	0.56	NA	NA	NA	NA
AH	46.5	51.8	0.57	NA	NA	NA	NA
AI	45.6	51.2	0.58	NA	NA	NA	NA
AJ	46	51.9	0.58	NA	NA	NA	NA
AK	45.5	51.2	0.59	NA	NA	NA	NA
AL	45.8	50.1	0.624	125	NA	NA	7696
AM	45.7	49.4	0.619	128	NA	NA	7209
AN	46.2	49.3	0.548	124	NA	NA	2348
AP	45.9	49.5	0.72	128	7,660.0 (76600)	4,026.0 (40260)	1,911.0 (19110)
AQ	46.0	50	0.71	131	6,831.0 (68310)	3,248.0 (32480)	1,781.7 (17817)
AR	46.1	49.6	0.383	117	NA	NA	387
AS	45.6	50.5	0.325	108	NA	NA	NA
AT	47.2	NA	0.48	NA	NA	NA	NA
NA = Not available							

**Example 10**

**[0325]** This example illustrates the effect of the predominance of the type of 2,2,4,4-tetramethyl-1,3-cyclobutanediol isomer (cis or trans) on the glass transition temperature of the polyester.

**[0326]** Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 40 Pa (0.3 mm) of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass

transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 45 mol%.

**[0327]** Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by <sup>1</sup>H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

**[0328]** The table below shows the experimental data for the polyesters of this Example. The data shows that cis 2,2,4,4-tetramethyl-1,3-cyclobutanediol is approximately twice as effective as trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol at increasing the glass transition temperature for a constant inherent viscosity.

Table 10

Effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol cis/trans composition on T <sub>g</sub>							
Example	mol% TMCD	IV (dL/g)	T <sub>g</sub> (°C)	η <sub>o</sub> at 260°C in Pa*s (Poise)	η <sub>o</sub> at 275°C in Pa*s (Poise)	η <sub>o</sub> at 290°C in Pa*s (Poise)	% cis TMCD
A	45.8	0.71	119	N.A.	N.A.	N.A.	4.1
B	43.2	0.72	122	N.A.	N.A.	N.A.	22.0
C	46.8	0.57	119	2,630.6 (26306)	1,694.1 (16941)	660.1 (6601)	22.8
D	43.0	0.67	125	5,506.0 (55060)	3,674.7 (36747)	1,441.0 (14410)	23.8
E	43.8	0.72	127	10,100.0 (101000)	6,275.0 (62750)	2,533.0 (25330)	24.5
F	45.9	0.533	119	1,147.4 (11474)	686.4 (6864)	280.6 (2806)	26.4
G	45.0	0.35	107	N.A.	N.A.	N.A.	27.2
H	41.2	0.38	106	121.4 (1214)	75.7 (757)	N.A.	29.0
I	44.7	0.59	123	N.A.	N.A.	N.A.	35.4
J	44.4	0.55	118	N.A.	N.A.	N.A.	35.6
K	44.3	0.51	119	N.A.	N.A.	N.A.	36.3
L	44.0	0.49	128	N.A.	N.A.	N.A.	71.7
M	43.6	0.52	128	N.A.	N.A.	N.A.	72.1
N	43.6	0.54	127	N.A.	N.A.	N.A.	72.3
O	41.5	0.58	133	1,541.9 (15419)	1,025.3 (10253)	425.2 (4252)	88.7
P	43.8	0.57	135	1,621.9 (16219)	1,022.6 (10226)	423.5 (4235)	89.6
Q	41.0	0.33	120	521 (521)	35.1 (351)	226.1 (2261)	90.4
R	43.0	0.56	134	N.A.	N.A.	N.A.	90.6
S	43.0	0.49	132	705.5 (7055)	462.0 (4620)	226.1 (2120)	90.6
T	43.1	0.55	134	1,297.0 (12970)	844.3 (8443)	353.1 (3531)	91.2

(continued)

Effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol cis/trans composition on $T_g$							
Example	mol% TMCD	IV (dL/g)	$T_g$ (°C)	$\eta_o$ at 260°C in Pa*s (Poise)	$\eta_o$ at 275°C in Pa*s (Poise)	$\eta_o$ at 290°C in Pa*s (Poise)	% cis TMCD
U	45.9	0.52	137	N.A.	N.A.	N.A.	98.1
NA = not available							

**Example 11**

**[0329]** This example illustrates the preparation of a copolyester containing 100 mol% dimethyl terephthalate residues, 55 mol% 1,4-cyclohexanedimethanol residues, and 45 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**[0330]** A mixture of 97.10 g (0.5 mol) dimethyl terephthalate, 52.46 g (0.36 mol) 1,4-cyclohexanedimethanol, 34.07 g (0.24 mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.0863 g (300 ppm) dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200°C. The contents of the flask were heated at 200°C for 1 hour and then the temperature was increased to 210°C. The reaction mixture was held at 210°C for 2 hours and then heated up to 290°C in 30 minutes. Once at 290°C, a vacuum of 69 Pa (0.01 psig) was gradually applied over the next 3 to 5 minutes. Full vacuum (69 Pa (0.01 psig)) was maintained for a total time of about 45 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 125°C and an inherent viscosity of 0.64 dl/g.

**Example 12-Comparative Example**

**[0331]** This example illustrates that a polyester based on 100% 2,2,4,4-tetramethyl-1,3-cyclobutanediol has a slow crystallization half-time.

**[0332]** A polyester based solely on terephthalic acid and 2,2,4,4-tetramethyl-1,3-cyclobutanediol was prepared in a method similar to the method described in Example 1A with the properties shown on Table 11. This polyester was made with 300 ppm dibutyl tin oxide. The trans/cis ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol was 65/35.

**[0333]** Films were pressed from the ground polymer at 320°C. Crystallization half-time measurements from the melt were made at temperatures from 220 to 250°C at 10°C increments and are reported in Table 11. The fastest crystallization half-time for the sample was taken as the minimum value of crystallization half-time as a function of temperature. The fastest crystallization half-time of this polyester is around 1300 minutes. This value contrasts with the fact that the polyester (PCT) based solely on terephthalic acid and 1,4-cyclohexanedimethanol (no comonomer modification) has an extremely short crystallization half-time (<1 min) as shown in Figure 1.

**Table 11**

Crystallization Half-times (min)							
Comonomer (mol %)	IV (dl/g)	$T_g$ (°C)	$T_{max}$ (°C)	at 220°C (min)	at 230°C (min)	at 240°C (min)	at 250°C (min)
100 mol% F	0.63	170.0	330	3291	3066	1303	1888
where: F is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (65/35 Trans/Cis)							

**Example 13**

**[0334]** Sheets comprising a polyester that had been prepared with a target composition of 100 mole % terephthalic acid residues, 80 mole % 1,4-cyclohexanedimethanol residues, and 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues were produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 4,495  $\mu$ m (177 mil) and then various sheets were sheared to size. Inherent viscosity and glass transition temperature were measured on one sheet. The sheet inherent viscosity was measured to be 0.69 dl/g. The glass transition temperature of the sheet was measured to be 106°C. Sheets were then conditioned at 50% relative humidity and 60°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets

EP 1 907 442 B9

were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example G). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 106°C can be thermoformed under the conditions shown below, as evidenced by these sheets having at least 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	86	145	501	64	N
B	100	150	500	63	N
C	118	156	672	85	N
D	135	163	736	94	N
E	143	166	760	97	N
F	150	168	740	94	L
G	159	172	787	100	L

Example 14

**[0335]** Sheets comprising a polyester that had been prepared with a target composition of 100 mole % terephthalic acid residues, 80 mole % 1,4-cyclohexanedimethanol residues, and 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues were produced using a 88.9 mm (3.5 inch) single screw. A sheet was extruded continuously, gauged to a thickness of 4,495 μm (177 mil) and then various sheets were sheared to size. Inherent viscosity and glass transition temperature were measured on one sheet. The sheet inherent viscosity was measured to be 0.69 dl/g. The glass transition temperature of the sheet was measured to be 106°C. Sheets were then conditioned at 100% relative humidity and 25°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 60/40/40% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example G). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 106°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having at least 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	141	154	394	53	N
B	163	157	606	82	N
C	185	160	702	95	N
D	195	161	698	95	N
E	215	163	699	95	L
F	230	168	705	96	L

(continued)

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
G	274	174	737	100	H
H	275	181	726	99	H

**Example 15-Comparative Example**

**[0336]** Sheets consisting of Kelvx 201 were produced using a 3.5 inch single screw extruder. Kelvx is a blend consisting of 69.85% PCTG (Estar from Eastman Chemical Co. having 100 mole % terephthalic acid residues, 62 mole % 1,4-cyclohexanedimethanol residues, and 38 mole % ethylene glycol residues); 30% PC (bisphenol A polycarbonate); and 0.15% Weston 619 (stabilizer sold by Crompton Corporation). A sheet was extruded continuously, gauged to a thickness of 4,495  $\mu\text{m}$  (177 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 100°C. Sheets were then conditioned at 50% relative humidity and 60°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example E). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 100°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having at least 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	90	146	582	75	N
B	101	150	644	83	N
C	111	154	763	98	N
D	126	159	733	95	N
E	126	159	775	100	N
F	141	165	757	98	N
G	148	168	760	98	L

**Example 16-Comparative Example**

**[0337]** Sheets consisting of Kelvx 201 were produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 4,495  $\mu\text{m}$  (177 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 100°C. Sheets were then conditioned at 100% relative humidity and 25°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 60/40/40% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example H). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 100°C can be thermoformed under

**EP 1 907 442 B9**

the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

5  
10  
15  
20

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	110	143	185	25	N
B	145	149	529	70	N
C	170	154	721	95	N
D	175	156	725	96	N
E	185	157	728	96	N
F	206	160	743	98	L
G	253	NR	742	98	H
H	261	166	756	100	H
NR = Not recorded					

**Example 17-Comparative Example**

25  
30  
35

**[0338]** Sheets consisting of PCTG 25976 (100 mole % terephthalic acid residues, 62 mole % 1,4-cyclohexanedimethanol residues, and 38 mole % ethylene glycol residues) were produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 87°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.17 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 87°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

40  
45  
50

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	102	183	816	100	N
B	92	171	811	99	N
C	77	160	805	99	N
D	68	149	804	99	N
E	55	143	790	97	N
F	57	138	697	85	N

**Example 18-Comparative Example**

**[0339]** A miscible blend consisting of 20 wt% Teijin L-1250 polycarbonate (a bisphenol-A polycarbonate), 79.85 wt%

EP 1 907 442 B9

PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 94°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.25 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 94°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	92	184	844	100	H
B	86	171	838	99	N
C	73	160	834	99	N
D	58	143	787	93	N
E	55	143	665	79	N

Example 19-Comparative Example

**[0340]** A miscible blend consisting of 30 wt% Teijin L-1250 polycarbonate, 69.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 31.8 mm (1.25 inch) single screw extruder. Sheets consisting of the blend were then produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 99°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.25 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 99°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	128	194	854	100	H
B	98	182	831	97	L
C	79	160	821	96	N
D	71	149	819	96	N

EP 1 907 442 B9

(continued)

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
E	55	145	785	92	N
F	46	143	0	0	NA
G	36	132	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

**Example 20-Comparative Example**

**[0341]** A miscible blend consisting of 40 wt% Teijin L-1250 polycarbonate, 59.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 31.8 mm (1.25 inch) single screw extruder. Sheets consisting of the blend were then produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 105°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.265 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Examples 8A to 8E). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 105°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	111	191	828	100	H
B	104	182	828	100	H
C	99	179	827	100	N
D	97	177	827	100	N
E	78	160	826	100	N
F	68	149	759	92	N
G	65	143	606	73	N

**Example 21-Comparative Example**

**[0342]** A miscible blend consisting of 50 wt% Teijin L-1250 polycarbonate, 49.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 31.8 mm (1.25 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 111°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.225 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine

## EP 1 907 442 B9

the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Examples A to D). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 111 °C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	118	192	815	100	H
B	99	182	815	100	H
C	97	177	814	100	L
D	87	171	813	100	N
E	80	160	802	98	N
F	64	154	739	91	N
G	60	149	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

### Example 22-Comparative Example

**[0343]** A miscible blend consisting of 60 wt% Teijin L-1250 polycarbonate, 39.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 31.8 mm (1.25 inch) single screw extruder. Sheets consisting of the blend were then produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 117°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.215 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 117°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	114	196	813	100	H
B	100	182	804	99	H
C	99	177	801	98	L
D	92	171	784	96	L
E	82	168	727	89	L

**EP 1 907 442 B9**

(continued)

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
F	87	166	597	73	N

**Example 23-Comparative Example**

**[0344]** A miscible blend consisting of 65 wt% Teijin L-1250 polycarbonate, 34.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 31.8 mm (1.25 inch) single screw extruder. Sheets consisting of the blend were then produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 120°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.23 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 120°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	120	197	825	100	H
B	101	177	820	99	H
C	95	174	781	95	L
D	85	171	727	88	L
E	83	166	558	68	L

**Example 24-Comparative Example**

**[0345]** A miscible blend consisting of 70 wt% Teijin L-1250 polycarbonate, 29.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 31.8 mm (1.25 inch) single screw extruder. Sheets consisting of the blend were then produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 123°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.205 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Examples A and B). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 123°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

EP 1 907 442 B9

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	126	198	826	100	H
B	111	188	822	100	H
C	97	177	787	95	L
D	74	166	161	19	L
E	58	154	0	0	NA
F	48	149	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

Example 25-Comparative Example

[0346] Sheets consisting of Teijin L-1250 polycarbonate were produced using a 88.9 mm (3.5 inch) single screw extruder. A sheet was extruded continuously, gauged to a thickness of 2,997 μm (118 mil) and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 149°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.16 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 149°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time(s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	152	216	820	100	H
B	123	193	805	98	H
C	113	191	179	22	H
D	106	188	0	0	H
E	95	182	0	0	NA
F	90	171	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

[0347] It can be clearly seen from a comparison of the data in the above relevant working examples that the polyesters of the present invention offer a definite advantage over the commercially available polyesters with regard to glass transition temperature, density, slow crystallization rate, melt viscosity, and toughness.

## Claims

1. A bottle comprising at least one polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of from 85 to 200°C.

2. The bottle of Claim 1, wherein the inherent viscosity of said polyester is from 0.35 to 1.0 dL/g, or 0.40 to 0.90 dL/g, or from greater than 0.42 to 0.80 dL/g, or from 0.45 to 0.75 dL/g, or from 0.50 to 0.68 dL/g, or from 0.35 to 0.75 dL/g, or from 0.35 to 0.80 dL/g, or from 0.35 to 0.70 dL/g, or from 0.35 to less than 0.70 dL/g, or from 0.35 to 0.68 dL/g, or from 0.35 to less than 0.68 dL/g, or from 0.50 to 0.75 dL/g, or from 0.50 to 0.70 dL/g, or from 0.50 to less than 0.70 dL/g, or from 0.50 to less than 0.68 dL/g, or from 0.55 to 0.80 dL/g, or from 0.55 to 0.75 dL/g, or from 0.55 to 0.70 dL/g, or from 0.55 to less than 0.70 dL/g, or from 0.55 to 0.68 dL/g, or from 0.60 to 0.80 dL/g, or from 0.60 to 0.75 dL/g, or from 0.60 to 0.70 dL/g, or from 0.60 to less than 0.70 dL/g, or from 0.60 to 0.68 dL/g.

3. The bottle of Claim 1, wherein the inherent viscosity of said polyester is from 0.60 to 0.72 dL/g.

4. The bottle of Claim 1, wherein said polyester has a Tg of 100 to 190°C, or 100 to 180°C, or 100 to 160°C, or 100 to 150°C, or 100 to 140°C, or 100 to 130°C, or 100 to 120°C, or of 110 to 180°C, or of 110 to 160°C, or 110 to 150°C, or 110 to 140°C, or 110 to 130°C, or 110 to 120°C, or of 115 to 180°C, or 115 to 170°C, or 115 to 160°C, or 115 to 150°C, or 115 to 140°C, or 115 to 130°C, or 115 to 120°C, or 120 to 160°C, or 120 to 150°C, or 130 to 160°C, or 130 to 150°C, or 130 to 145°C.

5. The bottle of Claim 3, wherein said polyester has a Tg of 130 to 145°C.

6. The bottle of Claim 1, wherein the glycol component of said polyester comprises 1 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 99 mole % 1,4-cyclohexanedimethanol, or 25 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 75 mole % 1,4-cyclohexanedimethanol, or 35 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 65 mole % 1,4-cyclohexanedimethanol, or 40 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 60 mole % 1,4-cyclohexanedimethanol, or 45 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 55 mole % 1,4-cyclohexanedimethanol, or 50 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 50 mole % 1,4-cyclohexanedimethanol, or 40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol, or greater than 50 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to less than 50 mole % 1,4-cyclohexanedimethanol, or greater than 50 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to less than 50 mole % 1,4-cyclohexanedimethanol, or greater than 51 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to less than 49 mole % 1,4-cyclohexanedimethanol, or 30 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 70 mole % 1,4-cyclohexanedimethanol, or 30 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 70 mole % 1,4-cyclohexanedimethanol.

7. The bottle of Claim 3, wherein the glycol component of said polyester comprises 40 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 60 mole % 1,4-cyclohexanedimethanol, or 40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol.

8. The bottle of Claim 5, wherein the glycol component of said polyester comprises 40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol.

9. The bottle of Claim 1, wherein the polyester comprises:

(b) a glycol component comprising:

- i) 5 to less than 50 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) greater than 50 to 95 mole % of 1,4-cyclohexanedimethanol residues,

wherein the inherent viscosity of the polyester is from 0.50 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein the polyester has a Tg of 85 to 120°C.

10. The bottle of Claim 9 wherein the inherent viscosity of said polyester is from 0.50 to less than 0.75 dL/g

11. The bottle of Claim 1, wherein the dicarboxylic acid component comprises 80 to 100 mole % of terephthalic acid residues, or 90 to 100 mole % of terephthalic acid residues, or 95 to 100 mole % of terephthalic acid residues.

12. The bottle of Claim 5, wherein the dicarboxylic acid component comprises 95 to 100 mole % of terephthalic acid residues.

13. The bottle of Claim 1, wherein said polyester comprises 1,3-propanediol residues, 1,4-butanediol residues, or mixture thereof.

14. The bottle of Claim 1, 3, or 5 wherein said 2,2,4,4-tetramethyl-1,3-cyclobutanediol is a mixture comprising greater than 50 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 50 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol.

15. The bottle of Claim 1, wherein said 2,2,4,4-tetramethyl-1,3-cyclobutanediol is a mixture comprising greater than 55 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 45 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol.

16. The bottle of Claim 1, wherein said polyester composition comprises at least one polymer chosen from poly(ether-imides), polyphenylene oxides, poly(phenylene oxide)/polystyrene blends, polystyrene resins, polyphenylene sulfides, polyphenylene sulfide/sulfones, poly(ester-carbonates), polycarbonates, polysulfones; polysulfone ethers, and poly(ether-ketones).

17. The bottle of Claim 1, wherein said polyester composition comprises at least one polycarbonate.

18. The bottle of Claim 1, wherein said polyester comprises at least one branching agent residue for the polyester.

19. The bottle of Claim 1, wherein said polyester comprises at least one branching agent residue in an amount of 0.01 to 10 weight % based on the total weight of the polyester.

20. The bottle of Claim 1, wherein the melt viscosity of said polyester is less than 3,000 Pa\*s (30,000 poise) as measured at 1 radian/second on a rotary melt rheometer at 290°C.

21. The bottle of Claim 1, wherein said polyester has a crystallization half-time of greater than 5 minutes at 170°C, or of greater than 50 minutes at 170°C, the crystallization half-time being determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage.

22. The bottle of Claim 1, wherein said polyester composition has a density of less than 1.3 g/ml at 23°C by using a gradient density column.

23. The bottle of Claim 1, wherein said polyester composition comprises at least one thermal stabilizer.

24. The bottle of Claim 1, wherein the polyester composition has a b\* value of from - 10 to less than 10 and the L\* values can be from 50 to 90 according to the L\*, a\* and b\* color system of the CIE (International Commission on Illumination).

25. The bottle of Claim 1, wherein said polyester has a notched Izod impact strength of at least 534 J/m (10 ft-lbs/in) at 23°C according to ASTM D256 with a 254 μm (10-mil) notch in a 3.2 mm (1/8-inch) thick bar.

26. The bottle of Claim 1, wherein said polyester has an inherent viscosity of from 0.5 to 1.2 dL/g

27. The bottle of Claim 1, wherein said polyester has an inherent viscosity of from 0.45 to 0.75 dL/g.

28. The bottle of Claim 1, wherein said polyester has an inherent viscosity of from 0.50 to 0.68 dL/g.

29. The bottle of Claim 1 or 26 wherein said bottle is chosen from baby bottles; water bottles; juice bottles; two liter beverage bottles, 0.567 kg (20 ounce) beverage bottles, 0.479 kg (16.9 ounce) beverage bottles; medical bottles; and bottles comprising at least one handle.

30. The bottle of Claim 1, wherein the polyester comprises:

(c) residues of at least one branching agent;

wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C.

### Patentansprüche

1. Flasche umfassend mindestens eine Polyesterzusammensetzung umfassend mindestens einen Polyester, welcher umfasst:

(a) eine Dicarbonsäurekomponente umfassend:

(i) 70 bis 100 Mol-% Terephthalsäurereste;

(ii) 0 bis 30 Mol-% aromatische Dicarbonsäurereste mit bis zu 20 Kohlenstoffatomen; und

(iii) 0 bis 10 Mol-% aliphatische Dicarbonsäurereste mit bis zu 16 Kohlenstoffatomen; und

(b) eine Glykolkomponente umfassend:

(i) 1 bis 99 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiolreste; und

(ii) 1 bis 99 Mol-% 1,4-Cyclohexandimethanolreste,

wobei die gesamten Mol-% der Dicarbonsäurekomponente 100 Mol-% betragen, und die gesamten Mol-% der Glykolkomponente 100 Mol-% betragen; wobei die inhärente Viskosität des besagten Polyesters 0,1 bis 1,2 dL/g beträgt wie bestimmt in 60/40 (Gewicht/Gewicht) Phenol/Tetrachlorethan bei einer Konzentration von 0,5 g/100 ml bei 25 °C; und wobei besagter Polyester eine Tg von 85 bis 200 °C aufweist.

2. Flasche nach Anspruch 1, wobei die inhärente Viskosität des besagten Polyesters beträgt: 0,35 bis 1,0 dL/g, oder 0,40 bis 0,90 dL/g, oder mehr als 0,42 bis 0,80 dL/g, oder 0,45 bis 0,75 dL/g, oder 0,50 bis 0,68 dL/g, oder 0,35 bis 0,75 dL/g, oder 0,35 bis 0,80 dL/g, oder 0,35 bis 0,70 dL/g, oder 0,35 bis weniger als 0,70 dL/g, oder 0,35 bis 0,68 dL/g, oder 0,35 bis weniger als 0,68 dL/g, oder 0,50 bis 0,75 dL/g, oder 0,50 bis 0,70 dL/g, oder 0,50 bis weniger als 0,70 dL/g, oder 0,50 bis weniger als 0,68 dL/g, oder 0,55 bis 0,80 dL/g, oder 0,55 bis 0,75 dL/g, oder 0,55 bis 0,70 dL/g, oder 0,55 bis weniger als 0,70 dL/g, oder 0,55 bis 0,68 dL/g, oder 0,60 bis 0,80 dL/g, oder 0,60 bis 0,75 dL/g, oder 0,60 bis 0,70 dL/g, oder 0,60 bis weniger als 0,70 dL/g, oder 0,60 bis 0,68 dL/g.

3. Flasche nach Anspruch 1, wobei die inhärente Viskosität des besagten Polyesters 0,60 bis 0,72 dL/g beträgt.

4. Flasche nach Anspruch 1, wobei besagter Polyester eine Tg aufweist von 100 bis 190 °C, oder von 100 bis 180 °C, oder von 100 bis 160 °C, oder von 100 bis 150 °C, oder von 100 bis 140 °C, oder von 100 bis 130 °C, oder von 100 bis 120 °C, oder von 110 bis 180 °C, oder von 110 bis 160 °C, oder von 110 bis 150 °C, oder von 110 bis 140 °C, oder von 110 bis 130 °C, oder von 110 bis 120 °C, oder von 115 bis 180 °C, oder von 115 bis 170 °C, oder von 115 bis 160 °C, oder von 115 bis 150 °C, oder von 115 bis 140 °C, oder von 115 bis 130 °C, oder von 115 bis 120 °C, oder von 120 bis 160 °C, oder von 120 bis 150 °C, oder von 130 bis 160 °C, oder von 130 bis 150 °C, oder von 130

bis 145 °C.

5. Flasche nach Anspruch 3, wobei besagter Polyester eine Tg von 130 bis 145 °C aufweist.
- 5 6. Flasche nach Anspruch 1, wobei die Glykolkomponente des besagten Polyesters umfasst: 1 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis 99 Mol-% 1,4-Cyclohexandimethanol, oder 25 bis 90 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 10 bis 75 Mol-% 1,4-Cyclohexandimethanol, oder 35 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis 65 Mol-% 1,4-Cyclohexandimethanol, oder 40 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis 60 Mol-% 1,4-Cyclohexandimethanol, oder 45 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis 55 Mol-% 1,4-Cyclohexandimethanol, oder 50 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis 50 Mol-% 1,4-Cyclohexandimethanol, oder 40 bis 65 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 35 bis 60 Mol-% 1,4-Cyclohexandimethanol, oder mehr als 50 bis 99 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 1 bis weniger als 50 Mol-% 1,4-Cyclohexandimethanol, oder mehr als 50 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis weniger als 50 Mol-% 1,4-Cyclohexandimethanol, oder mehr als 51 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis weniger als 49 Mol-% 1,4-Cyclohexandimethanol, oder 30 bis 60 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 40 bis 70 Mol-% 1,4-Cyclohexandimethanol, oder 30 bis 50 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 50 bis 70 Mol-% 1,4-Cyclohexandimethanol, oder 30 bis 45 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 55 bis 70 Mol-% 1,4-Cyclohexandimethanol, oder 30 bis 40 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 60 bis 70 Mol-% 1,4-Cyclohexandimethanol, oder 30 bis 35 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 65 bis 70 Mol-% 1,4-Cyclohexandimethanol.
- 10
7. Flasche nach Anspruch 3, wobei die Glykolkomponente des besagten Polyesters umfasst: 40 bis 80 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 20 bis 60 Mol-% 1,4-Cyclohexandimethanol, oder 40 bis 65 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 35 bis 60 Mol-% 1,4-Cyclohexandimethanol.
- 15
8. Flasche nach Anspruch 5, wobei die Glykolkomponente des besagten Polyesters umfasst: 40 bis 65 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiol und 35 bis 60 Mol-% 1,4-Cyclohexandimethanol.
- 20
9. Flasche nach Anspruch 1, wobei der Polyester umfasst:
- (b) eine Glykolkomponente umfassend:
- (i) 5 bis weniger als 50 Mol-% 2,2,4,4-Tetramethyl-1,3-cyclobutandiolreste; und
- 35 (ii) mehr als 50 bis 95 Mol-% 1,4-Cyclohexandimethanolreste,
- wobei die inhärente Viskosität des Polyesters 0,50 bis 1,2 dL/g beträgt wie bestimmt in 60/40 (Gewicht/Gewicht) Phenol/Tetrachlorethan bei einer Konzentration von 0,5 g/100 ml bei 25 °C; und wobei der Polyester eine Tg von 85 bis 120 °C aufweist.
- 40
10. Flasche nach Anspruch 9, wobei die inhärente Viskosität des besagten Polyesters 0,50 bis weniger 0,75 dL/g beträgt.
11. Flasche nach Anspruch 1, wobei die Dicarbonsäurekomponente umfasst: 80 bis 100 Mol-% Terephthalsäurereste, oder 90 bis 100 Mol-% Terephthalsäurereste, oder 95 bis 100 Mol-% Terephthalsäurereste.
- 45
12. Flasche nach Anspruch 5, wobei die Dicarbonsäurekomponente umfasst: 95 bis 100 Mol-% Terephthalsäurereste.
13. Flasche nach Anspruch 1, wobei besagter Polyester umfasst: 1,3-Propandiolreste, 1,4-Butandiolreste, oder eine Mischung davon.
- 50
14. Flasche nach Anspruch 1, 3 oder 5, wobei besagtes 2,2,4,4-Tetramethyl-1,3-cyclobutandiol eine Mischung ist umfassend: mehr als 50 Mol-% cis-2,2,4,4-Tetramethyl-1,3-cyclobutandiol und weniger als 50 Mol-% trans-2,2,4,4-Tetramethyl-1,3-cyclobutandiol.
- 55
15. Flasche nach Anspruch 1, wobei besagtes 2,2,4,4-Tetramethyl-1,3-cyclobutandiol eine Mischung ist umfassend: mehr als 55 Mol-% cis-2,2,4,4-Tetramethyl-1,3-cyclobutandiol und weniger als 45 Mol-% trans-2,2,4,4-Tetramethyl-1,3-cyclobutandiol.

## EP 1 907 442 B9

- 5
16. Flasche nach Anspruch 1, wobei besagte Polyesterzusammensetzung mindestens ein Polymer umfasst ausgewählt aus: Polyetherimide, Polyphenylenoxide, Polyphenylenoxid/Polystyrol-Blends, Polystyrolharze, Polyphenylensulfide, Polyphenylensulfid/-sulfone, Polyestercarbonate, Polycarbonate, Polysulfone, Polysulfonether, und Polyetherketone.
- 10
17. Flasche nach Anspruch 1, wobei besagte Polyesterzusammensetzung mindestens ein Polycarbonat umfasst.
18. Flasche nach Anspruch 1, wobei besagter Polyester umfasst: mindestens einen Rest eines Verzweigungsmittels für den Polyester.
- 15
19. Flasche nach Anspruch 1, wobei besagter Polyester umfasst: mindestens einen Rest eines Verzweigungsmittels in einer Menge von 0,01 bis 10 Gewichts-% bezogen auf das Gesamtgewicht des Polyesters.
20. Flasche nach Anspruch 1, wobei die Schmelzviskosität des besagten Polyesters weniger als 3.000 Pa·s (30.000 Poise) beträgt wie gemessen bei 1 Rad/s auf einem Schmelzviskosimeter bei 290 °C.
- 25
21. Flasche nach Anspruch 1, wobei besagter Polyester eine Kristallisationshalbwertszeit von mehr als fünf Minuten bei 170 °C, oder von mehr als 50 Minuten bei 170 °C aufweist, wobei die Kristallisationshalbwertszeit bestimmt wird durch Messung der Lichttransmission einer Probe mittels eines Lasers und Photodetektors als eine Funktion der Zeit auf einer temperaturgesteuerten heißen Platte.
- 30
22. Flasche nach Anspruch 1, wobei besagte Polyesterzusammensetzung eine Dichte von weniger als 1,3 g/ml bei 23 °C aufweist unter Verwendung einer Gradientendichtensäule.
23. Flasche nach Anspruch 1, wobei besagte Polyesterzusammensetzung mindestens einen Wärmestabilisator umfasst.
- 35
24. Flasche nach Anspruch 1, wobei die Polyesterzusammensetzung einen b\*-Wert von -10 bis weniger als 10 aufweist und die L\*-Werte 50 bis 90 sein können gemäß dem L\*, a\* und b\*-Farbsystem der CIE (International Commission on Illumination).
- 40
25. Flasche nach Anspruch 1, wobei besagter Polyester eine Kerbschlagzähigkeit nach Izod von mindestens 534 J/m (10 ft-lbs/in) bei 23 °C aufweist gemäß ASTM D256 gemessen mit einer 254µm (10-mil) Kerbe in einer 3,2 mm (1/8-inch) dicken Stange.
- 45
26. Flasche nach Anspruch 1, wobei besagter Polyester eine inhärente Viskosität von 0,5 bis 1,2 dL/g aufweist.
27. Flasche nach Anspruch 1, wobei besagter Polyester eine inhärente Viskosität von 0,45 bis 0,75 dL/g aufweist.
- 50
28. Flasche nach Anspruch 1, wobei besagter Polyester eine inhärente Viskosität von 0,5 bis 0,68 dL/g aufweist.
29. Flasche nach Anspruch 1 oder 26, wobei besagte Flasche ausgewählt ist aus Babyflaschen; Wasserflaschen, Fruchtsaftflaschen; Zwei-Liter-Getränkeflaschen, 0,567 kg (20 ounce) Getränkeflaschen; 0,479 kg (16,9 ounce) Getränkeflaschen; medizinischen Flaschen; und Flaschen, die mindestens einen Griff umfassen.
30. Flasche nach Anspruch 1, wobei der Polyester umfasst:
- (c) Reste mindestens eines Verzweigungsmittels;
- wobei die inhärente Viskosität des besagten Polyesters 0,35 bis 1,2 dL/g beträgt wie bestimmt in 60/40 (Gewicht/Gewicht) Phenol/Tetrachlorethan bei einer Konzentration von 0,5 g/100 ml bei 25 °C.

### Revendications

- 55
1. Bouteille comprenant au moins une composition de polyester comprenant au moins un polyester qui comprend :
- (a) un composant acide dicarboxylique comprenant :

## EP 1 907 442 B9

- i) 70 à 100 % en mol de résidus acide téréphtalique ;
- ii) 0 à 30 % en mol de résidus acide dicarboxylique aromatique ayant jusqu'à 20 atomes de carbone ; et
- iii) 0 à 10 % en mol de résidus acide dicarboxylique aliphatique ayant jusqu'à 16 atomes de carbone ; et

5 (b) un composant glycol comprenant :

- i) 1 à 99 % en mol de résidus 2,2,4,4-tétraméthyl-1,3-cyclobutanediol ; et
- ii) 1 à 99 % en mol de résidus 1,4-cyclohexanediméthanol,

10 où le pourcentage total en mol du composant acide dicarboxylique est de 100 % en mol et le pourcentage total en mol du composant glycol est de 100 % en mol ; où la viscosité intrinsèque dudit polyester est de 0,10 à 1,2 dl/g telle que déterminée dans du phénol/tétrachloroéthane 60/40 (p/p) à une concentration de 0,5 g/100 mol à 25°C ; et où ledit polyester a une Tg de 85 à 200°C.

15 **2.** Bouteille selon la revendication 1, où la viscosité intrinsèque dudit polyester est de 0,35 à 1,0 dl/g ou de 0,40 à 0,90 dl/g ou de plus de 0,42 à 0,80 dl/g ou de 0,45 à 0,75 dl/g ou de 0,50 à 0,68 dl/g ou de 0,35 à 0,75 dl/g ou de 0,35 à 0,80 dl/g ou de 0,35 à 0,70 dl/g ou de 0,35 à moins de 0,70 dl/g ou de 0,35 dl/g à 0,68 dl/g ou de 0,35 à moins de 0,68 dl/g ou de 0,50 à 0,75 dl/g ou de 0,50 à 0,70 dl/g ou de 0,50 à moins de 0,70 dl/g ou de 0,50 à moins de 0,68 dl/g ou de 0,55 à 0,80 dl/g ou de 0,55 à 0,75 dl/g ou de 0,55 à 0,70 dl/g ou de 0,55 à moins de 0,70 dl/g ou de 0,55 à 0,68 dl/g ou de 0,60 à 0,80 dl/g ou de 0,60 à 0,75 dl/g ou de 0,60 à 0,70 dl/g ou de 0,60 à moins de 0,70 dl/g ou de 0,60 à moins de 0,68 dl/g.

**3.** Bouteille selon la revendication 1, où la viscosité intrinsèque dudit polyester est de 0,60 à 0,72 dl/g.

25 **4.** Bouteille selon la revendication 1, où ledit polyester a une Tg de 100 à 190°C ou de 100 à 180°C ou de 100 à 160°C ou de 100 à 150°C ou de 100 à 140°C ou de 100 à 130°C ou de 100 à 120°C ou de 110 à 180°C ou de 110 à 160°C ou de 110 à 150°C ou de 110 à 140°C ou de 110 à 130°C ou de 110 à 120°C ou de 115 à 180°C ou de 115 à 170°C ou de 115 à 160°C ou de 115 à 150°C ou de 115 à 140°C ou de 115 à 130°C ou de 115 à 120°C ou de 120 à 160°C ou de 120 à 150°C ou de 130 à 160°C ou de 130 à 150°C ou de 130 à 145°C.

30 **5.** Bouteille selon la revendication 3, où ledit polyester a une Tg de 130 à 145°C.

35 **6.** Bouteille selon la revendication 1, où le composant glycol dudit polyester comprend 1 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à 99 % en mol de 1,4-cyclohexanediméthanol ou 25 à 90 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 10 à 75 % en mol de 1,4-cyclohexanediméthanol ou 35 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à 65 % en mol de 1,4-cyclohexanediméthanol ou 40 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à 60 % en mol de 1,4-cyclohexanediméthanol ou 45 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à 55 % en mol de 1,4-cyclohexanediméthanol ou 50 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à 50 % en mol de 1,4-cyclohexanediméthanol ou 40 à 65 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 35 à 60 % en mol de 1,4-cyclohexanediméthanol ou plus de 50 à 99 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 1 à moins de 50 % en mol de 1,4-cyclohexanediméthanol ou plus de 50 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à moins de 50 % en mol de 1,4-cyclohexanediméthanol ou plus de 51 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à moins de 49 % en mol de 1,4-cyclohexanediméthanol ou 30 à 60 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 40 à 70 % en mol de 1,4-cyclohexanediméthanol ou 30 à 50 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 50 à 70 % en mol de 1,4-cyclohexanediméthanol ou 30 à 45 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 55 à 70 % en mol de 1,4-cyclohexanediméthanol ou 30 à 40 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 60 à 70 % en mol de 1,4-cyclohexanediméthanol ou 30 à 35 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 65 à 70 % en mol de 1,4-cyclohexanediméthanol.

50 **7.** Bouteille selon la revendication 3, où le composant glycol dudit polyester comprend 40 à 80 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 20 à 60 % en mol de 1,4-cyclohexanediméthanol ou 40 à 65 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 35 à 60 % en mol de 1,4-cyclohexanediméthanol.

55 **8.** Bouteille selon la revendication 5, où le composant glycol dudit polyester comprend 40 à 65 % en mol de 2,2,4,4-tétraméthyl-1,3-cyclobutanediol et 35 à 60 % en mol de 1,4-cyclohexanediméthanol.

**9.** Bouteille selon la revendication 1, où le polyester comprend :

(b) un composant glycol comprenant :

- i) 5 à moins de 50 % en mol de résidus 2,2,4,4-tétraméthyl-1,3-cyclobutanediol ; et
- ii) plus de 50 à 95 % en mol de résidus 1,4-cyclohexanediméthanol.

5

où la viscosité intrinsèque du polyester est de 0,50 à 1,2 dl/g telle que déterminée dans du phénol/tétrachloroéthane 60/40 (p/p) à une concentration de 0,5 g/100 ml à 25°C ; et où le polyester a une Tg de 85 à 120°C.

10

10. Bouteille selon la revendication 9, où la viscosité intrinsèque dudit polyester est de 0,50 à moins de 0,75 dl/g.

11. Bouteille selon la revendication 1, où le composant acide dicarboxylique comprend 80 à 100 % en mol de résidus acide téréphtalique ou 90 à 100 % en mol de résidus acide téréphtalique ou 95 à 100 % en mol de résidus acide téréphtalique.

15

12. Bouteille selon la revendication 5, où le composant acide dicarboxylique comprend 95 à 100 % en mol de résidus acide téréphtalique.

20

13. Bouteille selon la revendication 1, où ledit polyester comprend des résidus 1,3-propanediol, des résidus 1,4-butanediol ou leur mélange.

14. Bouteille selon la revendication 1, 3 ou 5, où ledit 2,2,4,4-tétraméthyl-1,3-cyclobutanediol est un mélange comprenant plus de 50 % en mol de cis-2,2,4,4-tétraméthyl-1,3-cyclobutanediol et moins de 50 % en mol de trans-2,2,4,4-tétraméthyl-1,3-cyclobutanediol.

25

15. Bouteille selon la revendication 1, où ledit 2,2,4,4-tétraméthyl-1,3-cyclobutanediol est un mélange comprenant plus de 55 % en mol de cis-2,2,4,4-tétraméthyl-1,3-cyclobutanediol et moins de 45 % en mol de trans-2,2,4,4-tétraméthyl-1,3-cyclobutanediol.

30

16. Bouteille selon la revendication 1, où ladite composition de polyester comprend au moins un polymère choisi parmi les poly(étherimides), poly(oxydes de phénylène), mélanges poly(oxyde de phénylène)/polystyrène, résines de polystyrène, poly(sulfures de phénylène), poly(sulfures de phénylène)/sulfones, poly(ester-carbonates), polycarbonates, polysulfones ; polysulfone-éthers et poly(éther-cétones).

35

17. Bouteille selon la revendication 1, où ladite composition de polyester comprend au moins un polycarbonate.

18. Bouteille selon la revendication 1, où ledit polyester comprend au moins un résidu agent de ramification pour le polyester.

40

19. Bouteille selon la revendication 1, où ledit polyester comprend au moins un résidu agent de ramification en une quantité de 0,01 à 10 % en poids par rapport au poids total du polyester.

20. Bouteille selon la revendication 1, où la viscosité au fondu dudit polyester est inférieure à 3 000 Pa.s (30 000 poises) telle que mesurée à un radian/sec sur un rhéomètre rotatif à 290°C.

45

21. Bouteille selon la revendication 1, où ledit polyester a une demi-vie de cristallisation supérieure à 5 min à 170°C ou supérieure à 50 min à 170°C, la demi-vie de cristallisation étant déterminée par mesure de la phototransmission d'un échantillon au moyen d'un laser et d'un photodétecteur en fonction du temps sur une plaque chauffante à température contrôlée.

50

22. Bouteille selon la revendication 1, où ladite composition de polyester a une densité inférieure à 1,3 g/ml à 23°C en utilisant une colonne à gradient de densité.

23. Bouteille selon la revendication 1, où ladite composition de polyester comprend au moins un stabilisant thermique.

55

24. Bouteille selon la revendication 1, où la composition de polyester a une valeur b\* de -10 à moins de 10 et les valeurs L\* peuvent être de 50 à 90 selon le système de couleur L\*, a\* et b\* de la CIE (International Commission on Illumination).

25. Bouteille selon la revendication 1, où ledit polyester a une résistance au choc Izod avec entaille d'au moins 534 J/m

## EP 1 907 442 B9

(10 pieds-livres/pouce) à 23°C selon ASTM D256 pour une entaille de 254 µm (10 millièmes de mm) dans une barre de 3,2 mm (1/8 pouce) d'épaisseur.

- 5
- 26.** Bouteille selon la revendication 1, où ledit polyester a une viscosité intrinsèque de 0,5 à 1,2 dl/g.
- 27.** Bouteille selon la revendication 1, où ledit polyester a une viscosité intrinsèque de 0,45 à 0,75 dl/g.
- 28.** Bouteille selon la revendication 1, où ledit polyester a une viscosité intrinsèque de 0,50 à 0,68 dl/g.
- 10
- 29.** Bouteille selon la revendication 1 ou 26, où ladite bouteille est choisie parmi des biberons, des bouteilles d'eau, des bouteilles de jus de fruits, des bouteilles pour boissons de 2 litres, des bouteilles pour boissons de 0,567 kg (20 onces), des bouteilles pour boissons de 0,479 kg (16,9 onces) ; des flacons médicaux ; et des bouteilles comprenant au moins une poignée.
- 15
- 30.** Bouteille selon la revendication 1, où le polyester comprend :
- (c) des résidus d'au moins un agent de ramification ;
- 20
- où la viscosité intrinsèque dudit polyester est de 0,35 à 1,2 dl/g telle que déterminée dans du phénol/tétrachloroéthane 60/40 (p/p) à une concentration de 0,5 g/100 ml à 25°C.

25

30



35

40



45

50


55



*Fig. 1*



*Fig. 2*



■ ~18.5 MOLE% TMCD  
 ● ~30.8 MOLE% TMCD  
 ▲ ~45.9 MOLE% TMCD  
 — TREND FOR EACH TMCD/CHDM COMPOSITION

*Fig. 3*

**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- US 5654347 A [0181]
- US 5696176 A [0181]
- US 3772405 A [0201]
- US 4452933 A [0208]
- US 3169121 A [0213]
- US 3207814 A [0213]
- US 4194038 A [0213]
- US 4156069 A [0213]
- US 4430484 A [0213]
- US 4465820 A [0213]
- US 4981898 A [0213]