



(11) **EP 1 985 689 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
29.10.2008 Bulletin 2008/44

(51) Int Cl.:
C10M 163/00 (2006.01) **C10N 10/04** (2006.01)
C10N 30/02 (2006.01) **C10N 30/04** (2006.01)
C10N 40/26 (2006.01)

(21) Application number: **07251415.1**

(22) Date of filing: **30.03.2007**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE
SI SK TR**
Designated Extension States:
AL BA HR MK RS

(71) Applicant: **BP p.l.c.**
London SW1Y 4PD (GB)

(72) Inventor: **The designation of the inventor has not yet been filed**

(74) Representative: **Perkins, Nicholas David**
BP International Limited
Global Patents & Technology Law (Central)
Bldg 200, 1st floor
Chertsey Road
Sunbury-on-Thames, Middlesex TW16 7LN (GB)

(54) **Lubrication methods**

(57) A method of lubricating a two-stroke, diesel crosshead engine comprises lubricating the engine with a cylinder oil and with a system oil, which oils are different from each other, in which the system oil is an SAE 20 or SAE 30 oil, has a total base number of at least 10 mg KOH/g and comprises :- (a) a base oil; (b) at least one detergent additive in a total amount of detergent corresponding in performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of

a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group; and (c) at least one anti-wear additive. The method further comprising replenishing the system oil in the engine with a top-up system oil, in which the top-up system oil has the same additives as in the system oil previously charged to the engine but has a viscosity which is lower than that of the system oil previously charged to the engine.

EP 1 985 689 A1

Description

[0001] This invention relates to lubrication methods and in particular to methods for lubricating two-stroke, diesel crosshead engines.

[0002] Two-stroke, diesel crosshead engines are compression ignition engines in which each piston rod is connected to the crankshaft by a crosshead bearing (sometimes also just referred to as a crosshead). Such engines are usually used in marine applications and sometimes in land-based power generation plants. In two-stroke, diesel crosshead engines, the cylinder liner is lubricated by a cylinder oil which lubricates the inner walls of the cylinder and the piston ring pack and controls corrosive and mechanical wear. The cylinder oil also removes deposits from the outer surfaces of the pistons, and from the piston rings and/or cylinder liners. In two-stroke, diesel crosshead engines, the crankcase is lubricated with a system oil which lubricates the crankshaft, the crosshead, the main bearings, the crosshead bearings and the camshaft and protects the crankcase against corrosion. The system oil also cools the piston undercrown and removes deposits from the undercrown area. These two lubricating systems are separated by a barrier (sometimes referred to as a stuffing box) to minimise contamination of the system oil, for example by un-burnt fuel, by by-products of the combustion of the fuel, by used cylinder oil which may have leaked through the stuffing box, or by water which may have leaked from the engine's cooling system.

[0003] Generally, system oils do not have high base numbers or a high neutralisation capacity because the system oil is not generally exposed to acidic by-product gases produced by combustion of the diesel fuel. Generally, system oils do not have very high contaminant-handling performance because generally they are not expected to be subject to any great extent to contamination by un-burnt fuel etc. because of the separation provided by the stuffing box. However, current experience indicates that this is not always the case.

[0004] System oils typically available in the market to date have a viscosity in the SAE30 range typically about 11.5 cSt at 100 °C, and a total base number (sometimes referred to as BN) of typically 6 mg KOH/g or less.

[0005] Whilst such system oils may additionally contain some anti-wear, corrosion-inhibition and/or anti-oxidancy additives, they are generally not well suited to cope with the higher levels of contamination of system oil which are increasingly being encountered in modern crosshead engines, where such contamination may include unburnt fuel, by-products of the combustion of the fuel, used cylinder oil and/or water.

[0006] In use, over time, some of the system oil in the engine is consumed. Normal practice is to top-up the engine with fresh system oil which is the same as that previously charged to the engine. On-line cleaning of the system oil is usually also used. If contamination of the system oil is low, top-up with fresh system oil which is the same as that previously charged to the engine when combined with on-line cleaning may allow the properties of the system oil in the engine to remain within acceptable limits, for example, as defined by the engine designer.

[0007] If contamination of the system oil is too high, partial or complete replacement of the system oil in the engine with fresh system oil which is the same as that previously charged to the engine, may be required to maintain the properties of the system oil in the engine within acceptable limits.

[0008] One property of the system oil in the engine which may require correction is viscosity. This commonly increases during operation of the engine. Usually, partial replacement of the system oil in the engine with fresh system oil of the same viscosity as that previously charged to the engine is used to correct this viscosity increase. However, it is also known, but not common, to use a system oil (sometimes referred to as a cutter oil) which has a viscosity which is less than that of the system oil previously charged to the engine. This may reduce the extent of replacement of the system oil which is required to correct the viscosity increase. For example, according to www.lubmarine.com, ATLANTA MARINE 20 (trade mark) is said to be used to top up crankcase lubrication of slow 2 stroke crosshead diesel engines when the viscosity and the BN of the in service system oil is higher than the warning limit, due to contamination by cylinder lubricant through the stuffing box. It is said that it can be used to regularly top up in order to decrease and to maintain the viscosity at an acceptable level or to replace a part of the in service oil in order to drastically decrease the viscosity below the warning limit. ATLANTA MARINE 20 has a base number of only 2.

[0009] Although a top-up system oil which is added to the engine may have a lower viscosity than that previously charged to the engine, it will generally have the same additives, and in the same concentrations, as those in the system oil which was previously charged to the engine. In some cases, a system oil of the desired viscosity but with no, or relatively low, additive content may be used, for example a base oil or a hydraulic oil. Although these may correct the problem of increasing viscosity of the system oil in the engine, they do not do much to address other aspects of degradation of the performance of the system oil. In particular, they may not address the problem of increased contamination (for example leaked fuel, combustion debris and by-products, and/or waste cylinder oil) in the system oil, which is increasingly being encountered by modern two-stroke, diesel crosshead engines, and which is usually the dominant underlying cause of the viscosity increase.

[0010] With conventional system oils there is often a limit to the number of times one can cut back the viscosity by topping-up and/or partial replacement of the system oil in the engine, because other factors (for example, oil degradation and contamination) will eventually become dominant. This may require complete replacement of the system oil in the

engine, even though the viscosity may be within acceptable limits.

[0011] The range within which the viscosity of the system oil in the engine must be maintained is usually quite wide and may permit the viscosity of the system oil in the engine to be allowed to rise considerably above the viscosity of the system oil previously charged to the engine. However, fuel economy benefits may be obtained if the viscosity of the system oil in the engine can be maintained at a low value within the allowable range.

[0012] According to EP-1728849-A a typical system oil has a viscosity at 100 °C of 11.5 cSt and a total base number of 5 mg KOH/g (ASTM 2896-98). EP-1728849-A seeks to provide a method of lubricating a cylinder liner and a crankcase in a marine diesel crosshead engine with the same lubricant. This lubricant is said to comprise at least 40 mass % of an oil of lubricating viscosity, at least one detergent, at least one dispersant and at least one anti-wear additive, the lubricating oil composition having a BN, as measured using ASTM D 2896-98, of 10 to 55, preferably 20 to 45, mg KOH/g. Lubricating a crosshead engine with the same lubricant used as both cylinder oil and system oil has disadvantages, one of which at least, is that the properties of that lubricant will be a compromise of properties suited for cylinder oil duties and properties suited for system oil duties, and the oil is therefore not optimised for either duty. For example, according to EP-1728849-A, the lubricating oil composition preferably has a viscosity at 100 °C of 15 to 21 cSt. Such a high viscosity in a system oil is expected to cause poorer fuel economy than would be obtained, for example with a typical system oil having a viscosity at 100°C of 11.5 cSt.

[0013] There is thus a need for a method of lubricating two-stroke diesel engine which avoids or at least mitigates these problems.

[0014] Thus, according to the present invention there is provided a method of lubricating a two-stroke, diesel crosshead engine which method comprises lubricating the engine with a cylinder oil and with a system oil, which oils are different from each other, characterised in that the system oil is an SAE 20 or SAE 30 oil, has a total base number of at least 10 mg KOH/g and comprises :-

(a) a base oil;

(b) at least one detergent additive in a total amount of detergent corresponding in performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group; and

(c) at least one anti-wear additive.

[0015] The present invention solves the technical problems identified above by the use of a system oil comprising at least one anti-wear additive and having a defined performance and a defined base number. This can mitigate the problem of increased contamination (for example leaked fuel, combustion debris and by-products, and/or waste cylinder oil) in the system oil which is encountered by modern two-stroke, diesel crosshead engines, and which is usually the dominant underlying cause of the viscosity increase.

[0016] The present invention may be particularly beneficial when the system oil in the engine is partially replaced and/or topped-up to control the properties of the system oil in the engine, for example to control the viscosity of the system oil in the engine.

[0017] Thus, according to a further aspect of the present invention there is provided a method of lubricating a two-stroke, diesel crosshead engine which method comprises lubricating the engine with a cylinder oil and with a system oil, which oils are different from each other, characterised in that the system oil is an SAE 20 or SAE 30 oil, has a total base number of at least 10 mg KOH/g and comprises :-

(a) a base oil;

(b) at least one detergent additive in a total amount of detergent corresponding in performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group; and

(c) at least one anti-wear additive,

the method further comprising replenishing the system oil in the engine with a top-up system oil, in which the top-up system oil has the same additives as in the system oil previously charged to the engine but has a viscosity which is lower than that of the system oil previously charged to the engine.

[0018] In this embodiment of the present invention, when the system oil in the engine is topped-up and/or partially replaced with a system oil which has a viscosity which is less than that of the system oil originally charged to the engine, but has the same additives as those in the system oil which was previously charged to the engine, the problem of increasing viscosity of the system oil in the engine can be addressed at the same time as addressing other aspects of degradation of the performance of the system oil, such as the problem of increased contamination (for example leaked fuel, combustion debris and by-products, and/or waste cylinder oil) in the system oil. This may enable the viscosity of the system oil in the engine to be controlled within a range of viscosities which is lower than might otherwise be the

case. This can have benefits of fuel economy for the engine.

[0019] The top-up system oil of the present invention has the same additives as those in the system oil which was previously charged to the engine, but in concentrations which independently, may be the same or different to the concentrations in the system oil which was previously charged to the engine.

[0020] The system oil and top-up system oil of the present invention each comprise a base oil. The base oil may comprise at least one basestock selected from the group consisting of Group I basestocks; Group II basestocks; Group III basestocks; basestocks derived from Fischer-Tropsch synthesised, waxy, paraffinic hydrocarbon materials; naphthenic basestocks; mineral basestocks having a viscosity index in the range 40 to 80; and mixtures thereof.

[0021] Basestock groups are defined according to API standard 1509, "ENGINE OIL LICENSING AND CERTIFICATION SYSTEM", November 2004 version 15th edition Appendix E, as set out in Table 1 below :

Table I

Group	Saturated hydrocarbon content (wt%)		Sulphur content (wt%)		Viscosity Index
I	< 90	and/or	> 0.03	and	≥ 80 and < 120
II	≥ 90	and	≤ 0.03	and	≥ 80 and < 120
III	≥ 90	and	≤ 0.03	and	≥ 120
IV	polyalpha olefins				
V	all basestocks not in Groups I, II, III or IV				

[0022] Group I and Group II basestock are derived from mineral oil by known refinery process. Group III basestocks may be derived from mineral oil by refinery processes known in the art. Group III basestocks may also be known as synthetic basestocks and include for example, Shell XHVI (trade mark) and Nexbase (trade mark). Naphthenic basestocks and other mineral oil basestocks may be derived from mineral oil by refinery processes known in the art.

[0023] Basestocks derived from Fischer-Tropsch synthesised, waxy, paraffinic hydrocarbon materials may be made by any suitable known process for the manufacture of basestock from Fischer Tropsch processes. Processes for the manufacture of a basestock derived from Fischer-Tropsch synthesised, waxy, paraffinic hydrocarbon material which may be used, are described for example in US4943672, EP-A-0668342 and EP-A-0776959, the contents of which are hereby incorporated by reference. Thus, the basestock may be made by the steps of (i) producing Syngas, (ii) Fischer-Tropsch synthesis of hydrocarbons from the Syngas, (iii) hydrocracking of the hydrocarbons to produce naphtha and diesel/kerosene fuel process streams together with a waxy paraffinic residue and (iv) hydroisomerising the waxy residue to produce the basestock.

[0024] The system oil and top-up system oil each comprise at least one detergent additive in a total amount of detergent corresponding in performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group. Preferably, the system oil and top-up system oil each comprise at least one detergent additive in a total amount of detergent corresponding in performance, as measured by the Hot Filtration Test, to at least 1.75 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group.

[0025] The detergent additive performance is measured by the Hot Filtration Test. This compares the performance of a test sample against a reference sample. The Hot Filtration Test is a measure of detergency and fuel-contamination handling performance of the detergent additive. The following procedure may be used, the test being performed in duplicate :

1. A representative sample (25 g) of the lubricant to be tested is mixed thoroughly with 5 -15 % by weight of fuel oil, the amount depending upon the fuel oil quality. The fuel oil must be a residual fuel oil with a viscosity of approximately 380 cSt (measured at 50 °C) and preferably, having a heptane-insoluble asphaltene content measured by IP 143/01 method of between 8 and 10 % by weight.
2. The mixture is mixed thoroughly and the stored for 24 hours at a temperature of 100 °C.
3. A weighed sample of the mixture is then filtered at 100 °C through glass-fibre filter papers in the apparatus as prescribed in IP375/99, with a target filtrate volume equivalent to 10 g of the mixture from step (2).
4. After washing and drying the filters as prescribed in IP 375/99, the weight of sediment captured by the filters is measured and expressed as a percentage of the sample according to IP375/99.
5. The result is expressed as an average of the duplicate tests.

6. The procedure is repeated using a reference lubricant having 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group;

7. If the average percentage sediment measured for the test system oil is the same or less than that measured for the reference sample, the test system oil is deemed to have a total amount of detergent corresponding in detergency and fuel-contamination handling performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group.

[0026] Each of the one or more detergent additives may comprise a metal salt of an acidic organic compound and a base. The metal may be an alkali or alkaline earth metal, for example sodium, potassium, lithium, calcium, barium or magnesium. Mixtures of metal salts may be used. Preferably, the metal is calcium.

[0027] Each of the one or more detergent additives may comprise a metal salt of a carboxylate, a sulphonate, a phenate, a thiophosphate or a naphthenate. Mixtures of salts may be used. A preferred carboxylate is salicylate.

[0028] Preferably, the one or more detergent additives of the present invention comprise calcium phenates, calcium salicylates or mixtures thereof.

[0029] Preferably, the system oil comprises at least one calcium alkyl salicylate detergent additive, in which the alkyl group is a C₁₂ to C₃₀ alkyl group, in a total amount of at least 1.5 % by weight of the system oil, more preferably at least 1.75 % by weight, of calcium alkyl salicylate detergent soap.

[0030] Preferably, the system oil and top-up system oil each comprise at least one calcium alkyl salicylate detergent additive in which the alkyl group is a C₁₂ to C₃₀ alkyl group, in a total amount of at least 1.5 % by weight, more preferably at least 1.75 % by weight of the system oil and top-up system oil, of calcium alkyl salicylate detergent soap.

[0031] Each of the one or more detergent additives of the present invention may comprise a complex/hybrid detergent which may be prepared from a mixture of one or more metal surfactants, for example from a mixture of a calcium alkyl phenate and a calcium alkyl salicylate.

[0032] Each of the one or more detergent additives may contain at least one hydrocarbyl group, for example as a substituent on an aromatic ring. The term hydrocarbyl means that the group is primarily composed of hydrogen and carbon atoms and is bonded to the remainder of the compound via a carbon atom, but does not exclude the presence of other atoms or groups in a proportion insufficient to detract from the substantially hydrocarbon characteristics of the group. Advantageously, the alkyl groups have 5 to 100, preferably 7 to 30 carbon atoms.

[0033] Each of the one or more detergent additives may be sulphurised. Processes for sulphurizing are known in the art.

[0034] Each of the one or more detergent additives may be borated. Processes for borating are known in the art.

[0035] Each of the one or more detergent additives may be a neutral detergent, a low based detergent, a low overbased detergent or a high overbased detergent

[0036] Each of the one or more detergent additives may have a total base number in the range of from greater than 0 to 500 mg KOH/g, preferably in the range 25 to 500 mg KOH/g, more preferably in the range of 30 to 300 mg KOH/g.

[0037] Total base numbers may be measured according to ASTM D 2896-98.

[0038] The system oil and top-up system oil each may comprise at least one high base detergent additive in a relatively large amount - for example calcium phenate with a total base number of 400 mg KOH/g in an amount of 5 % by weight.

[0039] The system oil and top-up system oil of the present invention each comprise at least one anti-wear additive. Suitable anti-wear additives include dihydrocarbyl dithiophosphate metal salts. The metals of the dihydrocarbyl dithiophosphate metal salts may be alkali metals, alkaline earth metals, aluminium, lead, tin, molybdenum, manganese, nickel, zinc or copper. Preferably, the system oil and top-up system oil of the present invention each comprise at least one zinc dihydrocarbyl dithiophosphate anti-wear additive. Primary and/or secondary hydrocarbyl groups may be present in the anti-wear additives. The hydrocarbyl groups may be alkyl groups. Each hydrocarbyl group may have 1 to 18 carbon atoms. The total amount of the anti-wear additives in each of the system oil and the top-up system oil of the present invention is preferably in the range, expressed as zinc of up to 1100 ppm zinc. The total amount of the anti-wear additives in each of the system oil and the top-up system oil of the present invention is preferably in the range, expressed as phosphorus of up to 1000 ppm phosphorus, preferably in the range 100 to 600 ppm phosphorus and more preferably in the range of 200 to 400 ppm phosphorus.

[0040] The system oil and top-up system oil of the present invention may also comprise one or more dispersants. Preferably, the dispersants are ashless dispersants. These are non-metallic organic compounds that form substantially no ash on combustion. Each ashless dispersant may comprise a long chain hydrocarbon with a polar head. The polar head may comprise oxygen, phosphorus or nitrogen atoms. The hydrocarbon chain may have 40 to 500 carbon atoms. Suitable ashless dispersants are succinimides, for example polyisobutene succinic anhydride; polyamine condensation products; succinimides, for example polyisobutene succinimides; succinic esters, for example polyisobutene succinic esters; or aminated succinic ester, for example aminated polyisobutene succinic esters. The dispersants may be borated. If present, the total amount of dispersant in each of the system oil and top-up system oil of the present invention may be in the range of from greater than 0 to 3 % by weight, preferably in the range of from greater than 0 to 2 %, more preferably in the range of from greater than 0 to 1 % by weight.

[0041] The system oil and top-up system oil of the present invention may also comprise one or more anti-foam additives. Typical anti-foam additives which may be used include polydimethyl siloxanes and methacrylates. If present, the total amount of anti-foam additives in each of the system oil and top-up system oil of the present invention may be an amount expressed as silicon, of up to 50 ppm, preferably up to 30 ppm, more preferably up to 15 ppm.

[0042] The system oil and top-up system oil of the present invention may also comprise one or more anti-rust additives. Typical anti-rust additives which may be used include nonyl phenolamine, octyl phenolamine and non-phenol based anti-rust additives, for example alkylene glycols. If present, the total amount of anti-rust additives in each of the system oil and top-up system oil of the present invention may be up to 1 % by weight, preferably up to 0.5 % by weight and more preferably up to 0.2 % by weight.

[0043] The system oil and top-up system oil of the present invention may also comprise one or more pour point depressants. Typical pour point depressants which may be used include polymethacrylate compounds. If present, the total amount of pour point depressants in each of the system oil and top-up system oil of the present invention may be up to 1 % by weight, preferably up to 0.5 % by weight, more preferably up to 0.25 % by weight.

[0044] The system oil and top-up system oil of the present invention may also comprise one or more anti-oxidants in addition to the anti-wear additives and/or detergents, which may also act at least in part as anti-oxidants. Typical anti-oxidants which may be used include phenolic ashless anti-oxidants and aminic ashless anti-oxidants. If present, the total amount of anti-oxidants other than anti-wear additive and/or detergents which act at least in part as anti-oxidants, in each of the system oil and top-up system oil of the present invention may be up to 1 % by weight, preferably up to 0.5 % by weight, more preferably up to 0.2 % by weight.

[0045] The system oil and top-up system oil of the present invention may also comprise one or more friction modifiers. Typical friction modifiers include salicylates; stearates, for example calcium stearate; glycerol mono oleate and oleamides; and natural esters, for example sunflower oil. If present, the total amount of glycerol mono oleate and/or oleamide friction modifiers in each of the system oil and top-up system oil of the present invention may be up to 1 % by weight, preferably up to 0.5 % by weight, more preferably up to 0.2 % by weight. Other friction modifiers may be present at higher concentrations.

[0046] The system oil and top-up system oil for the present invention may each independently have a total base number of 10 to 40 mg KOH/g, preferably of 10 to 30 mg KOH/g, more preferably of 15 to 30 mg KOH/g, yet more preferably of 15 to 20 mg KOH/g. Preferably, the system oil and the top-up system oil have the same total base number. The top-up system oil may have a base number which is lower than the system oil previously charged to the engine. The top-up system oil may have a base number which is higher than the system oil previously charged to the engine, for example a top-up system oil with a total base number in the range of 15 - 20 mg KOH/g may be used with a system oil previously charged to the engine having a total base number in the range of 10 - 15 mg KOH/g.

[0047] Total base number may be measured according to ASTM D 2896-98.

[0048] The system oil is an SAE 20 or SAE 30 oil. SAE 20 oils have a viscosity at 100 °C in the range of 5.6 to less than 9.3 cSt. SAE 30 oils have a viscosity at 100 °C in the range of 9.3 to less than 12.5 cSt. Preferably, the system oil is an SAE 30 oil. However engine designers and manufacturers often specify minimum viscosities of system oil which may be used in the engine. For example, the system oil used in the present invention may have a kinematic viscosity at 100 °C in the range of 7.9 to less than 12.5 cSt, preferably in the range of 8.8 to 11.5 cSt, more preferably in the range of 9.3 to 11.5 cSt.

[0049] The viscosity of the system oil in the engine may be controlled by replenishing the system oil in the engine with a top-up system oil in which the top-up system oil has the same additives and in the same or different concentrations as in the system oil previously charged to the engine but which has a viscosity which is lower than that of the system oil previously charged to the engine.

[0050] In this embodiment of the present invention, the system oil in the engine may be replenished by adding to the engine, top-up system oil to replace engine oil which has been consumed or lost from the engine. The system oil in the engine may be replenished by removing part of the system oil from the engine and replacing it with top-up system oil. On-line cleaning may be used in conjunction with partial replacement of the system oil in the engine.

[0051] The top-up system oil may be an SAE 20 or an SAE 30 oil, preferably, the top-up system oil is an SAE 20 oil. Preferably, the top-up system oil has a kinematic viscosity measured at 100 °C which is in the range of 5 to 1 cSt less than that of the system oil previously charged to the engine, preferably in the range of 4 to 2 cSt less than that of the system oil originally charged to the engine.

[0052] The viscosity of the system oil in the engine may be regularly and/or continuously monitored. The viscosity of the system oil in the engine may be continuously monitored for example, with an in-line monitor. Addition of system top-up oil may be controlled by an in-line monitor which continuously monitors the viscosity of the system oil in the engine.

[0053] The cylinder oil may be any cylinder oil known in the art. Preferably, the cylinder oil is an SAE 50 oil. Suitable cylinder oils include Castrol Cyltech 50S (trade mark), Castrol Cyltech 80AW (trade mark), Castrol Cyltech 70 (trade mark), Castrol Cyltech 40 SX (trade mark), BP Energol CLO 50M (trade mark), BP Energol CL-DX 405 (trade mark) and BP Energol CL 505 (trade mark).

[0054] The methods of the present invention are used for lubricating a two-stroke, diesel crosshead engine. The diesel engine may be marine or land based.

[0055] The invention will now be described with respect to the following example. A system oil for use in the present invention was prepared using a mixture of Group I basestocks. This system oil comprised zinc dihydrocarbyl dithiophosphate anti-wear additive and had a concentration of salicylate and phenate detergents which will correspond in performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group.

[0056] The system oil was manufactured to a specification which included the features of :

- a kinematic viscosity at 100 °C as measured according to ASTM D445, in the range of 11.0 to 12.0 cSt;
- a total base number as measured according to ASTM D2896 in the range of 29.0 to 32.1 mg KOH/g and
- a zinc content as measured by IP308 in the range of 370 to 420 ppm by weight.

[0057] The system oil was used to lubricant a MAN B & W model 6L 70MC Mk6 marine diesel crosshead engine having a power of 16980 KW at 108 rpm. It was operated with a load of 12917 KW at 103 rpm and 76 to 78 % of its Maximum Continuous Rating.

[0058] An interim inspection of the engine and its oil system was carried out after 1464 hours of engine operation, 3 months into service and this showed the performance of the oil to be satisfactory.

[0059] It is anticipated that with use, the viscosity of the system oil will increase and/or some of the system oil will be lost and/or consumed in the engine. The system oil in the engine may be replenished with a top-up system oil, which has the same additives, in the same or different concentrations as in the system oil previously charged to the engine but which has a viscosity which is lower than that of the system oil previously charged to the engine. A suitable top-up system oil might be an SAE 30 with a kinematic viscosity at 100°C of less than 11.5 cSt. A suitable top-up system oil might be an SAE 20 oil.

Claims

1. A method of lubricating a two-stroke, diesel crosshead engine which method comprises lubricating the engine with a cylinder oil and with a system oil, which oils are different from each other, **characterised in that** the system oil is an SAE 20 or SAE 30 oil, has a total base number of at least 10 mg KOH/g and comprises:-
 - (a) a base oil;
 - (b) at least one detergent additive in a total amount of detergent corresponding in performance, as measured by the Hot Filtration Test, to at least 1.5 % by weight of the system oil, of a calcium alkyl salicylate detergent soap in which the alkyl group is a C₁₂ to C₃₀ alkyl group; and
 - (c) at least one anti-wear additive.
2. A method as claimed in claim 1 in which system oil has a total base number of 10 to 40 mg KOH/g, preferably of 10 to 30 mg KOH/g, more preferably of 15 to 30 mg KOH/g, yet more preferably of 15 to 20 mg KOH/g.
3. A method as claimed in claim 1 or claim 2 in which the system oil has a kinematic viscosity at 100 °C in the range of 7.9 to less than 12.5 cSt, preferably in the range of 8.8 to 11.5 cSt, more preferably in the range of 9.3 to 11.5 cSt.
4. A method as claimed in any one of the preceding claims in which the system oil comprises at least one calcium alkyl salicylate detergent additive, in which the alkyl group is a C₁₂ to C₃₀ alkyl group, in a total amount of at least 1.5 % by weight of the system oil, more preferably at least 1.75 % by weight, of calcium alkyl salicylate detergent soap.
5. A method as claimed in any one of the preceding claims in which the method further comprising replenishing the system oil in the engine with a top-up system oil, in which the top-up system oil has the same additives as in the system oil previously charged to the engine but has a viscosity which is lower than that of the system oil previously charged to the engine.
6. A method as claimed in claim 5 in which the top-up system oil has a total base number of 10 to 40 mg KOH/g, preferably of 10 to 30 mg KOH/g, more preferably of 15 to 30 mg KOH/g, yet more preferably of 15 to 20 mg KOH/g.
7. A method as claimed in claim 5 or claim 6 in which the top-up system oil and the system oil previously charged to the engine have the same base number.

EP 1 985 689 A1

8. A method as claimed in any one of claims 5 to 7 in which the top-up system oil is an SAE 20 or an SAE 30 oil.
9. A method as claimed in any one of claims 5 to 8 in which the top-up system oil has a kinetic viscosity measured at 100 °C which is in the range of 5 to 1 cSt less than that of the system oil previously charged to the engine, preferably in the range of 4 to 2 cSt less than that of the system oil previously charged to the engine.
10. A method as claimed in any one of claims 5 to 9 in which the system oil and the top-up system oil comprise at least one calcium alkyl salicylate detergent additive, in which the alkyl group is a C₁₂ to C₃₀ alkyl group, in a total amount of at least 1.5 % by weight of the system oil, more preferably at least 1.75 % by weight, of calcium alkyl salicylate detergent soap.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 07 25 1415

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	WO 2006/014866 A (LUBRIZOL CORP [US]; LEAHY RICHARD [GB]; MAYHEW ALEXANDRA [GB]; BARNES) 9 February 2006 (2006-02-09) * paragraphs [0002], [0012], [0026], [0039], [0064], [0072]; claims 1,10,14 *	1-4	INV. C10M163/00
A	EP 1 229 101 A (INFINEUM INT LTD [GB]) 7 August 2002 (2002-08-07) * paragraphs [0012], [0013]; examples *	1-4	ADD. C10N10/04 C10N30/02 C10N30/04 C10N40/26
			TECHNICAL FIELDS SEARCHED (IPC)
			C10M
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 27 November 2007	Examiner Kazemi, Pirjo
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

2
EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 07 25 1415

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-11-2007

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2006014866 A	09-02-2006	CA 2574950 A1	09-02-2006
		EP 1778824 A1	02-05-2007

EP 1229101 A	07-08-2002	CA 2370880 A1	06-08-2002
		CN 1369544 A	18-09-2002
		JP 2002275491 A	25-09-2002
		SG 105535 A1	27-08-2004
		US 2002155958 A1	24-10-2002

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- EP 1728849 A [0012] [0012] [0012]
- US 4943672 A [0023]
- EP 0668342 A [0023]
- EP 0776959 A [0023]

Non-patent literature cited in the description

- ENGINE OIL LICENSING AND CERTIFICATION SYSTEM. November 2004 [0021]