



(11) **EP 1 990 353 A8**

(12) **CORRECTED EUROPEAN PATENT APPLICATION**

(15) Correction information:
Corrected version no 1 (W1 A1)
Bibliography INID code(s) 72

(51) Int Cl.:
C08F 10/06 *(2006.01)* **H01B 3/44** *(2006.01)*

(48) Corrigendum issued on:
25.02.2009 Bulletin 2009/09

(43) Date of publication:
12.11.2008 Bulletin 2008/46

(21) Application number: **07009238.2**

(22) Date of filing: **08.05.2007**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR
Designated Extension States:
AL BA HR MK RS

(71) Applicant: **Borealis Technology Oy**
06101 Porvoo (FI)

(72) Inventors:
• **Stadlbauer, Manfred**
4040 Linz (AT)

- **Ernst, Eberhard**
4210 Unterweikersdorf (AT)
- **Huhtanen, Lauri**
07940 Loviisa (FI)
- **Daniels, Yvo**
3520 Zonhoven (BE)
- **Jacobs, Franck**
9940 Evergem (BE)

(74) Representative: **Lux, Berthold**
Maiwald Patentanwalts GmbH
Elisenhof
Elisenstraße 3
D-80335 München (DE)

(54) **Electrical insulation film**

(57) The present invention relates to a capacitor film comprising a biaxially oriented polypropylene wherein
a) said polypropylene has a draw ratio in machine direction of at least 4.0 and a draw ratio in transverse direction of at least 4.0, and

b) said polypropylene has an electrical breakdown strength EB63% according to IEC 60243-part 1 (1988) of at least 300 kV/mm at a draw ratio in machine direction and in transverse direction of 4.0.

EP 1 990 353 A8