



(11) **EP 2 077 181 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Claims EN 11

(51) Int Cl.:
B29C 45/16 (2006.01) B29C 45/14 (2006.01)

(48) Corrigendum issued on:
05.10.2011 Bulletin 2011/40

(45) Date of publication and mention
of the grant of the patent:
29.12.2010 Bulletin 2010/52

(21) Application number: **09150140.3**

(22) Date of filing: **07.01.2009**

(54) **Method for manufacturing a toothbrush, toothbrush obtained with said method and mould for such method**

Verfahren zur Herstellung einer Zahnbürste, mit besagtem Verfahren hergestellte Zahnbürste und Form für solch ein Verfahren

Procédé de fabrication d'une brosse à dents, brosse à dents obtenue avec ce procédé et moule pour un tel procédé

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL
PT RO SE SI SK TR**

(30) Priority: **07.01.2008 IT MI20080014**
17.03.2008 IT MI20080447

(43) Date of publication of application:
08.07.2009 Bulletin 2009/28

(60) Divisional application:
10190377.1 / 2 295 220

(73) Proprietor: **PONZINI S.p.A.**
20020 Lazzate (MB) (IT)

(72) Inventor: **Ponzini, Eligio**
20123 Milano (IT)

(74) Representative: **Faggioni, Carlo Maria et al**
Fumero
Studio Consulenza Brevetti Snc
Pettenkoferstrasse 20-22
80336 Munich (DE)

(56) References cited:
EP-A- 0 712 709 WO-A-01/96088
DE-A1- 10 303 548 FR-A- 2 079 455
GB-A- 2 050 156 JP-A- 11 254 475
JP-A- 2003 025 376 JP-A- 2003 135 147

EP 2 077 181 B9

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Field of the Invention

[0001] The present invention refers to a process for manufacturing a toothbrush and a bristle head thereof, as well as to the mould for such method.

Background art

[0002] It is known that toothbrushes of the most varied shapes and constructions are common on the market. Toothbrushes displaying a metal portion within the handle have also been on offer, especially in the past. An example is disclosed in GB 2050156.

[0003] The need has recently arisen to manufacture a toothbrush consisting mainly of plastic material (essentially polypropylene and elastomere), for it to appeal in terms of handling and to be resistant to external agents (water, toothpaste, and so on), but also being provided with a particularly sturdy inner core, such as a metal core.

[0004] A metal-core toothbrush has some significant advantages over conventional, full-plastic toothbrushes. Firstly, the metal material (or equivalent), having a much larger elastic modulus than plastic materials, allows to achieve greater strength, longer duration and innovative elastic properties. Moreover, due to the increased strength of the material, it is possible to largely reduce the dimensions - in particular the resistant section - of the structural part of the toothbrush, for example of the neck portion between the handle and the bristle head. That makes the toothbrush ergonomically more advantageous, because it stands apart for its slimness precisely in the portion which interferes with the user's mouth and where it is hence most appreciated when the bulk is minimal. Increased ergonomics also translate into better manoeuvrability and, in the last analysis, in increased cleaning effectiveness.

[0005] The plastic component, in addition to pleasant tactile sensations, ensures good protection of the metal component from any oxidation or contact with the mouth lining (which contact might underlie allergic reactions).

[0006] Furthermore, the combination of the metal component with the plastic component, provided the latter is sufficiently clear, allows to obtain innovative and valuable aesthetic effects.

[0007] Finally, the presence of a core of a material with a high specific weight allows to achieve innovative results in terms of the weight and balancing of the toothbrush.

[0008] Beyond these immediately understandable aspects, the known art does not offer yet an effective process to be able to assemble a plastic toothbrush with a metal core. As a matter of fact, technological difficulties exist in combining these two so incompatible materials, both in terms of their nature, and in terms of processing.

[0009] In particular, it is necessary to identify a configuration and a process suitable for maintaining the inner core securely fastened in the mould and suitably exposed

to be able to embed it and join it correctly to the plastic material injected into the mould.

[0010] Moreover, it would also be desirable to be able to have a process available which allows to introduce the use of a core into a toothbrush moulding method which, by becoming consolidated, has already allowed to achieve excellent results in terms of quality, economy and yield.

[0011] Moreover, in the toothbrush moulding process, the need arises to tuft the head portion by resorting to in-moulding or anchor-less processes, for the entire manufacturing process to remain effective and for it to be able to exploit uniform equipment.

[0012] However, it has been detected that these techniques still have drawbacks ensuing from the moulding of plastic material in the proximity of an enlarged portion of tuft root.

[0013] As a matter of fact, once the tufts have been processed to obtain an enlarged end or head, there are essentially two ways to anchor them to the remaining toothbrush portion. A first way provides to introduce the tufts into a suitable mould mask and hence to inject the remaining toothbrush head portion, wherein the enlarged ends remain embedded and joined together. In this case it is possible to suitably configure the mould and the mask to reduce to a minimum the problems during plastic injection.

[0014] A second way provides to introduce and fasten the tufts on a plate intended to then be fastened to the remaining toothbrush portion, which it will permanently form a part of.

[0015] In this last case, evidently, the plate is a toothbrush component which hence, both in terms of material and of the configuration, cannot be best adapted based solely on moulding requirements. It may therefore happen that, should it be required to inject molten plastic under pressure in the proximity of such component, leaks of material occur between the individual tufts and the respective housing holes.

[0016] This happens because the individual tufts are inserted in the holes and, despite being molten at their ends to form enlarged ends, they maintain a certain axial sliding play. The plastic material injected in the proximity of the enlarged end hence tends to seep in between such head and the plate, and then to leak out in the gap G (see fig. 6A) between filaments F and the perimeter H of the holes, which is certainly not sealed due to the very structure of the tufts.

[0017] The seepage of plastic material, as may be guessed, causes unpleasant burrs and the possible disassembly of the topography of the tufts on the toothbrush.

[0018] Examples of injection techniques are disclosed in EP 567 672, which, however, remain not fully satisfactory. A further moulding method is disclosed in JP-A-11 254 475.

[0019] The object of the present invention is hence that of providing an innovative manufacturing process of a toothbrush as described above, which allows to combine

the advantages of the consolidated moulding processes of plastic toothbrushes with the advantageous introduction of a core, in particular a metal core.

Summary of the Invention

[0020] This object is achieved through the method described in short in the accompanying claims.

[0021] In particular, according to the invention, a manufacturing process of a toothbrush of plastic material having an inner core is provided, of the type wherein the following steps are provided

- manufacturing a resistant core, in particular a metal core,
- introducing said resistant core into a mould cavity formed by opposite footprints belonging to a lower half-mould and to an upper half-mould and, subsequently,
- injecting molten plastic material into said mould cavity for the manufacture of at least part of the toothbrush handle, and wherein

said resistant core is arranged in a respective footprint of a lower half-mould in contact with at least two support platforms, apt to support said core in the proximity of a central line of the mould cavity, and in that before the injection of structural plastic material, said lower half-mould is coupled with an upper half-mould provided with at least one ribbing apt to come in contact with said metal core at least in a position between said support platforms and opposite thereto with respect to the core.

[0022] According to a further main aspect of the invention, a mould for a manufacturing process of a plastic toothbrush embedding a resistant core is provided, consisting of at least one footprint in a lower half-mould and one footprint in an upper half-mould, between which a mould cavity for the moulding of at least one first plastic component of a toothbrush is defined, the footprint of the lower half-mould providing at least two support platforms, apt to support a metal core of the toothbrush in the proximity of a central line of the mould cavity, and the footprint of said upper half-mould having a ribbing apt to come in contact with the resistant core at least in a position between said support platforms and in an opposite position thereto with respect to the core.

Brief Description of the Drawings

[0023] Further features and advantages of the method, of the mould and of the toothbrush according to the invention will be in any case more evident from the following detailed description of some preferred embodiments, given by way of example, and illustrated in the attached drawings, wherein:

figs. 1A-1D are top plan, side elevation, bottom per-

spective and top perspective views, respectively, of an exemplary metal core joined together with a bristle head;

fig. 2 is a perspective view of the semi-finished product of fig. 1A joined together to an assembly mask; fig. 3 is a perspective view of a lower half-mould whereto the mask of fig. 2 is applied;

fig. 4 is a longitudinal-section view taken along the symmetry axis of a full mould according to the invention;

figs. 5A-5C are bottom plan, elevation side and top plan views, respectively, of the semi-finished product of fig. 1 whereto a first component of plastic material has been added;

figs. 5D-5E are perspective views of the semi-finished product of figs. 5A-5C;

fig. 6, as mentioned, is a top plan view of a bristle head, whereof

fig. 6A shows a partial enlargement of some filaments introduced in a respective hole;

fig. 7 is an elevation side view of an exemplary full toothbrush;

fig. 8 is an elevation side view of a toothbrush component provided with holes to be tufted;

fig. 9 is an elevation side view of a group of tufts arranged according to the configuration with which they are to be tufted;

fig. 10 is a plan view of the back side of the component of fig. 8 provided with the molten tufts and with a membrane according to the invention; and

figs. 11A and 11B are elevation side and perspective views, respectively, of a full head manufactured according to the method of the invention.

Detailed Description of Some Preferred Embodiments

[0024] In the following, reference will be made, in an exemplary way, to a toothbrush comprising a metal core, but it is understood that the core might also be made of other materials having individual features with respect to the remaining portion of injectable plastic body.

The Metal Core

[0025] In order to manufacture a metal-core toothbrush, a core 1 of metal material is first manufactured, for example such as the one clearly shown in fig. 1A-1D. The metal core 1 has an elongated, slim profile - especially in the neck portion C, i.e. between the area G of engagement with the head and the handle area I - which is rather thin.

[0026] In the embodiment shown in the attached drawings, metal core 1 has an open-V, transversal profile, at least on the entire handle portion and on part of neck C. This profile allows to obtain a good inertia modulus which makes the entire core more rigid to bending, despite reduced material thickness.

[0027] The thickness preferably lies in the range 0.2

mm to 3 mm, preferably below 1.5 mm and even more preferably below 1 mm. As a matter of fact, it has been detected that a larger thickness would cause excessive thermal inertia which, depending on the material, would end up making the cooling times and the shrinkage ratios incompatible with those of the plastic material in which the core is intended to be embedded.

[0028] A preferred metal material for core 1 is a zinc-and-aluminium based alloy (zama), but it is not ruled out that also other metals may be equally suitable, such as aluminium, stainless steel, copper alloys and so on. An injectable metal alloy, such as a zama alloy, is preferable, which allows to obtain a core having a shape best suited to follow the profile of a toothbrush.

[0029] The metal core may be obtained in any case both by microfusion, and by shearing and bending, by MIM techniques, or other.

[0030] In the embodiment shown in the drawings, the head portion G of core 1, intended for the coupling with a bristle head, is "racket-shaped". In particular, the head portion G widens transversally with respect to the neck portion C and forks out into three prongs G_1 , G_2 e G_3 which join again at the vertex, between which apertures A_1 and A_2 are defined. This configuration makes the subsequent coupling with a bristle head particularly effective, as will be set forth in the following.

[0031] However, the provision of a different coupling element G at the head end of the metal core does not depart from the teachings of the present invention. For example, engaging means (not shown) may simply be provided, intended to remain uncovered at the end of the manufacturing process to then be joined, also by the user himself, to an interchangeable head having a matching shape.

The Bristle Head

[0032] Should the bristle head be fixedly joined to the toothbrush, at this point the process according to the invention provides to manufacture a bristle head separately. A head may be manufactured by the most preferred technology for the specific tuft topography which it is intended to offer.

[0033] The head consists, in a manner known per se, of a support component 20 provided with a plurality of through-holes 21 wherein bristle tufts 23 are provided to be inserted.

[0034] Component 20, being part of the toothbrush itself, is preferably made of a material consistent with that of the toothbrush, for example plastic material such as polypropylene.

[0035] Bristle tufts 23 are anchored to support component 20 by the anchor-free technology. The individual tufts 23 are hence inserted into holes 21 by means of suitable tufting equipment (not shown) and then molten at one base end 23a adjacent to the back side 20a (the lower one in fig. 8) of support component 20. The localised melting of ends 23a, obtained by heat supply or by

ultrasounds, causes a joining of the filaments with one another and creates an enlarged head which prevents the withdrawal of the tufts from holes 21 towards the outer side (the top one in fig. 8) of component 20.

[0036] Since the melting of ends 23a occurs when the tufts are already inserted in the component or support plate 20, a small adhesion may result between molten heads 23a and the inner side 20a of plate 20, which adhesion, however, cannot be very effective due to the different nature of the two materials. As a matter of fact, the filaments of tufts 23 are typically made of nylon, which melts at a different temperature from that of plate 20.

[0037] Moreover, since during the localised tuft melting a partial squashing of tuft heads 23a is caused, a mutual joining between the various heads may also occur, which further eases the, anchoring of the tufts on support 20.

[0038] However, if tufted plate 20 was thereby introduced in the mould, to inject a back portion finally covering the heads of tufts 23 and provides the completion of the head, the undesired seeping mentioned above would occur.

[0039] Therefore, according to the invention, after having assembled the tufts with support 20, it is provided to define/apply a thin protection membrane or film 30 adhering to heads 23a of the tufts, as shown in fig. 10.

[0040] Film 30 has such an extension area as to substantially cover all molten heads 23a of tufts 23 or, at least, those in the proximity of the injection point(s) into the mould intended to produce the back portion of the head.

[0041] In fig. 10, the film has a profile equivalent to that of support 20, but slightly smaller, so as to cover all the heads 23a of the tufts, except part of the peripheral ones.

[0042] This configuration is particularly advantageous because it allows to substantially cover all the tuft heads, but leaves a free peripheral rim which ensures an effective bonding of the subsequent injected material to the peripheral portion of support 20.

[0043] Film 30 must be of a material which does not melt immediately upon contact with the molten plastic material which is subsequently injected to complete the back portion of the head. This allows to preserve its shielding effectiveness - according to what is set forth below - at least for the entire initial step of the injection, during which the injection pressure is higher.

[0044] The Applicant could ascertain that also a paper-based material performs this task very well, since it is inexpensive and easily available and does not burn in the injection step since it is not in contact with oxygen.

[0045] According to a more preferred embodiment, protection film 30 has an adhesive side, for example it is an adhesive paper label. As a matter of fact, the adhesive side of the film is placed in contact with tuft heads 23a and allows to apply and keep easily in position the protection film or membrane 30 during the industrial process for the handling and moulding of the toothbrush.

[0046] The protection film can also be made of other materials, such as also metal alloys (for example alumin-

ium) or the very material of which the subsequently injected toothbrush head portion is made. For example, it is possible to obtain such shielding film directly in the toothbrush mould, performing a first low-pressure injection in the proximity of the head, so as to define a first shielding film 30 adjacent to the tufts.

[0047] In this last case, membrane or film 30 will melt together with the material supplied during the second high-pressure injection of plastic material (the one used to obtain the remaining toothbrush portion), but with a sufficient delay to perform in any case its protective function.

[0048] The thickness of membrane 30 depends on the material it is made of, it being proportionally larger in the case of a membrane of a plastic material partly melting at the injection temperatures/pressures. For example, it has been detected that an adhesive paper label can perform its task very well with a thickness of 50-400 μm .

[0049] The thickness is in any case preferably such that membrane 30 maintains a certain flexibility, so as to better adapt to the irregular surface 20a of support 20, scattered with the flattened heads 23a of the tufts.

[0050] In substance, after having applied protective film/membrane 30, support 20 complete with tufts 23 and with film 30 is ready to be inserted in the toothbrush mould.

[0051] In figs. 11A and 11B a head insert T according to a preferred embodiment is shown, once the moulding and hardening (cooling) step of the back portion and the corresponding ejection from the mould has been completed.

[0052] As can be seen clearly, in case the head must be coupled with a metal core as shown in the drawings, i.e. with "racket-shaped" head ends, the bristle head displays a back surface provided with a matching footprint. That is, the back of the head has recesses and reliefs in correspondence of prongs G_1 - G_3 and apertures A_1 - A_3 , respectively, of the head portion of core 1. This makes the coupling between the core and the head on the adhesion plane thereof potentially stable, so as to prevent undesired relative movements during the moulding step.

Moulding of the First Component.

[0053] A series of bristle heads T are formed and completed on a metal mask M, by means of which the heads can be handled and transferred along the production line.

[0054] Each mask M may comprise, as shown in the drawings, four footprints for an equal number of heads (fig. 2).

[0055] The bristle masks then arrive at an assembling/moulding station in correspondence of which they are housed - for example after having been methodically taken from a storage by a gripping hand with vacuum suction - and locked in a corresponding seat of a lower half-mould S_1 of the mould, wherein an equal number of footprints P_1 - P_4 is obtained, which define a part of the mould cavity for a semi-finished toothbrush.

[0056] Lower half-mould S_1 preferably comprises a footprint number multiple of the number of footprints existing on masks M and is hence arranged for housing a certain number of masks, for example four aligned masks next to one another.

[0057] On a rotary turntable (not shown) there are preferably mounted two half-moulds S_1 , in opposition one to the other, which can thereby be alternatively brought below a moulding head, where a coupling occurs with an upper half-mould S_2 and the injection of plastic material of a first component. Moulding turntable systems, of the prior art, are described for example in EP 893 225 and EP 836 923 in the name of G.B. Boucherie NV.

[0058] According to the invention, each of footprints P_1 - P_4 intended to house a metal core 1, as clearly visible in fig. 3, is provided with two support platforms Q_1 - Q_4 and R_1 - R_4 apt to support and retain core 1 in a central position with respect to the toothbrush body.

[0059] In substance, the two support platforms Q and R rise from the bottom of footprint P and define a support or contact surface which lies in the proximity of a central line of the mould cavity, i.e. of the toothbrush.

[0060] Preferably, the two platforms are arranged one (R) in the proximity of the handle end of the toothbrush, while the other one (Q) is in the proximity of the CG area of core 1, i.e. in the proximity of the connection between handle portion I and neck portion C.

[0061] For correct core retaining in the mould, the surfaces of the two platforms Q and R intended to come in contact with core 1 are preferably shaped so as to match the possibly-curved, corresponding surface conformation of core 1.

[0062] Since the two platforms R and Q are intended to occupy part of footprint P, depending on their location, their sizing and shape takes into account the fluidodynamic requirements of the plastic material which must be injected into the mould. In the embodiment shown, CG platform Q displays a minimal length and is rather elongated in the longitudinal direction of the footprint. The upstream edge Q' (leading edge), with respect to the injection point of the plastic material (Z_1), has a rising front with a rounded profile; conversely, the downstream edge Q'' (trailing edge) displays a tilted front and, possibly, with a more tapered profile.

[0063] Moreover, CG support platform Q preferably has a pin N intended to engage with a corresponding hole 1a of metal core 1. The pin projects from the respective platform according to a direction favourable to the introduction of hole 1a during the movement of deposition of core 1 into footprint P.

[0064] This pin N has the twofold task of longitudinally centring core 1 in its moulding footprint P, as well as of providing a valid constraint of the same core, which prevents undesired transversal displacements, especially during the pressure injection of the plastic material into the mould.

[0065] As a matter of fact, it must be considered that the secure fastening of the core to the inside of the mould

cavity is one of the critical points for the success of the finished product. The plastic material is normally injected at a high pressure (even up to the order of 700-800 bar) and hence the push imparted to the inner core would risk shifting it from its position established by the design.

[0066] Moreover, hole 1a maintains an advantageous usefulness also during the subsequent step of moulding the plastic material, as will be highlighted further on.

[0067] An upper half-mould S_2 is furthermore provided to cooperate with lower half-mould S_1 , so as to define a footprint P' which defines, together with lower footprint P , the moulding cavity of the first component.

[0068] According to the invention, upper half-mould S_2 also has a support for retaining metal core 1. In particular, the upper half-mould has an elongated ribbing L (the half-mould portion resting on core 1 visible in the section of fig. 4), intended to come in contact in the cavity of core 1 (i.e. above in the drawing of fig. 4) in an area lying between the two lower support platforms Q and R and opposite thereto with respect to the core.

[0069] Thereby, enclosing metal core 1 between three contact areas (two arranged on one side and one arranged on the opposite side, lying between the first two ones), an effective locking system for core 1 is configured. This locking system avoids any undesired movement of metal core 1 in the mould, especially during the injection of the first plastic component, but at the same time it is very little invasive and hence does not negatively affect the solidity of the moulded plastic material nor its final aesthetic result.

[0070] Finally, it is preferable for the two half-moulds S_1 and S_2 to be shaped so that footprints P and P' house the metal core entirely. In other words, metal core 1 is preferably suited to be fully covered by the plastic material of the first component, except for the areas resting on platforms Q and R and ribbing L .

[0071] In particular, it is deemed advantageous for at least the entire peripheral edge of the metal core to be covered with the first structural plastic component, for example polypropylene. This ensures good grafting of the plastic material to the metal core, as well as good bonding of the second (typically elastomeric) component and avoids undesired seepage of the second component between the metal core and the first component.

[0072] For such purpose, the support areas (which can be better defined as areas of contact with the metal core) of platforms Q and R and of ribbing L must be sufficiently narrow so as not to affect the peripheral edge area of the core.

[0073] Operatively, once metal core 1 has been placed into the lower half-mould (fig. 3) - well-centred and retained by the insertion of pin N into hole 1a- the turntable in the moulding station is caused to rotate and carries half-mould S_1 below the injection head, where it is closed with upper half-mould S_2 . and the injection of the first plastic structural component, typically made of polypropylene, begins.

[0074] The point of injection of the first component pref-

erably lies in the proximity of the rear end of the handle (Z_1 end of channel Z in fig. 4). The injection, since it occurs at the end of the mould cavity, is preferably pressure-controlled, in order to suitably adjust the pressure in the mould and the progress of the injection front. Injection may occur, for example, over 2-3 seconds with three-four different subsequent pressure events.

[0075] The fact that core 1 is well-centred along a central line within the mould cavity causes also the cavity volumes on both sides of the core to be substantially balanced: this avoids pressure peaks on either side of core 1, which might otherwise bend the core during injection and move it into an undesired position.

[0076] Another point of preventive low-pressure injection may be provided in the proximity of the head, should membrane 30 be provided directly in the mould.

[0077] In any case, the plastic material injected at high pressure closes and completes the back of the head.

[0078] The plastic material supplied during injection ends up bonding with at least part of the inner side 20a of support 20, in particular along the periphery thereof, being made of identical or substantially compatible and related material.

[0079] Due to the presence of membrane 30, found at least in correspondence of the points of injection high-pressure, the injected material is unable to seep below tuft heads 23a - otherwise leaking through the gaps provided with holes 21.

[0080] Moreover, the inclusion of membrane 30 comprises no contraindication. On the contrary, through a suitable choice of the materials - for example a clear plastic material (at least once cooled in the condition of use) for the toothbrush head and a variously coloured or patterned support for film 30 - it is possible to obtain appealing colour and aesthetic effects.

[0081] At the end of moulding, the rotation of the turntable brings the lower half-mould in the initial position, wherefrom the semi-finished products are taken, so as to free half-mould S_1 which is ready again for a subsequent loading cycle. In this step, the semi-finished products are as illustrated in figs. 5A-5E. In such respect, please notice the recesses left in first component 2 by support platforms Q and R (recesses 2a and 2c, respectively) and by ribbing L (recess 2b).

Moulding of the second Component

[0082] The semi-finished products are then sent to a second mould (possibly arranged on the same turntable or in a second moulding station) where a second finishing plastic component is applied, for example an elastomeric material.

[0083] The semi-finished product is therefore introduced, in a manner known per se, into a new mould into which the second component is injected which, in addition to aesthetically finishing the toothbrush, fills the recesses 2a-2c left by the support and locking system of metal core 1.

[0084] In this step, advantageously, the finishing and filling plastic material, injected by one of the two parts of hole 1a, for example into the recess 2b left by ribbing L, can overflow also onto the other side. The provision of hole 1a - in addition to the retaining function set forth above - hence allows both to inject plastic material on one side only of the two parts, and to obtain a resistant anchoring of the two opposite masses of elastomeric material to the toothbrush body, because they join through the hole.

[0085] Once this step too has ended, the toothbrush is complete (fig. 7) and may be sent to a quality assurance line and then for packaging.

[0086] As can be evinced from the above-reported description, the teachings according to the invention allow to define a moulding process and the corresponding mould, particularly suited for obtaining a toothbrush with a slim metal core.

[0087] The process, in particular, allows to perfectly embed the metal core into the plastic body of the toothbrush (so as not to leave it exposed to external agents), securely fastening also the bristle head component. The perfect retaining of the core in the mould, despite its slowness, further allows to obtain a product of excellent quality and finishing.

[0088] It is nevertheless understood that the invention is not limited to the particular embodiments illustrated above, which are only non-limiting examples of the scope of the invention, but that a number of variants are possible, all within the reach of a person skilled in the field, without departing from the scope of the invention.

[0089] For example, instead of providing a single pin N on CG support platform Q, a different coupling element may be provided which holds the metal core at least in its transversal direction inside its footprint P in mould 1.

[0090] Also, despite reference always having been made to bristle heads obtained separately and then applied to the remaining handle portion, the method of the invention is well-suited also to manufacture an entire toothbrush, wherein the head portion is integral with the handle and is subsequently bristled with a conventional anchor technique.

[0091] Finally, it is not ruled out for the resistant inner core to be made of non-metal materials, possibly having a high elastic modulus, obtaining a product with equivalent features.

Claims

1. Method for manufacturing a toothbrush of plastic material with resistant inner core, in particular a metal one, of the type wherein the following steps are provided

- manufacturing a resistant inner core,
- introducing said resistant inner core into a mould cavity defined by opposite footprints be-

longing to a lower half-mould (S_1) and to an upper half-mould (S_2) and, subsequently,
- injecting molten plastic material into said mould cavity to manufacture at least part of the toothbrush handle, wherein

said resistant inner core (1) is arranged in a respective footprint (P) of a lower half-mould (S_1) in contact with at least two support platforms (Q, R), apt to support said core (1) in the proximity of a central line of the mould cavity, **characterised in that**, before the injection of structural plastic material, said lower half-mould (S_1) is coupled with an upper half-mould (S_2) provided with at least one ribbing (L) apt to come in contact with said metal core at least in a position between said support platforms (Q, R) and in an opposite position thereto.

2. Method as claimed in claim 1), wherein, before the placing of said resistant core (1), a transport mask (M), into which a plurality of bristle heads has been introduced, is coupled with said lower half-mould (S_1) so that said heads lie in correspondence of respective toothbrush footprints (P_1 - P_4).
3. Method as claimed in claim 1) or 2), wherein it is provided for at least one of said support platforms (Q) to have transversal retaining means (N) for said metal core (1).
4. Method as claimed in claim 3), wherein said retaining means are in the shape of a pin (N) apt to couple with a corresponding through-hole (1a) obtained in said metal core.
5. Method as claimed in any one of the preceding claims, wherein at least one of said support platforms (Q) is arranged in the area of the centre of gravity of said core (1).
6. Method as claimed in any one of the preceding claims, wherein at least one of said platforms (Q) rises from the bottom of the footprint (P) of the lower half-mould (S_1) and has a lateral shape with a fluidodynamic profile with respect to the flow of molten material injected into said footprint.
7. Method as claimed in any one of the preceding claims, wherein following the injection of said structural plastic material, the thus-obtained semi-finished product is removed from the mould and introduced into a further mould into which at least a second finishing plastic component is injected, apt to fill any recesses (2a-2c) left by said support platforms (Q, R) and ribbing (L).
8. Method as claimed in claim 7), wherein at least one between said structural plastic material or finishing

plastic material is injected so that it goes through a through-hole (1a) of said metal core.

9. Method as claimed in any one of the preceding claims, wherein said core (1) is made of metal. 5
10. Method as claimed in any one of the preceding claims, further comprising the steps of
 - arranging at least one head component provided with through-holes and tufted with tufts of synthetic single-yarns, and of melting the bottom ends of said tufts in shape of heads (23a) larger than the corresponding holes (21), and wherein the back side (20a) of said head component is further completed by the injection of a completion molten material which is later caused to harden, 10
 - before said injection of molten material, applying a protection membrane (30) onto said back side (20a), the membrane having such an extension as to cover said tuft heads (23a) at least in areas in the proximity of high-pressure points of said molten material. 15
11. Mould for a manufacturing process as claimed in any one of the preceding claims, consisting of at least one footprint in a lower half-mould (S_1) and of a footprint in an upper half-mould (S_2) between which a mould cavity is defined for the moulding of at least one first plastic component of a toothbrush, **characterised in that** in the footprint (P_1 - P_4) of said lower half-mould (S_1) at least two support platforms (Q, R) are provided, apt to support a resistant toothbrush core (1) in the proximity of a central line of the mould cavity, and **in that** the footprint of said upper half-mould (S_2) has a ribbing (L) apt to come in contact with said resistant core (1) at least in a position between said support platforms (Q, R). 20
12. Toothbrush **characterised in that** it is obtained by a method according to any one of the preceding claims. 25

Patentansprüche

1. Verfahren zum Herstellen einer Zahnbürste aus Kunststoffmaterial mit resistantem inneren Kern, insbesondere einem metallischen, des Typs, bei dem die folgenden Schritte bereitgestellt werden:
 - Herstellen eines resistanten inneren Kerns,
 - Einführen des resistanten inneren Kerns in eine Formaushöhlung, die definiert ist durch sich gegenüberliegende Grundflächen gehörend zu einer unteren Halbform (S_1) und einer oberen Halbform (S_2), und, anschließend, 50

- Injizieren von geschmolzenem Kunststoffmaterial in die Formaushöhlung, um wenigstens einen Teil des Zahnbürstengriffs herzustellen, wobei

der resistente innere Kern (1) in einer entsprechenden Grundfläche (P) einer unteren Halbform (S_1) in Kontakt mit wenigstens zwei Stützplattformen (Q, R) angeordnet ist, die geeignet sind, um den Kern (1) in der Nähe einer zentralen Linie der Formaushöhlung zu stützen,

dadurch gekennzeichnet, dass vor dem Injizieren von strukturellem Kunststoffmaterial die untere Halbform (S_1) mit einer oberen Halbform (S_2) gekoppelt wird, die mit wenigstens einer Rifflung (L) bereitgestellt ist, die passend ist, um in Kontakt zu kommen mit dem Metallkern wenigstens in einer Position zwischen den Stützplattformen (Q, R) und in einer gegenüberliegenden Position dazu.

2. Verfahren nach Anspruch 1, wobei vor dem Anordnen des resistanten Kerns (1) eine Transportmaske (M), in die eine Vielzahl von Bürstenköpfen eingeführt worden ist, mit der unteren Halbform (S_1) so gekoppelt wird, dass die Köpfe in Korrespondenz der entsprechenden Zahnbürstengrundflächen (P_1 - P_4) liegen. 25
3. Verfahren nach Anspruch 1 oder 2, wobei für wenigstens eine der Stützplattformen (Q) es vorgesehen ist, transversale Haltemittel (N) für den Metallkern (1) aufzuweisen. 30
4. Verfahren nach Anspruch 3, wobei das Haltemittel in der Form eines Stifts (N) ist, der passend ist, um mit einem korrespondierenden Durchgangsloch (1a), das in dem Metallkern vorliegt, zu koppeln. 35
5. Verfahren nach einem der vorangehenden Ansprüche, wobei wenigstens eine der Stützplattformen (Q) angeordnet ist in der Fläche des Gewichtsschwerpunkts des Kerns (1). 40
6. Verfahren nach einem der vorangehenden Ansprüche, wobei wenigstens eine der Plattformen (Q) von dem Boden der Grundfläche (P) der unteren Halbform (S_1) aufsteigt und eine seitliche Form mit einem fluiddynamischen Profil in Bezug auf den Fluss des in die Grundfläche injizierten geschmolzenen Materials aufweist. 45
7. Verfahren nach einem der vorangehenden Ansprüche, wobei folgend der Injektion des strukturellen Kunststoffmaterials das so erhaltene halbfertige Produkt aus der Form entfernt wird und in eine weitere Form eingeführt wird, in die wenigstens eine zweite Endbearbeitungskunststoffkomponente injiziert wird, die passend ist, um jegliche Ausnehmungen 50

gen (2a-2c) zu befüllen, die durch die Stützplattformen (Q, R) und die Riffelung (L) belassen wurden.

8. Verfahren nach Anspruch 7, wobei wenigstens eines des strukturellen Kunststoffmaterials oder des Endbearbeitungskunststoffmaterials so injiziert wird, dass es durch ein Durchgangsloch (1a) des Metallkerns hindurch geht. 5
9. Verfahren nach einem der vorangehenden Ansprüche, wobei der Kern (1) aus Metall ist. 10
10. Verfahren nach einem der vorangehenden Ansprüche, weiter umfassend die Schritte: 15
 - Anordnen wenigstens einer Kopfkomponte, die mit Durchgangslöchern versehen ist und mit Büscheln aus synthetischem Einzelgarn bebüschelt ist, und Schmelzen der Bodenenden der Büschel in Form von Köpfen (23a), die größer sind als die korrespondierenden Löcher (21), und wobei die Rückseite (20a) der Kopfkomponte weiter vervollständigt wird durch die Injektion eines geschmolzenen Vervollständigungsmaterials, welches später veranlasst wird zu härten, 20
 - vor dem Injizieren des geschmolzenen Materials Auftragen einer Schutzmembran (30) auf die Rückseite (20a), wobei die Membran eine solche Abmessung aufweist, um die Büschelköpfe (23a) wenigstens in Flächen in der Nähe der Hochdruckpunkte des geschmolzenen Materials abzudecken. 25
11. Form für ein Herstellungsverfahren nach einem der vorangehenden Ansprüche, bestehend aus wenigstens einer Grundfläche in einer unteren Halbform (S₁) und einer Grundfläche in einer oberen Halbform (S₂), zwischen denen eine Formaushöhlung für das Formen wenigstens einer ersten Kunststoffkomponente einer Zahnbürste definiert ist, **dadurch gekennzeichnet, dass** in der Grundfläche (P₁-P₄) der unteren Halbform (S₁) wenigstens zwei Stützplattformen (Q, R) bereitgestellt sind, die passend sind, um einen resistenten Zahnbürstenkern (1) in der Nähe einer zentralen Linie der Formaushöhlung zu stützen, und dass die Grundfläche der oberen Halbform (S₂) eine Riffelung (L) aufweist, die passend ist zum Inkontaktkommen mit dem resistenten Kern (1) wenigstens in einer Position zwischen den Stützplattformen (Q, R). 30 35 40 45 50
12. Zahnbürste, **dadurch gekennzeichnet, dass** sie erhalten wird durch ein Verfahren nach einem der vorangehenden Ansprüche. 55

Revendications

1. Procédé de fabrication d'une brosse à dents en matière plastique possédant un coeur interne résistant, en particulier un noyau de métal, du type dans lequel les étapes suivantes sont prévues :
 - fabrication d'un noyau interne résistant,
 - introduction dudit noyau interne résistant dans une cavité de moule définie par des empreintes opposées appartenant à une moitié de moule inférieure (S₁) et à une moitié de moule supérieure (S₂) et, ensuite,
 - injection de matière plastique fondue dans ladite cavité de moule pour fabriquer au moins partie du manche de la brosse à dents, où ledit noyau interne résistant (1) est agencé dans une empreinte (P) respective d'une moitié de moule inférieure (S₁) en contact avec au moins deux plateformes de support (Q, R), aptes à supporter ledit noyau (1) à proximité d'une ligne centrale de la cavité de moule, **caractérisé en ce que** avant l'injection de matière plastique structurale, ladite moitié de moule inférieure (S₁) est accouplée avec une moitié de moule supérieure (S₂) pourvue d'au moins un nervurage (L) apte à venir en contact avec ledit noyau de métal au moins dans une position entre lesdites plateformes de support (Q, R) et dans une position opposée.
2. Procédé selon la revendication 1, dans lequel, avant le placement dudit noyau résistant (1), un masque de transport (M), dans lequel a été introduite une pluralité de têtes de poils, est accouplé avec ladite moitié de moule inférieure (S₁) de manière que lesdites têtes se placent en correspondance d'empreintes de brosses à dents respectives (P₁-P₄).
3. Procédé selon la revendication 1 ou 2, dans lequel pour au moins l'une (Q) desdites plateformes de support sont prévus des moyens de retenue transversaux (N) pour ledit noyau de métal (1).
4. Procédé selon la revendication 3, dans lequel lesdits moyens de retenue ont la forme d'une tige (N) apte à s'accoupler avec un trou traversant correspondant (1a) obtenu dans ledit noyau de métal.
5. Procédé selon l'une quelconque des revendications précédentes, dans lequel au moins l'une (Q) desdites plateformes de support est agencée dans la région du centre de gravité dudit noyau (1).
6. Procédé selon l'une quelconque des revendications précédentes, dans lequel au moins l'une (Q) desdites plateformes s'élève depuis le fond de l'empreinte

(P) de la moitié de moule inférieure (S_1) et a une forme latérale ayant un profil fluidodynamique par rapport à l'écoulement de matière fondue injectée dans ladite empreinte.

7. Procédé selon l'une quelconque des revendications précédentes, dans lequel, postérieurement à l'injection de ladite matière plastique structurelle, le produit semi-fini ainsi obtenu est extrait du moule et introduit dans un autre moule dans lequel au moins un deuxième composant de plastique de finition est injecté, apte à remplir tout évidement (2a-2c) laissé par lesdites plateformes de support (Q, R) et ledit nervurage (L).

8. Procédé selon la revendication 7, dans lequel au moins ladite matière plastique structurelle ou ladite matière plastique de finition est injectée de manière à passer par un trou traversant (1a) dudit noyau de métal.

9. Procédé selon l'une quelconque des revendications précédentes, dans lequel ledit noyau (1) est fait de métal.



10. Procédé selon l'une quelconque des revendications précédentes, comprenant, en outre, les étapes de :


- agencement d'au moins une pièce tête pourvue de trous traversants et touffetée de touffes de fils simples synthétiques, et fusion des extrémités inférieures desdites touffes en forme de têtes (23a) plus grosses que les trous correspondants (21), et où la face arrière (20a) de ladite pièce tête est en outre terminée par l'injection d'une matière fondue de finition qui est ensuite amenée à durcir,
- avant ladite injection de matière fondue, application d'une membrane de protection (30) sur ladite face arrière (20a), la membrane ayant une extension de façon à recouvrir lesdites têtes de touffes (23a) au moins dans des régions à proximité de points de pression élevée de ladite matière fondue.

11. Moule pour procédé de fabrication selon l'une quelconque des revendications précédentes, consistant en au moins une empreinte dans une moitié de moule inférieure (S_1) et une empreinte dans une moitié de moule supérieure (S_2) entre lesquelles une cavité de moule est définie pour le moulage d'au moins une première pièce en plastique d'une brosse à dents, **caractérisé en ce que** dans l'empreinte (P_1 - P_4) de ladite moitié de moule inférieure (S_1) au moins deux plateformes de support (Q, R) sont prévues, aptes à supporter un noyau de brosse à dents résistant (1) à proximité d'une ligne centrale de la cavité de moule, et **en ce que** l'empreinte de ladite moitié de moule

supérieure (S_2) comporte un nervurage (L) apte à venir en contact avec ledit noyau résistant (1) au moins dans une position entre lesdites plateformes de support (Q, R).

12. Brosse à dents, **caractérisée en ce qu'elle** est obtenue par un procédé selon l'une quelconque des revendications précédentes.








Fig. 2





Fig. 3










Fig.10





Fig.6




Fig.6A








Fig. 7





REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- GB 2050156 A [0002]
- EP 567672 A [0018]
- JP 11254475 A [0018]
- EP 893225 A [0057]
- EP 836923 A [0057]