



(11) **EP 2 199 361 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Description Paragraph(s) 91

(51) Int Cl.:
C09K 11/06 ^(2006.01) **H05B 33/14** ^(2006.01)
H05B 33/22 ^(2006.01)

(48) Corrigendum issued on:
08.02.2012 Bulletin 2012/06

(45) Date of publication and mention
of the grant of the patent:
19.10.2011 Bulletin 2011/42

(21) Application number: **10159212.9**

(22) Date of filing: **03.07.2003**

(54) **Organic electroluminescent devices and organic luminescent medium**

Organische elektrolumineszente Vorrichtungen und organisches lichtemittierendes Medium

Appareil electroluminescent organique et milieu luminescent organique

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR

(30) Priority: **19.07.2002 JP 2002211308**

(43) Date of publication of application:
23.06.2010 Bulletin 2010/25

(60) Divisional application:
10197190.1 / 2 295 519

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
03738656.2 / 1 541 657

(73) Proprietor: **Idemitsu Kosan Co., Ltd.**
Chiyoda-ku
Tokyo 100-8321 (JP)

(72) Inventors:
• **Matsuura, Masahide**
Sodegaura-shi Chiba 299-0205 (JP)
• **Funahashi, Masakazu**
Sodegaura-shi Chiba 299-0205 (JP)
• **Fukuoka, Kenichi**
Sodegaura-shi Chiba 299-0205 (JP)
• **Hosokawa, Chishio**
Sodegaura-shi Chiba 0299-0205 (JP)

(74) Representative: **Gille Hrabal Struck Neidlein Prop**
Roos
Patentanwälte
Brucknerstrasse 20
40593 Düsseldorf (DE)

(56) References cited:
WO-A-02/052904 JP-A- 2002 198 183

EP 2 199 361 B9

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionTECHNICAL FIELD

5 **[0001]** The present invention relates to an organic electroluminescence ("electroluminescence" will be referred to as "EL", hereinafter) device and an organic light emitting medium, and more particularly, to an organic EL device which exhibits excellent purity of color, has excellent heat resistance and a long life and efficiently emits bluish to yellowish light and an organic light emitting medium which is advantageously used for the organic EL device.

10 BACKGROUND ART

[0002] An organic EL is a spontaneous light emitting device which utilizes the principle that a fluorescent substance emits light by energy of recombination of holes injected from an anode and electrons injected from a cathode when an electric field is applied.

15 **[0003]** Since an organic EL device of the laminate type driven under a low electric voltage was reported by C. W. Tang of Eastman Kodak Company (C. W. Tang and S. A. Vanslyke, Applied Physics Letters, Volume 51, Pages 913, 1987), many studies have been conducted on organic EL devices using organic materials as the constituting materials.

[0004] Tang et al used a laminate structure using tris(8-hydroxy-quinolinato)aluminum for the light emitting layer and a triphenyldiamine derivative for the hole transporting layer. Advantages of the laminate structure are that the efficiency of hole injection into the light emitting layer can be increased, that the efficiency of forming excited particles which are formed by blocking and recombining electrons injected from the cathode can be increased and that excited particles formed within the light emitting layer can be enclosed. As the structure of the organic EL device, a two-layered structure having a hole transporting (injecting) layer and an electron transporting and light emitting layer and a three-layered structure having a hole transporting (injecting) layer, a light emitting layer and an electron transporting (injecting) layer are well known. To increase the efficiency of recombination of injected holes and electrons in the devices of the laminate type, the structure of the device and the process for forming the device have been studied.

25 **[0005]** As the light emitting material, chelate complexes such as tris(8-quinolinato)aluminum, coumarine derivatives, tetraphenyl-butadiene derivatives, bisstyrylarylene derivatives and oxadiazole derivatives are known. It is reported that light in the visible region ranging from blue light to red light can be obtained by using these light emitting materials and development of a device exhibiting color images is expected (For example, Japanese Patent Application Laid-Open Nos. Heisei 8(1996)-239655, Heisei 7(1995)-138561 and Heisei 3(1991)-200289).

30 **[0006]** Devices using bisanthracene derivatives as the hole transporting material or the light emitting material are disclosed in the United States Patent No. 3008897 and Japanese Patent Application Laid-Open No. Heisei 8(1996)-12600. Although bisanthracene derivatives can be used as the material emitting blue light, the efficiency of light emission and the life are insufficient for practical applications. In Japanese Patent Application Laid-Open No. 2001-207167, a device using an aminoanthracene derivative as the material emitting green light is disclosed. However, the organic EL device using this material cannot be used for the practical applications since the device has poor heat resistance due to the low glass transition temperature of the material and light emission of a long life and a high efficiency cannot be obtained. Other organic devices of a long life and excellent properties are recently reported. However, the life and the properties are not always sufficient. Therefore, the development of an organic EL device exhibiting more excellent properties have been strongly desired.


DISCLOSURE OF THE INVENTION

45 **[0007]** Under the above circumstances, the present invention has an object of providing an organic EL device which exhibits a high purity of color, has excellent heat resistance and a long life and efficiently emits bluish to yellowish light and an organic light emitting medium which can be advantageously used for the organic EL device.

[0008] As the result of extensive studies by the present inventors to achieve the above object, it was found that, when an organic light emitting medium comprised a combination of a specific arylamine compound and at least one compound selected from specific anthracene derivatives, spirofluorene derivatives, compounds having condensed rings and metal complex compounds and an organic electroluminescence device had a layer of the medium disposed between a pair of electrodes, the organic EL device exhibited a high purity of color, had excellent heat resistance and a long life and efficiently emitted bluish to yellowish light. The present invention has been completed based on this knowledge.

55 **[0009]** The present invention provides an electroluminescence device comprising a pair of electrodes and a layer of an organic light emitting medium disposed between the pair of electrodes, wherein the layer of an organic light emitting medium comprises:

(A) an arylamine compound represented by the following general formula (V):




wherein

X^3 represents a substituted or unsubstituted residue of pyrene or chrysene; Ar^5 and Ar^6 each independently represent a substituted or unsubstituted monovalent aromatic group having 6 to 40 carbon atoms, and

p represents an integer of 1 to 4; and

(B) at least one compound selected from anthracene derivatives represented by the following general formula (II):



wherein

An represents a substituted or unsubstituted divalent anthracene residue;

A^3 and A^4 each independently represent a substituted or unsubstituted aryl group having 6 to 40 carbon atoms,

at least one of A^3 and A^4 represents a substituted or unsubstituted monovalent condensed aromatic ring group, or a substituted or unsubstituted aryl group having 10 or more carbon atoms,

and A^3 and A^4 may be the same or different.


[0010] The present invention provides an organic light emitting medium which comprises (A) at least one compound selected from substituted and unsubstituted arylamines having 10 to 100 carbon atoms represented by general formula (V) above and (B) at least one compound selected from anthracene derivatives represented by general formula (II) shown above.

THE MOST PREFERRED EMBODIMENT TO CARRY OUT THE INVENTION

[0011] The organic EL device of the present invention is a device having a structure comprising a pair of electrodes and a layer of an organic light emitting medium disposed between the pair of electrodes.

[0012] In the present invention, an organic light emitting medium comprising a combination of (A) at least one compound selected from substituted and unsubstituted arylamine compounds having 10 to 100 carbon atoms represented by the above formula (V) and (B) at least one compound selected from the anthracene derivatives represented by the above general formula (II), is used in the layer of an organic light emitting medium.

[0013] The arylamine compounds of component (A) are arylamine compounds represented by the following general formula (V):




wherein X^3 represents a substituted or unsubstituted pyrene or chrysene ring group, Ar^5 and Ar^6 each independently represent a substituted or unsubstituted monovalent aromatic group having 6 to 40 carbon atoms, and p represents an integer of 1 to 4.

[0014] Examples of the monovalent aromatic group having 6 to 40 carbon atoms which is represented by Ar^5 and Ar^6 include phenyl group, naphthyl group, anthranlyl group, phenanthryl group, pyrenyl group, coronyl group, biphenyl group, terphenyl group, fluorenyl group, furanyl group, thienyl group, benzothienyl group, indolyl group and carbazolyl group. Among these groups, phenyl group, naphthyl group, pyrenyl group and biphenyl group are preferable.

[0015] As the arylamine compound represented by general formula (V), arylamine compounds represented by the

following general formula (V-a):



15 wherein X^3 is as defined in general formula (V), are preferable.

20 [0016] In the above general formula (V-a), Ar^{15} to Ar^{18} each independently represent hydrogen atom, a substituted or unsubstituted alkyl group having 1 to 50 carbon atoms and preferably 1 to 20 carbon atoms, a substituted or unsubstituted aryl group having 5 to 50 carbon atoms and preferably 5 to 20 carbon atoms, a substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms and preferably 7 to 40 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 50 carbon atoms and preferably 5 to 12 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms and preferably 1 to 6 carbon atoms, a substituted or unsubstituted aryloxy group having 5 to 50 carbon atoms and preferably 5 to 18 carbon atoms, a substituted or unsubstituted arylamino group having 5 to 50 carbon atoms and preferably 5 to 18 carbon atoms or a substituted or unsubstituted alkylamino group having 1 to 20 carbon atoms and preferably 1 to 6 carbon atoms.

25 [0017] Examples of the substituted or unsubstituted alkyl group represented by Ar^{15} to Ar^{18} include methyl group, ethyl group, propyl group, isopropyl group, butyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, heptyl group, octyl group, stearyl group, 2-phenylisopropyl group, trichloromethyl group, trifluoromethyl group, benzyl group, α -phenoxybenzyl group, α,α -dimethylbenzyl group, α,α -methylphenylbenzyl group, α,α -ditrifluoromethylbenzyl group, triphenylmethyl group and α -benzyloxybenzyl group.

30 [0018] Examples of the substituted or unsubstituted aryl group represented by Ar^{15} to Ar^{18} include phenyl group, 2-methylphenyl group, 3-methylphenyl group, 4-methylphenyl group, 4-ethylphenyl group, biphenyl group, 4-methylbiphenyl group, 4-ethylbiphenyl group, 4-cyclohexylbiphenyl group, terphenyl group, 3,5-dichlorophenyl group, naphthyl group, 5-methylnaphthyl group, anthryl group and pyrenyl group.

35 [0019] Examples of the substituted or unsubstituted aralkyl group represented by Ar^{15} to Ar^{18} include benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, α -naphthylmethyl group, 1- α -naphthylethyl group, 2- α -naphthylethyl group, 1- α -naphthylisopropyl group, 2- α -naphthylisopropyl group, β -naphthylmethyl group, 1- β -naphthylethyl group, 2- β -naphthylethyl group, 1- β -naphthylisopropyl group, 2- β -naphthylisopropyl group, 1-pyrrolylmethyl group, 2-(1-pyrrolyl)ethyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-chlorobenzyl group, m-chlorobenzyl group, o-chlorobenzyl group, p-bromobenzyl group, m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-aminobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group and 1-chloro-2-phenylisopropyl group.

40 [0020] Examples of the substituted or unsubstituted cycloalkyl group represented by Ar^{15} to Ar^{18} include cyclopropyl group, cyclobutyl group, cyclopentyl group and cyclohexyl group.

45 [0021] Examples of the substituted or unsubstituted alkoxy group represented by Ar^{15} to Ar^{18} include methoxy group, ethoxy group, propoxy group, isopropoxy group, butoxy group, isobutoxy group, sec-butoxy group, tert-butoxy group, various types of pentyloxy groups and various types of hexyloxy groups.

50 [0022] Examples of the substituted or unsubstituted aryloxy group represented by Ar^{15} to Ar^{18} include phenoxy group, tolyloxy group and naphthyloxy group.


[0023] Examples of the substituted or unsubstituted arylamino group represented by Ar^{15} to Ar^{18} include diphenylamino group, ditolylamino group, dinaphthylamino group and naphthylphenylamino group.

55 [0024] Examples of the substituted or unsubstituted alkylamino group represented by Ar^{15} to Ar^{18} include dimethylamino group, diethylamino group and dihexylamino group.

[0025] In general formula (V-a), g, h, i and j each represent an integer of 0 to 5 and preferably an integer of 0 to 2. Atoms and groups represented by a plurality of Ar^{15} to Ar^{18} may be the same with or different from each other and may be bonded to each other to form a saturated or unsaturated ring when g, h, i and j each represent an integer of 2 or

greater. n represents an integer of 0 to 3. At least one of Ar^{15} to Ar^{18} represents a substituted or unsubstituted secondary or tertiary alkyl group having 3 to 10 carbon atoms. Examples of the secondary or tertiary alkyl group include the secondary and tertiary alkyl groups among the groups described as the examples of the alkyl group represented by Ar^{15} to Ar^{18} .

[0026] As the arylamine compound represented by general formula (V), arylamine compounds represented by the following general formula (V-b):



wherein X^3 , Ar^{15} to Ar^{18} , g , h , i and j are as defined in general formula (V-a), and atoms and groups represented by a plurality of Ar^{15} to Ar^{18} may be the same with or different from each other and may be bonded to each other to form a saturated or unsaturated ring when g , h , i and j each represent an integer of 2 or greater, are also preferable.

[0027] In general formula (V-b), R^{24} and R^{25} each independently represent hydrogen atom, a substituted or unsubstituted alkyl group having 1 to 10 carbon atoms and preferably 1 to 6 carbon atoms, a substituted or unsubstituted aryl group having 6 to 20 carbon atoms and preferably 6 to 14 carbon atoms, a substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms and preferably 7 to 40 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms and preferably 1 to 6 carbon atoms or a substituted or unsubstituted aryloxy group having 5 to 50 carbon atoms and preferably 5 to 18 carbon atoms.

[0028] Examples of the groups represented by R^{24} and R^{25} include the groups in which the number of carbon atoms is within the above range among the groups described as the examples of the groups represented by Ar^{15} to Ar^{18} .

[0029] At least one of R^{24} and R^{25} represents a substituted or unsubstituted secondary or tertiary alkyl group having 3 to 10 carbon atoms. Examples of the secondary or tertiary alkyl group include the secondary and tertiary alkyl groups among the groups described as the examples of the alkyl group represented by Ar^{15} to Ar^{18} .

[0030] In general formula (V-b), k and m each represent an integer of 0 to 2.

[0031] In the present invention, the arylamine compound of component (A) may be used singly or in combination of two or more.

[0032] Examples of the substituent in the compounds represented by general formulae (V), (V-a) and (V-b) include alkyl groups having 1 to 6 carbon atoms, cycloalkyl groups having 3 to 6 carbon atoms, alkoxy groups having 1 to 6 carbon atoms, aryloxy groups having 5 to 18 carbon atoms, aralkyloxy groups having 7 to 18 carbon atoms, arylamino groups having 5 to 16 carbon atoms, nitro group, cyano group, ester groups having 1 to 6 carbon atoms and halogen atoms. Examples of the above groups and atoms include the atoms and groups described as the examples of the atoms and the groups represented by A^{12} to A^{14} in general formula (IV) described in the following.

[0033] In the present invention, the compound of component (B) is at least one compound selected from anthracene derivatives represented by the following general formula (II). Anthracene derivatives represented by general formula (II):



wherein An represents a substituted or unsubstituted divalent anthracene

[0034] residue group, A^3 and A^4 each independently represent a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, at least one of A^3 and A^4 represents a substituted or unsubstituted monovalent condensed aromatic ring or a substituted or unsubstituted aryl group having 10 or more carbon atoms, and A^3 and A^4 may represent the same group or different groups.

[0035] Examples of the aryl group represented by A^3 and A^4 include phenyl group, 2-methylphenyl group, 3-methylphenyl group, 4-methylphenyl group, 4-ethylphenyl group, biphenyl group, 4-methylbiphenyl group, 4-ethylbiphenyl group, 4-cyclohexylbiphenyl group, terphenyl group, 3,5-dichlorophenyl group and condensed aromatic ring groups which are residue groups derived from naphthalene, phenanthrene, fluoranthene, anthracene, pyrene, perylene, coronene, chrysene, picene, fluorene, terphenyl, diphenylanthracene, biphenyl, carbazole, triphenylene, rubicene, benzoanthracene, phenylanthracene, bisanthracene, dianthracenylbenzene and dibenzoanthracene, which may be substituted or unsubstituted.

[0036] As the anthracene derivative represented by the above general formula (II), anthracene derivatives represented by the following general formula (II-a):



5 wherein An represents a substituted or unsubstituted divalent anthracene residue group and X¹ and X² each independently represent a monovalent residue group derived from naphthalene, phenanthrene, fluoranthene, anthracene, pyrene, perylene, coronene, chrysene, picene, diphenylanthracene, carbazole, triphenylene, rubicene, benzoanthracene, phenylanthracene, bisanthracene, dianthracenylbenzene or dibenzoanthracene, which may be substituted or unsubstituted, are preferable.

10 **[0037]** Examples of the substituent in the compounds represented by the above general formulae (II), and (II-a) include alkyl groups having 1 to 6 carbon atoms, cycloalkyl groups having 3 to 6 carbon atoms, alkoxy groups having 1 to 6 carbon atoms, aryloxy groups having 5 to 18 carbon atoms, aralkyloxy groups having 7 to 18 carbon atoms, arylamino groups having 5 to 16 carbon atoms, nitro group, cyano group, ester groups having 1 to 6 carbon atoms and halogen atoms.

15 **[0038]** Examples of the alkyl group having 1 to 6 carbon atoms include methyl group, ethyl group, propyl group, isopropyl group, butyl group, isobutyl group, sec-butyl group, tert-butyl group, various types of pentyl group and various types of hexyl group.

[0039] Examples of the cycloalkyl group having 3 to 6 carbon atoms include cyclopropyl group, cyclobutyl group, cyclopentyl group and cyclohexyl group.

20 **[0040]** Examples of the alkoxy group having 1 to 6 carbon atoms include methoxy group, ethoxy group, propoxy group, isopropoxy group, butoxy group, isobutoxy group, sec-butoxy group, tert-butoxy group, various types of pentyloxy groups and various types of hexyloxy groups.

[0041] Examples of the aryloxy group having 5 to 18 carbon atoms include phenoxy group, tolyloxy group and naphthyloxy group.

25 **[0042]** Examples of the aralkyloxy group having 7 to 18 carbon atoms include benzyloxy group, phenetyloxy group and naphthylmethoxy group.

[0043] Examples of the arylamino group having 5 to 16 carbon atoms include diphenylamino group, ditolylamino group, dinaphthylamino group and naphthylphenylamino group.

30 **[0044]** Examples of the ester group having 1 to 6 carbon atoms include methoxycarbonyl group, ethoxycarbonyl group, propoxycarbonyl group and isopropoxycarbonyl group.

[0045] Examples of the halogen atoms include fluorine atom, chlorine atom and bromine atom. The aryl group in the present invention includes styrylphenyl group, styrylbiphenyl group and styrylnaphthyl group.

[0046] In the present invention, the anthracene derivative of component (B) may be used singly or in combination of two or more.

35 **[0047]** Specific examples of the anthracene derivative represented by the above general formula (II) are shown in the following.

40


45

50


55

5
10
15
20
25
30
35
40
45
50
55

EM1




EM2




(Me: methyl group; similarly in the following formulae)

EM3




EM4




5
10
15
20
25
30
35
40
45
50
55


EM 5



EM 6




EM 7



5

EM8

10




15

EM9

20


25



30

EM10

35




40

EM11

45

50




55

5

EM12

10

15




20

EM13

25

30




35

EM14

40

45




50

55

5

EM15

10




15

EM16

20

25



30

35

40


45

50

55

5

EM17




10

15

20

EM18



25

30

35

40


45

50

55

5

EM19




10

15

20

EM20




25

30

35


EM21



40

45

EM22



50


55

5

EM23

10


15



20

EM24

25




30

EM25

35

40




45

EM26


50

55



EM27


5



10

EM28


15



20

EM29


25



30

EM30


35



40

EM31

45



50


55

EM32

5

10


15



20

EM33


25



30

EM34


35



40

EM35


45



50

EM36


55



EM37

5

10




EM38

15

20


25



EM39

30


35



EM40

40


45



EM41


50

55




[0048] Specific examples of the arylamine compounds represented by the above general formulae (V), (V-a) and (V-b) are shown in the following.


5




EM57




EM58




EM59



EM60




EM61




EM62

10

15




EM97




EM98

20

25




EM99




EM100

30

35



EM101



EM102



40

45

50




55

5



10

15



20





EM110

EM111

EM112

25

30



35




EM113

EM114

EM115

EM116

40



45


EM131

EM132


EM133

50


55




EM134




EM135













EM161




EM193



EM194





EM227

[0049] In the present invention, the ratio of the amount by weight of the arylamine of component (A) to the amount by weight of the anthracene derivative of component (B) in the layer of an organic light emitting medium is in the range of 1:99 to 99:1. It is preferable that the ratio of the amounts is suitably selected in accordance with the type of the compounds used. It is more preferable that, taking it into consideration that the compound of component (A) has the hole transporting property and the compound of component (B) has the electron transportation property, the ratio of the amounts is selected in a manner such that the life and the efficiency of the obtained device are maximized.

[0050] It is preferable that the ratio of the amount by weight of component (A) to the amount by weight of component (B) is in the range of 1:99 to 20:80. A particularly high efficiency can be obtained in this range.

[0051] It is preferable that the layer of an organic light emitting medium has a thickness in the range of 5 to 200 nm and more preferably in the range of 10 to 40 nm since the voltage applied to the device can be lowered to a great extent.

[0052] Due to the use of component (A) in combination with component (A) for the layer of an organic light emitting medium, the efficiency can be increased by 3 to 5 times as much as the efficiency obtained by using component (A) alone and the life can be increased by at least 3 times, and by at least 10 times when optimized, as long as the life obtained by using component (A) alone.

[0053] Due to the use of the arylamine represented by general formula (V) as component (A), the concentration quenching due to an increase in the association of molecules can be prevented since the steric hindrance increases and the life can be further increased. When a branched alkyl group is introduced into the substituent of amino group or the condensed aromatic ring, the half width of the spectrum of the emitted light which can be used as the index for the purity of color is decreased since the steric repulsion between the condensed aromatic ring and the substituent of amino group is increased and the spectrum of the emitted light becomes sharp. Therefore, the obtained device is suitable for full color displays.

[0054] Due to the use of component (A) and component (B) in combination, the stability and the heat resistance are improved since the layer of an organic light emitting layer becomes more amorphous. It is preferable that the compound of component (B) has a glass transition temperature of 110°C or higher. It is also preferable that the compound of component (A) has a glass transition temperature of 70°C or higher. By mixing the compounds having the above glass transition temperatures, the glass transition temperature of the layer of an organic light emitting medium can be made 90°C or higher and a durability in storage of 500 hours or longer at 85°C can be achieved.

[0055] The organic EL device of the present invention comprises the layer of an organic light emitting medium (referred to as the light emitting medium layer, hereinafter) which comprises the combination of component (A) and component (B) and is disposed between a pair of electrodes. In the organic EL device of the present invention, it is preferable that various intermediate layers are disposed between the electrodes and the light emitting medium layer. Examples of the intermediate layer include a hole injecting layer, a hole transporting layer, an electron injecting layer and an electron transporting layer. It is known that various organic and inorganic compounds can be used for these layers.

[0056] Typical examples of the construction of the organic EL device include:

- (1) An anode / a light emitting layer / a cathode;
- (2) An anode / a hole injecting layer / a light emitting layer / a cathode;
- (3) An anode / a light emitting layer / an electron injecting layer / a cathode;
- (4) An anode / a hole injecting layer / a light emitting layer / an electron injecting layer / a cathode;
- (5) An anode / an organic semiconductor layer / a light emitting layer / a cathode;
- (6) An anode / an organic semiconductor layer / an electron barrier layer / a light emitting layer / a cathode;
- (7) An anode / an organic semiconductor layer / a light emitting layer / an adhesion improving layer / a cathode;
- (8) An anode / a hole injecting layer / a hole transporting layer / a light emitting layer / an electron injecting layer / a cathode;

(9) An anode / an insulating layer / a light emitting layer / an insulating layer / a cathode;

(10) An anode / an inorganic semiconductor layer / an insulating layer / a light emitting layer / an insulating layer / a cathode;

(11) An anode / an organic semiconductor layer / an insulating layer / a light emitting layer / an insulating layer / a cathode;

(12) An anode / an insulating layer / a hole injecting layer / a hole transporting layer / a light emitting layer / an insulating layer / a cathode; and

(13) An anode / an insulating layer / a hole injecting layer / a hole transporting layer / a light emitting layer / an electron injecting layer / a cathode.

[0057] Among the above constructions, construction (8) is preferable. However, the construction of the organic EL device is not limited to the above examples.

[0058] In general, the organic EL device is prepared on a substrate which transmits light. The substrate which transmits light is the substrate which supports the organic EL device. It is preferable that the substrate which transmits light has a transmittance of light of 50% or greater in the visible region of 400 to 700 nm. It is also preferable that a flat and smooth substrate is used.

[0059] As the substrate which transmits light, for example, glass plates and synthetic resin plates are advantageously used. Specific examples of the glass plate include plates made of soda ash glass, glass containing barium and strontium, lead glass, aluminosilicate glass, borosilicate glass, barium borosilicate glass and quartz. Specific examples of the synthetic resin plates include plates made of polycarbonate resins, acrylic resins, polyethylene terephthalate resins, polyether sulfide resins and polysulfone resins.

[0060] As the anode, an electrode made of a material such as a metal, an alloy, a conductive compound and a mixture of these materials which has a great work function (4 eV or more) is preferably used. Specific examples of the material for the anode include metals such as Au and conductive materials such as CuI, ITO (indium tin oxide), SnO₂, ZnO and In-Zn-O. The anode can be prepared by forming a thin film of the electrode material described above in accordance with a process such as the vapor deposition process and the sputtering process. When the light emitted from the light emitting layer is obtained through the anode, it is preferable that the anode has a transmittance of the emitted light greater than 10%. It is also preferable that the sheet resistivity of the anode is several hundred Ω/□ or smaller. The thickness of the anode is, in general, selected in the range of 10 nm to 1 μm and preferably in the range of 10 to 200 nm although the preferable range may be different depending on the used material.

[0061] As the cathode, an electrode made of a material such as a metal, an alloy, a conductive compound and a mixture of these materials which has a small work function (4 eV or smaller) is used. Specific examples of the material for the cathode include sodium, sodium-potassium alloys, magnesium, lithium, magnesium-silver alloys, aluminum/aluminum oxide, Al/Li₂O, Al/LiO₂, Al/LiF, aluminum-lithium alloys, indium and rare earth metals.

[0062] The cathode can be prepared by forming a thin film of the electrode material described above in accordance with a process such as the vapor deposition process and the sputtering process.

[0063] When the light emitted from the light emitting medium layer is obtained through the cathode, it is preferable that the cathode has a transmittance of the emitted light greater than 10%. It is also preferable that the sheet resistivity of the cathode is several hundred Ω/□ or smaller. The thickness of the cathode is, in general, selected in the range of 10 nm to 1 μm and preferably in the range of 50 to 200 nm although the preferable range may be different depending on the material used.

[0064] In the organic EL device of the present invention, it is preferable that a layer of a chalcogenide, a metal halide or a metal oxide (this layer may occasionally be referred to as a surface layer) is disposed on the surface of at least one of the pair of electrodes prepared as described above. Specifically, it is preferable that a layer of a chalcogenide (including an oxide) of a metal such as silicon and aluminum is disposed on the surface of the anode at the side of the light emitting medium layer and a layer of a metal halide or a metal oxide is disposed on the surface of the cathode at the side of the light emitting medium layer. Due to the above layers, stability in driving can be improved.

[0065] Preferable examples of the chalcogenide include SiO_x (1 ≤ x ≤ 2), AlO_x (1 ≤ x ≤ 1.5), SiON and SiAlON. Preferable examples of the metal halide include LiF, MgF₂, CaF₂ and fluorides of rare earth metals. Preferable examples of the metal oxide include Cs₂O, Li₂O, MgO, SrO, BaO and CaO.

[0066] In the organic EL device of the present invention, the electron transporting property and the hole transporting property of the light emitting medium layer are simultaneously improved by suitably adjusting the relative amounts of component (A) and component (B) described above and the above intermediate layers such as the hole injecting layer, the hole transporting layer and the electron injecting layer can be omitted. In this case, it is preferable that the surface layer described above is disposed.

[0067] In the organic EL device of the present invention, it is preferable that a mixed region of an electron transfer compound and a reducing dopant or a mixed region of a hole transfer compound and an oxidizing dopant is disposed on the surface of at least one of the pair of electrodes prepared as described above. Due to the mixed region disposed

as described above, the electron transfer compound is reduced to form an anion and injection and transportation of electrons from the mixed region into the light emitting medium can be facilitated. The hole transfer compound is oxidized to form a cation and injection and transportation of holes from the mixed region into the light emitting medium is facilitated. Preferable examples of the oxidizing dopant include various types of Lewis acid and acceptor compounds. Preferable examples of the reducing dopant include alkali metals, compounds of alkali metals, alkaline earth metals, rare earth metals and compounds of these metals.

[0068] In the organic EL device of the present invention, the light emitting medium layer has the following functions:

- (1) The injecting function: the function of injecting holes from the anode or the hole injecting layer and injecting electrons from the cathode or the electron injecting layer when an electric field is applied;
- (2) The transporting function: the function of transporting injected charges (electrons and holes) by the force of the electric field; and
- (3) The light emitting function: the function of providing the field for recombination of electrons and holes and leading the recombination to the emission of light.

[0069] As the process for forming the light emitting medium layer, a conventional process such as the vapor deposition process, the spin coating process and the Langmuir-Blodgett process (the LB process) can be used. It is particularly preferable that the organic light emitting medium layer is a molecular deposit film. The molecular deposit film is a thin film formed by deposition of a material compound in the gas phase or a thin film formed by solidification of a material compound in a solution or in the liquid phase. In general, the molecular deposit film can be distinguished from the thin film formed in accordance with the LB process (the molecular accumulation film) based on the differences in the aggregation structure and higher order structures and functional differences caused by these structural differences.

[0070] As disclosed in Japanese Patent Application Laid-Open No. Showa 57(1982)-51781, the light emitting medium layer can also be formed by dissolving a binder such as a resin and the material compounds into a solvent to prepare a solution, followed by forming a thin film from the prepared solution in accordance with the spin coating process or the like.

[0071] In the present invention, where desired, the light emitting medium layer may comprise conventional organic light emitting media other than component (A) and component (B) described above or the light emitting medium layer comprising the compounds described in the present invention may be laminated with a light emitting medium layer comprising other conventional organic light emitting media as long as the object of the present invention is not adversely affected.

[0072] The hole injecting layer and the hole transporting layer are layers which help injection of holes into the light emitting medium layer and transport the holes to the light emitting region. The layers exhibit a great mobility of holes and, in general, have an ionization energy as small as 5.5 eV or smaller. For the hole injecting layer and the hole transporting layer, a material which transports holes to the light emitting medium layer at a small electric field strength is preferable. A material which exhibits, for example, a mobility of holes of at least 10^{-6} cm²/V-sec under application of an electric field of 10^4 to 10^6 V/cm is more preferable. A material can be selected from materials which are conventionally used as the charge transporting material of holes in photoconductive materials and conventional materials which are used for the hole injecting layer in organic EL devices.

[0073] To form the hole injecting layer or the hole transporting layer, a thin film may be formed from a material for the hole injecting layer or the hole transporting layer, respectively, in accordance with a conventional process such as the vacuum vapor deposition process, the spin coating process, the casting process and the LB process. The thickness of the hole injecting layer and the hole transporting layer is not particularly limited. In general, the thickness is 5 nm to 5 μm.

[0074] The electron injection layer is a layer which helps injection of electrons into the light emitting medium layer and exhibits a great mobility of electrons. The adhesion improving layer is a layer made of a material exhibiting excellent adhesion with the cathode among the electron injecting layer. As the material for the electron injecting layer, metal complexes of 8-hydroxyquinoline and derivatives thereof are preferably used. Specific examples of the metal complex of 8-hydroxyquinoline and derivatives thereof include metal chelates of oxinoid compounds including chelates of oxine (in general, 8-quinolinol or 8-hydroxyquinoline). For example, tris(8-quinolinol)aluminum can be used as the electron injecting material.

[0075] The organic EL device of the present invention tends to form defects in pixels due to leak and short circuit since an electric field is applied to ultra-thin films. To prevent the formation of the defects, a layer of an insulating thin film may be inserted between the pair of electrodes.

[0076] Examples of the material used for the insulating layer include aluminum oxide, lithium fluoride, lithium oxide, cesium fluoride, cesium oxide, magnesium oxide, magnesium fluoride, calcium oxide, calcium fluoride, aluminum nitride, titanium oxide, silicon oxide, germanium oxide, silicon nitride, boron nitride, molybdenum oxide, ruthenium oxide and vanadium oxide. Mixtures and laminates of the above compounds can also be used.

[0077] To prepare the organic EL device of the present invention, for example, the anode, the light emitting medium layer and, where necessary, the hole injecting layer and the electron injecting layer are formed in accordance with the

above process using the above materials and the cathode is formed in the last step. The organic EL device may be prepared by forming the above layers in the order reverse to that described above, i.e., the cathode being formed in the first step and the anode in the last step.

5 **[0078]** An embodiment of the process for preparing an organic EL device having a construction in which an anode, a hole injecting layer, a light emitting medium layer, an electron injecting layer and a cathode are disposed successively on a substrate which transmits light will be described in the following.

10 **[0079]** On a suitable substrate which transmits light, a thin film made of a material for the anode is formed in accordance with the vapor deposition process or the sputtering process so that the thickness of the formed thin film is 1 μm or smaller and preferably in the range of 10 to 200 nm. The formed thin film is used as the anode. Then, a hole injecting layer is formed on the anode. The hole injecting layer can be formed in accordance with the vacuum vapor deposition process, the spin coating process, the casting process or the LB process, as described above. The vacuum vapor deposition process is preferable because a uniform film can be easily obtained and the possibility of formation of pin holes is small. When the hole injecting layer is formed in accordance with the vacuum vapor deposition process, in general, it is preferable that the conditions are suitably selected in the following ranges: the temperature of the source of the deposition: 50 to 15 450°C; the vacuum: 10^{-7} to 10^{-3} Torr; the rate of deposition: 0.01 to 50 nm/second; the temperature of the substrate: -50 to 300°C and the thickness of the film: 5 nm to 5 μm ; although the conditions of the vacuum vapor deposition are different depending on the used compound (the material for the hole injecting layer) and the crystal structure and the recombination structure of the hole injecting layer to be formed.

20 **[0080]** Then, the light emitting medium layer is formed on the hole injecting layer formed above. Using the organic light emitting medium described in the present invention, a thin film of the organic light emitting medium can be formed in accordance with the vacuum vapor deposition process, the sputtering process, the spin coating process or the casting process and the formed thin film is used as the light emitting medium layer. The vacuum vapor deposition process is preferable because a uniform film can be easily obtained and the possibility of formation of pin holes is small. When the light emitting medium layer is formed in accordance with the vacuum vapor deposition process, in general, the conditions 25 of the vacuum vapor deposition process can be selected in the same ranges as those described for the vacuum vapor deposition of the hole injecting layer although the conditions are different depending on the used compound. It is preferable that the thickness is in the range of 10 to 40 nm.

30 **[0081]** An electron injecting layer is formed on the light emitting medium layer formed above. Similarly to the hole injecting layer and the light emitting medium layer, it is preferable that the electron injecting layer is formed in accordance with the vacuum vapor deposition process since a uniform film must be obtained. The conditions of the vacuum vapor deposition can be selected in the same ranges as those described for the vacuum vapor deposition of the hole injecting layer and the light emitting medium layer.

35 **[0082]** A cathode is formed on the electron injecting layer formed above in the last step and an organic EL device can be obtained. The cathode is made of a metal and can be formed in accordance with the vacuum vapor deposition process or the sputtering process. It is preferable that the vacuum vapor deposition process is used in order to prevent formation of damages on the lower organic layers during the formation of the film.


[0083] In the above preparation of the organic EL device, it is preferable that the above layers from the anode to the cathode are formed successively while the preparation system is kept in a vacuum after being evacuated.

40 **[0084]** The organic EL device which can be prepared as described above emits light when a direct voltage of 3 to 40 V is applied in the condition that the anode is connected to a positive electrode (+) and the cathode is connected to a negative electrode (-). When the connection is reversed, no electric current is observed and no light is emitted at all. When an alternating voltage is applied to the organic EL device, light emission is observed only in the condition that the polarity of the anode is positive and the polarity of the cathode is negative. When an alternating voltage is applied to the organic EL device, any type of wave shape can be used.

45 **[0085]** The present invention also provides the organic light emitting medium comprising component (A) and component (B) described above. The organic light emitting medium is advantageously used for the organic electroluminescence device having excellent heat resistance and a long life and efficiently emitting bluish to yellowish light.

[0086] The present invention will be described more specifically with reference to examples in the following. However, the present invention is not limited to the examples.

50 **[0087]** The following compounds which are used in the examples are not part of the invention:



55 Example 1(not part of the invention)

[0088] On a glass plate having a size of 25 × 75 × 1.1 mm, a transparent electrode made of indium tin oxide and having a thickness of 120 nm was formed. After the glass substrate was cleaned by irradiation with ultraviolet light and

EP 2 199 361 B9

exposure to ozone, the glass substrate was placed in a vacuum vapor deposition apparatus.

[0089] After N,N'-bis[4-(diphenylamino)phenyl]-N,N'-diphenylbiphenyl-4,4'-diamine was vapor deposited so that a hole injecting layer having a thickness of 60 nm was formed, N,N,N',N'-tetrakis(4-biphenyl)-4,4'-benzidine was vapor deposited on the formed hole injecting layer so that a hole transporting layer having a thickness of 20 nm was formed. Then, compound (EM4) shown above as component (B) and compound (EM83)

Example 20

[0090] An organic EL device was prepared in accordance with the same procedures as those conducted in Example 1 except that compounds shown in Table 2 were used as component (B) and component (A) and Alq:Cs/Al was used as the cathode. Alq:Cs/Al was a mixed layer containing Alq and Cs (cesium) metal as the electron transporting compounds in relative amounts by mole of 1:1. The results of testing the obtained device by passing an electric current at a current density of 10 mA/cm² are shown in Table 2. The half-life time obtained by the test of continuous passage of a direct current at the initial luminance shown in Table 2 is also shown in Table 2.

Examples 21 to 41

[0091] An organic EL device was prepared in accordance with the same procedures as those conducted in Example 20 except that compounds shown in Table 2 were used as component (B) and component (A). The results of testing the obtained devices by passing an electric current at a current density of 10 mA/cm² are shown in Table 2. The half-life times obtained by the test of continuous passage of a direct current at initial luminances shown in Table 2 are also shown in Table 2.

Table 1 - 1

	Components of light emitting layer		Voltage (V)	Luminance of emitted light (cd/m ²)	Efficiency of light emission (cd/A)
	component (B)	component (A)			
Example 1*	EM4	EM83	6.5	205	2.05
Example 2	EM4	EM110	6.3	310	3.10
Example 3	EM5	EM111	6.0	325	3.25
Example 4*	EM5	EM77	6.8	195	1.95
Example 5*	EM5	EM117	6.0	295	2.95
Example 6	EM27	EM110	6.5	190	1.90
Example 7	EM37	EM111	6.0	180	1.80
Example 8*	EM43	EM110	6.2	165	1.65
Example 9*	EM49	EMU1	6.3	170	1.70
Example 10	EM4	EM60	6.0	350	3.50
Example 11	EM4	EM98	6.0	730	7.30
Example 12	EM5	EM60	6.0	345	3.45
Example 13	EM5	EM98	6.0	815	8.15
Example 14	EM5	EM97	6.5	5	5.50
Example 15	EM27	EM98	6.0	355	3.55
Example 16*	EM42	EM97	6.5	395	3.95
Example 17*	EM46	EM98	6.0	500	5.00
Example 18*	EM4	EM89	7.0	1050	10.50
Example 19*	EM4	EM94	7.5	950	9.50
Comparative Example 1		EM4	6.3	90	0.90
Comparative Example 2	EM4	H2	6.8	105	1.05
Comparative Example 3	EM4	H3	6.5	200	2.00
Comparative Example 4	EM4	H4	7.0	96	0.96

EP 2 199 361 B9

(continued)

	Components of light emitting layer		Voltage (V)	Luminance of emitted light (cd/m ²)	Efficiency of light emission (cd/A)
	component (B)	component (A)			
5 Comparative Example 5	EM4	H5	6.8	510	5.10

*: not part of the invention

Table 1 - 2

	Color of emitted light	Half width (nm)	Half-life time (hour)	Initial luminance (cd/m ²)
15 Example 1*	pure blue	42	900	500
Example 2	pure blue	43	2900	500
Example 3	pure blue	45	3050	500
Example 4*	pure blue	42	680	500
20 Example 5*	pure blue	44	1000	500
Example 6	pure blue	44	1150	500
Example 7	pure blue	45	1200	500
Example 8*	pure blue	43	950	500
Example 9*	pure blue	45	1100	500
25 Example 10	blue	40	800	1000
Example 11	blue	50	3100	1000
Example 12	blue	41	700	1000
Example 13	blue	49	3200	1000
30 Example 14	blue	48	2950	1000
Example 15	blue	49	1500	1000
Example 16*	blue	49	900	1000
Example 17*	blue	50	1000	1000
Example 18*	green	68	1050	3000
35 Example 19*	green	65	750	3000
Comparative Example 1	pure blue	45	90	500
Comparative Example 2	pure blue	58	300	500
Comparative Example 3	green	69	200	1000
40 Comparative Example 4	pure blue	46	100	500
Comparative Example 5	blue	62	500	1000

*: not part of the invention

Table 2 - 1

	Components of light emitting layer		Voltage (V)	Luminance of emitted light (cd/m ²)	Efficiency of light emission (cd/A)
	component (B)	component (A)			
50 Example 20	EM32	EM111	5.0	290	2.90
Example 21*	EM4	EM128	6.5	260	2.60
Example 22*	EM5	EM128	6.0	250	2.50
Example 23*	EM42	EM128	6.5	155	1.55
Example 24	EM5	EM131	6.7	964	9.64
55 Example 25	EM5	EM133	6.5	1015	10.15
Example 26*	EM43	EM139	7.0	950	9.50
Example 27*	EM5	EM139	6.5	2040	20.40

EP 2 199 361 B9

(continued)

	Components of light emitting layer		Voltage (V)	Luminance of emitted light (cd/m ²)	Efficiency of light emission (cd/A)	
	component (B)	component (A)				
5	Example 28*	EM42	EM144	6.5	1050	10.50
	Example 29*	EM5	EM144	6.4	2100	21.00
	Example 30*	EM32	EM144	6.0	1555	15.60
	Example 31*	EM32	EM160	6.5	1430	14.30
10	Example 32*	EM32	EM189	6.0	980	9.80
	Example 33*	Alq	EM139	7.0	1420	14.20
	Example 34	EM4	EM215	6.5	340	3.40
	Example 35	EM5	EM215	6.5	355	3.55
	Example 36*	EM42	EM215	6.7	185	1.85
15	Example 37	EM4	EM195	6.0	1050	10.50
	Example 38	EM4	EM197	6.4	1030	10.30
	Example 39*	EM5	EM202	6.5	1870	18.70
	Example 40*	EM5	EM204	6.5	1850	18.50
20	Example 41*	EM5	EM208	6.9	1350	13.50

*: not part of the invention

Table 2 - 2

	Color of emitted light	Half width (nm)	Half-life time (hour)	Initial luminance (cd/m ²)	
	Example 20	pure blue	44	1300	500
	Example 21*	pure blue	43	2100	500
	Example 22*	pure blue	43	2350	500
30	Example 23*	pure blue	44	1000	500
	Example 24	blue	49	4000	1000
	Example 25	blue	50	4100	1000
	Example 26*	green	68	900	3000
35	Example 27*	green	67	4500	3000
	Example 28*	green	67	1100	3000
	Example 29*	green	68	4750	3000
	Example 30*	green	68	1050	3000
	Example 31*	green	64	1800	3000
40	Example 32*	green	65	950	3000
	Example 33*	green	69	1500	3000
	Example 34	pure blue	44	3500	500
	Example 35	pure blue	44	3950	500
45	Example 36*	pure blue	43	970	500
	Example 37	blue	50	4050	1000
	Example 38	blue	49	3950	1000
	Example 39*	green	68	2100	3000
	Example 40*	green	68	1950	3000
50	Example 41*	green	65	1500	3000

*: not part of the invention

[0092] As shown in Table 1 and Table 2, the excellent efficiencies and the excellent lives could be achieved in the devices emitting green light, blue light and pure blue light, which was hard to obtain, as shown in Examples 1 to 41. The above results were achieved since the light having more excellent purity of color could be emitted due to the decrease in the half width in comparison to those of the devices of Comparative Examples.

[0093] In particular, the devices comprising the diaminopyrene derivatives emitting blue light and the diaminochrysene derivatives emitting pure blue light as component (A) exhibited more excellent efficiencies of light emission and lives in comparison to those of any of the devices of Comparative Examples.

[0094] Since the anthracene derivative was used as component (B) and the diaminopyrene derivative or the diaminochrysene derivative was used as component (A), the most excellent efficiency of light emission and life could be achieved by the devices emitting green light, blue light and pure blue light.

INDUSTRIAL APPLICABILITY


[0095] In accordance with the present invention, the organic EL device which exhibits excellent purity of color, has excellent heat resistance and a long life and efficiently emits bluish to yellowish light and an organic light emitting medium which can be advantageously used for the organic electroluminescence device, can be provided.

[0096] The organic EL device can be advantageously used as the light emitting device in various types of display apparatuses and is particularly suitable for full color display apparatuses.

Claims

1. An electroluminescence device comprising a pair of electrodes and a layer of an organic light emitting medium disposed between the pair of electrodes, wherein the layer of the organic light emitting medium comprises:

(A) an arylamine compound represented by the following general formula (V):



wherein

X^3 represents a substituted or unsubstituted residue of pyrene or chrysene;

Ar^5 and Ar^6 each independently represent a substituted or unsubstituted monovalent aromatic group having 6 to 40 carbon atoms, and

p represents an integer of 1 to 4; and

(B) at least one compound selected from anthracene derivatives represented by the following general formula (II):



wherein

An represents a substituted or unsubstituted divalent anthracene residue;

A^3 and A^4 each independently represent a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, at least one of A^3 and A^4 represents a substituted or unsubstituted monovalent condensed aromatic ring group, or a substituted or unsubstituted aryl group having 10 or more carbon atoms,

and A^3 and A^4 may be the same or different.


2. The electroluminescence device according to claim 1, wherein the anthracene derivative is represented by formula (II-a):



wherein An is as defined in claim 1 and X^1 and X^2 each independently represent a monovalent residue of naphthalene, phenanthrene, fluoranthene, anthracene, pyrene, perylene, coronene, chrysene, picene, diphenylanthracene, carbazole, triphenylene, rubicene, benzoanthracene, phenylanthracene, bisanthracene, dianthracenylbenzene or

dibenzoanthracene, which may be substituted or unsubstituted.

3. The electroluminescence device according to claim 1 or 2, wherein the monovalent aromatic group represented by Ar^5 and Ar^6 is selected from a phenyl group, naphthyl group, anthranyl group, phenanthryl group, pyrenyl group, coronyl group, biphenyl group, terphenyl group, fluorenyl group, furanyl group, thienyl group, benzothienyl group, indolyl group and carbazolyl group.
4. The electroluminescence device according to any one of claims 1 to 3, wherein the substituent of the residue of pyrene or chrysene represented by X^3 is selected from alkyl groups having 1 to 6 carbon atoms, cycloalkyl groups having 3 to 6 carbon atoms, alkoxy groups having 1 to 6 carbon atoms, aryloxy groups having 5 to 18 carbon atoms, aralkyloxy groups having 7 to 18 carbon atoms, arylamino groups having 5 to 16 carbon atoms, nitro group, cyano group, ester groups having 1 to 6 carbon atoms and halogen atoms, and the substituent of the monovalent aromatic group represented by Ar^5 and Ar^6 is selected from alkyl groups having 1 to 6 carbon atoms, cycloalkyl groups having 3 to 6 carbon atoms, alkoxy groups having 1 to 6 carbon atoms, aryloxy groups having 5 to 18 carbon atoms, aralkyloxy groups having 7 to 18 carbon atoms, arylamino groups having 5 to 16 carbon atoms, nitro group, cyano group, ester groups having 1 to 6 carbon atoms and halogen atoms.
5. The electroluminescence device according to any one of claims 1 to 3, wherein the arylamine compound is represented by the following general formula (V-a):



wherein

X^3 is defined as in claim 1;

A^{15} to A^{18} each independently represents a hydrogen atom, a substituted or unsubstituted alkyl group having 1 to 50 carbon atoms, a substituted or unsubstituted aryl group having 5 to 50 carbon atoms, a substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms, a substituted or unsubstituted aryloxy group having 5 to 50 carbon atoms, a substituted or unsubstituted arylamino group having 5 to 50 carbon atoms or a substituted or unsubstituted alkylamino group having 1 to 20 carbon atoms, g , h , i and j each represent an integer of 0 to 5;


n represents an integer of 0 to 3;

two or more A^{15} 's, A^{16} 's, A^{17} 's and A^{18} 's may be the same or different and may be bonded to each other to form a saturated or unsaturated ring when g , h , i and j each represent an integer of 2 or greater; and

at least one of A^{15} to A^{18} represents a substituted or unsubstituted secondary or tertiary alkyl group having 3 to 10 carbon atoms.

6. The electroluminescence device according to any one of claims 1 to 3, wherein the arylamine compound is represented by the following general formula (V-b):

(V-b)



wherein

X^3 represents a substituted or unsubstituted residue of pyrene or chrysene; A^{15} to A^{18} each independently represents a hydrogen atom, a substituted or unsubstituted alkyl group having 1 to 50 carbon atoms, a substituted or unsubstituted aryl group having 5 to 50 carbon atoms, a substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms, a substituted or unsubstituted aryloxy group having 5 to 50 carbon atoms, a substituted or unsubstituted arylamino group having 5 to 50 carbon atoms or a substituted or unsubstituted alkylamino group having 1 to 20 carbon atoms;

g , h , i and j each represent an integer of 0 to 5;

two or more A^{15} 's, A^{16} 's, A^{17} 's and A^{18} 's may be the same or different and may be bonded to each other to form a saturated or unsaturated ring when g , h , i and j each represent an integer of 2 or greater;


R^{24} and R^{25} each independently represents a hydrogen atom, a substituted or unsubstituted alkyl group having 1 to 10 carbon atoms, a substituted or unsubstituted aryl group having 6 to 20 carbon atoms, a substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms or a substituted or unsubstituted aryloxy group having 5 to 50 carbon atoms;

k and m each represent an integer of 0 to 2; and

at least one of R^{24} and R^{25} represents a substituted or unsubstituted secondary or tertiary alkyl group having 3 to 10 carbon atoms.

7. The electroluminescence device according to any one of Claims 1 to 6,
 wherein the ratio of the amount by weight of component (A) to the amount by weight of component (B) is in a range of 1:99 to 20:80.
8. The electroluminescence device according to any one of Claims 1 to 7,
 wherein a layer of a chalcogenide, a layer of a metal halide or a layer of a metal oxide is disposed at least on one surface of the pair of electrodes.
9. The electroluminescence device according to any one of Claims 1 to 8,
 wherein a mixed region comprising a reducing dopant and organic substances or a mixed region comprising an oxidizing dopant and organic substances is disposed at least on one surface of the pair of electrodes.
10. The electroluminescence device according to any one of Claims 1 to 9,
 wherein the layer of an organic light emitting medium has a thickness in a range of 10 to 400 nm.
11. An organic light emitting medium which comprises:

(A) an arylamine compound represented by the following general formula (V):



wherein

X³ represents a substituted or unsubstituted residue of pyrene or chrysene,

Ar⁵ and Ar⁶ each independently represent a substituted or unsubstituted monovalent aromatic group having 6 to 40 carbon atoms, and

p represents an integer of 1 to 4; and

(B) at least one compound selected from anthracene derivatives represented by the following general formula (II):



wherein

An represents a substituted or unsubstituted divalent anthracene residue;

A³ and A⁴ each independently represent a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, at least one of A³ and A⁴ represents a substituted or unsubstituted monovalent condensed aromatic ring group


or a substituted or unsubstituted aryl group having 10 or more carbon atoms,

and A³ and A⁴ may be the same with or different from each other.

30 Patentansprüche

1. Elektrolumineszenzvorrichtung umfassend ein Paar von Elektroden und eine Schicht von einem organischen lichtemittierenden Medium, die zwischen dem Paar von Elektroden angeordnet ist, wobei die Schicht des organischen lichtemittierenden Mediums folgendes umfasst:

35 (A) eine durch die folgende allgemeine Formel (V) dargestellte Arylaminverbindung:



wobei

X³ einen substituierten oder unsubstituierten Pyren- oder Chrysenrest darstellt; Ar⁵ und Ar⁶ unabhängig eine substituierte oder substituierte einwertige aromatische Gruppe mit 6 bis 40 Kohlenstoffatomen darstellen, und p eine ganze Zahl von 1 bis 4 darstellt; und

(B) mindestens eine Verbindung, die aus Anthracenderivaten ausgewählt ist, die durch die folgende allgemeine Formel (II) dargestellt sind:



wobei

An einen substituierten oder unsubstituierten zweiwertigen Anthracenrest darstellt;

Ar³ und Ar⁴ jeweils unabhängig eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 40 Kohlenstoffatomen darstellen,
 mindestens eines von Ar³ und Ar⁴ eine substituierte oder unsubstituierte einwertige kondensierte aromatische Ringgruppe oder eine substituierte oder unsubstituierte Arylgruppe mit 10 oder mehr Kohlenstoffatomen darstellt,
 und Ar³ und Ar⁴ gleich oder verschieden sein können.

2. Elektrolumineszenzvorrichtung nach Anspruch 1, wobei das Anthracenderivat durch die Formel (II-a) dargestellt ist:




wobei An wie in Anspruch 1 definiert ist und X¹ und X² jeweils unabhängig einen einwertigen Rest von Naphthalin, Phenanthren, Fluoranthren, Anthracen, Pyren, Perylen, Coronen, Chrysen, Picen, Diphenylanthracen, Carbazol, Triphenylen, Rubicen, Benzanthracen, Phenylanthracen, Bisanthracen, Dianthracenylbenzol, oder Dibenzanthracen, der substituiert oder unsubstituiert sein kann, darstellen.

3. Elektrolumineszenzvorrichtung nach Anspruch 1 oder 2, wobei die durch Ar⁵ und Ar⁶ dargestellte einwertige aromatische Gruppe aus einer Phenylgruppe, Naphthylgruppe, Anthranylgruppe, Phenanthrylgruppe, Pyrenylgruppe, Coronylgruppe, Biphenylgruppe, Terphenylgruppe, Fluorenylgruppe, Furanylgruppe, Thienylgruppe, Benzothienylgruppe, Indolylgruppe und Carbazolylgruppe ausgewählt ist.

4. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 3, wobei der Substituent des durch X³ dargestellten Pyren- oder Chrysenrests aus Alkylgruppen mit 1 bis 6 Kohlenstoffatomen, Cycloalkylgruppen mit 3 bis 6 Kohlenstoffatomen, Alkoxygruppen mit 1 bis 6 Kohlenstoffatomen, Aryloxygruppen mit 5 bis 18 Kohlenstoffatomen, Aralkyloxygruppen mit 7 bis 18 Kohlenstoffatomen, Arylaminogruppen mit 5 bis 16 Kohlenstoffatomen, Nitrogruppen, Cyanogruppen, Estergruppen mit 1 bis 6 Kohlenstoffatomen und Halogenatomen ausgewählt ist, und der Substituent der durch Ar⁵ und Ar⁶ dargestellten einwertigen aromatischen Gruppe aus Alkylgruppen mit 1 bis 6 Kohlenstoffatomen, Cycloalkylgruppen mit 3 bis 6 Kohlenstoffatomen, Alkoxygruppen mit 1 bis 6 Kohlenstoffatomen, Aryloxygruppen mit 5 bis 18 Kohlenstoffatomen, Aralkyloxygruppen mit 7 bis 18 Kohlenstoffatomen, Arylaminogruppen mit 5 bis 16 Kohlenstoffatomen, Nitrogruppen, Cyanogruppen, Estergruppen mit 1 bis 6 Kohlenstoffatomen und Halogenatomen ausgewählt ist.

5. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 3, wobei die Arylaminverbindung durch die folgende allgemeine Formel (V-a) dargestellt ist:



wobei X³ wie in Anspruch 1 definiert ist;
 A¹⁵ bis A¹⁸ jeweils unabhängig ein Wasserstoffatom, eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Arylgruppe mit 5 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Aralkylgruppe mit 7 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Cycloalkylgruppe mit 3 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Alkoxygruppe mit 1 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Aryloxygruppe mit 5 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Arylaminogruppe mit 5 bis 50 Kohlenstoffatomen oder eine substituierte oder unsubstituierte Alkylaminogruppe mit 1 bis 20 Kohlenstoffatomen darstellen;


g, h, i und j jeweils eine ganze Zahl von 0 bis 5 darstellen;

n eine ganze Zahl von 0 bis 3 darstellt;

zwei oder mehrere der A¹⁵, A¹⁶, A¹⁷ und A¹⁸ gleich oder verschieden sein können und aneinander gebunden sein können, um einen gesättigten oder ungesättigten Ring zu bilden, wenn g, h, i und j jeweils eine ganze Zahl von 2 oder größer darstellen; und

mindestens eines von A¹⁵ bis A¹⁸ eine substituierte oder unsubstituierte sekundäre oder tertiäre Alkylgruppe mit 3 bis 10 Kohlenstoffatomen darstellt.

6. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 3, wobei die Arylaminverbindung durch die folgende allgemeine Formel (V-b) dargestellt ist:



wobei X³ einen substituierten oder unsubstituierten Pyren- oder Chrysenrest darstellt;

A¹⁵ bis A¹⁸ jeweils unabhängig ein Wasserstoffatom, eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Arylgruppe mit 5 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Aralkylgruppe mit 7 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Cycloalkylgruppe mit 3 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Alkoxygruppe mit 1 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Aryloxygruppe mit 5 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Arylaminogruppe mit 5 bis 50 Kohlenstoffatomen oder eine substituierte oder unsubstituierte Alkylaminogruppe mit 1 bis 20 Kohlenstoffatomen darstellen;

g, h, i und j jeweils eine ganze Zahl von 0 bis 5 darstellen;

zwei oder mehrere der A¹⁵, A¹⁶, A¹⁷ und A¹⁸ gleich oder verschieden sein können und aneinander gebunden sein können, um einen gesättigten oder ungesättigten Ring zu bilden, wenn g, h, i und j jeweils eine ganze Zahl von 2 oder größer darstellen;

R²⁴ und R²⁵ jeweils unabhängig ein Wasserstoffatom, eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 10 Kohlenstoffatomen, eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 20 Kohlenstoffatomen, eine substituierte oder unsubstituierte Aralkylgruppe mit 7 bis 50 Kohlenstoffatomen, eine substituierte oder unsubstituierte Alkoxygruppe mit 1 bis 50 Kohlenstoffatomen oder eine substituierte oder unsubstituierte Aryloxygruppe mit 5 bis 50 Kohlenstoffatomen darstellen;

k und m jeweils eine ganze Zahl von 0 bis 2 darstellen; und


mindestens eines von R²⁴ und R²⁵ eine substituierte oder unsubstituierte sekundäre oder tertiäre Alkylgruppe mit 3 bis 10 Kohlenstoffatomen darstellt.

7. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 6, wobei das Verhältnis der gewichtsbezogenen Menge von Komponente (A) zu der gewichtsbezogenen Menge von Komponente (B) in einem Bereich von 1:99 bis 20:80 liegt.
8. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 7, wobei eine Schicht von einem Chalkogenid, eine Schicht von einem Metallhalogenid oder eine Schicht von einem Metalloxid auf mindestens einer Oberfläche des Paares von Elektroden angeordnet ist.
9. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 8, wobei eine gemischte Region umfassend ein reduzierendes Dotierungsmittel und organische Substanzen oder eine gemischte Region umfassend ein oxidierendes Dotierungsmittel und organische Substanzen auf mindestens einer Oberfläche des Paares von Elektroden angeordnet ist.

10. Elektrolumineszenzvorrichtung nach einem der Ansprüche 1 bis 9, wobei die Schicht von einem organischen lichtemittierenden Medium eine Dicke in einem Bereich von 10 bis 400 nm hat.

11. Organisches lichtemittierendes Medium, welches folgendes umfasst:

(A) eine durch die allgemeine Formel (V) dargestellte Arylaminverbindung



wobei

X³ einen substituierten oder unsubstituierten Pyren- oder Chrysenrest darstellt; Ar⁵ und Ar⁶ jeweils unabhängig eine substituierte oder unsubstituierte einwertige aromatische Gruppe mit 6 bis 40 Kohlenstoffatomen darstellen, und p eine ganze Zahl von 1 bis 4 darstellt; und

(B) mindestens eine Verbindung, die aus Anthracenderivaten ausgewählt ist, die durch die folgende allgemeine Formel (II) dargestellt sind:



wobei

An einen substituierten oder unsubstituierten zweiwertigen Anthracenrest darstellt;

Ar³ und Ar⁴ jeweils unabhängig eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 40 Kohlenstoffatomen darstellen,


mindestens eines von Ar³ und Ar⁴ eine substituierte oder unsubstituierte einwertige kondensierte aromatische Ringgruppe oder eine substituierte oder unsubstituierte Arylgruppe mit 10 oder mehr Kohlenstoffatomen darstellt,

und Ar³ und Ar⁴ voneinander gleich oder verschieden sein können.

Revendications

1. Dispositif électroluminescent comprenant un pair d'électrodes et une couche d'un milieu organique émettant de la lumière qui est disposée entre le pair d'électrodes, dans lequel la couche du milieu organique émettant de la lumière comprend:

(A) un composé arylamine représenté par la formule générale suivante (V):



dans lequel

X^3 représente un résidu de pyrène ou chrysène substitué ou non substitué;

Ar^5 et Ar^6 chaqu'un indépendamment représentent un groupe substitué ou non substitué monovalent aromatique ayant 6 à 40 atomes de carbone, et

p représente un nombre entier de 1 à 4; et

(B) au moins un composé sélectionné parmi des dérivés d'anthracène représentés par la formule générale suivante (II):



dans lequel An représente un résidu d'anthracène bivalent substitué ou non substitué;

Ar^3 et Ar^4 chaqu'un représente indépendamment un groupe aryle substitué ou non substitué ayant 6 à 40 atomes de carbone,

au moins l'un de Ar^3 et Ar^4 représente un groupe annulaire substitué ou non substitué monovalent fusionné ou un groupe aryle substitué ou non substitué ayant 10 atomes de carbone ou plus, et Ar^3 et Ar^4 peuvent être égaux ou différents.

2. Dispositif électroluminescent selon la revendication 1, dans lequel le dérivé anthracène est représenté par la formule (II-a):




dans lequel An est défini tel que dans la revendication 1 et X^1 et X^2 chaqu'un indépendamment représentent un résidu de naphthalène, phénanthrène, fluoranthène, anthracène, pyrène, perylène, coronène, chrysène, picène, diphenylanthracène, carbazole, triphénylène, rubicène, benzoanthracène, phenylanthracène, bisanthracène, dianthracenylbenzène ou dibenzoanthracène, qui peut être substitué ou non substitué.

3. Dispositif électroluminescent selon la revendication 1 ou 2, dans lequel le groupe aromatique monovalent représenté par Ar^5 et Ar^6 est sélectionné parmi un groupe phényle, un groupe naphthyle, un groupe anthranyle, un groupe phenantryle, un groupe pyrenyle, un groupe coronyle, un groupe biphenyle, un groupe terphenyle, un groupe fluorenyle, un groupe furanyle, un groupe thienyle, un groupe benzothiényne, un groupe indolyle, et un groupe carbazolyle.

4. Dispositif électroluminescent selon l'une des revendications 1 à 3, dans lequel le substituent du résidu de pyrène ou chrysène représenté par X^3 est sélectionné parmi les groupes alkyle ayant 1 à 6 atomes de carbone, les groupes cycloalkyle ayant 3 à 6 atomes de carbone, les groupes alkoxy ayant 1 à 6 atomes de carbone, les groupes aryloxy ayant 5 à 18 atomes de carbone, les groupes aralkyloxy ayant 7 à 18 atomes de carbone, les groupes arylamino ayant 5 à 16 atomes de carbone, les groupes nitro, les groupes cyano, les groupes ester ayant 1 à 6 atomes de carbone et des atomes d'halogène, et

le substituent du groupe aromatique monovalent représenté par Ar^5 et Ar^6 est sélectionné parmi les groupes alkyle ayant 1 à 6 atomes de carbone, les groupes cycloalkyle ayant 3 à 6 atomes de carbone, les groupes alkoxy ayant 1 à 6 atomes de carbone, les groupes aryloxy ayant 5 à 18 atomes de carbone, les groupes aralkyloxy ayant 7 à 18 atomes de carbone, les groupes arylamino ayant 5 à 16 atomes de carbone, les groupes nitro, les groupes cyano, les groupes ester ayant 1 à 6 atomes de carbone et les atomes d'halogène.

5. Dispositif électroluminescent selon une des revendications 1 à 3, dans lequel le composé d'arylamine est représenté par la formule générale suivante (V-a):




20 dans lequel X^3 est défini tel que dans la revendication 1;

A^{15} à A^{18} chaqu'un indépendamment représentent un atome d'hydrogène, un groupe alkyle substitué ou non substitué ayant 1 à 50 atomes de carbone, un groupe aryle substitué ou non substitué ayant 5 à 50 atomes de carbone, un groupe aralkyle substitué ou non substitué ayant 7 à 50 atomes de carbone, un groupe cycloalkyle substitué ou non substitué ayant 3 à 50 atomes de carbone, un groupe alkoxy ayant 1 à 50 atomes de carbone, un groupe aryloxy substitué ou non substitué ayant 5 à 50 atomes de carbone, un groupe arylamino substitué ou non substitué ayant 5 à 50 atomes de carbone ou un groupe alkylamino substitué ou non substitué ayant 1 à 20 atomes de carbone, g , h , i et j chaqu'un représente un nombre entier de 0 à 5;

n représente un nombre entier de 0 à 3;

25 deux ou plusieurs des A^{15} , A^{16} , A^{17} et A^{18} peuvent être égaux ou différents et peuvent être liés l'un à l'autre pour former un anneau saturé ou non saturé, lorsque g , h , i et j chaqu'un représente un nombre entier de 2 ou plus grand; et au moins l'un de A^{15} à A^{18} représente un groupe alkyle secondaire ou tertiaire substitué ou non substitué ayant 3 à 10 atomes de carbone.

- 30 6. Dispositif électroluminescent selon l'une des revendications 1 à 3, dans lequel le composé arylamine est représenté parmi la formule générale suivante Formel (V-b):



45 dans lequel X^3 représente un résidu pyrène ou chrysène substitué ou non substitué;

A^{15} à A^{18} chaqu'un indépendamment représentent un atome d'hydrogène, un groupe alkyle substitué ou non substitué ayant 1 à 50 atomes de carbone, un groupe aryle substitué ou non substitué ayant 5 à 50 atomes de carbone, un groupe aralkyle substitué ou non substitué ayant 7 à 50 atomes de carbone, un groupe cycloalkyle substitué ou non substitué ayant 3 à 50 atomes de carbone, un groupe alkoxy ayant 1 à 50 atomes de carbone, un groupe aryloxy substitué ou non substitué ayant 5 à 50 atomes de carbone, un groupe arylamino substitué ou non substitué ayant 5 à 50 atomes de carbone ou un groupe alkylamino substitué ou non substitué ayant 1 à 20 atomes de carbone, g , h , i et j chaqu'un représente un nombre entier de 0 à 5;

50 deux ou plusieurs des A^{15} , A^{16} , A^{17} et A^{18} peuvent être égaux ou différents et peuvent être liés l'un à l'autre pour former un anneau saturé ou non saturé, lorsque g , h , i et j chaqu'un représente un nombre entier de 2 ou supérieur; R^{24} et R^{25} chaqu'un indépendamment représente un atome d'hydrogène, un groupe alkyle substitué ou non substitué ayant 1 à 10 atomes de carbone, un groupe aryle substitué ou non substitué ayant 6 à 20 atomes de carbone, un groupe aralkyle substitué ou non substitué ayant 7 à 50 atomes de carbone, un groupe alkoxy substitué ou non

substitué ayant 1 à 50 atomes de carbone ou un groupe aryloxy substitué ou non substitué ayant 5 à 50 atomes de carbone;

k et m chacun représente un nombre entier de 0 à 2; et

au moins l'un de R²⁴ et R²⁵ représente un groupe alkyle substitué ou non substitué secondaire ou tertiaire ayant 3 à 10 atomes de carbone.

7. Dispositif électroluminescent selon l'une des revendications 1 à 6, dans lequel le rapport de la quantité par poids du composant (A) à la quantité par poids du composé (B) est dans la gamme de 1:99 à 20:80.


8. Dispositif électroluminescent selon l'une des revendications 1 à 7, dans lequel une couche de chalcogénure, une couche d'halogénure de métal ou une couche d'oxyde de métal est disposée sur au moins une surface de la paire d'électrodes.

9. Dispositif électroluminescent selon l'une des revendications 1 à 8, dans lequel une région mixte comprenant un dopant réductif et des substances organiques ou une région mixte comprenant un dopant oxydatif et des substances organiques est disposée sur au moins une surface de la paire d'électrodes.

10. Dispositif électroluminescent selon l'une des revendications 1 à 9, dans lequel la couche du milieu organique émettant de la lumière a une épaisseur dans la gamme de 10 à 400 nm.

11. Milieu organique émettant de la lumière comprenant:

(A) un composé arylamine représenté par la formule générale suivante (V):



dans lequel

X³ représente un résidu de pyrène ou chrysène substitué ou non substitué;

Ar⁵ et Ar⁶ indépendamment représentent un groupe substitué ou non substitué monovalent aromatique ayant 6 à 40 atomes de carbone, et

p représente un nombre entier de 1 à 4; et

(B) au moins un composé sélectionné parmi des dérivés d'anthracène représenté par la formule générale suivante (II):



dans lequel An représente un résidu d'anthracène bivalent substitué ou non substitué;

Ar³ et Ar⁴ chacun représente indépendamment un groupe aryle substitué ou non substitué ayant 6 à 40 atomes de carbone,

au moins l'un de Ar³ et Ar⁴ représente un groupe annulaire substitué ou non substitué monovalent fusionné ou un groupe aryle substitué ou non substitué ayant 10 atomes de carbone ou plus,

et Ar³ et Ar⁴ peuvent être égaux ou différents.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP HEISEI81996239655 B [0005]
- JP HEISEI71995138561 B [0005]
- JP HEISEI31991200289 B [0005]
- US 3008897 A [0006]
- JP HEISEI8199612600 B [0006]
- JP 2001207167 A [0006]
- JP SHOWA57198251781 B [0070]

Non-patent literature cited in the description

- **C. W. Tang ; S. A. Vanslyke.** *Applied Physics Letters*, 1987, vol. 51, 913 [0003]