



(11) **EP 2 208 770 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Claims EN 1

(48) Corrigendum issued on:
31.10.2012 Bulletin 2012/44

(45) Date of publication and mention
of the grant of the patent:
01.08.2012 Bulletin 2012/31

(21) Application number: **08792334.8**

(22) Date of filing: **08.08.2008**

(51) Int Cl.:
C09K 3/18 (2006.01) **C08K 5/205** (2006.01)
C08L 33/14 (2006.01) **D06M 15/277** (2006.01)
C08F 220/10 (2006.01) **C08F 220/24** (2006.01)
D06M 15/227 (2006.01) **D06M 15/256** (2006.01)
D06M 15/273 (2006.01) **D06M 15/576** (2006.01)
C08F 214/18 (2006.01) **C09D 133/16** (2006.01)

(86) International application number:
PCT/JP2008/064277

(87) International publication number:
WO 2009/054176 (30.04.2009 Gazette 2009/18)

(54) **WATER-REPELLENT OIL-REPELLENT AGENT**

HYDRO- UND OLEOPHOBIERMITTEL
AGENT HYDROPHOBE ET OLÉOPHOBE

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT
RO SE SI SK TR**

(30) Priority: **22.10.2007 JP 2007273280**

(43) Date of publication of application:
21.07.2010 Bulletin 2010/29

(73) Proprietor: **Unimatec Co., Ltd.**
Tokyo 105-8585 (JP)

(72) Inventors:
• **JIN, Ji-Shan**
Kitaibaraki-shi
Ibaraki 319-1544 (JP)
• **MOURI, Sumiko**
Kitaibaraki-shi
Ibaraki 319-1544 (JP)

• **SATO, Katsuyuki**
Kitaibaraki-shi
Ibaraki 319-1544 (JP)

(74) Representative: **Albrecht, Thomas et al**
Kraus & Weisert
Patent- und Rechtsanwälte
Thomas-Wimmer-Ring 15
80539 München (DE)

(56) References cited:
EP-A1- 1 174 484 EP-A1- 1 770 146
EP-A1- 1 788 047 WO-A1-2005/105872
WO-A1-2006/022122 JP-A- 2005 344 032

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

EP 2 208 770 B9

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[Technical Field]

5 **[0001]** The present invention relates to a water- and oil-repellent. More specifically, the present invention relates to a water- and oil-repellent of which washing resistance is improved.

[Background Art]

10 **[0002]** The expression of water- and oil-repellency results from the low surface energy of fluorine, and, usually, fluorine-containing acrylate polymers are widely used as active ingredients of water- and oil-repellents. Previous various investigations have shown that the presence of crystallinity in a fluorine-containing polymer is necessary for expressing water- and oil-repellency in practical applications. In particular, it has been recognized that the hydrophobicity of a fluorine-containing polymer depends on the number of carbon atoms of a side-chain fluoroalkyl group and that the expression
15 of crystallinity is observed when the number of carbon atoms is eight or more.

[Non-Patent Document 1] Secchaku (Adhesion), Vol. 50, No. 5, pp. 16-22 (2006)

[0003] Therefore, it has been regarded that a fluorine-containing polymer having a short fluoroalkyl group, i.e., a side-chain fluoroalkyl group having 7 or less, in particular, 6 or less carbon atoms, is low in or does not have crystallinity and thereby cannot provide water-repellent performance that is sufficient for practical use. In addition, since water- and oil-repellents are required to have washing resistance and abrasion resistance, fluorine-containing acrylic polymers having
20 long side chains are used.

[0004] However, polymers including a side-chain fluoroalkyl group having 8 or more carbon atoms are very hard due to their high crystallinity and have a problem that flexibility of textile products is impaired. Furthermore, since the water-repellent process needs high curing temperature, there are problems such as a change in color of fibers. In addition,
25 since a long side-chain having 8 or more carbon atoms is excessively hydrophobic, a large amount of an emulsifier is necessary for producing a water- and oil-repellent.

[0005] The present applicant has before proposed a water- and oil-repellent composed of an aqueous emulsion in which a copolymer of a fluoroalkyl group-containing polymerizable monomer and vinylidene chloride or benzyl (meth)acrylate, and a carboxyl group-containing water-soluble polymer are dispersed in water using a nonionic surfactant. The
30 fluoroalkyl group of a fluoroalkyl group-containing polymerizable monomer that is copolymerized with vinylidene chloride or benzyl (meth)acrylate is recognized to be a perfluoroalkyl group having 4 to 20 carbon atoms, but the perfluoroalkyl group used in the above-mentioned polymerization example is recognized to be a mixture of perfluoroalkyl groups having 6 to 14 carbon atoms, 9.0 on average.

[Patent Document 1] JP-A-11-80710

[0006] Furthermore, as a water-dispersible water- and oil-repellent composition in which both the repeated washing resistance and the water pressure resistance of water- and oil-repellency are achieved, a water-dispersible water- and oil-repellent composition including as active ingredients (A) a fluorine-containing copolymer having a hydroxyl group,
35 (B) a fluorine-containing copolymer having an epoxy group, (C) a compound having a blocked isocyanate group and not having a carbon-carbon unsaturated bond, and (D) an amino resin has been proposed. The fluorine-containing copolymers having the hydroxyl group or the epoxy group are each a copolymer of a polymerizable monomer having a polyfluoroalkyl group, wherein the number of carbon atoms of the perfluoroalkyl group of a perfluoroalkylalkyl group is 2 to 20, preferably 6 to 16. A perfluoropentyl group and a perfluorohexyl group are shown as examples, and in the
40 Examples, a mixture of $F(CF_2)_m$ groups of which m is from 6 to 16 and is 9 on average is used.

[Patent Document 2] WO 00/58416

[0007] Accordingly, it is believed that a water- and oil-repellent showing excellent in flexibility and also excellent in washing resistance can be obtained if water- and oil-repellency can be expressed with a fluorine-containing polymer including a short fluoroalkyl group having 6 or less carbon atoms.

[0008] Furthermore, acrylic acid derivatives of perfluoroalkylalkyl alcohol, for example, $CF_3(CF_2)_7CH_2CH_2OCOCH=CH_2$, are widely used as synthetic monomers for fluorine-containing copolymer that forms a
50 water- and oil-repellent for fiber, but recently, it has been reported that among these types of compounds, compounds including perfluoroalkyl groups having approximately 8 carbon atoms are high in bioaccumulation potential and therefore have an environmental problem. Accordingly, it is concerned that the manufacturing and the use of these compounds will become difficult in the future. However, compounds including perfluoroalkyl groups having 6 or less carbon atoms are recognized to be low in bioaccumulation potential.

[0009] It has been also proposed a surface-treating agent showing excellent water repellency, oil repellency, and antifouling property by using a polymer having a short fluoroalkyl group having 1 to 6 carbon atoms as the side chain, but the fluoroalkyl group-containing monomer used therein is a fluorine-containing monomer compound represented by the general formula:



X: F, Cl, Br, I, CFX¹X², CN, a fluoroalkyl group having 1 to 20 carbon atoms, benzyl group, or phenyl group,
 Y: an aliphatic group having 1 to 10 carbon atoms, an aromatic or alicyclic group having 6 to 10 carbon atoms, a
 CH₂CH₂NR¹SO₂ group, or a CH₂CH(OY¹)CH₂ group, and
 Rf: a fluoroalkyl group having 1 to 6 carbon atoms.

Acrylic acid derivatives in which X is H are shown as comparative manufacturing examples, and methacrylic acid derivatives in which X is CH₃ are intendedly excluded.

[Patent Document 3] JP-A-2004-352976

[0010] Furthermore, it has been proposed a water- and oil-repellent composition of which essential component is a copolymer containing as a polymerization unit (a) an Rf group-containing monomer of which homopolymer does not have a melting point derived from the Rf group in the microcrystals or has a melting point of 55°C or less and has a glass transition point of 20°C or more and (b) an Rf group-free monomer having a cross-linkable functional group, wherein the composition can impart excellent water- and oil-repellency to products, even in low temperature treatment, and also can perform a water- and oil-repellent process with providing soft textile feeling and also excellent durability.

[Patent Document 4] WO 2004/035708

[0011] In the above, a perfluoroalkylalkyl (meth)acrylate is used as the component monomer (a), but a specific monomer, such as a 2-butanone oxime adduct, pyrazole adduct, or ε-caprolactam adduct of a ω-isocyanate alkyl(meth)acrylate, is used as the component monomer (b) in the copolymerization reaction.

[0012] Furthermore, the use of water- and oil-repellency processing treatment is extended to the outdoor field such as sportswear, and the water- and oil-repellency is required to be durable to repeated washing in such an application field. However, though the above-mentioned Patent Document 2 describes the water-dispersible water- and oil-repellent composition as that in which both the repeated washing resistance and the water resistance of water- and oil-repellency are achieved, a fluorine-containing copolymer including a perfluoroalkyl group having 6 or less carbon atom is not substantially used alone, and also the water-dispersible water- and oil-repellent composition can not impart sufficient water- and oil-repellency not only to synthetic fibers but also to natural fibers when it is used for water- and oil-repellency treatment.

[Disclosure of the Invention]


[Problems to be Solved by the Invention]

[0013] It is an object of the present invention to provide a water- and oil-repellent that includes, as an active ingredient, a copolymer of a perfluoroalkylalkyl (meth)acrylate being low in bioaccumulation potential, and can impart sufficient water- and oil-repellency not only to synthetic fibers but also to natural fibers, and is also improved in washing resistance.

[Means for Solving the Problems]

[0014] Such an object of the present invention is achieved by a water- and oil-repellent comprising an aqueous dispersion of a fluorine-containing copolymer including as a copolymerization unit

(a) at least one of perfluoroalkylalkyl acrylates and corresponding methacrylates represented by the general formula:



(wherein R represents hydrogen atom or methyl group; n represents 4, 5, or 6; and m represents 1, 2, 3, or 4),

(b) benzyl acrylate or benzyl methacrylate,

(c) vinylidene chloride and

(d) a cross-linkable group-containing polymerizable monomer;

and


a blocked isocyanate added to the aqueous dispersion in a weight ratio of 0.05 to 3.0 to the weight of the solid content of the aqueous dispersion.

[Effect of the Invention]

[0015] The water- and oil-repellent according to the present invention is a water- and oil-repellent of which an active ingredient is a copolymer of a perfluoroalkylalkyl (meth)acrylate being low in bioaccumulation potential, wherein the copolymer is not that in which a specific monomer is copolymerized; the curing temperature in water- and oil-repellent treatment using the copolymer as an active ingredient is low; and excellent textile feeling can be imparted to a water- and oil-repellent-treated fabric. In particular, the water- and oil-repellent can impart sufficient water- and oil-repellency not only to synthetic fibers but also to natural fibers, and is also excellent in washing resistance.

[Best Mode for Carrying Out the Invention]

[0016] Preferred examples of the component (a), perfluoroalkylalkyl (meth)acrylate, represented by the general formula:





R: a hydrogen atom or a methyl group

n: 4, 5, or 6

m: 1, 2, 3, or 4

include the following compounds:



and




[0017] The component (a), perfluoroalkylalkyl (meth)acrylate, is supplied to a copolymerization reaction in such a ratio that its proportion in the resulting copolymer is about 10 to 80% by weight, preferably about 25 to 80% by weight, and more preferably about 40 to 80% by weight. By the copolymerization of such a monomer component (a), an aqueous dispersion showing excellent emulsion stability can be formed, and water- and oil-repellency is expressed.

[0018] The component (b), benzyl acrylate or benzyl methacrylate, is supplied to the copolymerization reaction in such a ratio that its proportion in the resulting copolymer is about 5 to 80% by weight, preferably about 5 to 50% by weight, and more preferably about 5 to 35% by weight. By the copolymerization of the benzyl (meth)acrylate, the copolymer shows a good film-forming property and orientation.

[0019] As the component (c), vinylidene chlorides is used.

[0020] The fluorine-free polymerizable monomer other than benzyl (meth)acrylates is supplied to the copolymerization reaction in such a ratio that its proportion in the resulting copolymer is about 5 to 80% by weight, preferably about 5 to 60% by weight, and more preferably about 5 to 40% by weight.

[0021] Examples of the component (d), cross-linkable group-containing polymerizable monomer, include epoxy group-containing monomers such as allyl glycidyl ether and glycidyl (meth)acrylate; N-methylol group-containing monomers such as N-methylol (meth)acrylamide and N-butoxymethylol (meth)acrylamide; hydroxyalkyl group-containing monomers such as 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl acrylate, 4-hydroxybutyl acrylate, and 2-hydroxy-3-chloropropyl (meth)acrylate; amide group-containing monomers such as (meth)acrylamide, N-methyl acrylamide, diacetone acrylamide; and compounds represented by the formula:



or



aziridinyl group-containing monomers such as aziridinylethyl (meth)acrylate; and polyol poly(meth)acrylates such as

ethylene glycol di(meth)acrylate, polyoxyethylene di(meth)acrylate, and polyoxypropylene glycol di(meth)acrylate. Hydrophilic monomers are preferably used.


[0022] Further copolymerization of the cross-linkable group-containing polymerizable monomer strengthens the adhesion, to base materials such as fibers, of the fluorine-containing copolymer used as an active component for water- and oil-repellency; also shows an effect of improving, for example, the durability, washing resistance, and dry-cleaning resistance of the water- and oil-repellent; and also usually gives a secondary effect of improving the polymerization stability during emulsion polymerization. Therefore, the component (d) is used in such a ratio that its proportion in the copolymer is about 0.5 to 40% by weight and preferably about 1 to 15% by weight.

[0023] The copolymerization reaction using these polymerizable monomers is performed by emulsion polymerization in the presence of a surface-active emulsifier composed of a polyethylene oxide adduct type cationic surfactant or of both said cationic surfactant and a polyethylene oxide adduct type nonionic surfactant and in the presence of an emulsifying aid composed of a glycol-based compound. The ratio of the surface-active emulsifier is about 1 to 20% by weight and preferably about 1 to 10% by weight, and the ratio of the emulsifying aid is about 10 to 100% by weight and preferably about 15 to 70% by weight, based on the total amount of the monomers for the copolymerization.

[0024] As such a cationic surfactant, a polyethylene oxide adduct of a quaternary ammonium-based surfactant, for example, an alkylammonium chloride or alkylpyridinium salt having 1 to 3 polyoxyethylene groups, is used. On this occasion, a cationic surfactant without the polyethylene oxide, for example, a quaternary ammonium-based surfactant, can be simultaneously used. In such a case, the weight ratio is preferably about 0.1 to 2 to the polyethylene oxide adduct type.

[0025] In addition, as the polyethylene oxide adduct type nonionic surfactant simultaneously used with the cationic surfactant, for example, a reaction product of a polyethylene oxide with an alcohol such as an aliphatic alcohol or an aromatic alcohol, an alkyl ether, oleic acid, a C₁₂ to C₁₈ alkylamine, or sorbitan mono fatty acid is used in a ratio of about 80% by weight or less and preferably about 30 to 80% by weight in the total amount with the polyethylene oxide adduct type cationic surfactant.

[0026] Here, instead of the cationic surfactant, those in which an amine compound having a polyethylene oxide chain, for example, a polyoxyethylene octadecylamine (such as Amiet-320, a Kao product), a polyoxyethylene alkyldiamine (such as Esoduomin T/25, a Lion product) represented by the general formula:



or a polyoxyethylene dodecylamine (such as Nymeen L-207, a NOF product) is neutralized with an organic acid such as acetic acid can be used.

[0027] Examples of the glycol compound as the emulsifying aid used in a combination with the emulsifier include ethylene glycol, polyethylene (n=2 to 4 or more) glycol, propylene glycol, polypropylene (n=2 to 4 or more) glycol, their terminal monomethyl ethers, hexylene glycol, and propylene glycol adducts of glycerin. A polypropylene glycol-based compound having a molecular weight of about 300 to 3000 or hexylene glycol is preferably used.

[0028] Prior to the copolymerization reaction, a polymerizable monomer mixture containing a perfluoroalkylalkyl (meth)acrylate and another polymerizable monomer is subjected to emulsification treatment in the presence of a surface-active emulsifier and an emulsifying aid. The emulsification treatment is sufficiently carried out using a high-pressure homogenizer or the like.

[0029] The copolymerization reaction of the emulsified polymerizable monomer mixture is performed in the presence of a radical polymerization initiator added to the reaction system. The radical polymerization initiator may be any of organic peroxides, azo compounds, and persulfates. Preferably, a water-soluble organic peroxide, for example, 2,2'-azobis(2-amidinopropane)-dihydrochloride, is used in a ratio of about 0.1 to 10% by weight and preferably about 0.5 to 7% by weight to the total weight of the polymerizable monomer mixture.

[0030] The copolymerization reaction is carried out in an aqueous solvent at about 40 to 80°C for about 1 to 10 hours to form an aqueous dispersion (aqueous emulsion) serving as a stock solution having a solid content concentration of about 15 to 35% by weight. As the aqueous solvent, in addition to the use of water alone, preferably used an aqueous solvents containing about 1 to 30% by weight of a water-soluble organic solvent, for example, a ketone such as acetone or methyl ethyl ketone, an alcohol such as methanol or ethanol, or a glycol such as ethylene glycol, propylene glycol, dipropylene glycol, a monomethyl ether thereof, or a tripropylene glycol. In the reaction, a molecular weight modifier may be used, and, for example, an alkyl mercaptan such as n-octyl mercaptan, n-dodecyl mercaptan, or tertiary dodecyl mercaptan is preferably used.

[0031] To the resulting aqueous dispersion (aqueous emulsion), a blocked isocyanate is added as a cross-linking agent in a weight ratio of 0.05 to 3.0, preferably 0.2 to 2.0, to the weight of solid content of the aqueous dispersion. The blocked isocyanate can impart excellent water-repellency and high washing resistance to also natural fibers such as cotton. When the amount of the blocked isocyanate is lower than the above-mentioned ratio, the washing resistance is decreased. On the other hand, when the blocked isocyanate is used in an amount higher than the ratio, the textile feeling

of a fabric is deteriorated.

[Patent Document 5] WO 2005/118737

5 **[0032]** The blocked isocyanate herein is a compound having one or more blocked isocyanate group and not having a polymerizable carbon-carbon unsaturated bond, i.e., a compound having a structure in which the isocyanate group is blocked with a blocking agent. As such a blocked isocyanate, a preferred structure is obtained by reacting a polyisocyanate and a compound having two or more active hydrogen atoms in a molecule thereof and blocking the isocyanate group of the resulting compound with a blocking agent.

10 **[0033]** Examples of the polyisocyanate include aromatic isocyanates such as 4,4'-diphenylmethane diisocyanate, 2,4'-diphenylmethane diisocyanate, and tolylene diisocyanate; aliphatic isocyanates such as trimethylene diisocyanate, tetramethylene diisocyanate, pentamethylene diisocyanate, hexamethylene diisocyanate, 1,2-propane diisocyanate, 1,2-butane diisocyanate, trimethylhexamethylene diisocyanate, isophorone diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, and cyclohexylene diisocyanate; and their isocyanurate modified compounds, prepolymer modified compounds, biuret modified compounds, and allophanate modified compounds.

15 **[0034]** The compound having two or more active hydrogen atoms in the molecule is preferably a polyol or a polyamine. Examples of the polyol include ethylene glycol, propylene glycol, butanediols, pentanediols, hexanediols, glycerin, trimethylolpropane, pentaerythritol, sorbitol, neopentyl glycol, bisphenol A, xylylene glycol, and at least one of modified compounds of these alcohols. Examples of the polyamine include hexamethylenediamine and 3,3'-iminobispropylamine. The polyol herein may be a polyester polyol, and as the polyester polyol, those having an ester bond obtained by a reaction of a polyol and a polyvalent carboxylic acid such as phthalic acid, adipic acid, fumaric acid, pyromellitic acid, trimellitic acid, aliphatic dicarboxylic acid, or a derivative thereof are used.

20 **[0035]** As the blocking agent for the isocyanate, alkyl ketone oximes, phenols, alcohols, β -diketones, and lactams are used, and preferably, methyl ethyl ketone oxime, ϵ -caprolactam, phenol, cresol, acetylacetone, diethyl malonate, isopropyl alcohol, tert-butyl alcohol, and maleic acid imide, more preferably compounds having a dissociation temperature of from 120 to 180°C represented by dialkyl ketone oximes such as methyl ethyl ketone oxime and lactams such as ϵ -caprolactam are used.

25 **[0036]** The blocked isocyanate is obtained by, as described above, reacting a polyol to an isocyanate compound and then reacting the resulting compound to a blocking agent. These reactions are preferably performed in a non-aqueous solvent such as ketones, ethers, or hydrocarbons. In addition, it is preferable that the equivalent weights of the isocyanate compound, the compound having two or more active hydrogen atoms, and the blocking agent become equal to one another at the time of completion of all the reactions.

30 **[0037]** After the above-described blocking reaction, the blocked isocyanate is preferably emulsified with water and a nonionic emulsifier, a nonionic/cationic emulsifier, or a nonionic/anionic emulsifier, in particular, a nonionic/cationic emulsifier. The solvent is removed after the emulsification, according to need.

35 **[0038]** As the blocked isocyanate, commercially available products, for example, RucoGuard XTS, a Rudolf product; RucoGuard WEB, a Rudolf product; NK Assist-NY, a Nikka Chemical product; NK Assist-V, a Nikka Chemical product; NK Assist-FU, a Nikka Chemical product; Prominate XC-830, a Gantsu Chemical product; Prominate XC-915, a Gantsu Chemical product; Prominate XC-950, a Gantsu Chemical product; and Elastron BN-69, a Daiichi Kogyo Seiyaku product can be used as such.

40 **[0039]** The aqueous dispersion can further contain other additives indispensable for the water- and oil-repellent use, for example, a cross-linking agent other than the blocked isocyanate, such as a melamine resin or a urea resin, a polymer extender, another water-repellent such as a silicone resin or oil, or wax, an insecticide, an antistatic agent, a dye stabilizer, an anticreasing agent, and a stain blocker.

45 **[0040]** The thus obtained aqueous dispersion containing the block isocyanate is diluted with water, preferably with ion-exchanged water to give a solid content concentration of about 0.1 to 10% by weight, and then is effectively applied, as a water- and oil-repellent, to, for example, fibers, a fabric, a woven fabric, paper, a film, a carpet, or a fabric product made of filaments, threads, or fibers. The application is performed by coating, dipping, spraying, padding, roll coating, or a combination thereof. For example, a bath containing a solid content in a concentration of about 0.1 to 10% by weight is used as a pad bath. A material to be treated is padded in this pad bath and is then subjected to removal of excessive liquid with a squeezing roller, followed by drying, thereby allowing the fluorine-containing copolymer to adhere to the material to be treated in a ratio of about 0.01 to 10% by weight to the amount of the material. Subsequently, drying, which varies depending on the type of the material to be treated, is usually conducted at about 100 to 120°C for about 50 from 1 minute to 2 hours to complete the water- and oil-repellent treatment.

[Examples]

55 **[0041]** Next, the present invention will be described with reference to Examples. Note that percentage in parentheses means % by weight.

Reference Example 1

[0042]

5	2-(n-Perfluorohexyl)ethyl methacrylate	58.3 g (45.6%)
	Benzyl methacrylate	29.2 g (22.8%)
	2-Hydroxyethyl methacrylate	5.6 g (4.4%)
	Polyethylene glycol (n=4) monomethacrylate (PE-200, a NOF product)	11.7 g (9.1%)
10	Lauryl mercaptan (chain transfer agent)	0.5 g
	Polyoxyethylene polycyclic phenyl ether (surfactant) (Newcol-740, a Nippon Nyukazai product)	7.0 g
	Hexylene glycol (emulsifying aid)	35.0 g
15	Ion-exchanged water	267.1 g

[0043] The above-mentioned components were put in a 1-L glass reaction vessel and were mixed, and further subjected to emulsification mixing using a high-pressure homogenizer. The resulting emulsion was substituted by nitrogen gas for 30 minutes. Then, the inner temperature of the reaction vessel was gradually increased to 40°C, and then

20	vinylidene chloride	17.5 g (13.7%)
	N-methylol acrylamide (dissolved in 29.3 g of ion-exchanged water)	5.6 g (4.4%)
	2,2'-azobis(2-amidinopropane)-dihydrochloride (dissolved in 30.4 g of ion-exchanged water)	2.8 g

25 were added thereto (the total amount including 285.5 g of total ion-exchanged water was 500.0 g). Furthermore, the inner temperature was gradually increased to 70°C, followed by the reaction at the temperature for 4 hours. After the completion of the reaction and cooling, an aqueous dispersion having a solid content concentration of 25.0% by weight was obtained. The melting point (DSC method) of the copolymer separated from the aqueous dispersion was 45°C.

Reference Examples 2 to 4

30 **[0044]** In Reference Example 1, aqueous dispersions B to D each having a solid content concentration of 25.0% by weight (excluding Reference Example 2 in which the concentration is 25.3% by weight) were prepared by changing the kinds and the amounts of the comonomers (a) to (d) and the total amount of ion-exchanged water to those shown in Table 1. In Table 1, the melting points (DSC method) of the copolymers that are obtained by separating them from the aqueous dispersions are also shown.

Table 1

Comonomer	Reference Example 2		Reference Example 3		Reference Example 4		
	g	%	g	%	g	%	
45	Component (a)						
	FAMAC-6	78.5	61.5	100.6	79.1	62.8	49.2
	FAAC-6					15.7	12.3
	Component (b)						
	BzMA	22.4	17.6	7.4	5.8	22.4	17.6
50	Component (c)						
	PEGM	4.2	3.3	4.2	3.3	4.2	3.3
	VDC	11.2	8.8	3.8	3.0	11.2	8.8

55

EP 2 208 770 B9

(continued)

Component (d)							
5	HEA	5.6	4.4	5.6	4.4	5.6	4.4
	NMAM	5.6	4.4			5.6	4.4
	NMMA			5.6	4.4		
	Total amount of water (g)	323.5		327.5		327.2	
	Aqueous dispersion	B		C		D	
10	Copolymer melting point (°C)	44		46		44	

Notes

- FAMAC-6: 2-(perfluorohexyl)ethyl methacrylate
- FAAC-6: 2-(perfluorohexyl)ethyl acrylate
- 15 BzMA: benzyl methacrylate
- PEGM: polyethylene glycol (n=4) monomethacrylate (PE-200)
- VDC: vinylidene chloride
- HEA: 2-hydroxyethyl acrylate
- NMAM: N-methylol acrylamide
- 20 NMMA: N-methylol methacrylamide

Example 1

25 **[0045]** To 2.0 parts by weight (corresponding to 0.5 parts by weight of the solid content) of the aqueous dispersion A prepared in Reference Example 1, 0.375 parts by weight (corresponding to 0.15 parts by weight of the solid content) of an aqueous emulsion containing 2-butanone-o,o'[methylenebis(4,1-phenyleneaminocarboxy)]dioxime (abbreviation: MDI-BTO) as the blocked isocyanate were added, followed by dilution with 97.625 parts by weight of ion-exchanged water to give a water- and oil-repellent A.

30 Examples 2 to 4

[0046] In Example 1, a water- and oil-repellents B to D were prepared by using each of the aqueous dispersions B to D, respectively prepared in Reference Examples 2 to 4, in the same amount.

35 Example 5

[0047] In Example 1, a water- and oil-repellent E was prepared by changing the amount of the aqueous emulsion of MDI-BTO as the blocked isocyanate to 1.25 parts by weight and the amount of ion-exchanged water to 96.75 parts by weight.

40 Example 6

45 **[0048]** In Example 1, a water- and oil-repellent F was prepared by changing the amount of the aqueous emulsion of MDI-BTO as the blocked isocyanate to 0.125 parts by weight and the amount of ion-exchanged water to 97.875 parts by weight.

Comparative Example 1

50 **[0049]** A water- and oil-repellent G was prepared by diluting 2.0 parts by weight of the aqueous dispersion A, prepared in Reference Example 1, with 98.0 parts by weight of ion-exchanged water.

Comparative Examples 2 to 4

55 **[0050]** In Comparative Example 1, water- and oil-repellents H to J were prepared by using each of the aqueous dispersions B to D, respectively prepared in Reference Examples 2 to 4, in the same amount.

[0051] To the thus obtained water- and oil-repellents A-J a cotton fabric, a cotton/polyester blended fabric, a polyester fabric, or a nylon fabric was immersed therein for measuring water-repellency (according to JIS L 1092) and oil-repellency (according to AATCC-TM118-1992). The wet pick-ups after squeezing were 80% for the cotton fabric and 100% for the

EP 2 208 770 B9

cotton blended fabric, 40% for the polyester fabric, and 60% for the nylon fabric. The drying conditions were 80°C for 10 minutes, and the curing conditions were 150°C for 3 minutes, for all the fabrics.

[0052] The evaluation criteria for water-repellency were defined in conformity with the rules of the above-mentioned JIS.

5	Degree of water-repellency	Condition
	100	Showing no wet state and adhesion of water droplets on the surface
	90	Showing little adhesion of water droplets on the surface
	80	Partially showing separate wet state on the surface
10	70	Showing wet state on a half area of the surface
	50	Showing wet state on the entire surface
	0	Showing complete wet state on both surfaces

[0053] The evaluation criteria for oil-repellency were defined in conformity with the rules of the above-mentioned AATCC. A drop of a test solution was dropped onto an oil-repellent treated fabric, and conditions at 30 seconds after the dropping were investigated. When the test solution dropped was held on the fabric, a test using a test solution having a larger number was further conducted. The oil-repellency was evaluated with the test solution that was the limit for being held on the fabric and on the basis of the oil-repellency evaluation shown in the following table (when Nujol is not held at all (100%), it is defined 0).

15	Oil-repellency No.	Test solution	Surface tension (mN/m, 25°C)
	8	n-heptane	20.0
	7	n-octane	21.8
25	6	n-decane	23.5
	5	n-dodecane	25.0
	4	n-tetradecane	26.7
	3	n-hexadecane	27.3
30	2	Nujol/n-hexadecane (volume ratio: 65%:35%)	29.6
	1	Nujol	31.2

[Washing resistance test]

[0054] A cotton fabric, a cotton/polyester blend fabric, a polyester fabric, or a nylon fabric was each subjected to water- and oil-repellency treatment with each of the water- and oil-repellents A to J, as described above, and then washed 5 times or 10 times according to the water washing method defined by JIS L0217, Appendix Table 103 and then air-dried, followed by evaluation for water-repellency and oil-repellency. The evaluation results are shown in the form of water-repellency evaluation/oil-repellency evaluation in the following Table 2.

Table 2
Water-repellency evaluation/Oil-repellency evaluation

40	Example	Water- and oil-repellent Fabric	Cotton Fabric	Blended Fabric	Polyester Fabric	Nylon Fabric
			[Number of washing: 0 times]			
45	Example 1	A	100/1	100/4	100/4	100/5
	Example 2	B	100/4	100/5	100/5	100/6
	Example 3	C	100/5	100/5	100/6	100/6
	Example 4	D	100/5	100/5	100/6	100/6
50	Example 5	E	100/4	100/5	100/5	100/6
	Example 6	F	100/4	100/5	100/5	100/6
	Comp.Ex.1	G	100/1	100/4	100/4	100/5
	Comp.Ex.2	H	100/3	100/5	100/5	100/6
55	Comp.Ex.3	I	100/5	100/5	100/6	100/6
	Comp.Ex.4	J	100/5	100/5	100/6	100/6
			[Number of washing: 5 times]			

(continued)

Water-repellency evaluation/Oil-repellency evaluation

Example	Water- and oil-repellent Fabric	Cotton Fabric	Blended Fabric	Polyester Fabric	Nylon Fabric	
5	Example 1	A	100/1	100/4	100/4	100/6
	Example 2	B	100/4	100/5	100/5	100/6
	Example 3	C	100/5	100/5	100/6	100/6
	Example 4	D	100/4	100/5	100/6	100/6
	Example 5	E	100/4	100/4	100/4	100/6
10	Example 6	F	100/3	100/5	100/5	100/6
	Comp.Ex.1	G	70/0	80/1	100/4	100/5
	Comp.Ex.2	H	70/2	100/4	100/5	100/6
	Comp.Ex.3	I	70/3	100/4	100/6	100/6
15	Comp.Ex.4	J	70/3	100/4	100/6	100/6
	[Number of washing: 10 times]					
	Example 1	A	70/1	100/3	100/4	100/5
	Example 2	B	90/3	100/4	100/5	100/5
	Example 3	C	90/3	100/4	100/6	100/6
20	Example 4	D	90/4	100/5	100/5	100/6
	Example 5	E	90/3	100/4	100/5	100/5
	Example 6	F	90/3	100/4	100/5	100/5
	Comp.Ex.1	G	50/0	70/0	100/4	100/4
25	Comp.Ex.2	H	70/1	80/4	100/5	100/5
	Comp.Ex.3	I	70/1	80/4	100/5	100/5
	Comp.Ex.4	J	70/1	80/4	100/5	100/5

30 **Claims**

1. A water- and oil-repellent comprising an aqueous dispersion of a fluorine-containing copolymer including as a copolymerization unit

35 (a) at least one of perfluoroalkylalkyl acrylates and corresponding methacrylates represented by the general formula:



40 (wherein R represents hydrogen atom or methyl group; n represents 4, 5, or 6; and m represents 1, 2, 3, or 4),

(b) benzyl acrylate or benzyl methacrylate,

(c) vinylidene chloride, and

(d) a cross-linkable group-containing polymerizable monomer;

45 and

a blocked isocyanate added to the aqueous dispersion in a weight ratio of 0.05 to 3.0 to the weight of the solid content of the aqueous dispersion.

2. The water- and oil-repellent according to Claim 1, wherein the component (d), cross-linkable group-containing polymerizable monomer, of the fluorine-containing copolymer is a hydrophilic monomer.

3. The water- and oil-repellent according to Claim 1, wherein the fluorine-containing copolymer has a copolymerization composition comprising 10 to 80% by weight of the component (a), 5 to 80% by weight of the component (b), 5 to 80% by weight of the component (c), and 0.5 to 40% by weight of the component (d).

55

Patentansprüche

1. Hydro- und Oleophobiermittel, umfassend eine wässrige Dispersion eines fluorhaltigen Copolymers, das als Copolymerisationseinheit folgendes umfasst:

(a) mindestens eines aus Perfluoralkylalkylacrylaten und entsprechenden Methacrylaten, dargestellt durch die allgemeine Formel:



(wobei R ein Wasserstoffatom oder eine Methylgruppe darstellt; n 4, 5 oder 6 darstellt; und m 1, 2, 3 oder 4 darstellt),

(b) Benzylacrylat oder Benzylmethacrylat,

(c) Vinylidenchlorid, und

(d) ein eine vernetzbare Gruppe enthaltendes polymerisierbares Monomer; und

eines blockierten Isocyanats, das zur wässrigen Dispersion in einem Gewichtsverhältnis von 0,05 bis 3,0 zum Gewicht des Feststoffgehalts der wässrigen Zusammensetzung zugegeben wird.


2. Hydro- und Oleophobiermittel gemäß Anspruch 1, wobei die Komponente (d), das eine vernetzbare Gruppe enthaltende polymerisierbare Monomer, des fluorhaltigen Copolymers ein hydrophiles Monomer ist.

3. Hydro- und Oleophobiermittel gemäß Anspruch 1, wobei das fluorhaltige Copolymer eine Copolymerisationszusammensetzung besitzt, umfassend 10 bis 80 Gew.-% der Komponente (a), 5 bis 80 Gew.-% der Komponente (b), 5 bis 80 Gew.-% der Komponente (c) sowie 0,5 bis 40 Gew.-% der Komponente (d).

Revendications

1. Agent hydrophobe et oléophobe comprenant une dispersion aqueuse d'un copolymère contenant du fluor comprenant comme motif de copolymérisation

(a) au moins l'un des acrylates de perfluoroalkylalkyle et des méthacrylates correspondants représentés par la formule générale :



(où R représente un atome d'hydrogène ou un groupe méthyle ; n représente 4, 5 ou 6 ; et m représente 1, 2, 3 ou 4),

(b) de l'acrylate de benzyle ou du méthacrylate de benzyle,

(c) du chlorure de vinylidène, et

(d) un monomère polymérisable contenant un groupe réticulable ; et

un isocyanate bloqué ajouté à la dispersion aqueuse dans un rapport en poids de 0,05 à 3,0 par rapport au poids de la teneur en matière solide de la dispersion aqueuse.

2. Agent hydrophobe et oléophobe selon la revendication 1, dans lequel le composant (d), le monomère polymérisable contenant un groupe réticulable, du copolymère contenant du fluor est un monomère hydrophile.

3. Agent hydrophobe et oléophobe selon la revendication 1, dans lequel le copolymère contenant du fluor a une composition de copolymérisation comprenant de 10 à 80 % en poids du composant (a), de 5 à 80 % en poids du composant (b), de 5 à 80 % en poids du composant (c) et de 0,5 à 40 % en poids du composant (d).

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 11080710 A [0005]
- WO 0058416 A [0006]
- JP 2004352976 A [0009]
- WO 2004035708 A [0010]
- WO 2005118737 A [0031]

Non-patent literature cited in the description

- *Secchaku*, 2006, vol. 50 (5), 16-22 [0002]