



(11) **EP 2 210 968 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Claims EN 3

(48) Corrigendum issued on:
04.12.2013 Bulletin 2013/49

(45) Date of publication and mention
of the grant of the patent:
17.07.2013 Bulletin 2013/29

(21) Application number: **08831970.2**

(22) Date of filing: **19.09.2008**

(51) Int Cl.:
C25B 11/12 (2006.01) C04B 35/52 (2006.01)
C25B 1/24 (2006.01)

(86) International application number:
PCT/JP2008/067021

(87) International publication number:
WO 2009/038192 (26.03.2009 Gazette 2009/13)

(54) **CARBONACEOUS SUBSTRATE AND ELECTRODE FOR ELECTROLYTIC PRODUCTION OF FLUORINE**

KOHLENSTOFFHALTIGES SUBSTRAT UND ELEKTRODE ZUR ELEKTROLYTISCHEN
HERSTELLUNG VON FLUOR

SUBSTRAT CARBONÉ ET ÉLECTRODE PERMETTANT UNE PRODUCTION ÉLECTROLYTIQUE
DU FLUOR

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT
RO SE SI SK TR**

(30) Priority: **20.09.2007 JP 2007244557**

(43) Date of publication of application:
28.07.2010 Bulletin 2010/30

(73) Proprietor: **Toyo Tanso Co., Ltd.**
Osaka-shi
Osaka 555-0011 (JP)

(72) Inventors:
• **TAO, Rie**
Osaka-shi
Osaka 555-0011 (JP)
• **KAWANO, Takanori**
Osaka-shi
Osaka 555-0011 (JP)

• **SHODAI, Yoshio**
Osaka-shi
Osaka 555-0011 (JP)

(74) Representative: **TBK**
Bavariaring 4-6
80336 München (DE)

(56) References cited:
JP-A- 2000 200 603 JP-A- 2000 200 603
JP-A- 2006 097 054 JP-A- 2006 249 557
US-A1- 2006 066 203 US-A1- 2006 219 570

• **DATABASECA[Online] CHEMICAL ABSTRACTS
SERVICE, COLUMBUS, OHIO, US; MIFUJI,
YASUHIKO ET AL: "Carbonaceous anodes for
secondary nonaqueous batteries and their
manufacture", XP002603724, retrieved from STN
Database accession no. 124:321597 & JP 8
078010 A (MATSUSHITA ELECTRIC IND CO LTD,
JAPAN) 22 March 1996 (1996-03-22)**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 210 968 B9

Description

TECHNICAL FIELD

[0001] The present invention relates to: a carbonaceous substrate which, when contacting fluorine or fluoride, is hardly intercalated and is suitable for formation of a diamond thin film; and an electrode for fluorine electrolysis, which is usable in an electrolytic method adopting an electrolyte containing fluoride ion. In particular, the present invention relates to electrodes for fluorine electrolysis, each of which has a diamond structure, restrains an anode effect even in operations with a high electric current density, produces less sludge due to wear of the electrodes, produces less carbon tetrafluoride gas, and enables continuation of stable electrolysis.

BACKGROUND ART

[0002] For the chemical stability, electrodes using a carbonaceous substrate have been suitably adopted as an electrolyte for containing fluoride ion electrolysis.

[0003] Patent Documents 1 and 2 each describes an exemplary carbon electrode used for synthesizing a fluorine-containing material through electrolysis using an electrolyte containing fluoride ion. Similarly, electrolysis for producing fluorine gas also uses a carbon electrode. The market and uses of fluorine gas are expected to grow significantly in a semiconductor field, as a cleaning gas, an etching gas, or a gas for reforming surfaces of plastic materials. Production of a large amount of fluorine gas with a high electric current density is crucial. However, a carbon electrode polarizes due to an anode effect. For this reason, use of a carbon electrode makes an operation with a high electric current density difficult sometimes.

[0004] To solve the above problem, a carbon electrode is coated with conductive diamond which is chemically stable and has a wide potential window. Use of this electrode enables an electrolysis operation with a high electric current density. Further, highly efficient and stable synthesis of fluorine compound is possible for a long time. Such an electrode is disclosed in Patent Documents 3 and 4.

[0005]

[Patent Document 1] Japanese Unexamined Patent Publication No. 047297/02 (Tokukaihei 02-047297)

[Patent Document 2] Japanese Unexamined Patent Publication No. 005194/05 (Tokukaihei 05-005194)

[Patent Document 3] Japanese Unexamined Patent Publication No. 249557/2006 (Tokukai 2006-249557)

[Patent Document 4] Japanese Unexamined Patent Publication No. 097054/2006 (Tokukai 2006-097054)

[0006] JP 2000200603 (A) discloses a negative-electrode material, its manufacturing method, and a battery, capable of obtaining a large charging/discharging capacity. This negative-electrode material has a carbon material in which a first phase 11, a second phase 12, and a third phase 13, differing in lattice spacing d002 of 002 planes from each other, coexist in one particle. This negative-electrode material is obtained by adding a catalyst such as Ni to a raw material of a hardly graphitizable carbon and heating it. The spacing d002 of the first phase 11 is smaller than 0.3375 nm, d002 of the second phase 12 is equal to or larger than 0.3375 nm and smaller than 0.3425 nm, and d002 of the third phase 13 is equal to or larger than 0.3425 nm. This negative-electrode material has the characteristics of all the phases and distortion produced in the first phase 11 by the storing/desorbing of atoms or ions can be absorbed by the third phase 13, and therefore a large charge/discharge capacity can be obtained.

DISCLOSURE OF THE INVENTION

[TECHNICAL PROBLEM]

[0007] However, when synthesizing a fluorine-containing material through an electrolysis using the carbonaceous substrate, a use of a typical carbonaceous substrate may cause intercalation attributed to structural disorder of the carbon crystal or infiltration of the electrolyte. This intercalation may deteriorate the property of the carbonaceous substrate or destroy the carbonaceous substrate itself. If diamond thin films are formed on this material, the expansion of the carbonaceous substrate may cause cracks or peeling of the thin films.

[0008] Further, when the coating is conductive diamond, the conductive diamond has polycrystalline structure and therefore causes difficulty in coating the entire substrate perfectly without even a small defect. An uncoated portion of the carbonaceous substrate may be intercalated due to development of the crystallinity, and the conductive diamond may be peeled due to infiltration of the electrolyte into the carbonaceous substrate.

[0009] In view of this, the present invention is made, and it is an object of the present invention to provide a carbonaceous substrate in which structural disorder of the carbon crystal due to intercalation or infiltration to the electrolyte are restrained,

carbonaceous substrate being suitable for forming a diamond thin film, and an electrodes for a fluorine-producing electrolysis, which is coated with a conductive diamond having a good adhesiveness.

[TECHNICAL SOLUTION]

[0010] A carbonaceous substrate of the present invention is such that, at the time of electrolysis of electrolyte containing fluoride ions, a graphite fluoride is formed in priority to formation of a charge-transfer type intercalation compound. Further, carbonaceous substrate, wherein: an X-ray diffraction pattern of the carbonaceous substrate is a complex profile and includes at least two (002) diffraction lines; and the substrates contains crystallites with different interlayer spacings. Particularly, in an X-ray diffraction pattern thereof, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ have an asymmetric shape; and the X-ray diffraction pattern includes two pattern components which are a diffraction line whose center is at $2\theta=26^\circ$ and a diffraction line whose center is at a lower angle than $2\theta=26^\circ$. Further, in the carbonaceous substrate, it is preferable that the presence proportion of the diffraction line whose center is at the $2\theta=26^\circ$ is 30% or more of the total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$. Further, the carbonaceous substrate contains crystals wherein the interlayer spacing (periodic distance d_{002}) is 0.34 nm or more and the crystallite size L_{c002} is 20 nm or less based on the X-ray diffraction lines. Further, the carbonaceous substrate is preferably an isotropic carbon material. Further, the carbonaceous substrate of the present invention is preferably manufactured through a cold isostatic pressing method, using mesophase microbeads as the filler. Additionally, the open porosity of the carbonaceous substrate is preferably between 5 to 30 volume%. When such a carbonaceous substrate is coated with a conductive diamond thin film and used as an electrode, tissue breakdown attributed to intercalation of fluorine ion will not take place in a portion without the diamond structure. Further, the surface is fluorinated and becomes electrochemically inertness. Since electrolysis only takes place on the conductive diamond thin film having the diamond structure, stable operation is possible for a long time.

[0011] An electrode of the present invention for a fluorine electrolysis includes the above mentioned carbonaceous substrate on which a conductive diamond thin film is formed. That is, it is preferable that a conductive diamond thin film is formed on a carbonaceous substrate wherein an X-ray diffraction pattern thereof is a complex profile and includes at least two (002) diffraction lines, the substrates containing crystallites with different interlayer spacings.

[0012] Further, it is preferable to coat, with a conductive diamond thin film, a carbonaceous substrate wherein, in an X-ray diffraction pattern thereof, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ have an asymmetric shape; and the X-ray diffraction pattern includes at least two pattern components which are a diffraction line whose center is at $2\theta=26^\circ$ and a diffraction line whose center is at a lower angle than $2\theta=26^\circ$.

[0013] Further, the carbonaceous substrate coated with a conductive diamond thin film is preferably a substrate as follows. Specifically, the presence area of the diffraction line whose center is at the $2\theta=26^\circ$ is preferably 30% or more of a total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$.

[0014] Further, it is preferable that the carbonaceous substrate contain crystals wherein the interlayer spacing (periodic distance d_{002}) is 0.34 nm or more and the crystallite size L_{c002} is 20 nm or less based on the X-ray diffraction lines.

[0015] Further, the carbonaceous substrate is preferably an isotropic carbon material.

[0016] Further, the carbonaceous substrate preferably contains mesophase microbeads as filler material.

[0017] Further, the open porosity of the carbonaceous substrate is preferably 5 to 30 volume%.

[0018] Further, the conductive diamond thin film preferably contains boron as a p-type dopant and nitrogen or phosphorous as an n-type dopant; and the content of the p-type dopant and/or the n-type dopant is preferably not more than 100,000 ppm.

[0019] Further, a film thickness of the conductive diamond thin film is preferably $0.5\mu\text{m}$ or more but not more than $10\mu\text{m}$.

[0020] Further, 10% or more of the surface of the carbonaceous substrate is preferably coated with the conductive diamond thin film.

[0021] Further, the crystallinity of the conductive diamond thin film is preferably such that the lattice constant derived from the X-ray diffraction is 0.357 nm or less, and in Raman spectrum resulted from Raman spectroscopic analysis, the full width at half maximum of a peak between 1320 and 1340 cm^{-1} of the C-C stretch mode of SP^3 bonding is 100 cm^{-1} or less.

[EFFECT OF THE INVENTION]

[0022] With the present invention, a double-layered electrode in which a carbonaceous substrate is coated with a conductive diamond thin film is used as an anode for synthesizing a fluorine-containing material by an electrolytic method. The crystallinity of the carbonaceous substrate used in such an electrode is controlled so as to prevent structural disorder of the carbon crystal and/or infiltration of the electrolyte attributed to intercalation. As a result, stable synthesis of a fluorine compound with a high electric current density is possible without causing peeling of the conductive diamond thin film.

BEST MODE FOR CARRYING OUT THE INVENTION

[0023] The following describes a suitable embodiment of the present invention.

[0024] The following details an electrode of the present invention for synthesizing fluorine-containing material and a carbonaceous substrate used in the synthesis. The electrode in the present invention is manufactured by a crystallinity-adjusted carbonaceous substrate with a conductive diamond thin film having diamond structure.

[0025] In the electrode, the conductive diamond thin film is polycrystal. For this reason, it is difficult to completely coat with the conductive diamond thin film the whole substrate without defect. In view of this, in the present embodiment, a carbonaceous substrate is coated with chemically stable conductive diamond. Such a carbonaceous substrate, when immersed into an electrolyte which contains fluoride ion, prevents structural disorder of the carbon crystal and/or infiltration of the electrolyte which are caused by intercalation. Further, providing an insulation coating on the carbonaceous substrate enables the substrate to self-stabilize.

[0026] The carbonaceous substrate is such that, during an electrolysis using an electrolyte containing fluoride ion, a charge-transfer type intercalation compound forms before formation of graphite fluoride. An X-ray diffraction pattern of this carbonaceous substrate is a complex profile and includes at least two (002) diffraction lines; and the substrate contains crystallites with different interlayer spacings. Further, in the X-ray diffraction pattern, the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ have an asymmetric shape; and the X-ray diffraction pattern includes at least two pattern components which are a diffraction line whose center is at $2\theta=26^\circ$ and a diffraction line whose center is at a lower angle than $2\theta=26^\circ$. The presence area of the diffraction line whose center is at the $2\theta=26^\circ$ is 30% or more of a total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$. With the crystal of carbon being intercalated with fluorine ion, polarization can be relatively restrained. Note that the presence proportion of the diffraction line whose center is at $2\theta=26^\circ$ is preferably 50% or more of the total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$.

[0027] The carbonaceous substrate can be either unitary or binary, and is made of a carbonaceous material which is obtained by mixing, moulding and calcining one or two or more of the following raw materials (fillers): mesophase microbeads, coal pitch coke, petroleum pitch coke, coal coke, petroleum coke, coal tar, a high polymer compound such as phenol resin or the like. Moulding method may be carried on a cold isostatic pressing method, or an extrusion moulding method. However, it is preferable to adopt an isotropic carbon material moulded through a cold isostatic pressing method in which the physical property is not affected by the direction.

[0028] The open porosity of the substrate is 5 to 30 volume%, and is preferably 5 to 20 mass%. When the open porosity is less than 5 volume%, the anchor effect at the time of coating with the conductive diamond is not obtained. When the open porosity is more than 30 volume%, suitable density and strength of the carbonaceous substrate are not achieved. Therefore, when synthesizing a fluorine-containing material through electrolysis using an electrolyte containing fluoride ion, the fluorine ion intercalates between layers of carbon crystals. Further, the adopted carbonaceous substrate contains crystals wherein the interlayer spacing (periodic distance d_{002}) is 0.34 nm or more and the crystallite size L_{c002} is 20 nm or less based on the X-ray diffraction lines. Due to the low crystallinity of the carbonaceous substrate having the above-described periodic distance and crystallite size, the periodic distance is not sufficient for fluorine to enter. Therefore, when such a carbonaceous substrate is used, intercalation hardly occurs as compared with a material such as a graphite having a developed crystallinity. Even if intercalation occurs, the interlayer spacing (periodic distance d_{002}) barely changes. Therefore, structural disorder is preventable.

[0029] An electrode in which the above carbonaceous substrate is coated with conductive diamond is used in synthesizing a fluorine-containing material. When such an electrode is used, a portion of the electrodes not having a diamond structure will not have tissue break down attributed to intercalation of fluorine ion. Further, fluorinating and forming an insulation coating on the surface of the electrode makes the electrode electrochemically inertness. The electrode is preferably (CF)_n and electrochemically inertness. Therefore, the electrolysis occurs only on the conductive diamond thin film portion having a diamond structure. This enables stable operation for a long time.

[0030] Note that when the carbonaceous substrate adopted contains crystals whose d_{002} (interlayer spacing) based on a diffraction line is less than 0.34 nm and whose crystallite size L_{c002} is adjusted to a size larger than 30 nm, intercalation occurs in the fluorine compound atmosphere. The intercalation increases the interlayer spacing (periodic distance d_{002}) and destroys the crystal structure. When adopting, for synthesizing a fluorine-containing material, an electrode made by coating the carbonaceous substrate with a conductive diamond, the electrolyte is infiltrated and causes peeling of the conductive diamond. For this reason, stable electrolysis for synthesizing a fluorine compound is not continued for a long time.

[0031] The method of forming the conductive diamond thin film on the substrate is not particularly limited, and any given method is adoptable. Examples of typical method includes a hot-filament CVD (chemical vapor deposition) method, a micro plasma CVD method, a plasma arc-jet method, and a physical vapor deposition (PVD) method, or the like.

[0032] To synthesize conductive diamond, the following materials are used as the raw materials of diamond in any of the above methods: a hydrogen gas or a rare gas such as He, Ar, and Ne which are an inert gas, and a mix gas serving as a carbon source presented as radicals in the gas. To provide electric conductivity to the diamond, one or both of a

p-type dopant and an n-type dopant is/are added as the inert gas. A preferable p-type dopant is a boron, and a preferable n-type dopant is nitrogen or phosphorous. In any case, the content of the dopant in the conductive diamond is preferably not more than 100,000 ppm.

[0033] Regardless of the method for manufacturing the conductive diamond, the conductive diamond is preferably polycrystal. For example, the diamond thin film contains amorphous carbon, a graphite component, or nano crystal diamond. These components are confirmed by Raman spectroscopic analysis. Where: I (Dia) is the intensity of C-C stretch mode for SP^3 bonding which is characteristic in diamond; I (D-band) is the peak intensity nearby 1350 cm^{-1} (between 1340 and 1380 cm^{-1}) which belongs to the D band of amorphous carbon; and I (G-band) is the peak intensity nearby 1580 cm^{-1} (between 1560 and 1600 cm^{-1}) which belongs to the G band of the graphite component, the ratio I (Dia)/I (D-band) is 1 or more, and the ratio I (Dia) / I (G-band) is 1 or more. Further, the content of diamond is preferably more than the content of amorphous carbon or that of the graphite component. Use of such a conductive diamond improves the characteristics of electrolysis.

[0034] The conductive diamond thin film is 0.5 to $10\mu\text{m}$ in film thickness, and the rate of the conductive diamond coating on the carbonaceous substrate is 10% or more. The film thickness of the conductive diamond thin film may vary approximately $\pm 0.5\mu\text{m}$ at the time of film formation. Therefore, to achieve the rate of conductive diamond coating of 10% or more, the average film thickness of the conductive diamond thin film is preferably $0.5\mu\text{m}$ or more. Use of an electrode whose diamond coating rate is less than 10% in electrolysis will result in the same limit electric current density and life as those in cases where only a carbon substrate is used in the electrolysis. Further, if the film thickness of the conductive diamond thin film surpasses $10\mu\text{m}$, an internal stress is generated in the diamond thin film. This internal stress causes cracking or peeling. Even if no peeling occurs, the resistance of the electrode will significantly increase. Note that the average film thickness of the conductive diamond thin film is preferably 0.5 to $5\mu\text{m}$, and more preferably 0.5 to $3\mu\text{m}$. The diamond coating rate is preferably 50% or more.

[Examples]

[0035] With reference to examples and comparative examples, the following further details the present invention. However, the scope of the present invention is not limited to the examples below. First detailed are examples in relation to the carbonaceous substrate.

<Example 1>

[0036] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which was an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ had an asymmetric shape. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the interlayer spacing (periodic distances d_{002}) of the carbonaceous substrate were 0.356 nm and 0.339 nm , the crystallite sizes (L_{c002}) were 2 nm and 3 nm , the pore diameter was $0.26\mu\text{m}$, the open porosity was 9 volume%, and the bending strength was 103 MPa . The weight of the carbonaceous substrate increased by 0.7 mass%, after the carbonaceous substrate was exposed to F_2/HF gas for 96 hours, at 60°C . The weight further increased by 5.2 mass% after 1008 hours of the exposure. The weight further increased by 6.8 mass% after 1464 hours of the exposure. The substrate exposed to the F_2/HF gas was subjected to the X-ray diffraction analysis. As a result, formation of GIC (abbrv. of graphite intercalation compound) by fluorine ion was confirmed.

<Example 2>

[0037] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which was an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ had an asymmetric shape. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the interlayer spacing (periodic distances d_{002}) of the carbonaceous substrate were 0.350 nm and 0.344 nm , the crystallite sizes (L_{c002}) were 3 nm and 5 nm , the pore diameter was $0.22\mu\text{m}$, the open porosity was 12 volume%, and the bending strength was 75 MPa . The weight of the carbonaceous substrate increased by 0.1 mass%, after the carbonaceous substrate was exposed to F_2/HF gas for 96 hours, at 60°C . The weight further increased by 4.9 mass% after 1008 hours of the exposure. The weight further increased by 5.7 mass% after 1464 hours of the exposure. The substrate exposed to the F_2/HF gas was subjected to the X-ray diffraction analysis. As a result, formation of GIC (abbrv. of graphite intercalation compound) caused by the intercalation of fluorine ion was confirmed.

<Example 3>

[0038] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which was an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta = 30^\circ$ had an asymmetric shape. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the interlayer spacing (periodic distances d_{002}) of the carbonaceous substrate were 0.356 nm and 0.330 nm, the crystallite sizes (L_{c002}) were 2 nm and 3 nm, the pore diameter was $0.26\mu\text{m}$, the open porosity was 9 volume%, the electric resistance was $46.7\mu\Omega\cdot\text{m}$, and the bending strength was 103 MPa. This carbonaceous substrate was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. The electric current density was varied to study the limit electric current density. The limit electric current density was $34.8\text{A}/\text{dm}^2$ in the molten-salt of KF-2HF with the water content of 200 ppm or less, and was $24.0\text{A}/\text{dm}^2$ in the molten-salt of KF-2HF with the water content of 500 ppm.

<Example 4>

[0039] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which was an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta = 30^\circ$ had an asymmetric shape. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the interlayer spacing (periodic distances d_{002}) of the carbonaceous substrate were 0.350 nm and 0.344 nm, the crystallite sizes (L_{c002}) were 3 nm and 5 nm, the pore diameter was $0.22\mu\text{m}$, the open porosity was 12 volume%, the electric resistance was $26.4\mu\Omega\cdot\text{m}$, and the bending strength was 75 MPa. This carbonaceous substrate was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. The electric current density was varied to study the limit electric current density. The limit electric current density was $32.8\text{A}/\text{dm}^2$ in the molten-salt of KF-2HF with the water content of 200 ppm or less, and was $10.2\text{A}/\text{dm}^2$ in the molten-salt of KF-2HF with the water content of 500 ppm.

<Comparative Example 1>

[0040] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which is an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta = 30^\circ$ form an asymmetric shape. The presence area of a diffraction line whose center was at $2\theta=26^\circ$ was approximately 49% of the total surficial area of the asymmetric shape formed by the (002) diffraction lines. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the periodic distance d_{002} (interlayer spacing) of the carbonaceous substrate was 0.339 nm, the crystallite size (L_{c002}) was 23 nm, the pore diameter was $0.22\mu\text{m}$, the open porosity was 15 volume%, and the bending strength was 93 MPa. This carbonaceous substrate was exposed to F_2/HF gas for 96 hours, at 60°C . The weight increased by 0.1 mass%. The weight further increased by 15.2 mass% after 1008 hours of the exposure. Further examination was intended; however, the carbonaceous substrate cracked. Cracking of the substrate was found to take place, after 1104 hours of exposure to F_2/HF gas and when the weight increases by more than 10 mass%. From this finding and from Examples 1 and 2, it was understood that the interlayer spacing d_{002} based on the X-ray diffraction pattern needs to be 0.34 nm or more.

<Comparative Example 2>

[0041] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which was an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta = 30^\circ$ had an asymmetric shape. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the interlayer spacing (periodic distance d_{002}) of the carbonaceous substrate was 0.339 nm, the crystallite size (L_{c002}) was 62 nm, the pore diameter was $0.22\mu\text{m}$, the open porosity was 15 volume%, the electric resistance was $15.5\mu\Omega\cdot\text{m}$, and the bending strength was 93 MPa. This carbonaceous substrate was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. The electric current density was varied to study the limit electric current density. The limit electric current density was inferior to that of Example 3, and was $29.8\text{A}/\text{dm}^2$ in the molten-salt of KF-2HF with water content of 200 ppm or less and $8.3\text{A}/\text{dm}^2$ with the water content of 500 ppm. From this finding, it is understood that the limit electric current density drops when the interplanar spacing d_{002} based on the X-ray diffraction pattern drops to 0.34 nm or less.

<Comparative Example 3>

[0042] A carbonaceous substrate made of an isotropic carbon material was manufactured through a cold isostatic pressing method using petroleum coke and a pulverized graphite product. In an X-ray diffraction pattern of the carbonaceous substrate which is an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ form an asymmetric shape. The presence area of a diffraction line whose center was at $2\theta=26^\circ$ was approximately 20% of the total surficial area of the asymmetric shape formed by the (002) diffraction lines. Further, based on the diffraction lines in the X-ray diffraction pattern of this carbonaceous substrate, the interlayer spacing (periodic distance d_{002}) of the carbonaceous substrate was 0.337 nm, the crystallite size was 37 nm, and the bending strength was 43 MPa. This carbonaceous substrate was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. Then, constant current electrolysis was performed with the electric current density of 20A/dm². The electrode cracked within 24 hours of electrolysis, and the electrolysis was no longer possible.

<Comparative Example 4>

[0043] A glasslike carbonaceous substrate was manufactured by using phenol resin. In an X-ray diffraction pattern of the glasslike carbonaceous substrate, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ had a symmetric shape. The presence proportion of the diffraction line whose center was at $2\theta=26^\circ$ was 0% of the total surficial area of the symmetric shape formed by the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$. With the glasslike carbonaceous substrate, there was prepared a carbonaceous substrate wherein, based on a diffraction line in an X-ray diffraction pattern thereof, the interlayer spacing d_{002} was 0.350 nm, the crystallite size (L_{c002}) was 2 nm, and the open porosity was 5 volume% or less. This carbonaceous substrate was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. The electric current density was varied to study the limit electric current density. Polarization occurred immediately after the current was applied, and the voltage had excessively increased and the electrolysis was no longer possible.

[0044] Next, the following details in the case of using of the electrode for fluorine electrolysis, which is coated a diamond thin film on carbonaceous substrate.

<Example 5>

[0045] Adopting mesophase microbeads as the filler, a carbonaceous substrate was fabricated through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ had an asymmetric shape. The presence area of the diffraction line whose center was at the $2\theta=26^\circ$ was 57% of a total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$. Based on the diffraction line resulting from the X-ray diffraction analysis, the interlayer spacing (periodic distances d_{002}) of the carbonaceous substrate were 0.355 nm and 0.339 nm, the crystallite sizes were 2 nm and 3 nm, the pore diameter was 0.26 μ m, and the open porosity was 9 volume%. The physical properties of the carbonaceous substrate were as follows. Namely, the CTE (thermal expansion coefficient) was 6.4 to 6.8 $\times 10^{-6}$ /K, the electric resistance was 46.7 $\mu\Omega\cdot$ m, and the bending strength was 103 MPa. In a chamber, the carbonaceous substrate was brought into contact with a mix gas prepared by adding 1 vol% of methane gas and 0.5 ppm of trimethyl boron gas to hydrogen gas. While maintaining the pressure inside the chamber at 75 Torr, the power was applied to a filament inside the chamber to raise the temperature to 2400°C so that the temperature of the substrate is 860°C. Then, through a CVD method, the carbonaceous substrate was coated with conductive diamond, to obtain an electrode of Example 5 according to the present invention, for use in a fluorine-producing electrolysis. The film thickness of the diamond thin film of the electrode for use in the fluorine-producing electrolysis was 3 μ m. Further, from the X-ray diffraction analysis, deposited thin film was confirmed diamonds. The lattice constant of the diamond was 0.3568 nm. In Raman spectroscopic analysis, there is confirmed a diamond-attributed peak of 41.9cm⁻¹ which is the full width at half maximum of the peak at 1333.7cm⁻¹ of the C-C stretch mode of SP³ bonding.

[0046] The electrode for fluorine-producing electrolysis manufactured in Example 5 was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. Then, constant current electrolysis was performed with the electric current density of 20A/dm². The cell voltage was 5.6 V, after 24 hours of the electrolysis. The electrolysis was continued. The cell voltage was 5.6 V after another 24 hours of the electrolysis. Analyzing the gas generated at the anode, it is found that the generated gas was F₂, and that the amount of gas generated (generation efficiency) accounts 98% of the theoretical amount of gas generated for the quantity of electricity consumed. Further, no change was observed between the cell voltage 24 hours after the start of charging and the cell voltage after another 24 hours. From these results, it is assumed that the electrolysis was smoothly performed without polarization of the electrode.

[0047] The surface energy was calculated from the contact angle of water and methylene iodide with respect to the

portion of the electrode for fluorine-producing electrolysis before being used in the electrolysis, which portion is coated by the conductive polycrystal diamond. As a result, the surface energy was 40.1 mN/m. The surface energy of a portion not having the diamond structure was 41.5 mN/m. The electrode for fluorine-producing electrolysis was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. Then, constant current electrolysis was performed with the electric current density of 100A/dm². The cell voltage was 5.5 V, after 24 hours of the electrolysis. The electrolysis was continued. The cell voltage was 5.5V after another 24 hours of the electrolysis. Analyzing the gas generated at the anode, it is found that the gas generated was fluorine (F₂), and that the generation efficiency was 98%. The electrolysis was further continued with the electric current density of 100A/dm², and then stopped after another 24 hours. The electrode was then taken out, and washed with anhydrous hydrogen fluoride. Then, the surface energy was calculated through the same method used before the electrolysis. The surface energy of the portion coated by the conductive polycrystal diamond was 38.0 mN/m, and the surface energy of the portion not coated by the conductive polycrystal diamond was 3.5 mN/m. From these results, it is found that the conductive diamond portion was stable in the fluorine containing electrolysis synthesis, while the portion having no diamond structure was fluorinated and was electrochemically inactive with the formation of the insulation coating.

<Example 6>

[0048] Using mesophase microbeads as the filler, a carbonaceous substrate of an isotropic carbon material was manufactured through a cold isostatic pressing method. In an X-ray diffraction pattern of the carbonaceous substrate which is an isotropic carbon material, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta = 30^\circ$ had an asymmetric shape. The presence area of the diffraction line whose center was at the $2\theta=26^\circ$ was 57% of a total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta = 30^\circ$. Based on the diffraction line resulting from the X-ray diffraction analysis, the interlayer spacing (periodic distances d_{002}) of the carbonaceous substrate were 0.355 nm and 0.340 nm, the crystallite sizes were 2 nm and 3 nm, the pore diameter was 0.26 μ m, and the open porosity was 9 volume%. The physical properties of the carbonaceous substrate were as follows. Namely, the CTE (Coefficient of Thermal Expansion) was 6.4 to 6.8 x 10⁻⁶/K, the electric resistance was 46.7 $\mu\Omega\cdot$ m, and the bending strength was 103 MPa. In a chamber, the carbonaceous substrate was brought into contact with a mix gas prepared by adding 1 vol% of methane gas and 0.5 ppm of tri methyl boron gas to hydrogen gas. While maintaining the pressure inside the chamber at 75 Torr, the power was applied to a filament inside the chamber to raise the temperature to 2400°C so that the temperature of the substrate is 860°C. Then, through a CVD method, the carbonaceous substrate was coated with conductive diamond, to obtain an electrode of Example 6 according to the present invention, for use in a fluorine-producing electrolysis. The film thickness of the diamond thin film of the electrode for fluorine-producing electrolysis was 0.6 μ m in average. From the observation of the cross section, the film thickness was found to be ± 0.5 to 1 μ m. Further, from the X-ray diffraction analysis, deposition of diamond was confirmed. The lattice constant of the diamond was 0.3568 nm. In Raman spectroscopic analysis, there is confirmed a diamond-attributed peak of 41.9cm⁻¹ which is the full width at half maximum of the peak at 1333.7cm⁻¹ of the C-C stretch mode of SP³ bonding. When the G-band and D-band were compared, the strength ratio was 1 or higher.

[0049] The electrode for fluorine-producing electrolysis manufactured in Example 6 was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. Then, constant current electrolysis was performed with the electric current density of 20A/dm². The cell voltage was 5.5 V, after 24 hours of the electrolysis. The electrolysis was continued. The cell voltage was 5.5V after another 24 hours of the electrolysis. The gas generated at this time was F₂ gas, and the generation efficiency was 98%. Further, no change was observed between the cell voltage 24 hours after the start of charging and the cell voltage after another 24 hours. From these results, it is assumed that the electrolysis was smoothly performed without polarization of the electrode.

<Example 7>

[0050] An electrode of Example 7 for fluorine-producing electrolysis was obtained in the same way as the electrode of Example 6, except in that the period for CVD was extended and the film thickness of the diamond thin film was made 10 μ m. Further, from the X-ray diffraction analysis, deposition of diamond was confirmed, for the electrode of Example 7 for fluorine-producing electrolysis too. The lattice constant of the diamond was 0.3568 nm. In Raman spectroscopic analysis, there is confirmed a diamond-attributed peak of 41.9cm⁻¹ which is the full width at half maximum of the peak at 1333.7cm⁻¹ of the C-C stretch mode of SP³ bonding. When the G-band and D-band were compared, the strength ratio was 1 or higher.

[0051] The electrode for fluorine-producing electrolysis manufactured in Example 7 was used as an anode in a molten-salt of KF-2HF immediately after the initial make-up of electrolytic bath. A nickel plate was used as a cathode material. Then, constant current electrolysis was performed with the electric current density of 20A/dm². As in Example 6, the cell voltage was 5.5 V, after 24 hours of the electrolysis. The electrolysis was continued. The cell voltage was 5.5V after

another 24 hours of the electrolysis. The gas generated at this time was F_2 gas, and the generation efficiency was 98%. Further, no change was observed between the cell voltage 24 hours after the start of charging and the cell voltage after another 24 hours. From these results, it is assumed that the electrolysis was smoothly performed without polarization of the electrode.

<Comparative Example 5>

[0052] On a carbonaceous substrate mentioned in Comparative Example 4, a diamond thin film of $3\mu m$ in film thickness was formed with the same conditions as those in Example 6. The adhesiveness of the diamond to the carbonaceous substrate was significantly weak. The electrode for fluorine-producing electrolysis was used as an anode in a molten-salt of KF-2HF immediately after initial make-up of electrolytic bath. A nickel plate was used as a cathode material. The electric current density was varied to study the limit of the electric current density. The diamond thin film peeled and polarization occurred, and the voltage increased excessively. The electrolysis was therefore no longer possible.

<Comparative Example 6>

[0053] An electrode of Comparative Example 6 for fluorine-producing electrolysis was obtained in the same way as the electrode of Example 6, except in that the period for CVD was shortened and the film thickness of the diamond thin film was made $0.4\mu m$. The diamond thin film of the electrode of Comparative Example 6 for fluorine-producing electrolysis was subjected to Raman spectroscopic analysis. The full width at half maximum of the peak in the C-C stretch mode of the SP^3 bonding which is a characteristic of diamond was $100cm^{-1}$. The intensity ratio of intensity I (Dia) to the G-band and D-band attributed to the graphite component was less than 1. From these results, it is supposed that the carbonaceous substrate was not sufficiently coated with the diamond thin film.

<Comparative Example 7>

[0054] An electrode of Comparative Example 7 for fluorine-producing electrolysis was obtained in the same way as the electrode of Example 6, except in that the period for CVD was extended and the film thickness of the diamond thin film was made $11\mu m$. Further, from the X-ray diffraction analysis, deposition of diamond was confirmed, for the electrode of Comparative Example 7 for fluorine-producing electrolysis too. The lattice constant of the diamond was $0.3568 nm$. In Raman spectroscopic analysis, there is confirmed a diamond-attributed peak of $41.9cm^{-1}$ which is the full width at half maximum of the peak at $1333.7cm^{-1}$ of the C-C stretch mode of SP^3 bonding.

[0055] However, the thin film cracked and peeled off from the carbonaceous substrate, due to the stress applied when the electrode of Comparative Example 7 for fluorine-producing electrolysis was taken out from the synthesizing apparatus. Thus, electrode of Comparative Example 7 was not usable as an electrode.

[0056] Table 1 indicates the results of Examples 1 to 7 and Comparative Examples 1 to 7.

[Table 1]

	Diamond Coating	Thickness of Conductive diamond film (μm)	Shape of (002) diffraction lines	presence area of (002) diffraction lines with their centers at $2\theta = 26^\circ$ VS. total surficial area of the (002) diffraction lines between $2\theta = 10^\circ$ and $2\theta = 30^\circ$	interlayer spacing d_{002} based on diffraction lines (nm)		Crystallite sizes (L_{c002}) (nm)		Pore diameters (μm)	Open porosity (vol %)	Bending strength (MPa)	Electric resistance (μΩ·m)	Weight increase rate after exposure to F ₂ H ₂ F	Electrolysis in KF·2HF
Example 1	No	—	Asymmetrical	—	0.355	0.339	2	3	0.26	9	103	—	0.7%, after 96 hrs. 5.2% after 1008 hrs. 6.8% after 1464 hrs.	—
Example 2	No	—	Asymmetrical	—	0.350	0.344	3	5	0.22	12	75	—	0.1%, after 96 hrs. 4.9% after 1008 hrs. 5.7% after 1464 hrs.	—
Example 3	No	—	Asymmetrical	—	0.356	0.330	2	3	0.26	9	103	46.7	—	(Water Content) 200 ppm: 34.8A/dm ² 500 ppm: 24.0A/dm ²
Example 4	No	—	Asymmetrical	—	0.350	0.344	3	5	0.22	12	75	26.4	—	(Water Content) 200 ppm: 32.8A/dm ² 500 ppm: 10.2A/dm ²
Example 5	Yes	3	Asymmetrical	57%	0.355	0.339	2	3	0.26	9	103	46.7	—	—
Example 6	Yes	0.6	Asymmetrical	57%	0.335	0.340	2	3	0.26	9	103	46.7	—	—
Example 7	Yes	10	Asymmetrical	57%	0.335	0.340	2	3	0.26	9	103	46.7	—	—
Comparative Example 1	No	—	Asymmetrical	49%	0.339	—	23	—	0.22	15	93	—	Significantly increased	—
Comparative Example 2	No	—	Asymmetrical	—	0.339	—	62	—	0.22	15	93	15.5	—	(Water Content) 200 ppm: 34.8A/dm ² 500 ppm: 10.2A/dm ²
Comparative Example 3	No	—	Asymmetrical	20%	0.337	—	37	—	—	—	43	—	—	Electrode cracked after 24 hours
Comparative Example 4	No	—	Symmetrical	0%	0.350	—	2	—	—	5 or less	—	—	—	Polarized immediately
Comparative Example 5	Yes	3	Symmetrical	0%	0.350	0.334 or more	2	—	—	5 or less	—	—	—	Thin film peeled immediately after electrolysis started
Comparative Example 6	Yes	0.4	Asymmetrical	57%	0.335	0.340	2	3	0.26	9	103	46.7	—	—
Comparative Example 7	Yes	11	Asymmetrical	57%	0.335	0.340	2	3	0.26	9	103	46.7	Thin film broke when taken out from apparatus	—

[0057] Embodiment and Examples of an electrode for fluorine-producing electrolysis according to the present invention were thus described above.

Claims

1. An electrode for fluorine producing electrolysis comprising a carbonaceous substrate on which a conductive diamond thin film is formed, wherein:

an X-ray diffraction pattern of the carbonaceous substrate is a complex profile and includes at least two (002) diffraction lines; and

the substrates contains crystallites with different interlayer spacings.

2. The electrode according to claim 1, wherein, in the X-ray diffraction pattern, (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$ have an asymmetric shape; and the X-ray diffraction pattern includes at least two pattern components which are a diffraction line whose center is at $2\theta=26^\circ$ and a diffraction line whose center is at a lower angle than $2\theta=26^\circ$.

3. The electrode according to claim 2, wherein the carbonaceous substrate is such that the presence area of the diffraction line whose center is at the $2\theta=26^\circ$ is 30% or more of a total surficial area of the (002) diffraction lines between $2\theta=10^\circ$ and $2\theta=30^\circ$.

4. The electrode according to any one of claims 1 to 3, wherein the carbonaceous substrate contains crystals wherein the interlayer spacing is 0.34 nm or more and the crystallite size L_{c002} is 20 nm or less based on the X-ray diffraction lines.

5. The electrode according to any one of claims 1 to 4, wherein the carbonaceous substrate is an isotropic carbon material.

6. The electrode according to any one of claims 1 to 5, wherein the carbonaceous substrate contains mesophase microbeads as filler thereof.

7. The electrode according to any one of claims 1 to 6, wherein the open porosity of the carbonaceous substrate is 5 to 30 volume%.

8. The electrode according to any one of claims 1 to 7, wherein:

the conductive diamond thin film contains boron as a p-type dopant and nitrogen or phosphorous as an n-type dopant; and
the content of the p-type dopant and/or the n-type dopant is not more than 100,000 ppm.

9. The electrode according to any one of claims 1 to 8, wherein a film thickness of the conductive diamond thin film is 0.5 μm or more but not more than 10 μm .

10. The electrode according to any one of claims 1 to 9, wherein 10% or more of the surface of the carbonaceous substrate is coated with the conductive diamond thin film.

11. The electrode according to any one of claims 1 to 10, wherein
the crystallinity of the conductive diamond thin film is such that the lattice constant derived from the X-ray diffraction is 0.357 nm or less, and in Raman spectrum resulted from Raman spectroscopic analysis, the full width at half maximum of a peak between 1320 and 1340 cm^{-1} of the C-C stretch mode of SP^3 bonding is 100 cm^{-1} or less.

12. Use of an electrode in a fluorine-producing electrolysis, wherein the electrode is an electrode according to any one of claims 1 to 11.

Patentansprüche

1. Elektrode für die fluorherstellende Elektrolyse, die ein kohlenstoffhaltiges Substrat umfasst, auf welchem ein leitfähiger Diamantendünnschicht gebildet ist, wobei:

ein Röntgenstrahldiffraktionsmuster des kohlenstoffhaltigen Substrats ein komplexes Profil ist und zumindest zwei (002) Diffraktionslinien beinhaltet; und
das Substrat Kristallite mit unterschiedlichen Zwischenschichtabständen enthält.

2. Elektrode nach Anspruch 1, wobei in dem Röntgenstrahldiffraktionsmuster (002) Diffraktionslinien zwischen $2\theta=10^\circ$ und $2\theta=30^\circ$ eine asymmetrische Form aufweisen; und das Röntgenstrahldiffraktionsmuster zumindest zwei Musterkomponenten beinhaltet, welche eine Diffraktionslinie, deren Zentrum bei $2\theta=26^\circ$ ist, und eine Diffraktionslinie, deren Zentrum bei einem kleineren Winkel als $2\theta=26^\circ$ ist, sind.

3. Elektrode nach Anspruch 2, wobei das kohlenstoffhaltige Substrat so ist, dass der vorliegende Bereich der Diffraktionslinie, deren Zentrum bei der $2\theta=26^\circ$ ist, 30% oder mehr eines gesamten superfiziellen Bereichs der (002) Diffraktionslinien zwischen $2\theta=10^\circ$ und $2\theta=30^\circ$ ist.

4. Elektrode nach einem der Ansprüche 1 bis 3, wobei das kohlenstoffhaltige Substrat Kristalle enthält, wobei der Zwischenschichtabstand 0,34 nm oder mehr ist und die Kristallitgröße LC_{002} 20 nm oder weniger ist basierend auf den Röntgenstrahldiffraktionslinien.

5. Elektrode nach einem der Ansprüche 1 bis 4, wobei das kohlenstoffhaltige Substrat ein isotropes Kohlenstoffmaterial ist.

6. Elektrode nach einem der Ansprüche 1 bis 5, wobei das kohlenstoffhaltige Substrat mesophasen Mikrokügelchen als dessen Füllmittel enthält.

7. Elektrode nach einem der Ansprüche 1 bis 6, wobei die offene Porosität des kohlenstoffhaltigen Substrats 5 bis 30 Volumen-% ist.

8. Elektrode nach einem der Ansprüche 1 bis 7, wobei:

der leitfähige Diamantendünnschicht Bor als ein p-Typ Dotierungsmittel und Stickstoff oder Phosphor als ein n-Typ

Dotierungsmittel enthält; und

der Gehalt des p-Typ Dotierungsmittels und/oder des n-Typ Dotierungsmittels nicht mehr als 100000 ppm ist.

9. Elektrode nach einem der Ansprüche 1 bis 8, wobei eine Filmdicke des leitfähigen Diamantendünnsfilms 0,5 μm oder mehr, aber nicht mehr als 10 μm ist.

10. Elektrode nach einem der Ansprüche 1 bis 9, wobei 10% oder mehr der Oberfläche des kohlenstoffartigen Substrats mit dem leitfähigen Diamantendünnsfilm beschichtet ist.

11. Elektrode nach einem der Ansprüche 1 bis 10, wobei die Kristallinität des leitfähigen Diamantendünnsfilms so ist, dass die Gitterkonstante, die von der Röntgenstrahldiffraktion abgeleitet ist, 0,357 nm oder weniger ist, und im Raman-Spektrum, das aus Raman spektroskopischer Analyse resultiert, die Halbwertsbreite eines Peaks zwischen 1320 und 1340 cm^{-1} des C-C Streckmodus der SP^3 Bindung 100 cm^{-1} oder weniger ist.

12. Verwendung einer Elektrode in einer fluorherstellenden Elektrolyse, wobei die Elektrode eine Elektrode nach einem der Ansprüche 1 bis 11 ist.

Revendications

1. Electrode pour une électrolyse produisant du fluor comprenant un substrat carboné sur lequel un film mince de diamant conducteur est formé, où :

un diagramme de diffraction de rayons X du substrat carboné est un profil complexe et comporte au moins deux lignes de diffraction (002) ; et les substrats contiennent des cristallites avec différents espacements intercouches.

2. Electrode selon la revendication 1, dans laquelle, dans le diagramme de diffraction de rayons X, des lignes de diffraction (002) entre $2\theta=10^\circ$ et $2\theta=30^\circ$ ont une forme asymétrique ; et le diagramme de diffraction de rayons X comporte au moins deux composantes de diagramme qui sont une ligne de diffraction dont le centre se trouve à $2\theta=26^\circ$ et une ligne de diffraction dont le centre se trouve à un angle inférieur à $2\theta=26^\circ$.

3. Electrode selon la revendication 2, dans laquelle le substrat carboné est tel que la zone de présence de la ligne de diffraction dont le centre se trouve à $2\theta=26^\circ$ est de 30% ou plus d'une zone superficielle totale des lignes de diffraction (002) entre $2\theta=10^\circ$ et $2\theta=30^\circ$.

4. Electrode selon l'une quelconque des revendications 1 à 3, dans laquelle le substrat carboné contient des cristaux où l'espacement intercouches est de 0,34 nm ou plus et la dimension cristalline LC_{002} est de 20 nm ou moins en se basant sur les lignes de diffraction de rayons X.

5. Electrode selon l'une quelconque des revendications 1 à 4, dans laquelle le substrat carboné est un matériau de carbone isotrope.

6. Electrode selon l'une quelconque des revendications 1 à 5, dans laquelle le substrat carboné contient des microbilles de mésophase en tant que charge de celui-ci.

7. Electrode selon l'une quelconque des revendications 1 à 6, dans laquelle la porosité ouverte du substrat carboné est de 5 à 30% en volume.

8. Electrode selon l'une quelconque des revendications 1 à 7, dans laquelle :

le film mince de diamant conducteur contient du bore en tant que dopant de type p et de l'azote ou du phosphore en tant que dopant de type n ; et

la teneur du dopant de type p et/ou du dopant de type n ne dépasse pas 100000 ppm.

9. Electrode selon l'une quelconque des revendications 1 à 8, dans laquelle une épaisseur de film du film mince de diamant conducteur est de 0,5 μm ou plus mais ne dépasse pas 10 μm .

10. Electrode selon l'une quelconque des revendications 1 à 9, dans laquelle 10% ou plus de la surface du substrat carboné est revêtu avec le film mince de diamant conducteur.

11. Electrode selon l'une quelconque des revendications 1 à 10, dans laquelle la cristallinité du film mince de diamant conducteur est telle que la constante du réseau cristallin dérivée de la diffraction de rayons X est de 0,357 nm ou moins, et dans un spectre Raman résultant de l'analyse spectroscopique Raman, la largeur à mi-hauteur d'un pic entre 1320 et 1340 cm^{-1} du mode d'étirement C-C de la liaison SP^3 est de 100 cm^{-1} ou moins.

12. Utilisation d'une électrode dans une électrolyse produisant du fluor, dans laquelle l'électrode est une électrode selon l'une quelconque des revendications 1 à 11.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 04729702 B [0005]
- JP TOKUKAIHEI02047297 B [0005]
- JP 00519405 A [0005]
- JP TOKUKAIHEI05005194 B [0005]
- JP 2006249557 A [0005]
- JP TOKUKAI2006249557 B [0005]
- JP 2006097054 A [0005]
- JP TOKUKAI2006097054 B [0005]
- JP 2000200603 A [0006]