## (11) **EP 2 311 927 A8**

## (12) CORRECTED EUROPEAN PATENT APPLICATION

published in accordance with Art. 153(4) EPC

(15) Correction information:

Corrected version no 1 (W1 A1) Corrections, see Bibliography INID code(s) 72

(48) Corrigendum issued on: **29.06.2011 Bulletin 2011/26** 

(43) Date of publication: **20.04.2011 Bulletin 2011/16** 

(21) Application number: 09802648.7

(22) Date of filing: 10.07.2009

(51) Int Cl.:

C10M 171/00 (2006.01)
C10M 117/00 (2006.01)
C10N 20/00 (2006.01)
C10N 30/06 (2006.01)
C10N 50/10 (2006.01)
C10N 50/10 (2006.01)

(86) International application number: PCT/JP2009/003239

(87) International publication number:

WO 2010/013398 (04.02.2010 Gazette 2010/05)

(84) Designated Contracting States:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

(30) Priority: 01.08.2008 JP 2008199548

(71) Applicants:

 Panasonic Corporation Kadoma-shi
 Osaka 571-8501 (JP)
 Idemitsu Kosan Co., Ltd.

Chiyoda-ku Tokyo 100-8321 (JP) (72) Inventors:

 Ohno, Hideaki, c/o Panasonic Corporation Osaka-shi,
 Osaka 540-6207 (JP)

 Fujinami, Yukitoshi Ichihara-shi,
 Chiba 299-0107 (JP)

(74) Representative: Ehlers, Jochen et al Eisenführ, Speiser & Partner Johannes-Brahms-Platz 1 20355 Hamburg (DE)

## (54) GREASE COMPOSITION FOR MOUNTER, GUIDING DEVICE CONTAINING THE SAME, AND MOUNTER

(57) The present invention has the object of providing a grease composition for a mounter that exhibits excellent stability to mechanical shearing, and excellent mixing stability, a guiding device for a mounter that includes the grease composition, and a mounter that mounts the guiding device. A grease composition for a mounter includes

a base oil and a thickening agent, has a worked penetration of 200 - 400, a dropping point of greater than or equal to 220°C, and a worked penetration change during a roll stability test of 0 to less than or equal to +100.

EP 2 311 927 A8