

(19)



(11)

EP 2 322 504 B9

(12)

CORRECTED EUROPEAN PATENT SPECIFICATION

(15) Correction information:

Corrected version no 1 (W1 B1)
Corrections, see
Description Paragraph(s) 123
Claims EN 1, 9

(51) Int Cl.:

C07C 263/04 ^(2006.01) **C07C 265/14** ^(2006.01)
C07C 269/04 ^(2006.01) **C07C 271/42** ^(2006.01)

(48) Corrigendum issued on:

06.09.2017 Bulletin 2017/36

(86) International application number:

PCT/JP2009/005013

(45) Date of publication and mention of the grant of the patent:

28.09.2016 Bulletin 2016/39

(87) International publication number:

WO 2011/021258 (24.02.2011 Gazette 2011/08)

(21) Application number: **09845052.1**

(22) Date of filing: **29.09.2009**

(54) **PROCESS FOR THE PREPARATION OF N-SUBSTITUTED CARBAMIC ACID ESTER AND PROCESS FOR THE PREPARATION OF ISOCYANATE USING THE N-SUBSTITUTED CARBAMIC ACID ESTER**

VERFAHREN ZUR HERSTELLUNG EINES N-SUBSTITUIERTEN CARBAMINSÄUREESTERS SOWIE VERFAHREN ZUR HERSTELLUNG EINES ISOCYANATS MITHILFE DES N-SUBSTITUIERTEN CARBAMINSÄUREESTERS

PROCÉDÉ POUR LA PRÉPARATION D'ESTER D'ACIDE CARBAMIQUE N-SUBSTITUÉ ET PROCÉDÉ POUR LA PRÉPARATION D'ISOCYANATE À L'AIDE DE L'ESTER D'ACIDE CARBAMIQUE N-SUBSTITUÉ

(84) Designated Contracting States:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

- **OKUBO, Atsushi**
Tokyo 101-8101 (JP)

(30) Priority: **21.08.2009 JP 2009192250**
21.08.2009 JP 2009192268

(74) Representative: **D Young & Co LLP**
120 Holborn
London EC1N 2DY (GB)

(43) Date of publication of application:
18.05.2011 Bulletin 2011/20

(56) References cited:

WO-A1-2008/059953	WO-A1-2008/120645
DE-A1- 3 928 595	JP-A- 6 041 045
JP-A- 6 192 204	JP-A- 6 239 826
JP-A- 7 157 463	JP-A- 59 108 754
US-A- 2 145 242	US-A- 4 925 971

(73) Proprietor: **Asahi Kasei Kabushiki Kaisha**
Chiyoda-ku
Tokyo 101-8101 (JP)

(72) Inventors:

- **MIYAKE, Nobuhisa**
Tokyo 101-8101 (JP)
- **SHINOHATA, Masaaki**
Tokyo 101-8101 (JP)

- **YADAV, L. D. S. ET AL.:** 'Three-component coupling strategy for expeditious synthesis of 4-aminobenzoxazinones on mineral support' **SYNLETT** vol. 20, 2005, pages 3055 - 3058, **XP008144479**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 322 504 B9

- **STEDMAN, E. ET AL.: 'Methylurethans of the isomeric α -hydroxyphenylethyldimethylamines and their Miotic activity' JOURNAL OF THE CHEMICAL SOCIETY 1929, pages 609 - 617, XP009055833**

Description

Technical Field


5 **[0001]** The present invention relates to a method for producing N-substituted carbamic acid ester and a method for producing isocyanate that uses the N-substituted carbamic acid ester.

Background Art

10 **[0002]** Isocyanates are widely used as production raw materials of such products as polyurethane foam, paints and adhesives. Although a plurality of reaction mechanisms can be considered for industrial production of isocyanates, the main industrial production method involves reaction of an amine with phosgene (phosgene method) as indicated in the following formula (i), and nearly the entire amount of isocyanates produced throughout the world are produced according to the phosgene method. However, the phosgene method has numerous problems.

15

20



25

[0003] Firstly, this method requires the use of a large amount of phosgene as raw material. Phosgene is extremely toxic and requires special handling precautions to prevent exposure of handlers thereof, and also requires special apparatuses to detoxify waste.

[0004] Secondly, since highly corrosive hydrogen chloride is produced in large amounts as a by-product of the phosgene method, in addition to requiring a process for detoxifying the hydrogen chloride, in many cases hydrolytic chlorine is contained in the isocyanates produced, which may have a detrimental effect on the weather resistance and heat resistance of polyurethane products in the case of using isocyanates produced using the phosgene method.

30


[0005] On the basis of this background, a method for producing isocyanate compounds is sought that does not use phosgene.

[0006] Although examples of such methods may include a method for synthesizing aliphatic isocyanate from an aliphatic nitro compound and carbon monoxide, and a method for converting an aliphatic amide compound to isocyanate by Hoffmann decomposition, both of these methods have poor yield and are inadequate for industrial application.

35

[0007] Methods for obtaining an isocyanate and a hydroxyl compound by thermal decomposition of N-substituted carbamic acid-O-alkyl ester compound have long been known, an example of which is the method of A.W. Hoffmann (see Non-Patent Document 1). This method enables a high yield to be achieved more easily than the methods described above, and the basic reaction employed in this method is indicated in the following formula (ii).

40



45

[0008] Thermal decomposition represented by the above general formula is reversible, and although the equilibrium thereof is biased towards the N-substituted carbamic acid-O-alkyl ester on the left side at low temperatures, the right side with the isocyanate and a alcohol side are advantageous at high temperatures. Thus, methods for obtaining isocyanate by thermal decomposition of N-substituted carbamic acid-O-alkyl ester are carried out at high temperatures (see, for example, Examples 12 and 13 of Patent Document 1). Here, although dependent on the ester group of the N-substituted carbamic acid-O-alkyl ester, the boiling point of N-substituted carbamic acid-O-methyl ester, for example, is 110°C (during reduced pressure of about 2 kPa) (line 9 from the top of the right column of Non-Patent Document 2). On the other hand, the boiling point of hexamethylene diisocyanate, which is formed in the corresponding thermal decomposition reaction, is 130 to 140°C (during reduced pressure of about 2 kPa) (Non-Patent Document 3). Namely, this indicates that the N-substituted carbamic acid-O-methyl ester has a lower boiling point than the product in the form of hexamethylene diisocyanate. Although the details of the thermal decomposition temperature of the N-substituted carbamic acid-O-methyl ester are not described, thermal decomposition proceeds at 200°C or higher. In the case of carrying out the thermal decomposition reaction at the described temperature of 250°C under reduced pressure, since these conditions exceed the boiling point of the N-substituted carbamic acid-O-methyl ester, the thermal decomposition reaction

55

iting the formation of products of undesirable side reactions during thermal decomposition of N-substituted carbamic acid-O-alkyl esters.

5 [0015] Among N-substituted carbamic acid-O-esters (N-substituted carbamic acid-O-esters refer to carbamic acid esters containing a carbamic acid group and an organic group, and in the explanation of the present invention, indicate N-substituted carbamic acid-O-aryl esters, in which the organic group is derived from an aromatic hydroxy group and/or N-substituted carbamic acid-O-alkyl esters in which the organic group is derived from an alcohol), N-substituted carbamic acid-O-aryl esters, in which the ester group that composes the N-substituted carbamic acid-O-ester is an aromatic group (namely, carbamic acid ester group derived from an aromatic hydroxy group) offer the advantage of allowing the setting of a lower temperature for the thermal decomposition reaction as compared with N-substituted carbamic acid-O-alkyl esters, in which the ester group is an alkyl group (see, for example, Patent Document 10). In other words, the above-mentioned undesirable side reaction products can be inhibited if it were possible to set the thermal decomposition temperature to a low temperature.

10 [0016] On the other hand, the production of such N-substituted carbamic acid-O-aryl esters is more difficult than the production of N-substituted carbamic acid-O-alkyl esters. This is caused by the reactivities of the alcohol and aromatic hydroxy compound used as raw materials of their respective esterification reactions. The first reason for this is that aromatic hydroxy compounds have lower nucleophilicity than alcohols. The second reason is that the esterification reaction proceeds with difficulty due to the weakly acidic nature of aromatic hydroxy compounds.

15 [0017] Patent Document 11 describes a method for producing aliphatic N-substituted carbamic acid-O-aryl ester without using phosgene. In this method, N-substituted carbamic acid-O-aryl ester is produced oxidatively using a precious metal catalyst from a primary amine, carbon monoxide and an aliphatic alcohol or aromatic hydroxy compound. However, this method has the problems of a complex procedure and considerable costs. These problems refer to the use of highly toxic carbon monoxide, and the need to recover the catalyst from the product in the form of N-substituted carbamic acid-O-aryl ester due to the use of an expensive precious metal catalyst. Patent Document 12 describes a method for producing N-substituted carbamic acid-O-aryl ester by reacting an N-alkyl-N,N'-dialkyl urea, an aromatic hydroxy compound and hydrogen chloride gas. However, this method also has a complicated procedure and requires considerable costs. Namely, this method uses corrosive hydrogen chloride gas, consumes an expensive and uncommon urea compound, and results in difficulty in recovering the N-substituted carbamic acid-O-aryl ester from a hydrochloride of N,N'-dialkylamine formed as a by-product. In the method described in Patent Document 13, N-substituted carbamic acid-O-aryl ester is produced by a one-stage reaction between urea, aromatic hydroxy compound and aliphatic primary amine. In the method described in Patent Document 14, urea and an aromatic hydroxy compound are reacted in a first step, and N-substituted carbamic acid-O-aryl ester is produced by reacting with primary amine in a subsequent second step.

20 [0018] Technologies have also been disclosed for improving the low nucleophilicity of aromatic hydroxy compounds and the difficulty in shifting the equilibrium thereof. Patent Document 15 and Patent Document 16 disclose methods for producing aliphatic O-aryl urethane from a single-stage reaction of urea and/or O-aryl carbamate (non-N-substituted carbamic acid-O-aryl ester), aromatic hydroxy compound and aliphatic primary amine. In these methods, considerable improvement is made with respect to the removal of ammonia, such as by using reactive distillation or a method for introducing a large amount of inert gas. Patent Document 17 discloses a method for continuously producing urethane while continuously supplying a primary polyamine, urea and/or non-N-substituted carbamic acid ester and organic hydroxy compound to a reaction column to form the corresponding urethane and continuously extracting ammonia formed within the reaction column from the reaction column. On the other hand, Patent Document 18 describes a method that does not use a lowly nucleophilic aromatic hydroxy compound as described above. This method allows a corresponding N-alkyl carbamic acid-O-aryl ester to be obtained at a yield of 90 to 95% by reacting a primary alkyl amine with a diaryl carbonate in the presence of a solvent such as benzene, dioxane or carbon tetrachloride. This method has the advantage of allowing the obtaining of N-substituted carbamic acid-O-aryl ester at a low temperature as well as high selectivity. However, it is currently difficult to apply this method industrially due to the high cost of the diaryl carbonate.

25 [0019] In the case of methods using safe and inexpensive raw materials in the form of urea and carbonic acid derivatives, it is necessary to use an excess of urea or carbonic acid derivative based on the amino group of the primary amine in order to improve the yield based on the comparatively expensive primary amine. However, this does not mean that these methods have successfully inhibited side reactions or improved selectivity with respect to the primary amine.

30 [0020] The method described in Patent Document 19 contains recovering non-N-substituted carbamic acid-O-aryl ester from a resulting reaction liquid and recycling for use as a raw material of the reaction when producing N-substituted carbamic acid-O-aryl ester by reacting an aliphatic primary polyamine, aromatic hydroxy compound, urea and/or non-N-substituted carbamic acid-O-aryl ester. Namely, this method serves to reduce the amount used of the urea and/or non-N-substituted carbamic acid-O-aryl ester. In this method, after obtaining an aromatic hydroxy compound and isocyanic acid by thermal decomposition of non-N-substituted carbamic acid-O-aryl ester contained in the reaction liquid, and distilling the aromatic hydroxy compound at a low temperature, the isocyanic acid is again reacted with the distilled aromatic hydroxy compound and recovered in the form of non-N-substituted carbamic acid-O-aryl ester. However, in addition to this method having a complex procedure, the recovery rate of the non-N-substituted carbamic acid-O-aryl

ester is unsatisfactory.

[0021] In this manner, a method for producing N-substituted carbamic acid-O-aryl ester using safe urea or carbonic acid derivative that satisfies the amounts of urea or carbonic acid derivative and primary amine has yet to be disclosed. This is due to the low nucleophilicity of aromatic hydroxy compounds as previously described as well as the low cationicity of the carbonyl carbons of the urea and carbonic acid derivative.

[0022] Despite the above-mentioned problems, since it would be extremely industrially useful to obtain isocyanates without using phosgene, various methods have been proposed for improving methods for producing isocyanates using N-substituted carbamic acid-O-esters in addition to those described above. There are methods that are carried out in a gaseous phase at high temperatures as well as methods that are carried out in a liquid phase under comparatively low temperature conditions. As was previously described, however, since there are cases in which side reactions occur during the course of thermal decomposition of N-substituted carbamic acid-O-alkyl esters resulting in the formation of precipitates, polymeric substances and obstructions in the reactor and recovery apparatuses or the formation of substances adhered to the reactor walls, economic efficiency is poor in the case of producing isocyanates over an extended period of time. Thus, although, for example, the use of chemical methods such as the use of a special catalyst (see Patent Document 20 or Patent Document 21), or a catalyst in combination with an inert solvent (see Patent Document 22) have been proposed for improving yield during thermal decomposition of N-substituted carbamic acid-O-alkyl esters, problems encountered during the production of N-substituted carbamic acid-O-aryl esters have yet to be solved. For example, the method described in Patent Document 23 is a method for producing hexamethylene diisocyanate. This method contains thermal decomposition of hexamethylene dicarbamic acid-O-ethyl ester in the presence of a catalyst mixture containing methyl toluene sulfonate and diphenyl tin dichloride while using dibenzyl toluene as a solvent. However, production and isolation of the starting components as well as purification and arbitrary recovery of the solvent and catalyst mixture are not described in detail, and the economic efficiency of this method is extremely low.

[0023] In the method described in Patent Document 24, N-substituted carbamic acid-O-alkyl ester is easily decomposed to isocyanate and alcohol in a carbon-containing fluidized bed without using a catalyst. However, the yield of isocyanate obtained in the thermal decomposition reaction is from about 83.8 to 98.7%, and although reaction by-products and the like are not described, since N-substituted carbamic acid-O-alkyl ester is still subjected to thermal decomposition and the resulting compounds contain isocyanate and alcohol that are susceptible to the occurrence of reverse reactions in the same manner as in the prior art, the above-mentioned side reactions cannot be said to be inhibited. In the method described in Patent Document 25, a circulating method to produce an alicyclic diisocyanate by reacting an alicyclic primary diamine, urea and alcohol to obtain an alicyclic dicarbamic acid-O-alkyl ester, followed by subjecting the alicyclic dicarbamic acid-O-alkyl ester to thermal decomposition. This method succeeds at reducing the amounts of materials used by recovering unreacted alcohol, non-N-substituted carbamic acid-O-ester and dialkyl carbonates, and recirculating a portion of the reaction mixture of the thermal decomposition step along with by-products to the initial step. However, this method requires the alicyclic dicarbamic acid-O-alkyl ester to be distilled at a high temperature of about 230°C to remove residue unable to be used in the production method. Since this high distillation temperature is within the temperature range at which carbamic acid-O-alkyl esters undergo thermal decomposition, isocyanate groups formed during distillation ends up reacting with the alicyclic dicarbamic acid-O-alkyl ester resulting in the possibility of the formation of solid polymers. Although it is described in the examples that yield is maintained over a long operating time, there is no description regarding the presence of accumulation of polymers or clogging of the apparatus due to the occurrence of side reactions.


[0024] In addition, the method described in Patent Document 26 involves partially removing worthless by-products prior to thermal decomposition of N-substituted carbamic acid-O-alkyl ester. In this method, however, since N-substituted carbamic acid-O-alkyl ester is also removed together with the partially removed by-products, the yield of isocyanate based on primary amine and carbonic acid derivative is ultimately decreased. In addition, polymeric compounds are formed as a result of by-products remaining in the reactor without being discharged from the reactor being heated, and since these compounds adhered to the reactor, continuous operation over a long period of time is difficult.

[0025] In reactions for obtaining N-substituted carbamic acid-O-(alkyl or aryl) esters by reacting urea and carbonic acid derivative (or carbamic acid derivative) with a primary amine and alcohol or aromatic hydroxy compound, urea and carbonic acid derivative (or carbamic acid derivative) are used in excess to improve the selectivity of the expensive primary amine.


[0026] A reaction formula of N-substituted carbamic acid-O-alkyl ester in the case of using a primary amine and urea as raw materials is shown in the following formula (iv). Although an adequate amount of urea is present based on the primary amine in the initial phase of the reaction, as the reaction enters the latter phase, the concentrations of both (primary amine and urea) decrease resulting in the N-substituted carbamic acid-O-alkyl ester being present at a high concentration. As was previously described, the cationicity of urea and carbonyl carbons of carbonic acid derivatives is low (due to accepting electron donation by NH₂ groups and alkoxy groups) and the difference in reactivity between carbonyl carbons of the product in the form of N-substituted carbamic acid-O-alkyl ester and the primary amine is small. Thus, unless the amount of urea is present in excess based on the primary amine, the reaction proceeds as indicated

by formula (v) during the latter phase of the reaction. Namely, the primary amine reacts with the product in the form of N-substituted carbamic acid-O-(alkyl or aryl) ester causing it to be denatured to a compound having undesirable N,N-di-substituted urea bonds. In the case of using polyamine, since each amino group reacts successively, various denatured forms are formed in addition to that shown in the following formula (v). In addition, reactions also occur such as that based on the following formula (vii) involving reaction with isocyanate formed according to the following formula (vi), and it can be easily presumed based on a knowledge of organic chemistry and reaction rates that as the N-substituted carbamic acid-O-(alkyl or aryl) ester accumulates and urea concentration decreases, the formation of these denaturation products increases dramatically. Polymerized high molecular weight substances are naturally additionally formed based on the principles of the formulas (v), (vi) and (vii). Since compounds having N,N-di-substituted urea bonds formed due to this denaturation have low levels of reactivity, re-addition of dissociated alcohol becomes difficult. Although such reactions occur at high temperatures, since the formation of isocyanates by thermal decomposition of N-substituted carbamic acid-O-(alkyl or aryl) ester also begins to occur at high temperatures, this results in the occurrence of a diverse range of side reactions.

(Initial reaction)





(Latter reaction: reaction with N-substituted carbamic acid-O-(alkyl or aryl) ester)



(Latter reaction: reaction with isocyanate)

Isocyanate formation



[0027] Since polymeric substances formed based on the above-mentioned reactions have extremely low solubility in solvents and the like, they frequently adhere and solidify in the reactor, thereby making such methods industrially unsatisfactory. In response to such problems, although methods have been examined (see Patent Document 4) for producing N-substituted carbamic acid-O-alkyl ester by producing bis-urea from primary amine, urea and alcohol and then reacting the bis-urea with alcohol as previously described, these methods are targeted at reaction with a highly nucleophilic alcohol and are not carried out to solve the problem in thermal decomposition of the N-substituted carbamic acid-O-alkyl ester, thereby preventing such methods from solving the problems that occur during thermal decomposition of N-substituted carbamic acid-O-alkyl ester as described above. In addition, although a method for producing bis-urea has been proposed involving the reaction of molten urea and amine in the absence of a solvent (see, for example, Non-Patent Document 6), due to the high melting temperature of urea (about 135°C), there are many cases in which the reaction proceeds non-uniformly resulting in the occurrence of urea denaturation reactions and reactions resulting in the formation of compounds having N,N-di-substituted urea bonds, thereby preventing the above-mentioned problems from being solved.

[0028] In addition, a method for purifying such polymeric substances by crystallization has also been developed (Patent Document 27). In this method as well, it is difficult to selectively crystallize compounds having similar structures at high yield, while on the other hand, energy is expended for separating solids and liquids as well as recovery of the crystallization solvent.

Prior Art Documents

Patent Documents

5 **[0029]**

- Patent Document 1 : U.S. Patent No. 7122697
Patent Document 2 : U.S. Patent No. 2677698
Patent Document 3 : U.S. Patent No. 4713476
10 Patent Document 4 : EP Application No. 0568782
Patent Document 5 : EP Application No. 0657420
Patent Document 6 : U.S. Patent No. 4497963
Patent Document 7 : U.S. Patent No. 4290970
Patent Document 8 : Japanese Patent Application Laid-open No. H6-41045
15 Patent Document 9 : U.S. Patent No. 2,409,701
Patent Document 10 : U.S. Patent No. 3992430
Patent Document 11 : U.S. Patent No. 4297501
Patent Document 12 : U.S. Patent No. 3873553
Patent Document 13 : U.S. Patent No. 4925971
20 Patent Document 14 : Japanese Patent Application Laid-open No. H4-164060
Patent Document 15 : Japanese Patent Application Laid-open No. H2-759
Patent Document 16 : Japanese Patent Application Laid-open No. H3-20254
Patent Document 17 : Japanese Patent Application Laid-open No. H8-277255
Patent Document 18 : Japanese Patent Application Laid-open No. S52-71443
25 Patent Document 19 : Japanese Patent Application Laid-open No. H7-157463
Patent Document 20 : U.S. Patent No. 2692275
Patent Document 21 : U.S. Patent No. 3734941
Patent Document 22 : U.S. Patent No. 4081472
Patent Document 23 : U.S. Patent No. 4388426
30 Patent Document 24 : U.S. Patent No. 4482499
Patent Document 25 : EP Application No. 0355443
Patent Document 26 : Japanese Patent No. 3382289
Patent Document 27 : Japanese Patent No. 2804132

35 Non-Patent Documents

[0030]

- Non-Patent Document 1 : Berichte der Deutschen Chemischen Gesellschaft, Vol. 3, p. 653, 1870
40 Non-Patent Document 2: Journal of the American Chemical Society, Vol. 73, p. 1831, 1951, line 9 from the top of the right column
Non-Patent Document 3 : Journal of the Chemical Society, Perkin Transactions 1: Organic and Bio-Organic Chemistry (1972-1999), pp. 141-143, 1976
Non-Patent Document 4 : Berichte der Deutschen Chemischen Gesellschaft, Vol. 3, p. 649, 1870
45 Non-Patent Document 5 : Journal of the American Chemical Society, Vol. 81, p. 2138, 1959
Non-Patent Document 6 : Polymer, Vol. 35, p. 3766, 1994
Non-Patent Document 7: Yadav et al; Synlett 2005, No. 20, pp 3055-58 discloses a three component coupling strategy for synthesis of 4-aminobenzoxazinones. The reactions involve substituted salicylaldehydes, N-substituted ureas/carbamates and ammonia acetate or amine. An N-substituted carbamic acid-O-aryl ester is formed as an
50 intermediate product.

Disclosure of Invention

Problems to be Solved by the Invention

55 **[0031]** As has been described above, even with any of the methods examined thus far, it is still difficult to obtain N-substituted carbamic acid-O-(alkyl or aryl) esters at high yield using urea and non-N-substituted carbamic acid-O-esters as raw materials, and generally the reaction products thereof include compounds having urea bonds (-NHCONH-),

compounds having urea terminals (-NHCONH₂), compounds having amino group terminals (-NH₂) or compounds having allophanate bonds and the like in nearly all cases. In methods using the least expensive and safest raw material in the form of urea, the problem of inhibiting increases in the amounts of urea and primary amine used caused by their side reactions have yet to be solved, and an alternative to the phosgene method has yet to be achieved due to clogging and other problems relating to the process as well as the high production cost of isocyanates.

[0032] In this manner, numerous problems involving the production of isocyanate precursors in the form of N-substituted carbamic acid-O-(alkyl or aryl) esters still remain, and there is an urgent need to solve these problems.

[0033] As has been previously described, various methods have been proposed as methods for producing N-substituted carbamic acid-O-(alkyl or aryl) ester using urea or carbonic acid derivatives. Corresponding isocyanates are known to be able to be obtained by thermal decomposition of N-substituted carbamic acid-O-(alkyl or aryl) esters.

[0034] However, in the case of using an N-substituted carbamic acid-O-aryl ester as a precursor, the formed isocyanate and the raw material in the form of the N-substituted carbamic acid-O-aryl ester react due to the high thermal decomposition temperature resulting in increased susceptibility to the occurrence of denaturation. In addition, in the thermal decomposition reaction, both alcohol and isocyanate are present in the gaseous phase. Since the reaction between alcohol and isocyanate is rapid, a reaction occurs in which the isocyanate returns to N-substituted carbamic acid-O-aryl ester by a reverse reaction in the gaseous phase, thereby resulting in increased susceptibility to the occurrence of clogging of lines such as the line for extracting isocyanate from the reactor.

[0035] On the other hand, in the case of using an N-substituted carbamic acid-O-aryl ester as a precursor, there are problems with the production of the N-substituted carbamic acid-O-aryl ester. This is due to the low nucleophilicity of aromatic hydroxy compounds and the difficulty in increasing reaction selectivity for the N-substituted carbamic acid-O-aryl esters from primary amines. The cause of the decrease in selectivity is the slow esterification rate and the reaction rates of other undesirable side reactions being faster than the esterification due to the low nucleophilicity of aromatic hydroxy compounds.

[0036] Also, the disclosed methods require the use of an excess of urea or carbonic acid derivative based on the amino groups of the primary amine in order to improve the yield based on the comparative expensive primary amine. However, a method for efficiently recovering and reusing the excess urea or carbonic acid derivative has yet to be described, and increases in basic units of urea or carbonic acid derivative are unable to be avoided.

[0037] The inventors of the present invention have previously disclosed a method for inhibiting thermal denaturation reactions of N-substituted carbamic acid-O-alkyl esters by using a specific aromatic hydroxy compound as a reaction solvent (International Patent Publication WO 2008/120645), and have also disclosed a method for improving thermal stability of aromatic hydroxy compounds by having a trace amount of a carbonic acid derivative present during thermal decomposition of N-substituted carbamic acid-O-alkyl ester, which is obtained by reacting carbonic acid ester and primary amine, in the presence of an aromatic hydroxy compound (International Patent Publication WO 2008/084824).


[0038] As a result of studies conducted by the inventors of the present invention, it was clearly determined that when a specified amount or more of urea or carbonic acid derivative is present in the reaction liquid of an N-substituted carbamic acid-O-aryl ester obtained by using urea or carbonic acid derivative, the adherence and/or accumulation of insoluble solids presumed to be reactants of the urea and/or carbonic acid derivative and isocyanate is observed during the course of obtaining isocyanate by thermal decomposition of the N-substituted carbamic acid-O-aryl ester, thereby resulting in the potential for causing problems including those relating to long-term operation of production equipment.

[0039] An object of the present invention is to provide a method for producing N-substituted carbamic acid-O-aryl ester that is free of the various problems described above, and to provide a method for producing isocyanate by thermal decomposition of the N-substituted carbamic acid-O-aryl ester.


[0040] In view of the above, as a result of conducting extensive studies on the above-mentioned problems, the inventors of the present invention found that the problems are solved by obtaining N-substituted carbamic acid-O-aryl ester derived from a compound having ureido groups and an aromatic hydroxy compound from the compound having ureido groups and a specific aromatic hydroxy composition, and producing isocyanate by subjecting the N-substituted carbamic acid-O-aryl ester to thermal decomposition, thereby leading to completion of the present invention.

[0041] Namely, in a first aspect thereof, the present invention provides:

[1] A method for producing at least one N-substituted carbamic acid-O-aryl ester (wherein the N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to an aromatic ring) derived from a compound having an ureido group represented by the following formula (1) and an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2), the method comprising the step of carrying out esterification or esterification and transesterification from the compound having the ureido group and the aromatic hydroxy composition:



(1)




(2)

(wherein

R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number a of ureido group(s), and the a represents an integer of from 1 to 10, and ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at arbitrary location(s) that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and the the b represents an integer of from 1 to 6).

[2] The production method according to item [1] above, wherein the compound having the ureido group is a compound having an ureido group obtained by a process comprising the following step A:

step (A): a step of obtaining at least one type of compound having an ureido group derived from an organic primary amine represented by the following formula (3) and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction:



(3)


(wherein

R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number c of NH₂ group(s), and the c represents an integer of from 1 to 10).

[3] The production method according to item [2] above, wherein the organic primary amine is an organic primary monoamine or an organic primary diamine.

[4] The production method according to item [2] above, wherein the step (A) is carried out in the presence of water and/or alcohol and/or an aromatic hydroxyl composition containing at least one type of aromatic hydroxy compound.

[5] The production method according to item [2], wherein the step (A) is carried out in the presence of an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2):



(2)

(wherein

ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at an arbitrary location(s) that maintain aromatic properties, which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and the b represents an integer of from 1 to 6).

[6] The production method according to item [2], wherein the step (A) is carried out in the presence of an alcohol represented by the following formula (4):




(wherein

R^2 represents an aliphatic group, or an aliphatic group in which an aromatic group is bonded, which contains an integral number of carbon atoms within a range of from 1 to 14, and the OH group of the alcohol represented by formula (4) is an OH group that is not bonded to an aromatic ring).

[0042] Further, in a second aspect thereof, the present invention provides:

[7] A composition for transfer and storage of a compound having an ureido group, wherein the number of molecules of at least one type of aromatic hydroxy compound represented by the following formula (2) in an aromatic hydroxy composition that contains the aromatic hydroxy compound, based on the number of the ureido group contained in the compound having the ureido group represented by the following formula (1) in the composition, is an integer of from 1 to 100:




(wherein

R^1 represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number a of ureido group(s), and the a represents an integer of from 1 to 10), and ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at arbitrary location(s) that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and the b represents an integer of from 1 to 6).

[8] The production method according to item [1] above, further comprising the following steps (A) and (B):

step (A): a step of obtaining at least one type of compound having an ureido group derived from an organic primary amine represented by the following formula (3) and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction, and

step (B): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting the at least one type of compound having the ureido group and the aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2) in a liquid phase, and extracting ammonia formed as a by-product to a gaseous phase:



(wherein

R^1 represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number c of NH_2 group(s), and the c represents an integer of 1 to 10, and

EP 2 322 504 B9

ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at arbitrary location(s) that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and the b represents an integer of 1 to 6).

5

[9] The production method according to item [1] above, further comprising the following steps (A), (R) and (P):

step (A): a step of obtaining at least one type of compound having an ureido group derived from an organic primary amine represented by the following formula (3) and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction,


10

step (R): a step of obtaining N-substituted carbamic acid-O-R² ester by reacting the at least one type of compound having the ureido group and an alcohol represented by the following formula (4) in a liquid phase and extracting ammonia formed as a by-product to a gaseous phase (wherein the N-substituted carbamic acid-O-R² ester represents an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to an R² group derived from an alcohol), and

15

step (P): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting the N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2) in a liquid phase and extracting alcohol formed as a by-product to a gaseous phase:

20



25



30

(wherein

R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number c of NH₂ group(s), and the c represents an integer of from 1 to 10, ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at arbitrary location(s) that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and the b represents an integer of from 1 to 6, and

35

R² represents an aliphatic group, or an aliphatic group in which an aromatic group is bonded, which contains an integral number of carbon atoms within a range of from 1 to 14, and the OH group of the alcohol represented by formula (4) is an OH group that is not bonded to an aromatic ring).

40


[10] The production method according to item [8] or [9] above, wherein the organic primary amine is an aromatic organic primary monoamine represented by the following formula (5), the following step (C) is carried out after the step (B), after the step (R) or after the step (P), and N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with a methylene group (-CH₂-), is obtained from the N-substituted carbamic acid-O-(R² or aryl) ester obtained in the step (B), the step (R) or the step (P):

45

50

step (C): a step of obtaining N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with a methylene group (-CH₂-), by reacting the N-substituted carbamic acid-O-(R² or aryl) ester with formaldehyde or a methylenating crosslinking agent and crosslinking aromatic groups derived from the aromatic organic primary monoamine contained in the N-substituted carbamic acid-O-(R² or aryl) ester with the methylene group (-CH₂-) (wherein the N-substituted carbamic acid-O-(R² or aryl) ester represents an N-substituted carbamic acid-O-R² ester or an N-substituted carbamic acid-O-aryl ester):

55



5

(wherein

at least one location at the ortho position and/or para position of the NH₂ group of an aromatic organic primary monoamine represented by formula (5) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from the group consisting of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of 0 to 7, and a total number of carbon atoms that compose the aromatic organic primary monoamine represented by formula (5) is an integer of from 6 to 13).

10

15

20

[11] The production method according to item [8] or [9] above, comprising the step of recovering urea by carrying out the following step (D) before the step (B) or the step (P) and/or simultaneous to the step (B) or the step (P):

step (D): a step of removing urea by distillation or sublimation.

25

[12] The production method according to item [8] or [9] above, comprising the following step (E) of recycling the recovered urea to the step (A):

step (E): a step of recycling urea recovered in step (D) to step (A).

30

[13] The production method according to item [1] above, comprising the step of obtaining an isocyanate represented by the following formula (6), which is derived from the N-substituted carbamic acid-O-aryl ester, and an aromatic hydroxy composition by carrying out thermal decomposition on the N-substituted carbamic acid-O-aryl ester in the following step (F):

35

step (F): a step of obtaining an isocyanate and an aromatic hydroxy composition from the N-substituted carbamic acid-O-aryl ester:



40

(wherein


R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number s of NCO group(s), and the s represents an integer of from 1 to 10).

45

[14] The production method according to item [8] or [9] above, as defined in claim 14.

[15] The production method according to any one of items [1], [8] and [9], wherein an aromatic hydroxy compound that composes the aromatic hydroxy composition is at least one type of aromatic hydroxy compound represented by the following formula (7):

50




55

(wherein

ring A represents an aromatic ring selected from a benzene ring, a naphthalene ring and an anthracene ring,

the OH groups and groups R⁷ to R¹⁴ respectively represent groups substituted at arbitrary location(s) that maintain aromatic properties of ring A, groups R⁷ to R¹⁴ may respectively and independently substitute ring A, groups R⁷ to R¹⁴ may bond together to form a ring with an aromatic ring by bonding to ring A, groups R⁷ to R¹⁴ respectively and independently represent a hydrogen atom, a halogen atom or a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group, an aryl group having a hydroxy group, an aralkyl group and an ether group (substituted and/or unsubstituted alkyl ether and/or substituted and/or unsubstituted aryl ether and/or substituted and/or unsubstituted aralkyl ether group), and/or a group to which one or more types of groups selected from the group are bonded, and/or a group to which one or more types of groups selected from the group are bonded by saturated aliphatic bonds and/or ether bonds, and ring A and groups R⁷ to R¹⁴ are composed of an integral total number of carbon atoms within a range of from 6 to 50, b represents an integer of from 1 to 6, d, e, f, g, h, i, j and k represent integers of from 0 to 5, the value of d + e + f + g + h + i + j + k represents an integer equal to 6-b in the case ring A is the benzene ring, represents an integer equal to 8-b in the case ring A is the naphthalene ring, or represents an integer equal to 10-b in the case ring A is the anthracene ring, and a group selected from groups R⁷ to R¹⁴ as described above may be cyclically bonded to ring A by carbon-carbon bonds and/or ether bonds).

[16] The composition for transfer and storage of the compound having the ureido group according to item [7] above, wherein the aromatic hydroxy compound that composes the aromatic hydroxy composition is at least one type of aromatic hydroxy compound represented by the following formula (7):



(7)

(wherein

ring A represents an aromatic ring selected from a benzene ring, a naphthalene ring and an anthracene ring, the OH groups and groups R⁷ to R¹⁴ respectively represent groups substituted at arbitrary location(s) that maintain aromatic properties of ring A, groups R⁷ to R¹⁴ may respectively and independently substitute ring A, groups R⁷ to R¹⁴ may bond together to form a ring with an aromatic ring by bonding to ring A, groups R⁷ to R¹⁴ respectively and independently represent a hydrogen atom, halogen atom or group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group, an aryl group having a hydroxy group, an aralkyl group and an ether group (substituted and/or unsubstituted alkyl ether and/or substituted and/or unsubstituted aryl ether and/or substituted and/or unsubstituted aralkyl ether group), and/or a group to which one or more types of groups selected from the group are bonded, and/or a group to which one or more types of groups selected from the group are bonded by saturated aliphatic bonds and/or ether bonds, and ring A and groups R⁷ to R¹⁴ are composed of an integral total number of carbon atoms within a range of from 6 to 50, b represents an integer of from 1 to 6, d, e, f, g, h, i, j and k represent integers of from 0 to 5, the value of d + e + f + g + h + i + j + k represents an integer equal to 6-b in the case ring A is the benzene ring, represents an integer equal to 8-b in the case ring A is the naphthalene ring, or represents an integer equal to 10-b in the case ring A is the anthracene ring, and a group selected from groups R⁷ to R¹⁴ as described above may be cyclically bonded to ring A by carbon-carbon bonds and/or ether bonds).

[17] The production method according to any one of items [2], [8] and [9], wherein the aromatic hydroxy compound that composes the aromatic hydroxy composition has a standard boiling point that differs by 10°C or more from the standard boiling point of an isocyanate having a structure in which all amino groups of the organic primary amine (primary amino groups) are converted to isocyanate groups.

[18] The production method according to any one of items [1], [8] and [9], wherein the aromatic hydroxy compound contained in the aromatic hydroxy composition is a monovalent and/or divalent aromatic hydroxy compound (namely, that in which b is 1 and/or 2).

[19] The composition for transfer and storage of the compound having the ureido group according to item [7] above, wherein the aromatic hydroxy compound contained in the aromatic hydroxy composition is a monovalent and/or divalent aromatic hydroxy compound (namely, that in which b is 1 and/or 2).

[20] The production method according to item [18] above, as defined in claim 20.

[21] The production method according to item [8] or [9] above, further comprising the following step (G) of recovering ammonia formed as a by-product in the step (A) and/or the step (B) and/or the step (R); regenerating urea by reacting the ammonia with carbon dioxide; and recycling the urea to the step (A):

5 step (G): a step of recovering ammonia formed as a by-product, regenerating urea by reacting the ammonia with carbon dioxide, and recycling the urea to step (A)

Advantageous Effects of the Invention

10 **[0043]** According to the production method of N-substituted carbamic acid-O-aryl ester of the present embodiment, by producing the N-substituted carbamic acid-O-aryl ester from a compound having an ureido group and an aromatic hydroxy composition, inhibiting side reactions and efficiently recovering and reusing urea and the like used in excess in the reaction, N-substituted carbamic acid-O-aryl ester can be produced without any losses in the amounts of urea and organic primary amine used. In addition, since various side reaction products can be inhibited and the various side reaction products can be dissolved by an aromatic hydroxy compound and removed outside the system, operation is possible over a long period of time. Moreover, the composition for transfer and storage of a compound having an ureido group can be preferably used as a raw material for production of the N-substituted carbamic acid-O-aryl ester.

Brief Description of the Drawings

20 **[0044]**

FIG. 1 shows a conceptual drawing depicting a production method of a compound having the ureido group(s) according to a step (A) in the present embodiment;

25 FIG. 2 shows a conceptual drawing depicting a step (B) in the present embodiment;

FIG. 3 shows a conceptual drawing depicting a step (R) in the present embodiment;

FIG. 4 shows a conceptual drawing depicting a step (P) in the present embodiment;

FIG. 5 shows a conceptual drawing depicting a step (P) in the present embodiment;

30 FIG. 6 shows a conceptual drawing depicting a step (P) in the present embodiment;

FIG. 7 shows a conceptual drawing depicting an N-substituted carbamic acid ester production method that uses an aromatic hydroxy composition containing an active aromatic hydroxy compound and an inactive aromatic hydroxy compound in the present embodiment;

FIG. 8 shows a conceptual drawing depicting one aspect of the present embodiment that combines a route 1) with steps (D), (E), (F) and (G);

35 FIG. 9 shows a conceptual drawing depicting one aspect of the present embodiment that combines a route 2) with steps (D), (E), (F) and (G);

FIG. 10 shows a conceptual drawing depicting one aspect of the present embodiment that combines a route 3) with steps (D), (E), (F) and (G);

FIG. 11 shows a conceptual drawing depicting one aspect of the present embodiment that combines a route 4) with steps (D), (E), (F) and (G);

40 FIG. 12 shows a conceptual drawing depicting one aspect of the present embodiment that combines a route 5) with steps (D), (E), (F) and (G);

FIG. 13 shows a conceptual drawing depicting an N-substituted carbamic acid ester production apparatus in an example of the present embodiment;

45 FIG. 14 shows a conceptual drawing depicting an N-substituted carbamic acid ester production apparatus in an example of the present embodiment;

FIG. 15 shows a conceptual drawing depicting an N-substituted carbamic acid ester production apparatus in an example of the present embodiment;

FIG. 16 shows a conceptual drawing depicting a transesterification reaction apparatus in an example of the present embodiment;

50 FIG. 17 shows a conceptual drawing depicting an isocyanate production apparatus in an example of the present embodiment;

FIG. 18 shows a conceptual drawing depicting an isocyanate production apparatus in an example of the present embodiment;

55 FIG. 19 shows a conceptual drawing depicting an apparatus for producing a compound having ureido groups in an example of the present embodiment;

FIG. 20 shows a conceptual drawing depicting an N-substituted carbamic acid ester production apparatus in a comparative example of the present embodiment;

FIG. 21 shows a conceptual drawing depicting an N-substituted carbamic acid ester production apparatus in an example of the present embodiment;

FIG. 22 shows a conceptual drawing depicting a urea production apparatus in an example of the present embodiment;

FIG. 23 shows the $^1\text{H-NMR}$ spectrum of a composition for transfer and storage of a compound having the ureido groups of Example 97 of the present embodiment;

FIG. 24 shows the $^1\text{H-NMR}$ spectrum of a composition for transfer and storage of a compound having the ureido groups of Example 106 of the present embodiment;


FIG. 25 shows the $^1\text{H-NMR}$ spectrum of a composition for transfer and storage of a compound having the ureido groups of Example 122 of the present embodiment; and

FIG. 26 shows the $^1\text{H-NMR}$ spectrum of a composition for transfer and storage of a compound having the ureido groups of Example 142 of the present embodiment.

Mode for Carrying Out the Invention

[0045] An explanation is first given of a composition for transfer and storage of a compound having ureido groups in the present embodiment. To begin with, an explanation is given of the composite ratios and so forth of compounds contained in the composition for transfer and storage of a compound having ureido groups, and is followed by a detailed explanation of compounds contained in the composition for transfer and storage of a compound having ureido groups.

[0046] The composition for transfer and storage of a compound having ureido groups in the present embodiment refers to a composition for transferring and storing compounds having ureido groups, in which the number of molecules of an aromatic hydroxy compound in an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)) based on the number of ureido groups contained in a compound having ureido groups represented by the following formula (1) in the composition is an integer of from 1 to 100:



(wherein,

R^1 represents an organic group which contains an integral number of carbon atoms within a range of from 1 to 85, and which is substituted by a number of ureido groups, and a represents an integer of from 1 to 10, and ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy groups at arbitrary locations that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and b represents an integer of from 1 to 6).

[0047] Details of the compound having ureido groups represented by formula (1) and the aromatic hydroxy compound represented by formula (2) will be subsequently explained.

[0048] Since the compound having ureido groups used in the present embodiment easily forms hydrogen bonds between molecules thereof due to the ureido groups that compose the compound having ureido groups, there are many cases in which it has a high melting point. In the transfer of such a compound having ureido groups, transfer is carried out by, for example, crushing a solid compound having ureido groups or shaping such as by forming into pellets. Alternatively, methods are also employed in which the compound having ureido groups is heated to a temperature higher than the melting point thereof to transfer the compound having the ureido groups in the form of a liquid. However, in the case of transferring a solid compound having ureido groups that has undergone shaping processing, there are cases in which this causes clogging of the transfer line since there is considerable variation in the shape of the compound having ureido groups. Consequently, there are many cases in which complicated apparatuses are required to stably transfer a fixed amount of compound having the ureido groups or a step is required for aligning the shape of the compound having ureido groups to within a certain range. On the other hand, in the case of heating a compound having the ureido groups and transferring in the form of a liquid, it is necessary to heat the compound having the ureido groups to a

temperature higher than the melting point thereof (for example, 150°C) in consideration of preventing solidification during transfer. In the case of holding the compound having the ureido groups under such high temperatures, there are frequently cases in which isocyanate may be formed at undesirable locations due to the occurrence of a thermal decomposition reaction of the compound having the ureido groups or the occurrence of a thermal denaturation reaction of the compound having the ureido groups. The composition of the present embodiment demonstrates the effect of being able to maintain the stability of the compound having the ureido groups by inhibiting thermal denaturation of the compound having the ureido groups in the composition during transfer or storage of the composition. Although the mechanism by which the effect of inhibiting thermal denaturation of the compound having the ureido groups is demonstrated is not clear, the inventors of the present invention presumed that, as a result of the aromatic hydroxy compound that composes the composition forming a state in which urethane bonds have difficulty in approaching each other due to the formation of hydrogen bonds between ureido bonds (-NHCONH₂) of the compound having the ureido groups and the weakly acidic aromatic hydroxy compound, it is difficult for a reaction to occur that forms compounds having ureylene (-NHCONH-) groups.

[0049] Furthermore, ureylene groups (-NHCONH-) may be referred to as ureine groups in the explanation of the present embodiment.

[0050] The composition for transfer and storage can be preferably used in the production of N-substituted carbamic acid-O-aryl ester in particular (although the term N-substituted carbamic acid-O-aryl ester is used frequently in the following explanations, the term N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to an aromatic ring, the aromatic ring referring to an aromatic ring in which a group is bonded to an aromatic group, said group being selected from the group consisting of aromatic groups and/or aliphatic groups, and the aromatic ring being formed by bonding said group of integer numbers of at least 0 with the aromatic group, the details of which will be subsequently described). More specifically, the method contains transferring the composition for transfer and storage to an N-substituted carbamic acid-O-aryl ester synthesis step, applying a compound having ureido groups contained in the composition to an esterification reaction, and recovering the N-substituted carbamic acid-O-aryl ester formed. In general, the N-substituted carbamic acid-O-aryl ester synthesis step is carried out at a high temperature, and if compounds having the ureido groups are supplied in a state of having hydrogen bonds between molecules thereof, denaturation to compounds having thermally stable ureylene groups is thermodynamically advantageous. A compound having ureylene groups is a condensed form of the compound having ureido groups and is a high molecular weight compound. Thus, there are many cases in which problems occur due to the formation of polymers that adhere or solidify in the reactor. In addition, there are many cases in which the compound having the ureido groups contains compounds such as ammonia or urea. These compounds, and particularly urea, frequently undergo thermal decomposition to isocyanic acid and ammonia at the synthesis temperature range of the N-substituted carbamic acid-O-aryl ester synthesis step, and when the isocyanic acid reacts with the compound having ureido groups, they are denatured to compounds having biuret bonds. The compounds having biuret bonds have a high thermal decomposition temperature, and present difficulties in forming N-substituted carbamic acid-O-aryl ester due to reacting with aromatic hydroxy compounds. However, the inventors of the present invention found that denaturation of compounds having ureido groups during transfer and storage of the composition for transfer and storage is inhibited even if the composition for transfer and storage contains specific amounts of this ammonia and urea. This effect is particularly remarkable during long-term storage, and there are many cases in which denaturation is unable to be confirmed even during accelerated evaluation and testing. This finding was heretofore unknown and is surprising. Although the mechanism by which this effect is demonstrated is unclear, the inventors of the present invention have surmised that, during transfer and storage of the composition, the aromatic hydroxy compound inhibits denaturation of compounds of ammonia and urea or the like and the compounds having the ureido groups by trapping water and oxygen present in trace amounts, and when producing N-substituted carbamic acid-O-aryl ester using this composition, the aromatic hydroxy compound also functions as an esterification catalyst of the N-substituted carbamic acid-O-aryl ester.

[0051] In the composition for transfer and storage, the ratio of the number of molecules (y) of the aromatic hydroxy compound that composes the aromatic hydroxy composition to the number of ureido groups (x) that compose (or are contained in) the compound having ureido groups is within a range of from 1 to 100. Although y is preferably in excess based on x in the case of assuming the mechanism described above, on the other hand, in consideration of the transfer efficiency of the compound having the ureido groups and the size of the storage tank during storage, the ratio of y to x is preferably within a range of greater than 2 but less than 50, and more preferably within a range of greater than 3 but less than 20.

[0052] In the composition for transfer and storage, the compound having the ureido groups contained in the composition is preferably a compound having ureido groups that is obtained by reacting an organic primary amine, urea and/or carbonic acid derivative (to be subsequently explained in detail) and/or isocyanic acid and/or non-N-substituted carbamic acid. In consideration of ease of industrial acquisition, the compound having the ureido groups is more preferably a compound having ureido groups that is obtained by reacting an organic primary amine and urea.

[0053] The composition for transfer and storage may also contain components other than the compound having the

ureido groups and the aromatic hydroxy compound. Examples of such components may include the above-mentioned ammonia, urea, carbonic acid derivative (the carbonic acid derivative indicated in the present embodiment will be subsequently explained in detail), non-N-substituted carbamic acid, compound having a biuret bond, compound having a ureylene group, water, alcohol, inert gas (such as nitrogen gas, carbon dioxide gas, argon gas or ammonia gas) and N-substituted carbamic acid-O-ester such as N-substituted carbamic acid-O-(alkyl or aryl) ester obtained by reacting the composition for transfer and storage with an aromatic hydroxy composition (to be subsequently explained in detail). Although there are no particular limitations on the amounts at which these components are contained, if unnecessary side reactions appear to occur attributable to the storage temperature and the like, the amounts thereof are preferably adjusted as the occasion demands. Particularly noteworthy components are oxygen, ammonia, water, oxidizing substances and reducing substances. There are many cases in which the composition for transfer and storage contains compounds containing nitrogen atoms, or the aromatic hydroxy composition may be denatured as a result of being oxidized by oxygen resulting in the occurrence of phenomena such as coloring. In addition, since the composition becomes a flammable composition in nearly all cases, oxygen gas is to be managed using known methods in the same manner as ordinary storage of organic chemical substances carried out in this technical field. For example, the concentration of gaseous phase oxygen in a storage tank is controlled by purging with nitrogen so that the oxygen concentration is 10% or less, preferably 1 % or less and more preferably 100 ppm or less. In the case of allowing an inert gas such as nitrogen to flow through the gaseous phase, the oxygen concentration of the inert gas is controlled to 10 ppm or less. The dissolved ammonia concentration in the composition is controlled to 1 % by weight or less and preferably to 0.1 % by weight or less. The control method may be a known method such as purging the liquid phase with an inert gas such as nitrogen gas. Since there are cases in which large amounts of water may cause phenomena that prevent the composition from being uniform, the water concentration in the composition is 10% by weight or less and preferably 1% by weight or less, although dependent upon the components of the composition, and in the case of using the composition as a raw material of an N-substituted carbamic acid-O-aryl ester, the water concentration is more preferably 100 ppm or less since a large amount of water present may cause side reactions attributable to the water. The concentration of water may be controlled by a known method such as the use of a dehydrating agent or desiccant, distilling under a reduced pressure, an increased pressure or a normal pressure, or purging a liquid phase with an inert gas to remove the water together with the inert gas. Since the presence of an oxidizing substance or reducing substance may cause denaturation of the aromatic hydroxy compound, these substances are controlled using a known method for controlling aromatic hydroxy compounds. Oxidizing substances refer to Bronsted acids such as organic acids or inorganic acids and Lewis acids, while reducing substances refer to Bronsted bases such as organic bases or inorganic bases, Lewis bases and hydrogen gas. Reducing substances do not include compounds derived from the composition, such as the above-mentioned ammonia, urea, carbonic acid derivative or compounds that compose the composition (for example, N-substituted carbamic acid-O-esters such as N-substituted carbamic acid-O-aryl ester, N-substituted carbamic acid-O-alkyl ester or N-substituted carbamic acid-O-R² ester (the N-substituted carbamic acid-O-R² ester will be subsequently described in detail)). Although there are no particular limitations on the content of N-substituted carbamic acid-O-(R² or aryl) ester (the N-substituted carbamic acid-O-R² ester will be subsequently described in detail) obtained in a process for producing N-substituted carbamic acid-O-aryl ester from the composition for transfer and storage and an aromatic hydroxy composition (to be subsequently described in detail), since there are cases in which the compound having the ureido groups and the N-substituted carbamic acid-O-(R² or aryl) ester reacts during storage resulting in the formation of a dealcoholized or de-aromatic hydroxylated compound that condenses by forming ureylene bonds, the amount thereof based on the compound having the ureido groups contained in the composition for transfer and storage is controlled to 10 molar equivalents or less and preferably 1 molar equivalent or less. Examples of other components that may be contained may include urea and alcohol. There are no particular limitations on the contents of either of these components. The composition for transfer and storage may be in the form of a slurry or solid. It is preferably in the form of a slurry and more preferably in the form of a liquid. Since urea tends to solidify easily, in consideration of fluidity, it is controlled to 20 molar equivalents or less and preferably 10 molar equivalents or less based on the compound having the ureido groups contained in the composition for transfer and storage. Although there are also no limitations on alcohol, it may be controlled corresponding to the need to distill off alcohol following transfer. For example, the amount of alcohol is controlled to 100 molar equivalents or less and preferably 10 molar equivalents or less based on the compound having the ureido groups contained in the composition for transfer and storage.

[0054] Although the term N-substituted carbamic acid-O-(R² or aryl) ester is frequently used in the present specification, this refers to an N-substituted carbamic acid-O-R² ester or N-substituted carbamic acid-O-aryl ester.

[0055] Although there are no particular limitations on the conditions for storage and transfer of the composition, there are conditions at which a thermal decomposition reaction of the compound having the ureido groups occurs extremely easily at high temperatures. Although varying according to the storage period, storage is carried out within a range of from -40 to 280°C, and in cases in which fluidity and stability are impaired, preferably at 0 to 260°C and more preferably at 40 to 260°C. The storage temperature may be controlled corresponding to the application of the composition, the storage period and the handling ease of the composition. Although transfer is also carried out at a temperature within

the temperature range during storage, when using the composition as a raw material of N-substituted carbamic acid-O-aryl ester, and when transferring to the N-substituted carbamic acid-O-aryl ester synthesis step, transfer may be carried out after confirming that transfer can be carried out safely according to the conditions of the reaction step and the equipment used in the reaction step since transfer to the reactor of the synthesis step is typically carried out after preheating to the reaction temperature. Generally, transfer is carried out within a range of from -40 to 280°C, and in cases in which fluidity and stability are impaired, is preferably carried out at 0 to 260°C and more preferably at 40 to 260°C. Transfer may be controlled depending on the application of the composition, transfer time and handling ease of the composition as previously described. Although there are no particular limitations on pressure during transfer, storage may be carried out under conditions of a reduced pressure to conditions of an increased pressure. When storing under a reduced pressure, since the aromatic hydroxy composition may be distilled off, the ratio of the compound having the ureido groups and the aromatic hydroxy composition in the composition is controlled to be within the previously described range. There are no particular limitations on storage vessels, lines and the like during storage and transfer. A vessel is selected in accordance with applicable handling regulations in consideration of the handling of a flammable organic substance while paying attention to the flash point of the composition being handled. There are also no particular limitations on the material, and a known material can be used. Examples of materials may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Known equipment may be incidentally provided as necessary as equipment for storage and transfer of the composition, such as pumps, temperature control equipment or instrumentation.

[0056] The composition for transfer and storage of the compound having the ureido groups indicated above may be prepared by mixing the compound having the ureido groups, aromatic hydroxy composition, ammonia, N-substituted carbamic acid-O-(R² or aryl) ester, urea, alcohol, carbonic acid derivative and other components as previously described so as to be formulated as previously described, or may be prepared by adding and/or removing an aromatic hydroxy composition, urea, alcohol, ammonia or carbonic acid derivative and the like so as to be formulated as previously described based on a composition containing a compound having ureido groups obtained in the production of the compound having the ureido groups. The method for producing the compound having the ureido groups can be preferably carried out in the manner subsequently described.

[0057] The following provides an explanation of a method for producing N-substituted carbamic acid-O-aryl ester of the present embodiment. The present embodiment refers to a method for producing at least one N-substituted carbamic acid-O-aryl ester (wherein an N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to an aromatic ring) derived from a compound having ureido groups and an aromatic hydroxy composition from a compound having ureido groups represented by formula (1) and an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by formula (2), which comprises the step of carrying out an esterification reaction or an esterification reaction and transesterification reaction. (The above-mentioned formulas (1) and (2) will subsequently be explained in detail.)

[0058] Namely, the production method of the present embodiment is a method for producing an N-substituted carbamic acid-O-aryl ester derived from a compound having ureido groups and an aromatic hydroxy composition from the compound having ureido groups and the aromatic hydroxy composition (indicating a group of aromatic hydroxy compounds containing at least one type of aromatic hydroxy compound) (and although subsequently described in detail, a method for obtaining N-substituted carbamic acid-O-aryl ester and by-product ammonia by reacting the compound having ureido groups and the aromatic hydroxy composition, as well as a method for obtaining N-substituted carbamic acid-O-R² ester and by-product alcohol (R²OH) by obtaining an N-substituted carbamic acid-O-R² ester and by-product ammonia by esterifying the compound having ureido groups and an alcohol (although subsequently explained, the alcohol refers to an alcohol represented by R²OH in the following formula (4)) followed by transesterifying the N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition, are also present embodiments). Namely, the production method of the present embodiment is a method for producing N-substituted carbamic acid-O-aryl ester in a step comprising an esterification reaction from a compound having ureido groups and an aromatic hydroxy composition. More specifically, the production method of the present embodiment is a method for producing N-substituted carbamic acid-O-aryl ester in a step comprising an esterification reaction or an esterification reaction and a transesterification reaction. An esterification reaction refers to a reaction in which ureido groups (-NHCONH₂) in a compound having ureido groups are converted to carbamic acid groups and ammonia is formed as a by-product thereof. More specifically, this esterification reaction contains a reaction in which the ureido groups (-NHCONH₂) are converted to carbamic acid-O-aryl ester groups (-NHCOOAr) obtained from ureido groups in a compound having ureido groups and an aromatic hydroxy compound, with ammonia being formed as a by-product accompanying the reaction, or a reaction in which the ureido groups (-NHCONH₂) are converted to carbamic acid-O-R² ester groups (-NHCOOR²) obtained from ureido groups in a compound having ureido groups and an alcohol (R²OH), with ammonia being formed as a by-product accompanying the reaction. The Ar indicated for the above-mentioned carbamic acid-O-aryl ester groups refers to a residue in which a single hydrogen atom of a hydroxyl group directly bonded to an aromatic hydrocarbon ring has been removed from an aromatic hydroxy compound. In providing a more detailed explanation of the esterification reaction, the esterification reaction refers to a

reaction in which an N-substituted carbamic acid-O-aryl ester represented by formula (43) is obtained from a compound having ureido groups represented by formula (1) to be subsequently indicated and an aromatic hydroxy compound represented by formula (2), with ammonia being formed as a by-product accompanying the reaction, and a reaction in which an N-substituted carbamic acid-O-R² ester represented by formula (49) is obtained from a compound having ureido groups represented by formula (1) and an alcohol represented by formula (4), with ammonia being formed as a by-product accompanying the reaction. In addition, the above-mentioned transesterification reaction specifically refers to a reaction in which an N-substituted carbamic acid-O-R² ester represented by formula (49) and an aromatic hydroxy compound are reacted to convert the carbamic acid-O-ester groups (-NHCOOR²) in the N-substituted carbamic acid-O-R² ester to carbamic acid-O-aryl ester groups (-NHCOOAr), with alcohol (R²OH) being formed as a by-product of the reaction. Ar is the same as previously defined. (These will also be subsequently described in detail.)

[0059] Namely, the present embodiment includes the case of obtaining an N-substituted carbamic acid-O-aryl ester by directly carrying out an esterification reaction on a compound having ureido groups and an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound), and the case of obtaining an N-substituted carbamic acid-O-aryl ester by carrying out an esterification reaction on a compound having ureido groups and an alcohol, and then carrying out a transesterification reaction on an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound).

[0060] In addition, although the method for producing the compound having ureido groups may be a known method, and can be obtained by, for example, reacting an organic primary amine, urea and/or carbonic acid derivative (to be subsequently described in detail) and/or isocyanic acid and/or non-N-substituted carbamic acid, at least one type of compound having ureido groups derived from an organic primary amine and urea is preferably obtained by a production method that reacts the organic primary amine and urea in a ureidation reaction.

[0061] Next, an explanation is given of compounds used in the production method of the present embodiment, and compounds that compose the composition for transfer and storage of compounds having ureido groups.

<Organic Primary Amine>

[0062] An organic primary amine used in the present embodiment (wherein an organic primary amine refers to a "primary amine" (mono primary amines and poly primary amines) as defined in rule C-8 of the nomenclature (IUPAC Nomenclature of Organic Chemistry) stipulated by the International Union of Pure and Applied Chemistry (IUPAC) is an organic primary amine represented by the following formula (3). This rule is based on Recommendations on Organic & Biochemical Nomenclature. Hereinafter, in the case of referring to IUPAC rules in the present specification as well as subsequently indicated nomenclature rules defined by IUPAC (with the exception of cases specially citing IUPAC recommendations of other years), such referrals cite "Yukikagaku Seikagaku Meimeihou" (Organic Chemistry and Biochemistry Nomenclature) (2nd revision published in Japan in 1992 by Nankodo Co., Ltd.), which is based on an edition containing all rules of organic chemistry and biochemistry, along with transliteration rules for Japanese, published as a supplement to "Chemical Fields" in 1980 based on the Recommendations 1979, as well as all subsequent revisions and recommendations. The term "organic" refers generically to a group of compounds considered to be subject to the nomenclature disclosed in the above publications. The subjects may be subjects described in recommendations published in 1993 (in the case it is difficult to acquire the above-mentioned publications published in Japan, 1979 recommendations and 1993 recommendations may be referred to). However, "organic" compounds covered by the nomenclature described above include organometallic compounds and metal complexes. In the present invention, although the following provides explanations of "organic", and/or "organic groups", and/or "substituents" and the like, as well as compounds used in the present embodiment, when not specifically explained, these are composed of atoms that do not include metal atoms and/or semimetals. More preferably, "organic compounds", "organic groups" and "substituents" composed of atoms selected from H (hydrogen atoms), C (carbon atoms), N (nitrogen atoms), O (oxygen atoms), S (sulfur atoms), Cl (chlorine atoms), Br (bromine atoms) and I (iodine atoms) are used in the present embodiment.


[0063] In addition, for limitation "aliphatic" and "aromatic" are frequently used in the following explanations. According to the above-mentioned IUPAC rules, organic compounds are described as being classified into aliphatic and aromatic. Aliphatic compounds refer to the definitions of groups in accordance with aliphatic compounds based on the 1995 IUPAC recommendations. Aliphatic compounds are defined in these recommendations as "acyclic or cyclic saturated or unsaturated carbon compounds, excluding aromatic compounds". Aliphatic groups, which are frequently used in the present specification, refer to groups composed of the aliphatic compounds. These groups are such that an R moiety, in which a hydrogen atom has been removed from an aliphatic compound in the form of RH, for example, is defined as a monovalent aliphatic group. In addition, aliphatic and aliphatic groups used in the explanation of the present invention include saturated and unsaturated as well as linear and cyclic aliphatic compounds, and refer to "organic compounds", "organic groups" and "substituents" composed of atoms selected from the above-mentioned H (hydrogen atoms); C (carbon atoms); N (nitrogen atoms); O (oxygen atoms); S (sulfur atoms); Si (silicon atoms); and halogen atoms selected from Cl (chlorine atoms), Br (bromine atoms) and I (iodine atoms). In addition, in the case an aromatic group such as an aralkyl group is

bonded to an aliphatic group, such groups are frequently denoted in the manner of "aliphatic group substituted with an aromatic group" or "group composed of an aliphatic group bonded to an aromatic group". This is based on the reactivity in the present embodiment, and because properties relating to reactions of groups in the manner of aralkyl groups closely resemble the reactivity of aliphatic groups and not aromatic groups. In addition, non-aromatic reactive groups including groups such as aralkyl groups and alkyl groups are frequently denoted as "aliphatic groups optionally substituted with an aromatic group", "aliphatic group substituted with an aromatic group" or "aliphatic group bonded to an aromatic group" and the like. Furthermore, although definitions in accordance with nomenclature rules defined by IUPAC as described above are used when explaining general formulas of compounds used in the present specification, terms such as "organic primary amine" or "N-substituted carbamic acid-O-aryl ester" are also used, common names are frequently used for the names of specific groups and names of exemplary compounds.

[0064] In addition, although numbers of molecules, numbers of substituents and individual numbers are frequently described in the present specification, these all represent zero or a positive integer (and there are also frequently cases in which zero is treated as a positive integer).

[0065] A primary amine refers to a compound having an amino group (-NH₂) in which an aliphatic compound and/or aromatic compound and/or aliphatic group and aromatic group are bonded. Namely, an organic primary amine as referred to in the present application indicates a "primary amine" that is classified as being "organic" as previously described.

[0066] An organic primary amine preferably used in the present embodiment is an organic primary amine represented by the following formula (3):






(wherein

R¹ represents an organic group which contains carbon atoms within a range of from 1 to 85, and which is substituted by number c of NH₂ groups, and c represents an integer of from 1 to 10).

[0067] In formula (3) above, R¹ is an organic group classified as "organic" as previously described, and an organic primary amine in the present embodiment refers to an organic primary amine in which number c of NH₂ groups are bonded to an organic group containing carbon atoms within a range of from 1 to 85.

[0068] R¹ represents an aliphatic group, aromatic group or group bonded to an aliphatic group and an aromatic group, and represents a group composed of an acyclic hydrocarbon group or cyclic hydrocarbon group (such as a monocyclic hydrocarbon group, condensed polycyclic hydrocarbon group, crosslinked cyclic hydrocarbon group, spirohydrocarbon group, ring-assembling hydrocarbon group, cyclic hydrocarbon group having a side chain, heterocyclic group, heterocyclic spiro group, hetero-crosslinked ring group or compound ring group), a group bonded from one or more types of groups selected from the above-mentioned acyclic hydrocarbon groups and cyclic hydrocarbon groups, and groups in which the above-mentioned groups are bonded through a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon). In addition, a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon) as described above is in a state in which the above-mentioned groups are bonded by a covalent bond with, for example, groups represented by the following formulas (8) to (16).





5

10 [0069] Among these R¹ groups, R¹ groups that can be preferably used in the present embodiment in consideration of less susceptibility to the occurrence of side reactions contains groups selected from the group consisting of acyclic hydrocarbon groups and cyclic hydrocarbon groups selected from aliphatic groups, aromatic groups and groups bonded to aliphatic groups and aromatic groups (such as a monocyclic hydrocarbon group, condensed polycyclic hydrocarbon group, crosslinked cyclic hydrocarbon group, spirohydrocarbon group, ring-assembling hydrocarbon group or cyclic hydrocarbon group having a side chain), and groups bonded to at least one type of group selected from this group (mutually substituted groups), having carbon atoms within the range of 1 to 85. In consideration of fluidity and the like, the number of carbon atoms of the groups is preferably within a range of from 1 to 70 and more preferably within a range of from 1 to 13.

15

[0070] Preferable examples of organic amines composed by the R¹ group may include:

- 20 1) optionally aliphatic- and/or aromatic-substituted aromatic organic mono primary amines in which the R¹ group has 6 to 85 carbon atoms and contains one or more types of an aromatic ring optionally substituted with an aliphatic group and/or aromatic group, an aromatic group in the R¹ group is substituted with an NH₂ group, and c is 1,
 2) aromatic organic poly primary amines in which the R¹ group has 6 to 85 carbon atoms and contains one or more types of an aromatic ring optionally substituted with an aliphatic group and/or aromatic group, an aromatic group in the R¹ group is substituted with an NH₂ group, and c is 2 or more, and
 25 3) aliphatic organic poly primary amines in which the R¹ group is an aliphatic group having 1 to 85 carbon atoms optionally substituted with an aromatic group, and c is 2 or 3. In the above descriptions, atoms bonded to an NH₂ group (and preferably carbon atoms) that are contained in an aromatic ring are denoted as aromatic organic amines, while cases of bonding to atoms not in an aromatic ring (mainly carbon) are denoted as aliphatic organic amines.
 30 More preferable aliphatic groups are linear hydrocarbon groups, cyclic hydrocarbon groups and at least one type of group selected from the linear hydrocarbon groups and cyclic hydrocarbon groups (referring to, for example, cyclic hydrocarbon groups substituted with a linear hydrocarbon group or linear hydrocarbon groups substituted with a cyclic hydrocarbon group) having 6 to 70 carbon atoms.


35

[0071] The following lists specific examples of preferable organic primary amines.

1) Aromatic Organic Mono Primary Amines

40 [0072] Optionally aliphatic- and/or aromatic-substituted aromatic organic mono primary amines in which the R¹ group is a group having 6 to 85 carbon atoms and contains one or more types of an aromatic ring optionally substituted with an aliphatic group and/or aromatic group, an aromatic group in the R¹ group is substituted with an NH₂ group and c is 1, preferably aromatic organic mono primary amines in which the R¹ group is a group having 6 to 70 carbon atoms and c is 1, and more preferably in consideration of fluidity and the like, aromatic organic mono primary amines in which the R¹ group has 6 to 13 carbon atoms and c is 1, which are aromatic organic mono primary amines represented by the following formula (5).

45



50

(wherein

55


at least one location at the ortho position and/or para position of the NH₂ group of an aromatic organic primary monoamine represented by formula (5) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring,

groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the aromatic organic primary monoamine represented by formula (5) is an integer of from 6 to 13).

[0073] Preferable examples of aromatic organic mono primary amines represented by formula (5) may include those in which the R³ to R⁶ groups are hydrogen atoms or groups selected from alkyl groups such as a methyl group or an ethyl group, and examples of such aromatic organic mono primary amines may include aniline, aminotoluene, dimethylaniline, diethylaniline dipropylaniline, aminonaphthalene, aminomethylnaphthalene, dimethylnaphthylamine, and trimethylnaphthylamine, with aniline being used more preferably.

2) Aromatic Organic Poly Primary Amines

[0074] Aromatic organic poly primary amines in which the R¹ group is a group having 6 to 85 carbon atoms and containing one or more aromatic rings optionally substituted with an aliphatic group and/or aromatic group, an aromatic group in the R¹ group is substituted with an NH₂ group and c is 2 or more, preferably aromatic organic poly primary amines in which the R¹ group is a group having 6 to 70 carbon atoms and c is 2 or more, and more preferably in consideration of fluidity and the like, aromatic organic poly primary amines in which the R¹ group contains one or more aromatic rings, the aromatic ring are groups of 6 to 13 carbon atoms that may be further substituted with an alkyl group, an aryl group or an aralkyl group, an NH₂ group is bonded to the aromatic group contained in the R¹ group, and c is 2 or more. Examples of such aromatic organic polyamines may include diaminobenzene, diaminotoluene, methylenedianiline, diaminomesitylene, diaminobiphenyl, diaminodibenzyl, bis (aminophenyl)methane, bis (aminophenyl)propane, bis(aminophenyl) ether, bis(aminophenoxyethane), α α' -diaminoxylene, diaminoenisole, diaminophenetol, diaminonaphthalene, diamino-methylbenzene, diamino-methylpyridine, diamino-methylnaphthalene and polymethylene polyphenyl polyamines represented by the following formula (17).



(wherein,
m is an integer of from 0 to 6).

3) Aliphatic Organic Poly Primary Amines

[0075] Aliphatic organic poly primary amines in which the R¹ group of an organic amine represented by formula (3) is an aliphatic group in which the number of carbon atoms is an integer within a range of from 1 to 85 and which may be substituted with an aromatic group, and c is 2 or 3.


[0076] More preferable organic amines are aliphatic organic primary amines in which the aliphatic group is a linear hydrocarbon group, cyclic hydrocarbon group or group to which is bonded at least one type of group selected from the linear hydrocarbon groups and the cyclic hydrocarbon groups (such as cyclic hydrocarbon group substituted with a linear hydrocarbon group or linear hydrocarbon group substituted with a cyclic hydrocarbon group). More preferably, the organic amine is an aliphatic organic poly primary amine in which the R¹ group is an aliphatic group that is an acyclic hydrocarbon group, a cyclic hydrocarbon group or a group to which is bonded at least one type of group selected from the acyclic hydrocarbon groups and the cyclic hydrocarbon groups (such as a cyclic hydrocarbon group substituted with an acyclic hydrocarbon group or acyclic hydrocarbon group substituted with a cyclic hydrocarbon group) having 1 to 70 carbon atoms, and c is 2 or 3. In consideration of fluidity and the like during large-volume industrial production, the organic amine is more preferably an aliphatic organic poly primary amine in which the R¹ group is an acyclic hydrocarbon group, a cyclic hydrocarbon group or a group to which is bonded at least one type of group selected from the acyclic hydrocarbon groups and the cyclic hydrocarbon groups (such as a cyclic hydrocarbon group substituted with an acyclic hydrocarbon group or an acyclic hydrocarbon group substituted with a cyclic hydrocarbon group) having 6 to 13 carbon atoms and composed of carbon atoms and hydrogen atoms. Namely, this refers to the case in which the R¹ group is a linear and/or branched alkyl group, a cycloalkyl group or a group composed of the alkyl groups and cycloalkyl groups. Examples of

these organic amines may include aliphatic di-primary amines such as ethylenediamine, diaminopropane, diaminobutane, diaminopentane, diaminoheptane or diaminodecane; aliphatic triamines such as triaminohexane, triaminononane or triaminodecane; and, substituted cyclic aliphatic polyamines such as diaminocyclobutane, diaminocyclohexane, 3-aminomethyl-3,5,5-trimethylcyclohexylamine (cis and/or trans forms) or methylenebis(cyclohexylamine). Examples thereof may include alkyl di-primary amines such as ethylenediamine, diaminopropane, diaminobutane, diaminopentane, diaminoheptane, diaminooctane, diaminononane or diaminodecane; alkyl tri-primary amines such as triaminohexane, triaminoheptane, triaminooctane, triaminononane or triaminodecane; cycloalkyl primary amines such as diaminocyclobutane, diaminocyclopentane or diaminocyclohexane; and, cyclohexyl poly-primary amines substituted with an alkyl group such as 3-aminomethyl-3,5,5-trimethylcyclohexylamine (cis and/or trans form) or methylenebis(cyclohexylamine).

[0077] The organic primary amines explained in 1), 2) and 3) above are used preferably, and in particular the organic primary amine is more preferably an organic primary monoamine, organic primary diamine or organic primary triamine (in which c in formula (3) above is an integer of 1, 2 or 3).

<Compound Having Ureido Groups>

[0078] A compound having ureido groups used when producing an N-substituted carbamic acid-O-aryl ester from the composition for transfer and storage of the compound having ureido groups of the present embodiment and/or an aromatic hydroxy composition is a compound represented by the following formula (1):





(1)

(wherein

R¹ represents an organic group which contains an integral number of carbon atoms within a range of from 1 to 85, and which is substituted by a number of ureido groups, and a represents an integer of from 1 to 10).

[0079] The compound having the ureido groups represented by formula (1) above is a compound having "ureido groups" as defined in nomenclature rule C-971 stipulated by IUPAC. In formula (1) above, R¹ is an organic group classified as "organic" as described above, and the compound having the ureido groups according to the present embodiment is a compound having ureido groups bonded to a number of ureido groups (-NH-CONH₂) including carbon atoms within a range of from 1 to 85. R¹ represents an aliphatic group, an aromatic group or a group bonded to an aliphatic group and an aromatic group, and represents a group composed of an acyclic hydrocarbon group or a cyclic hydrocarbon group (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group, a cyclic hydrocarbon group having a side chain, a heterocyclic group, a heterocyclic spiro group, a hetero-crosslinked ring group or a heterocyclic group), a group bonded from one or more types of groups selected from the above-mentioned acyclic hydrocarbon groups and cyclic hydrocarbon groups, and groups in which the above-mentioned groups are bonded through a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon). In addition, a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon) as described above is in a state in which the above-mentioned groups are bonded by a covalent bond with, for example, groups represented by the following formulas (8) to (16).





15 **[0080]** Among these R¹ groups, R¹ groups that can be preferably used in the present embodiment in consideration of less susceptibility to the occurrence of side reactions contains groups selected from the group consisting of acyclic hydrocarbon groups and cyclic hydrocarbon groups selected from aliphatic groups and aromatic groups (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group or a cyclic hydrocarbon group having a side chain), and groups bonded to at least one type of group selected from this group (mutually substituted groups), containing 1 to 85 carbon atoms. In consideration of fluidity and the like of the composition for transfer and storage, the number of carbon atoms is preferably 1 to 70 and more preferably 1 to 13.

20 **[0081]** Preferable examples of compounds having a ureido group composed by the R¹ group may include: 1) N-substituted aromatic organic monoureas in which the R¹ group has 6 to 85 carbon atoms and contains one or more types of an aromatic ring optionally substituted with an aliphatic group and/or an aromatic group, an aromatic group in the R¹ group is substituted with a ureido group, and c is 1, 2) N-substituted aromatic organic polyureas in which the R¹ group has 6 to 85 carbon atoms and contains one or more types of an aromatic ring optionally substituted with an aliphatic group and/or an aromatic group, an aromatic group in the R¹ group is substituted with a ureido group, and c is 2 or more, and 3) N-substituted aliphatic organic polyureas in which the R¹ group is an aliphatic group having 1 to 85 carbon atoms optionally substituted with an aromatic group, and c is 2 or 3. In the above descriptions, compounds in which atoms bonded to a ureido group (mainly carbon atoms) that are contained in an aromatic ring are denoted as N-substituted aromatic organic ureas, while cases of bonding to atoms not in an aromatic ring (mainly carbon atoms) are denoted as N-substituted aliphatic organic ureas. More preferably, an aliphatic group is a linear hydrocarbon group, a cyclic hydrocarbon group and at least one type of group bonded to a group selected from the linear hydrocarbon groups and cyclic hydrocarbon groups (referring to, for example, cyclic hydrocarbon groups substituted with a linear hydrocarbon group or linear hydrocarbon groups substituted with a cyclic hydrocarbon group) having 6 to 70 carbon atoms.

35 **[0082]** Although the method for producing the compound having the ureido groups may be a known method, and can be obtained by, for example, reacting an organic primary amine, urea and/or carbonic acid derivative (to be subsequently described in detail) and/or isocyanic acid and/or non-N-substituted carbamic acid, at least one type of compound having the ureido groups derived from an organic primary amine and urea is preferably obtained by a production method that reacts the organic primary amine and urea in a ureidation reaction, and in the present embodiment, a compound having ureido groups preferably uses a compound having ureido groups obtained in a process that includes the following step A:

45 step (A): a step of obtaining at least one type of compound having ureido groups derived from an organic primary amine represented by the following formula (3) and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction:



55 (wherein R¹ represents an organic group which contains an integral number of carbon atoms within a range of 1 to 85, and which is substituted by number c of NH₂ groups, and c represents an integer of from 1 to 10).

[0083] A compound having ureido groups obtained in step (A) above is a compound having ureido groups that has an organic group derived from the above-mentioned organic primary amine. Namely, this step contains reacting organic primary amino groups (-NH₂) of the organic primary amine with urea to form the ureido groups (this reaction is frequently referred to as an ureidation reaction in the present embodiment). (-CONH₂) groups within the ureido groups (-NHCONH₂) are formed from the urea reacted in the reaction. In addition, a indicated in formula (1) is an integer equal to or less than c indicated in formula (3), and preferably is an integer such that a = c.


[0084] Although the term "derived" is frequently used in the present specification, the term "derived" is used in the sense of inheriting a group possessed by a raw material when a functional group of the raw material compound changes in a reaction. For example, in the reaction described above in which the compound having the ureido groups is obtained from an organic primary amine, the compound having the ureido groups has a structure that has inherited the organic primary amino groups (-NH₂) of the organic primary amine, while the (-CONH₂) groups within the ureido groups refer to (-CONH₂) groups contained in the reacted urea (NH₂CONH₂). Thus, in the above-mentioned formulas (1) and (3), a is an integer equal to or less than c, and a and c are preferably the same integers.

[0085] The following indicates specific examples of preferable compounds having ureido groups. A ureido group is the same of a substituent, and in the present specification, is described as the name of a compound in the form of an "N-substituted (substituent name) urea". In order to clearly indicate that the nitrogen atom (N) of the urea is substituted (namely, that the nitrogen atom is not an -NH₂ group), "N-substituted" is clearly indicated, the substituent is clearly indicated as being an aromatic group or aliphatic group, and the term "organic" is also intentionally clearly indicated in the sense that the compound is an organic compound. A compound is clearly indicated as being "monourea" in the case of a single ureido group within a molecule thereof, or is clearly indicated as being a "polyurea" in the case of multiple ureido groups within a molecule thereof. Since the compound is an N-substituted urea, even in cases of multiple ureido groups, the ureido groups contained in a compound having ureido groups explained below are indicated by attaching the prefix "poly", "di" or "tri" and the like immediately before the term "urea" as indicated above to facilitate distinction thereof.

[0086] Throughout the entire present specification, the descriptions of "substituted" "mono" are not used, but rather descriptions in accordance with IUPAC nomenclature or common names are described when indicating examples of specific compounds.

1) N-substituted Aromatic Organic Monourea

[0087] N-substituted aromatic organic monourea refers to that in which the R¹ group has 6 to 85 carbon atoms and contains one or more types of an aromatic ring optionally substituted with an aliphatic group and/or aromatic group, an aromatic group in the R¹ group is substituted with a ureido group, and c is 1, preferably refers to an aromatic organic monourea in which the R¹ group is a group having 6 to 70 carbon atoms and c is 1, and in consideration of fluidity and the like, more preferably refers to an N-substituted aromatic organic monourea in which the R¹ group is a group having 6 to 13 carbon atoms and c is 1, and is an N-substituted aromatic organic monourea represented by the following formula (41):



(4 1)


(wherein

at least one location at the ortho position and/or para position of a ureido group of the N-substituted aromatic organic monourea represented by formula (41) is not substituted, groups R¹⁰ to R¹³ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R¹⁰ to R¹³ may respectively and independently substitute an aromatic ring or groups R¹⁰ to R¹³ may together bond to form a ring with an aromatic ring, groups R¹⁰ to R¹³ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the N-substituted aromatic organic monourea represented by formula (41), excluding ureido groups (-NH-CO-NH₂), is an integer of 6 to 13).

[0088] Preferable examples of such N-substituted aromatic organic monoureas represented by formula (41) may include those in which groups R¹⁰ to R¹³ are hydrogen atoms or groups selected from alkyl groups such as a methyl group or an ethyl group, and examples of such N-substituted aromatic organic monoureas may include N-phenylurea, N-tolylurea, N-dimethylphenylurea, N-diethylphenylurea, N-dipropylphenylurea, N-naphthalen-ylurea, N-methylnaphthalen-ylurea, N-dimethylnaphthalen-ylurea and N-trimethylnaphthalen-ylurea. In particular, N-phenylurea is used more preferably.

2) N-substituted Aromatic Organic Polyurea

[0089] N-substituted aromatic organic polyurea refers to that in which the R¹ group is a group having 6 to 85 carbon atoms that contains one or more aromatic rings optionally substituted with an aliphatic group and/or an aromatic group, an aromatic group in the R¹ group is substituted with a ureido group and c is 2 or more, preferably an N-substituted aromatic organic polyurea in which the R¹ group is a group having 6 to 70 carbon atoms and c is 2 or more, and more preferably in consideration of fluidity and the like, an N-substituted aromatic organic polyurea in which the R¹ group contains one or more types of aromatic rings, the aromatic ring has 6 to 13 carbon atoms and may be further substituted with an alkyl group, an aryl group or an aralkyl group, a ureido group is bonded to the aromatic group contained in the R¹ group, and c is 2 or more. Examples of such N-substituted aromatic organic polyureas may include N,N'-phenylene diurea, N,N'-methylphenylene diurea, N,N'-mesitylene diphenylene diurea, N,N'-mesitylene diurea, N,N'-biphenylene diurea, N,N'-dibenzyl diurea, N,N'-propan-diylphenylene diurea, N,N'-oxydiphenylene diurea, N,N'-diphenyl-diyl-dipropan-diyl diurea, N,N'-phenylene dimethylene diurea, N,N'-methoxyphenylene diurea, N,N'-ethoxyphenylene diurea, N,N'-naphthalen-diylurea, N,N'-pyridine-diyl dimethylene diurea, N,N'-naphthalen-diyl dimethylene diurea, and polymethylene polyphenylene polyamines represented by the following formula (42).



(wherein
m is an integer of from 0 to 6).

3) N-substituted Aliphatic Organic Polyurea

[0090] N-substituted aliphatic organic polyurea is that in which the R¹ group is an aliphatic group having 1 to 85 carbon atoms that is optionally substituted with an aromatic group, and c is 2 or 3. Preferable N-substituted aliphatic organic polyureas are N-substituted aliphatic organic polyureas in which the aliphatic group is a linear hydrocarbon group, a cyclic hydrocarbon group (including aromatic groups) or a group to which is bonded at least one type of group selected from the linear hydrocarbon groups and the cyclic hydrocarbon groups (such as cyclic hydrocarbon group substituted with a linear hydrocarbon group or linear hydrocarbon group substituted with a cyclic hydrocarbon group). More preferably, the N-substituted aliphatic organic polyurea is an N-substituted aliphatic organic polyurea in which the R¹ group is an aliphatic group that is an acyclic hydrocarbon group, a cyclic hydrocarbon group or a group to which is bonded at least one type of group selected from the acyclic hydrocarbon groups and the cyclic hydrocarbon groups (such as a cyclic hydrocarbon group substituted with an acyclic hydrocarbon group or acyclic hydrocarbon group substituted with a cyclic hydrocarbon group) having 1 to 70 carbon atoms, and c is 2 or 3. In consideration of fluidity and the like during large-volume industrial production, the N-substituted aliphatic organic polyurea is more preferably an N-substituted aliphatic organic polyurea in which the R¹ group is an acyclic hydrocarbon group, a cyclic hydrocarbon group or a group to which is bonded at least one type of group selected from the acyclic hydrocarbon groups and the cyclic hydrocarbon groups (such as a cyclic hydrocarbon group substituted with an acyclic hydrocarbon group or an acyclic hydrocarbon group substituted with a cyclic hydrocarbon group) having 6 to 13 carbon atoms that is composed of carbon atoms and hydrogen atoms. Namely, this refers to the case in which the R¹ group is a linear or branched alkyl group, a cycloalkyl group or a group composed of the alkyl groups and cycloalkyl groups. Examples thereof may include N-substituted aliphatic organic polyureas such as methylenediurea, 1,2-dimethylenediurea, 1,3-trimethylenediurea, 1,4-tetramethylenediurea, 1,5-pentamethylenediurea, 1,6-hexamethylenediurea, 1,8-octamethylenediurea, cyclopentane-diurea, cyclohexane-diurea, cy-

cloheptane-diurea, cyclooctane-diurea, methylcyclopentane-diurea, ethylcyclopentane-diurea, methylcyclohexane-diurea, ethylcyclohexane-diurea, propylcyclohexane-diurea, butylcyclohexane-diurea, pentylcyclohexane-diurea, hexylcyclohexane-diurea, dimethylcyclohexane-diurea, diethylcyclohexane-diurea, dibutylcyclohexane-diurea, 1,5,5-trimethylcyclohexane-diurea, 1,5,5-triethylcyclohexane diurea, 1,5,5-tributylcyclohexane-diurea or 3-ureidomethyl-3,5,5-trimethylcyclohexylurea.

[0091] The following provides an explanation of alcohol used in the present embodiment.

<Alcohol>

[0092] Although the details of step (A) will be described later, step (A) may be carried out in the presence of water and/or alcohol and/or an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound) in addition to the organic primary amine and urea.

[0093] In the case of carrying out step (A) in the presence of an aromatic hydroxy composition, the step (A) is preferably carried out in the presence of the above-mentioned aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)).


[0094] In addition, one aspect of the present embodiment is a process for producing N-substituted carbamic acid-O-aryl ester which comprises the step (A), the following step (R) and the following step (P) by carrying out the step (R) (esterification reaction step) to obtain N-substituted carbamic acid-O-R² ester (the details of which will be subsequently described) and then carrying out the step (P) (transesterification reaction step) to obtain N-substituted carbamic acid-O-aryl ester after having carried out the step (A). An alcohol represented by the following formula (4) is also used for the alcohol used at that time. The aromatic hydroxy composition used in the following step (P) (composition containing at least one type of aromatic hydroxy compound represented by formula (2)) will be subsequently described in detail:

[0095]

step (R): a step of obtaining N-substituted carbamic acid-O-R² ester by reacting the at least one type of compound having ureido groups and an alcohol represented by the following formula (4) in a liquid phase and extracting ammonia formed as a by-product to a gaseous phase (where the N-substituted carbamic acid-O-R² ester represents an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to an R² group derived from an alcohol), and

step (P): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting the N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition (containing at least one type of aromatic hydroxy compound represented by the following formula (2)) in a liquid phase and extracting alcohol formed as a by-product to a gaseous phase:


[0096] An alcohol represented by the following formula (4) is preferably used for the alcohol used in the present embodiment.



(wherein

R² represents a group composed of an aliphatic group or an aliphatic group in which an aromatic group is bonded, which contains an integral number of carbon atoms within a range of from 1 to 14, and the OH group of the alcohol represented by formula (4) is an OH group that is not bonded to an aromatic ring).

[0097] A preferable alcohol represented by formula (4) is an alcohol in which the R² group is a group composed of an aliphatic group or an aliphatic group in which an aromatic group is bonded, and in which the OH group of an alcohol represented by formula (4) is an OH group that is not bonded to an aromatic group. The R² group represents a group composed of an acyclic hydrocarbon group or a cyclic hydrocarbon group (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group, a cyclic hydrocarbon group having a side chain, a heterocyclic group, heterocyclic spiro group, a hetero-crosslinked ring group or a heterocyclic group), a group bonded from one or more types of groups selected from the above-mentioned acyclic hydrocarbon groups and cyclic hydrocarbon groups, and a group in which the above-mentioned groups are bonded through a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon). In addition, a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon) as described above is in a state in which the above-mentioned groups are bonded by a covalent bond with, for example, groups represented by the following formulas (8) to (16).



[0098] Among these R² groups, R² groups that can be preferably used in the present embodiment in consideration of less susceptibility to the occurrence of side reactions contain groups selected from the group consisting of acyclic hydrocarbon groups and cyclic hydrocarbon groups selected from aliphatic groups and/or aliphatic groups in which aromatic groups are bonded (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group or a cyclic hydrocarbon group having a side chain), groups bonded to at least one type of group selected from this group (mutually substituted groups), and groups in which the above-mentioned groups are substituted with an aromatic group, and which contain a number of carbon atoms within a range of from 1 to 14. In the step (P) of the present embodiment, an N-substituted carbamic acid-O-R² ester is preferably transesterified with an aromatic hydroxy composition and the by-product alcohol is removed outside the system. Thus, the alcohol used in the step (A) and/or the step (R) preferably has a boiling point that is lower than the aromatic hydroxy compound contained in the aromatic hydroxy composition, and more preferably the R² group is a group containing a number of carbon atoms within a range of from 1 to 10. The R² group more preferably contains a number of carbon atoms within a range of from 1 to 8. Even more preferably, R² is an alkyl group, group in which a cycloalkyl group and an alkyl group are bonded, or an aralkyl group. Preferable examples of such alcohols may include methanol, ethanol, propanol, butanol, pentanol, hexanol, heptanol, octanol, benzyl alcohol, tolyl methanol, xylyl methanol and phenylethyl alcohol. Even more preferable examples of alcohols may include the alcohols listed above in which R² is an alkyl group, and among the carbon atoms that compose the alkyl group, the carbon atom at the α position of the hydroxy group (carbon atom that composes the alkyl group to which an OH group is bonded) is a secondary carbon atom (-CH₂-).

[0099] Next, an explanation is given of the aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2)) used in the present embodiment.

<Aromatic Hydroxy Composition>

[0100] There are various methods and steps that use an aromatic hydroxy composition in the present embodiment. An aromatic hydroxy composition is used as a compound that composes the composition for transfer and storage of the compound having the ureido groups as previously described. In addition, the step (A) is preferably carried out in the presence of an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2)). Further, an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2)) is used also in the step (P) described in the above explanation of the alcohol. In addition, an example of another aspect of the present embodiment is a method for obtaining N-substituted carbamic acid-O-aryl ester by a process that includes the step (A) (ureidation reaction step) and the following step (B) (esterification reaction step), and an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2)) is also used in the step (B):


step (B): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting the at least one type of compound having ureido groups with an aromatic hydroxy composition (composition containing at least one type of aromatic

hydroxy compound represented by formula (2)) in a liquid phase and extracting the ammonia formed as a by-product to a gaseous phase.

[0101] Although there are cases an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2)) is used in addition to the steps listed above, the aromatic hydroxy composition used in the present embodiment is an aromatic hydroxy composition that contains at least one type of aromatic hydroxy compound represented by formula (2) as previously described.

[0102] An aromatic hydroxy composition in the present embodiment refers to a composition that contains one type of aromatic hydroxy compound or a plurality of types of aromatic hydroxy compounds. The following provides an explanation of aromatic hydroxy compounds preferably used as aromatic hydroxy compounds that compose the aromatic hydroxy composition.

[0103] Aromatic hydroxy compounds that compose (or are contained in) the aromatic hydroxy composition are at least one type of aromatic hydroxy compound represented by the following formula (2):




(wherein


ring A represents an organic group which contains 6 to 50 carbon atoms and which contains an aromatic group substituted with number b of hydroxy groups at an arbitrary location that maintains aromatic properties, may be a single ring or multiple rings, may be a heterocyclic ring or may be substituted by other substituents, and b is an integer of from 1 to 6).

[0104] Examples of substituents that substitute an aromatic group of an aromatic hydroxy compound represented by formula (2) above may include groups selected from a hydrogen atom, a halogen atom, aliphatic groups and aromatic groups and groups in which the above-mentioned groups are bonded that are composed of acyclic hydrocarbon groups or cyclic hydrocarbon groups (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group, a cyclic hydrocarbon group having a side chain, a heterocyclic group, a heterocyclic spiro group, a hetero-crosslinked ring group or a heterocyclic group), groups bonded to one or more types of groups selected from the acyclic hydrocarbon groups and the cyclic hydrocarbon groups, and groups in which the above-mentioned groups are bonded through a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon atom). In addition, covalent bonding with a specific non-metal atom as described above (carbon, oxygen, nitrogen, sulfur or silicon atom) refers to a state in which, for example, a group represented by the following formulas (8) to (11) and formulas (13) to (16) and the above-mentioned groups are bonded with a covalent bond.

[0105] Ring A has a structure that contains at least one structure selected from the group consisting of a benzene ring, a naphthalene ring and an anthracene ring, ring A preferably has a structure that contains at least one structure selected from the group consisting of a benzene ring, a naphthalene ring and an anthracene ring, and more preferably ring A has a structure that contains a single benzene ring.

[0106] The hydroxy groups bonded to the aromatic group of ring A are hydroxy groups that are bonded to a carbon atom of the aromatic group of ring A, and the number of the hydroxy groups is preferably an integer of from 1 to 6, more preferably an integer of from 1 to 3, even more preferably an integer of from 1 to 2, and still more preferably 1 (namely, b=1).





5
10
15
20
[0107] Among such substituents, substituents that can be preferably used in the present embodiment in consideration of less susceptibility to the occurrence of side reactions contain groups selected from the group consisting of acyclic hydrocarbon groups and cyclic hydrocarbon groups (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group or a cyclic hydrocarbon group having a side chain), and groups bonded to at least one type of group selected from this group (mutually substituted groups).

25
[0108] In addition, in the case of transferring a composition for transfer and storage of a compound having ureido groups at a high temperature or in the case of reacting a compound having ureido groups and/or an N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition to obtain an N-substituted carbamic acid-O-aryl ester at a high temperature, ring A of the aromatic hydroxy compound is preferably an aromatic hydroxy compound composed of a group having at least one inactive substituent (including hydrogen atoms) in addition to the aromatic group and hydroxy groups bonded to the aromatic group (here, an inactive substituent refers to, for example, a substituent that does not have an active hydrogen in which the pKa of a compound in which the inactive substituent is bonded to a phenyl group is 30 or less, although it may have an aromatic hydroxyl group).

30
[0109] In providing a more detailed explanation of the substituent, the aromatic hydroxy compound represented by formula (2) is an aromatic hydroxy compound having at least one substituent selected from the groups of substituents indicated below in addition to the aromatic group and hydroxy group bonded to the aromatic group:

(i) a hydrogen atom,

35 (ii) a group composed of carbon atoms and hydrogen atoms (which may also form a ring structure by bonding with ring A),

(iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, ether group composed of aromatic groups or ether group composed of aliphatic groups and aromatic groups, but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group or a carboxyl group,


40 (iv) a halogen atom, and

(v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms (but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, a carboxyl group, a NH₂ group, a NH group, a NOH group, a SH group, a SO₃H group or a SOH group).

45 [0110] Active hydrogen refers to a hydrogen atom bonded to oxygen, sulfur or nitrogen (but excluding aromatic hydroxyl groups). Although aromatic hydroxyl groups (OH groups directly bonded to an aromatic group) are included in the above-mentioned definition of active hydrogen, since the aromatic hydroxyl groups are also contained in the composition of the present embodiment and reaction raw materials and do not have a detrimental effect in particular, aromatic hydroxyl groups are not included in groups containing active hydrogen unless specifically indicated otherwise. Although the "groups containing active hydrogen" are frequently described in other locations of the invention of the present application, the above-mentioned definition applies to such groups.

50 [0111] In addition, ring A is a structure that contains at least one structure selected from the group consisting of a benzene ring, a naphthalene ring and an anthracene ring, and preferably is an aromatic hydroxy compound represented by the following formula (7):

55



(7)

(wherein


ring A represents an aromatic ring selected from a benzene ring, a naphthalene ring and an anthracene ring, the OH groups and groups R⁷ to R¹⁴ respectively represent groups substituted at arbitrary locations that maintain aromatic properties of ring A, groups R⁷ to R¹⁴ may respectively and independently substitute ring A, groups R⁷ to R¹⁴ may bond together to form a ring with ring A, groups R⁷ to R¹⁴ respectively and independently represent a hydrogen atom, a halogen atom or a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group, an aryl group having a hydroxy group, an aralkyl group and an ether group (substituted and/or unsubstituted alkyl ether and/or aryl ether and/or aralkyl ether group), and/or a group to which one or more types of groups selected from the group are bonded, and/or a group to which one or more types of groups selected from the group are bonded by saturated aliphatic bonds and/or ether bonds, and ring A and groups R⁷ to R¹⁴ are composed of an integral total number of carbon atoms within a range of from 6 to 50,

b represents an integer of from 1 to 6, d, e, f, g, h, i, j and k represent integers of from 0 to 5, the value of d + e + f + g + h + i + j + k represents an integer equal to 6-b in the case ring A is a benzene ring, represents an integer equal to 8-b in the case ring A is a naphthalene ring, or represents an integer equal to 10-b in the case ring A is an anthracene ring, and a group selected from groups R⁷ to R¹⁴ as described above may be cyclically bonded to ring A by carbon-carbon bonds and/or ether bonds).

[0112] In consideration of industrial use, the aromatic hydroxy compound represented by the above-mentioned formula (7) is preferably an aromatic hydroxy compound in which one or two aromatic hydroxyl groups are bonded to ring A (namely, b = 1 or 2), and more preferably an aromatic monohydroxy compound in which one aromatic hydroxyl group is bonded to ring A, since they typically have low viscosity.

[0113] In addition, since the aromatic hydroxy compound is a compound that has ureido groups by carrying out the step (B) and undergoing esterification, it forms an N-substituted carbamic acid-O-aryl ester derived from the ureido groups and the aromatic hydroxy compound (namely, an N-substituted carbamic acid-O-aryl ester in which the O-aryl group that forms the carbamic acid-O-aryl ester is formed by the aromatic hydroxy compound, while the N-substituted carbamic acid group moiety is formed from the compound having ureido groups), while in the case of carrying out the step (P), an N-substituted carbamic acid-O-R² ester derived from the N-substituted carbamic acid-O-R² ester and the aromatic hydroxy compound is formed from the N-substituted carbamic acid-O-R² ester by carrying out a transesterification reaction (namely, the N-substituted carbamic acid-O-aryl ester is an N-substituted carbamic acid-O-R² ester in which the O-alkyl ester group of the N-substituted carbamic acid-O-R² ester has undergone transesterification with the aromatic hydroxy compound). The N-substituted carbamic acid-O-aryl ester is used as an isocyanate precursor. Although the production method of isocyanate derived from the N-substituted carbamic acid-O-aryl ester will be subsequently described in detail, an N-substituted carbamic acid-O-aryl ester obtained by the process of the present embodiment is preferably thermally decomposed in the following step (F) to obtain an isocyanate represented by the following formula (6), which is derived from the N-substituted carbamic acid-O-aryl ester, and an aromatic hydroxy composition:

step (F): a step of obtaining an isocyanate and an aromatic hydroxy composition from the N-substituted carbamic acid-O-aryl ester:



(6)

(wherein

R¹ represents an organic group which contains an integral number of carbon atoms within a range of from 1 to 85, and which is substituted by number s of NCO groups, and s represents an integer of from 1 to 10).

[0114] The production method contains thermally decomposing the N-substituted carbamic acid-O-aryl ester to obtain an aromatic hydroxy compound and isocyanate derived from the N-substituted carbamic acid-O-aryl ester. Herein, isocyanate derived from the N-substituted carbamic acid-O-aryl ester refers to an isocyanate compound in which the carbamic acid O-aryl group (-NHCOOAr, where Ar represents an aryl group derived from the aromatic hydroxy compound) of the N-substituted carbamic acid-O-aryl ester is converted to an isocyanate group (-NCO). In consideration of the reaction formula, the aromatic hydroxy compound formed at that time is an aromatic hydroxy compound contained in the aromatic hydroxy composition reacted with the compound having ureido groups when obtaining the N-substituted carbamic acid-O-aryl ester. Namely, an aromatic hydroxy compound represented by the formula (2), and preferably by the formula (7), is formed as a by-product together with isocyanate during thermal decomposition of the N-substituted carbamic acid-O-aryl ester. In one aspect of the present embodiment, although depending on the particular case, the aromatic hydroxy compound and isocyanate are separated by distillation following the thermal decomposition step, and the separated aromatic hydroxy compound may be recycled in the form of an aromatic hydroxy composition that is reacted with the compound having ureido groups. Namely, this aspect of the present embodiment is a preferable aspect in which the aromatic hydroxy composition obtained in the step (F) is separated from isocyanate, and then used by recycling to the step (A) and/or the step (B), or to the step (A) and/or the step (R) and/or the step (P).

[0115] Thus, in consideration of the process through the isocyanate production step in which the step (F) is carried out, it is necessary to take into consideration the separability of the aromatic hydroxy compound serving as a raw material of the N-substituted carbamic acid-O-aryl ester and the isocyanate formed from the N-substituted carbamic acid-O-aryl ester. Although it is difficult to generally define separability, it is defined on the basis of the finding that normally two components to be separated can be adequately separated by distillation industrially if the standard boiling points thereof are 10°C or more apart. Thus, this definition refers to a value that is limited by currently known separation means, and is not intended to serve as a basis of the present embodiment.

[0116] The following Table (1) indicates the standard boiling points of aromatic hydroxy compounds or boiling points at a reduced pressure in the case measurement thereof is difficult at the normal pressure. Although the reactivity of the aromatic hydroxy compound that composes the aromatic hydroxy composition used in the present embodiment with a compound containing a ureido group and/or an N-substituted carbamic acid-O-R² ester (details regarding this N-substituted carbamic acid-O-R² ester will be described hereinafter) and/or urea is important, the standard boiling point is also an important selection index with respect to separation of each component. As shown in the following Table (1), the types and numbers of substituents, the locations of substituents and the like have a considerable influence on the boiling point of the aromatic hydroxy compound. Boiling point is a physical property that is also dependent on intermolecular forces, and is commonly known among persons with ordinary skill in the art to be unable to be defined by the structure of a single molecule. Thus, selection of an aromatic hydroxy compound according to an important aspect of the present invention in the form of standard boiling point is carried out by measuring or investigating the structure and properties (standard boiling point) of the desired N-substituted carbamic acid-O-Ar ester (the details of which will be described hereinafter) and/or isocyanate. Measurement of standard boiling point can be carried out with known methods, and can be routinely carried out by a researcher with ordinary skill in the relevant technical field. As has been described above, it is difficult to define separation of aromatic hydroxy compounds used in the present invention with a structure such as a general formula, and the intended method of the present embodiment is not to predict the standard boiling point of an aromatic hydroxy compound. Thus, a person with ordinary skill in the art is able to carry out the present embodiment by referring to or measuring standard boiling point corresponding to the compound used as previously described.

[Table 1]

Aromatic Hydroxy Compounds	Boiling Point °C (values in parentheses indicate pressure during measurement, and the absence of values in parentheses means that measurement was carried out at normal pressure)
Phenol	182
2-methylphenol	191
3-methylphenol	203
4-methylphenol	202
2,4-dimethylphenol	211
2,6-dimethylphenol	203
2,5-dimethylphenol	212
3,4-dimethylphenol	227
3,5-dimethylphenol	222


(continued)

Aromatic Hydroxy Compounds	Boiling Point °C (values in parentheses indicate pressure during measurement, and the absence of values in parentheses means that measurement was carried out at normal pressure)
2,4,6-trimethylphenol	220
4-propylphenol	232
2-propylphenol	225
2-(propan-2-yl)phenol	212
4-(propan-2-yl) phenol	212
3-(propan-2-yl) phenol	228
2,6-dimethylphenol	219
4-butylphenol	138-139 (2.40 kPa)
4-pentylphenol	250
2-(2-methylbutan-2-yl)phenol	92 (0.53 kPa)
2,4-bis(propan-2-yl)phenol	249
2,6-bis(propan-2-yl) phenol	256
2-(phenylmethyl)phenol	312
3,5-dimethoxyphenol	172 (2.27 kPa)
2,6-dimethoxyphenol	167 (1.33 kPa)
2-ethoxyphenol	216
4-heptylphenol	156 (1.20 kPa)
4-octylphenol	150 (0.53 kPa) (lit.)
4-butoxyphenol	278
4-(2,4,4-trimethylpentan-2-yl)phenol	175 (4.00 kPa)
2,4-bis(2-methylbutan-2-yl) phenol	170 (0.267 kPa)
Naphthalen-2-ol	285
Naphthalen-1-ol	278
Pyrocatechol	245
Resorcinol	178 (2.13 kPa)
Hydroquinone	285
Pyrogallol	309
2-bromophenol	195
3-bromophenol	236
4-bromophenol	235-236
2-chlorophenol	175-176
3-chlorophenol	214
4-chlorophenol	220
4-chloro-2-methylphenol	220-225
2-chloro-4-methylphenol	195-196

[0117] In providing an explanation using one of the present embodiments as an example, an organic primary amine represented by the above-mentioned formula (3) and the above-mentioned urea subjected to a ureidation reaction in step (A) to obtain a compound having ureido groups indicated in formula (1), the compound having ureido groups and an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2) (and preferably by formula (7)) are subjected to an esterification reaction by carrying out the step (B) to obtain a compound having an N-substituted carbamic acid-O-aryl ester group, and the step (F) is carried out using the N-substituted carbamic acid-O-aryl ester to produce an aromatic hydroxy compound and isocyanate derived from the N-substituted carbamic acid-O-aryl ester. Alternatively, an aromatic hydroxy compound and isocyanate derived from the N-substituted carbamic acid-O-aryl ester are produced by a method that comprises the steps (A), (R), (P) and (F). Alternatively, in the case the organic primary amine is an aromatic organic primary monoamine represented by the following formula (5), the following step (C) is carried out after the step (B) or the step (P) (the details of step (C) will be subsequently described), and an N-substituted carbamic acid-O-aryl ester, in which at least two molecules of the N-

substituted carbamic acid-O-aryl ester are crosslinked with methylene groups (-CH₂-), is obtained from the N-substituted carbamic acid-O-aryl ester obtained in the step (B) or the step (P), followed by carrying out the step (F) to produce an aromatic hydroxy compound and isocyanate derived from the N-substituted carbamic acid-O-aryl ester:

step (C): a step of obtaining N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with methylene groups (-CH₂-), by reacting the N-substituted carbamic acid-O-(R² or aryl) ester with formaldehyde or a methylene crosslinking agent, and crosslinking aromatic groups derived from the aromatic organic primary monoamine contained in the N-substituted carbamic acid-O-(R² or aryl) ester with methylene groups (-CH₂-):



(wherein


at least one location at the ortho position and/or para position of the NH₂ group of an aromatic organic primary monoamine represented by formula (5) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the aromatic organic primary monoamine represented by formula (5) is an integer of from 6 to 13).

[0118] Furthermore, although the term "N-substituted carbamic acid-O-(R² or aryl) ester" is frequently used in the present specification, this refers to "N-substituted carbamic acid-O-R² ester or N-substituted carbamic acid-O-aryl ester".

[0119] Thus, the structures of the aromatic hydroxy compound and isocyanate to be separated following the thermal decomposition reaction are such that the aromatic hydroxy compound is an aromatic hydroxy compound that composes (or is contained in) an aromatic hydroxy composition used when converting a compound having ureido groups to an N-substituted carbamic acid-O-aryl ester, while the other product in the form of the isocyanate is derived from a compound having ureido groups represented by formula (1) or an organic primary amine represented by formula (3) (namely, an isocyanate is obtained having a structure in which a ureido group (-NHCONH₂) of the compound having ureido groups is converted to an isocyanate group (-NCO), or a primary amino group (-NH₂) of the organic primary amine is converted to an isocyanate group (-NCO)).

[0120] Namely, if the standard boiling points of an aromatic hydroxy compound represented by formula (2), or preferably by formula (7), and an isocyanate represented by formula (6) differ by 10°C or more, the aromatic hydroxy compound and the isocyanate can be separated by currently known techniques. As was previously described, since isocyanate represented by formula (6) obtained by the method of the present embodiment is produced by using as starting materials a compound having ureido groups or an organic primary amine, the standard boiling point of the isocyanate to be produced may be the standard boiling point of an isocyanate in which all ureido groups or all primary amino groups of the compound having ureido groups or the organic primary amine are converted to isocyanate groups. In a preferable aspect, the compound having ureido groups is a compound having ureido groups that is obtained by carrying out the step (A). Namely, an aromatic hydroxy compound is preferable in which the standard boiling point of the aromatic hydroxy compound that composes the aromatic hydroxy composition differs by 10°C or more from the standard boiling point of an isocyanate having a structure in which all of the amino groups (primary amino groups) of the organic primary amine are converted to isocyanate groups.

[0121] Moreover, in consideration of industrial use, an aromatic monohydroxy compound having an easily acquirable benzene ring for the skeleton thereof is preferable. Preferable examples of such an aromatic monohydroxy compound may include aromatic monohydroxy compounds represented by the following formula (31):



(3 1)

(wherein

10 R¹⁹, R²⁰, R²¹, R²² and R²³ are groups independently selected from the above-mentioned groups R⁷ to R¹⁴ (excluding aryl groups having a hydroxy group), and the aromatic hydroxy compound represented by formula (31) is an aromatic monohydroxy compound in which the number of carbon atoms is an integer of from 6 to 50, namely the total number of carbon atoms of groups R¹⁹, R²⁰, R²¹, R²² and R²³ is an integer of from 0 to 44).

15 **[0122]** Among the aromatic monohydroxy compounds represented by the above-mentioned formula (31), groups R¹⁹, R²⁰, R²¹, R²² and R²³ are preferably hydrogen atoms and/or groups respectively and independently selected from the groups indicated in the following (i) to (iii):

20 (i): a group in which the atom at the α position (atom bonded to the aromatic ring) is a carbon atom, the number of carbon atoms is from 1 to 44, a group bonded to the α position carbon atom is a hydrogen atom, alkyl group having 1 to 43 carbon atoms, cycloalkyl group having 1 to 44 carbon atoms, alkoxy group having 1 to 44 carbon atoms, polyoxyalkylene alkyl ether group having 2 to 44 carbon atoms but not having an OH group on a terminal thereof, aryl group having 6 to 43 carbon atoms, aralkyl group having 7 to 43 carbon atoms or aralkyloxy group having 7 to 19 carbon atoms, and three groups selected from groups in which one or more types of the above groups are bonded are bonded to the carbon atom,

25 (ii) an aryl group in which the number of carbon atoms is from 1 to 44, the aryl group is substituted by substituents, and the substituents are aryl groups that may be substituted with an integral number of from 1 to 5 of the following substituents, the substituents being selected from a hydrogen atom, an alkyl group having 1 to 38 carbon atoms, a cycloalkyl group having 4 to 38 carbon atoms, an alkoxy group having 1 to 38 carbon atoms, a polyoxyalkylene alkyl ether group having 2 to 38 carbon atoms but not having an OH group on a terminal thereof, an aryl group having 6 to 38 carbon atoms, an aralkyl group having 7 to 38 carbon atoms, an aralkyloxy group having 7 to 38 carbon atoms, and a group in which one or more types of the above groups are bonded,

30 (iii) a group in which the atom at the α position (atom bonded to the aromatic ring) is an oxygen atom, the number of carbon atoms is from 1 to 44, and a group bonded to the α position oxygen atom is a group selected from an alkyl group having 1 to 43 carbon atoms, a cycloalkyl group having 4 to 44 carbon atoms, an alkoxy group having 1 to 44 carbon atoms, a polyoxyalkylene alkyl ether group having 2 to 44 carbon atoms but not having an OH group on a terminal thereof, an aryl group having 6 to 43 carbon atoms, an aralkyl group having 7 to 43 carbon atoms, and a group in which one or more types of the above groups are bonded.

35 **[0123]** Furthermore, although the term "atom at the α position" is used in the above-mentioned formula (31), an "atom at the α position" refers to an atom that composes the groups R¹⁹, R²⁰, R²¹, R²² and R²³ are that is adjacent to a carbon atom on the aromatic hydrocarbon ring to which groups R¹⁹, R²⁰, R²¹, R²² and R²³ are bonded. Examples of these R¹⁹, R²⁰, R²¹, R²² and R²³ may include hydrogen atoms, alkyl groups and/or cycloalkyl groups and/or cycloalkyl groups substituted with an alkyl group and/or alkyl groups substituted with a cycloalkyl group such as a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, a decyl group, a dodecyl group, an octadecyl group, cyclopentyl group, cyclohexyl group, cycloheptyl group, cyclooctyl group, bis(cyclohexyl) alkane, methylcyclopentyl group, ethylcyclopentyl group, methylcyclohexyl group, ethylcyclohexyl group, propylcyclohexyl group, butylcyclohexyl group, pentylcyclohexyl group, hexylcyclohexyl group, dimethylcyclohexyl group, diethylcyclohexyl group or dibutylcyclohexyl group, alkoxy groups and/or cycloalkoxy groups and/or cycloalkoxy groups substituted with an alkoxy group and/or alkoxy groups substituted with a cycloalkoxy group such as a methoxy group, an ethoxy group, propoxy group, a butyloxy group, a pentyloxy group, a hexyloxy group, a heptyloxy group, an octyloxy group, a nonyloxy group, a decyloxy group, a dodecyloxy group, an octadecyloxy group, a cyclopentyloxy group, a cyclohexyloxy group, a cycloheptyloxy group, a cyclooctyloxy group, a methylcyclopentyloxy group, an ethylcyclopentyloxy group, a methylcyclohexyloxy group, an ethylcyclohexyloxy group, a propylcyclohexyloxy group, a butylcyclohexyloxy group, a pentylcyclohexyloxy group, a hexylcyclohexyloxy group, a dimethylcyclohexyloxy group, a diethylcyclohexyloxy group or a dibutylcyclohexyloxy group; substituted or unsubstituted aryl groups such as a phenyl group, a methylphenyl group, an ethylphenyl group, a propylphenyl group, a butylphenyl group, a pentylphenyl group, a hexylphenyl group, a heptylphenyl group, an octylphenyl group, a nonylphenyl group, a decylphenyl group, a biphenyl group, a dimethylphenyl group, a diethylphenyl group, a dipropylphenyl group, a dibutylphenyl group, a dipentylphenyl

group, a dihexylphenyl group, a diheptylphenyl group, a terphenyl group, a trimethylphenyl group, a triethylphenyl group, a tripropylphenyl group or a tributylphenyl group; substituted or unsubstituted aryloxy groups such as a phenoxy group, a methylphenoxy group, an ethylphenoxy group, a propylphenoxy group, a butylphenoxy group, a pentylphenoxy group, a hexylphenoxy group, a heptylphenoxy group, an octylphenoxy group, a nonylphenoxy group, a decylphenoxy group, a phenylphenoxy group, a dimethylphenoxy group, a diethylphenoxy group, a dipropylphenoxy group, a dibutylphenoxy group, a dipentylphenoxy group, a dihexylphenoxy group, a diheptylphenoxy group, a diphenylphenoxy group, a trimethylphenoxy group, a triethylphenoxy group, a tripropylphenoxy group or a tributylphenoxy group; substituted or unsubstituted aralkyl groups such as a phenylmethyl group, a phenylethyl group, a phenylpropyl group, a phenylbutyl group, a phenylpentyl group, a phenylhexyl group, a phenylheptyl group, a phenyloctyl group or a phenylnonyl group, aralkyloxy groups such as a phenylmethoxy group, a phenylethoxy group, a phenylpropyloxy group, a phenylbutyloxy group, a phenylpentyloxy group, a phenylhexyloxy group, a phenylheptyloxy group, a phenyloctyloxy group, or a phenylnonyloxy group, and groups composed of hydroxyaryl groups and alkyl groups such as a hydroxyphenyl group, a hydroxyphenoxy group, a hydroxyphenylmethyl group, a hydroxyphenylethyl group or a hydroxyphenylpropyl group.


[0124] Preferable examples of aromatic monohydroxy compounds represented by the above-mentioned formula (30) may include the following compounds: phenol, methylphenol, ethylphenol, propylphenol, butylphenol, pentylphenol, hexylphenol, heptylphenol, octylphenol, nonylphenol, decylphenol, dodecylphenol, octadecylphenol, dimethylphenol, dimethylphenol, dipropylphenol, dibutylphenol, dipentylphenol, dihexylphenol, diheptylphenol, dioctylphenol, dinonylphenol, didodecylphenol, didodecylphenol, dioctadecylphenol, trimethylphenol, triethylphenol, tripropylphenol, tributylphenol, tripentylphenol, trihexylphenol, triheptylphenol, trioctylphenol, trinonylphenol, tridecylphenol, tridodecylphenol, trioctadecylphenol, (methoxymethyl)phenol, (ethoxymethyl)phenol, (propoxymethyl)phenol, (butyloxymethyl)phenol, (pentyloxymethyl)phenol, (hexyloxymethyl)phenol, (heptyloxymethyl)phenol, (octyloxymethyl)phenol, (nonyloxymethyl)phenol, (decyloxymethyl)phenol, (dodecyloxymethyl)phenol, (octadecyloxymethyl)phenol, (cyclopentyloxymethyl)phenol, (cyclohexyloxymethyl)phenol, (cycloheptyloxymethyl)phenol, (cyclooctyloxymethyl)phenol, (methylcyclopentyloxymethyl)phenol, (ethylcyclopentyloxymethyl)phenol, (methylcyclohexyloxymethyl)phenol, (ethylcyclohexyloxymethyl)phenol, (propylcyclohexyloxymethyl)phenol, (butylcyclohexyloxymethyl)phenol, (pentylcyclohexyloxymethyl)phenol, (hexylcyclohexyloxymethyl)phenol, (dimethylcyclohexyloxymethyl)phenol, (diethylcyclohexyloxymethyl)phenol, (dibutylcyclohexyloxymethyl)phenol, (phenoxymethyl)phenol, (methylphenoxymethyl)phenol, (ethylphenoxymethyl)phenol, (propylphenoxymethyl)phenol, (butylphenoxymethyl)phenol, (pentylphenoxymethyl)phenol, (hexylphenoxymethyl)phenol, (heptylphenoxymethyl)phenol, (octylphenoxymethyl)phenol, (nonylphenoxymethyl)phenol, (decylphenoxymethyl)phenol, (phenylphenoxymethyl)phenol, (dimethylphenoxymethyl)phenol, (diethylphenoxymethyl)phenol, (dipropylphenoxymethyl)phenol, (dibutylphenoxymethyl)phenol, (dipentylphenoxymethyl)phenol, (dihexylphenoxymethyl)phenol, (diheptylphenoxymethyl)phenol, (diphenylphenoxymethyl)phenol, (trimethylphenoxymethyl)phenol, (triethylphenoxymethyl)phenol, (tripropylphenoxymethyl)phenol, (tributylphenoxymethyl)phenol, (phenylmethoxymethyl)phenol, (phenylethoxymethyl)phenol, (phenylpropyloxymethyl)phenol, (phenylbutyloxymethyl)phenol, (phenylpentyloxymethyl)phenol, (phenylhexyloxymethyl)phenol, (phenylheptyloxymethyl)phenol, (phenyloctyloxymethyl)phenol, (phenylnonyloxymethyl)phenol, di(methoxymethyl)phenol, di(ethoxymethyl)phenol, di(propoxymethyl)phenol, di(butyloxymethyl)phenol, di(pentyloxymethyl)phenol, di(hexyloxymethyl)phenol, di(heptyloxymethyl)phenol, di(octyloxymethyl)phenol, di(nonyloxymethyl)phenol, di(decyloxymethyl)phenol, di(dodecyloxymethyl)phenol, di(octadecyloxymethyl)phenol, di(cyclopentyloxymethyl)phenol, di(cyclohexyloxymethyl)phenol, di(cycloheptyloxymethyl)phenol, di(cyclooctyloxymethyl)phenol, di(methylcyclopentyloxymethyl)phenol, di(ethylcyclopentyloxymethyl)phenol, di(methylcyclohexyloxymethyl)phenol, di(ethylcyclohexyloxymethyl)phenol, di(propylcyclohexyloxymethyl)phenol, di(butylcyclohexyloxymethyl)phenol, di(pentylcyclohexyloxymethyl)phenol, di(hexylcyclohexyloxymethyl)phenol, bis(dimethylcyclohexyloxymethyl)phenol, bis(diethylcyclohexyloxymethyl)phenol, bis(dibutylcyclohexyloxymethyl)phenol, di(phenoxymethyl)phenol, di(methylphenoxymethyl)phenol, di(ethylphenoxymethyl)phenol, di(propylphenoxymethyl)phenol, di(butylphenoxymethyl)phenol, di(pentylphenoxymethyl)phenol, di(hexylphenoxymethyl)phenol, di(heptylphenoxymethyl)phenol, di(octylphenoxymethyl)phenol, di(nonylphenoxymethyl)phenol, di(decylphenoxymethyl)phenol, di(phenylphenoxymethyl)phenol, bis(dimethylphenoxymethyl)phenol, bis(diethylphenoxymethyl)phenol, bis(dipropylphenoxymethyl)phenol, bis(dibutylphenoxymethyl)phenol, bis(dipentylphenoxymethyl)phenol, bis(dihexylphenoxymethyl)phenol, bis(diheptylphenoxymethyl)phenol, bis(diphenylphenoxymethyl)phenol, di(trimethylphenoxymethyl)phenol, di(triethylphenoxymethyl)phenol, di(tripropylphenoxymethyl)phenol, di(tributylphenoxymethyl)phenol, (phenylmethoxymethyl)phenol, di(phenylethoxymethyl)phenol, di(phenylpropyloxymethyl)phenol, di(phenylbutyloxymethyl)phenol, di(phenylpentyloxymethyl)phenol, di(phenylhexyloxymethyl)phenol, di(phenylheptyloxymethyl)phenol, di(phenyloctyloxymethyl)phenol, di(phenylnonyloxymethyl)phenol, tri(methoxymethyl)phenol, tri(ethoxymethyl)phenol, tri(propoxymethyl)phenol, tri(butyloxymethyl)phenol, tri(pentyloxymethyl)phenol, tri(hexyloxymethyl)phenol, tri(hptyloxymethyl)phenol, tri(octyloxymethyl)phenol, tri(nonyloxymethyl)phenol, tri(decyloxymethyl)phenol, tri(dodecyloxymethyl)phenol, tri(octadecyloxymethyl)phenol, tri(cyclopentyloxymethyl)phenol, tri(cyclohexyloxymethyl)phenol, tri(cycloheptyloxymethyl)phenol, tri(cyclooctyloxymethyl)phenol, tri(methylcyclopenty-

nyloxy) phenol, diterphenyloxyphenol, di(trimethylphenyloxy) phenol, di(triethylphenyloxy) phenol, di(tripropylphenyloxy) phenol, di(tributylphenyloxy) phenol, (phenylmethyloxy) phenol, di(phenylethyloxy) phenol, di(phenylpropyloxy) phenol, di(phenylbutyloxy) phenol, di(phenylpentyloxy) phenol, di(phenylhexyloxy) phenol, di(phenylheptyloxy) phenol, di(phenyloctyloxy) phenol, di(phenylnonyloxy) phenol, trimethoxyphenol, triethoxyphenol, tripropyloxyphenol, tributylloxyphenol, tripentyloxyphenol, trihexyloxyphenol, triheptyloxyphenol, trioctyloxyphenol, trinonyloxyphenol, tridecyloxyphenol, tridodecyloxyphenol, trioctadecyloxyphenol, tricyclopentyloxyphenol, tricyclohexyloxyphenol, tricycloheptyloxyphenol, tricyclooctyloxyphenol, tri(methylcyclopentyloxy) phenol, tri(ethylcyclopentyloxy) phenol, tri(methylcyclohexyloxy) phenol, tri(ethylcyclohexyloxy) phenol, tri(propylcyclohexyloxy) phenol, tri(butylcyclohexyloxy) phenol, tri(pentylcyclohexyloxy) phenol, tri(hexylcyclohexyloxy) phenol, tri(dimethylcyclohexyloxy) phenol, tri(diethylcyclohexyloxy) phenol, tri(dibutylcyclohexyloxy) phenol, phenyloxyphenol, tri(methylphenyloxy) phenol, tri(ethylphenyloxy) phenol, tri(propylphenyloxy) phenol, tri(butylphenyloxy) phenol, tri(pentylphenyloxy) phenol, tri(hexylphenyloxy) phenol, tri(heptylphenyloxy) phenol, tri(octylphenyloxy) phenol, tri(nonylphenyloxy) phenol, tri(decylphenyloxy) phenol, tribiphenyloxyphenol, tri(dimethylphenyloxy) phenol, tri(diethylphenyloxy) phenol, tri(dipropylphenyloxy) phenol, tri(dibutylphenyloxy) phenol, tri(dipentylphenyloxy) phenol, tri(dihexylphenyloxy) phenol, tri(diheptylphenyloxy) phenol, triterphenyloxyphenol, tri(trimethylphenyloxy) phenol, tri(triethylphenyloxy) phenol, tri(tripropylphenyloxy) phenol, tri(tributylphenyloxy) phenol, (phenylmethyloxy) phenol, tri(phenylethyloxy) phenol, tri(phenylpropyloxy) phenol, tri(phenylbutyloxy) phenol, tri(phenylpentyloxy) phenol, tri(phenylhexyloxy) phenol, tri(phenylheptyloxy) phenol, tri(phenyloctyloxy) phenol, tri(phenylnonyloxy) phenol, phenylphenol, hydroxyphenylphenol, hydroxyphenoxy phenol, hydroxyphenylmethyl phenol, hydroxyphenylethyl phenol, hydroxyphenylpropyl phenol, naphthol, phenoxyphenol, and diphenoxyphenol.

[0125] Preferable examples of the above-mentioned aromatic monohydroxy compounds may include those in which at least two of the groups R^{19} , R^{20} , R^{21} , R^{22} and R^{23} are hydrogen atoms due to ease of transfer, and more preferably the number of carbon atoms that compose the groups R^{19} , R^{20} , R^{21} , R^{22} and R^{23} is from 0 to 13. Even more preferably, the aromatic monohydroxy compound is an aromatic monohydroxy compound in which the groups R^{20} , R^{21} , R^{22} and R^{23} are groups having 0 to 9 carbon atoms that are selected hydrogen atoms, linear or branched alkyl groups, cycloalkyl groups, substituted or unsubstituted aryl groups, linear or branched alkoxy groups, substituted or unsubstituted aryloxy groups and substituted or unsubstituted aralkyl groups.

[0126] The following provides an explanation of an active aromatic monohydroxy compound. An aromatic hydroxy compound represented by the above-mentioned formula (2) and/or formula (7) and/or formula (31) can be preferably used as an aromatic hydroxy compound that composes an aromatic composition used in a composition for transfer and storage of a compound having ureido groups. In addition, it can also be preferably used as the aromatic hydroxy compound that composes an aromatic hydroxy composition used during production of an N-substituted carbamic acid-O-aryl ester by reacting with a compound having ureido groups and/or an N-substituted carbamic acid-O- R^2 ester. However, the latter aromatic hydroxy compound that composes an aromatic hydroxy composition used during production of an N-substituted carbamic acid-O-aryl ester is a compound that composes an -O-aryl ester group in an N-substituted carbamic acid-O-aryl ester by reacting with a compound having ureido groups and/or an N-substituted carbamic acid-O- R^2 ester. In the case of using the composition for transfer and storage of a compound having ureido groups as a raw material of an N-substituted carbamic acid-O-aryl ester, in the case of producing an N-substituted carbamic acid-O-aryl ester by using a compound having ureido groups as a raw material, or when using as a raw material of an N-substituted carbamic acid-O- R^2 ester followed by producing an N-substituted carbamic acid-O-aryl ester, although the aromatic hydroxy compound is included in the above-mentioned formula (2) and/or formula (7) and/or formula (31), an aromatic hydroxy compound represented by the following formula (32) is used particularly preferably (an aromatic hydroxy compound represented by formula (32) is frequently referred to as an "active aromatic hydroxy compound" in the present specification in order to express the ease by which the reaction occurs). The active aromatic hydroxy compound represented by the following formula (32) may be used alone as an aromatic hydroxy composition used in a composition for transfer and storage of a compound having ureido groups, or may be used as one type of aromatic hydroxy compound that composes an aromatic hydroxy composition. In addition, the aromatic hydroxy compound represented by the following formula (32) may be used alone as an aromatic hydroxy composition for obtaining an N-substituted carbamic acid-O-aryl ester by reacting with a compound having ureido groups and/or an N-substituted carbamic acid-O- R^2 ester, or may be used as one type of aromatic hydroxy compound that composes an aromatic hydroxy composition. Naturally, a plurality of active aromatic hydroxy compounds represented by the following formula (32) may also be used in each of the cases described above.

[0127] The active aromatic monohydroxy compound is represented by the following formula (32):



(32)

5

10 (wherein
ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy groups at
arbitrary locations that maintain aromatic properties, may be a single or multiple heterocyclic ring, and may be substituted
by other substituents, and an integral number of from 1 to 6 OH groups represented by formula (32) are substituted on
an aromatic ring contained in the ring A (namely, the formula (32) constitutes a portion of the ring A, and an integral
15 number of from 1 to 6 structures to which the above-mentioned R²⁴ group, OH group and R²⁵ group are adjacent are
respectively present on the ring A).

[0128] R²⁴ and R²⁵ are groups bonded to the aromatic ring to which the hydroxy group is bonded, and which are
bonded to a carbon atom adjacent to the carbon atom to which the hydroxy group is bonded. An integral number of from
1 to 6 hydroxy groups are bonded to ring A, and thus, an integral number of from 1 to 6 of R²⁴ and R²⁵ are respectively
20 bonded to ring A. An aromatic hydroxy compound represented by formula (32) is an aromatic hydroxy compound that
contains an integral number of carbon atoms within a range of from 6 to 50.

[0129] A substituent that substitutes an aromatic group of an aromatic hydroxy compound represented by formula
(32) above (while groups R²⁴ and R²⁵ will be subsequently explained in detail) is selected from the group consisting of
a hydrogen atom, a halogen atom, an aliphatic group, an aromatic group and an aliphatic group in which an aromatic
group is bonded, is a group composed of an acyclic hydrocarbon group or a cyclic hydrocarbon group (such as a
25 monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a
spirohydrocarbon group, a ring-assembling hydrocarbon group, a cyclic hydrocarbon group having a side chain, a
heterocyclic group, a heterocyclic spiro group, a hetero-crosslinked ring group or a heterocyclic group), a group bonded
from one or more types of groups selected from the above-mentioned acyclic hydrocarbon groups and cyclic hydrocarbon
groups, and groups in which the above-mentioned groups are bonded through a covalent bond with a specific non-metal
30 atom (carbon, oxygen, nitrogen, sulfur or silicon). In addition, a covalent bond with a specific non-metal atom (carbon,
oxygen, nitrogen, sulfur or silicon) as described above is in a state in which the above-mentioned groups are bonded
by a covalent bond with, for example, groups represented by the above-mentioned formulas (8) to (11) and (13) to (16).

[0130] Among such substituents, examples of substituents that can be preferably used in the present embodiment in
consideration of less susceptibility to the occurrence of side reactions may include groups selected from the group
consisting of acyclic hydrocarbon groups and cyclic hydrocarbon groups (such as a monocyclic hydrocarbon group, a
condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-
assembling hydrocarbon group or a cyclic hydrocarbon group having a side chain), and groups bonded to at least one
35 type of group selected from this group (mutually substituted groups).

[0131] In addition, in the case of transferring a composition containing a compound having ureido groups at a high
temperature, or in the case carrying out a reaction for obtaining an N-substituted carbamic acid-O-aryl ester by reacting
a compound having ureido groups and/or an N-substituted carbamic acid O-R² ester and an aromatic hydroxy composition
at a high temperature, the ring A of the aromatic hydroxy compound is preferably composed of a group having at least
one inactive substituent (including hydrogen atoms) in addition to the aromatic group and the hydroxy group bonded to
45 the aromatic group (here, an inactive substituent refers to a group in which the inactive substituent does not contain an
active hydrogen as previously described, although it may have an aromatic hydroxyl group).

[0132] In providing a more detailed explanation of the substituent, an aromatic hydroxy compound represented by
formula (32) is an aromatic hydroxy compound having at least one substituent selected from the group of substituents
explained in the following (i) to (v) in addition to the aromatic group and the hydroxy group bonded to the aromatic group
50 (while groups R²⁴ and R²⁵ will be subsequently explained in detail).

(i) a hydrogen atom,

(ii) a group composed of carbon atoms and hydrogen atoms (which may also form a condensed ring structure by
bonding with ring A),

55 (iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether
group composed of aliphatic groups, an ether group composed of aromatic groups or an ether group composed of
aliphatic groups and aromatic groups, but excluding carbonyl group, an ester group, a terminal methine group and
an alcoholic OH group or a carboxyl group),



(iv) a halogen atom, and

(v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms (but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, a carboxyl group, a NH_2 group, a NH group, a NOH group, a SH group, a SO_3H group or a SOH group).


5

[0133] R^{24} and R^{25} respectively and independently represent any of the groups defined in the following (i) to (v), and R^{24} and R^{25} may further form a condensed ring structure by bonding with ring A. In the case the relationship between ring A and the hydroxyl group in the above-mentioned formula (32), for example, is a structure shown in the following formula (33) or formula (34), although the number of R^{24} and R^{25} bonded to a carbon adjacent to the OH group bonded to the aromatic group that composes ring A may frequently not coincide with the number of the OH groups, in the structure represented by the following formula (33), ring A may be a ring moiety shown on the right side of the following formula (35), while R^{25} may form a ring structure by bonding with ring A. In the case of formula (34), the aromatic hydroxyl group bonded to ring A is the center OH group, while the adjacent OH groups may be groups R^{24} and R^{25} , respectively:

15



20





25

(i) a hydrogen atom,

(ii) a group composed of carbon atoms and hydrogen atoms (which may also form a condensed ring structure by bonding with ring A), in which the atom at the α position (atom that forms the R^{24} and R^{25} that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a primary or secondary carbon atom (namely, representing a carbon atom of a methyl group or carbon atom that forms a $-\text{CH}_2-$ bond), provided that in the case the R^{24} and/or R^{25} form a saturated and/or unsaturated condensed ring structure with ring A and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom as in, for example, the case of the following formula (36) or formula (37), and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R^{24} and R^{25} that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom,

40



45

(iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, an ether group composed of aromatic groups or an ether group composed of aliphatic groups and aromatic groups, but not having an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group or a methine group on a terminal thereof), in which the atom at the α position (atom that forms the R^{24} and R^{25} that is bonded to the aromatic ring of ring A) is a carbon atom or oxygen atom, and in the case of a carbon atom, the carbon atom is a primary or secondary carbon atom (namely, a carbon atom of a methyl group or a carbon atom that forms a $-\text{CH}_2-$ bond), provided that in the case the R^{24} and/or R^{25} form a saturated and/or unsaturated condensed ring structure with ring A and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom, and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R^{24} and R^{25} that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom,

(iv) a halogen atom,

55


(v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms (but excluding an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group, a terminal methine group, a NH₂ group, a NH group, a NOH group, a SH group, a SO₃H group or a SOH group), in which the atom at the α position (atom that forms the R²⁴ and R²⁵ that is bonded to the aromatic ring of ring A) is a carbon atom, oxygen atom or sulfur atom, in the case of a carbon atom, the carbon atom is a primary or secondary carbon atom (namely, a carbon atom of a methyl group or a carbon atom that forms a -CH₂- bond), and in the case of a sulfur atom, the sulfur atom is a divalent sulfur atom (namely, a sulfur atom that forms an -S-bond), provided that in the case the R²⁴ and/or R²⁵ form a saturated and/or unsaturated condensed ring structure with ring A and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom, and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R²⁴ and R²⁵ that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom.

[0134] Although the term "active hydrogen" is used here, active hydrogen refers to a hydrogen atom bonded to oxygen, sulfur or nitrogen. However, aromatic hydroxyl groups are excluded. Although aromatic hydroxyl groups (OH groups directly bonded to an aromatic group) also constitute active hydrogen, since the aromatic hydroxyl groups are also contained in the composition of the present embodiment and reaction raw materials and do not have a detrimental effect, aromatic hydroxyl groups are not included in groups containing active hydrogen unless specifically indicated otherwise. Although the "groups containing active hydrogen" are frequently described in other locations of the present embodiment, the above-mentioned definition applies to such groups. Such active hydrogen is highly reactive, and reacts with the organic primary amine, urea compound and the like used in the present embodiment as well as with compounds having ureido groups, N-substituted carbamic acid-O-(R² or aryl) esters and the like formed in the present embodiment resulting in the formation of reaction by-products, thereby making them undesirable.

[0135] In addition, ring A is preferably a structure that contains at least one structure selected from the group consisting of a benzene ring, a naphthalene ring and an anthracene ring. In consideration of the industrial use, the active aromatic hydroxy compound represented by the above-mentioned formula (32) is preferably an aromatic monohydroxy compound in which one or two aromatic hydroxyl groups are bonded to ring A (namely, b = 1 or 2), and more preferably an aromatic monohydroxy compound in which one aromatic hydroxyl group is bonded to ring A, since they typically have low viscosity.

[0136] As was previously described, an aromatic hydroxy compound represented by formula (2), (7), (31) or (32) is formed as a by-product together with isocyanate during thermal decomposition of the N-substituted carbamic acid-O-aryl ester when carrying out the step (F) (frequently referred to as the thermal decomposition step, thermal decomposition or during thermal decomposition). In one aspect of the present embodiment, although depending on the case, the aromatic hydroxy compound and isocyanate are separated by distillation following the thermal decomposition step, and the separated aromatic hydroxy compound may be recycled in the form of the aromatic hydroxy composition of the present embodiment. Separation is carried out using standard boiling point as an indicator, and the method is selected in accordance with the previously described definition.

[0137] Moreover, in consideration of the industrial use, the active aromatic hydroxy compound is preferably an easily acquirable aromatic monohydroxy compound. A preferable example of such an aromatic monohydroxy compound is an aromatic monohydroxy compound represented by the following formula (38):




(wherein

R²⁸, R²⁹ and R³⁰ are groups respectively and independently selected from the above-mentioned groups R⁷ to R¹⁴ (excluding aryl groups having a hydroxy group), groups R²⁶ and R²⁷ are groups respectively and independently selected from the above-mentioned groups R²⁴ and R²⁵, and the aromatic hydroxy compound represented by formula (38) is an aromatic monohydroxy compound having an integral number of from 6 to 50 carbon atoms, provided that the total number of carbon atoms of groups R²⁶, R²⁷, R²⁸, R²⁹ and R³⁰ is an integer of from 0 to 44, and R²⁶ and R²⁷ are respectively and independently any group defined in the following (i) to (iii).

[0138] R²⁶ and R²⁷ are groups respectively and independently selected from the above-mentioned groups R²⁴ and R²⁵, and are respectively and independently any group defined in the following (i) to (iii):

(i) a hydrogen atom,

(ii) a group composed of carbon atoms and hydrogen atoms (which may also form a ring structure by bonding with ring A), in which the atom at the α position (atom that forms the R^{26} and R^{27} that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a primary or secondary carbon atom (namely, representing a carbon atom of a methyl group or carbon atom that forms a $-CH_2-$ bond), provided that in the case the R^{26} and/or R^{27} form a saturated and/or unsaturated condensed ring structure with an aromatic ring and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom as in, for example, the case of the following formula (36) or formula (37), and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R^{26} and R^{27} that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom,



(iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, an ether group composed of aromatic groups or an ether group composed of aliphatic groups and aromatic groups, but not having an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group or a methine group on a terminal thereof), in which the atom at the α position (atom that forms the R^{26} and R^{27} that is bonded to the aromatic ring of ring A) is a carbon atom or an oxygen atom, and in the case of a carbon atom, the carbon atom is a primary or secondary carbon atom (namely, a carbon atom of a methyl group or a carbon atom that forms a $-CH_2-$ bond), provided that in the case the R^{26} and/or R^{27} form a saturated and/or unsaturated condensed ring structure and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom, and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R^{26} and R^{27} that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom.

[0139] Active aromatic monohydroxy compounds in which the R^{26} and the R^{27} are hydrogen atoms are preferable, and examples of such aromatic monohydroxy compounds may include phenol, methylphenol, ethylphenol, 2-n-propylphenol, 2-n-butylphenol, 2-n-pentylphenol, 2-n-hexylphenol, 2-n-heptylphenol, 2-n-octylphenol, 2-n-nonylphenol, 2-n-decylphenol, 2-n-dodecylphenol, 2-n-octadecylphenol, 3-propylphenol, 3-butylphenol, 3-pentylphenol, 3-hexylphenol, 3-heptylphenol, 3-octylphenol, 3-nonylphenol, 3-dodecylphenol, 3-octadecylphenol, 4-propylphenol, 4-butylphenol, 4-pentylphenol, 4-hexylphenol, 4-heptylphenol, 4-octylphenol, 4-nonylphenol, 4-decylphenol, 4-dodecylphenol, 4-octadecylphenol, dimethylphenol, diethylphenol, di(n-propyl)phenol, di(n-butyl)phenol, di(n-pentyl)phenol, di(n-hexyl)phenol, di(n-heptyl)phenol, di(n-octyl)phenol, di(n-nonyl)phenol, di(n-decyl)phenol, di(n-dodecyl)phenol, di(n-octadecyl)phenol, trimethylphenol, triethylphenol, tri(n-propyl)phenol, tri(n-butyl)phenol, tri(n-pentyl)phenol, tri(n-hexyl)phenol, tri(n-heptyl)phenol, tri(n-octyl)phenol, tri(n-nonyl)phenol, tri(n-decyl)phenol, tri(n-dodecyl)phenol, tri(n-octadecyl)phenol, (methoxymethyl)phenol, (ethoxymethyl)phenol, (propoxymethyl)phenol, (butyloxymethyl)phenol (including isomers), (pentyloxymethyl)phenol, (hexyloxymethyl)phenol, (heptyloxymethyl)phenol, (octyloxymethyl)phenol, (nonyloxymethyl)phenol, (decyloxymethyl)phenol, (dodecyloxymethyl)phenol, (octadecyloxymethyl)phenol, (cyclopentyloxymethyl)phenol, (cyclohexyloxymethyl)phenol, (cycloheptyloxymethyl)phenol, (cyclooctyloxymethyl)phenol, (methylcyclopentyloxymethyl)phenol, (ethylcyclopentyloxymethyl)phenol, (methylcyclohexyloxymethyl)phenol, (ethylcyclohexyloxymethyl)phenol, (propylcyclohexyloxymethyl)phenol, (butylcyclohexyloxymethyl)phenol, (pentylcyclohexyloxymethyl)phenol, (hexylcyclohexyloxymethyl)phenol, (dimethylcyclohexyloxymethyl)phenol, (diethylcyclohexyloxymethyl)phenol, (dibutylcyclohexyloxymethyl)phenol, (phenoxymethyl)phenol, (methylphenoxymethyl)phenol, (ethylphenoxymethyl)phenol, (propylphenoxymethyl)phenol, (butylphenoxymethyl)phenol, (pentylphenoxymethyl)phenol, (hexylphenoxymethyl)phenol, (heptylphenoxymethyl)phenol, (octylphenoxymethyl)phenol, (nonylphenoxymethyl)phenol, (decylphenoxymethyl)phenol, (phenylphenoxymethyl)phenol, (dimethylphenoxymethyl)phenol, (diethylphenoxymethyl)phenol, (dipropylphenoxymethyl)phenol, (dibutylphenoxymethyl)phenol, (dipentylphenoxymethyl)phenol, (dihexylphenoxymethyl)phenol, (diheptylphenoxymethyl)phenol, (diphenylphenoxymethyl)phenol, (trimethylphenoxymethyl)phenol, (triethylphenoxymethyl)phenol, (tripropylphenoxymethyl)phenol, (tributylphenoxymethyl)phenol, (phenylmethoxymethyl)phenol, (phenylethoxymethyl)phenol, (phenylpropyloxymethyl)phenol, (phenylbutyloxymethyl)phenol, (phenylpentyloxymethyl)phenol, (phenylhexyloxymethyl)phenol, (phenylheptyloxymethyl)phenol, (phenyloctyloxymethyl)phenol, (phenylnonyloxymethyl)phenol, di(methoxymethyl)phenol, di(ethoxymethyl)phenol, di(propoxymethyl)phenol,

di(butyloxymethyl) phenol di(pentyloxymethyl) phenol , di(hexyloxymethyl) phenol , di(heptyloxymethyl) phenol , di(octyloxymethyl) phenol , di(nonyloxymethyl) phenol , di(decyloxymethyl) phenol , di(dodecyloxymethyl) phenol , di(octadecyloxymethyl) phenol , di(cyclopentyloxymethyl) phenol , di(cyclohexyloxymethyl) phenol , di(cycloheptyloxymethyl) phenol , di(cyclooctyloxymethyl) phenol , di(methylcyclopentyloxymethyl) phenol , di(ethylcyclopentyloxymethyl) phenol ,
 5 di(methylcyclohexyloxymethyl) phenol , di(ethylcyclohexyloxymethyl) phenol , di(propylcyclohexyloxymethyl) phenol , di(butylcyclohexyloxymethyl) phenol , di(pentylcyclohexyloxymethyl) phenol , di(hexylcyclohexyloxymethyl) phenol , bis(dimethylcyclohexyloxymethyl) phenol , bis(diethylcyclohexyloxymethyl) phenol , bis(dibutylcyclohexyloxymethyl) phenol ; di(phenoxymethyl) phenol , di(methylphenoxymethyl) phenol ; di(ethylphenoxymethyl) phenol , di(propylphenoxymethyl) phenol , di(butylphenoxymethyl) phenol , di(pentylphenoxymethyl) phenol , di(hexylphenoxymethyl) phenol , di(heptylphenoxymethyl) phenol , di(octylphenoxymethyl) phenol , di(nonylphenoxymethyl) phenol , di(decylphenoxymethyl) phenol di(phenylphenoxymethyl) phenol , bis(dimethylphenoxymethyl) phenol , bis(diethylphenoxymethyl) phenol , bis(dipropylphenoxymethyl) phenol , bis(dibutylphenoxymethyl) phenol , bis(dipentylphenoxymethyl) phenol , bis(dihexylphenoxymethyl) phenol , bis(diheptylphenoxymethyl) phenol , bis(diphenylphenoxymethyl) phenol , di(trimethylphenoxymethyl) phenol , di(triethylphenoxymethyl) phenol , di(tripropylphenoxymethyl) phenol , di(tributylphenoxymethyl) phenol , (phenylmethoxymethyl) phenol , di(phenylethoxymethyl) phenol di(phenylpropyloxymethyl) phenol , di(phenylbutyloxymethyl) phenol , di(phenylpentyloxymethyl) phenol , di(phenylhexyloxymethyl) phenol , di(phenylheptyloxymethyl) phenol , di(phenyloctyloxymethyl) phenol , di(phenylnonyloxymethyl) phenol , tri(methoxymethyl) phenol , tri(ethoxymethyl) phenol , tri(propoxymethyl) phenol , tri(butyloxymethyl) phenol , tri(pentyloxymethyl) phenol , tri(hexyloxymethyl) phenol , tri(heptyloxymethyl) phenol , tri(octyloxymethyl) phenol , tri(nonyloxymethyl) phenol , tri(decyloxymethyl) phenol , tri(dodecyloxymethyl) phenol , tri(octadecyloxymethyl) phenol , tri(cyclopentyloxymethyl) phenol , tri(cyclohexyloxymethyl) phenol , tri(cycloheptyloxymethyl) phenol , tri(cyclooctyloxymethyl) phenol , tri(methylcyclopentyloxymethyl) phenol , tri(ethylcyclopentyloxymethyl) phenol , tri(methylcyclohexyloxymethyl) phenol , tri(ethylcyclohexyloxymethyl) phenol , tri(propylcyclohexyloxymethyl) phenol , tri(butylcyclohexyloxymethyl) phenol , tri(pentylcyclohexyloxymethyl) phenol , tri(hexylcyclohexyloxymethyl) phenol , bis(dimethylcyclohexyloxymethyl) phenol , bis(diethylcyclohexyloxymethyl) phenol , bis(dibutylcyclohexyloxymethyl) phenol , tri(phenoxymethyl) phenol , tri(methylphenoxymethyl) phenol , tri(ethylphenoxymethyl) phenol , tri(propylphenoxymethyl) phenol , tri(butylphenoxymethyl) phenol , tri(pentylphenoxymethyl) phenol , tri(hexylphenoxymethyl) phenol , tri(heptylphenoxymethyl) phenol , tri(octylphenoxymethyl) phenol , tri(nonylphenoxymethyl) phenol , tri(decylphenoxymethyl) phenol , tri(phenylphenoxymethyl) phenol bis(dimethylphenoxymethyl) phenol , bis(diethylphenoxymethyl) phenol , bis(dipropylphenoxymethyl) phenol , bis(dibutylphenoxymethyl) phenol , bis(dipentylphenoxymethyl) phenol , bis(dihexylphenoxymethyl) phenol , bis(diheptylphenoxymethyl) phenol , bis(diphenylphenoxymethyl) phenol , tri(trimethylphenoxymethyl) phenol , tri(triethylphenoxymethyl) phenol , tri(tripropylphenoxymethyl) phenol , tri(tributylphenoxymethyl) phenol , tri(phenylmethoxymethyl) phenol , tri(phenylethoxymethyl) phenol , tri(phenylpropyloxymethyl) phenol , tri(phenylbutyloxymethyl) phenol , tri(phenylpentyloxymethyl) phenol , tri(phenylhexyloxymethyl) phenol , tri(phenylheptyloxymethyl) phenol , tri(phenyloctyloxymethyl) phenol , tri(phenylnonyloxymethyl) phenol , (phenylmethyl) phenol , ((methylphenyl)methyl) phenol , ((ethylphenyl)methyl) phenol , ((propylphenyl)methyl) phenol , ((butylphenyl)methyl) phenol , ((pentylphenyl)methyl) phenol , ((hexylphenyl)methyl) phenol , ((heptylphenyl)methyl) phenol , ((octylphenyl)methyl) phenol , ((nonylphenyl)methyl) phenol , ((decylphenyl)methyl) phenol , ((biphenyl)methyl) phenol , ((dimethylphenyl)methyl) phenol , ((diethylphenyl)methyl) phenol , ((dipropylphenyl)methyl) phenol , ((dibutylphenyl)methyl) phenol , ((dipentylphenyl)methyl) phenol , ((dihexylphenyl)methyl) phenol , ((diheptylphenyl)methyl) phenol , ((terphenyl)methyl) phenol , ((trimethylphenyl)methyl) phenol , ((triethylphenyl)methyl) phenol , ((tripropylphenyl)methyl) phenol , ((tributylphenyl)methyl) phenol , di(phenylmethyl) phenol , di((methylphenyl)methyl) phenol , di((ethylphenyl)methyl) phenol , di((propylphenyl)methyl) phenol , di((butylphenyl)methyl) phenol , di((pentyphenyl)methyl) phenol , di((hexylphenyl)methyl) phenol , di((heptylphenyl)methyl) phenol , di((octylphenyl)methyl) phenol , di((nonylphenyl)methyl) phenol , di((decylphenyl)methyl) phenol , di((biphenyl)methyl) phenol , di((dimethylphenyl)methyl) phenol , di((diethylphenyl)methyl) phenol , di((dipropylphenyl)methyl) phenol , di((dibutylphenyl)methyl) phenol , di((dipentylphenyl)methyl) phenol , di((dihexylphenyl)methyl) phenol , di((diheptylphenyl)methyl) phenol , di((terphenyl)methyl) phenol , di((trimethylphenyl)methyl) phenol , di((triethylphenyl)methyl) phenol , di((tripropylphenyl)methyl) phenol di((tributylphenyl)methyl) phenol , tri(phenylmethyl) phenol , tri((methylphenyl)methyl) phenol , , tri((ethylphenyl)methyl) phenol , tri((propylphenyl)methyl) phenol , tri((butylphenyl)methyl) phenol , tri((pentylphenyl)methyl) phenol , tri((hexylphenyl)methyl) phenol , tri((heptylphenyl)methyl) phenol , tri((octylphenyl)methyl) phenol , tri((nonylphenyl)methyl) phenol , tri((decylphenyl)methyl) phenol , tri((biphenyl)methyl) phenol tri((dimethylphenyl)methyl) phenol , tri((diethylphenyl)methyl) phenol , tri((dipropylphenyl)methyl) phenol , tri((dibutylphenyl)methyl) phenol , tri((dipentylphenyl)methyl) phenol tri((dihexylphenyl)methyl) phenol , tri((diheptylphenyl)methyl) phenol , tri((terphenyl)methyl) phenol , tri((trimethylphenyl)methyl) phenol , tri((triethylphenyl)methyl) phenol , tri((tripropylphenyl)methyl) phenol , tri((tributylphenyl)methyl) phenol , phenylethylphenol , phenyl-n-propylphenol , phenyl-n-butylphenol , phenyl-n-pentylphenol , phenyl-n-hexylphenol , phenyl-n-heptylphenol , phenyl-n-octylphenol , phenyl-n-nonylphenol , methoxyphenol , ethoxyphenol , propyloxyphenol , butyloxyphenol , pentyloxyphenol , hexyloxyphenol , heptyloxyphenol , octyloxyphenol , nonyloxyphenol , decyloxyphenol , dodecyloxyphenol , octa-

decyloxyphenol, cyclopentyloxyphenol, cyclohexyloxyphenol, cycloheptyloxyphenol, cyclooctyloxyphenol, (methylcyclopentyloxy)phenol, (ethylcyclopentyloxy)phenol, (methylcyclohexyloxy)phenol, (ethylcyclohexyloxy)phenol, (propylcyclohexyloxy)phenol, (butylcyclohexyloxy)phenol, (pentylcyclohexyloxy)phenol, (hexylcyclohexyloxy)phenol, (dimethylcyclohexyloxy)phenol, (diethylcyclohexyloxy)phenol, (dibutylcyclohexyloxy)phenol, phenyloxyphenol, (methylphenyloxy)phenol, (ethylphenyloxy)phenol, (propylphenyloxy)phenol, (butylphenyloxy)phenol, (pentylphenyloxy)phenol, (hexylphenyloxy)phenol, (heptylphenyloxy)phenol, (octylphenyloxy)phenol, (nonylphenyloxy)phenol, (decylphenyloxy)phenol, biphenyloxyphenol, (dimethylphenyloxy)phenol, (diethylphenyloxy)phenol, (dipropylphenyloxy)phenol, (dibutylphenyloxy)phenol, (dipentylphenyloxy)phenol, (dihexylphenyloxy)phenol, (diheptylphenyloxy)phenol, terphenyloxyphenol, (trimethylphenyloxy)phenol, (triethylphenyloxy)phenol, (tripropylphenyloxy)phenol, (tributylphenyloxy)phenol, (phenylmethylphenyloxy)phenol, (phenylethyloxy)phenol, (phenylpropyloxy)phenol, (phenylbutyloxy)phenol, (phenylpentyloxy)phenol, (phenylhexyloxy)phenol, (phenylheptyloxy)phenol, (phenyloctyloxy)phenol, (phenylnonyloxy)phenol, dimethoxyphenol, diethoxyphenol, dipropoxyphenol, dibutoxyphenol, dipentyloxyphenol, dihexyloxyphenol, diheptyloxyphenol, dioctyloxyphenol, dinonyloxyphenol, didecyloxyphenol, didodecyloxyphenol, dioctadecyloxyphenol, dicyclopentyloxyphenol, dicyclohexyloxyphenol, dicycloheptyloxyphenol, dicyclooctyloxyphenol, di(methylcyclopentyloxy)phenol, di(ethylcyclopentyloxy)phenol, di(methylcyclohexyloxy)phenol, di(ethylcyclohexyloxy)phenol, di(propylcyclohexyloxy)phenol, di(butylcyclohexyloxy)phenol, di(pentylcyclohexyloxy)phenol, di(hexylcyclohexyloxy)phenol, bis(dimethylcyclohexyloxy)phenol, bis(diethylcyclohexyloxy)phenol, bis(dibutylcyclohexyloxy)phenol, bis(dipentylcyclohexyloxy)phenol, bis(dihexylcyclohexyloxy)phenol, bis(diheptylcyclohexyloxy)phenol, bis(dioctylcyclohexyloxy)phenol, bis(dinonylcyclohexyloxy)phenol, bis(didecylcyclohexyloxy)phenol, bis(didodecylcyclohexyloxy)phenol, bis(dioctadecylcyclohexyloxy)phenol, bis(dimethylphenyloxy)phenol, bis(diethylphenyloxy)phenol, bis(dipropylphenyloxy)phenol, bis(dibutylphenyloxy)phenol, bis(dipentylphenyloxy)phenol, bis(dihexylphenyloxy)phenol, bis(diheptylphenyloxy)phenol, bis(dioctylphenyloxy)phenol, bis(dinonylphenyloxy)phenol, bis(didecylphenyloxy)phenol, bis(didodecylphenyloxy)phenol, bis(dioctadecylphenyloxy)phenol, bis(trimethylphenyloxy)phenol, bis(triethylphenyloxy)phenol, bis(tripropylphenyloxy)phenol, bis(tributylphenyloxy)phenol, bis(phenylmethylphenyloxy)phenol, bis(phenylethyloxy)phenol, bis(phenylpropyloxy)phenol, bis(phenylbutyloxy)phenol, bis(phenylpentyloxy)phenol, bis(phenylhexyloxy)phenol, bis(phenylheptyloxy)phenol, bis(phenyloctyloxy)phenol, bis(phenylnonyloxy)phenol, trimethoxyphenol, triethoxyphenol, tripropoxyphenol, tributylphenyloxyphenol, tripentyloxyphenol, trihexyloxyphenol, triheptyloxyphenol, trioctyloxyphenol, trinonyloxyphenol, tridecyloxyphenol, tridodecyloxyphenol, trioctadecyloxyphenol, tricyclopentyloxyphenol, tricyclohexyloxyphenol, tricycloheptyloxyphenol, tricyclooctyloxyphenol, tri(methylcyclopentyloxy)phenol, tri(ethylcyclopentyloxy)phenol, tri(methylcyclohexyloxy)phenol, tri(ethylcyclohexyloxy)phenol, tri(propylcyclohexyloxy)phenol, tri(butylcyclohexyloxy)phenol, tri(pentylcyclohexyloxy)phenol, tri(hexylcyclohexyloxy)phenol, tri(dimethylcyclohexyloxy)phenol, tri(diethylcyclohexyloxy)phenol, tri(dibutylcyclohexyloxy)phenol, phenyloxyphenol, tri(methylphenyloxy)phenol, tri(ethylphenyloxy)phenol, tri(propylphenyloxy)phenol, tri(butylphenyloxy)phenol, tri(pentylphenyloxy)phenol, tri(hexylphenyloxy)phenol, tri(heptylphenyloxy)phenol, tri(octylphenyloxy)phenol, tri(nonylphenyloxy)phenol, tri(decylphenyloxy)phenol, tribiphenyloxyphenol, tri(dimethylphenyloxy)phenol, tri(diethylphenyloxy)phenol, tri(dipropylphenyloxy)phenol, tri(dibutylphenyloxy)phenol, tri(dipentylphenyloxy)phenol, tri(dihexylphenyloxy)phenol, tri(diheptylphenyloxy)phenol, triterphenyloxyphenol, tri(trimethylphenyloxy)phenol, tri(triethylphenyloxy)phenol, tri(tripropylphenyloxy)phenol, tri(tributylphenyloxy)phenol, (phenylmethylphenyloxy)phenol, tri(phenylethyloxy)phenol, tri(phenylpropyloxy)phenol, tri(phenylbutyloxy)phenol, tri(phenylpentyloxy)phenol, tri(phenylhexyloxy)phenol, tri(phenylheptyloxy)phenol, tri(phenyloctyloxy)phenol, tri(phenylnonyloxy)phenol, naphthol, phenoxyphenol, and diphenoxyphenol. Particularly preferable examples include aromatic monohydroxy compounds in which the R²⁶ and the R²⁷ are hydrogen atoms, while other substituents are linear and/or cyclic saturated alkyl groups, naphthol, phenoxyphenol and diphenoxyphenol.

[0140] As has been previously described, an aromatic hydroxy compound having a specific structure is used preferably from the viewpoint of reactivity in the reaction between a compound having ureido groups and/or an N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition (namely, an esterification reaction or transesterification reaction).


[0141] Conversely, the inventors of the present invention found that, in the case a group bonded to the atom at the α position of a substituent of at least one ortho position of the aromatic hydroxy compound is a bulky substituent, the formation rate of N-substituted carbamic acid-O-aryl ester decreases considerably. More specifically, this refers to an aromatic hydroxy compound in which a substituent in which the atom at the α position is a tertiary or quaternary carbon atom or tertiary nitrogen atom is bonded to at least one ortho position relative to a hydroxy group of the aromatic hydroxy compound. The demonstration of such an effect by this aromatic hydroxy compound is also not found in the prior art. Hereinafter, an aromatic hydroxy compound for which the formation rate of N-substituted carbamic acid-O-Ar ester is low is frequently referred to as a low activity aromatic hydroxy compound.

[0142] Moreover, as a result of focusing on the fact that the formation rate of N-substituted carbamic acid-O-aryl ester differs depending on the type of aromatic hydroxy compound as described above, the inventors of the present invention

conceived of and completed an N-substituted carbamic acid-O-aryl ester production method that uses an aromatic hydroxy composition containing a plurality of types of aromatic hydroxy compounds.

[0143] The aromatic hydroxy compound explained below is a low activity aromatic hydroxy compound that is used in a N-substituted carbamic acid-O-aryl ester production method which uses an aromatic hydroxy composition containing a plurality of types of aromatic hydroxy compounds, and which uses an aromatic hydroxy composition that contains an active aromatic hydroxy compound and a low activity hydroxy compound. Namely, the production method is an N-substituted carbamic acid-O-ester production method that uses an aromatic hydroxy composition containing an aromatic hydroxy compound having a high formation rate of N-substituted carbamic acid-O-aryl ester as indicated above (the above-mentioned active aromatic hydroxy compound) and an aromatic hydroxy compound having a low formation rate of N-substituted carbamic acid-O-ester (frequently referred to as a low activity aromatic hydroxy compound).

[0144] The low activity aromatic hydroxy compound described above is represented by the following formula (39):



(39)

(wherein

ring A represents an organic group, which contains an aromatic group substituted by b number of hydroxy groups at arbitrary locations that maintain aromatic properties, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and an integral number of from 1 to 6 OH groups represented by formula (39) are substituted on an aromatic ring contained in the ring A (namely, the formula (39) constitutes a portion of the ring A, and an integral number of 1 to 6 structures to which the above-mentioned R³¹ group, OH group and R³² group are adjacent are respectively present on the ring A).

[0145] R³¹ and R³² are groups that substitute the aromatic ring to which the hydroxy group is bonded, and which are bonded to a carbon atom adjacent to the carbon atom to which the hydroxy group is bonded. An integral number of from 1 to 6 hydroxy groups are bonded to ring A, and thus, a maximum integral number of from 1 to 6 of R³¹ and R³² are respectively bonded to ring A. An aromatic hydroxy compound represented by formula (39) is an aromatic hydroxy compound that contains an integral number of carbon atoms within a range of from 6 to 50.

[0146] Examples of substituents that substitute an aromatic group of the aromatic hydroxy compound represented by formula (39) above (groups R³¹ and R³² will be subsequently explained in detail) may include groups selected from a hydrogen atom, a halogen atom, an aliphatic group and an aromatic group that are composed of an acyclic hydrocarbon group or a cyclic hydrocarbon group (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group, a cyclic hydrocarbon group having a side chain, a heterocyclic group, a heterocyclic spiro group, a hetero-crosslinked ring group or a heterocyclic group), a group bonded from one or more types of groups selected from the above-mentioned acyclic hydrocarbon groups and cyclic hydrocarbon groups, and groups in which the above-mentioned groups are bonded through a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon). In addition, a covalent bond with a specific non-metal atom (carbon, oxygen, nitrogen, sulfur or silicon) as described above is in a state in which the above-mentioned groups are bonded by a covalent bond with, for example, groups represented by the above-mentioned formulas (8) to (11) and (13) to (16).

[0147] Among these substituents, examples of substituents that can be preferably used in the present embodiment in consideration of less susceptibility to the occurrence of side reactions include groups selected from the group consisting of acyclic hydrocarbon groups and cyclic hydrocarbon groups (such as a monocyclic hydrocarbon group, a condensed polycyclic hydrocarbon group, a crosslinked cyclic hydrocarbon group, a spirohydrocarbon group, a ring-assembling hydrocarbon group or a cyclic hydrocarbon group having a side chain), and groups bonded to at least one type of group selected from this group (mutually substituted groups).

[0148] In addition, in the case of transferring a composition containing a compound having ureido groups at a high temperature or in the case of reacting a compound having ureido groups and/or an N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition to obtain an N-substituted carbamic acid-O-aryl ester at a high temperature, ring A of the aromatic hydroxy compound is preferably an aromatic hydroxy compound composed of a group having at least one inactive substituent (including hydrogen atoms) in addition to the aromatic group and hydroxy groups bonded to the aromatic group (herein an inactive substituent refers to a group in which the inactive substituent does not contain active hydrogen as previously described, although it may have an aromatic hydroxyl group).

[0149] In providing a more detailed explanation of the substituent, the aromatic hydroxy compound represented by

formula (39) is an aromatic hydroxy compound having at least one substituent selected from the groups of substituents explained in the following (i) to (v) in addition to the aromatic group and hydroxy group bonded to the aromatic group (groups R³¹ and R³² will be subsequently explained in detail):

- 5 (i) a hydrogen atom,
 (ii) a group composed of carbon atoms and hydrogen atoms (which may also form a ring structure by bonding with ring A),
 (iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, ether group composed of aromatic groups or ether group composed of aliphatic groups and aromatic groups, but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group or a carboxyl group),
 10 (iv) a halogen atom, and
 (v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms (but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, a carboxyl group, a NH₂ group, a NH group, a NOH group, a SH group, a SO₃H group or a SOH group).
 15

[0150] R³¹ and R³² respectively and independently represent any of the groups defined in the following (i) to (viii), at least either one is a group defined in the following (vi) to (viii), and R³¹ and R³² may further form a condensed ring structure by bonding with ring A. In the relationship between ring A and the hydroxyl group in the above-mentioned formula (39), for example, although there are frequently cases in which the number of R³¹ and R³² groups bonded to a carbon adjacent to an OH group does not coincide with the number of the OH groups (as explained in the above-mentioned formula (32)), such cases are permitted provided that either R³¹ or R³² is a group defined in the following (vi) to (viii):
 20

- 25 (i) a hydrogen atom,
 (ii) a group composed of carbon atoms and hydrogen atoms (which may also form a ring structure by bonding with ring A), in which the atom at the α , position (atom that forms the R³¹ and R³² that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a primary or secondary carbon atom (namely, representing a carbon atom of a methyl group or a carbon atom that forms a -CH₂-bond), provided that in the case the R³¹ and/or R³¹ form
 30 a saturated and/or unsaturated condensed ring structure with ring A and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom, and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R³¹ and R³² that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom,
 35 (iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, an ether group composed of aromatic groups or an ether group composed of aliphatic groups and aromatic groups, but not having an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group or a methine group on a terminal thereof), in which the atom at the α position (atom that forms the R³¹ and R³² that is bonded to the aromatic ring of ring A) is a carbon atom or oxygen atom, and in the case of a
 40 carbon atom, the carbon atom is a primary or secondary carbon atom (namely, a carbon atom of a methyl group or a carbon atom that forms a -CH₂- bond), provided that in the case the R³¹ or R³² form a saturated and/or unsaturated condensed ring structure with ring A and the condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom, and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R³¹ and R³² that is bonded to the
 45 aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom,
 (iv) a halogen atom,
 (v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms (but excluding an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group, a terminal methine group, a NH₂ group, a NH group, a NOH group, a SH group, a SO₃H group or a SOH group), in
 50 which the atom at the α position (atom that forms the R³¹ and R³² that is bonded to the aromatic ring of ring A) is a carbon atom, oxygen atom or sulfur atom, in the case of a carbon atom, the carbon atom is a primary or secondary carbon atom (namely, a carbon atom of a methyl group or a carbon atom that forms a -CH₂- bond), and in the case of a sulfur atom, the sulfur atom is a divalent sulfur atom (namely, a sulfur atom that forms an -S-bond), provided that in the case the R³¹ or R³² form a saturated and/or unsaturated condensed ring structure with ring A and the
 55 condensed ring has six members or less, the carbon at the α position may be a tertiary or quaternary carbon atom, and in the case the carbon atom at the α position forms a double bond or triple bond with an atom at the β position (adjacent to an atom that forms the R³¹ and R³² that is bonded to the aromatic ring of ring A) as well, the carbon at the α position may be a tertiary or quaternary carbon atom,

(vi) a group composed of carbon atoms and hydrogen atoms (which may also form a ring structure by bonding with ring A), in which the atom at the α position (atom that forms the R^{31} and R^{32} that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a tertiary or quaternary carbon atom (namely, a carbon atom that forms a -CH- bond or carbon atom not bonded by hydrogen), provided that in the case the R^{31} and/or R^{32} form a saturated and/or unsaturated condensed ring structure with ring A, the condensed ring may have seven members or more, and in the case the carbon atom at the α position forms a double bond with an atom at the β position (adjacent to an atom that forms the R^{31} and R^{32} that is bonded to the aromatic ring of ring A), the carbon at the α position may be a quaternary carbon atom, but excluding the carbon at the α position forming a triple bond with the atom at the β position,

(vii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, an ether group composed of aromatic groups or an ether group composed of aliphatic groups and aromatic groups, but not having an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group or a methine group on a terminal thereof), in which the atom at the α position (atom that forms the R^{31} and R^{32} that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a tertiary or quaternary carbon atom (namely, a carbon atom that forms a -CH- bond or carbon atom not bonded by hydrogen), provided that in the case the R^{31} and/or R^{32} form a saturated and/or unsaturated condensed ring structure with ring A, the condensed ring may have seven members or more, and in the case the carbon atom at the α position forms a double bond with an atom at the β position (adjacent to an atom that forms the R^{31} and R^{32} that is bonded to the aromatic ring of ring A), the carbon at the α position may be a quaternary carbon atom, but excluding the carbon at the α position forming a triple bond with the atom at the β position, and


(viii) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms (but excluding an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group, a terminal methine group, a NH_2 group, a NH group, a NOH group, a SH group, a SO_3H group or a SOH group), in which the atom at the α position (atom that forms the R^{31} and R^{32} that is bonded to the aromatic ring of ring A) is a carbon atom or nitrogen atom, in the case of a carbon atom, the carbon atom is a tertiary or quaternary carbon atom (namely, a carbon atom that forms a -CH- bond or carbon atom not bonded by hydrogen), provided that in the case the R^{31} and/or R^{32} form a saturated and/or unsaturated condensed ring structure with ring A, the condensed ring may have seven members or more, and in the case the carbon atom at the α position forms a double bond with an atom at the β position (adjacent to an atom that forms the R^{31} and R^{32} that is bonded to the aromatic ring of ring A), the carbon at the α position may be a quaternary carbon atom, but excluding the carbon at the α position forming a triple bond with the atom at the β position, while in the case of a nitrogen atom, the nitrogen atom may be a tertiary nitrogen atom that bonds with the atom at the β position with a single bond.

[0151] In addition, ring A is preferably a structure that contains at least one structure selected from the group consisting of a benzene ring, a naphthalene ring and an anthracene ring. In consideration of the industrial use, the inactive aromatic hydroxy compound represented by the above-mentioned formula (39) is preferably an aromatic monohydroxy compound in which one or two aromatic hydroxyl groups are bonded to ring A (namely, $b = 1$ or 2), and more preferably an aromatic monohydroxy compound in which one aromatic hydroxyl group is bonded to ring A, since they typically have low viscosity.

[0152] Although an explanation of a method for using an inactive aromatic hydroxy compound of the present embodiment will be provided later, in one aspect of the present embodiment, the aromatic hydroxy compound and isocyanate are separated by distillation, and the separated aromatic hydroxy compound may be recycled in the form of an aromatic hydroxy composition that is reacted with the compound having ureido groups. Separation is carried out using standard boiling point as an indicator, and the method is selected in accordance with the previously described definition.

[0153] In addition, when the above-mentioned active aromatic hydroxy compound and inactive aromatic hydroxyl compound are used as an aromatic hydroxy composition although it is easy to separate and purify the two components if the aromatic hydroxy compound is selected so that a relationship exists in which the standard boiling point of the active aromatic hydroxy compound is $10^\circ C$ or more higher than the standard boiling point of the inactive aromatic hydroxy compound, this is not required. In the case of using a plurality of active aromatic hydroxy compounds and a plurality of inactive aromatic hydroxy compounds, the aromatic hydroxy compounds are selected such that a relationship exists in which the standard boiling point of the active aromatic hydroxy compound having the lowest standard boiling point is $10^\circ C$ or more higher than the standard boiling point of the inactive aromatic hydroxy compound having the highest standard boiling point. In consideration of separation and purification, the number of types of active and low-active aromatic hydroxy compounds use is as low as possible, and for example, only one type each is used preferably.

[0154] Moreover, in consideration of the industrial use, the inactive aromatic hydroxy compound is preferably an easily acquirable aromatic monohydroxy compound. A preferable example of such an aromatic monohydroxy compound is an aromatic monohydroxy compound represented by the following formula (40):



(wherein

10 R^{35} , R^{36} and R^{37} are groups respectively and independently selected from the above-mentioned groups R^7 to R^{14} (excluding aryl groups having a hydroxy group), groups R^{33} and R^{34} are groups respectively and independently selected from the above-mentioned groups R^{31} and R^{32} , and the aromatic hydroxy compound represented by formula (40) is an aromatic monohydroxy compound having an integral number of from 6 to 50 carbon atoms, provided that the total number of carbon atoms of groups R^{33} , R^{34} , R^{35} , R^{36} and R^{37} is an integer of from 0 to 44, and R^{33} and R^{34} are respectively and independently any group defined in the following (i) to (ii):

(i) a group composed of carbon atoms and hydrogen atoms (which may also form a ring structure by bonding with ring A), in which the atom at the α position (atom that forms the R^{33} and R^{34} that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a tertiary or quaternary carbon atom (namely, a carbon atom that forms a -CH- bond or carbon atom not bonded by hydrogen), provided that in the case the R^{33} and/or R^{34} form a saturated and/or unsaturated condensed ring structure with ring A, the condensed ring may have seven members or more, and in the case the carbon atom at the α position forms a double bond with an atom at the β position (adjacent to an atom that forms the R^{33} and R^{34} that is bonded to the aromatic ring of ring A), the carbon at the α position may be a quaternary carbon atom, but excluding the carbon at the α position forming a triple bond with the atom at the β position, and

(ii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms (representing, for example, an ether group composed of aliphatic groups, an ether group composed of aromatic groups or an ether group composed of aliphatic groups and aromatic groups, but not having an alcoholic OH group, a carbonyl group, an ester group, a carboxyl group or a methine group on a terminal thereof), in which the atom at the α position (atom that forms the R^{33} and R^{34} that is bonded to the aromatic ring of ring A) is a carbon atom, and the carbon atom is a tertiary or quaternary carbon atom (namely, a carbon atom that forms a -CH- bond or carbon atom not bonded by hydrogen), provided that in the case the R^{33} and/or R^{34} form a saturated and/or unsaturated condensed ring structure with ring A, the condensed ring may have seven members or more, and in the case the carbon atom at the α position forms a double bond with an atom at the β position (adjacent to an atom that forms the R^{33} and R^{34} that is bonded to the aromatic ring of ring A), the carbon at the α position may be a quaternary carbon atom, but excluding the carbon at the α position forming a triple bond with the atom at the β position.

[0155] Preferable examples of such aromatic monohydroxy compounds represented by formula (40) may include 2-tert-propylphenol, 2-tert-butylphenol, 2-tert-pentylphenol, 2-tert-hexylphenol, 2-tert-heptylphenol, 2-tert-octylphenol, 2-tert-nonylphenol, 2-tert-decylphenol, 2-tert-dodecylphenol, 2-tert-octadecylphenol, 2-sec-propylphenol, 2-sec-butylphenol, 2-sec-pentylphenol, 2-sec-hexylphenol, 2-sec-heptylphenol, 2-sec-octylphenol, 2-sec-nonylphenol, 2-sec-decylphenol, 2-sec-dodecylphenol, 2-sec-octadecylphenol, 2,4-di-tert-propylphenol, 2,4-di-tert-butylphenol, 2,4-di-tert-pentylphenol, 2,4-di-tert-hexylphenol, 2,4-di-tert-heptylphenol, 2,4-di-tert-octylphenol, 2,4-di-tert-nonylphenol, 2,4-di-tert-decylphenol, 2,4-di-tert-dodecylphenol, 2,4-di-tert-octadecylphenol, 2,4-di-sec-propylphenol, 2,4-di-sec-butylphenol, 2,4-di-sec-pentylphenol, 2,4-di-sec-hexylphenol, 2,4-di-sec-heptylphenol, 2,4-di-sec-octylphenol, 2,4-di-sec-nonylphenol, 2,4-di-sec-decylphenol, 2,4-di-sec-dodecylphenol, 2,4-di-sec-octadecylphenol, 2,6-di-tert-propylphenol, 2,6-di-tert-butylphenol, 2,6-di-tert-pentylphenol, 2,6-di-tert-hexylphenol, 2,6-di-tert-heptylphenol, 2,6-di-tert-octylphenol, 2,6-di-tert-nonylphenol, 2,6-di-tert-decylphenol, 2,6-di-tert-dodecylphenol isomers), 2,6-di-tert-octadecylphenol, 2,6-di-sec-propylphenol, 2,6-di-sec-butylphenol, 2,6-di-sec-pentylphenol, 2,6-di-sec-hexylphenol, 2,6-di-sec-heptylphenol, 2,6-di-sec-octylphenol, 2,6-di-sec-nonylphenol, 2,6-di-sec-decylphenol, 2,6-di-sec-dodecylphenol, 2,6-di-sec-octadecylphenol, 2,4,6-tri-tert-propylphenol, 2,4,6-tri-tert-butylphenol, 2,4,6-tri-tert-pentylphenol, 2,4,6-tri-tert-hexylphenol, 2,4,6-tri-tert-heptylphenol, 2,4,6-tri-tert-octylphenol, 2,4,6-tri-tert-nonylphenol, 2,4,6-tri-tert-decylphenol, 2,4,6-tri-tert-dodecylphenol, 2,4,6-tri-tert-octadecylphenol, 2,4,6-tri-sec-propylphenol, 2,4,6-tri-sec-butylphenol, 2,4,6-tri-sec-pentylphenol, 2,4,6-tri-sec-hexylphenol, 2,4,6-tri-sec-heptylphenol, 2,4,6-tri-sec-octylphenol, 2,4,6-tri-sec-nonylphenol, 2,4,6-tri-sec-decylphenol, 2,4,6-tri-sec-dodecylphenol, 2,4,6-tri-sec-octadecylphenol, (2-methoxy-2-methylethyl)phenol, (2-ethoxy-2-methylethyl)phenol, (2-propoxy-2-methylethyl)phenol, (2-butyloxy-2-methylethyl)phenol, (2-pentyloxy-2-methylethyl)phenol, (2-hexyloxy-2-methylethyl)phenol, (2-heptyloxy-2-methylethyl)phenol, (2-octyloxy-2-methylethyl)phenol, (2-nonyloxy-2-methylethyl)phenol, (2-decyloxy-2-methylethyl)phenol, (2-dodecyloxy-2-methyl-

heptylphenoxy)-2-methylethyl)phenol, di(2-(diphenylphenoxy)-2-methylethyl)phenol, di(2-(trimethylphenoxy)-2-methyl-
 ethyl)phenol, di(2-(triethylphenoxy)-2-methylethyl)phenol, di(2-(tripropylphenoxy)-2-methylethyl)phenol, di(2-(tributyl-
 phenoxy)-2-methylethyl)phenol, di(2-(phenylmethoxy)-2-methylethyl)phenol, di(2-(phenylethoxy)-2-methylethyl)phenol,
 di(2-(phenylpropyloxy)-2-methylethyl)phenol, di(2-(phenylbutyloxy)-2-methylethyl)phenol, di(2-(phenylpentyloxy)-2-
 5 methylethyl)phenol, di(2-(phenylhexyloxy)-2-methylethyl)phenol, di(2-(phenylheptyloxy)-2-methylethyl)phenol,
 di(2-(phenyloctyloxy)-2-methylethyl)phenol, di(2-(phenylnonyloxy)-2-methylethyl)phenol, di(2-methoxy-2-methylpropyl)
 phenol, di(2-ethoxy-2-methylpropyl)phenol, di(2-propoxy-2-methylpropyl)phenol, di(2-butyloxy-2-methylpropyl)phenol,
 di(2-pentyloxy-2-methylpropyl)phenol, di(2-hexyloxy-2-methylpropyl)phenol, di(2-heptyloxy-2-methylpropyl)phenol,
 di(2-octyloxy-2-methylpropyl)phenol, di(2-nonyloxy-2-methylpropyl)phenol, di(2-decyloxy-2-methylpropyl)phenol, di(2-
 10 dodecyloxy-2-methylpropyl)phenol, di(2-octadecyloxy-2-methylpropyl)phenol, di(2-cyclopentyloxy-2-methylpropyl)phe-
 nol, di(2-cyclohexyloxy-2-methylpropyl)phenol, di(2-cycloheptyloxy-2-methylpropyl)phenol, di(2-cyclooctyloxy-2-meth-
 ylpropyl)phenol, di(2-(methylcyclopentyloxy)-2-methylpropyl)phenol, di(2-(ethylcyclopentyloxy)-2-methylpropyl)phenol,
 di(2-(methylcyclohexyloxy)-2-methylpropyl)phenol, di(2-(ethylcyclohexyloxy)-2-methylpropyl)phenol, di(2-(propylcy-
 clohexyloxy)-2-methylpropyl)phenol, di(2-(butylcyclohexyloxy)-2-methylpropyl)phenol, di(2-(pentylcyclohexyloxy)-2-
 15 methylpropyl)phenol, di(2-(hexylcyclohexyloxy)-2-methylpropyl)phenol, di(2-(dimethylcyclohexyloxy)-2-methylpro-
 pyl)phenol, di(2-(diethylcyclohexyloxy)-2-methylpropyl)phenol, di(2-(dibutylcyclohexyloxy)-2-methylpropyl)phenol, di(2-
 phenoxy-2-methylpropyl)phenol, di(2-(methylphenoxy)-2-methylpropyl)phenol, di(2-(ethylphenoxy)-2-methylpro-
 pyl)phenol, di(2-(propylphenoxy)-2-methylpropyl)phenol, di(2-(butylphenoxy)-2-methylpropyl)phenol (including iso-
 20 mers), di(2-(pentylphenoxy)-2-methylpropyl)phenol, di(2-(hexylphenoxy)-2-methylpropyl)phenol, di(2-(heptylphenoxy)-
 2-methylpropyl)phenol, di(2-(octylphenoxy)-2-methylpropyl)phenol, di(2-(nonylphenoxy)-2-methylpropyl)phenol,
 di(2-(decylphenoxy)-2-methylpropyl)phenol, di(2-(phenylphenoxy)-2-methylpropyl)phenol, di(2-(dimethylphenoxy)-2-
 methylpropyl)phenol, di(2-(diethylphenoxy)-2-methylpropyl)phenol, di(2-(dipropylphenoxy)-2-methylpropyl)phenol,
 di(2-(dibutylphenoxy)-2-methylpropyl)phenol, di(2-(dipentylphenoxy)-2-methylpropyl)phenol, di(2-(dihexylphenoxy)-2-
 25 methylpropyl)phenol, di(2-(diheptylphenoxy)-2-methylpropyl)phenol, di(2-(diphenylphenoxy)-2-methylpropyl)phenol,
 di(2-(trimethylphenoxy)-2-methylpropyl)phenol, di(2-(triethylphenoxy)-2-methylpropyl)phenol, di(2-(tripropylphenoxy)-
 2-methylpropyl)phenol, di(2-(tributylphenoxy)-2-methylpropyl)phenol, di(2-(phenylmethoxy)-2-methylpropyl)phenol,
 di(2-(phenylethoxy)-2-methylpropyl)phenol, di(2-(phenylpropyloxy)-2-methylpropyl)phenol, di(2-(phenylbutyloxy)-2-
 methylpropyl)phenol, di(2-(phenylpentyloxy)-2-methylpropyl)phenol, di(2-(phenylhexyloxy)-2-methylpropyl)phenol,
 di(2-(phenylheptyloxy)-2-methylpropyl)phenol, di(2-(phenyloctyloxy)-2-methylpropyl)phenol, di(2-(phenylnonyloxy)-2-
 30 methylpropyl)phenol, tri(2-methoxy-2-methylethyl)phenol, tri(2-ethoxy-2-methylethyl)phenol, tri(2-propoxy-2-methyle-
 thyl)phenol, tri(2-butyloxy-2-methylethyl)phenol, tri(2-pentyloxy-2-methylethyl)phenol, tri(2-hexyloxy-2-methylethyl)
 phenol, tri(2-heptyloxy-2-methylethyl)phenol, tri(2-octyloxy-2-methylethyl)phenol, tri(2-nonyloxy-2-methylethyl)phenol,
 tri(2-decyloxy-2-methylethyl)phenol, tri(2-dodecyloxy-2-methylethyl)phenol, tri(2-octadecyloxy-2-methylethyl)phenol,
 tri(2-cyclopentyloxy-2-methylethyl)phenol, tri(2-cyclohexyloxy-2-methylethyl)phenol, tri(2-cycloheptyloxy-2-methyle-
 35 thyl)phenol, tri(2-cyclooctyloxy-2-methylethyl)phenol, tri(2-(methylcyclopentyloxy)-2-methylethyl)phenol, tri(2-(ethyl-
 cyclopentyloxy)-2-methylethyl)phenol, tri(2-(methylcyclohexyloxy)-2-methylethyl)phenol, tri(2-(ethylcyclohexyloxy)-2-
 methylethyl)phenol, tri(2-(propylcyclohexyloxy)-2-methylethyl)phenol, tri(2-(butylcyclohexyloxy)-2-methylethyl)phe-
 nol, tri(2-(pentylcyclohexyloxy)-2-methylethyl)phenol, tri(2-(hexylcyclohexyloxy)-2-methylethyl)phenol, tri(2-(tri-
 methylcyclohexyloxy)-2-methylethyl)phenol, tri(2-(triethylcyclohexyloxy)-2-methylethyl)phenol, tri(2-(tributylcyclohexy-
 40 loxy)-2-methylethyl)phenol, tri(2-phenoxy-2-methylethyl)phenol, tri(2-(methylphenoxy)-2-methylethyl)phenol,
 tri(2-(ethylphenoxy)-2-methylethyl)phenol, tri(2-(propylphenoxy)-2-methylethyl)phenol, tri(2-(butylphenoxy)-2-methyle-
 thyl)phenol, tri(2-(pentylphenoxy)-2-methylethyl)phenol, tri(2-(hexylphenoxy)-2-methylethyl)phenol, tri(2-(heptylpheno-
 xy)-2-methylethyl)phenol, tri(2-(octylphenoxy)-2-methylethyl)phenol, tri(2-(nonylphenoxy)-2-methylethyl)phenol,
 tri(2-(decylphenoxy)-2-methylethyl)phenol, tri(2-(phenylphenoxy)-2-methylethyl)phenol, tri(2-(trimethylphenoxy)-2-
 45 methylethyl)phenol, tri(2-(triethylphenoxy)-2-methylethyl)phenol, tri(2-(tripropylphenoxy)-2-methylethyl)phenol,
 tri(2-(tributylphenoxy)-2-methylethyl)phenol, tri(2-(tripentylphenoxy)-2-methylethyl)phenol, tri(2-(triheptylphenoxy)-2-
 methylethyl)phenol, tri(2-(triheptylphenoxy)-2-methylethyl)phenol, tri(2-(triphenylphenoxy)-2-methylethyl)phenol,
 tri(2-(trimethylphenoxy)-2-methylethyl)phenol, tri(2-(triethylphenoxy)-2-methylethyl)phenol, tri(2-(tripropylphenoxy)-2-
 methylethyl)phenol, tri(2-(tributylphenoxy)-2-methylethyl)phenol, tri(2-(phenylmethoxy)-2-methylethyl)phenol,
 50 tri(2-(phenylethoxy)-2-methylethyl)phenol, tri(2-(phenylpropyloxy)-2-methylethyl)phenol, tri(2-(phenylbutyloxy)-2-meth-
 ylethyl)phenol, tri(2-(phenylpentyloxy)-2-methylethyl)phenol, tri(2-(phenylhexyloxy)-2-methylethyl)phenol, tri(2-(phe-
 nylheptyloxy)-2-methylethyl)phenol, tri(2-(phenyloctyloxy)-2-methylethyl)phenol, tri(2-(phenylnonyloxy)-2-methylethyl)
 phenol, tri(2-methoxy-2-methylpropyl)phenol, tri(2-ethoxy-2-methylpropyl)phenol, tri(2-propoxy-2-methylpropyl)phe-
 nol, tri(2-butyloxy-2-methylpropyl)phenol, tri(2-pentyloxy-2-methylpropyl)phenol, tri(2-hexyloxy-2-methylpropyl)phenol,
 55 tri(2-heptyloxy-2-methylpropyl)phenol, tri(2-octyloxy-2-methylpropyl)phenol, tri(2-nonyloxy-2-methylpropyl)phenol,
 tri(2-decyloxy-2-methylpropyl)phenol, tri(2-dodecyloxy-2-methylpropyl)phenol, tri(2-octadecyloxy-2-methylpropyl)phe-
 nol, tri(2-cyclopentyloxy-2-methylpropyl)phenol, tri(2-cyclohexyloxy-2-methylpropyl)phenol, tri(2-cycloheptyloxy-2-
 methylpropyl)phenol, tri(2-cyclooctyloxy-2-methylpropyl)phenol, tri(2-(methylcyclopentyloxy)-2-methylpropyl)phenol,

tri(2-(ethylcyclopentyloxy)-2-methylpropyl) phenol, tri(2-(methylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(ethylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(propylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(butylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(pentylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(hexylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(trimethylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(triethylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-(tributylcyclohexyloxy)-2-methylpropyl) phenol, tri(2-phenoxy-2-methylpropyl) phenol, tri(2-(methylphenoxy)-2-methylpropyl) phenol, tri(2-(ethylphenoxy)-2-methylpropyl) phenol, tri(2-(propylphenoxy)-2-methylpropyl) phenol, tri(2-(butylphenoxy)-2-methylpropyl) phenol, tri(2-(pentylphenoxy)-2-methylpropyl) phenol, tri(2-(hexylphenoxy)-2-methylpropyl) phenol, tri(2-(heptylphenoxy)-2-methylpropyl) phenol, tri(2-(octylphenoxy)-2-methylpropyl) phenol, tri(2-(nonylphenoxy)-2-methylpropyl) phenol, tri(2-(decylphenoxy)-2-methylpropyl) phenol, tri(2-(phenylphenoxy)-2-methylpropyl) phenol, tri(2-(trimethylphenoxy)-2-methylpropyl) phenol, tri(2-(triethylphenoxy)-2-methylpropyl) phenol, tri(2-(tripropylphenoxy)-2-methylpropyl) phenol, tri(2-(tributylphenoxy)-2-methylpropyl) phenol, tri(2-(tripentylphenoxy)-2-methylpropyl) phenol, tri(2-(trihexylphenoxy)-2-methylpropyl) phenol, tri(2-(triheptylphenoxy)-2-methylpropyl) phenol, tri(2-(triphenylphenoxy)-2-methylpropyl) phenol, tri(2-(trimethylphenoxy)-2-methylpropyl) phenol, tri(2-(triethylphenoxy)-2-methylpropyl) phenol, tri(2-(tripropylphenoxy)-2-methylpropyl) phenol, tri(2-(tributylphenoxy)-2-methylpropyl) phenol, tri(2-(phenylmethoxy)-2-methylpropyl) phenol, tri(2-(phenylethoxy)-2-methylpropyl) phenol, tri(2-(phenylpropyloxy)-2-methylpropyl) phenol, tri(2-(phenylbutyloxy)-2-methylpropyl) phenol, tri(2-(phenylpentyloxy)-2-methylpropyl) phenol, tri(2-(phenylhexyloxy)-2-methylpropyl) phenol, tri(2-(phenylheptyloxy)-2-methylpropyl) phenol, tri(2-(phenyloctyloxy)-2-methylpropyl) phenol, tri(2-(phenylnonyloxy)-2-methylpropyl) phenol, (dimethylamino) phenol, (diethylamino) phenol, (dipropylamino) phenol, (dibutylamino) phenol, (dipentylamino) phenol, (dihexylamino) phenol, (diheptylamino) phenol, (dioctylamino) phenol, (dinonylamino) phenol, (didecylamino) phenol, (didodecylamino) phenol, (dioctadecylamino) phenol, (2-phenyl-isopropyl) phenol, (2-(methylphenyl)-isopropyl) phenol, (2-(ethylphenyl)-isopropyl) phenol, (2-(propylphenyl)-isopropyl) phenol, (2-(butylphenyl)-isopropyl) phenol, (2-(pentylphenyl)-isopropyl) phenol, (2-(hexylphenyl)-isopropyl) phenol, (2-(heptylphenyl)-isopropyl) phenol, (2-(octylphenyl)-isopropyl) phenol, (2-(nonylphenyl)-isopropyl) phenol, (2-(decylphenyl)-isopropyl) phenol, (2-(biphenyl)-isopropyl) phenol, (2-(dimethylphenyl)-isopropyl) phenol, (2-(diethylphenyl)-isopropyl) phenol, (2-(dipropylphenyl)-isopropyl) phenol, (2-(dibutylphenyl)-isopropyl) phenol, (2-(dipentylphenyl)-isopropyl) phenol, (2-(dihexylphenyl)-isopropyl) phenol, (2-(diheptylphenyl)-isopropyl) phenol, (2-(terphenyl)-isopropyl) phenol, (2-(trimethylphenyl)-isopropyl) phenol, (2-(triethylphenyl)-isopropyl) phenol, (2-(tripropylphenyl)-isopropyl) phenol, (2-(tributylphenyl)-isopropyl) phenol, di(2-phenyl-isopropyl) phenol, di(2-(methylphenyl)-isopropyl) phenol, di(2-(ethylphenyl)-isopropyl) phenol, di(2-(propylphenyl)-isopropyl) phenol, di(2-(butylphenyl)-isopropyl) phenol, di(2-(pentylphenyl)-isopropyl) phenol, di(2-(hexylphenyl)-isopropyl) phenol, di(2-(heptylphenyl)-isopropyl) phenol, di(2-(octylphenyl)-isopropyl) phenol, di(2-(nonylphenyl)-isopropyl) phenol, di(2-(decylphenyl)-isopropyl) phenol, di(2-(biphenyl)-isopropyl) phenol, di(2-(dimethylphenyl)-isopropyl) phenol, di(2-(diethylphenyl)-isopropyl) phenol, di(2-(dipropylphenyl)-isopropyl) phenol, di(2-(dibutylphenyl)-isopropyl) phenol, di(2-(dipentylphenyl)-isopropyl) phenol, di(2-(dihexylphenyl)-isopropyl) phenol, di(2-(diheptylphenyl)-isopropyl) phenol, di(2-(terphenyl)-isopropyl) phenol, di(2-(trimethylphenyl)-isopropyl) phenol, di(2-(triethylphenyl)-isopropyl) phenol, di(2-(tripropylphenyl)-isopropyl) phenol, di(2-(tributylphenyl)-isopropyl) phenol, tri(2-phenyl-isopropyl) phenol (including isomers), tri(2-(methylphenyl)-isopropyl) phenol, tri(2-(ethylphenyl)-isopropyl) phenol, tri(2-(propylphenyl)-isopropyl) phenol, tri(2-(butylphenyl)-isopropyl) phenol, tri(2-(pentylphenyl)-isopropyl) phenol, tri(2-(hexylphenyl)-isopropyl) phenol, tri(2-(heptylphenyl)-isopropyl) phenol, tri(2-(octylphenyl)-isopropyl) phenol, tri(2-(nonylphenyl)-isopropyl) phenol, tri(2-(decylphenyl)-isopropyl) phenol, tri(2-(biphenyl)-isopropyl) phenol, tri(2-(dimethylphenyl)-isopropyl) phenol, tri(2-(diethylphenyl)-isopropyl) phenol, tri(2-(dipropylphenyl)-isopropyl) phenol, tri(2-(dibutylphenyl)-isopropyl) phenol, bi(2-(dipentylphenyl)-isopropyl) phenol, tri(2-(dihexylphenyl)-isopropyl) phenol, tri(2-(diheptylphenyl)-isopropyl) phenol, tri(2-(terphenyl)-isopropyl) phenol, tri(2-(trimethylphenyl)-isopropyl) phenol, tri(2-(triethylphenyl)-isopropyl) phenol, t(i(2-(tripropylphenyl)-isopropyl) phenol, tri(2-(tributylphenyl)-isopropyl) phenol, (2-phenyl-sec-butyl) phenol, (2-(methylphenyl)-sec-butyl) phenol, (2-(ethylphenyl)-sec-butyl) phenol, (2-(propylphenyl)-sec-butyl) phenol, (2-(butylphenyl)-sec-butyl) phenol, (2-(pentylphenyl)-sec-butyl) phenol, (2-(hexylphenyl)-sec-butyl) phenol, (2-(heptylphenyl)-sec-butyl) phenol, (2-(octylphenyl)-sec-butyl) phenol, (2-(nonylphenyl)-sec-butyl) phenol, (2-(decylphenyl)-sec-butyl) phenol, (2-(biphenyl)-sec-butyl) phenol, (2-(dimethylphenyl)-sec-butyl) phenol, (2-(diethylphenyl)-sec-butyl) phenol, (2-(dipropylphenyl)-sec-butyl) phenol, (2-(dibutylphenyl)-sec-butyl) phenol, (2-(dipentylphenyl)-sec-butyl) phenol, (2-(dihexylphenyl)-sec-butyl) phenol, (2-(diheptylphenyl)-sec-butyl) phenol, (2-(terphenyl)-sec-butyl) phenol, (2-(trimethylphenyl)-sec-butyl) phenol, (2-(triethylphenyl)-sec-butyl) phenol, (2-(tripropylphenyl)-sec-butyl) phenol, (2-(tributylphenyl)-sec-butyl) phenol, di(2-phenyl-sec-butyl) phenol, di(2-(methylphenyl)-sec-butyl) phenol, di(2-(ethylphenyl)-sec-butyl) phenol, di(2-(propylphenyl)-sec-butyl) phenol, di(2-(butylphenyl)-sec-butyl) phenol, di(2-(pentylphenyl)-sec-butyl) phenol, di(2-(hexylphenyl)-sec-butyl) phenol, di(2-(heptylphenyl)-sec-butyl) phenol, di(2-(octylphenyl)-sec-butyl) phenol, di(2-(nonylphenyl)-sec-butyl) phenol, di(2-(decylphenyl)-sec-butyl) phenol, di(2-(biphenyl)-sec-butyl) phenol, di(2-(dimethylphenyl)-sec-butyl) phenol, di(2-(diethylphenyl)-sec-butyl) phenol, di(2-(dipropylphenyl)-sec-butyl) phenol, di(2-(dibutylphenyl)-isopropyl) phenol, di(2-(dipentylphenyl)-sec-butyl) phenol, di(2-(dihexylphenyl)-sec-butyl) phenol, di(2-(diheptylphenyl)-sec-butyl) phenol, di(2-(terphenyl)-sec-butyl) phenol, di(2-(trimethylphenyl)-sec-butyl) phenol, di(2-(triethylphenyl)-sec-butyl) phenol,

di(2-(tripropylphenyl)-sec-butyl) phenol, di(2-(tributylphenyl)-sec-butyl) phenol, tri(2-phenyl-sec-butyl) phenol, tri(2-(methylphenyl)-sec-butyl) phenol, tri(2-(ethylphenyl)-sec-butyl) phenol, tri(2-(propylphenyl)-sec-butyl) phenol, tri(2-(butylphenyl)-sec-butyl) phenol, tri(2-(pentylphenyl)-sec-butyl) phenol, tri(2-(hexylphenyl)-sec-butyl) phenol, tri(2-(heptylphenyl)-sec-butyl) phenol, tri(2-(octylphenyl)-sec-butyl) phenol, tri(2-(nonylphenyl)-sec-butyl) phenol, tri(2-(decylphenyl)-sec-butyl) phenol, tri(2-(biphenyl)-isopropyl) phenol, tri(2-(dimethylphenyl)-isopropyl) phenol, tri(2-(diethylphenyl)-sec-butyl) phenol, tri(2-(dipropylphenyl)-sec-butyl) phenol, tri(2-(dibutylphenyl)-sec-butyl) phenol, tri(2-(dipentylphenyl)-sec-butyl) phenol, tri(2-(dihexylphenyl)-sec-butyl) phenol, tri(2-(diheptylphenyl)-sec-butyl) phenol, tri(2-(terphenyl)-sec-butyl) phenol, tri(2-(trimethylphenyl)-sec-butyl) phenol, tri(2-(triethylphenyl)-sec-butyl) phenol, tri(2-(tripropylphenyl)-sec-butyl) phenol, and tri(2-(tributylphenyl)-sec-butyl) phenol

[0156] More preferable examples thereof may include aromatic monohydroxy compounds in which groups R³³, R³⁴, R³⁵, R³⁶ and R³⁷ are linear and/or cyclic saturated alkyl groups, and in which at least one of R³³ and R³⁴ has a tertiary or quaternary carbon atom for the carbon atom at the α position.

<Carbonic Acid Derivative>

[0157] The carbonic acid derivative in the present embodiment refers to a compound represented by the following formula (19). In the case of using the composition for transfer and storage of the compound having the ureido groups in an N-substituted carbamic acid-O-R² ester production step or N-substituted carbamic acid-O-aryl ester production step, namely in the above-mentioned step (R), step (P) or step (B), or in the case of using a component recycled from these production steps when producing a compound having ureido groups, the carbonic acid derivative is a component that may be contained in the composition for transfer and storage of the compound having the ureido groups. In addition, the carbonic acid derivative is a component that also serves as a raw material of a compound having ureido groups.




(wherein

X and Y represent organic groups or amino groups (-NH₂) having 1 to 50 carbon atoms, provided that X and Y are not simultaneously amino groups, and the value of the number of carbon atoms is an integral value).

[0158] Examples of compounds represented by the above-mentioned formula (19) that are used in the present embodiment may include non-N-substituted carbamic acid-O-aryl esters, non-N-substituted carbamic acid-O-R² esters and carbonic acid esters. Although the expressions "non-N-substituted carbamic acids", "non-N-substituted carbamic acid-O-aryl esters" and "non-N-substituted carbamic acid-O-R² esters" are used in the explanation of the present embodiment and as general formula names of compounds, here the term "non-N-substituted carbamic acid" is used in the sense of the NH₂ group of the carbamoyl group (NH₂-CO-) not being substituted by a substituent. Namely, the NH₂ group of the carbamoyl group (NH₂-CO-) of a non-N-substituted carbamic acid is an NH₂ group.



[0159] A non-N-substituted carbamic acid-O-R² ester represented by the following formula (21) is preferably used for the non-N-substituted carbamic acid-O-R² ester:



(wherein

the R² group is the same as the R² group of an alcohol represented by formula (4) and represents a group composed of an aliphatic group to which is bonded an aliphatic group or aromatic group containing an integral number of carbon atoms within a range of from 1 to 14, and the -O-R² group of the non-N-substituted carbamic acid-O-R² ester represented by formula (21) is an R²O group of R²OH of an alcohol represented by formula (4)).

[0160] The non-N-substituted carbamic acid-O-R² ester may be formed as a by-product during production of N-substituted carbamic acid-O-aryl ester in a process comprising the step (A) and/or the step (R) that use an alcohol (namely, a process in which alcohol is used), or may be a non-N-substituted carbamic acid-O-R² ester produced by the known method. The known method is preferably a method for obtaining non-N-substituted carbamic acid-O-R² ester from urea and alcohol as shown in the following reaction formula (23) by reacting isocyanic acid (HNCO) and alcohol as shown in the following reaction formula (22), and a non-N-substituted carbamic acid-O-R² ester represented by formula (21) above can be obtained by using an alcohol represented by formula (4) for the alcohol used at that time.




5

[0161] R² groups listed as examples in the explanation of an alcohol represented by formula (4) can be preferably used for the R² group.

[0162] Examples of such non-N-substituted carbamic acid-O-R² esters represented by formula (21) may include methyl carbamate, ethyl carbamate, propyl carbamate, butyl carbamate, pentyl carbamate, hexyl carbamate, heptyl carbamate, octyl carbamate, nonyl carbamate, decyl carbamate, undecyl carbamate, dodecyl carbamate, tridecyl carbamate, tetradecyl carbamate, pentadecyl carbamate, hexadecyl carbamate, heptadecyl carbamate, octadecyl carbamate, nonadecyl carbamate, benzyl carbamate, (methylbenzyl) carbamate, (dimethylbenzyl) carbamate, (phenylethyl) carbamate, (phenylpropyl) carbamate, (phenylbutyl) carbamate, (phenylpentyl) carbamate, (phenylhexyl) carbamate, (phenylheptyl) carbamate, (phenyloctyl) carbamate and (phenylnonyl) carbamate. More preferable examples include non-N-substituted carbamic acid alkyl esters and non-N-substituted carbamic acid aralkyl esters.

[0163] Compounds having ureido groups can be obtained from the above-mentioned non-N-substituted carbamic acid-O-R² esters by reacting with organic primary amine using the known method. The reaction formula is shown in the following formula (24). In formula (24), although a monoamine structure is shown for the structure of the organic primary amine, the structure may also be that of an organic primary polyamine.


25



[0164] In the present embodiment, although a compound having ureido groups is preferably obtained by carrying out the step (A) in which an organic primary amine and urea are reacted, the reaction of reaction formula (24) above may also be carried out simultaneously thereto. In addition, this method is preferable since it enables reaction side-products to be used effectively.

[0165] A non-N-substituted carbamic acid-O-aryl ester represented by the following formula (25) is preferably used for the non-N-substituted carbamic acid-O-aryl ester:

35




40

(wherein

Ar represents a group derived from an aromatic hydroxy compound that composes an aromatic hydroxy composition, and the Ar-O- group represents a residue in which a hydrogen atom of a hydroxyl group bonded directly to an aromatic hydrocarbon ring has been removed from the aromatic hydroxy compound).

[0166] The compound represented by formula (25) may be a non-N-substituted carbamic acid-O-aryl ester either formed as a by-product during production of N-substituted carbamic acid-O-aryl ester by a process comprising any of the step (A), step (P) or step (B) using an aromatic hydroxy composition, or produced using the known method. The known method is preferably a method in non-N-substituted carbamic acid-O-aryl ester is obtained from urea and aromatic hydroxy compound as shown in the following reaction formula (27) in a reaction between isocyanic acid (HNCO) and aromatic hydroxy compound as shown in the following reaction formula (26), and by using an aromatic hydroxy compound represented by formula (2) for the aromatic hydroxy compound used at that time, a non-N-substituted carbamic acid-O-aryl ester represented by formula (25) above can be obtained:


55



problems with such compound being contained. Furthermore, although there are cases in which the term "non-N-substituted carbamic acid-O-(R² or aryl) ester" is used in the explanation of the present specification, this refers to "an N-substituted carbamic acid-O-R² ester or N-substituted carbamic acid-O-aryl ester".

5 <N-Substituted Carbamic Acid-O-Aryl Ester>

[0175] The N-substituted carbamic acid-O-aryl ester produced with the method of the present embodiment is a compound represented by the following formula (43). Although subsequently explained in detail, the present embodiment refers to a method for esterifying a compound having ureido groups and an aromatic hydroxy composition, or a method for obtaining an N-substituted carbamic acid-O-R² ester by esterifying a compound having ureido groups and an alcohol followed by transesterifying the N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition to obtain N-substituted carbamic acid-O-aryl ester (and the N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which an oxygen atom of the carbamic acid group (-NHCOO-) is bonded to an aromatic ring). In providing a more detailed explanation, the O-aryl group in the carbamic acid-O-aryl ester group of the N-substituted carbamic acid-O-aryl ester is a residue in which a hydrogen atom has been removed from a single hydroxy group (OH group) bonded to an aromatic ring carbon atom of an aromatic hydroxy compound. Namely, the former method described above is a method for esterifying a ureido group (-NHCONH₂) and an aromatic hydroxy compound to obtain a carbamic acid-O-aryl group (-NHCOOAr), while the latter method described above is a method for esterifying a ureido group (-NHCONH₂) and an alcohol to obtain a carbamic acid-O-R² group (-NHCOOR²) followed by transesterifying with an aromatic hydroxy compound to obtain a carbamic acid-O-aryl group (-NHCOOAr):



(4 3)


(wherein

30 R¹ represents a group derived from an organic primary amine or compound having ureido groups as previously defined,
 Ar represents a group derived from an aromatic hydroxy compound represented by formula (2) that composes an aromatic hydroxy composition, and the Ar-O- group represents a residue in which a single hydrogen atom of a hydroxyl group bonded directly to an aromatic hydrocarbon ring has been removed from the aromatic hydroxy compound, and
 35 q represents an integer of from 1 to a or an integer of from 1 to c, and a and c are as previously defined).


[0176] The specific structure of the N-substituted carbamic acid-O-aryl ester represented by formula (43) above is determined by the organic primary amine and/or compound having ureido groups and aromatic hydroxy composition used. For example, in the case of using a compound having ureido groups represented by formula (1) and/or an organic primary amine represented by formula (3) and using an aromatic hydroxy compound represented by formula (2) for the aromatic hydroxy composition, an N-substituted carbamic acid-O-aryl ester represented by the following formula (44) is obtained, in the case of using an organic primary amine represented by formula (5) and an aromatic hydroxy compound represented by formula (2) for the aromatic hydroxy composition (and in the case b = 1), an N-substituted carbamic acid-O-aryl ester represented by the following formula (45) is obtained, in the case of using a compound having ureido groups represented by formula (1) and/or an organic primary amine represented by formula (3) and using an aromatic hydroxy compound represented by formula (7) for the aromatic hydroxy composition, an N-substituted carbamic acid-O-aryl ester represented by the following formula (46) is obtained, and in the case of using an organic primary amine represented by formula (5) and an aromatic hydroxy compound represented by formula (2) for the aromatic hydroxy composition (and in the case b = 1) and producing by a method that includes the step (C), an N-substituted poly(carbamic acid-O-aryl ester) represented by the following formula (47) is obtained (the above-mentioned N-substituted poly(carbamic acid-O-aryl ester) refers to an N-substituted carbamic acid-O-alkyl ester having a plurality of carbamic acid-O-aryl ester groups in a molecule thereof). In this manner, a diverse range of N-substituted carbamic acid-O-aryl esters can be obtained with the production method of the present embodiment, and can be typically represented by the above-mentioned formula (43). (Although the term "aryl", according to nomenclature rules defined by IUPAC, refers to a mono-valent aromatic ring, and the term "aryl" is used in the present embodiment since a suitable term that generically refers to compounds in the present embodiment was unable to be found, the group referred to by the N-substituted carbamic acid-O-aryl ester of the present embodiment contains the N-substituted carbamic acid-O-aryl esters indicated above.

Alternatively, an N-substituted carbamic acid-O-aryl ester in the present embodiment may also be referred to as an N-substituted carbamic acid-O-Ar ester, or in other words, Ar has the same meaning as previously described.):


5



10



15



20

(wherein

- 25 R¹ represents a group derived from an organic primary amine as previously defined,
 ring A represents a group derived from an aromatic hydroxy compound that composes an aromatic hydroxy composition as previously defined, which is a residue in which a single hydrogen atom of a hydroxyl group directly bonded to an aromatic hydrocarbon ring has been removed from the aromatic hydroxy compound,
 R³ to R¹⁴ represent groups as previously defined,
 30 b, d, e, f, g, h, i, j, k, m and q are integers as previously defined, and
 q represents an integer of from 1 to a or an integer of from 1 to c, and a and c are as previously defined).

35 **[0177]** Although a polymer having a complex structure may be obtained as a result of a plurality of hydroxy groups on the aromatic group separately reacting with a compound having ureido groups in the case of using a polyvalent aromatic hydroxy compound, since an excess of aromatic hydroxy compound is used in the present embodiment, generally an N-substituted carbamic acid-O-aryl ester represented by formula (43) above is obtained.


40 **[0178]** Although all possible examples of specific compounds cannot be listed since the production method of the present embodiment can be applied to a diverse range of compounds having ureido groups, organic primary amines, alcohols and aromatic hydroxy compounds as previously described, examples of such specific compounds may include
 N,N'-hexanediy-di(carbamic acid phenyl ester), N,N'-hexanediy-di(carbamic acid (methylphenyl) ester), N,N'-hexanediy-di(carbamic acid (ethylphenyl) ester), N,N'-hexanediy-di(carbamic acid (propylphenyl) ester), N,N'-hexanediy-di(carbamic acid (butylphenyl) ester), N,N'-hexanediy-di(carbamic acid (pentylphenyl) ester), methylene-di(cyclohexylcarbamic acid phenyl ester), methylene-di(cyclohexylcarbamic acid (methylphenyl) ester), methylene-di(cyclohexylcarbamic acid (ethylphenyl) ester), methylene-di(cyclohexylcarbamic acid (propylphenyl) ester), methylene-di(cyclohexylcarbamic acid (butylphenyl) ester), methylene-di(cyclohexylcarbamic acid (pentylphenyl) ester), methylene-di(cyclohexylcarbamic acid (hexylphenyl) ester), methylene-di(cyclohexylcarbamic acid (heptylphenyl) ester), methylene-di(cyclohexylcarbamic acid (octylphenyl) ester), 3-(phenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid phenyl ester, 3-(methylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (methylphenyl) ester, 3-(ethylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (ethylphenyl) ester, 3-(propylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (propylphenyl) ester, 3-(butylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (butylphenyl) ester, 3-(pentylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (pentylphenyl) ester, 3-(hexylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (hexylphenyl) ester, 3-(heptylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (heptylphenyl) ester, 3-(octylphenoxy-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (octylphenyl) ester, toluene-di(carbamic acid phenyl ester), toluene-di(carbamic acid (methylphenyl) ester), toluene-di(carbamic acid (ethylphenyl) ester), toluene-di(carbamic acid (propylphenyl) ester), toluene-di(carbamic acid (butylphenyl) ester), toluene-di(carbamic acid (pentylphenyl) ester), toluene-di(carbamic acid (hexylphenyl) ester), toluene-di(carbamic acid (heptylphenyl) ester), toluene-di(carbamic acid (octylphenyl) ester), N,N'-(methanediy-di-phenyl)-di(carbamic acid phe-

55

nyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (methylphenyl) ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (ethylphenyl) ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (propylphenyl) ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (butylphenyl) ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (pentylphenyl) ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (hexylphenyl) ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid (heptylphenyl) ester) and N,N'-(methanediyl-diphenyl)-di(carbamic acid (octylphenyl) ester) (including isomers). Preferable N-substituted carbamic acid-O-aryl esters contain N-substituted carbamic acid-O-aryl esters obtained by using preferable compounds previously explained for the above-mentioned organic primary amines, aromatic hydroxy compounds and compounds having ureido groups, examples of which may include N-substituted carbamic acid-O-aryl esters obtained by reacting an active aromatic monohydroxy compound with an N-substituted aromatic organic monourea, N-substituted aromatic organic polyurea or N-substituted aliphatic organic polyurea, and N-substituted carbamic acid-O-aryl esters obtained by condensing an N-substituted carbamic acid-O-aryl ester obtained from an active aromatic monohydroxy compound and an N-substituted aromatic organic monourea with a condensing agent. In addition, N-substituted carbamic acid-O-aryl esters are also preferable in which all ureido groups or primary amino groups contained in a compound having ureido groups or organic primary amine are substituted with carbamic acid-O-aryl ester groups (namely, a = q or c = q).

<N-Substituted Carbamic Acid-O-R² Ester>

[0179] An N-substituted carbamic acid O-R² ester produced with the production method of the present embodiment is a compound represented by the following formula (49). Although subsequently explained in detail, the present invention as referred to here indicates a compound obtained when producing an N-substituted carbamic acid-O-aryl ester by a process that includes the above-mentioned step (R). This is a compound in which a compound having ureido groups is esterified with an alcohol represented by formula (4) to convert the ureido groups (-NHCONH₂) to carbamic acid-O-R² ester groups (-NHCOOR²). Namely, this is an N-substituted carbamic acid-O-R² ester, which is obtained by reacting at least one type of compound having ureido groups with an alcohol represented by formula (4) in a liquid phase followed by extracting the ammonia formed as a by-product to a gaseous phase, and the N-substituted carbamic acid-O-R² ester refers to an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to the R² group derived from the alcohol. In providing a more detailed explanation, the OR² group in the carbamic acid-O-R² ester group (-NHCOOR²) of the N-substituted carbamic acid-O-R² ester is a residue in which a hydrogen atom has been removed from a single hydroxy group (OH group) bonded to a carbon atom of the alcohol:



(49)

(wherein

R¹ represents a group derived from an organic primary amine as previously defined,
 R² represents a group derived from an alcohol as previously defined,
 r is an integer of from 1 to a or from 1 to c, and a and c are as previously defined).


[0180] Although all possible examples of specific compounds cannot be listed since the production method of the present embodiment can be applied to a diverse range of compounds having ureido groups, organic primary amines and alcohols as previously described, examples of such specific compounds may include N,N'-hexanediyldi(carbamic acid methyl ester), N,N'-hexanediyldi(carbamic acid ethyl ester), N,N'-hexanediyldi(carbamic acid propyl ester), N,N'-hexanediyldi(carbamic acid butyl ester), N,N'-hexanediyldi(carbamic acid pentyl ester), N,N'-hexanediyldi(carbamic acid hexyl ester), methylene-di(cyclohexylcarbamic acid methyl ester), methylene-di(cyclohexylcarbamic acid ethyl ester), methylene-di(cyclohexylcarbamic acid propyl ester), methylene-di(cyclohexylcarbamic acid butyl ester), methylene-di(cyclohexylcarbamic acid pentyl ester), methylene-di(cyclohexylcarbamic acid hexyl ester), methylene-di(cyclohexylcarbamic acid heptyl ester), methylene-di(cyclohexylcarbamic acid octyl ester), 3-(methoxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid methyl ester, 3-(ethoxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid ethyl ester, 3-(propyloxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid propyl ester, 3-(butyloxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid butyl ester, 3-(pentyloxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid pentyl ester, 3-(hexyloxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid hexyl ester, 3-(heptyloxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid heptyl ester, 3-(octyloxycarbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid octyl ester, toluene-di(carbamic acid methyl ester), toluene-

di(carbamic acid ethyl ester), toluene-di(carbamic acid propyl ester), toluene-di(carbamic acid butyl ester), toluene-di(carbamic acid pentyl ester), toluene-di(carbamic acid hexyl ester), toluene-di(carbamic acid heptyl ester), toluene-di(carbamic acid octyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid methyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid ethyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid propyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid butyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid pentyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid hexyl ester), N,N'-(methanediyl-diphenyl)-di(carbamic acid heptyl ester) and N,N'-(methanediyl-diphenyl)-di(carbamic acid octyl ester). Preferable N-substituted carbamic acid-O-R² esters contain N-substituted carbamic acid-O-R² esters obtained by using preferable compounds previously explained for the above-mentioned organic primary amines, alcohols and compounds having ureido groups, examples of which may include N-substituted carbamic acid-O-R² esters obtained by reacting an alcohol with an N-substituted aromatic organic monourea, N-substituted aromatic organic polyurea or N-substituted aliphatic organic polyurea, and N-substituted carbamic acid-O-R² esters obtained by condensing an N-substituted carbamic acid-O-R² ester obtained from an alcohol and an N-substituted aromatic organic monourea with a condensing agent. In addition, N-substituted carbamic acid-O-R² esters are also preferable in which all ureido groups or primary amino groups contained in a compound having ureido groups or organic primary amine are substituted with carbamic acid-O-alkyl ester groups (namely, a = r).

<Carbonic Acid Ester>

[0181] The carbonic acid ester is a component that is preferably contained at a specific amount in the composition for transfer and storage of the present embodiment.

[0182] A carbonic acid ester refers to a compound in which one or both of the two hydrogen atoms of carbonic acid (CO(OH)₂) are substituted with an aliphatic group or aromatic group. A compound represented by the following formula (20) is preferably used in the present embodiment:



(wherein

R³⁸ and R³⁹ are groups that are respectively and independently selected from the above-mentioned R² and Ar groups).

[0183] The above-mentioned carbonic acid ester is formed by a reaction between urea and an alcohol and/or aromatic hydroxy compound, a reaction between an N-substituted carbamic acid-O-(R² or aryl) ester and an alcohol and/or aromatic hydroxy compound, or a disproportionation reaction of the formed carbonic acid ester.

[0184] Examples of the R² and Ar groups may include the R² and Ar groups explained for the N-substituted carbamic acid-O-(R² or aryl) ester.

[0185] Examples of carbonic acid ester represented by the formula (20) may include dimethyl carbonate, diethyl carbonate, dipropyl carbonate, dibutyl carbonate, dipentyl carbonate, dihexyl carbonate, diheptyl carbonate, dioctyl carbonate, dinonyl carbonate, didecyl carbonate, diundecyl carbonate, didodecyl carbonate, ditridecyl carbonate, ditetradecyl carbonate, dipentadecyl carbonate, dihexadecyl carbonate, diheptadecyl carbonate, dioctadecyl carbonate, dinonadecyl carbonate, diphenyl carbonate, di(methylphenyl) carbonate, di(ethylphenyl) carbonate, di(propylphenyl) carbonate, di(butylphenyl) carbonate, di(pentylphenyl) carbonate, di(hexylphenyl) carbonate, di(heptylphenyl) carbonate, di(octylphenyl) carbonate, di(nonylphenyl) carbonate, di(decylphenyl) carbonate, di(biphenyl) carbonate, di(dimethylphenyl) carbonate, di(diethylphenyl) carbonate, di(dipropylphenyl) carbonate, di(dibutylphenyl) carbonate, di(dipentylphenyl) carbonate, di(dihexylphenyl) carbonate, di(diheptylphenyl) carbonate, di(phenylphenyl) carbonate, di(trimethylphenyl) carbonate, di(triethylphenyl) carbonate, di(tripropylphenyl) carbonate, di(tributylphenyl) carbonate, di(phenylmethyl) carbonate, di(phenylethyl) carbonate, di(phenylpropyl) carbonate, di(phenylbutyl) carbonate, di(phenylpentyl) carbonate, di(phenylhexyl) carbonate, di(phenylheptyl) carbonate, di(phenyloctyl) carbonate, di(phenylnonyl) carbonate, (methyl)(ethyl) carbonate, (methyl)(propyl) carbonate, (methyl)(butyl) carbonate, (methyl)(pentyl) carbonate, (methyl)(hexyl) carbonate, (methyl)(heptyl) carbonate, (methyl)(octyl) carbonate, (methyl)(nonyl) carbonate, (methyl)(decyl) carbonate, (methyl)(undecyl) carbonate, (methyl)(dodecyl) carbonate, (methyl)(tridecyl) carbonate, (methyl)(tetradecyl) carbonate, (methyl)(pentadecyl) carbonate, (methyl)(hexadecyl) carbonate, (methyl)(heptadecyl) carbonate, (methyl)(octadecyl) carbonate, (methyl)(nonadecyl) carbonate, (methyl)(phenyl) carbonate, (methyl)(methylphenyl) carbonate, (methyl)(ethylphenyl) carbonate, (methyl)(propylphenyl) carbonate, (methyl)(butylphenyl) carbonate, (methyl)(pentylphenyl) carbonate, (methyl)(hexylphenyl) carbonate, (methyl)(heptylphenyl) carbonate, (methyl)(octylphenyl) carbonate, (methyl)(nonylphenyl) carbonate, (methyl)(decylphenyl) carbonate, (methyl)(biphenyl) carbonate, (methyl)(dimethylphenyl) carbonate, (methyl)(diethylphenyl) carbonate, (methyl)(dipropylphenyl) carbonate, (methyl)(dib-

utylphenyl) carbonate, (methyl)(dipentylphenyl) carbonate, (methyl)(dihexylphenyl) carbonate, (methyl)(diheptylphenyl) carbonate, (methyl)(phenylphenyl) carbonate, (methyl)(trimethylphenyl) carbonate, (methyl)(triethylphenyl) carbonate, (methyl)(tripropylphenyl) carbonate, (methyl)(tributylphenyl) carbonate, (methyl)(phenylmethyl) carbonate, (methyl)(phenylethyl) carbonate, (methyl)(phenylpropyl) carbonate, (methyl)(phenylbutyl) carbonate (methyl)(phenyl(pentyl) carbonate, (methyl)(phenylhexyl) carbonate, (methyl)(phenylheptyl) carbonate, (methyl)(phenyloctyl) carbonate, (methyl)(phenylnonyl) carbonate, (ethyl)(propyl) carbonate, (ethyl)(butyl) carbonate, (ethyl)(pentyl) carbonate, (ethyl)(hexyl) carbonate, (ethyl)(heptyl) carbonate, (ethyl)(octyl) carbonate, (ethyl)(nonyl) carbonate, (ethyl)(decyl) carbonate, (ethyl)(undecyl) carbonate, (ethyl)(dodecyl) carbonate, (ethyl)(tridecyl) carbonate, (ethyl)(tetradecyl) carbonate, (ethyl)(pentadecyl) carbonate, (ethyl)(hexadecyl) carbonate, (ethyl)(heptadecyl) carbonate, (ethyl)(octadecyl) carbonate, (ethyl)(nonadecyl) carbonate, (ethyl)(phenyl) carbonate, (ethyl)(methylphenyl) carbonate, (ethyl)(ethylphenyl) carbonate, (ethyl)(propylphenyl) carbonate, (ethyl)(butylphenyl) carbonate, (ethyl)(pentylphenyl) carbonate, (ethyl)(hexylphenyl) carbonate, (ethyl)(heptylphenyl) carbonate, (ethyl)(octylphenyl) carbonate, (ethyl)(nonylphenyl) carbonate, (ethyl)(decylphenyl) carbonate, (ethyl)(biphenyl) carbonate, (ethyl)(dimethylphenyl) carbonate, (ethyl)(diethylphenyl) carbonate, (ethyl)(dipropylphenyl) carbonate, (ethyl)(dibutylphenyl) carbonate, (ethyl)(dipentylphenyl) carbonate, (ethyl)(dihexylphenyl) carbonate, (ethyl)(diheptylphenyl) carbonate, (ethyl)(phenylphenyl) carbonate, (ethyl)(trimethylphenyl) carbonate, (ethyl)(triethylphenyl) carbonate, (ethyl)(tripropylphenyl) carbonate, (ethyl)(tributylphenyl) carbonate, (ethyl)(phenylmethyl) carbonate, (ethyl)(phenylethyl) carbonate, (ethyl)(phenylpropyl) carbonate, (ethyl)(phenylbutyl) carbonate, (ethyl)(phenylpentyl) carbonate, (ethyl)(phenylhexyl) carbonate, (ethyl)(phenylheptyl) carbonate, (ethyl)(phenyloctyl) carbonate, (ethyl)(phenylnonyl) carbonate, (propyl)(butyl) carbonate, (propyl)(pentyl) carbonate, (propyl)(hexyl) carbonate, (propyl)(heptyl) carbonate, (propyl)(octyl) carbonate, (propyl)(nonyl) carbonate, (propyl)(decyl) carbonate, (propyl)(undecyl) carbonate, (propyl)(dodecyl) carbonate, (propyl)(tridecyl) carbonate, (propyl)(tetradecyl) carbonate, (propyl)(pentadecyl) carbonate, (propyl)(hexadecyl) carbonate, (propyl)(heptadecyl) carbonate, (propyl)(octadecyl) carbonate, (propyl)(nonadecyl) carbonate, (propyl)(phenyl) carbonate, (propyl)(methylphenyl) carbonate, (propyl)(ethylphenyl) carbonate, (propyl)(propylphenyl) carbonate, (propyl)(butylphenyl) carbonate, (propyl)(pentylphenyl) carbonate, (propyl)(hexylphenyl) carbonate, (propyl)(heptylphenyl) carbonate, (propyl)(octylphenyl) carbonate, (propyl)(nonylphenyl) carbonate, (propyl)(decylphenyl) carbonate, (propyl)(biphenyl) carbonate, (propyl)(dimethylphenyl) carbonate, (propyl)(diethylphenyl) carbonate, (propyl)(dipropylphenyl) carbonate, (propyl)(dibutylphenyl) carbonate, (propyl)(dipentylphenyl) carbonate, (propyl)(dihexylphenyl) carbonate, (propyl)(diheptylphenyl) carbonate, (propyl)(phenylphenyl) carbonate, (propyl)(trimethylphenyl) carbonate, (propyl)(triethylphenyl) carbonate, (propyl)(tripropylphenyl) carbonate, (propyl)(tributylphenyl) carbonate, (propyl)(phenylmethyl) carbonate, (propyl)(phenylethyl) carbonate, (propyl)(phenylpropyl) carbonate, (propyl)(phenylbutyl) carbonate, (propyl)(phenylpentyl) carbonate, (propyl)(phenylhexyl) carbonate, (propyl)(phenylheptyl) carbonate, (propyl)(phenyloctyl) carbonate, (propyl)(phenylnonyl) carbonate, (butyl)(pentyl) carbonate, (butyl)(hexyl) carbonate, (butyl)(heptyl) carbonate, (butyl)(octyl) carbonate, (butyl)(nonyl) carbonate, (butyl)(decyl) carbonate, (butyl)(undecyl) carbonate, (butyl)(dodecyl) carbonate, (butyl)(tridecyl) carbonate isome, (butyl)(tetradecyl) carbonate, (butyl)(pentadecyl) carbonate, (butyl)(hexadecyl) carbonate, (butyl)(heptadecyl) carbonate, (butyl)(octadecyl) carbonate, (butyl)(nonadecyl) carbonate, (butyl)(phenyl) carbonate, (butyl)(methylphenyl) carbonate, (butyl)(ethylphenyl) carbonate, (butyl)(propylphenyl) carbonate, (butyl)(butylphenyl) carbonate, (butyl)(pentylphenyl) carbonate, (butyl)(hexylphenyl) carbonate, (butyl)(heptylphenyl) carbonate, (butyl)(octylphenyl) carbonate, (butyl)(nonylphenyl) carbonate, (butyl)(decylphenyl) carbonate, (butyl)(biphenyl) carbonate, (butyl)(dimethylphenyl) carbonate, (butyl)(diethylphenyl) carbonate, (butyl)(dipropylphenyl) carbonate, (butyl)(dibutylphenyl) carbonate, (butyl)(dipentylphenyl) carbonate, (butyl)(dihexylphenyl) carbonate, (butyl)(diheptylphenyl) carbonate, (butyl)(phenylphenyl) carbonate, (butyl)(trimethylphenyl) carbonate, (butyl)(triethylphenyl) carbonate, (butyl)(tripropylphenyl) carbonate, (butyl)(tributylphenyl) carbonate, (butyl)(phenylmethyl) carbonate, (butyl)(phenylethyl) carbonate, (butyl)(phenylpropyl) carbonate, (butyl)(phenylbutyl) carbonate, (butyl)(phenylpentyl) carbonate, (butyl)(phenylhexyl) carbonate, (butyl)(phenylheptyl) carbonate, (butyl)(phenyloctyl) carbonate, (butyl)(phenylnonyl) carbonate, (pentyl)(hexyl) carbonate, (pentyl)(heptyl) carbonate, (pentyl)(octyl) carbonate, (pentyl)(nonyl) carbonate, (pentyl)(decyl) carbonate, (pentyl)(undecyl) carbonate, (pentyl)(dodecyl) carbonate, (pentyl)(tridecyl) carbonate, (pentyl)(tetradecyl) carbonate, (pentyl)(pentadecyl) carbonate, (pentyl)(hexadecyl) carbonate, (pentyl)(heptadecyl) carbonate, (pentyl)(octadecyl) carbonate, (pentyl)(nonadecyl) carbonate, (pentyl)(phenyl) carbonate, (pentyl)(methylphenyl) carbonate, (pentyl)(ethylphenyl) carbonate, (pentyl)(propylphenyl) carbonate, (pentyl)(butylphenyl) carbonate, (pentyl)(pentylphenyl) carbonate, (pentyl)(hexylphenyl) carbonate, (pentyl)(heptylphenyl) carbonate, (pentyl)(octylphenyl) carbonate, (pentyl)(nonylphenyl) carbonate, (pentyl)(decylphenyl) carbonate, (pentyl)(biphenyl) carbonate, (pentyl)(dimethylphenyl) carbonate, (pentyl)(diethylphenyl) carbonate, (pentyl)(dipropylphenyl) carbonate, (pentyl)(dibutylphenyl) carbonate, (pentyl)(dipentylphenyl) carbonate, (pentyl)(dihexylphenyl) carbonate, (pentyl)(diheptylphenyl) carbonate, (pentyl)(phenylphenyl) carbonate, (pentyl)(trimethylphenyl) carbonate, (pentyl)(triethylphenyl) carbonate, (pentyl)(tripropylphenyl) carbonate, (pentyl)(tributylphenyl) carbonate, (pentyl)(phenylmethyl) carbonate, (pentyl)(phenylethyl) carbonate, (pentyl)(phenylpropyl) carbonate, (pentyl)(phenylbutyl) carbonate, (pentyl)(phenylpentyl) carbonate, (pentyl)(phenylhexyl) carbonate, (pentyl)(phenylheptyl) carbonate, (pentyl)(phenyloctyl) carbonate,

(pentyl)(phenylnonyl) carbonate, (hexyl)(heptyl) carbonate, (hexyl)(octyl) carbonate, (hexyl)(nonyl) carbonate, (hexyl)(decyl) carbonate, (hexyl)(undecyl) carbonate, (hexyl)(dodecyl) carbonate, (hexyl)(tridecyl) carbonate, (hexyl)(tetradecyl) carbonate, (hexyl)(pentadecyl) carbonate, (hexyl)(hexadecyl) carbonate, (hexyl)(heptadecyl) carbonate, (hexyl)(octadecyl) carbonate, (hexyl)(nonadecyl) carbonate, (hexyl)(phenyl) carbonate (hexyl)(methylphenyl) carbonate, (hexyl)(ethylphenyl) carbonate, (hexyl)(propylphenyl) carbonate, (hexyl)(butylphenyl) carbonate, (hexyl)(pentylphenyl) carbonate, (hexyl)(hexylphenyl) carbonate, (hexyl)(heptylphenyl) carbonate, (hexyl)(octylphenyl) carbonate, (hexyl)(nonylphenyl) carbonate, (hexyl)(decylphenyl) carbonate, (hexyl)(biphenyl) carbonate, (hexyl)(dimethylphenyl) carbonate, (hexyl)(diethylphenyl) carbonate, (hexyl)(dipropylphenyl) carbonate, (hexyl)(dibutylphenyl) carbonate, (hexyl)(dipentylphenyl) carbonate, (hexyl)(diethylphenyl) carbonate, (hexyl)(diheptylphenyl) carbonate, (hexyl)(phenylphenyl) carbonate, (hexyl)(trimethylphenyl) carbonate, (hexyl)(triethylphenyl) carbonate, (hexyl)(tripropylphenyl) carbonate, (hexyl)(tributylphenyl) carbonate, (hexyl)(phenylmethyl) carbonate, (hexyl)(phenylethyl) carbonate (hexyl)(phenylpropyl) carbonate, (hexyl)(phenylbutyl) carbonate, (hexyl)(phenylpentyl) carbonate, (hexyl)(phenylhexyl) carbonate, (hexyl)(phenylheptyl) carbonate, (hexyl)(phenyloctyl) carbonate, (hexyl)(phenylnonyl) carbonate, (heptyl)(octyl) carbonate, (heptyl)(nonyl) carbonate, (heptyl)(decyl) carbonate, (heptyl)(undecyl) carbonate, (heptyl)(dodecyl) carbonate, (heptyl)(tridecyl) carbonate, (heptyl)(tetradecyl) carbonate, (heptyl)(pentadecyl) carbonate, (heptyl)(hexadecyl) carbonate, (heptyl)(heptadecyl) carbonate, (heptyl)(octadecyl) carbonate, (heptyl)(nonadecyl) carbonate, (heptyl)(phenyl) carbonate, (heptyl)(methylphenyl) carbonate, (heptyl)(ethylphenyl) carbonate, (heptyl)(propylphenyl) carbonate, (heptyl)(butylphenyl) carbonate, (heptyl)(pentylphenyl) carbonate, (heptyl)(hexylphenyl) carbonate, (heptyl)(heptylphenyl) carbonate, (heptyl)(octylphenyl) carbonate, (heptyl)(nonylphenyl) carbonate, (heptyl)(decylphenyl) carbonate, (heptyl)(biphenyl) carbonate, (heptyl)(dimethylphenyl) carbonate, (heptyl)(diethylphenyl) carbonate, (heptyl)(dipropylphenyl) carbonate, (heptyl)(dibutylphenyl) carbonate, (heptyl)(dipentylphenyl) carbonate, (heptyl)(diethylphenyl) carbonate, (heptyl)(diheptylphenyl) carbonate, (heptyl)(phenylphenyl) carbonate, (heptyl)(trimethylphenyl) carbonate, (heptyl)(triethylphenyl) carbonate, (heptyl)(tripropylphenyl) carbonate, (heptyl)(tributylphenyl) carbonate, (heptyl)(phenylmethyl) carbonate, (heptyl)(phenylethyl) carbonate, (heptyl)(phenylpropyl) carbonate, (heptyl)(phenylbutyl) carbonate, (heptyl)(phenylpentyl) carbonate, (heptyl)(phenylhexyl) carbonate, (heptyl)(phenylheptyl) carbonate, (heptyl)(phenyloctyl) carbonate, (heptyl)(phenylnonyl) carbonate, (octyl)(nonyl) carbonate, (octyl)(decyl) carbonate, (octyl)(undecyl) carbonate, (octyl)(dodecyl) carbonate, (octyl)(tridecyl) carbonate, (octyl)(tetradecyl) carbonate, (octyl)(pentadecyl) carbonate, (octyl)(hexadecyl) carbonate, (octyl)(heptadecyl) carbonate, (octyl)(octadecyl) carbonate, (octyl)(nonadecyl) carbonate, (octyl)(phenyl) carbonate, (octyl)(methylphenyl) carbonate, (octyl)(ethylphenyl) carbonate, (octyl)(propylphenyl) carbonate, (octyl)(butylphenyl) carbonate, (octyl)(pentylphenyl) carbonate, (octyl)(hexylphenyl) carbonate, (octyl)(heptylphenyl) carbonate, (octyl)(octylphenyl) carbonate, (octyl)(nonylphenyl) carbonate, (octyl)(decylphenyl) carbonate, (octyl)(biphenyl) carbonate, (octyl)(dimethylphenyl) carbonate, (octyl)(diethylphenyl) carbonate, (octyl)(dipropylphenyl) carbonate, (octyl)(dibutylphenyl) carbonate, (octyl)(dipentylphenyl) carbonate, (octyl)(diethylphenyl) carbonate, (octyl)(diheptylphenyl) carbonate, (octyl)(phenylphenyl) carbonate, (octyl)(trimethylphenyl) carbonate, (octyl)(triethylphenyl) carbonate, (octyl)(tripropylphenyl) carbonate, (octyl)(tributylphenyl) carbonate, (octyl)(phenylmethyl) carbonate, (octyl)(phenylethyl) carbonate, (octyl)(phenylpropyl) carbonate, (octyl)(phenylbutyl) carbonate (octyl)(phenylpentyl) carbonate, (octyl)(phenylhexyl) carbonate, (octyl)(phenylheptyl) carbonate (octyl)(phenyloctyl) carbonate, (octyl)(phenylnonyl) carbonate, (methylphenyl)(ethylphenyl) carbonate, (methylphenyl)(propylphenyl) carbonate, (methylphenyl)(butylphenyl) carbonate, (methylphenyl)(pentylphenyl) carbonate, (methylphenyl)(hexylphenyl) carbonate, (methylphenyl)(heptylphenyl) carbonate, (methylphenyl)(octylphenyl) carbonate, (methylphenyl)(nonylphenyl) carbonate, (methylphenyl)(decylphenyl) carbonate, (methylphenyl)(biphenyl) carbonate, (methylphenyl)(dimethylphenyl) carbonate, (methylphenyl)(diethylphenyl) carbonate, (methylphenyl)(dipropylphenyl) carbonate, (methylphenyl)(dibutylphenyl) carbonate, (methylphenyl)(dipentylphenyl) carbonate, (methylphenyl)(diethylphenyl) carbonate, (methylphenyl)(diheptylphenyl) carbonate, (methylphenyl)(phenylphenyl) carbonate, (methylphenyl)(trimethylphenyl) carbonate, (methylphenyl)(triethylphenyl) carbonate, (methylphenyl)(tripropylphenyl) carbonate, (methylphenyl)(tributylphenyl) carbonate, (methylphenyl)(phenylmethyl) carbonate, (methylphenyl)(phenylethyl) carbonate, (methylphenyl)(phenylpropyl) carbonate, (methylphenyl)(phenylbutyl) carbonate, (methylphenyl)(phenylpentyl) carbonate, (methylphenyl)(phenylhexyl) carbonate, (methylphenyl)(phenylheptyl) carbonate, (methylphenyl)(phenyloctyl) carbonate, (methylphenyl)(phenylnonyl) carbonate, (ethylphenyl)(propylphenyl) carbonate, (ethylphenyl)(butylphenyl) carbonate, (ethylphenyl)(pentylphenyl) carbonate, (ethylphenyl)(hexylphenyl) carbonate, (ethylphenyl)(heptylphenyl) carbonate, (ethylphenyl)(octylphenyl) carbonate, (ethylphenyl)(nonylphenyl) carbonate, (ethylphenyl)(decylphenyl) carbonate, (ethylphenyl)(biphenyl) carbonate, (ethylphenyl)(dimethylphenyl) carbonate, (ethylphenyl)(diethylphenyl) carbonate, (ethylphenyl)(dipropylphenyl) carbonate, (ethylphenyl)(dibutylphenyl) carbonate, (ethylphenyl)(dipentylphenyl) carbonate, (ethylphenyl)(diethylphenyl) carbonate, (ethylphenyl)(diheptylphenyl) carbonate, (ethylphenyl)(phenylphenyl) carbonate, (ethylphenyl)(trimethylphenyl) carbonate, (ethylphenyl)(triethylphenyl) carbonate, (ethylphenyl)(tripropylphenyl) carbonate, (ethylphenyl)(tributylphenyl) carbonate, (ethylphenyl)(phenylmethyl) carbonate, (ethylphenyl)(phenylethyl) carbonate, (ethylphenyl)(phenylpropyl) carbonate, (ethylphenyl)(phenylbutyl) carbonate, (ethylphenyl)(phenylpentyl) carbonate, (ethylphenyl)(phenylhexyl) carbonate, (ethylphenyl)(phenylheptyl) carbon-

pylphenyl)(phenylpentyl) carbonate, (dipropylphenyl)(phenylhexyl) carbonate, (dipropylphenyl)(phenylheptyl) carbonate, (dipropylphenyl)(phenyloctyl) carbonate, (dipropylphenyl)(phenylnonyl) carbonate, (dibutylphenyl)(dipentylphenyl) carbonate, (dibutylphenyl)(dihexylphenyl) carbonate, (dibutylphenyl)(diheptylphenyl) carbonate, (dibutylphenyl)(phenylphenyl) carbonate, (dibutylphenyl)(trimethylphenyl) carbonate, (dibutylphenyl)(triethylphenyl) carbonate, (dibutylphenyl)(tripropylphenyl) carbonate, (dibutylphenyl)(tributylphenyl) carbonate, (dibutylphenyl)(phenylmethyl) carbonate, (dibutylphenyl)(phenylethyl) carbonate, (dibutylphenyl)(phenylpropyl) carbonate, (dibutylphenyl)(phenylbutyl) carbonate, (dibutylphenyl)(phenylpentyl) carbonate, (dibutylphenyl)(phenylhexyl) carbonate, (dibutylphenyl)(phenylheptyl) carbonate, (dibutylphenyl)(phenyloctyl) carbonate, (dibutylphenyl)(phenylnonyl) carbonate, (dipentylphenyl)(dihexylphenyl) carbonate, (dipentylphenyl)(diheptylphenyl) carbonate, (dipentylphenyl)(phenylphenyl) carbonate, (dipentylphenyl)(trimethylphenyl) carbonate, (dipentylphenyl)(triethylphenyl) carbonate, (dipentylphenyl)(tripropylphenyl) carbonate, (dipentylphenyl)(tributylphenyl) carbonate, (dipentylphenyl)(phenylmethyl) carbonate, (dipentylphenyl)(phenylethyl) carbonate, (dipentylphenyl)(phenylpropyl) carbonate, (dipentylphenyl)(phenylbutyl) carbonate, (dipentylphenyl)(phenylpentyl) carbonate, (dipentylphenyl)(phenylhexyl) carbonate, (dipentylphenyl)(phenylheptyl) carbonate, (dipentylphenyl)(phenyloctyl) carbonate, (dipentylphenyl)(phenylnonyl) carbonate, (trimethylphenyl)(trethylphenyl) carbonate, (trimethylphenyl)(tripropylphenyl) carbonate, (trimethylphenyl)(tributylphenyl) carbonate, (trimethylphenyl)(phenylmethyl) carbonate, (trimethylphenyl)(phenylethyl) carbonate, (trimethylphenyl)(phenylpropyl) carbonate, (trimethylphenyl)(phenylbutyl) carbonate, (trimethylphenyl)(phenylpentyl) carbonate, (trimethylphenyl)(phenylhexyl) carbonate, (trimethylphenyl)(phenylheptyl) carbonate, (trimethylphenyl)(phenyloctyl) carbonate and (trimethylphenyl)(phenylnonyl) carbonate.

[0186] A trace amount of carbonic acid ester is formed as a by-product during production of N-substituted carbamic acid-O-aryl ester from the composition for transfer and storage of a compound having ureido groups of the present embodiment and an aromatic hydroxy compound and/or during production of N-substituted carbamic acid-O-R² ester from a compound having ureido groups and an alcohol as previously described. A preferable aspect involves producing the N-substituted carbamic acid-O-aryl ester followed by recycling the compounds used in each step when producing isocyanate by thermally decomposing the N-substituted carbamic acid-O-aryl ester. The carbonic acid ester may be contained at that time when the composition for transfer and storage of a compound having ureido groups is produced by recovering the carbonic acid ester along with the aromatic hydroxy compound. The carbonic acid ester formed as a by-product is a carbonic acid ester derived from the aromatic hydroxy compound and/or alcohol used when producing the N-substituted carbamic acid-O-aryl ester, namely a carbonic acid ester in which R³⁸OH and R³⁹OH, in which hydroxyl groups have been added to R³⁸ and R³⁹ of the above-mentioned formula (20), correspond to the above-mentioned aromatic hydroxy compound and/or alcohol. When producing N-substituted carbamic acid-O-aryl ester using the compound for transfer and storage of a compound having ureido groups that contains the carbonic acid ester, there is also a mechanism by which N-substituted carbamic acid-O-(R² or aryl) ester is regenerated by addition to an undesirable compound having ureylene groups that is formed due to condensation of the N-substituted carbamic acid-O-(R² or aryl) ester, thereby making this aspect preferable. In addition, although there may be cases in which complexly substituted monomers or polymers of urea compounds, biurets or nurates and the like are contained in addition to the urea compound, carbamic acid ester and carbonic acid ester, there are no problems with such compounds being contained.

[0187] A brief explanation has been provided of several steps in the explanation of compounds used in the present embodiment as described above. Next, a detailed explanation is given of a method for producing N-substituted carbamic acid-O-aryl ester from a compound having ureido groups and an aromatic hydroxy composition, as well as a detailed explanation of each step contained in the method for producing isocyanate from N-substituted carbamic acid-O-aryl ester. The production method of N-substituted carbamic acid-O-aryl ester of the present embodiment is a method for producing at least one N-substituted carbamic acid-O-aryl ester derived from a compound having ureido groups and an aromatic hydroxy composition comprising a step of carrying out an esterification reaction or steps for carrying out an esterification reaction and a transesterification reaction from the compound having ureido groups represented by formula (1) and the aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by formula (2) (herein the N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which an oxygen atom of the carbamic acid group (-NHCOO-) is bonded to an aromatic ring, or in other words, an N-substituted carbamic acid-O-ester derived from the compound having ureido groups and the aromatic hydroxy compound). More specifically, the production method is a method for producing N-substituted carbamic acid-O-aryl ester comprising a step of esterifying a compound having ureido groups and at least one type of aromatic hydroxy composition represented by formula (2), or a method for producing the N-substituted carbamic acid-O-aryl ester comprising a step of esterifying a compound having ureido groups and an alcohol represented by formula (4) to obtain N-substituted carbamic acid-O-R² ester, and a step of transesterifying the N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition. More specifically, the production method is a method for producing N-substituted carbamic acid-O-aryl ester from the compound having ureido groups and the aromatic hydroxy composition that comprises a step (B), or a method for producing the N-substituted carbamic acid-O-aryl ester from the compound having ureido groups, the aromatic hydroxy composition and an alcohol represented by formula (4) that comprises a step (R) and a step (P). Preferably, the compound

having ureido groups is a compound having ureido groups obtained in step (A), and the above-mentioned production methods respectively contains a production method that comprises the step (A) and the step (B) and a production method that comprises the step (A), the step (R) and the step (P). The above-mentioned N-substituted carbamic acid-O-R² ester refers to an N-substituted carbamic acid-O-ester derived from a compound having ureido groups and an R² group of an alcohol represented by formula (4).

[0188] First, a brief explanation is provided of the previously mentioned steps (A), (B), (C), (R), (P) and (F) along with the following steps (D), (E) and (G) that are also included in the production method of the present embodiment.

<Step (D)>

[0189] The following step (D) is carried out to recover urea before step (B), step (R) or step (P), or simultaneous to step (B), step (R) or step (P):

step (D): a step of removing urea by distillation or sublimation.

<Step (E)>

[0190] Step (E): a step of recycling the urea recovered in step (D) to step (A).

<Step (G)>

[0191] The following step (G) is carried out to recover ammonia formed as a by-product in step (A) and/or step (B) and/or step (R), react with carbon dioxide to regenerate urea, and recycle the urea to step (A):

step (G): a step of recovering ammonia formed as a by-product, reacting with carbon dioxide to regenerate urea, and recycling the urea to step (A).

[0192] The above-mentioned steps (D), (E) and (G) will be subsequently described in detail.

[0193] The production method of N-substituted carbamic acid-O-aryl ester of the present embodiment enables the production of diverse N-substituted carbamic acid-O-aryl esters by selecting the compounds used, such as organic primary amine, aromatic hydroxy composition and additionally alcohol and the like, together with selecting and combining the above-mentioned steps (A) to (G), and further enables the obtaining of isocyanate from the N-substituted carbamic acid-O-aryl ester.

<Production Method of Compound Having Ureido Groups>

[0194] As was previously described, the compound having the ureido groups used in the present embodiment may be a compound having ureido groups that is obtained by the known method. Preferably, it is a compound having ureido groups that is obtained using the following step (A):

step (A): a step of obtaining at least one type of compound having ureido groups derived from an organic primary amine represented by the following formula (3) and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction.


[0195] The term "eliminated" does not refer to an ammonia radical, but rather to dissolving and/or dispersing in a liquid phase.

[0196] FIG. 1 shows a conceptual drawing of the step (A) in the present embodiment. In addition, the above-mentioned ureidation reaction indicates a reaction between an amino group of an organic primary amine and an ureido group, namely a reaction in which the organic primary amine is converted to a compound having ureido groups.

[0197] As a result of extensive studies conducted by the inventors of the present invention, the inventors of the present invention surmised the reaction mechanism by which a compound having ureido groups is formed from an organic primary amine and urea to be as indicated below, although the entirety of which is not yet clear. Furthermore, in order to simplify the following explanation, an organic primary amine having two amino groups is shown for the organic primary amine. Naturally, cases of using an organic primary amine other than that shown here can be considered in the same manner.

[0198] The reaction for forming a compound having ureido groups from an organic primary amine and urea appears to be as shown in the following formula (111), and proceeds while forming ammonia as a by-product although not shown



in the formula:



(wherein

R represents an organic group substituted with two substituents).

10 **[0199]** In the reaction for forming a compound having ureido groups of formula (111) above, a reaction, for example, in which a compound having ureylene groups is formed from a compound having ureido groups and organic primary amine as represented by the following formula (113), or for example, a reaction in which a compound having biuret groups is formed by condensing a compound having ureido groups as represented by the following formula (114), may occur concomitantly as side reactions (the reaction formulas used to explain the present embodiment are for indicating the concepts of the reactions (whether compounds are reactants or products), and frequently do not indicate numbers indicating stoichiometric ratios):




(wherein

R represents a divalent organic group).

30 **[0200]** The following provides an explanation of the amounts of organic primary amine and urea used as raw materials in step (A). The amount of urea is within a range of a stoichiometric ratio of from 1 to 100 times based on amino groups of the organic primary amine. Although previously explained for non-N-substituted carbamic acid ester, a compound having ureido groups can be obtained by reacting with organic primary amine in the same manner as urea also in the case of non-N-substituted carbamic acid-O-R² ester and/or N-substituted carbamic acid-O-aryl ester. Namely, the amounts of urea indicated previously and indicated to follow are stoichiometric values of the total of urea, non-N-substituted carbamic acid-O-R² ester and non-N-substituted carbamic acid O-aryl ester. In the case the amount used of urea (and non-N-substituted carbamic acid ester) is low, since complexly substituted carbonyl compounds and the like attributable to formula (113) above are formed easily, it is preferable to use an excess of urea and non-N-substituted carbamic acid ester.

40 **[0201]** In addition, urea and non-N-substituted carbamic acid ester present in excess in the reaction system of step (A) are presumed to have the effect of stabilizing the compound having ureido groups formed (non-N-substituted carbamic acid-O-R² ester and/or non-N-substituted carbamic acid-O-aryl ester are frequently collectively referred to as non-N-substituted carbamic acid ester). According to studies conducted by the inventors of the present invention, there are cases in which compounds having a biuret bond (such as the compound on the right side of the following formula (125)) or compounds having a biuret terminal (compound on the right side of the following formula (126)) are formed during the course of producing the compound having ureido groups depending on the reaction conditions. In order to selectively form a target compound having ureido groups, it is important to inhibit the formation of such compounds. As a result of extensive studies conducted by the inventors of the present invention, it was surprisingly found that there is an intimate relationship between the amount of urea (and the amount of non-N-substituted carbamic acid ester) in the reaction system and the amounts of such compounds formed, and that the amounts of such compounds are reduced the larger the amount of amount of urea (and non-N-substituted carbamic acid ester) present. Although the mechanism by which urea present in the reaction system demonstrates this effect is unclear, the inventors of the present invention made the presumptions indicated below regarding this mechanism.


50 **[0202]** First, the mechanism by which compounds having a biuret bond and compounds having a biuret terminal are formed is considered. The compound having ureido groups forms a compound having an isocyanate terminal (-NCO group) and ammonia due to thermal decomposition of the ureido groups depending on the reaction conditions (according to the following formula (124), for example):




5 (wherein
R represents a divalent organic group).

[0203] There is presumed to be cases in which the compound having an isocyanate terminal reacts with urea (and non-N-substituted carbamic acid ester) (as in, for example, the following formulas (125) and (126) explained using urea) to form a compound having a biuret bond or compound having a biuret terminal:

10



15



(wherein

20 R represents a divalent organic group).

[0204] The urea (and non-N-substituted carbamic acid ester) is presumed to stabilize the ureido groups by coordinating with the ureido groups by hydrogen bonding in the reaction liquid, and has the effect of inhibiting the first reaction in particular (namely the reaction represented by formula (124) above) among this series of reactions.

[0205] In this manner, the use of an excess amount of urea (and non-N-substituted carbamic acid ester) is important for selectively forming the compound having ureido groups. However, the use of an overly excessive amount of urea (and non-N-substituted carbamic acid ester) increases the size of the reactor making industrial application difficult, or as will be described later, may hinder separation and recovery of the urea (and non-N-substituted carbamic acid ester). Thus, the amount of urea used in terms of the stoichiometric ratio based on amino groups of the organic primary amine is preferably within a range of from 1 to 100 times, more preferably within a range of from 1.1 to 10 times and most preferably within a range of from 1.5 to 5 times.

30

[0206] In addition, it is also necessary to pay attention to the procedure when carrying out the reaction in consideration of the role of the urea (and non-N-substituted carbamic acid ester) as described above. Namely, a method is preferably carried out in which, for example, the entire amount of urea (and non-N-substituted carbamic acid ester) used is dissolved in advance in a reaction solvent (the details of which will be subsequently described) followed by addition of the organic primary amine to this mixed solution so as to continuously maintain the number of molecules of urea (and non-N-substituted carbamic acid ester) in the reaction system in a state of excess (and in a state of large excess if possible) based on the number of amino groups of the organic primary amine.

35

[0207] Next, an explanation is given of the ammonia concentration in the system. Furthermore, the preferable range of the ammonia concentration described here refers to the ammonia concentration in the reaction liquid after the compound having ureido groups has formed to a certain degree (such as at a yield of not less than 5% based on the organic amine), and does not refer to that at the start of the reaction.

40



[0208] The reaction in which N-substituted carbamic acid-O-(R² and/or aryl) ester is formed (such as the reaction of the following formula (118)) is an equilibrium reaction, and the equilibrium is considerably biased towards the reactants side. However, as a result of studies conducted by the inventors of the present invention, the reaction in which the compound having ureido groups is formed (reaction of the following formula (117)) was determined to be a reaction in which the equilibrium thereof is considerably biased towards the products side or be an irreversible reaction, and be virtually independent of the ammonia concentration in the system. Such a finding was heretofore unknown and is surprising. Thus, it was found that the compound having ureido groups can be formed selectively by maintaining the ammonia concentration in the reaction liquid of step (A) at a certain level or higher and inhibiting the formation of N-substituted carbamic acid ester by a reaction between the compound having ureido groups formed and an aromatic hydroxy compound (reaction of the above-mentioned formula (118)), and it was further found that the compound having ureido groups can be obtained with good selectivity by inhibiting side reactions by maintaining the ammonia concentration at a certain level or higher. In previously disclosed methods for producing compounds having ureido groups, side reaction products easily formed when obtaining a compound having ureido groups according to the above-mentioned reaction, and were contained within a range at which N-substituted carbamic acid-O-alkyl ester formed in accordance with the following formula (118) is simultaneously formed in large amounts, thus resulting in the serious problem of the concomitant occurrence of side reactions attributable to the N-substituted carbamic acid-O-alkyl ester. In order to solve this problem, the amount of the urea (and non-N-substituted carbamic acid ester) used and/or the ammonia concentration is important.

50

55

The ammonia concentration preferable for demonstrating such an effect is higher than 10 ppm, more preferably higher than 100 ppm, even more preferably higher than 300 ppm, and most preferably higher than 1000 ppm.

[0209] Furthermore, although the term "N-substituted carbamic acid-O-(R² and/or aryl) ester" is used in the explanation of the present specification, this refers to "N-substituted carbamic acid-O-R² ester and/or N-substituted carbamic acid-O-aryl ester":



(wherein

R represents an organic group substituted with two substituents, and

R'OH represents a monovalent hydroxy compound (alcohol or aromatic hydroxy compound)).

[0210] Step (A) can be carried out at a reaction temperature within a range of from 30 to 250°C. Although a high temperature is preferable to increase the reaction rate, on the other hand; since undesirable reactions occur at high temperatures (such as decomposition of the carbamic acid derivative) resulting in the formation of complexly substituted urea compounds and carbonyl compounds, the reaction temperature is preferably within a range of from 50 to 200°C and more preferably within a range of from 70 to 180°C. The known cooling apparatus or heating apparatus may be installed in the reactor for carrying out step (A) to maintain a constant reaction temperature.

[0211] Although varying according to the types of compounds used, composition of the reaction system, reaction temperature, reaction apparatus and the like, generally the reaction is preferably carried out at a reaction pressure within a range of from 0.01 kPa to 10 MPa (absolute pressure), and in consideration of ease of the industrial application, is preferably carried out at reaction pressure within a range of from 0.1 kPa to 5 MPa (absolute pressure).

[0212] There are no particular limitations on the reaction time (residence time in the case of a continuous method) in the step (A), and the reaction time is generally from 0.001 to 100 hours, preferably from 0.01 to 80 hours and more preferably from 0.1 to 50 hours. In addition, the reaction may be terminated after confirming that a desired amount of the compound having ureido groups has been formed by sampling the reaction liquid and determining the amount of the compound having ureido groups by liquid chromatography, for example. Although step (A) is a step of producing a compound having ureido groups, in step (A), if a large amount of amino groups derived from unreacted organic amine are present, compounds having ureylene groups and the like are formed during storage when using in the form of a composition for transfer and storage of a compound having ureido groups, or in step (B) or step (R) using the reaction liquid after step (A), which frequently not only causes a decrease in the amount of N-substituted carbamic acid-O-ester formed, but also causes adhesion and solidification in the reactor. Thus, in step (A), it is preferable to reduce the amount of amino groups derived from the organic primary amine by forming the compound having ureido groups at as high a yield as possible. More specifically, the reaction is preferably continued until the ratio of the number of amino groups derived from the organic primary amine to the number of ureido groups composing the compound having ureido groups becomes preferably 0.25 or less, more preferably 0.1 or less, and even more preferably 0.05 or less.

[0213] In the present embodiment, a catalyst can be used as necessary, and examples of catalysts that can be used may include organic metal compounds and inorganic metal compounds of tin, lead, copper or titanium, and basic catalysts such as alcoholate of alkaline metals or alkaline earth metals in the form of methylates, ethylates and butyrates of lithium, sodium, potassium, calcium or barium. If a catalyst is added, since there are many cases in which it is necessary to remove the catalyst, the reaction is preferably carried out without adding a catalyst. In the case of using a catalyst, the catalyst may be removed after the reaction. Since there are cases in which a catalyst may have a detrimental effect on compounds in the steps of the present embodiment, the catalyst is preferably separated or removed during the course of obtaining isocyanate by thermally decomposing N-substituted carbamic acid-O-aryl ester and purifying the isocyanate. If isocyanate is stored with the catalyst present, discoloration and other undesirable phenomena may occur. The known method can be used to remove the catalyst, and methods such as membrane separation, distillative separation or crystallization can be used. The catalyst is preferably removed for the reasons described above without being limited to step (A). More preferably, the catalyst is removed at completion of each step in which it is used. Known methods as previously described can be preferably used to remove the catalyst.

[0214] The reaction of step (A) is preferably carried out in a liquid phase in the presence of a solvent from the viewpoint of lowering the viscosity of the reaction liquid and/or making the reaction system homogeneous. Examples of solvents

that can be preferably used as reaction solvents may include alkanes such as pentane, hexane, heptane, octane, nonane or decane, aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene, ethyl benzene, diisopropyl benzene, dibutyl benzene or naphthalene; nitrile compounds such as acetonitrile or benzonitrile; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene, bromobenzene, dibromobenzene, chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted, diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene; aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as tetrahydrofuran, 1,4-dioxane, 1,2-dimethoxyethane, diphenyl ether or diphenyl sulfide; ketone compounds such as acetone or methyl ethyl ketone; ester compounds such as ethyl acetate or ethyl benzoate; sulfoxides such as dimethylsulfoxide or diphenylsulfoxide, and hydroxy compounds such as water, alcohols or aromatic hydroxy compounds. However, from the viewpoint of solubility of the product in the form of the compound having ureido groups, the reaction solvent is preferably water or a hydroxy composition (composition containing alcohol and/or aromatic hydroxy compound), and more preferably a hydroxy composition (the hydroxy composition being a hydroxy composition composed of one type or a plurality of types of hydroxy compounds (alcohol represented by formula (4) and/or aromatic hydroxy compound represented by formula (2)), and a hydroxy composition preferably used as a reaction solvent in step (A) is hereinafter referred to as "hydroxy composition a"). Furthermore, these solvents can be used alone or as a mixture of two or more types thereof.

[0215] Although hydroxy compounds that compose the hydroxy composition a may be completely identical, partially identical or different from the hydroxy composition used in step (B), step (R) or step (P) (composition composed of the aromatic hydroxy compound and/or alcohol that composes the aromatic hydroxy composition), in order to facilitate the procedure, the hydroxy composition a is preferably either the same as the hydroxy composition used in step (B) or step (P) or is a composition composed of that hydroxy composition. Although an explanation thereof is provided to follow, the reaction of step (A) is more preferably either carried out in the presence of an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)), or the reaction of step (A) is carried out in the presence of an alcohol or aromatic hydroxy composition followed by the addition of an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)). The step (A) is more preferably carried out in the presence of an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)). Although only alcohol may be used in the case of carrying out step (R) after step (A), in this case, an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)) is added after carrying out the reaction of step (A).

[0216] Although the reaction solvents indicated here can be used in an arbitrary amount, in the case of using an alcohol for the reaction solvent, it can be used at a stoichiometric ratio within a range of greater than 1 time to less than 100 times based on the amino groups of the organic primary amine. Although it is preferable to use an excess of alcohol based on the amino groups of the organic primary amine in order to improve the fluidity of the reaction liquid and allow the reaction to proceed efficiently, since problems may result such as an increase in the size of the reactor if an overly excessive amount of alcohol is used, the alcohol can be used at a stoichiometric ratio more preferably within a range of greater than 5 times to less than 50 times and even more preferably within a range of greater than 8 times to less than 20 times the amino groups of the organic primary amine.

[0217] In addition, in the case of using an aromatic hydroxy composition for the reaction solvent of step (A), it can be used at a stoichiometric ratio within a range of greater than 1 time to less than 100 times the amino groups of the organic primary amine. Although it is preferable to use an excess of alcohol based on the amino groups of the organic primary amine in order to improve the fluidity of the reaction liquid and allow the reaction to proceed efficiently, since problems may result such as an increase in the size of the reactor if an overly excessive amount of alcohol is used, alcohol can be used at a stoichiometric ratio more preferably within a range of greater than 2 times to less than 50 times and even more preferably within a range of greater than 3 times to less than 20 times the amino groups of the organic primary amine.

[0218] Among hydroxy compounds represented by compounds selected from alcohols represented by the above-mentioned formula (4) and aromatic hydroxy compounds represented by formula (2), an aromatic hydroxy compound is used preferably in consideration of solubility of the compound having ureido groups formed. - For example, although Japanese Examined Patent Publication No. H2-48539 describes to the effect that a compound having ureido groups is poorly soluble in n-butanol, with respect to this point, aromatic hydroxy compounds frequently have superior solubility for compounds having ureido groups. Moreover, aromatic hydroxy compounds also demonstrate the effect of promoting reactions between organic primary amine and urea (and non-N-substituted carbamic acid ester). Although the mechanism by which this effect is demonstrated is unclear, it has been surmised by the inventors of the present invention that, although urea (and non-N-substituted carbamic acid ester) generally tend to adopt an associated state due to hydrogen bonding, aromatic hydroxy compounds have acidic hydroxy groups, and the hydroxy groups inhibit association between the urea (and non-N-substituted carbamic acid ester), thereby making it easier for amines to approach the reaction sites

of the urea (and non-N-substituted carbamic acid ester) (which are presumed to be carbons that compose the carbonyl groups of the urea (and non-N-substituted carbamic acid ester)).

5 [0219] In the case of using an aromatic hydroxy composition for the reaction solvent, although an aromatic hydroxy compound may be used alone or mixed with other solvents, the amount of the aromatic hydroxy compound used is within the range of the previously described values. In the case of adding an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)) after having carried out step (A) in the presence of alcohol as well, the aromatic hydroxy composition is used within the previously described ranges. At that time, the amount of alcohol used during the reaction of step (A) is also used at the stoichiometric ratio indicated for the aromatic hydroxy compound based on the organic primary amine as previously described. In the case of using water in step (A), the water is preferably used together with an aromatic hydroxy composition and/or alcohol. Although water alone may be used as a solvent, it may be necessary to remove the water following completion of step (A). When an aromatic hydroxy compound in the amount described above is added to obtain a composition for transfer and storage of a compound having ureido groups by using a compound having ureido groups obtained in step (A), there are cases in which the reaction liquid separates into an aqueous phase and organic phase or the aromatic hydroxy compound and compound having ureido groups solidify. In addition, when step (R) or step (B) is carried out after adding the aromatic hydroxy compound in the amount described above following completion of step (A), a homogeneous liquid may be unable to be transferred or transfer pumps and lines may become clogged for the reasons described above. Thus, in the case of using only water for the solvent in step (A), the water is removed before or after adding the aromatic hydroxy compound. Although varying according to the compounds used and composition, water is removed until the amount of water is within a range of from 10 ppm to 10% by weight, preferably from 10 ppm to 5% by weight and more preferably from 10 ppm to 2% by weight in the reaction liquid (or mixed liquid) following removal thereof. The known method for removing water can be used for the water removal method, and examples of methods that can be used may preferably include removal by distillation at a reduced pressure or a normal pressure, the use of an adsorbent such as zeolite, the addition of a hydrolyzable compound such as an acetal followed by removal of water by a hydrolysis reaction, and removal of water with a compound that reacts with water in the manner of N,N-dicyclohexylcarbodiimide. Water is more preferably removed by distillation. In the case of using water together with an aromatic hydroxy composition and/or alcohol as a solvent in step (A), the amount of water in the reaction is within a range of from 10 ppm to 10% by weight, preferably from 10 ppm to 5% by weight, and more preferably from 10 ppm to 2% by weight. The inventors of the present invention surprisingly found that the reaction of step (A) demonstrates an improvement in reaction rate due to the presence of water. Thus, having water present during the reaction is a preferable method. Although the details of this effect have not been determined, it is presumed that the water demonstrates the effect of enhancing nucleophilicity of the organic primary amine.

20 [0220] There are no particular limitations on the reaction apparatus used when carrying out the reaction, and the known reactor can be used. For example, conventionally known reactors can be suitably combined, such as a stirring tank, a pressurized stirring tank, a depressurized stirring tank, a column type reactor, a distillation column, a packed column or a thin film distiller. A tank-type reactor provided with a stirrer is used preferably. There are no particular limitations on the material of the reactors, and known materials can be used. Examples thereof may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, a known method such as steam or a heater may be used for heating, and a known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of removing the ammonia formed, a step of purifying the organic primary amine, a step of dissolving the urea in the aromatic hydroxy compound, a step of dissolving the aromatic hydroxy compound, a step of separating the alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying the compound having ureido groups from the formed reaction liquid or a step of incinerating or discarding by-products and the like.

25 [0221] In the case of using a reaction solvent in step (A), the reaction solvent may be removed from the reaction liquid of step (A) when preparing the composition for transfer and storage of a compound having ureido groups to a desired composition or prior to carrying out step (B) or step (R), or the composition may be prepared or the step may be carried out without removing the reaction solvent. In particular, the hydroxy compound used as a reaction solvent in step (A) is preferably used as is as a portion of the hydroxy composition of step (B) or step (R).

30 [0222] Ammonia formed as a by-product in the step (A) may be recovered in the form of ammonia gas by introducing into a condenser provided in the reactor at a reduced pressure or a normal pressure, and condensing all or a portion of the hydroxy composition used in step (A) with a compound having carbonyl groups derived from urea.

35 [0223] In the present embodiment, by carrying out a process that includes a step of esterifying, or esterifying and transesterifying a compound having ureido groups (and preferably a compound having N-substituted ureido groups) and an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by formula

(2) (namely, a process that includes step (B) or step (R) and step (P)), examples of aspects of a method for producing at least one N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and the aromatic hydroxy composition (where the N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which an oxygen atom of the carbamic acid group (-NHCOO-) is bonded to an aromatic ring) include the five aspects indicated below if the method additionally includes a method for carrying out step (C). Other aspects are also possible based on the present embodiment, and the present embodiment is not limited to the five aspects indicated below.

[0224] Examples of aspects of the present embodiment may include the following five routes that are carried out after obtaining a compound having ureido groups or after obtaining at least one type of compound having ureido groups (or reaction liquid containing a compound having ureido groups) by carrying out step (A):

- route 1) method for carrying out step (B);
- route 2) method for carrying out step (B) and then step (C);
- route 3) method for carrying out step (R) and then step (P)
- route 4) method for carrying out step (R), step (P) and then step (C); and,
- route 5) method for carrying out step (R), step (C) and then step (P).

[0225] A method that includes step (B) is a method for obtaining N-substituted carbamic acid-O-aryl ester from a compound having ureido groups (or reaction liquid containing a compound having ureido groups) and an aromatic hydroxy composition by an esterification reaction, while a method that includes step (R) is a method for obtaining N-substituted carbamic acid-O-aryl ester by esterifying a compound having ureido groups and an alcohol to obtain an N-substituted carbamic acid-O-R² ester, and then transesterifying the N-substituted carbamic acid-O-R² ester and aromatic hydroxy composition in a step that includes step (P).

[0226] In either of the above-mentioned methods, N-substituted carbamic acid-O-aryl ester is obtained from the compound having the ureido groups (or after obtaining the same) and the aromatic hydroxy composition.

[0227] An explanation is first given of route 1).

<Route 1)>

[0228] Route 1) comprises a method for carrying out step (B).

[0229] Route 1) is a method for producing an N-substituted carbamic acid-O-aryl ester by reacting a compound having ureido groups and an aromatic hydroxy composition or from a composition for transfer and storage of a compound having ureido groups.

<Step (B)>

[0230] Step (B): A step of obtaining N-substituted carbamic acid-O-aryl ester by reacting the at least one type of compound having ureido groups and an aromatic hydroxy composition (composition containing at least one type or aromatic hydroxy compound represented by formula (2)) in a liquid phase and then extracting ammonia formed as a by-product to a gaseous phase (the reaction is an esterification reaction).

[0231] At least one type of compound having the ureido groups may be a compound having ureido groups produced using the known method provided it is the compound having ureido groups represented by formula (1). It is preferably at least one type of compound having ureido groups produced in step (A) or a reaction liquid containing at least one type of compound having ureido groups produced in step (A). The reaction liquid refers to the liquid resulting from completion of the reaction of step (A) and/or a reaction liquid to which has been added an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by formula (2)) after having carried out the reaction of step (A) in the presence of an alcohol or aromatic hydroxy composition, and represents a reaction liquid containing at least one type of compound having ureido groups and a hydroxy composition. Alternatively, a composition for transfer and storage of a compound having ureido groups as previously explained may be used in place of the reaction liquid containing at least one type of compound having ureido groups produced in the above-mentioned step (A), and this method is also one aspect of the present embodiment.

[0232] Step (B) may be a step of producing N-substituted carbamic acid-O-aryl ester by esterifying a compound having ureido groups and an aromatic hydroxy composition, and is a preferable aspect. FIG. 2 shows a conceptual drawing depicting the step (B).

[0233] The organic primary amine used in this route is an organic primary amine represented by formula (3), the compound having the ureido groups obtained in step (A) of this route is a compound having ureido groups represented by formula (1) derived from the organic primary amine, and the N-substituted carbamic acid-O-aryl ester obtained in step (B) of this route is an N-substituted carbamic acid-O-aryl ester represented by formula (43) derived from the compound having ureido groups. Indications of specific examples of each of these compounds are respectively contained

in previous explanations thereof.

5 [0234] As was previously described, in the case the hydroxy composition a used as a reaction solvent in step (A) is the same as the hydroxy composition of step (B) (namely, composition containing an alcohol represented by formula (4) and/or an aromatic hydroxy compound represented by formula (2) that contains the aromatic hydroxy composition used in step (B)), step (B) can be carried out as is by using the reaction liquid obtained in step (A). In addition, in the case the hydroxy composition a used as a reaction solvent in step (A) differs from the hydroxy composition of step (B), step (B) may be carried out after newly adding a hydroxy compound to the reaction liquid obtained in step (A), one or a plurality of types of hydroxy compounds may be newly added to the reaction liquid obtained in step (A) followed by carrying out step (B) after separating all or a portion of the hydroxy composition used as a reaction solvent of step (A), or step (B) may be carried out after removing all or a portion of the hydroxy composition used as a reaction solvent in step (A) followed by newly adding one or a plurality of types of hydroxy compounds. Herein, the newly added hydroxy compound is an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the above-mentioned formula (2).

10 [0235] Among these, the aromatic hydroxy composition used in step (B) is preferably an aromatic hydroxy composition containing an aromatic hydroxy compound represented by formula (7) or formula (31), and more preferably an aromatic hydroxy composition containing an active aromatic hydroxy compound, and even more preferably an aromatic hydroxy composition represented by formula (32) and even more preferably by formula (38) in order to conduct step (B). As was previously described, a method for producing N-substituted carbamic acid-O-alkyl ester by using a compound having ureido groups and reacting with alcohol is disclosed in Japanese Patent Application Laid-open No. H6-41045. As was previously explained, this N-substituted carbamic acid-O-alkyl ester is susceptible to thermal denaturation and easily forms a compound having ureylene groups. In addition, if the N-substituted carbamic acid-O-alkyl ester is subjected to thermal decomposition in an attempt to produce isocyanate, the thermal decomposition temperature becomes high and a reverse reaction of the thermal decomposition reaction occurs easily. As a result of studies conducted by the inventors of the present invention, in the case of obtaining N-substituted carbamic acid-O-aryl ester by reacting a compound having ureido groups and an aromatic hydroxy compound, it was found that N-substituted carbamic acid-O-aryl ester can be obtained at high yield without undergoing thermal denaturation.

15 [0236] There are no particular limitations on the method for separating the reaction solvent used in step (A), and although a known method such as distillative separation, membrane separation or extraction separation can be used, distillative separation is preferable. In the case of carrying out step (B) after having carried out step (A), there are cases in which step (A) is preferably carried out in the presence of an aromatic hydroxy composition, and there are also cases in which step (A) is preferably carried out in the absence of alcohol and in the presence of an aromatic hydroxy composition. As was previously described, in the case of using a compound having ureido groups for the starting raw material as well, there are many cases in which N-substituted carbamic acid-O-alkyl ester is susceptible to thermal denaturation. As a result of studies conducted by the inventors of the present invention, even if an alcohol is used in step (A) and a trace amount of N-substituted carbamic acid-O-R² ester is formed in step (B), denaturation was found to be significantly inhibited even in the presence of an aromatic hydroxy composition.

20 [0237] In the case of carrying out step (B) in the presence of alcohol, since there are cases in which a trace amount of N-substituted carbamic acid-O-R² ester is formed together with N-substituted carbamic acid-O-aryl ester, the alcohol is preferably removed before carrying out step (B) or simultaneous to carrying out step (B). Since N-substituted carbamic acid-O-R² ester is a compound that has a higher thermal decomposition temperature when carrying out step (F) as compared with N-substituted carbamic acid-O-aryl ester, in the case of route 1) or route 2) that includes step (B), alcohol is preferably not used in step (A) whenever possible (namely, alcohol is not used throughout the entire step) to inhibit the amount of N-substituted carbamic acid-O-R² ester formed.

25 [0238] Although varying according to the compounds reacted, the reaction conditions for producing N-substituted carbamic acid-O-aryl ester by reacting a compound having ureido groups and an aromatic hydroxy composition of step (B) are such that the amount of aromatic hydroxy compound in the aromatic hydroxy composition used has a stoichiometric ratio within a range of from 1 to 500 times based on the ureido groups of the compound having ureido groups used. Although it is preferable to use an excess of aromatic hydroxy compound since complexly substituted carbonyl compounds and high molecular weight compounds having carbonyl bonds in molecules thereof form easily if the stoichiometric ratio is less than 1 time, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 1 to 100 times, more preferably within a range of from 2 to 50 times and even more preferably within a range of from 3 to 20 times.

30 [0239] Although varying according to the compounds used, the reaction temperature is preferably within a range of from 100 to 350°C. If the temperature is lower than 100°C, the reaction slows or the reaction hardly proceeds at all, or complexly substituted carbonyl compounds increase, thereby making this undesirable. On the other hand, at temperatures higher than 350°C, the N-substituted carbamic acid-O-aryl ester either remains in step (A), the urea (and non-N-substituted carbamic acid ester) formed in the system of step (B) decompose, the hydroxy composition is subjected to dehydrogenative denaturation, or decomposition and denaturation reactions of the product in the form of N-substituted car-

bamic acid-O-aryl ester occur easily, thereby making this undesirable. From such viewpoints, the reaction temperature is more preferably within a range of from 120 to 320°C and even more preferably within a range of from 140 to 300°C.

[0240] As has been previously described, the reaction by which N-substituted carbamic acid-O-aryl ester is formed is an equilibrium reaction, and since the reaction is biased towards the reactants side, the reaction is preferably carried out while removing ammonia formed as a by-product outside the system as much as possible. Ammonia is preferably removed so that the ammonia concentration in the reaction liquid is preferably 1000 ppm or less, more preferably 300 ppm or less, even more preferably 100 ppm or less and most preferably 30 ppm or less (being contained in the reaction liquid refers to being contained in a liquid phase when carrying out the step (B)). Ammonia can be removed using methods such as reactive distillation, use of an inert gas, membrane separation and adsorptive separation. For example, the reactive distillation refers to a method for separating continuously formed ammonia during the reaction by distillation in the form of a gas. This can be carried out while boiling an aromatic hydroxy compound, solvent or hydroxy composition in order to increase the distillation efficiency of the ammonia. In addition, a method using an inert gas refers to a method for separating continuously formed ammonia during the reaction from the reaction system in the form of a gas along with the inert gas. Examples of inert gases used may include nitrogen, helium, argon, carbon dioxide, methane, ethane and propane, these may be used alone or as a mixture, and a method in which the inert gas is introduced into the reaction system is preferable. Examples of adsorbents used in methods using adsorptive separation may include adsorbents able to be used under the temperature conditions at which the reaction is carried out, such as silica, alumina, various types of zeolite or diatomaceous earth. These methods for removing ammonia outside the system may be carried out alone or a plurality of types may be carried out in combination.

[0241] A catalyst can be used in the reaction for the purpose of increasing the reaction rate, for example. Examples of catalysts that are used preferably may include basic catalysts such as methylates, ethylates or butyrates (including isomers) of lithium, sodium, potassium, calcium or barium, rare earth elements, antimony or bismuth alone or oxides, sulfides and salts thereof, boron alone or boron compounds, metals of the copper family, zinc family, aluminum family, carbon family and titanium family in the periodic table as well as metal oxides and sulfides thereof, and carbides and nitrides of elements of the carbon family excluding carbon, titanium family, vanadium family and chromium family in the periodic table. Although there are no particular limitations on the amount of catalyst used in the case of using a catalyst, a catalyst can be used within a range of a stoichiometric ratio of from 0.0001 to 100 times the ureido groups of the compound having ureido groups. Since there are many cases in which it is necessary to remove the catalyst if a catalyst is added, the reaction is preferably carried out without adding a catalyst.

[0242] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus and the like, the reaction pressure is generally within a range of from 0.01 Pa to 10 MPa (absolute pressure), and in consideration of ease of industrial application, the reaction pressure is more preferably within a range of from 0.1 Pa to 5 MPa (absolute pressure), and in consideration of removing gaseous ammonia outside the system, even more preferably from 0.1 Pa to 1.5 MPa (absolute pressure).

[0243] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus, reaction pressure and the like, the reaction time (residence time in the case of a continuous reaction) is generally from 0.01 to 100 hours. The reaction time can also be determined according to the formed amount of the target compound in the form of N-substituted carbamic acid-O-aryl ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-R² ester). For example, the reaction may be stopped after having sampled the reaction liquid, determined the content of N-substituted carbamic acid-O-aryl ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-R² ester) in the reaction liquid and confirming that the N-substituted carbamic acid-O-aryl ester has been formed at a yield of 10% or more based on the compound having ureido groups, or the reaction may be stopped after having confirmed that the yield is 90% or more. Isocyanate is obtained by applying the reaction liquid containing the N-substituted carbamic acid-O-aryl ester in step (B) to the thermal decomposition reaction in step (F). At this time, if the content of N-substituted carbamic acid-O-aryl ester is low (namely, yield is low) in step (B), a decrease in the yield of isocyanate may result. Thus, the yield is preferably 50% or more, more preferably 80% or more and even more preferably 90% or more.

[0244] Although the use of a reaction solvent is not necessarily required in the reaction, a suitable solvent is preferably used as a reaction solvent for the purpose of facilitating the reaction procedure, examples of which include alkanes such as pentane, hexane, heptane, octane, nonane or decane; aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene, ethyl benzene, diisopropyl benzene, dibutyl benzene or naphthalene; nitrile compounds such as acetonitrile or benzonitrile; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene, bromobenzene, dibromobenzene, chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene; aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as tetrahydrofuran, 1,4-dioxane,

1,2-dimethoxyethane, diphenyl ether or diphenyl sulfide; ketone compounds such as acetone or methyl ethyl ketone; ester compounds such as ethyl acetate or ethyl benzoate; and sulfoxides such as dimethylsulfoxide or diphenylsulfoxide. Naturally, a hydroxy composition used in excess in the reaction is also preferably used as a reaction solvent.

5 [0245] The reaction is carried out in a system having a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea (a compound that inherits a carbonyl group possessed by urea, such as a non-N-substituted carbamic acid ester or biuret, which refers to a compound excluding N-substituted carbamic acid-O-esters) and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out. Although the majority of the reaction is carried out in the liquid phase, it may also be carried out in the gaseous phase depending on the reaction conditions. At that time, the volumetric content of the liquid phase in the reaction in which the reaction is carried out is preferably 50% or less. In the case of carrying out the reaction continuously over a long period of time, although polymeric by-products may form due to fluctuations in operating conditions (such as temperature or pressure) and the like, if the volumetric content of the liquid phase in the reactor is high, adhesion and accumulation of such polymeric by-products in the reactor can be avoided. However, since the efficiency of removal of by-product ammonia may become poor and the yield of the N-substituted carbamic acid-O-aryl ester may decrease if the volumetric content of the liquid phase is excessively high, the volumetric content of the liquid phase based on the gaseous phase is preferably 50% or less, more preferably 30% or less and even more preferably 20% or less (the volumetric content of the liquid phase refers to volumetric ratio of the liquid phase based on the volume of the reaction tank in the case of a tank-type reactor, the volume of the stage lower than the feed stage (not including the tank bottom and reboiler) in the case of a column-type reactor, or the volume of the thin film distiller in the case of a thin film distiller).

20 [0246] Although there are no particular limitations on the reaction apparatus used when carrying out the reaction and a known reactor can be used, a tank-type and/or column-type reactor is used preferably. The reactor used is preferably equipped with a condenser.

25 [0247] As was previously described, the reaction is preferably carried out in a system containing a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out under conditions such that the volumetric content of the liquid phase in the reactor in which the reaction is carried out is 50% or less, and a reactor that satisfies these conditions is selected for the reactor in which the reaction is carried out.

30 [0248] More specifically, conventionally known reactors can be suitably combined and used, examples of which may include a stirring tank, a pressurized stirring tank, a depressurized stirring tank, a column-type reactor, a distillation column, a packed column or a thin film distiller.

35 [0249] There are no particular limitations on the type of condenser provided in the reactor and the known condenser can be used. For example, conventionally known condensers such as a multitubular cylindrical condenser, a double tube condenser, a single tube condenser or an air-cooled condenser can be suitably combined and used. The condenser may be provided inside the reactor or outside the reactor, or may be connected with the reactor by a line, and various types can be employed in consideration of the forms of the reactor and condenser, the manner in which condensed liquid is handled and the like.

40 [0250] There are no particular limitations on the materials of the reactor and condenser and known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, a known method such as steam or a heater may be used for heating, and a known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving the compound having ureido groups in the aromatic hydroxy composition, a step of dissolving the aromatic hydroxy compound, a step of separating alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying N-substituted carbamic acid-O-aryl ester from the formed reaction liquid, or a step of incinerating or discarding by-products and the like.

45 [0251] Step (B) is a step of producing N-substituted carbamic acid-O-aryl ester by reacting a compound having ureido groups and an aromatic hydroxy composition in a liquid phase using a reactor (equipped with a condenser). The gaseous component formed in the step (B) containing a compound having carbonyl groups derived from urea and ammonia formed as a by-product in the reaction is introduced into the condenser provided in the reactor and all or a portion of the aromatic hydroxy composition and compound having carbonyl groups derived from urea are condensed followed by recovery of ammonia in the form of a gas. At that time, the compound having carbonyl groups derived from urea that is contained in ammonia recovered as a gas from the condenser is present at a specific amount or less. Namely, the ratio of the number of carbonyl groups (-C(=O)-) contained in the compound having carbonyl groups derived from urea contained in the ammonia to the number of ammonia molecules is 1 or less, preferably 0.5 or less, more preferably 0.1 or less and even more preferably 0.01 or less. The reason for making the amount of the compound having carbonyl

groups derived from urea contained in the ammonia to be within a specific range is to avoid adhesion and accumulation of solid components in the line for transferring ammonia from the condenser.

[0252] Although all solid components that adhere and accumulate in the line for transferring ammonia cannot be identified, as a result of studies conducted by the inventors of the present invention, the majority were determined to be compounds having carbonyl groups. Although one possible method for avoiding adhesion and accumulation of such solid components contains heating the line for transferring ammonia to decompose compounds having carbonyl groups, according to studies conducted by the inventors of the present invention, there are many cases in which heating alone causes polymerization of decomposition products (such as isocyanic acid) or reaction with other compounds having carbonyl groups, thereby making it difficult to completely avoid adhesion and accumulation of solid components. In addition, in the case of simply heating the line, it was determined that compounds having carbonyl groups contained in the ammonia and their decomposition products solidify as a result of being rapidly cooled at the outlet of the line for transferring ammonia (such as the portion in contact with the atmosphere), thereby frequently resulting in prominent adhesion and accumulation of solid components. As a result of conducting extensive studies regarding this problem, the inventors of the present invention surprisingly found that the problem of adhesion and accumulation of solid components can be solved by making the amount of the compound having carbonyl groups derived from carbonic acid derivative contained in the ammonia to be equal to or less than the specific amount described above. Although the mechanism by which this effect is demonstrated is unclear, the inventors of the present invention surmised that adhesion and accumulation in the line is caused by the compound having carbonyl groups derived from the carbonic acid derivative itself as well as decomposition and/or polymerization products of the compound having carbonyl groups derived from the carbonic acid derivative, and that by making the amount of carbonyl groups contained in the compound having carbonyl groups derived from the carbonic acid derivative equal to or less than a specific concentration, adhesion of the compound having carbonyl groups derived from the carbonic acid derivative itself as well as the reaction rates of decomposition and/or polymerization of that compound are lowered considerably.

[0253] On the other hand, the condensed aromatic hydroxy composition and compound having carbonyl groups derived from urea are made to be such that the stoichiometric ratio of the condensed aromatic hydroxy composition to the condensed compound having carbonyl groups derived from urea is 1 or more, preferably 2 or more and more preferably 3 or more. The reason for defining such ranges is to enable a mixture of the aromatic hydroxy composition and compound having carbonyl groups derived from urea condensed in the condenser to be in the form of a homogeneous liquid mixture. As a result, not only is handling of the mixture easier, but occurrence of problems such as adhesion and accumulation of solid components in the condenser can be avoided.

[0254] Moreover, in step (B) the mixture of the aromatic hydroxy composition and the compound having carbonyl groups derived from urea condensed by the condenser may be circulated within the reactor and reused in the reaction of step (A). At that time, the concentration of ammonia contained in the mixture is preferably 5000 ppm or less, more preferably 3000 ppm or less and even more preferably 2000 ppm or less.

[0255] As has been described above, although various compounds are recovered in the form of compounds having carbonyl groups derived from urea, there are no particular limitations on the reuse of these compounds.

<Route 2>

[0256] Route 2) is a method for carrying out step (B) followed by carrying out step (C). Route 2) is one aspect of the method indicated in route 1).


[0257] The method of route 2) is a method for obtaining N-substituted carbamic acid-O-aryl ester from the N-substituted carbamic acid-O-aryl ester of step (B) in which the organic primary amine is an aromatic organic primary monoamine represented by the following formula (5), the following step (C) is carried out after step (B), and at least two molecules of the N-substituted carbamic acid-O-aryl ester are crosslinked with methylene groups (-CH₂-). Preferably, the aromatic hydroxy compound constituting the aromatic hydroxy composition used in step (A) and /or step (B) is an aromatic monohydroxy compound.

[0258] Step (C): a step of obtaining N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with methylene groups (-CH₂-), by reacting the N-substituted carbamic acid-O-(R² or aryl) ester with formaldehyde or a methylenating crosslinking agent and crosslinking aromatic groups derived from the aromatic organic primary monoamine contained in the N-substituted carbamic acid-O-(R² or aryl) ester with the methylene groups (-CH₂-)

[0259] The N-substituted carbamic acid-O-R² ester in the route 2) represents an N-substituted carbamic acid-O-R² ester formed as a by-product in the case of using an alcohol in step (A) and/or step (B).

[0260] In this route, step (A) is carried out using an organic primary amine represented by the following formula is used for the organic primary amine to obtain a compound having ureido groups derived from the organic primary amine, after which step (B) is carried out to obtain N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups, followed by carrying out step (C). Namely, the organic primary amine used in this route is an organic


primary amine represented by formula (5), the compound having ureido groups obtained in step (A) of this route is a compound having ureido groups represented by formula (41) derived from the organic primary amine, and more specifically a compound having ureido groups represented by formula (148), and the N-substituted carbamic acid-O-aryl ester obtained in step (B) of this route is an N-substituted carbamic acid-O-aryl ester represented by formula (43) derived from the compound having ureido groups, and more specifically an N-substituted carbamic acid-O-aryl ester represented by the following formula (149). Indications of specific examples of each of these compounds are respectively contained in previous explanations thereof.



15 (wherein

at least one location at the ortho position and/or para position of the NH₂ group of an aromatic organic primary monoamine represented by formula (5) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the aromatic organic primary monoamine represented by formula (5) is an integer of from 6 to 13).


25 **[0261]** In this case, the compound having ureido groups obtained in step (A) is at least one type of compound having ureido groups represented by the following formula (148). In addition, the groups R³, R⁴, R⁵ and R⁶ in the following formula (148) are selected from the groups R³, R⁴, R⁵ and R⁶ of an organic primary amine represented by the above-mentioned formula (5), and the compound having ureido groups is a compound in which amino groups (-NH₂ groups) of the organic primary amine represented by formula (5) are in the form of ureido groups (-NH-CO-NH₂):



40 (wherein

at least one location at the ortho position and/or para position of the ureido group of an N-substituted aromatic organic monourea represented by formula (148) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the N-substituted aromatic organic monourea represented by formula (148), excluding ureido groups (-NH-CO-NH₂), is an integer of from 6 to 13).

50 **[0262]** In this case, the N-substituted carbamic acid-O-aryl ester obtained in step (B) is at least one type of N-substituted carbamic acid-O-aryl ester represented by the following formula (149). In addition, the groups R³, R⁴, R⁵ and R⁶ in the following formula (149) are selected from the groups R³, R⁴, R⁵ and R⁶ of an organic primary amine represented by the above-mentioned formula (5), and the compound is a compound in which ureido groups (-NH-CO-NH₂) of a compound having ureido groups represented by formula (148) are in the form of carbamic acid-O-aryl ester groups:



(149)

(wherein

groups R^3 to R^6 are the groups indicated above).

[0263] In steps (A) and (B) of this route, the organic primary amine used is an organic primary amine represented by formula (5), and steps (A) and (B) of this route are carried out under the conditions of steps (A) and (B) of route 1).

[0264] Step (C) is a step of obtaining N-substituted carbamic acid-O-(R^2 or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R^2 or aryl) ester are crosslinked with methylene groups ($-CH_2-$), by crosslinking

at least one type of N-substituted carbamic acid-O-aryl ester (or reaction liquid containing the same) obtained in step (B) with methylene groups ($-CH_2-$). As a result of carrying out step (C), N-substituted carbamic acid-O-aryl ester is

obtained in which at least two molecules of at least one type of N-substituted carbamic acid-O-aryl ester represented by the following formula (150) are crosslinked with the methylene groups ($-CH_2-$). Herein, when carrying out route 2),

an aromatic hydroxy composition containing an aromatic monohydroxy compound is preferably used for the aromatic hydroxy compound used in step (A) and/or step (B) as previously described (namely, an aromatic hydroxy compound

in which $b=1$ in the aromatic hydroxy compound represented by formula (2)). Although a polyvalent aromatic hydroxy compound may be used, crosslinking may occur at locations other than the desired locations at that time. In the following


formula (150), in the case of using the above-mentioned aromatic monohydroxy compound (namely in the case $b=1$), ring A of the following formula does not have other aromatic hydroxy groups or alcoholic hydroxy groups. An aromatic

hydroxy compound represented by the above-mentioned formula (31) is preferable for the aromatic monohydroxy compound, the case of using an active aromatic hydroxy compound, of the active aromatic hydroxy compounds, represented

by formula (38) is more preferable, and the case of using an aromatic hydroxy compound represented by formula (38), in which groups R^{26} and R^{27} are hydrogen atoms while other substituents are linear and/or cyclic saturated alkyl groups,

or the case of being naphthol (including isomers), phenoxyphenol (including isomers) or diphenoxyphenol (including isomers), in which the ortho position or para position of the hydroxy group is not substituted, is even more preferable.

[0265] Although compounds in which m is an integer from 0 to 6 are represented by the formula (150), this value can be adjusted according to the amount used and reaction rate of the methylenating crosslinking agent that is reacted (to be subsequently explained and frequently referred to as a methylenating agent):



(150)

(wherein

R^1 represents a group derived from an organic primary amine as previously defined,

ring A represents a group derived from an aromatic hydroxy compound that composes an aromatic hydroxy composition as previously defined, and which represents a residue in which one hydrogen atom of hydroxyl groups directly bonded to an aromatic hydrocarbon ring has been removed from the aromatic hydroxy compound,

groups R^3 to R^6 represent groups as previously defined, and

m represents an integer of from 0 to 6).

[0266] Although a monoisocyanate can be produced by applying the N-substituted carbamic acid-O-mono(aryl ester) represented by the above-mentioned formula (149) to a thermal decomposition reaction as is, when considering that isocyanates are typically used in applications such as paint and polyurethane, the isocyanate is preferably a polyfunctional isocyanate. Thus, a method can be carried out in which, after having preliminarily polymerized the N-substituted carbamic acid mono (aryl ester) by the above-mentioned step (C), the polymer is applied to a thermal decomposition reaction to

obtain a polyfunctional isocyanate. The above-mentioned N-substituted carbamic acid-O-mono(aryl ester) refers to an N-substituted carbamic acid-O-aryl ester having one carbamic acid-O-aryl ester group in a molecule thereof.

[0267] The following provides an explanation of the step (C). In the following explanation, the N-substituted carbamic acid-O-aryl ester having one carbamic acid-O-aryl ester group in a molecule thereof is referred to as a monofunctional N-substituted carbamic acid-O-aryl ester.

[0267] The following provides an explanation of the step (C). In the following explanation, the N-substituted carbamic acid-O-aryl ester having one carbamic acid-O-aryl ester group in a molecule thereof is referred to as a monofunctional N-substituted carbamic acid-O-aryl ester.

acid-O-aryl ester obtained in step (B) of route 2) is frequently indicated as N-substituted carbamic acid-O-mono(aryl ester) or N-substituted carbamic acid monoaryl ester.

[0268] The known method (see, for example, Federal Republic of Germany Patent No. 1042891) can be used for the step (C).

[0269] Prior to carrying out step (C), the aromatic hydroxy composition obtained in step (B) is separated from the reaction liquid containing the resulting N-substituted carbamic acid-O-aryl ester. Although step (C) may be carried out in the presence of an aromatic hydroxy compound, since the aromatic hydroxy compound may be crosslinked by the methylenating crosslinking agent resulting in the formation of by-products such as polyaromatic hydroxy compounds, or the amount of methylenating crosslinking agent used may increase, aromatic hydroxy compounds are preferably separated. The known method can be used for the separation method, and although varying according to the compounds used, examples of separation methods that can be used may include a distillation method, an extraction separation method that uses the difference in solubility between the N-substituted carbamic acid-O-aryl ester and aromatic hydroxy compound, and a filtration method carried out by solidifying either the N-substituted carbamic acid-O-aryl ester or aromatic hydroxy compound. Although these methods cannot be indicated specifically since they depend on the respective physical properties of the compounds used, the method and conditions thereof can be adequately selected within the scope of knowledge of a person with ordinary skill in the art.

[0270] When carrying out step (C), the aromatic hydroxy compound is removed until the amount of aromatic hydroxy compound present following the above-mentioned separation procedure is a stoichiometric ratio of 1 time or less, preferably 0.5 times and more preferably 0.1 times based on the N-substituted carbamic acid-O-aryl ester. At this time, the aromatic hydroxy compound may be removed in the presence of solvent used in step (C) to be subsequently explained.

[0271] Examples of methylenating crosslinking agents preferably used in the step (C) may include formaldehyde, paraformaldehyde, trioxane, dialkoxymethanes having a lower alkyl group having 1 to 6 carbon atoms (such as dimethoxymethane, diethoxymethane, dipropoxymethane, dipentanoxymethane or dihexyloxymethane), and diacyloxymethanes having a lower carboxyl group such as diacetoxymethane or dipropioxymethane. These may be used alone or two or more types may be used as a mixture. Among these methylenating crosslinking agents, aqueous solutions of formaldehyde are particularly preferable in consideration of cases of industrial application, ease of handling of the methylenating crosslinking agent and the like.

[0272] In carrying out the reaction of the step (C), although there are no particular limitations on the ratio of N-substituted carbamic acid-O-mono(aryl ester) to methylenating crosslinking agent, the N-substituted carbamic acid-O-monoaryl ester is preferably used at a stoichiometric ratio of from 2 to 20 times the methylenating crosslinking agent. Although the formation of polynuclear forms (referring to N-substituted carbamic acid-O-aryl esters in which three or more aromatic rings (aromatic rings derived from organic primary amine) are bonded by a methylene crosslinked structure, or in other words, compounds in which m is an integer of from 1 or more in the above-mentioned formula (150)) is inhibited the greater the amount of N-substituted carbamic acid-monoaryl ester used, if an overly excessive amount of N-substituted carbamic acid-O-monoaryl ester is used, there are many cases in which the remaining amount of raw material N-substituted carbamic acid-O-mono(aryl ester) increases. Thus, the amount of N-substituted carbamic acid-O-monoaryl ester used in terms of the stoichiometric ratio with the methylenating crosslinking agent is more preferably within a range of from 3 to 15 times and even more preferably within a range of from 5 to 10 times.

[0273] An acid catalyst is preferably used as a catalyst in the condensation reaction. Examples of acid catalysts may include inorganic acids such as hydrochloric acid, sulfuric acid, phosphoric acid or boric acid, and organic acids such as formic acid, acetic acid, oxalic acid or toluenesulfonic acid. In addition, acids referred to as super strong acids such as hydrobromic acid, perchloric acid, chlorosulfonic acid or trifluoromethanesulfonic acid are also effective. In addition, ion exchange resins having acidic groups such as carboxyl groups or sulfonate groups as well as acids referred to as Lewis acids, such as trifluoroboric acid, iron chloride, aluminum chloride, zinc chloride or titanium chloride, are also effective.

[0274] In the case of a protonic acid such as the above-mentioned inorganic acids, organic acids or super strong acids, the amount of these acids used is within a range of a stoichiometric ratio of from 0.001 to 10, and preferably within a range of from 0.01 to 5, based on the raw material N-substituted carbamic acid ester. In addition, in the case these acids are used in the form of aqueous solutions, they can be used at a concentration within a range of from 10 to 95% by weight and preferably within a range of from 20 to 80% by weight based on the amount of water in the reaction system. If the concentration is less than 10% by weight, the reaction rate of the condensation reaction becomes extremely slow, while if the concentration exceeds 95% by weight, hydrolysis of the raw material and other undesirable side reactions may occur.

[0275] The condensation reaction can be carried out in the presence or absence of solvent. Examples of solvents that are used preferably may include linear, branched or cyclic hydrocarbons such as pentane, hexane, heptane, octane, nonane, decane, hexadecane, cyclopentane or cyclohexane; aromatic hydrocarbons such as benzene, toluene or xylene and their alkyl-, halogen- and nitro-substituted forms; halogenated hydrocarbons such as chloroform, methylene chloride, carbon tetrachloride, dichloroethane, trichloroethane or tetrachloroethane; aliphatic alkyl esters such as methyl acetate

or ethyl acetate; and ethers such as diethyl ether, diisopropyl ether, dioxane or tetrahydrofuran. In addition, thioacetals, acetals or acylals are used preferably since they do not form free formaldehyde under the reaction conditions and do not substantially form water by reacting with water formed as a by-product in the reaction. Acetals and acylals are used particularly preferably. In addition, the above-mentioned acids themselves are also preferably used as solvents. These

solvents may be used alone or two or more types may be used as a mixture.

[0276] These solvents can be used at a weight ratio within a range of from 0.1 to 100 times and preferably within a range of from 0.2 to 50 times based on the raw material N-substituted carbamic acid-O-monoaryl ester.

[0277] The reaction temperature is preferably from 10 to 160°C, more preferably from 20 to 140°C and even more preferably from 50 to 120°C. Although the reaction is advantageously carried out at a high temperature in order to increase the reaction rate and complete the reaction quickly, an excessively high temperature may cause undesirable side reactions such as hydrolysis.

[0278] Although varying according to the reaction method, compounds used and reaction conditions, the reaction time can be within a range of from 1 minute to 20 hours. In addition, the reaction may be terminated when the reduction in the amount of raw material N-substituted carbamic acid-O-monoaryl ester has reached a certain level by sampling the reaction liquid and using the known analytical method such as liquid chromatography, or the reaction may be terminated when the average molecular weight of the product in the form of N-substituted carbamic acid-O-aryl ester has reached a certain level by using the known analytical method such as gel permeation chromatography.

[0279] The N-substituted carbamic acid-O-aryl ester obtained by the method described above is an N-substituted carbamic acid-O-aryl ester represented by the above-mentioned formula (150). Although those N-substituted carbamic acid-O-aryl esters in which m is 0 are preferable in consideration ease of handling and particularly solution viscosity and the like, there are no problems with containing trinuclear or larger polynuclear forms (namely, compounds represented by formula (150) in which m is 1 or more) provided they do not contradict the purport of the present embodiment.

[0280] The N-substituted carbamic acid-O-aryl ester obtained in step (C) is preferably used in step (F).

[0281] Compounds remaining in the reaction liquid of step (C) may be removed from the reaction liquid (such as the methylenating agent, reaction solvent or catalyst used in step (C)). The known method can be used for the removal method, and although examples of such methods may include membrane separation, distillative separation and crystallization, distillative separation is preferable. In the case of removing a compound remaining in the reaction liquid of step (C) by distillative separation, by adding the aromatic hydroxy composition used in the subsequent step (F) to the reaction liquid of step (C) to obtain a mixed liquid, followed by removing the compounds remaining in the reaction liquid of step (C) (such as the methylenating agent, reaction solvent or catalyst used in step (C)) from the mixed liquid, distillative separation can be carried out without causing precipitation of the N-substituted carbamic acid ester, thereby making this method preferable.

[0282] Although caution is required with respect to the materials of the reactor and the condenser since an acid is used in step (C), there are no particular limitations on the materials provided they do not cause problems such as corrosion attributable to the compounds used in step (C), and known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary, and for example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added.

<Route 3>

[0283] Route 3) is a route that includes a method for carrying out step (R) followed by carrying out step (P).

[0284] First, N-substituted carbamic acid-O-R² ester is obtained in step (R) using a compound having ureido groups, after which the N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition are reacted in step (P) to obtain N-substituted carbamic acid-O-aryl ester. Alternatively, a compound having ureido groups (or reaction liquid containing the same) is obtained in step (A) and step (R) is carried out using the compound having ureido groups (or reaction liquid containing the same) followed by carrying out step (P) to obtain N-substituted carbamic acid-O-aryl ester.

<Step (R)> N-substituted Carbamic Acid-O-R² Ester Production Step

[0285] Step (R) is a step of producing N-substituted carbamic acid-O-R² ester by reacting a compound having ureido groups with alcohol. Alternatively, N-substituted carbamic acid-O-R² ester is produced by reacting (esterifying) a compound having ureido groups (or reaction liquid containing the same) obtained in step (A) with an alcohol.

[0286] FIG. 3 is a conceptual drawing depicting the step (R).

[0287] The compound having ureido groups obtained in step (A) of this route is a compound having ureido groups

represented by formula (1) that is derived from the organic primary amine, the N-substituted carbamic acid-O-R² ester obtained in step (R) of this route is an N-substituted carbamic acid-O-R² ester represented by formula (49) that is derived from the compound having ureido groups and an alcohol, and the N-substituted carbamic acid-O-aryl ester obtained in step (P) of this route is an N-substituted carbamic acid-O-aryl ester represented by formula (43) that is derived from the N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition.

[0288] As was previously stated, in the case the hydroxy composition a used as a reaction solvent in step (A) is the same as the hydroxy composition of step (R) (namely, a composition containing an alcohol represented by formula (4), including the alcohol represented by formula (4) used in step (R), and/or an aromatic hydroxy compound represented by formula (2)), step (R) can be carried out directly by using the reaction liquid obtained in step (A). In addition, in the case the hydroxy composition a used as a reaction solvent in step (A) differs from the hydroxy composition of step (R), step (R) may be carried out after newly adding a hydroxy compound (alcohol represented by formula (4) and/or aromatic hydroxy compound represented by formula (2)) to the reaction liquid obtained in step (A), one or a plurality of types of hydroxy compounds may be newly added to the reaction liquid obtained in step (A) followed by carrying out step (R) after separating all or a portion of the hydroxy composition used as a reaction solvent of step (A), or step (R) may be carried out after removing all or a portion of the hydroxy composition used as a reaction solvent in step (A) followed by newly adding one or a plurality of types of hydroxy compounds. Herein, the newly added hydroxy compound is an alcohol represented by formula (4) and/or an aromatic hydroxy composition. There are no particular limitations on the method for separating the reaction solvent used in step (A), and although the known method such as distillative separation, membrane separation or extraction separation can be used, distillative separation is preferable. In the case of carrying out step (R) after having carried out step (A), there are cases in which step (A) is preferably carried out in the presence of an alcohol, and there are also cases in which step (A) is preferably carried out in the absence of an aromatic hydroxy composition and in the presence of alcohol. In the case of carrying out step (R) in the presence of an aromatic hydroxy compound, although there are cases in which a trace amount of N-substituted carbamic acid-O-aryl ester is formed together with N-substituted carbamic acid-O-R² ester, in the method for producing N-substituted carbamic acid-O-aryl ester of the present embodiment, after carrying out step (R) this does not present any problem whatsoever since the N-substituted carbamic acid-O-R² ester is converted to N-substituted carbamic acid-O-aryl ester by carrying out a step (P) to be subsequently explained.

[0289] As was previously described, with respect to a method for producing N-substituted carbamic acid-O-alkyl ester by using a compound having ureido groups and reacting with alcohol, a method that coincides with the objective of obtaining a corresponding isocyanate and alcohol by thermal decomposition of the N-substituted carbamic acid-O-alkyl ester is disclosed in Japanese Patent Application Laid-open No. H6-41045. As was previously explained, this method is susceptible to the formation of by-products when obtaining a compound having ureido groups, contains a range over which in which a large amount of N-substituted carbamic acid-O-alkyl ester is simultaneously formed, and the N-substituted carbamic acid-O-alkyl ester is susceptible to thermal denaturation causing compounds having ureylene groups to be easily formed. In addition, if isocyanate is attempted to be produced by thermally decomposing the N-substituted carbamic acid-O-alkyl ester, the thermal decomposition temperature becomes higher resulting in increased susceptibility to a reverse reaction of the thermal decomposition reaction and increased susceptibility to the occurrence of clogging of the thermal decomposition reactor. As a result of studies conducted by the inventors of the present invention, in the case of obtaining N-substituted carbamic acid-O-aryl ester by reacting a compound having ureido groups and an aromatic hydroxy compound, it was found that N-substituted carbamic acid-O-aryl ester can be obtained at high yield with little thermal denaturation.

[0290] On the other hand, although there are many cases in which compounds having ureylene groups and the like are formed as by-products even in cases of obtaining N-substituted carbamic acid-O-R² ester from a compound having ureido groups and alcohol, when obtaining N-substituted carbamic acid-O-R² ester from a compound having ureido groups and alcohol, it was found that the formation of by-products can be inhibited considerably if an aromatic hydroxy compound is present. Although this is thought to be due to association of the compound having ureido groups inhibiting the aromatic hydroxy compound thereby inhibiting side reactions, such a finding is not present in the prior art and is an effect that was first discovered by the inventors of the present invention. Thus, although depending on the particular case, step (R) is preferably carried out in the presence of an aromatic hydroxy composition or aromatic hydroxy compound when carrying out step (R) as well. In this case, the aromatic hydroxy composition or aromatic hydroxy compound is selected from aromatic hydroxy compounds represented by formula (2), and is preferably an aromatic hydroxy compound represented by formula (7), and more preferably an aromatic hydroxy compound represented by formula (31). Although a preferable method for using a plurality of types of aromatic hydroxy compounds will be subsequently explained, the aromatic hydroxy compound or aromatic hydroxy composition is preferably selected in accordance with the criteria explained therein.

[0291] Although varying according to the compounds reacted, the reaction conditions for producing N-substituted carbamic acid-O-R² ester by reacting a compound having ureido groups and an alcohol of step (R) are such that the amount of alcohol used has a stoichiometric ratio within a range of from 1 to 500 times based on the ureido groups of

the compound having ureido groups used. Although it is preferable to use an excess of alcohol since complexly substituted carbonyl compounds and high molecular weight compounds having carbonyl bonds in molecules thereof form easily if the stoichiometric ratio is less than 1 time, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 1 to 100 times, more preferably within a range of from 5 to 50 times and even more preferably within a range of from 8 to 20 times.

[0292] Although varying according to the compounds used, the reaction temperature is preferably within a range of from 100 to 350°C. If the temperature is lower than 100°C, the reaction slows or the reaction hardly proceeds at all, or complexly substituted carbonyl compounds increase, thereby making this undesirable. On the other hand, at temperatures higher than 350°C, the N-substituted carbamic acid-O-R² ester either remains in step (A), the urea (and non-N-substituted carbamic acid ester) formed in the system of step (R) decompose, the hydroxy composition is subjected to dehydrogenative denaturation, or decomposition and denaturation reactions of the product in the form of N-substituted carbamic acid-O-R² ester occur easily, thereby making this undesirable. From such viewpoints, the reaction temperature is more preferably within a range of from 120 to 320°C and even more preferably within a range of from 140 to 300°C.

[0293] As has been previously described, the reaction by which N-substituted carbamic acid-O-R² ester is formed is an equilibrium reaction, and since the reaction is biased towards the reactants side, the reaction is preferably carried out while removing ammonia formed as a by-product outside the system as much as possible. Ammonia is preferably removed so that the ammonia concentration in the reaction liquid is preferably 1000 ppm or less, more preferably 300 ppm or less, even more preferably 100 ppm or less and most preferably 30 ppm or less (being contained in the reaction liquid refers to being contained in a liquid phase when carrying out the step (R)). Ammonia can be removed using methods such as reactive distillation, use of an inert gas, membrane separation and adsorptive separation. For example, the reactive distillation refers to a method for separating continuously formed ammonia during the reaction by distillation in the form of a gas. This can be carried out while boiling alcohol, a solvent or hydroxy composition in order to increase the distillation efficiency of the ammonia. In addition, a method using an inert gas refers to a method for separating continuously formed ammonia during the reaction from the reaction system in the form of a gas along with the inert gas. Examples of inert gases used may include nitrogen, helium, argon, carbon dioxide, methane, ethane and propane, these may be used alone or as a mixture, and a method in which the inert gas is introduced into the reaction system is preferable. Examples of adsorbents used in methods using adsorptive separation may include adsorbents able to be used under the temperature conditions at which the reaction is carried out, such as silica, alumina, various types of zeolite or diatomaceous earth. These methods for removing ammonia outside the system may be carried out alone or a plurality of types may be carried out in combination.

[0294] A catalyst can be used in the reaction for the purpose of increasing the reaction rate, for example. Examples of catalysts that are used preferably may include basic catalysts such as methylates, ethylates or butyrates (including isomers) of lithium, sodium, potassium, calcium or barium, rare earth elements, antimony or bismuth alone or oxides, sulfides and salts thereof, boron alone or boron compounds, metals of the copper family, zinc family, aluminum family, carbon family and titanium family in the periodic table as well as metal oxides and sulfides thereof, and carbides and nitrides of elements of the carbon family excluding carbon, titanium family, vanadium family and chromium family in the periodic table. Although there are no particular limitations on the amount of catalyst used in the case of using a catalyst, a catalyst can be used within the range of a stoichiometric ratio of from 0.0001 to 100 times the ureide groups of the compound having ureide groups. Since there are many cases in which it is necessary to remove the catalyst if a catalyst is added, the reaction is preferably carried out without adding a catalyst.

[0295] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus and the like, the reaction pressure is normally within a range of from 0.01 Pa to 10 MPa (absolute pressure), and in consideration of ease of industrial application, the reaction pressure is more preferably within a range of from 0.1 Pa to 5 MPa (absolute pressure), and in consideration of removing gaseous ammonia outside the system, even more preferably from a to 1.5 MPa (absolute pressure).

[0296] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus, reaction pressure and the like, the reaction time (residence time in the case of a continuous reaction) is generally from 0.01 to 100 hours. The reaction time can also be determined according to the formation amount of the target compound in the form of N-substituted carbamic acid-O-R² ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester). For example, the reaction may be stopped after having sampled the reaction liquid, determined the content of N-substituted carbamic acid ester in the reaction liquid (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester) and confirming that the N-substituted carbamic acid-O-R² ester has been formed at a yield of 10% or more based on the compound having ureido groups, or the reaction may be stopped after having confirmed that the yield is 90% or more. The reaction liquid containing the N-substituted carbamic acid-O-R² ester obtained in step (R) is converted to N-substituted carbamic acid-O-aryl ester in a process that contains step (P) to be subsequently described, followed by obtaining an isocyanate in step (F). At that time, if the content of N-substituted carbamic acid-O-R² ester in step (R) is low (the yield thereof is low), there are cases in which this can cause a decrease

in the yield of isocyanate. Thus, the yield of the N-substituted carbamic acid-O-R² ester is preferably 50% or more, more preferably 80% or more and even more preferably 90% or more.

[0297] Although the use of a reaction solvent is not necessarily required in the reaction, a suitable solvent is preferably used as a reaction solvent for the purpose of facilitating the reaction procedure, examples of which include alkanes such as pentane (including isomers), hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; nitrile compounds such as acetonitrile or benzonitrile; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as tetrahydrofuran, 1,4-dioxane, 1,2-dimethoxyethane, diphenyl ether or diphenyl sulfide; ketone compounds such as acetone or methyl ethyl ketone; ester compounds such as ethyl acetate or ethyl benzoate; and sulfoxides such as dimethylsulfoxide or diphenylsulfoxide. Naturally, a hydroxy composition used in excess in the reaction is also preferably used as a reaction solvent.

[0298] The reaction is carried out in a system having a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea (a compound that inherits a carbonyl group possessed by urea, such as a non-N-substituted carbamic acid ester or biuret, which refers to a compound excluding N-substituted carbamic acid-O-esters) and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out. Although the majority of the reaction is carried out in the liquid phase, it may also be carried out in the gaseous phase depending on the reaction conditions. At that time, the volumetric content of the liquid phase in the reaction in which the reaction is carried out is preferably 50% or less. In the case of carrying out the reaction continuously over a long period of time, although polymeric by-products may form due to fluctuations in operating conditions (such as temperature or pressure) and the like, if the volumetric content of the liquid phase in the reactor is high, adhesion and accumulation of such polymeric by-products in the reactor can be avoided. However, since the efficiency of removal of by-product ammonia may become poor and the yield of the N-substituted carbamic acid-O-R² ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester) may decrease if the volumetric content of the liquid phase is excessively high, the volumetric content of the liquid phase based on the gaseous phase is preferably 50% or less, more preferably 30% or less and even more preferably 20% or less (the volumetric content of the liquid phase refers to volumetric ratio of the liquid phase based on the volume of the reaction tank in the case of a tank-type reactor, the volume of the stage lower than the feed stage (not including the tank bottom and reboiler) in the case of a column-type reactor, or the volume of the thin film distiller in the case of a thin film distiller).

[0299] Although there are no particular limitations on the reaction apparatus used when carrying out the reaction and the known reactor can be used, a tank-type and/or a column-type reactor is used preferably. The reactor used is preferably equipped with a condenser.

[0300] As was previously described, the reaction is preferably carried out in a system having a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out under conditions such that the volumetric content of the liquid phase in the reactor is 50% or less, and a reactor that satisfies these conditions is selected for the reactor in which the reaction is carried out.

[0301] More specifically, conventionally known reactors can be suitably combined and used, examples of which may include a stirring tank, a pressurized stirring tank, a reduced pressure stirring tank, a column-type reactor, a distillation column, a packed column or a thin film distiller.

[0302] There are no particular limitations on the type of condenser provided in the reactor and the known condenser can be used. For example, conventionally known condensers such as a multitubular cylindrical condenser, a double tube condenser, a single tube condenser or an air-cooled condenser can be suitably combined and used. The condenser may be provided inside the reactor or provided outside the reactor or may be connected with the reactor by a line, and various types can be employed in consideration of the forms of the reactor and condenser, the manner in which condensed liquid is handled and the like. There are no particular limitations on the materials of the reactor and condenser and known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving

the urea in the aromatic hydroxy compound, a step of dissolving the aromatic hydroxy compound, a step of separating the alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying the N-substituted carbamic acid-O-R² ester from the formed reaction liquid or a step of incinerating or discarding by-products and the like.

5 **[0303]** Step (R) is a step of producing N-substituted carbamic acid-O-R² ester by reacting a compound having ureido groups and an alcohol in a liquid phase using a reactor (equipped with a condenser). The gaseous component formed in the step (R) containing a compound having carbonyl groups derived from urea and ammonia formed as a by-product in the reaction is introduced into the condenser provided in the reactor and all or a portion of the alcohol and compound having carbonyl groups derived from urea are condensed followed by recovery of ammonia in the form of a gas.

10 **[0304]** At that time, the compound having carbonyl groups derived from urea that is contained in ammonia recovered as a gas from the condenser is present at a specific amount or less. Namely, the ratio of the number of carbonyl groups (-C(=O)-) contained in the compound having carbonyl groups derived from urea contained in the ammonia to the number of ammonia molecules is 1 or less, preferably 0.5 or less, more preferably 0.1 or less and even more preferably 0.01 or less. The reason for making the amount of the compound having carbonyl groups derived from urea contained in the ammonia to be within a specific range is to avoid adhesion and accumulation of solid components in the line for transferring ammonia from the condenser.

15 **[0305]** Although all solid components that adhere and accumulate in the line for transferring ammonia cannot be identified, as a result of studies conducted by the inventors of the present invention, the majority were determined to be compounds having carbonyl groups. Although one possible method for avoiding adhesion and accumulation of such solid components contains heating the line for transferring ammonia to decompose compounds having carbonyl groups, according to studies conducted by the inventors of the present invention, there are many cases in which heating alone causes polymerization of decomposition products (such as isocyanic acid) or reaction of the decomposition products with other compounds having carbonyl groups, thereby making it difficult to completely avoid adhesion and accumulation of solid components. In addition, in the case of simply heating the line, it was determined that compounds having carbonyl groups contained in the ammonia and their decomposition products solidify as a result of being rapidly cooled at the outlet of the line for transferring ammonia (such as the portion in contact with the atmosphere), thereby frequently resulting in prominent adhesion and accumulation of solid components. As a result of conducting extensive studies regarding this problem, the inventors of the present invention surprisingly found that the problem of adhesion and accumulation of solid components can be solved by making the amount of the compound having carbonyl groups derived from carbonic acid derivative contained in the ammonia to be equal to or less than the specific amount described above. Although the mechanism by which this effect is demonstrated is unclear, the inventors of the present invention surmised that adhesion and accumulation in the line is caused by the compound having carbonyl groups derived from the carbonic acid derivative itself as well as decomposition and/or polymerization products of the compound having carbonyl groups derived from the carbonic acid derivative, and that by making the amount of carbonyl groups contained in the compound having carbonyl groups derived from the carbonic acid derivative equal to or less than a specific concentration, adhesion of the compound having carbonyl groups derived from the carbonic acid derivative itself as well as the reaction rates of decomposition and/or polymerization of that compound are lowered considerably.

20 **[0306]** On the other hand, the condensed hydroxy composition and compound having carbonyl groups derived from urea are made to be such that the stoichiometric ratio of the condensed hydroxy composition to the condensed compound having carbonyl groups derived from urea is 1 or more, preferably 2 or more and more preferably 3 or more. The reason for defining such ranges is to enable a mixture of the hydroxy composition and compound having carbonyl groups derived from urea condensed in the condenser to be in the form of a homogeneous liquid mixture. As a result, not only is handling of the mixture easier, but occurrence of problems such as adhesion and accumulation of solid components in the condenser can be avoided.

25 **[0307]** Moreover, the mixture of the hydroxy composition and the compound having carbonyl groups derived from urea condensed by the condenser in step (R) may be circulated within the reactor and reused in the reaction of step (A). At that time, the amount of ammonia contained in the mixture is preferably 5000 ppm or less, more preferably 3000 ppm or less and even more preferably 2000 ppm or less.

30 **[0308]** As has been described above, although various compounds are recovered in the form of compounds having carbonyl groups derived from urea, there are no particular limitations on the reuse of these compounds.

35
50 <Step (P)> Transesterification Step

[0309] Although the N-substituted carbamic acid-O-R² ester produced according to step (R) also allows the obtaining of isocyanate by thermal decomposition of the N-substituted carbamic acid-O-R² ester, a more preferably used N-substituted carbamic acid ester is an N-substituted carbamic acid-O-aryl ester.

55 **[0310]** In general, N-substituted carbamic acid-O-aryl esters are more susceptible to thermal decomposition than N-substituted carbamic acid-O-R² esters, and are known to easily decompose to the corresponding isocyanate and aromatic hydroxy compound.

[0311] After converting an easily thermally decomposable N-substituted carbamic acid-O-aryl ester by a transesterification reaction according to step (P), the resulting N-substituted carbamic acid-O-aryl ester can be used in an isocyanate reaction. Furthermore, since this step is a step of converting the ester group of the N-substituted carbamic acid-O-R² ester, it is also generally referred to as a "transesterification step" in the present embodiment.

[0312] Step (P): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound represented by the following formula (2)) in a liquid phase and extracting alcohol formed as a by-product to a gaseous phase.

[0313] FIG. 4 shows a conceptual drawing depicting the step (P).

[0314] Furthermore, an alcohol derived from N-substituted carbamic acid-O-R² ester is formed in the step (P). The following provides an explanation of step (P).

[0315] Here, the target N-substituted carbamic acid-O-R² ester refers to an N-substituted carbamic acid-O-R² ester represented by the above-mentioned formula (49).

[0316] The aromatic hydroxy compound in the reacted aromatic hydroxy composition may be any of an aromatic hydroxy compound represented by the above-mentioned formula (2), formula (7), formula (31), formula (32), formula (38), formula (39) or formula (40). The case in which an aromatic hydroxy compound represented by formula (7) or formula (31) is contained is preferable, the case in which an aromatic hydroxy composition is used that contains an active aromatic hydroxy compound represented by formula (32) is more preferable, and the case in which an aromatic hydroxy composition is used that contains an active aromatic hydroxy compound represented by formula (38) is even more preferable.

[0317] Various methods can be carried out for the step (P) according to the compounds used and the like with reference to known methods (see, for example, WO 2008/059953).

[0318] Although varying according to the compounds reacted, the reaction conditions of step (P) are such that the amount of aromatic hydroxy compound in the aromatic hydroxy composition used has a stoichiometric ratio within a range of from 2 to 1000 times based on the ester groups that compose the raw material N-substituted carbamic acid-O-R² ester. Although it is preferable to use an excess of the aromatic hydroxy compound based on ester groups that compose the raw material N-substituted carbamic acid-O-R² ester in order to complete the reaction quickly, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 2 to 100 times and more preferably within a range of from 5 to 50 times.

[0319] The reaction temperature is generally within a range of from 100 to 300°C, and a high temperature is preferable for increasing the reaction rate, but since side reactions may occur easily at high temperatures, the reaction temperature is preferably within a range of from 150 to 250°C. A known cooling apparatus or heating apparatus may be installed in the reactor for maintaining a constant reaction temperature. In addition, although varying according to the types of compounds used and the reaction temperature, the reaction may be carried out at reduced pressure, normal pressure or increased pressure and generally at a reaction pressure within a range of from 20 to 1 x 10⁶ Pa. There are no particular limitations on the reaction time (residence time in the case of a continuous method), and is generally from 0.001 to 100 hours, preferably from 0.01 to 50 hours and more preferably from 0.1 to 30 hours. In addition, the reaction can be terminated after confirming that a desired amount of the target N-substituted carbamic acid-O-aryl ester has been formed by sampling the reaction liquid and determining the amount formed by liquid chromatography, for example.

[0320] Although a catalyst is not necessarily required in step (P), a catalyst may be used without problem to lower the reaction temperature or complete the reaction more quickly. The catalyst is used at 0.01 to 30% by weight and preferably at 0.5 to 20% by weight based on the weight of the N-substituted carbamic acid-O-R² ester. Examples of catalysts may include Lewis acids as well as transition metal compounds that form a Lewis acid, organic tin compounds, copper group metals, zinc or iron group metal compounds, and more specifically, Lewis acids and transition metal compounds that form a Lewis acid represented by AlX₃, TiX₃, TiX₄, VOX₃, VX₅, ZnX₂, FeX₃ or SnX₄ (wherein X represents a halogen, an acetoxo group, an alkoxy group or an aryloxy group); organic tin compounds represented by (CH₃)₃SnOCHCH₃, (C₂H₅)₃SnOCOC₆H₅, Bu₃SnOCOCH₃, Ph₃SnOCOCH₃, Bu₂Sn(OCOCH₃)₂, Bu₂Sn(OCOC₁₁H₂₃)₂, Ph₃SnOCH₃, (C₂H₅)₃SnOPh, Bu₂Sn(OCH₃)₂, Bu₂Sn(OC₂H₅)₂, Bu₂Sn(OPh)₂, Ph₂Sn(CH₃)₂, (C₂H₅)₃SnOH, PhSnOH, Bu₂SnO, (C₈H₁₇)₂SnO, Bu₂SnCl₂ or BuSnO(OH); copper family metal compounds represented by CuCl, CuCl₂, CuBr, CuBr₂, CuI, CuI₂, Cu(OAc)₂, Cu(acac)₂, copper olefinate, Bu₂Cu, (CH₃O)₂Cu, AgNO₃, AgBr, silver picrate or AgC₆H₆ClO₄; zinc compounds represented by Zn(acac)₂; and, iron family metal compounds represented by Fe(C₁₀H₈)(CO)₅, Fe(CO)₅, Fe(C₄H₆)(CO)₃, Co(mesitylene)₂(PEt₂Ph₂), CoC₅F₅(CO)₇ or ferrocene. (In the above listing of examples, Bu refers to a butyl group, Ph refers to a phenyl group, and acac refers to an acetyl acetone chelate ligand.) Amines such as 1,4-diazabicyclo[2,2,2]octane, triethylenediamine or triethylamine are suitable for use as catalysts, while organic metal catalysts such as dibutyl tin dilaurate, lead octoate or stannous octoate are particularly preferable. These compounds may be used alone or two or more types may be used as a mixture.

[0321] Although the use of a reaction solvent is not necessarily required in the present embodiment, a suitable inert solvent can be preferably used as a reaction solvent for the purpose of facilitating the reaction procedure and the like,

examples of which may include alkanes such as hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as diphenyl ether or diphenyl sulfide; sulfoxides such as dimethylsulfoxide or diphenyl-sulfoxide; and silicone oil. These solvents can be used alone or two or more types can be used as a mixture.

[0322] The transesterification reaction in the present embodiment is an equilibrium reaction. Thus, it is preferable to allow the reaction to proceed while removing the product in the form of alcohol (alcohol derived from the raw material N-substituted carbamic acid-O-R² ester) from the reaction system in order to carry out transesterification efficiently. Thus, if the aromatic hydroxy compound is selected such that the standard boiling point of the aromatic hydroxy compound used in transesterification is higher than the standard boiling point of the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester, the compound having the lowest standard boiling point in the reaction system becomes the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester, thereby facilitating removal of products from the reaction system. Based on the finding that normally industrially adequate distillative separation is possible if the standard boiling points of two components to be separated are 10°C or more apart, an aromatic hydroxy compound is preferably used such that the standard boiling point of the compound having the lowest standard boiling point in the aromatic hydroxy composition (based on a comparison of standard boiling points) is 10°C or more higher than the standard boiling point of the alcohol.

[0323] In addition, transesterification is preferably carried out by the continuous method to allow transesterification to proceed efficiently. Namely, the raw material N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition are continuously supplied to a reactor, transesterification is carried out, alcohol derived from the raw material N-substituted carbamic acid-O-R² ester that is formed is extracted from the reactor in the form of a gaseous component, and a reaction liquid containing the N-substituted carbamic acid-O-aryl ester formed and the aromatic hydroxy composition is continuously extracted from the bottom of the reactor.

[0324] Although the material of the reactor and lines used to carry out transesterification may be known materials provided they do not have a detrimental effect on the starting substances and reactants, materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving the aromatic hydroxy compound, a step of separating the alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying the N-substituted carbamic acid-O-aryl ester from the formed reaction liquid or a step of incinerating or discarding by-products and the like.

[0325] There are no particular limitations on the type of reactor, and a known tank-type or a column-type reactor can be used. Various known methods are used for such a reactor, examples of which may include types using reactors containing a stirring tank, a multistage stirring tank, a distillation column, a multistage distillation column, a multitubular reactor, a continuous multistage distillation column, a packed column, a thin film evaporator, a reactor provided with a support inside, a forced circulation reactor, a falling film evaporator, a falling drop evaporator, a trickle flow reactor or a bubble column, and types using combinations thereof. Methods using a thin film evaporator or a column-type reactor are preferable from the viewpoint of efficiently shifting the equilibrium to the products side, while a structure having a large gas-liquid contact area is preferable for being able to rapidly transfer the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester formed to the gaseous phase.

[0326] A multistage distillation column refers to a distillation column having multiple stages in which the number of theoretical plates of distillation is 2 or more, and any multistage distillation column may be used provided it allows continuous distillation. Any multistage distillation column can be used for the multistage distillation column provided it is ordinarily used as a multistage distillation column, examples of which may include tray column types using a tray such as a bubble tray, a porous plate tray, a valve tray or a counter-current tray, and packed column types packed with various types of packing materials such as a raschig ring, a lessing ring, a pole ring, Berl saddle, Interlock saddle, Dixon packing, McMahan packing, Helipack, Sulzer packing or Mellapak. Any packed column can be used provided the column is packed with a known packing material as described above. Moreover, a combination tray-packed column type is also used preferably that combines a tray portion with a portion packed with a packing material.

[0327] A line for supplying inert gas and/or liquid inert solvent from the lower portion of the reactor may be separately

attached, and in the case the mixture of the target N-substituted carbamic acid-O-aryl ester and aromatic hydroxy compound contains raw material N-substituted carbamic acid-O-R² ester, a line may be attached for re-circulating all or a portion of the mixture to the reactor. Furthermore, in the case of using the above-mentioned inert solvent, the inert solvent may be in the form of a gas and/or a liquid.

[0328] The gaseous component extracted from the reactor containing alcohol derived from the raw material N-substituted carbamic acid-O-R² ester is preferably purified using a known method such as that which uses a distillation column, and can be reused as an alcohol of step (A) and/or step (R).

<Route 4>


[0329] Route 4) is a method for carrying out step (R) followed by carrying out step (P) and step (C). Route 4) is one aspect of the method indicated in route 2).

[0330] The method of route 4) is a method for obtaining N-substituted carbamic acid-O-aryl ester, in which at least two molecules of the N-substituted carbamic acid-O-aryl ester are crosslinked with methylene (-CH₂-) groups, from the N-substituted carbamic acid-O-aryl ester obtained in step (P) by carrying out the following step (C) after step (P), in which the organic primary amine used in step (A) is an aromatic organic primary monoamine represented by the following formula (5). An aromatic monohydroxy compound is preferably used for the aromatic hydroxy compound that composes the aromatic hydroxy composition used in step (A) and/or step (R) and/or step (P).

[0331] Step (C): a step of obtaining N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with methylene groups (-CH₂-), by reacting the N-substituted carbamic acid-O-(R² or aryl) ester with formaldehyde or a methylenating crosslinking agent and crosslinking aromatic groups derived from the aromatic organic primary monoamine contained in the N-substituted carbamic acid-O-(R² or aryl) ester with the methylene groups (-CH₂-).

[0332] The N-substituted carbamic acid-O-R² ester of this route 4) refers to unreacted N-substituted carbamic acid-O-R² ester in step (P).

[0333] In this route, step (A) is carried out using an organic primary amine represented by the following formula for the organic primary amine to obtain a compound having ureido groups represented by formula (1) derived from the organic primary amine, followed by carrying out step (R) to obtain an N-substituted carbamic acid-O-R² ester derived from the compound having ureido groups, carrying out step (P) to obtain an N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups, and finally carrying out step (C). Namely, the organic primary amine used in this route is an organic primary amine represented by formula (5), the compound having ureido groups obtained in step (A) of this route is a compound having ureido groups represented by formula (41) derived from the organic primary amine, the N-substituted carbamic acid-O-R² ester obtained in step (R) of this route is an N-substituted carbamic acid-O-R² ester in which r=1 that is represented by formula (49) and derived from the ureido groups and an alcohol, and more specifically an N-substituted carbamic acid-O-R² ester represented by the following formula (146), and the N-substituted carbamic acid-O-aryl ester obtained in step (P) of this route is an N-substituted carbamic acid-O-aryl ester in which q=1 that is represented by formula (43) and derived from the N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition, and more specifically an N-substituted carbamic acid-O-aryl ester represented by the following formula (149). Indications of specific examples of each of these compounds are respectively contained in previous explanations thereof.




(wherein,

at least one location at the ortho position and/or para position of the NH₂ group of an aromatic organic primary monoamine represented by formula (5) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the aromatic organic primary monoamine represented by formula (5) is an integer of from 6 to 13).

[0334] In this case, the compound having ureido groups obtained in step (A) is at least one type of compound having

EP 2 322 504 B9


ureido groups represented by the following formula (148). In addition, the groups R^3 , R^4 , R^5 and R^6 in the following formula (148) are selected from the groups R^3 , R^4 , R^5 and R^6 of an organic primary amine represented by the above-mentioned formula (5), and is a compound in which amino groups ($-NH_2$ groups) of the organic primary amine represented by formula (5) are in the form of ureido groups ($-NH-CO-NH_2$):



(1 4 8)

(wherein

at least one location at the ortho position and/or para position of the ureido group of an N-substituted aromatic organic monourea represented by formula (148) is not substituted, groups R^3 to R^6 respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R^3 to R^6 may respectively and independently substitute an aromatic ring or groups R^3 to R^6 may together bond to form a ring with an aromatic ring, groups R^3 to R^6 are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R^3 to R^6 is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the N-substituted aromatic organic monourea represented by formula (148), excluding ureido groups ($-NH-CO-NH_2$), is an integer of from 6 to 13).




(1 4 6)

(wherein

groups R^2 to R^6 are the groups indicated above).

[0335] In this case, the N-substituted carbamic acid-O-aryl ester obtained in step (P) by carrying out step (R) is at least one type of N-substituted carbamic acid-O-aryl ester represented by the following formula (149). In addition, the groups R^3 , R^4 , R^5 and R^6 in the following formula (149) are selected from the groups R^3 , R^4 , R^5 and R^6 of an organic primary amine represented by the above-mentioned formula (5), and is a compound in which ureido groups ($-NH-CO-NH_2$) of a compound having ureido groups represented by formula (148) are in the form of carbamic acid-O-aryl ester groups:



(1 4 9)

(wherein

groups R^3 to R^6 are the groups indicated above).

[0336] In steps (A), (R) and (P) of this route, the organic primary amine used is an organic primary amine represented by formula (5), and steps (A), (R) and (P) of this route are carried out under the conditions of steps (A), (R) and (P) of route 3).

[0337] Although varying according to the compounds reacted, the reaction conditions for producing N-substituted

carbamic acid-O-R² ester by reacting a compound having ureido groups and an alcohol of step (R) are such that the amount of alcohol used has a stoichiometric ratio within a range of from 1 to 500 times based on the ureido groups of the compound having ureido groups used. Although it is preferable to use an excess of alcohol since complexly substituted carbonyl compounds and high molecular weight compounds having carbonyl bonds in molecules thereof form easily if the stoichiometric ratio is less than 1 time, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 1 to 200 times, more preferably within a range of from 1.5 to 100 times and even more preferably within a range of from 2 to 50 times.

[0338] Although varying according to the compounds used, the reaction temperature is preferably within a range of from 100 to 350°C. If the temperature is lower than 100°C, the reaction slows or the reaction hardly proceeds at all, or complexly substituted carbonyl compounds increase, thereby making this undesirable. On the other hand, at temperatures higher than 350°C, the N-substituted carbamic acid-O-R² ester either remains in step (A), the urea (and non-N-substituted carbamic acid ester) formed in the system of step (R) decompose, the hydroxy composition is subjected to dehydrogenative denaturation, or decomposition and denaturation reactions of the product in the form of N-substituted carbamic acid-O-R² ester occur easily, thereby making this undesirable. From such viewpoints, the reaction temperature is more preferably within a range of from 120 to 320°C and even more preferably within a range of from 140 to 300°C.

[0339] As has been previously described, the reaction by which N-substituted carbamic acid-O-R² ester is formed is an equilibrium reaction, and since the reaction is biased towards the reactants side, the reaction is preferably carried out while removing ammonia formed as a by-product outside the system as much as possible. Ammonia is preferably removed so that the ammonia concentration in the reaction liquid is preferably 1000 ppm or less, more preferably 300 ppm or less, even more preferably 100 ppm or less and most preferably 30 ppm or less (being contained in the reaction liquid refers to being contained in a liquid phase when carrying out the step (R)). Ammonia can be removed using methods such as reactive distillation, use of an inert gas, membrane separation and adsorptive separation. For example, the reactive distillation refers to a method for separating continuously formed ammonia during the reaction by distillation in the form of a gas. This can be carried out while boiling alcohol, an aromatic hydroxy compound, solvent or hydroxy composition in order to increase the distillation efficiency of the ammonia. In addition, a method using an inert gas refers to a method for separating continuously formed ammonia during the reaction from the reaction system in the form of a gas along with the inert gas. Examples of inert gases used may include nitrogen, helium, argon, carbon dioxide, methane, ethane and propane, these may be used alone or as a mixture, and a method in which the inert gas is introduced into the reaction system is preferable. Examples of adsorbents used in methods using adsorptive separation may include adsorbents able to be used under the temperature conditions at which the reaction is carried out, such as silica, alumina, various types of zeolite or diatomaceous earth. These methods for removing ammonia outside the system may be carried out alone or a plurality of types may be carried out in combination.

[0340] A catalyst can be used in the reaction for the purpose of increasing the reaction rate, for example. Examples of catalysts that are used preferably may include basic catalysts such as methylates, ethylates or butyrates (including isomers) of lithium, sodium, potassium, calcium or barium, rare earth elements, antimony or bismuth alone or oxides, sulfides and salts thereof, boron alone or boron compounds, metals of the copper family, zinc family, aluminum family, carbon family and titanium family in the periodic table as well as metal oxides and sulfides thereof, and carbides and nitrides of elements of the carbon family excluding carbon, titanium family, vanadium family and chromium family in the periodic table. Although there are no particular limitations on the amount of catalyst used in the case of using a catalyst, a catalyst can be used within the range of a stoichiometric ratio of from 0.0001 to 100 times the ureido groups of the compound having ureido groups.

[0341] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus and the like, the reaction pressure is generally within a range of preferably from 0.01 Pa to 10 MPa (absolute pressure), and in consideration of ease of industrial application, the reaction pressure is more preferably within a range of from 0.1 Pa to 5 MPa (absolute pressure), and in consideration of removing gaseous ammonia outside the system, even more preferably from 0.1 Pa to 1.5 MPa (absolute pressure).

[0342] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus, reaction pressure and the like, the reaction time (residence time in the case of a continuous reaction) is generally from 0.01 to 100 hours. The reaction time can also be determined according to the formation amount of the target compound in the form of N-substituted carbamic acid-O-R² ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester). For example, the reaction may be stopped after having sampled the reaction liquid, determined the content of N-substituted carbamic acid ester in the reaction liquid (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester) and confirming that the N-substituted carbamic acid-O-R² ester has been formed at a yield of 10% or more based on the compound having ureido groups, or the reaction may be stopped after having confirmed that the yield is 90% or more. The reaction liquid containing the N-substituted carbamic acid-O-R² ester obtained in step (R) is converted to N-substituted carbamic acid-O-aryl ester in a process that contains step (P) to be subsequently described, followed by obtaining an isocyanate in step (F). At that time, if the content of N-substituted

carbamic acid-O-R² ester in step (R) is low (the yield thereof is low), there are cases in which this can cause a decrease in the yield of isocyanate. Thus, the yield of the N-substituted carbamic acid-O-R² ester is preferably 50% or more, more preferably 80% or more and even more preferably 90% or more.

5 [0343] Although the use of a reaction solvent is not necessarily required in the reaction, a suitable solvent is preferably used as a reaction solvent for the purpose of facilitating the reaction procedure, examples of which may include alkanes such as pentane (including isomers), hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; nitrile compounds such as acetonitrile or benzonitrile; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as tetrahydrofuran, 1,4-dioxane, 1,2-dimethoxyethane, diphenyl ether or diphenyl sulfide; ketone compounds such as acetone or methyl ethyl ketone; ester compounds such as ethyl acetate or ethyl benzoate; and sulfoxides such as dimethylsulfoxide or diphenylsulfoxide. Naturally, a hydroxy composition used in excess in the reaction is also preferably used as a reaction solvent.

10 [0344] The reaction is carried out in a system having a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea (a compound that inherits a carbonyl group possessed by urea, such as a non-N-substituted carbamic acid ester or biuret, which refers to a compound excluding N-substituted carbamic acid-O-esters) and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out. Although the majority of the reaction is carried out in the liquid phase, it may also be carried out in the gaseous phase depending on the reaction conditions. At that time, the volumetric content of the liquid phase in the reaction in which the reaction is carried out is preferably 50% or less. In the case of carrying out the reaction continuously over a long period of time, although polymeric by-products may form due to fluctuations in operating conditions (such as temperature or pressure) and the like, if the volumetric content of the liquid phase in the reactor is high, adhesion and accumulation of such polymeric by-products in the reactor can be avoided. However, since the efficiency of removal of by-product ammonia may become poor and the yield of the N-substituted carbamic acid-O-R² ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester) may decrease if the volumetric content of the liquid phase is excessively high, the volumetric content of the liquid phase based on the gaseous phase is preferably 50% or less, more preferably 30% or less and even more preferably 20% or less (the volumetric content of the liquid phase refers to volumetric ratio of the liquid phase based on the volume of the reaction tank in the case of a tank-type reactor, the volume of the stage lower than the feed stage (not including the tank bottom and reboiler) in the case of a column-type reactor, or the volume of the thin film distiller in the case of a thin film distiller).

15 [0345] Although there are no particular limitations on the reaction apparatus used when carrying out the reaction and a known reactor can be used, a tank-type and/or a column-type reactor is used preferably. The reactor used is preferably equipped with a condenser.

20 [0346] As was previously described, the reaction is preferably carried out in a system containing a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out, and under conditions such that the volumetric content of the liquid phase in the reactor in which the reaction is carried out is 50% or less, and a reactor that satisfies these conditions is selected for the reactor in which the reaction is carried out.

25 [0347] More specifically, conventionally known reactors can be suitably combined and used, examples of which may include a stirring tank, a pressurized stirring tank, a depressurized stirring tank, a column-type reactor, a distillation column, a packed column or a thin film distiller.

30 [0348] There are no particular limitations on the type of condenser provided in the reactor and the known condenser can be used. For example, conventionally known condensers such as a multitubular cylindrical condenser, a double tube condenser, a single tube condenser or an air-cooled condenser can be suitably combined and used. The condenser may be provided inside the reactor or outside the reactor, or may be connected with the reactor by a line, and various types can be employed in consideration of the forms of the reactor and condenser, the manner in which condensed liquid is handled and the like.

35 [0349] There are no particular limitations on the materials of the reactor and condenser and known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water

or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving the compound having ureido groups in the aromatic hydroxy composition, a step of dissolving the aromatic hydroxy compound, a step of separating alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying N-substituted carbamic acid-O-R² ester from the formed reaction liquid, or a step of incinerating or discarding by-products and the like.

[0350] Step (R) is a step of producing N-substituted carbamic acid-O-R² ester by reacting (esterifying) a compound having ureido groups and an alcohol in a liquid phase using a reactor (equipped with a condenser). The gaseous component formed in the step (R) containing a compound having carbonyl groups derived from urea and ammonia formed as a by-product in the reaction is introduced into the condenser provided in the reactor and all or a portion of the alcohol and compound having carbonyl groups derived from urea are condensed followed by recovery of ammonia in the form of a gas.

[0351] At that time, the compound having carbonyl groups derived from urea that is contained in ammonia recovered as a gas from the condenser is present at a specific amount or less. Namely, the ratio of the number of carbonyl groups (-C(=O)-) contained in the compound having carbonyl groups derived from urea contained in the ammonia to the number of ammonia molecules is 1 or less, preferably 0.5 or less, more preferably 0.1 or less and even more preferably 0.01 or less. The reason for making the amount of the compound having carbonyl groups derived from urea contained in the ammonia to be within a specific range is to avoid adhesion and accumulation of solid components in the line for transferring ammonia from the condenser.

[0352] Although all solid components that adhere and accumulate in the line for transferring ammonia cannot be identified, as a result of studies conducted by the inventors of the present invention, the majority were determined to be compounds having carbonyl groups. Although one possible method for avoiding adhesion and accumulation of such solid components contains heating the line for transferring ammonia to decompose compounds having carbonyl groups, according to studies conducted by the inventors of the present invention, there are many cases in which heating alone causes polymerization of decomposition products (such as isocyanic acid) or reaction with other compounds having carbonyl groups, thereby making it difficult to completely avoid adhesion and accumulation of solid components. In addition, in the case of simply heating the line, it was determined that compounds having carbonyl groups contained in the ammonia and their decomposition products solidify as a result of being rapidly cooled at the outlet of the line for transferring ammonia (such as the portion in contact with the atmosphere), thereby frequently resulting in prominent adhesion and accumulation of solid components. As a result of conducting extensive studies regarding this problem, the inventors of the present invention found that the problem of adhesion and accumulation of solid components can be solved by making the amount of the compound having carbonyl groups derived from the carbonic acid derivative contained in the ammonia to be equal to or less than the specific amount described above. Although the mechanism by which this effect is demonstrated is unclear, the inventors of the present invention surmised that adhesion and accumulation in the line is caused by the compound having carbonyl groups derived from the carbonic acid derivative itself as well as decomposition and/or polymerization products of the compound having carbonyl groups derived from the carbonic acid derivative, and that by making the amount of carbonyl groups contained in the compound having carbonyl groups derived from the carbonic acid derivative equal to or less than a specific concentration, adhesion of the compound having carbonyl groups derived from the carbonic acid derivative itself as well as the reaction rates of decomposition and/or polymerization of that compound are lowered considerably.

[0353] On the other hand, the condensed hydroxy composition and compound having carbonyl groups derived from urea are made to be such that the stoichiometric ratio of the condensed hydroxy composition to the condensed compound having carbonyl groups derived from urea is 1 or more, preferably 2 or more and more preferably 3 or more. The reason for defining such ranges is to enable a mixture of the hydroxy composition and compound having carbonyl groups derived from urea condensed in the condenser to be in the form of a homogeneous liquid mixture. As a result, not only is handling of the mixture easier, but occurrence of problems such as adhesion and accumulation of solid components in the condenser can be avoided.

[0354] Moreover, the mixture of the hydroxy composition and the compound having carbonyl groups derived from urea condensed by the condenser in step (R) may be circulated within the reactor and reused in the reaction of step (A). At that time, the amount of ammonia contained in the mixture is preferably 5000 ppm or less, more preferably 3000 ppm or less and even more preferably 2000 ppm or less.

[0355] As has been described above, although various compounds are recovered in the form of compounds having carbonyl groups derived from urea, there are no particular limitations on the reuse of these compounds.

<Step (P)> Esterification Step

[0356] Since this step is a step of converting the ester group of an N-substituted carbamic acid-O-R² ester, it is also generally referred to as an "esterification step" in the present embodiment.

[0357] FIG. 5 shows a conceptual drawing depicting the step (P).

[0358] Furthermore, an alcohol derived from N-substituted carbamic acid-O-R² ester is formed in this step (P). The following provides an explanation of the step (P).

[0359] The aromatic hydroxy compound in the reacted aromatic hydroxy composition may be any of an aromatic hydroxy compound represented by the above-mentioned formula (2), formula (7), formula (31), formula (32), formula (38), formula (39) or formula (40). The case in which an aromatic hydroxy compound represented by formula (7) or formula (31) is contained is preferable, the case in which an aromatic hydroxy composition is used that contains an active aromatic hydroxy compound represented by formula (32) is more preferable, and the case in which an aromatic hydroxy composition is used that contains an active aromatic hydroxy compound represented by formula (38) is even more preferable.

[0360] Various methods can be carried out for the step (P) according to the compounds used and the like with reference to known methods (see, for example, WO 2008/059953).

[0361] Although varying according to the compounds reacted, the reaction conditions of step (P) are such that the amount of aromatic hydroxy compound in the aromatic hydroxy composition used has a stoichiometric ratio within a range of from 2 to 1000 times based on the ester groups that compose the raw material N-substituted carbamic acid-O-R² ester. Although it is preferable to use an excess of the aromatic hydroxy compound based on ester groups that compose the raw material N-substituted carbamic acid-O-R² ester in order to complete the reaction quickly, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 2 to 100 times and more preferably within a range of from 5 to 50 times.

[0362] The reaction temperature is generally within a range of from 100 to 300°C, and a high temperature is preferable for increasing the reaction rate, but since side reactions may occur easily at high temperatures, the reaction temperature is preferably within a range of from 150 to 250°C. A known cooling apparatus or heating apparatus may be installed in the reactor for maintaining a constant reaction temperature. In addition, although varying according to the types of compounds used and the reaction temperature, the reaction may be carried out at reduced pressure, normal pressure or increased pressure and normally at a reaction pressure within a range of from 20 to 1 x 10⁶ Pa. There are no particular limitations on the reaction time (residence time in the case of a continuous method), and is generally from 0.001 to 100 hours, preferably from 0.01 to 50 hours and more preferably from 0.1 to 30 hours. In addition, the reaction can be terminated after confirming that a desired amount of the target N-substituted carbamic acid-O-aryl ester has been formed by sampling the reaction liquid and determining the amount formed by liquid chromatography, for example.

[0363] Although a catalyst is not necessarily required in step (P), a catalyst may be used without problem to lower the reaction temperature or complete the reaction more quickly. The catalyst is used at 0.01 to 30% by weight and preferably at 0.5 to 20% by weight based on the weight of the N-substituted carbamic acid-O-R² ester. Examples of catalysts may include Lewis acids as well as transition metal compounds that form a Lewis acid, organic tin compounds, copper group metals, zinc or iron group metal compounds, and more specifically, Lewis acids and transition metal compounds that form a Lewis acid represented by AlX₃, TiX₃, TiX₄, VOX₃, VX₅, ZnX₂, FeX₃ or SnX₄ (wherein X represents a halogen, an acetoxy group, an alkoxy group or an aryloxy group); organic tin compounds represented by (CH₃)₃SnOCHCH₃, (C₂H₅)₃SnOCOC₆H₅, Bu₃SnOCOCH₃, Ph₃SnOCOCH₃, Bu₂Sn(OCOCH₃)₂, Bu₂Sn(OCOC₁₁H₂₃)₂, Ph₃SnOCH₃, (C₂H₅)₃SnOPh, Bu₂Sn(OCH₃)₂, Bu₂Sn(OC₂H₅)₂, Bu₂Sn(OPh)₂, Ph₂Sn(CH₃)₂, (C₂H₅)₃SnOH, PhSnOH, Bu₂SnO, (C₈H₁₇)₂SnO, Bu₂SnCl₂ or BuSnO(OH); copper family metal compounds represented by CuCl, CuCl₂, CuBr, CuBr₂, CuI, CuI₂, Cu(OAc)₂, Cu(acac)₂, copper olefinate, Bu₂Cu, (CH₃O)₂Cu, AgNO₃, AgBr, silver picrate or AgC₆H₆ClO₄; zinc compounds represented by Zn(acac)₂; and, iron family metal compounds represented by Fe(C₁₀H₈)(CO)₅, Fe(CO)₅, Fe(C₄H₆)(CO)₃, Co(mesitylene)₂(PEt₂Ph₂), CoC₅F₅(CO)₇ or ferrocene. (In the above listing of examples, Bu refers to a butyl group, Ph refers to a phenyl group, and acac refers to an acetyl acetone chelate ligand.) Amines such as 4-diazabicyclo[2,2,2]octane, triethylenediamine or triethylamine are suitable for use as catalysts, while organic metal catalysts such as dibutyl tin dilaurate, lead octoate or stannous octoate are particularly preferable. These compounds may be used alone or two or more types may be used as a mixture.

[0364] Although the use of a reaction solvent is not necessarily required in the present embodiment, a suitable inert solvent can be preferably used as a reaction solvent for the purpose of facilitating the reaction procedure and the like, examples of which may include alkanes such as hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as diphenyl ether or diphenyl sulfide; sulfoxides such as dimethylsulfoxide or diphenyl-

sulfoxide; and silicone oil. These solvents can be used alone or two or more types can be used as a mixture.

[0365] The transesterification reaction in the present embodiment is an equilibrium reaction. Thus, it is preferable to allow the reaction to proceed while removing the product in the form of alcohol (alcohol derived from the raw material N-substituted carbamic acid-O-R² ester) from the reaction system in order to carry out transesterification efficiently. Thus, if the aromatic hydroxy compound is selected such that the standard boiling point of the aromatic hydroxy compound used in transesterification is higher than the standard boiling point of the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester, the compound having the lowest standard boiling point in the reaction system becomes the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester, thereby facilitating removal of products from the reaction system. Based on the finding that normally industrially adequate distillative separation is possible if the standard boiling points of two components to be separated are 10°C or more apart, an aromatic hydroxy compound is preferably used such that the standard boiling point of the compound having the lowest standard boiling point in the aromatic hydroxy composition (based on a comparison of standard boiling points) is 10°C or more higher than the standard boiling point of the alcohol.

[0366] In addition, transesterification is preferably carried out by a continuous method to allow transesterification to proceed efficiently. Namely, the raw material N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition are continuously supplied to a reactor, transesterification is carried out, alcohol derived from the raw material N-substituted carbamic acid-O-R² ester that is formed is extracted from the reactor in the form of a gaseous component, and a reaction liquid containing the N-substituted carbamic acid-O-aryl ester formed and the aromatic hydroxy composition is continuously extracted from the bottom of the reactor.

[0367] Although the material of the reactor and lines used to carry out transesterification may be known materials provided they do not have a detrimental effect on the starting substances and reactants, materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving the aromatic hydroxy compound, a step of separating the alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying the N-substituted carbamic acid-O-aryl ester from the formed reaction liquid or a step of incinerating or discarding by-products and the like. There are no particular limitations on the type of reactor, and a known tank-type or a column-type reactor can be used. Various known methods are used for such a reactor, examples of which may include types using reactors containing a stirring tank, a multistage stirring tank, a distillation column, a multistage distillation column, a multitubular reactor, a continuous multistage distillation column, a packed column, a thin film evaporator, a reactor provided with a support inside, a forced circulation reactor, a falling film evaporator, a falling drop evaporator, a trickle flow reactor or a bubble column, and types using combinations thereof. Methods using a thin film evaporator or a column-type reactor are preferable from the viewpoint of efficiently shifting the equilibrium to the products side, while a structure having a large gas-liquid contact area is preferable for being able to rapidly transfer the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester formed to the gaseous phase.

[0368] A multistage distillation column refers to a distillation column having multiple stages in which the number of theoretical plates of distillation is 2 or more, and any multistage distillation column may be used provided it allows continuous distillation. Any multistage distillation column can be used for the multistage distillation column provided it is ordinarily used as a multistage distillation column, examples of which may include tray column types using a tray such as a bubble tray, a porous plate tray, a valve tray or a counter-current tray, and packed column types packed with various types of packing materials such as a Raschig ring, a Lessing ring, a pole ring, Berl saddle, Interlock saddle, a Dixon packing, a McMahon packing, Helipack, a Sulzer packing or Mellapak. Any packed column can be used provided the column is packed with the known packing material as described above. Moreover, a combination tray-packed column type is also used preferably that combines a tray portion with a portion packed with a packing material.


[0369] A line for supplying inert gas and/or liquid inert solvent from the lower portion of the reactor may be separately attached, and in the case the mixture of the target N-substituted carbamic acid-O-aryl ester and aromatic hydroxy compound contains raw material N-substituted carbamic acid-O-R² ester, a line may be attached for re-circulating all or a portion of the mixture to the reactor. Furthermore, in the case of using the above-mentioned inert solvent, the inert solvent may be in the form of a gas and/or a liquid.

[0370] The gaseous component extracted from the reactor containing alcohol derived from the raw material N-substituted carbamic acid-O-R² ester is preferably purified using the known method such as that which uses a distillation column, and can be reused as an alcohol of step (A) and/or step (R).

[0371] Step (C) is a step of obtaining N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with methylene groups (-CH₂-), by crosslinking at least one type of N-substituted carbamic acid-O-aryl ester (or reaction liquid containing the same) obtained in step

(P) with methylene groups (-CH₂-). As a result of carrying out step (C), N-substituted carbamic acid-O-aryl ester is obtained in which at least two molecules of at least one type of N-substituted carbamic acid-O-aryl ester represented by the following formula (150) are crosslinked with the methylene groups (-CH₂-). Here, when carrying out route 2), an aromatic hydroxy composition containing an aromatic hydroxy compound is preferably used for the aromatic hydroxy compound used in step (A) and/or step (R) and/or step (P) as previously described (namely, an aromatic hydroxy compound in which b=1 in the aromatic hydroxy compound represented by formula (2)). Although a polyvalent aromatic hydroxy compound may be used, crosslinking may occur at locations other than the desired locations at that time. In the following formula (150), in the case of using the above-mentioned aromatic hydroxy compound (namely in the case b=1), ring A of the following formula does not have other aromatic hydroxy groups or alcoholic hydroxy groups. An aromatic hydroxy compound represented by the above-mentioned formula (31) is preferable for the aromatic hydroxy compound, the case of using an active aromatic hydroxy compound represented by formula (38) is more preferable, and the case of using an aromatic hydroxy compound represented by formula (38), in which groups R²⁶ and R²⁷ are hydrogen atoms while other substituents are linear and/or cyclic saturated alkyl groups, or the case of being naphthol (including isomers), phenoxyphenol (including isomers) or diphenoxyphenol (including isomers), in which the ortho position or para position of the hydroxy group is not substituted, is even more preferable.

[0372] Although compounds in which m is an integer from 0 to 6 are represented by the formula (150), this value can be adjusted according to the amount used and reaction rate of the methylenating crosslinking agent that is reacted (to be subsequently explained and frequently referred to as a methylenating agent):



(wherein

R¹ represents a group derived from an organic primary amine as previously defined,
 ring A represents a group derived from an aromatic hydroxy compound that composes an aromatic hydroxy composition as previously defined, and which represents a residue in which at least one hydrogen atom of hydroxyl groups directly bonded to an aromatic hydrocarbon ring has been removed from the aromatic hydroxy compound,
 groups R³ to R⁶ represent previously defined groups, and
 m represents an integer of from 0 to 6).

[0373] Although a monoisocyanate can be produced by applying the N-substituted carbamic acid-O-mono(aryl ester) represented by the above-mentioned formula (149) to a thermal decomposition reaction as is, when considering that isocyanates are typically used in applications such as paint and polyurethane, the isocyanate is preferably a polyfunctional isocyanate. Thus, a method can be carried out in which, after having preliminarily polymerized the N-substituted carbamic acid-O-mono(aryl ester) by the above-mentioned step (C), the polymer is applied to a thermal decomposition reaction to obtain a polyfunctional isocyanate.

[0374] The following provides an explanation of the step (C). In the following explanation, the N-substituted carbamic acid-O-aryl ester obtained in step (P) of route 4) is frequently indicated as N-substituted carbamic acid-O-mono(aryl ester) or N-substituted carbamic acid monoaryl ester.

[0375] The known method (see, for example, Federal Republic of Germany Patent No. 1042891) can be used for the step (C).

[0376] Prior to carrying out step (C), the aromatic hydroxy composition obtained in step (P) is separated from the reaction liquid containing the resulting N-substituted carbamic acid-O-aryl ester. Although step (C) may be carried out in the presence of an aromatic hydroxy compound, since the aromatic hydroxy compound may be crosslinked by the methylenating crosslinking agent resulting in the formation of by-products such as polyaromatic hydroxy compounds, or the amount of methylenating crosslinking agent used may increase, aromatic hydroxy compounds are preferably separated. The known method can be used for the separation method, and although varying according to the compounds used, examples of separation methods that can be used may include a distillation method, an extraction separation method that uses the difference in solubility between the N-substituted carbamic acid-O-aryl ester and aromatic hydroxy compound, and a filtration method carried out by solidifying either the N-substituted carbamic acid-O-aryl ester or aromatic hydroxy compound. Although these methods cannot be indicated specifically since they depend on the respective physical properties of the compounds used, the method and conditions thereof can be adequately selected within the scope of knowledge of a person with ordinary skill in the art.

[0377] When carrying out step (C), the aromatic hydroxy compound is removed until the amount of aromatic hydroxy compound present following the above-mentioned separation procedure is a stoichiometric ratio of 1 time or less, preferably 0.5 times and more preferably 0.1 times based on the N-substituted carbamic acid-O-aryl ester. At this time, the aromatic hydroxy compound may be removed in the presence of solvent used in step (C) to be subsequently explained.

[0378] Examples of methylenating crosslinking agents preferably used in the step (C) may include formaldehyde, paraformaldehyde, trioxane, dialkoxymethanes having a lower alkyl group having 1 to 6 carbon atoms (such as dimethoxymethane, diethoxymethane, dipropoxymethane, dipentoxymethane or dihexyloxymethane), and diacyloxymethanes having a lower carboxyl group such as diacetoxymethane or dipropioxymethane. These may be used alone or two or more types may be used as a mixture. Among these methylenating agents, aqueous solutions of formaldehyde are particularly preferable in consideration of cases of industrial application, ease of handling of the methylenating crosslinking agent and the like.

[0379] In carrying out the reaction of the step (C), although there are no particular limitations on the ratio of N-substituted carbamic acid-O-mono(aryl ester) to methylenating crosslinking agent, the N-substituted carbamic acid-O-monoaryl ester is preferably used at a stoichiometric ratio of from 2 to 20 times the methylenating crosslinking agent. Although the formation of polynuclear forms (referring to N-substituted carbamic acid-O-aryl esters in which three or more aromatic rings (aromatic rings derived from organic primary amine) are bonded by a methylene crosslinked structure, or in other words, compounds in which m is an integer of 1 or more in the above-mentioned formula (150)) is inhibited the greater the amount of N-substituted carbamic acid-monoaryl ester used, if an overly excessive amount of N-substituted carbamic acid-O-monoaryl ester is used, there are many cases in which the remaining amount of raw material N-substituted carbamic acid-O-mono(aryl ester) increases. Thus, the amount of N-substituted carbamic acid-O-monoaryl ester used in terms of the stoichiometric ratio with the methylenating crosslinking agent is more preferably within a range of from 3 to 15 times and even more preferably within a range of from 5 to 10 times.

[0380] An acid catalyst is preferably used as a catalyst in the condensation reaction. Examples of acid catalysts may include inorganic acids such as hydrochloric acid, sulfuric acid, phosphoric acid or boric acid, and organic acids such as formic acid, acetic acid, oxalic acid or toluenesulfonic acid. In addition, acids referred to as super strong acids such as hydrobromic acid, perchloric acid, chlorosulfonic acid or trifluoromethanesulfonic acid are also effective. In addition, ion exchange resins having acidic groups such as carboxyl groups or sulfonate groups as well as acids referred to as Lewis acids, such as trifluoroboric acid, iron chloride, aluminum chloride, zinc chloride or titanium chloride, are also effective.

[0381] In the case of a protonic acid such as the above-mentioned inorganic acids, organic acids or super strong acids, the amount of these acids used is within a range of a stoichiometric ratio of from 0.001 to 10, and preferably within a range of from 0.01 to 5, based on the raw material N-substituted carbamic acid ester. In addition, in the case these acids are used in the form of aqueous solutions, they can be used at a concentration within a range of from 10 to 95% by weight and preferably within a range of from 20 to 80% by weight based on the amount of water in the reaction system. If the concentration is less than 10% by weight, the reaction rate of the condensation reaction becomes extremely slow, while if the concentration exceeds 95% by weight, hydrolysis of the raw material and other undesirable side reactions may occur.

[0382] The condensation reaction can be carried out in the presence or absence of solvent. Examples of solvents that are used preferably may include linear, branched or cyclic hydrocarbons such as pentane, hexane, heptane, octane, nonane, decane, hexadecane, cyclopentane or cyclohexane; aromatic hydrocarbons such as benzene, toluene or xylene and their alkyl-, halogen- and nitro-substituted forms; halogenated hydrocarbons such as chloroform, methylene chloride, carbon tetrachloride, dichloroethane, trichloroethane or tetrachloroethane; aliphatic alkyl esters such as methyl acetate or ethyl acetate; and ethers such as diethyl ether, diisopropyl ether, dioxane or tetrahydrofuran. In addition, thioacetals, acetals or acylals are used preferably since they do not form free formaldehyde under the reaction conditions and do not substantially form water by reacting with water formed as a by-product in the reaction. Acetals and acylals are used particularly preferably. In addition, the above-mentioned acids themselves are also preferably used as solvents. These solvents may be used alone or two or more types may be used as a mixture.

[0383] These solvents can be used at a weight ratio within a range of from 0.1 to 100 times and preferably within a range of from 0.2 to 50 times based on the raw material N-substituted carbamic acid-O-monoaryl ester.

[0384] The reaction temperature is preferably from 10 to 160°C, more preferably from 20 to 140°C and even more preferably from 50 to 120°C. Although the reaction is advantageously carried out at a high temperature in order to increase the reaction rate and complete the reaction quickly, an excessively high temperature may cause undesirable side reactions such as hydrolysis.

[0385] Although varying according to the reaction method, compounds used and reaction conditions, the reaction time can be within a range of from 1 minute to 20 hours. In addition, the reaction may be terminated when the reduction in the amount of raw material N-substituted carbamic acid-O-monoaryl ester has reached a certain level by sampling the reaction liquid and using the known analytical method such as liquid chromatography, or the reaction may be terminated when the average molecular weight of the product in the form of N-substituted carbamic acid-O-aryl ester has reached

a certain level by using the known analytical method such as gel permeation chromatography.

[0386] The N-substituted carbamic acid-O-aryl ester obtained by the method described above is an N-substituted carbamic acid-O-aryl ester represented by the above-mentioned formula (150). Although those N-substituted carbamic acid-O-aryl esters in which m is 0 are preferable in consideration ease of handling and particularly solution viscosity and the like, there are no problems with containing trinuclear or larger polynuclear forms (namely, compounds represented by formula (150) in which m is 1 or more) provided they do not contradict the purport of the present embodiment.

[0387] The N-substituted carbamic acid-O-aryl ester obtained in step (C) is preferably used in step (F).

[0388] Compounds remaining in the reaction liquid of step (C) may be removed from the reaction liquid (such as the methylenating agent, reaction solvent or catalyst used in step (C)). The known method can be used for the removal method, and although examples of such methods may include membrane separation, distillative separation and crystallization, distillative separation is preferable. In the case of removing a compound remaining in the reaction liquid of step (C) by distillative separation, by adding the aromatic hydroxy composition used in the subsequent step (F) to the reaction liquid of step (C) to obtain a mixed liquid, followed by separating by distillation the compounds remaining in the reaction liquid of step (C) (such as the methylenating agent, reaction solvent or catalyst used in step (C)) from the mixed liquid, distillative separation can be carried out without causing precipitation of the N-substituted carbamic acid ester, thereby making this method preferable.

[0389] Although caution is required with respect to the materials of the reactor and the condenser since an acid is used in step (C), there are no particular limitations on the materials provided they do not cause problems such as corrosion attributable to the compounds used in step (C), and the known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary, and for example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added.

<Route 5>

[0390] Route 5) is a method for carrying out step (R), carrying out step (C) and carrying out step (P). Route 5) is one aspect of the method indicated in route 3).

[0391] The method of route 5) is a method for obtaining N-substituted carbamic acid-O-R² ester, in which at least two molecules of the N-substituted carbamic acid-O-R² ester are crosslinked with methylene (-CH₂-) groups, from the N-substituted carbamic acid-O-R² ester obtained in step (R) by carrying out the following step (C) after step (R), in which the organic primary amine used in step (A) is an aromatic organic primary monoamine represented by the following formula (5), and then carrying out step (P) to obtain N-substituted carbamic acid-O-aryl ester derived from the N-substituted carbamic acid-O-R² ester and aromatic hydroxy composition, in which at least two molecules of the N-substituted carbamic acid-O-R² ester are crosslinked with the methylene groups (-CH₂-), by reacting the N-substituted carbamic acid-O-R² ester, in which at least two molecules of the N-substituted carbamic acid-O-R² ester are crosslinked with the methylene groups (-CH₂-), and the aromatic hydroxy composition.


[0392] Step (C): a step of obtaining N-substituted carbamic acid-O-(R² or aryl) ester, in which at least two molecules of the N-substituted carbamic acid-O-(R² or aryl) ester are crosslinked with methylene groups (-CH₂-), by reacting the N-substituted carbamic acid-O-(R² or aryl) ester with formaldehyde or a methylenating crosslinking agent and crosslinking aromatic groups derived from the aromatic organic primary monoamine contained in the N-substituted carbamic acid-O-(R² or aryl) ester with the methylene groups (-CH₂-).

[0393] The N-substituted carbamic acid-O-aryl ester of this route 5) refers to N-substituted carbamic acid-O-aryl ester formed in trace amounts when using an aromatic hydroxy composition in step (A) and/or step (R).

[0394] In this route, step (A) is carried out using an organic primary amine represented by the following formula (5) for the organic primary amine to obtain a compound having ureido groups represented by formula (1) derived from the organic primary amine, followed by carrying out step (R) to obtain an N-substituted carbamic acid-O-R² ester derived from the compound having ureido groups, carrying out step (C) to obtain N-substituted carbamic acid-O-R² ester, in which at least two molecules of the N-substituted carbamic acid-O-R² ester are crosslinked with methylene groups (-CH₂-), and finally carrying out step (P) to obtain an N-substituted carbamic acid-O-aryl ester derived from the N-substituted carbamic acid-O-R² ester and aromatic hydroxy composition, in which the N-substituted carbamic acid-O-R² ester are crosslinked with methylene groups (-CH₂-).

[0395] Namely, the organic primary amine used in this route is an organic primary amine represented by formula (5), the compound having ureido groups obtained in step (A) of this route is a compound having ureido groups represented by formula (41) derived from the organic primary amine, and more specifically a compound having ureido groups represented by formula (148), the N-substituted carbamic acid-O-R² ester obtained in step (R) of this route is an N-substituted


carbamic acid-O-R² ester in which r=1 that is represented by formula (49) and derived from the ureido groups and an alcohol, and more specifically an N-substituted carbamic acid-O-R² ester represented by the following formula (146), the N-substituted carbamic acid-O-R² ester obtained in step (C) of this route is an N-substituted carbamic acid-O-R² ester represented by the following formula (151) derived from the N-substituted carbamic acid-O-R² ester, and the N-substituted carbamic acid-O-aryl ester obtained in step (P) of this route is an N-substituted carbamic acid-O-aryl ester represented by formula (150) derived from the N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition. Indications of specific examples of each of these compounds are respectively contained in previous explanations thereof.



(wherein

at least one location at the ortho position and/or para position of the NH₂ group of an aromatic organic primary monoamine represented by formula (5) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the aromatic organic primary monoamine represented by formula (5) is an integer of from 6 to 13).


[0396] In this case, the compound having ureido groups obtained in step (A) is at least one type of compound having ureido groups represented by the following formula (148). In addition, the groups R³, R⁴, R⁵ and R⁶ in the following formula (148) are selected from the groups R³, R⁴, R⁵ and R⁶ of an organic primary amine represented by the above-mentioned formula (5), and is a compound in which amino groups (-NH₂ groups) of the organic primary amine represented by formula (5) are in the form of ureido groups (-NH-CO-NH₂):



(wherein

at least one location at the ortho position and/or para position of the ureido group of an N-substituted aromatic organic monourea represented by formula (148) is not substituted, groups R³ to R⁶ respectively represent a group substituted at an arbitrary location that maintains aromatic properties of the ring, groups R³ to R⁶ may respectively and independently substitute an aromatic ring or groups R³ to R⁶ may together bond to form a ring with an aromatic ring, groups R³ to R⁶ are hydrogen atoms or groups selected from groups composed of groups in which a group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group and an aryl group having a hydroxy group is bonded by saturated aliphatic bonds and/or ether bonds, the number of carbon atoms of groups R³ to R⁶ is an integral number within a range of from 0 to 7, and the total number of carbon atoms that compose the N-substituted aromatic aromatic organic monourea represented by formula (148), excluding ureido groups (-NH-CO-NH₂), is an integer of from 6 to 13).

[0397] In this case, the N-substituted carbamic acid-O-R² ester obtained in step (R) by carrying out step (A) is at least one type of N-substituted carbamic acid-O-R² ester represented by the following formula (146). In addition, the groups R³, R⁴, R⁵ and R⁶ in the following formula (146) are selected from the groups R³, R⁴, R⁵ and R⁶ of a compound having ureido groups represented by the above-mentioned formula (148), and is a compound in which ureido groups (-NH-CO-NH₂) of a compound having ureido groups represented by formula (148) are in the form of carbamic acid-O-R² ester groups of the group R² deriving from alcohol:




(1 4 6)

(wherein

groups R² to R⁶ are the groups indicated above).

[0398] In this case, the N-substituted carbamic acid-O-R² ester obtained in step (C) by carrying out step (R) is at least one type of N-substituted carbamic acid-O-R² ester represented by the following formula (151). In addition, the groups R³, R⁴, R⁵ and R⁶ in the following formula (151) are selected from the groups R³, R⁴, R⁵ and R⁶ of an organic primary amine represented by the above-mentioned formula (5):



(1 5 1)

(wherein

groups R² to R⁶ are the groups indicated above, and m is an integer from 0 to 6).

[0399] In steps (A) and (R) of this route, the organic primary amine used is an organic primary amine represented by formula (5), and steps (A), (R) and (P) of this route are carried out under the conditions of steps (A) and (R) of route 4). In addition, step (C) of this route is carried out under the conditions of step (C) of route 4) with the exception that the reacted raw material is N-substituted carbamic acid-O-R² ester. In addition, in contrast to the raw material used in route 4) being N-substituted carbamic acid-O-mono(R² or aryl) ester, step (P) of this route is carried out under the conditions of step (P) described in route 4) with the exception of the raw material used being an N-substituted carbamic acid-O-R² ester in which the N-substituted carbamic acid-O-R² ester is crosslinked with methylene groups (-CH₂-).

[0400] Although varying according to the compounds reacted, the reaction conditions for producing N-substituted carbamic acid-O-R² ester by reacting a compound having ureido groups and an alcohol of step (R) are such that the amount of alcohol used has a stoichiometric ratio within a range of from 1 to 500 times based on the ureido groups of the compound having ureido groups used. Although it is preferable to use an excess of alcohol since complexly substituted carbonyl compounds and high molecular weight compounds having carbonyl bonds in molecules thereof form easily if the stoichiometric ratio is less than 1 time, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 1 to 200 times, more preferably within a range of from 1.5 to 100 times and even more preferably within a range of from 2 to 50 times.

[0401] Although varying according to the compounds used, the reaction temperature is preferably within a range of from 100 to 350°C. If the temperature is lower than 100°C, the reaction slows or the reaction hardly proceeds at all, or complexly substituted carbonyl compounds increase, thereby making this undesirable. On the other hand, at temperatures higher than 350°C, the N-substituted carbamic acid-O-R² ester either remains in step (A), the urea (and non-N-substituted carbamic acid ester) formed in the system of step (R) decompose, the hydroxy composition is subjected to dehydrogenative denaturation, or decomposition and denaturation reactions of the product in the form of N-substituted carbamic acid-O-R² ester occur easily, thereby making this undesirable. From such viewpoints, the reaction temperature is more preferably within a range of from 120 to 320°C and even more preferably within a range of from 140 to 300°C.

[0402] As has been previously described, the reaction by which N-substituted carbamic acid-O-R² ester is formed is an equilibrium reaction, and since the reaction is biased towards the reactants side, the reaction is preferably carried out while removing ammonia formed as a by-product outside the system as much as possible. Ammonia is preferably removed so that the ammonia concentration in the reaction liquid is preferably 1000 ppm or less, more preferably 300 ppm or less, even more preferably 100 ppm or less and most preferably 30 ppm or less (being contained in the reaction liquid refers to being contained in a liquid phase when carrying out the step (R)). Ammonia can be removed using

methods such as reactive distillation, use of an inert gas, membrane separation and adsorptive separation. For example, the reactive distillation refers to a method for separating continuously formed ammonia during the reaction by distillation in the form of a gas. This can be carried out while boiling alcohol, a solvent or hydroxy composition in order to increase the distillation efficiency of the ammonia. In addition, a method using an inert gas refers to a method for separating continuously formed ammonia during the reaction from the reaction system in the form of a gas along with the inert gas. Examples of inert gases used may include nitrogen, helium, argon, carbon dioxide, methane, ethane and propane, these may be used alone or as a mixture, and a method in which the inert gas is introduced into the reaction system is preferable. Examples of adsorbents used in methods using adsorptive separation may include adsorbents able to be used under the temperature conditions at which the reaction is carried out, such as silica, alumina, various types of zeolite or diatomaceous earth. These methods for removing ammonia outside the system may be carried out alone or a plurality of types may be carried out in combination.

[0403] A catalyst can be used in the reaction for the purpose of increasing the reaction rate, for example. Examples of catalysts that are used preferably may include basic catalysts such as methylates, ethylates or butyrates (including isomers) of lithium, sodium, potassium, calcium or barium, rare earth elements, antimony or bismuth alone or oxides, sulfides and salts thereof, boron alone or boron compounds, metals of the copper family, zinc family, aluminum family, carbon family and titanium family in the periodic table as well as metal oxides and sulfides thereof, and carbides and nitrides of elements of the carbon family excluding carbon, titanium family, vanadium family and chromium family in the periodic table. Although there are no particular limitations on the amount of catalyst used in the case of using a catalyst, a catalyst can be used within the range of a stoichiometric ratio of from 0.0001 to 100 times the ureido groups of the compound having ureido groups.

[0404] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus and the like, the reaction pressure is generally within a range of preferably from 0.01 Pa to 10 MPa (absolute pressure), and in consideration of ease of the industrial application, the reaction pressure is more preferably within a range of from 0.1 Pa to 5 MPa (absolute pressure), and in consideration of removing gaseous ammonia outside the system, even more preferably from 0.1 Pa to 1.5 MPa (absolute pressure).

[0405] Although varying according to the composition of the reaction system, reaction temperature, method used to remove ammonia, reaction apparatus, reaction pressure and the like, the reaction time (residence time in the case of a continuous reaction) is generally from 0.01 to 100 hours. The reaction time can also be determined according to the formation amount of the target compound in the form of N-substituted carbamic acid-O-R² ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester). For example, the reaction may be stopped after having sampled the reaction liquid, determined the content of N-substituted carbamic acid ester in the reaction liquid (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester) and confirming that the N-substituted carbamic acid-O-R² ester has been formed at a yield of 10% or more based on the compound having ureido groups, or the reaction may be stopped after having confirmed that the yield is 90% or more. The reaction liquid containing the N-substituted carbamic acid-O-R² ester obtained in step (R) is converted to N-substituted carbamic acid-O-aryl ester in a process that contains step (P) to be subsequently described, followed by obtaining an isocyanate in step (F). At that time, if the content of N-substituted carbamic acid-O-R² ester in step (R) is low (the yield thereof is low), there are cases in which this can cause a decrease in the yield of isocyanate. Thus, the yield of the N-substituted carbamic acid-O-R² ester is preferably 50% or more, more preferably 80% or more and even more preferably 90% or more.

[0406] Although the use of a reaction solvent is not necessarily required in the reaction, a suitable solvent is preferably used as a reaction solvent for the purpose of facilitating the reaction procedure, examples of which may include alkanes such as pentane (including isomers), hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; nitrile compounds such as acetonitrile or benzonitrile; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as tetrahydrofuran, 1,4-dioxane, 1,2-dimethoxyethane, diphenyl ether or diphenyl sulfide; ketone compounds such as acetone or methyl ethyl ketone; ester compounds such as ethyl acetate or ethyl benzoate; and sulfoxides such as dimethylsulfoxide or diphenylsulfoxide. Naturally, a hydroxy composition used in excess in the reaction is also preferably used as a reaction solvent.

[0407] The reaction is carried out in a system having a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea (a compound that inherits a carbonyl group possessed by urea, such as a

non-N-substituted carbamic acid ester or biuret, which refers to a compound excluding N-substituted carbamic acid-O-esters) and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out. Although the majority of the reaction is carried out in the liquid phase, it may also be carried out in the gaseous phase depending on the reaction conditions. At that time, the volumetric content of the liquid phase in the reaction in which the reaction is carried out is preferably 50% or less. In the case of carrying out the reaction continuously over a long period of time, although polymeric by-products may form due to fluctuations in operating conditions (such as temperature or pressure) and the like, if the volumetric content of the liquid phase in the reactor is high, adhesion and accumulation of such polymeric by-products in the reactor can be avoided. However, since the efficiency of removal of by-product ammonia may become poor and the yield of the N-substituted carbamic acid-O-R² ester (and depending on the case, the total amount resulting from adding the amount of N-substituted carbamic acid-O-aryl ester) may decrease if the volumetric content of the liquid phase is excessively high, the volumetric content of the liquid phase based on the gaseous phase is preferably 50% or less, more preferably 30% or less and even more preferably 20% or less (the volumetric content of the liquid phase refers to volumetric ratio of the liquid phase based on the volume of the reaction tank in the case of a tank-type reactor, the volume of the stage lower than the feed stage (not including the tank bottom and reboiler) in the case of a column-type reactor, or the volume of the thin film distiller in the case of a thin film distiller).

[0408] Although there are no particular limitations on the reaction apparatus used when carrying out the reaction and a known reactor can be used, a tank-type and/or a column-type reactor is used preferably. The reactor used is preferably equipped with a condenser.

[0409] As was previously described, the reaction is preferably carried out in a system containing a gaseous phase containing a hydroxy composition, a compound having carbonyl groups derived from urea and ammonia produced as a by-product in the reaction, and a liquid phase in which the reaction is carried out, and under conditions such that the volumetric content of the liquid phase in the reactor in which the reaction is carried out is 50% or less, and a reactor that satisfies these conditions is selected for the reactor in which the reaction is carried out.

[0410] More specifically, conventionally known reactors can be suitably combined and used, examples of which may include a stirring tank, a pressurized stirring tank, a depressurized stirring tank, a column-type reactor, a distillation column, a packed column or a thin film distiller.

[0411] There are no particular limitations on the type of condenser provided in the reactor and the known condenser can be used. For example, conventionally known condensers such as a multitubular cylindrical condenser, a double tube condenser, a single tube condenser or an air-cooled condenser can be suitably combined and used. The condenser may be provided inside the reactor or outside the reactor, or may be connected with the reactor by a line, and various types can be employed in consideration of the forms of the reactor and condenser, the manner in which condensed liquid is handled and the like.

[0412] There are no particular limitations on the materials of the reactor and condenser and known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving the compound having ureido groups in the aromatic hydroxy composition, a step of dissolving the aromatic hydroxy compound, a step of separating alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying N-substituted carbamic acid-O-R² ester from the formed reaction liquid, or a step of incinerating or discarding by-products and the like.

[0413] Step (R) is a step of producing N-substituted carbamic acid-O-R² ester by reacting a compound having ureido groups and an alcohol in a liquid phase using a reactor (equipped with a condenser). The gaseous component formed in the step (R) containing a compound having carbonyl groups derived from urea and ammonia formed as a by-product in the reaction is introduced into the condenser provided in the reactor and all or a portion of the alcohol and compound having carbonyl groups derived from urea are condensed followed by recovery of ammonia in the form of a gas.

[0414] At that time, the compound having carbonyl groups derived from urea that is contained in ammonia recovered as a gas from the condenser is present at a specific amount or less. Namely, the ratio of the number of carbonyl groups (-C(=O)-) contained in the compound having carbonyl groups derived from urea contained in the ammonia to the number of ammonia molecules is 1 or less, preferably 0.5 or less, more preferably 0.1 or less and even more preferably 0.01 or less. The reason for making the amount of the compound having carbonyl groups derived from urea contained in the ammonia to be within a specific range is to avoid adhesion and accumulation of solid components in the line for transferring ammonia from the condenser.

[0415] Although all solid components that adhere and accumulate in the line for transferring ammonia cannot be identified, as a result of studies conducted by the inventors of the present invention, the majority were determined to be

compounds having carbonyl groups. Although one possible method for avoiding adhesion and accumulation of such solid components contains heating the line for transferring ammonia to decompose compounds having carbonyl groups, according to studies conducted by the inventors of the present invention, there are many cases in which heating alone causes polymerization of decomposition products (such as isocyanic acid) or reaction of the decomposition products with other compounds having carbonyl groups, thereby making it difficult to completely avoid adhesion and accumulation of solid components. In addition, in the case of simply heating the line, it was determined that compounds having carbonyl groups contained in the ammonia and their decomposition products solidify as a result of being rapidly cooled at the outlet of the line for transferring ammonia (such as the portion in contact with the atmosphere), thereby frequently resulting in prominent adhesion and accumulation of solid components. As a result of conducting extensive studies regarding this problem, the inventors of the present invention surprisingly found that the problem of adhesion and accumulation of solid components can be solved by making the amount of the compound having carbonyl groups derived from carbonic acid derivative contained in the ammonia to be equal to or less than the specific amount described above. Although the mechanism by which this effect is demonstrated is unclear, the inventors of the present invention surmised that adhesion and accumulation in the line is caused by the compound having carbonyl groups derived from the carbonic acid derivative itself as well as decomposition and/or polymerization products of the compound having carbonyl groups derived from the carbonic acid derivative, and that by making the amount of carbonyl groups contained in the compound having carbonyl groups derived from the carbonic acid derivative equal to or less than a specific concentration, adhesion of the compound having carbonyl groups derived from the carbonic acid derivative itself as well as the reaction rates of decomposition and/or polymerization of that compound are lowered considerably.

[0416] On the other hand, the condensed hydroxy composition and compound having carbonyl groups derived from urea are made to be such that the stoichiometric ratio of the condensed hydroxy composition to the condensed compound having carbonyl groups derived from urea is 1 or more, preferably 2 or more and more preferably 3 or more. The reason for defining such ranges is to enable a mixture of the hydroxy composition and compound having carbonyl groups derived from urea condensed in the condenser to be in the form of a homogeneous liquid mixture. As a result, not only is handling of the mixture easier, but occurrence of problems such as adhesion and accumulation of solid components in the condenser can be avoided.


[0417] Moreover, the mixture of the hydroxy composition and the compound having carbonyl groups derived from urea condensed by the condenser in step (R) may be circulated within the reactor and reused in the reaction of step (A). At that time, the amount of ammonia contained in the mixture is preferably 5000 ppm or less, more preferably 3000 ppm or less and even more preferably 2000 ppm or less.

[0418] As has been described above, although various compounds are recovered in the form of compounds having carbonyl groups derived from urea, there are no particular limitations on the reuse of these compounds.

[0419] Step (C) of this route is a step of obtaining N-substituted carbamic acid-O-R² ester, in which at least two molecules of the N-substituted carbamic acid-O-R² ester are crosslinked with methylene groups (-CH₂-), by crosslinking at least one type of N-substituted carbamic acid-O-R² ester (or reaction liquid containing the same) obtained in step (R) with methylene groups (-CH₂-). As a result of carrying out step (C), N-substituted carbamic acid-O-aryl ester is obtained in which at least two molecules of at least one type of N-substituted carbamic acid-O-aryl ester represented by the above-mentioned formula (151) are crosslinked with the methylene groups (-CH₂-).

[0420] Here, when carrying out route 5), preferably an aromatic hydroxy compound represented by formula (2), and more preferably an aromatic hydroxy compound represented by formula (7), is used for the aromatic hydroxy compound that composes the aromatic hydroxy composition used in step (A) and/or step (R) as previously described. More preferably, the aromatic hydroxy compound is that represented by formula (31), naphthol (including isomers), phenoxyphenol (including isomers) or diphenoxyphenol (including isomers), in which the ortho position or para position of the hydroxy group is not substituted, or an aromatic monohydroxy compound in which groups R¹⁹ and R²³ of an aromatic hydroxy compound represented by formula (31) are linear and/or cyclic saturated alkyl groups. The aromatic hydroxy compound that composes the aromatic hydroxy composition used in step (P) of route 5) is preferably an active aromatic hydroxy compound, an aromatic hydroxy compound selected from aromatic hydroxy compounds represented by formula (32), and more preferably an aromatic hydroxy compound represented by formula (38).

[0421] Although compounds in which m is an integer from 0 to 6 are represented by the formulas (151) and (150), this value can be adjusted according to the amount used and reaction rate of the methylenating crosslinking agent that is reacted (to be subsequently explained and frequently referred to as a methylenating agent):



(wherein

R¹ represents a group derived from an organic primary amine as previously defined,
ring A represents a group derived from an aromatic hydroxy compound that composes an aromatic hydroxy composition as previously defined, and which represents a residue in which a single hydrogen atom of hydroxyl groups directly bonded to an aromatic hydrocarbon ring has been removed from the aromatic hydroxy compound, and R³ to R⁶ represent previously defined groups, and m represents an integer of from 0 to 6).

[0422] The following provides an explanation of the step (C). In the following explanation, the N-substituted carbamic acid-O-R² ester obtained in step (R) of route 5) is frequently indicated as N-substituted carbamic acid-O-mono(R² ester) or N-substituted carbamic acid mono-R² ester.

[0423] The known method (see, for example, Federal Republic of Germany Patent No. 1042891) can be used for the step (C).

[0424] Prior to carrying out step (C), in the case of having used an aromatic hydroxy composition in step (R), the aromatic hydroxy composition obtained in step (R) is separated from the reaction liquid containing the resulting N-substituted carbamic acid-O-R² ester. Although step (C) may be carried out in the presence of an aromatic hydroxy compound, since the aromatic hydroxy compound may be crosslinked by the methylenating crosslinking agent resulting in the formation of by-products such as polyaromatic hydroxy compounds, or the amount of methylenating crosslinking agent used may increase, aromatic hydroxy compounds are preferably separated. The known method can be used for the separation method, and although varying according to the compounds used, examples of separation methods that can be used may include a distillation method, an extraction separation method that uses the difference in solubility between the N-substituted carbamic acid-O-R² ester and aromatic hydroxy compound, and a filtration method carried out by solidifying either the N-substituted carbamic acid-O-R² ester or aromatic hydroxy compound. Although these methods cannot be indicated specifically since they depend on the respective physical properties of the compounds used, the method and conditions thereof can be adequately selected within the scope of knowledge of a person with ordinary skill in the art.

[0425] When carrying out step (C), the aromatic hydroxy compound is removed until the amount of aromatic hydroxy compound present following the above-mentioned separation procedure is a stoichiometric ratio of 1 time or less, preferably 0.5 times and more preferably 0.1 times based on the N-substituted carbamic acid-O-R² ester. At this time, the aromatic hydroxy compound may be removed in the presence of solvent used in step (C) to be subsequently explained.

[0426] Examples of methylenating crosslinking agents preferably used in the step (C) may include formaldehyde, paraformaldehyde, trioxane, dialkoxymethanes having a lower alkyl group having 1 to 6 carbon atoms (such as dimethoxymethane, diethoxymethane, dipropoxymethane, dipentanoxymethane or dihexyloxymethane), and diacyloxymethanes having a lower carboxyl group such as diacetoxymethane or dipropioxymethane. These may be used alone or two or more types may be used as a mixture. Among these methylenating crosslinking agents, aqueous solutions of formaldehyde are particularly preferable in consideration of cases of the industrial application, ease of handling of the methylenating crosslinking agent and the like.

[0427] In carrying out the reaction of the step (C), although there are no particular limitations on the ratio of N-substituted carbamic acid-O-mono(R² ester) to methylenating crosslinking agent, the N-substituted carbamic acid-O-mono(R² ester) is preferably used at a stoichiometric ratio of from 2 to 20 times the methylenating crosslinking agent. Although the formation of polynuclear forms (referring to N-substituted carbamic acid-O-R² esters in which three or more aromatic rings (aromatic rings derived from organic primary amine) are bonded by a methylene crosslinked structure, or in other words, compounds in which m is an integer of 1 or more in the above-mentioned formula (151)) is inhibited the greater the amount of N-substituted carbamic acid-mono (R² ester) used, if an overly excessive amount of N-substituted carbamic acid-O-mono(R² ester) is used, there are many cases in which the remaining amount of raw material N-substituted carbamic acid-O-mono(R² ester) increases. Thus, the amount of N-substituted carbamic acid-O-mono(R² ester) used in terms of the stoichiometric ratio with the methylenating crosslinking agent is more preferably within a range of from 3 to 15 times and even more preferably within a range of from 5 to 10 times.

[0428] An acid catalyst is preferably used as a catalyst in the condensation reaction. Examples of acid catalysts may include inorganic acids such as hydrochloric acid, sulfuric acid, phosphoric acid or boric acid, and organic acids such as formic acid, acetic acid, oxalic acid or toluenesulfonic acid. In addition, acids referred to as super strong acids such as hydrobromic acid, perchloric acid, chlorosulfonic acid or trifluoromethanesulfonic acid are also effective. In addition, ion exchange resins having acidic groups such as carboxyl groups or sulfonate groups as well as acids referred to as Lewis acids, such as trifluoroboric acid, iron chloride, aluminum chloride, zinc chloride or titanium chloride, are also effective.

[0429] In the case of a protonic acid such as the above-mentioned inorganic acids, organic acids or super strong acids, the amount of these acids used is within a range of a stoichiometric ratio of from 0.001 to 10, and preferably within a

range of from 0.01 to 5, based on the raw material N-substituted carbamic acid ester. In addition, in the case these acids are used in the form of aqueous solutions, they can be used at a concentration within a range of from 10 to 95% by weight and preferably within a range of 20 to 80% by weight based on the amount of water in the reaction system. If the concentration is less than 10% by weight, the reaction rate of the condensation reaction becomes extremely slow, while

if the concentration exceeds 95% by weight, hydrolysis of the raw material and other undesirable side reactions may occur. **[0430]** The condensation reaction can be carried out in the presence or absence of solvent. Examples of solvents that are used preferably may include linear, branched or cyclic hydrocarbons such as pentane, hexane, heptane, octane, nonane, decane, hexadecane, cyclopentane or cyclohexane; aromatic hydrocarbons such as benzene, toluene or xylene and their alkyl-, halogen- and nitro-substituted forms; halogenated hydrocarbons such as chloroform, methylene chloride, carbon tetrachloride, dichloroethane, trichloroethane or tetrachloroethane; aliphatic alkyl esters such as methyl acetate or ethyl acetate; and ethers such as diethyl ether, diisopropyl ether, dioxane or tetrahydrofuran. In addition, thioacetals, acetals or acylals are used preferably since they do not form free formaldehyde under the reaction conditions and do not substantially form water by reacting with water formed as a by-product in the reaction. Acetals and acylals are used particularly preferably. In addition, the above-mentioned acids themselves are also preferably used as solvents. These solvents may be used alone or two or more types may be used as a mixture.

[0431] These solvents can be used at a weight ratio within a range of from 0.1 to 100 times and preferably within a range of from 0.2 to 50 times based on the raw material N-substituted carbamic acid-O-mono(R² ester).

[0432] The reaction temperature is preferably from 10 to 160°C, more preferably from 20 to 140°C and even more preferably from 50 to 120°C. Although the reaction is advantageously carried out at a high temperature in order to increase the reaction rate and complete the reaction quickly, an excessively high temperature may cause undesirable side reactions such as hydrolysis.

[0433] Although varying according to the reaction method, compounds used and reaction conditions, the reaction time can be within a range of from 1 minute to 20 hours. In addition, the reaction may be terminated when the reduction in the amount of raw material N-substituted carbamic acid-O-mono(R² ester) has reached a certain level by sampling the reaction liquid and using the known analytical method such as liquid chromatography, or the reaction may be terminated when the average molecular weight of the product in the form of N-substituted carbamic acid-O-aryl ester has reached a certain level by using the known analytical method such as gel permeation chromatography.

[0434] The N-substituted carbamic acid-O-R² ester obtained by the method described above is an N-substituted carbamic acid-O-R² ester represented by the above-mentioned formula (151). Although those N-substituted carbamic acid-O-R² esters in which m is 0 are preferable in consideration ease of handling and particularly solution viscosity and the like, there are no problems with containing trinuclear or larger polynuclear forms (namely, compounds represented by formula (151) in which m is 1 or more) provided they do not contradict the purport of the present embodiment.

[0435] The N-substituted carbamic acid-O-R² ester obtained in step (C) is preferably used in step (P).

[0436] Compounds remaining in the reaction liquid of step (C) may be removed from the reaction liquid (such as the methylenating agent, reaction solvent or catalyst used in step (C)). The known method can be used for the removal method, and although examples of such methods may include membrane separation, distillative separation and crystallization, distillative separation is preferable. In the case of removing a compound remaining in the reaction liquid of step (C) by distillative separation, by adding the aromatic hydroxy composition used in the subsequent step (P) to the reaction liquid of step (C) to obtain a mixed liquid, followed by distilling and separating the compounds remaining in the reaction liquid of step (C) (such as the methylenating agent, reaction solvent or catalyst used in step (C)) from the mixed liquid, distillative separation can be carried out without causing precipitation of the N-substituted carbamic acid ester, thereby making this method preferable.

[0437] Although caution is required with respect to the materials of the reactor and the condenser since an acid is used in step (C), there are no particular limitations on the materials provided they do not cause problems such as corrosion attributable to the compounds used in step (C), and known materials can be used. Examples of materials that can be used may include glass, stainless steel, carbon steel, Hastelloy, glass-lined base materials and Teflon (registered trademark) coated materials. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps can also be added as necessary, and for example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added.

<Step (P)> Transesterification Step

[0438] Since this step is a step of converting the ester group of the N-substituted carbamic acid-O-R² ester, it is also generally referred to as a "transesterification step" in the present embodiment.

[0439] Step (P): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting N-substituted carbamic acid-O-R² ester and an aromatic hydroxy composition (composition containing at least one type of aromatic hydroxy compound

represented by the following formula (2)) in a liquid phase and extracting alcohol formed as a by-product to a gaseous phase.

[0440] FIG. 6 shows a conceptual drawing depicting the step (P).

[0441] Furthermore, an alcohol derived from N-substituted carbamic acid-O-R² ester is formed in the step (P). The following provides an explanation of step (P).

[0442] The aromatic hydroxy compound in the reacted aromatic hydroxy composition may be any of an aromatic hydroxy compound represented by the above-mentioned formula (2), formula (7), formula (31), formula (32), formula (38), formula (39) or formula (40). The case in which an aromatic hydroxy compound represented by formula (7) or formula (31) is contained is preferable, the case in which an aromatic hydroxy composition is used that contains an active aromatic hydroxy compound represented by formula (32) is more preferable, and the case in which an aromatic hydroxy composition is used that contains an active aromatic hydroxy compound represented by formula (38) is even more preferable.

[0443] Various methods can be carried out for the step (P) according to the compounds used and the like with reference to the known methods (see, for example, WO 2008/059953).

[0444] Although varying according to the compounds reacted, the reaction conditions of step (P) are such that the amount of aromatic hydroxy compound in the aromatic hydroxy composition used has a stoichiometric ratio within a range of from 2 to 1000 times based on the ester groups that compose the raw material N-substituted carbamic acid-O-R² ester. Although it is preferable to use an excess of the aromatic hydroxy compound based on ester groups that compose the raw material N-substituted carbamic acid-O-R² ester in order to complete the reaction quickly, in consideration of the size of the reactor, the stoichiometric ratio is preferably within a range of from 2 to 100 times and more preferably within a range of from 5 to 50 times.

[0445] The reaction temperature is generally within a range of from 100 to 300°C, and a high temperature is preferable for increasing the reaction rate, but since side reactions may occur easily at high temperatures, the reaction temperature is preferably within a range of from 150 to 250°C. The known cooling apparatus or heating apparatus may be installed in the reactor for maintaining a constant reaction temperature. In addition, although varying according to the types of compounds used and the reaction temperature, the reaction may be carried out at reduced pressure, normal pressure or increased pressure and generally at a reaction pressure within a range of from 20 to 1 x 10⁶ Pa. There are no particular limitations on the reaction time (residence time in the case of a continuous method), and is generally from 0.001 to 100 hours, preferably from 0.01 to 50 hours and more preferably from 0.1 to 30 hours. In addition, the reaction can be terminated after confirming that a desired amount of the target N-substituted carbamic acid-O-aryl ester has been formed by sampling the reaction liquid and determining the amount formed by liquid chromatography, for example.

[0446] Although a catalyst is not necessarily required in step (P), a catalyst may be used without problem to lower the reaction temperature or complete the reaction more quickly. The catalyst is used at 0.01 to 30% by weight and preferably at 0.5 to 20% by weight based on the weight of the N-substituted carbamic acid-O-R² ester. Examples of catalysts may include Lewis acids as well as transition metal compounds that form a Lewis acid, organic tin compounds, copper group metals, zinc or iron group metal compounds, and more specifically, Lewis acids and transition metal compounds that form a Lewis acid represented by AlX₃, TiX₃, TiX₄, VOX₃, VX₅, ZnX₂, FeX₃ or SnX₄ (wherein, X represents a halogen, an acetoxy group, an alkoxy group or an aryloxy group); organic tin compounds represented by (CH₃)₃SnOCHCH₃, (C₂H₅)₃SnOCOC₆H₅, Bu₃SnOCOCH₃, Ph₃SnOCOCH₃, Bu₂Sn(OCOCH₃)₂, Bu₂Sn(OCOC₁₁H₂₃)₂, Ph₃SnOCH₃, (C₂H₅)₃SnOPh, Bu₂Sn(OCH₃)₂, Bu₂Sn(OC₂H₅)₂, Bu₂Sn(OPh)₂, Ph₂Sn(CH₃)₂, (C₂H₅)₃SnOH, PhSnOH, Bu₂SnO, (C₈H₁₇)₂SnO, Bu₂SnCl₂ or BuSnO(OH); copper family metal compounds represented by CuCl, CuCl₂, CuBr, CuBr₂, CuI, CuI₂, Cu(OAc)₂, Cu(acac)₂, copper olefinate, Bu₂Cu, (CH₃O)₂Cu, AgNO₃, AgBr, silver picrate or AgC₆H₆ClO₄; zinc compounds represented by Zn(acac)₂; and, iron family metal compounds represented by Fe(C₁₀H₈)(CO)₅, Fe(CO)₅, Fe(C₄H₆)(CO)₃, Co(mesitylene)₂(PEt₂Ph₂), CoC₅F₅(CO)₇ or ferrocene. (In the above listing of examples, Bu refers to a butyl group, Ph refers to a phenyl group, and acac refers to an acetyl acetone chelate ligand.) Amines such as 1,4-diazabicyclo[2,2,2]octane, triethylenediamine or triethylamine are suitable for use as catalysts, while organic metal catalysts such as dibutyl tin dilaurate, lead octoate or stannous octoate are particularly preferable. These compounds may be used alone or two or more types may be used as a mixture.

[0447] Although the use of a reaction solvent is not necessarily required in the present embodiment, a suitable inert solvent can be preferably used as a reaction solvent for the purpose of facilitating the reaction procedure and the like, examples of which may include alkanes such as hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl

ethyl ketone or acetophenone; esters such as dibutyl phthalate, dihexyl phthalate, dioctyl phthalate or benzylbutyl phthalate; ethers and thioethers such as diphenyl ether or diphenyl sulfide; sulfoxides such as dimethylsulfoxide or diphenylsulfoxide; and silicone oil. These solvents can be used alone or two or more types can be used as a mixture.

5 [0448] The transesterification reaction in the present embodiment is an equilibrium reaction. Thus, it is preferable to allow the reaction to proceed while removing the product in the form of alcohol (alcohol derived from the raw material N-substituted carbamic acid-O-R² ester) from the reaction system in order to carry out transesterification efficiently. Thus, if the aromatic hydroxy compound is selected such that the standard boiling point of the aromatic hydroxy compound used in transesterification is higher than the standard boiling point of the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester, the compound having the lowest standard boiling point in the reaction system becomes the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester, thereby facilitating removal of products from the reaction system. Based on the finding that generally industrially adequate distillative separation is possible if the standard boiling points of two components to be separated are 10°C or more apart, an aromatic hydroxy compound is preferably used such that the standard boiling point of the compound having the lowest standard boiling point in the aromatic hydroxy composition (based on a comparison of standard boiling points) is 10°C or more higher than the standard boiling point of the alcohol.

10 [0449] In addition, transesterification is preferably carried out by a continuous method to allow transesterification to proceed efficiently. Namely, the raw material N-substituted carbamic acid-O-R² ester and the aromatic hydroxy composition are continuously supplied to a reactor, transesterification is carried out, alcohol derived from the raw material N-substituted carbamic acid-O-R² ester that is formed is extracted from the reactor in the form of a gaseous component, and a reaction liquid containing the N-substituted carbamic acid-O-aryl ester formed and the aromatic hydroxy composition is continuously extracted from the bottom of the reactor.

15 [0450] Although the material of the reactor and lines used to carry out transesterification may be known materials provided they do not have a detrimental effect on the starting substances and reactants, materials such as SUS304, SUS316 or SUS316L are inexpensive and can be used preferably. Known process apparatuses such as a flow meter, a thermometer and other measuring instruments or a reboiler, a pump or a condenser and the like may be added as necessary, the known method such as steam or a heater may be used for heating, and the known method such as air cooling, cooling water or brine can be used for cooling. Steps may also be added as necessary. For example, steps and apparatuses able to be conceived by a person or engineer with ordinary skill in the art may be added, such as a step of dissolving the aromatic hydroxy compound, a step of separating the alcohol, a step of separating and/or purifying the aromatic hydroxy compound, a step of purifying the N-substituted carbamic acid-O-aryl ester from the formed reaction liquid or a step of incinerating or discarding by-products and the like. There are no particular limitations on the type of reactor, and a known tank-type or a column-type reactor can be used. Various known methods are used for such a reactor, examples of which may include types using reactors containing a stirring tank, a multistage stirring tank, a distillation column, a multistage distillation column, a multitubular reactor, a continuous multistage distillation column, a packed column, a thin film evaporator, a reactor provided with a support inside, a forced circulation reactor, a falling film evaporator, a falling drop evaporator, a trickle flow reactor or a bubble column, and types using combinations thereof. Methods using a thin film evaporator or a column-type reactor are preferable from the viewpoint of efficiently shifting the equilibrium to the products side, while a structure having a large gas-liquid contact area is preferable for being able to rapidly transfer the alcohol derived from the raw material N-substituted carbamic acid-O-R² ester formed to the gaseous phase.

20 [0451] The multistage distillation column refers to a distillation column having multiple stages in which the number of theoretical plates of distillation is 2 or more, and any multistage distillation column may be used provided it allows continuous distillation. Any multistage distillation column can be used for the multistage distillation column provided it is ordinarily used as a multistage distillation column, examples of which may include tray column types using a tray such as a bubble tray, a porous plate tray, a valve tray or a counter-current tray, and packed column types packed with various types of packing materials such as a Raschig ring, a Lessing ring, a pole ring, a Berl saddle, a Interlock saddle, a Dixon packing, a McMahon packing, a Helipack, Sulzer packing or Mellapak. Any packed column can be used provided the column is packed with the known packing material as described above. Moreover, a combination tray-packed column type is also used preferably that combines a tray portion with a portion packed with a packing material.

25 [0452] A line for supplying inert gas and/or liquid inert solvent from the lower portion of the reactor may be separately attached, and in the case the mixture of the target N-substituted carbamic acid-O-aryl ester and aromatic hydroxy compound contains raw material N-substituted carbamic acid-O-R² ester, a line may be attached for re-circulating all or a portion of the mixture to the reactor. Furthermore, in the case of using the above-mentioned inert solvent, the inert solvent may be in the form of a gas and/or a liquid.

30 [0453] The gaseous component extracted from the reactor containing alcohol derived from the raw material N-substituted carbamic acid-O-R² ester is preferably purified using the known method such as that which uses a distillation column, and can be reused as an alcohol of step (A) and/or step (R).


35 [0454] The following provides an explanation of step (F) for obtaining isocyanate by thermally decomposing an N-

substituted carbamic acid-O-aryl ester obtained in the above-mentioned routes 1) to 5).

<Step (F): Step of Obtaining Isocyanate by Thermal Decomposition Reaction of N-substituted Carbamic Acid-O-Aryl Ester>

[0455] Step (F) is a method for obtaining isocyanate represented by the following formula (6), derived from an N-substituted carbamic acid-O-aryl ester, and an aromatic hydroxy composition by thermally decomposing the N-substituted carbamic acid-O-aryl ester in the following step (F).

[0456] Step (F): a step of obtaining an isocyanate and aromatic hydroxy composition from N-substituted carbamic acid-O-aryl ester:



(wherein

R¹ represents an organic group which has an integral number of carbon atoms within a range of from 1 to 85, and which is substituted with number s of NCO groups, and s represents an integer of from 1 to 10).

[0457] The N-substituted carbamic acid-O-aryl ester produced according to the method described above is preferably used to produce isocyanate. The following provides an explanation of a step of producing isocyanate by applying the N-substituted carbamic acid-O-aryl ester to a thermal decomposition reaction (to be referred to as step (F)).

[0458] Although a solvent may or may not be used in the step (F), it is preferably carried out in the presence of an aromatic hydroxy composition. Since an aromatic hydroxy composition is used in routes 1), 3) and 5) when carrying out step (B) or step (P), step (F) may be carried out using the reaction liquid obtained in those steps, or step (F) may be carried out by adjusting the amount of aromatic hydroxy composition if necessary. Alternatively, since an aromatic hydroxy composition is used in step (C) of routes 2) and 4), step (F) may be carried out by reusing the separated aromatic hydroxy composition, the amount of aromatic hydroxy composition used may be adjusted, or an aromatic hydroxy composition may be newly prepared and used. The solvent used in step (C) may be separated from the N-substituted carbamic acid-O-aryl ester or may be used with the aromatic hydroxy composition.

[0459] Although adjustment of the amount of aromatic hydroxy composition or the preparation of a new aromatic hydroxy composition has been described above, the amount thereof is such that the ratio of the number of aromatic hydroxy compounds in the aromatic hydroxy composition to the total number of ester groups of the -O-aryl ester contained in the N-substituted carbamic acid-O-aryl ester is from 0.2 to 50, preferably from 0.3 to 30 and more preferably from 1 to 20 in consideration of transfer efficiency of the N-substituted carbamic acid-O-aryl ester and size of the storage tank during storage. Examples of other solvents that may be added may include suitable inert solvents for the purpose of facilitating the reaction procedure and the like, including alkanes such as hexane (including isomers), heptane (including isomers), octane (including isomers), nonane (including isomers) or decane (including isomers); aromatic hydrocarbons and alkyl-substituted aromatic hydrocarbons such as benzene, toluene, xylene (including isomers), ethyl benzene, diisopropyl benzene (including isomers), dibutyl benzene (including isomers) or naphthalene; aromatic compounds substituted with a halogen or nitro group such as chlorobenzene, dichlorobenzene (including isomers), bromobenzene, dibromobenzene (including isomers), chloronaphthalene, bromonaphthalene, nitrobenzene or nitronaphthalene; polycyclic hydrocarbon compounds such as diphenyl, substituted diphenyl, diphenyl methane, terphenyl, anthracene or dibenzyl toluene (including isomers); aliphatic hydrocarbons such as cyclohexane, cyclopentane, cyclooctane or ethylcyclohexane; ketones such as methyl ethyl ketone or acetophenone; and dibutyl phthalate, dihexyl phthalate or dioctyl phthalate.

[0460] The reaction temperature of the thermal decomposition reaction carried out in step (F) is generally within a range of from 100 to 300°C, and although a high temperature is preferable for increasing the reaction rate, since side reactions as previously described may be induced by the N-substituted carbamic acid-O-aryl ester and/or product in the form of isocyanate at high temperatures, the reaction temperature is preferably within a range of from 150 to 250°C. The known cooling apparatus or heating apparatus may be installed in the reactor to maintain a constant reaction temperature. In addition, although varying according to the types of compounds used and the reaction temperature, the reaction may be carried out at reduced pressure, normal pressure or increased pressure and normally at a reaction pressure within a range of from 20 to 1 x 10⁶ Pa. There are no particular limitations on the reaction time (residence time in the case of a continuous method), and is generally from 0.001 to 100 hours, preferably from 0.005 to 50 hours and more preferably from 0.01 to 10 hours.

[0461] Although a catalyst is preferably not used in the present embodiment, in the case of using a catalyst in any of the steps when producing the N-substituted carbamic acid-O-aryl ester, the catalyst residue may be supplied to the

thermal decomposition step, although the presence of such catalyst residue does not present a problem.

[0462] In the case of having stored an N-substituted carbamic acid-O-aryl ester at a high temperature for a long period of time, there are cases in which side reactions occur such as a reaction by which urea bond-containing compounds are formed by an ester decarboxylation reaction of two molecules of N-substituted carbamic acid-O-aryl ester, or a reaction by which allophanate groups are formed by a reaction with isocyanate formed by thermal decomposition of N-substituted carbamic acid-O-aryl ester. Thus, the amount of time during which the N-substituted carbamic acid-O-aryl ester and the isocyanate are held at a high temperature is preferably as short as possible. Thus, the thermal decomposition reaction is preferably carried out in the form of the continuous method. The continuous method refers to a method in which a mixture containing the N-substituted carbamic acid-O-aryl ester is continuously supplied to a reactor where it is subjected to a thermal decomposition reaction, and the isocyanate and aromatic hydroxy compound formed are continuously extracted from the thermal decomposition reactor. In this continuous method, low boiling point components formed by thermal decomposition of urethane are preferably recovered from the upper portion of the thermal decomposition reactor in the form of gaseous phase components, while the remainder is recovered from the bottom of the thermal decomposition reactor in the form of liquid phase components. Although all compounds present in the thermal decomposition reactor can be recovered as gaseous phase components, the presence of liquid phase components in the thermal decomposition reactor has the effect of dissolving polymeric substances formed by side reactions caused by the N-substituted carbamic acid-O-aryl ester and/or isocyanate, thereby preventing adhesion and solidification of the polymeric substances in the thermal decomposition reactor. Although isocyanate and aromatic hydroxy compound are formed by thermal decomposition of N-substituted carbamic acid-O-aryl ester, at least one of these compounds is recovered in the form of a gaseous phase component. Which compound is recovered as a gaseous phase component is dependent upon such factors as the conditions of the thermal decomposition reaction.

[0463] Here, although the term "low boiling point component formed by thermal decomposition of N-substituted carbamic acid-O-aryl ester" used in the present embodiment is equivalent to the aromatic hydroxy compound and/or isocyanate formed by thermal decomposition of the N-substituted carbamic acid-O-aryl ester, it particularly refers to a compound that is able to be present as a gas under the conditions in which the thermal decomposition reaction is carried out.

[0464] For example, a method can be employed in which the isocyanate and aromatic hydroxy compound formed by the thermal decomposition reaction can be recovered in the form of gaseous phase components, while a liquid phase component is recovered that contains N-substituted carbamic acid-O-aryl ester. In this method, the isocyanate and aromatic hydroxy compound may be recovered separately in the thermal decomposition reactor. The recovered gaseous phase component that contains isocyanate is preferably supplied to a distillation apparatus for separating and purifying the isocyanate in the gaseous phase. Although the recovered gaseous phase component that contains isocyanate can be supplied to a distillation apparatus after converting to a liquid phase with a condenser and the like, there are many cases in which the apparatus becomes complex and the amount of energy used becomes large, thereby making this undesirable. In the case the liquid phase component contains N-substituted carbamic acid-O-aryl ester, all or a portion of the liquid phase component is preferably supplied to the upper portion of the thermal decomposition reactor where the N-substituted carbamic acid-O-aryl ester is again subjected to a thermal decomposition reaction. The upper portion of the thermal decomposition reactor as referred to here indicates the portion two or more stages above the bottom of the column in terms of the number of theoretical plates in the case of the thermal decomposition reactor being a distillation column, while in the case the thermal decomposition reactor is a thin film distiller, indicates the portion above the heated transfer surface portion. When supplying all or a portion of the liquid phase component to the upper portion of the thermal decomposition reactor, the liquid phase component is transferred while holding at a temperature of preferably from 50 to 180°C, more preferably from 70 to 170°C and even more preferably from 100 to 150°C.

[0465] In addition, a method can also be employed in which, for example, the isocyanate and aromatic hydroxy compound formed by the thermal decomposition reaction are recovered in the form of gaseous phase components, while a liquid phase component containing N-substituted carbamic acid-O-aryl ester is recovered from the bottom of the thermal decomposition reactor. In this method as well, the recovered gaseous component that contains isocyanate is preferably supplied to a distillation apparatus for separating and purifying the isocyanate in the gaseous phase. On the other hand, all or a portion of the liquid phase component that contains N-substituted carbamic acid-O-aryl ester is supplied to the upper portion of the thermal decomposition reactor where the N-substituted carbamic acid-O-aryl ester is again subjected to a thermal decomposition reaction. When supplying all or a portion of the liquid phase component to the upper portion of the thermal decomposition reactor, the liquid phase component is transferred while holding at a temperature of preferably from 50 to 180°C, more preferably from 70 to 170°C and even more preferably from 100 to 150°C.

[0466] Moreover, a method can also be employed in which, for example, the aromatic hydroxy compound among the isocyanate and aromatic hydroxy compound formed by the thermal decomposition reaction is recovered in the form of a gaseous phase component, while a mixture containing the isocyanate is recovered in the form of a liquid phase component from the bottom of the thermal decomposition reactor. In this case, the liquid phase component is supplied

to a distillation apparatus to recover the isocyanate. In the case N-substituted carbamic acid-O-aryl ester is contained in the liquid phase component, all or a portion of the mixture containing N-substituted carbamic acid-O-aryl ester is preferably supplied to the upper portion of the thermal decomposition reactor and the N-substituted carbamic acid-O-aryl ester is again subjected to a thermal decomposition reaction. When supplying all or a portion of the liquid phase component to the thermal decomposition reactor, the liquid phase component is transferred while holding at a temperature of preferably from 50 to 180°C, more preferably from 70 to 170°C and even more preferably from 100 to 150°C.

[0467] Although previously described, in the thermal decomposition reaction, the liquid phase component is preferably recovered from the bottom of the thermal decomposition reactor. This is because the presence of a liquid phase component in the thermal decomposition reactor has the effect of dissolving polymeric substances formed by side reactions caused by the N-substituted carbamic acid-O-aryl ester and/or isocyanate as previously described, thereby enabling the polymeric substances to be discharged from the thermal decomposition reactor and preventing adhesion and solidification of the polymeric substances in the thermal decomposition reactor.

[0468] In the case the liquid phase component contains N-substituted carbamic acid-O-aryl ester, although all or a portion of the liquid phase component is supplied to the upper portion of the thermal decomposition reactor where the N-substituted carbamic acid-O-aryl ester is again subjected to a thermal decomposition reaction, polymeric by-products may accumulate in the liquid phase component if this step is repeated. In this case, all or a portion of the liquid phase component can be removed from the reaction system or held to a fixed concentration to reduce accumulation of polymeric by-products.

[0469] Although there are no particular limitations on the type of the thermal decomposition reactor, the known distillation apparatus is used preferably in order to efficiently recover gaseous phase components. Various known methods are used for such a reaction vessel, examples of which may include types using reaction vessels containing a distillation column, a multistage distillation column, a multitubular reactor, a continuous multistage distillation column, a packed column, a thin film evaporator, a reactor provided with a support inside, a forced circulation reactor, a falling film evaporator or a falling drop evaporator, and types using combinations thereof. From the viewpoint of rapidly removing low boiling point components from the reaction system, a method using a tubular reactor is preferable, while a method using a reactor such as a tubular thin film evaporator or a tubular falling film evaporator is more preferable, and a structure having a large gas-liquid contact area is preferable for being able to rapidly transfer the low boiling point components formed to the gaseous phase.

[0470] Although the known material may be used for the material of the thermal decomposition reactor and lines provided it does not have a detrimental effect on the urethane or products in the form of the aromatic hydroxy compound and isocyanate, SUS304, SUS316 or SUS316L are inexpensive and can be used preferably.

[0471] The aromatic hydroxy compounds contained in the gaseous phase components and/or liquid phase component obtained in the thermal decomposition reaction as described above can each be separated, recovered and reused. More specifically, aromatic hydroxy compounds can be reused as aromatic hydroxy compounds used in step (A) and/or step (A) and/or step (B) and/or step (R) and/or step (P). In other words, it is preferable that the aromatic hydroxy composition obtained in the step (F) is separated from isocyanate, and then used by recycling to the step (A) and/or the step (B) described in route 1), or to the step (A) and/or the step (R) and/or the step (P) described in route 3).

[0472] In addition, in a preferable aspect of the present embodiment, unreacted N-substituted carbamic acid-O-aryl ester that did not undergo thermal decomposition in step (F) is preferably used by recycling to the above-mentioned step (A) and/or step (B) and/or step (R) and/or step (P) and/or step (F).

<Cleaning the Reactor>

[0473] There are cases in which polymeric side-reaction products may be formed, albeit in minute amounts, in the production N-substituted carbamic acid-O-aryl ester and the production of isocyanate using the N-substituted carbamic acid-O-aryl ester of the present embodiment. Since these polymeric side-reaction products have a high solubility with respect to aromatic hydroxy composition used in the present embodiment, they are removed from the reactor in the form of a solution of the aromatic hydroxy composition. However, in cases of fluctuations in reaction apparatus operating conditions or cases of long-term operation, the polymeric side-reaction products may adhere to the reactor.

[0474] In such cases, the inside (and particularly the inner walls) of the reactor can be cleaned with an acid that is a good solvent of the polymeric side-reaction products to keep the inside of the reactor clean.

[0475] There are no particular limitations on the cleaning acid provided it dissolves the polymeric side-reaction products, and although both organic acids and inorganic acids may be used, organic acids are used preferably. Although examples of organic acids that can be used may include carboxylic acid, sulfonic acid, sulfinic acid, phenols, enols, thiophenols, imides, oximes and aromatic sulfonamides, carboxylic acid and phenols are used preferably. Examples of such compounds may include saturated or unsaturated aliphatic monocarboxylic acid compounds such as formic acid, acetic acid, propionic acid, n-butyric acid, isobutyric acid, valeric acid, isovaleric acid, 2-methylbutanoic acid, pivalic acid, hexanoic acid, isocaproic acid, 2-ethylbutanoic acid, 2,2-dimethylbutanoic acid, heptanoic acid (including isomers), octanoic acid

(including isomers), nonanoic acid (including isomers), decanoic acid (including isomers), undecanoic acid (including isomers), dodecanoic acid (including isomers), tetradecanoic acid (including isomers), hexadecanoic acid (including isomers), acrylic acid, crotic acid, isocrotic acid, vinylacetic acid, methacrylic acid, angelic acid, tiglic acid, arylacetate or undecenoic acid (including isomers); saturated or unsaturated aliphatic dicarboxylic acids such as oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, heptanedioic acid (including isomers), octanedioic acid (including isomers), nonanedioic acid (including isomers), decanedioic acid (including isomers), maleic acid, fumaric acid, methylmaleic acid, methylfumaric acid, pentenedioic acid (including isomers), itaconic acid or allylmalonic acid; saturated or unsaturated aliphatic tricarboxylic acid compounds such as 1,2,3-propanetricarboxylic acid, 1,2,3-propenetricarboxylic acid or 2,3-dimethylbutane-1,2,3-tricarboxylic acid; aromatic carboxylic acid compounds such as benzoic acid, methylbenzoic acid (including isomers), ethylbenzoic acid (including isomers), propylbenzoic acid (including isomers), dimethylbenzoic acid (including isomers) or trimethylbenzoic acid (including isomers); aromatic dicarboxylic acid compounds such as phthalic acid, isophthalic acid, terephthalic acid or methylisophthalic acid; aromatic tricarboxylic acid compounds such as hemimellitic acid, trimellitic acid or trimesic acid; phenol; mono-substituted phenols such as methyl phenol (including isomers), ethyl phenol (including isomers), propyl phenol (including isomers), butyl phenol (including isomers), pentyl phenol (including isomers), hexyl phenol (including isomers), heptyl phenol (including isomers), octyl phenol (including isomers), nonyl phenol (including isomers), decyl phenol (including isomers), dodecyl phenol (including isomers), phenyl phenol (including isomers), phenoxyphenol (including isomers) or cumyl phenol (including isomers); and dimethyl phenol (including isomers), diethyl phenol (including isomers), dipropyl phenol (including isomers), dibutyl phenol (including isomers), dipentyl phenol (including isomers), dihexyl phenol (including isomers), diheptyl phenol (including isomers), dioctyl phenol (including isomers), dinonyl phenol (including isomers), didecyl phenol (including isomers), didodecyl phenol (including isomers), diphenyl phenol (including isomers), diphenoxyphenol (including isomers) or dicumyl phenol (including isomers). In consideration of effects in the case of the cleaning solvent remaining after cleaning the thermal decomposition reactor, more preferable examples of these organic acids may include aromatic hydroxy compounds, while even more preferable examples may include compounds of the same types as aromatic hydroxy compounds formed in the production method of N-substituted carbamic acid-O-aryl ester and/or thermal decomposition reaction of N-substituted carbamic acid-O-aryl ester of the present embodiment.

[0476] Furthermore, in the case of using an aromatic hydroxy compound for the cleaning acid, the standard boiling point of the aromatic hydroxy compound preferably has a difference in boiling point of 10°C or more from the standard boiling point of isocyanate formed by the thermal decomposition reaction of N-substituted carbamic acid-O-aryl ester described above from the viewpoint of cleaning effects.

[0477] Various methods can be used to clean the reactor using the above-mentioned cleaning solvent, examples of which may include a method in which the reactor is cleaned by introducing the cleaning solvent from the upper portion of the reactor, and a method in which the inside of the reactor is cleaned by introducing the cleaning agent into the bottom of the reactor and then boiling the cleaning reagent up through the reactor.

[0478] It is not necessary to carry out the cleaning procedure each time the reaction is carried out, but rather can be determined arbitrarily based on the compounds used, operating rate and the like, and the cleaning procedure is preferably carried out once every 1 to 20000 hours of operating time, more preferably once every one day to one year of operating time, and even more preferably once every one month to one year of operating time. The reactor may be equipped with a line for introducing the cleaning agent.

[0479] The steps (D), (E) and (G) explained below are carried out in addition to the above-mentioned method.

<Step (D)>

[0480] Urea is recovered by carrying out the following step (D) before step (B), step (R) or step (P) and/or simultaneous to step (B), step (R) or step (P):

step (D): a step of removing urea by distillation or sublimation.

[0481] When producing the compound having the ureido groups as described in step (A), urea is preferably used in excess based on the organic primary amine. At this time, since compounds having ureylene groups may be formed as by-products in the case an excess amount of unreacted urea is present in step (B), step (R) or step (P) while still containing an excess of urea, the urea is separated by distillation or sublimation. The known method can be used for the separation method, and although varying according to the compounds used, a method such as filtration, distillation or sublimation can be used. A method that is carried out simultaneous to step (B), step (R) or step (P) is preferable.

[0482] Namely, in the reaction carried out in step (B), step (R) or step (P), a gas containing a hydroxy composition (the hydroxy composition refers to a composition containing at least one type of aromatic hydroxy composition and/or aromatic hydroxy compound and/or alcohol), compound having carbonyl groups derived from urea and ammonia formed as a by-product in the reaction is introduced into a condenser provided in the reactor, and all or a portion of the hydroxy

composition and the compound having carbonyl groups derived from urea are condensed.

[0483] At that time, the condensed hydroxy composition is preferably present at a stoichiometric ratio of 1 or more based on the condensed urea and compound having carbonyl groups derived from urea.

[0484] In the present embodiment, a "compound having carbonyl groups derived from urea" that is condensed in the condenser includes compounds having carbonyl groups derived from urea used in the reaction with organic amine, urea and hydroxy composition, the urea itself used as a raw material (including unreacted urea and/or the excess portion in the case of having been used in excess based on organic amine), compounds obtained by a reaction between the urea and the hydroxy composition, and compounds obtained by a reaction between same or different types of carbonic acid derivatives. Although it is difficult to identify all compounds having carbonyl groups derived from urea, specific examples may include isocyanic acid, urea, urea compounds such as biurets or nurates, non-N-substituted carbamic acid-O-esters in which the ester groups are groups derived from the hydroxy composition, and carbonic acid esters in which the ester groups are groups derived from the hydroxy composition. Compounds having carbonyl groups derived from a carbonic acid derivative can be quantified by the method that detects carbonyl groups contained in the compound such as infrared spectroscopy, near infrared spectroscopy, Raman spectroscopy or ultraviolet spectroscopy, or by a method that specifically analyzes compounds formed such as gas chromatography, liquid chromatography or NMR. Many of these compounds having carbonyl groups derived from urea have a high melting point and tend to precipitate easily. Among the above-mentioned compounds having carbonyl groups derived from urea, urea in particular requires the greatest caution since it is formed in large amounts (detected amounts) and has a melting point of 135°C.

[0485] As a result of making the stoichiometric ratio of the condensed hydroxy composition to be 1 or more based on the condensed compound having carbonyl groups derived from the urea in the condensation procedure, a mixture thereof can be obtained in the form of a homogeneous liquid mixture in the condenser. Thus, not only does this facilitate handling of the mixture, but it is also possible to avoid the occurrence of problems such as adhesion and accumulation of solid components in the condenser. In addition, as will be described later, this is also effective for reducing the amount of compounds having carbonyl groups derived from the urea contained in ammonia recovered from the condenser to equal to or less than a specific amount. The amount of the condensed hydroxy composition based on the condensed compound having carbonyl groups derived from the urea in terms of the stoichiometric ratio is more preferably 2 or more and even more preferably 3 or more. In order to ensure that the amount of the condensed hydroxy composition based on the condensed compound having carbonyl groups derived from the urea is within the above ranges, the condenser is preferably maintained at a temperature at least 90°C lower than the standard boiling point of the hydroxy composition.

<Production Method of N-substituted Carbamic Acid-O-Aryl Ester Using an Aromatic Hydroxy Composition Containing a Plurality of Types of Aromatic Hydroxy Compounds>

[0486] An N-substituted carbamic acid-O-aryl ester can be produced in the above-mentioned steps 1) to 5) using an aromatic hydroxy composition containing a plurality of types of aromatic hydroxy compounds.

[0487] In addition, in the case of carrying out step (D) in route 1) or route 2), a gas containing the aromatic hydroxy composition, urea and compound having carbonyl groups derived from urea is condensed in a condenser in order to recover the urea and compound having carbonyl groups derived from urea in the form of a homogeneous solution. Consequently, the aromatic hydroxy composition preferably contains an aromatic hydroxy compound that is easily vaporized to a certain degree under the reaction conditions. On the other hand, since the compound having ureido groups and the aromatic hydroxy composition mainly react in the liquid phase to form N-substituted carbamic acid-O-aryl ester, the aromatic hydroxy composition preferably contains an aromatic hydroxy compound that is present as a liquid under the reaction conditions. Thus, an aromatic hydroxy composition that contains a plurality of types of aromatic hydroxy compounds having different standard boiling points can be preferably used for the aromatic hydroxy composition.

[0488] In this case, there are many cases in which, when all of the plurality of types of aromatic hydroxy compounds having different standard boiling points form N-substituted carbamic acid ester by reacting with the compound having ureido groups, a plurality of types of aromatic hydroxy compounds are formed together with isocyanate during production of isocyanate by thermal decomposition of the N-substituted carbamic acid ester, thereby making separation of the aromatic hydroxy compounds complex. Therefore, a method for producing N-substituted carbamic acid-O-aryl ester having ester groups derived from an active aromatic hydroxy compound with high selectivity is preferably carried out by using a combination of an active aromatic hydroxy compound and an inactive aromatic hydroxy compound. Moreover, if aromatic hydroxy compounds are selected such that the standard boiling point of the active aromatic hydroxy compound is the highest in the aromatic hydroxy composition, the concentration of the active aromatic hydroxy compound increases in the liquid phase in which the formation reaction of the N-substituted carbamic acid-O-aryl ester mainly takes place, thereby making it possible to form an N-substituted carbamic acid-O-ester derived from the active aromatic hydroxy compound with higher selectivity. An inactive aromatic hydroxy compound having a standard boiling point lower than the standard boiling point of the active aromatic hydroxy compound is preferably introduced into the condenser in the form of a gaseous phase component and condensed in the condenser together with the compound having carbonyl

groups derived from the carbonic acid derivative.

[0489] FIG. 7 shows a conceptual drawing of a production method of N-substituted carbamic acid ester that uses an aromatic hydroxy composition composed of a plurality of types of aromatic hydroxy compounds as described above (here, for the sake of simplicity of the explanation, an aromatic hydroxy composition is described that contains two types of aromatic hydroxy compounds containing an active aromatic hydroxy compound and an inactive aromatic hydroxy compound).

[0490] An example of this type of active aromatic hydroxy compound is an aromatic hydroxy compound represented by formula (32), and preferably an aromatic hydroxy compound represented by formula (38). In addition, an example of an inactive aromatic hydroxy compound is an aromatic hydroxy compound represented by formula (39), and more preferably an aromatic hydroxy compound represented by formula (40). Although it is difficult to generally define separability, based on the finding that generally two components to be separated can be adequately separated by distillation industrially if the standard boiling points thereof are 10°C or more apart, the difference between the standard boiling points of the active aromatic hydroxy compound and the inactive aromatic hydroxy compound is preferably such that the compound having the highest standard boiling point is an active aromatic hydroxy compound, while the compound having the lowest standard boiling point is an inactive aromatic hydroxy compound, and is preferably selected such that the standard boiling point is 10°C or more higher, and more preferably 20°C or more higher, based on the compound having the highest boiling point, and is also selected in consideration of the difference with the standard boiling point of the isocyanate formed as previously described. In this case, an active aromatic hydroxy compound is selected having a standard boiling point that is 10°C or more apart from that of the isocyanate formed. In the case of using an aromatic hydroxy compound having a standard boiling point higher than that of isocyanate, an active aromatic hydroxy compound is selected that has a standard boiling point 10°C or more higher than that of the isocyanate, and in the case of using an aromatic hydroxy compound having a standard boiling point lower than that of isocyanate, an active aromatic hydroxy compound is selected that has a standard boiling point 10°C or more lower than that of the isocyanate.

<Step (E)>

[0491] Step (E): a step of recycling urea recovered in step (D) to step (A).

[0492] Step (E) is a step of recycling urea recovered in step (D) as described above to step (A). The use of recycling is preferable since it allows the amount of urea used to be reduced. In step (E), the mixture recovered in step (D) may be recycled directly to step (A) or only the urea may be recycled. Components to be recycled may be separated as necessary or components may be added before recycling to step (A). Separation and addition can be carried out using known methods, and the urea, compound having carbonyl groups derived from urea and hydroxy composition and the like are analyzed and then suitably recycled.

<Step (G)>

[0493] The following step (G) is carried out to recover ammonia formed as a by-product in step (A) and/or step (B) and/or step (R) and react the ammonia with carbon dioxide to regenerate urea followed by recycling the urea to step (A):

Step (G): a step of recovering ammonia formed as a by-product, regenerating urea by reacting the ammonia with carbon dioxide, and recycling the urea to step (A).

[0494] In the present embodiment, ammonia discharged from the condenser in the above-mentioned step (A), step (B) and/or step (R) absorbs water resulting in the formation of aqueous ammonia, and although this can be used in refrigerants of ammonia-absorption refrigerators, textile oil cleaners, raw rubber coagulants, production of various types of ammonia salts, treatment of nitrogen oxides generated by thermoelectric power plants and the like or production of photographic emulsions and so forth, or can be used in the form of liquid ammonia by employing a method such as deep cooling separation in such applications as raw materials of nitrogen fertilizers, raw materials of synthetic fibers (such as caprolactam or acrylonitrile), treatment of nitrogen oxides generation by thermoelectric power plants and the like or refrigerants, it is preferably used to synthesize urea. The following provides an explanation of this urea synthesis step (to be referred to as step (G)).

[0495] The conventionally known method can be employed to produce urea by reacting ammonia and carbon dioxide, an example of which may include reacting ammonia and carbon dioxide at a pressure within a range of from 20 to 40 MPa and temperature within a range of from 190 to 200°C such that the ratio of ammonia to carbon dioxide is within a range of a stoichiometric ratio of from 3 to 5.

[0496] The urea produced by such a method may be used in the reaction of step (A).

[0497] Although the following indicates an example of a preferable aspect that combines the above-mentioned method, there are no particular limitations on other aspects provided they are based on the above-mentioned method. Additional

steps (such as steps (D), (E), (F) or (G)) may not be carried out or additional steps may be suitably selected and carried out. Step (F) is carried out when producing isocyanate from N-substituted carbamic acid-O-aryl ester. In the following aspect, a hydroxy composition refers to a composition containing at least one type of component selected from an aromatic hydroxy composition and/or aromatic hydroxy compound and/or alcohol. In the case accumulation of a by-product is observed in each step, the by-product is preferably suitably removed outside the system from the recycled composition or together with the recycled composition, and may be removed using the known method. The removal method can be suitably determined by a person with ordinary skill in the art. Examples of methods that can be used may include a method for partially removing a liquid phase component and/or gaseous phase component outside the system, and a method for removing a solid component by filtration and the like.

[0498] FIG. 8 shows a conceptual drawing depicting one aspect of the present embodiment that combines route 1) with steps (D), (E), (F) and (G).

[0499] First, the compound having the ureido groups is produced in step (A) by reacting the organic primary amine and urea. In this step (A), the aromatic hydroxy composition acts mainly as a reaction solvent. In the reaction of step (A), ammonia formed as a by-product can be extracted from the reaction liquid until the ammonia concentration in the reaction liquid is within the preferable ranges previously described. The reaction liquid obtained in step (A) contains a compound having ureido groups and an aromatic hydroxy composition, and the reaction liquid may be a composition for transfer and storage of a compound having ureido groups of the present embodiment depending on the raw materials used, composite ratio of the raw materials, reaction conditions of step (A) and the like. In the subsequent step (B), N-substituted carbamic acid-O-aryl ester is produced by reacting the compound having ureido groups and an aromatic hydroxy compound. Ammonia formed as a by-product in the reaction of this step (B) is extracted from the reaction liquid until the ammonia concentration is within the preferable ranges previously described, and is used in step (G) along with the ammonia extracted in step (A). The urea produced in step (G) is reused as a raw material of step (A). In addition, step (D) is carried out simultaneous to the step (B). Namely, unreacted or excess urea is removed by distillation or sublimation. At this time, the urea is distilled off together with a portion of the aromatic hydroxy composition, and is preferably removed and recovered in the form of a mixture with the aromatic hydroxy composition. The urea recovered in step (D) is reused as a raw material of step (A) by carrying out step (E).

[0500] The N-substituted carbamic acid-O-aryl ester obtained in step (B) is subjected to thermal decomposition in the subsequent step (F), resulting in the formation of the corresponding isocyanate and aromatic hydroxy composition. The aromatic hydroxy composition separated from the isocyanate in step (F) is reused as a raw material of step (A).

[0501] FIG. 9 shows a conceptual drawing depicting one aspect of the present embodiment that combines route 2) with steps (D), (E), (F) and (G).

[0502] This route 2) is an example of a preferable aspect in the case of using a monoaryl amine for the organic primary amine.

[0503] First, organic primary amine (monoaryl amine) and urea are reacted in step (A) to produce the compound having the ureido groups. In this step (A), the aromatic hydroxy composition acts mainly as a reaction solvent. In the reaction of step (A), ammonia formed as a by-product can be extracted from the reaction liquid until the ammonia concentration in the reaction liquid is within the preferable ranges previously described. The reaction liquid obtained in step (A) contains the compound having the ureido groups and the aromatic hydroxy composition, and the reaction liquid may be a composition for transfer and storage of the compound having the ureido groups of the present embodiment depending on the raw materials used, composite ratio of the raw materials, reaction conditions of step (A) and the like. In the subsequent step (B), N-substituted carbamic acid-O-mono(aryl ester) is produced by reacting the compound having the ureido groups and the aromatic hydroxy compound. Ammonia formed as a by-product in the reaction of this step (B) is extracted from the reaction liquid until the ammonia concentration is within the preferable ranges previously described, and is used in step (G) along with the ammonia extracted in step (A). The urea produced in step (G) is reused as a raw material of step (A). In addition, step (D) is carried out simultaneous to the step (B). Namely, unreacted or excess urea is removed by distillation or sublimation. At this time, the urea is distilled off together with a portion of the aromatic hydroxy composition, and is preferably removed and recovered in the form of a mixture with the aromatic hydroxy composition. The urea recovered in step (D) is reused as a raw material of step (A) by carrying out step (E).

[0504] The N-substituted carbamic acid-O-mono(aryl ester) obtained in step (B) is used to produce N-substituted carbamic acid-O-aryl ester, in which at least two molecules of the N-substituted carbamic acid-O-mono(aryl ester) are crosslinked with methylene (-CH₂-) groups by crosslinking with the methylene groups in the subsequent step (C). When carrying out the step (C), the aromatic hydroxy composition used in step (B) is separated from the reaction liquid containing N-substituted carbamic acid-O-mono(aryl ester). After carrying out step (C), aromatic hydroxy composition is preferably added to the resulting N-substituted carbamic acid-O-aryl ester to subject the N-substituted carbamic acid-O-aryl ester to a thermal decomposition reaction in step (F). In step (F), the N-substituted carbamic acid-O-aryl ester obtained in step (C) is subjected to thermal decomposition to form the corresponding isocyanate and an aromatic hydroxy composition. The aromatic hydroxy composition separated from the isocyanate in step (F) is reused as a raw material of step (A).

[0505] FIG. 10 shows a conceptual drawing depicting one aspect of the present embodiment that combines route 3)

with steps (D), (E), (F) and (G).

[0506] First, organic primary amine and urea are reacted in step (A) to produce a compound having ureido groups. An alcohol and/or aromatic hydroxy composition are preferably used for the reaction solvent in this step (A). In the reaction of step (A), ammonia formed as a by-product can be extracted from the reaction liquid until the ammonia concentration in the reaction liquid is within the preferable ranges previously described. A portion of unreacted or excess urea may be extracted as a gaseous phase component at that time. The reaction liquid obtained in step (A) may be a composition for transfer and storage of the compound having the ureido groups of the present embodiment depending on the raw materials used, composite ratio of the raw materials, reaction conditions of step (A) and the like. In the subsequent step (R), N-substituted carbamic acid-O-R² ester is produced by reacting the compound having the ureido groups and alcohol. Ammonia formed as a by-product in the reaction of this step (R) is extracted from the reaction liquid until the ammonia concentration is within the preferable ranges previously described, and is used in step (G) along with the ammonia extracted in step (A). The urea produced in step (G) is reused as a raw material of step (A). In addition, step (D) is carried out simultaneous to the step (R). Namely, unreacted or excess urea is removed by distillation or sublimation. At this time, the urea is distilled off together with a portion of the aromatic hydroxy composition (alcohol and/or aromatic hydroxy composition), and is preferably removed and recovered in the form of a mixture with the aromatic hydroxy composition. The urea recovered in step (D) is reused as a raw material of step (A) by carrying out step (E).

[0507] Next, the N-substituted carbamic acid-O-R² ester obtained in step (R) is converted to N-substituted carbamic acid-O-aryl ester by reacting with an aromatic hydroxy composition in step (P). Alcohol derived from the N-substituted carbamic acid-O-R² ester that is produced as a by-product by this reaction is reused in step (A). In addition, in the case removal of urea is inadequate in step (D) that is carried out simultaneous to step (R), step (D) can also be carried out simultaneous to step (P) to remove urea in the reaction liquid. The urea recovered in the step (D) is also reused as a raw material of step (A) by similarly carrying out step (E).

[0508] The N-substituted carbamic acid-O-aryl ester obtained in step (P) is subjected to a thermal decomposition reaction in the subsequent step (F) to form the corresponding isocyanate and an aromatic hydroxy composition. The aromatic hydroxy composition separated from the isocyanate in step (F) is reused as a raw material of step (A).

[0509] FIG. 11 shows a conceptual drawing depicting one aspect of the present embodiment that combines route 4) with steps (D), (E), (F) and (G).

[0510] This route 4) is an example of a preferable aspect in the case of using a monoaryl amine for the organic primary amine.

[0511] First, organic primary amine (monoaryl amine) and urea are reacted in step (A) to produce the compound having the ureido groups. In this step (A), an alcohol and/or aromatic hydroxy composition are preferably used for the reaction solvent. In the reaction of step (A), ammonia formed as a by-product can be extracted from the reaction liquid until the ammonia concentration in the reaction liquid is within the preferable ranges previously described. At that time, a portion of the unreacted or excess urea may also be extracted as a gaseous phase component. The reaction liquid obtained in step (A) may be a composition for transfer and storage of a compound having ureido groups of the present embodiment depending on the raw materials used, composite ratio of the raw materials, reaction conditions of step (A) and the like. In the subsequent step (R), N-substituted carbamic acid-O-mono(R² ester) is produced by reacting the compound having ureido groups and alcohol. Ammonia formed as a by-product in the reaction of this step (R) is extracted from the reaction liquid until the ammonia concentration is within the preferable ranges previously described, and is used in step (G) along with the ammonia extracted in step (A). The urea produced in step (G) is reused as a raw material of step (A). In addition, step (D) is carried out simultaneous to the step (R). Namely, unreacted or excess urea is removed by distillation or sublimation. At this time, the urea is distilled off together with a portion of a hydroxy composition (alcohol and/or aromatic hydroxy composition), and is preferably removed and recovered in the form of a mixture with the hydroxy composition. The urea recovered in step (D) is reused as a raw material of step (A) by carrying out step (E).

[0512] Next, the N-substituted carbamic acid-O-mono(R² ester) obtained in step (R) is converted to N-substituted carbamic acid-O-mono(aryl ester) by reacting with an aromatic hydroxy composition in step (P). Alcohol derived from the N-substituted carbamic acid-O-mono(R² ester) that is produced as a by-product by this reaction is reused in step (A). In addition, in the case removal of urea is inadequate in step (D) that is carried out simultaneous to step (R), step (D) can also be carried out simultaneous to step (P) to remove urea in the reaction liquid. The urea recovered in the step (D) is also reused as a raw material of step (A) by similarly carrying out step (E).

[0513] The N-substituted carbamic acid-O-mono(aryl ester) obtained in step (P) is used to produce N-substituted carbamic acid-O-aryl ester, in which at least two molecules of the N-substituted carbamic acid-O-mono(aryl ester) are crosslinked with methylene (-CH₂-) groups by crosslinking with the methylene groups in the subsequent step (C). When carrying out the step (C), aromatic hydroxy composition remaining in the reaction liquid of step (P) is separated from the reaction liquid containing N-substituted carbamic acid-O-mono(aryl ester). After carrying out step (C), aromatic hydroxy composition is preferably added to the resulting N-substituted carbamic acid-O-aryl ester to subject the N-substituted carbamic acid-O-aryl ester to a thermal decomposition reaction in step (F).

[0514] In step (F), the N-substituted carbamic acid-O-aryl ester obtained in step (C) is subjected to thermal decom-

position to form the corresponding isocyanate and an aromatic hydroxy composition. The aromatic hydroxy composition separated from the isocyanate in step (F) is reused as a raw material of step (A).

[0515] FIG. 12 shows a conceptual drawing depicting one aspect of the present embodiment that combines route 5) with steps (D), (E), (F) and (G).

[0516] This route 5) is an example of a preferable aspect in the case of using a monoaryl amine for the organic primary amine.

[0517] First, organic primary amine (monoaryl amine) and urea are reacted in step (A) to produce the compound having the ureido groups. In this step (A), an alcohol and/or aromatic hydroxy composition are preferably used for the reaction solvent. In the reaction of step (A), ammonia formed as a by-product can be extracted from the reaction liquid until the ammonia concentration in the reaction liquid is within the preferable ranges previously described. At that time, a portion of the unreacted or excess urea may also be extracted as a gaseous phase component. The reaction liquid obtained in step (A) may be a composition for transfer and storage of a compound having ureido groups of the present embodiment depending on the raw materials used, composite ratio of the raw materials, reaction conditions of step (A) and the like. In the subsequent step (R), N-substituted carbamic acid-O-mono(R² ester) is produced by reacting the compound having the ureido groups and alcohol. Ammonia formed as a by-product in the reaction of this step (R) is extracted from the reaction liquid until the ammonia concentration is within the preferable ranges previously described, and is used in step (G) along with the ammonia extracted in step (A). The urea produced in step (G) is reused as a raw material of step (A). In addition, step (D) is carried out simultaneous to the step (R). Namely, unreacted or excess urea is removed by distillation or sublimation. At this time, the urea is distilled off together with a portion of a hydroxy composition (alcohol and/or aromatic hydroxy composition), and is preferably removed and recovered in the form of a mixture with the hydroxy composition. The urea recovered in step (D) is reused as a raw material of step (A) by carrying out step (E).

[0518] Next, the N-substituted carbamic acid-O-mono(R² ester) obtained in step (R) is used to produce N-substituted carbamic acid-O-R² ester, in which at least two molecules of the N-substituted carbamic acid-O-mono(R² ester) are crosslinked with methylene (-CH₂-) groups by crosslinking with the methylene groups in step (C). When carrying out the step (C), aromatic hydroxy composition remaining in the reaction liquid of step (R) is separated from the reaction liquid containing N-substituted carbamic acid-O-mono(R² ester). In addition, in the case removal of urea is inadequate in step (D) that is carried out simultaneous to step (R), step (D) may also be carried out simultaneously when separating hydroxy composition remaining in the reaction liquid of step (R) from the reaction liquid followed by recovery of urea and hydroxy composition. The recovered urea and hydroxy composition are reused as raw materials of step (A) by carrying out step (E).

[0519] After carrying out step (C), the resulting N-substituted carbamic acid-O-R² ester is subjected to a transesterification reaction of step (P). Alcohol derived from the N-substituted carbamic acid-O-R² ester that is formed as a by-product by this reaction is reused in step (A).

[0520] The N-substituted carbamic acid-O-aryl ester obtained in step (P) is subjected to a thermal decomposition reaction in step (F) to form the corresponding isocyanate and an aromatic hydroxy composition. The aromatic hydroxy composition separated from the isocyanate in step (F) is reused as the aromatic hydroxy composition of step (P).

Examples

[0521] Although the following provides a detailed explanation of the present invention based on examples thereof, the scope of the present invention is not limited by these examples.

<Analytical Methods>

1) NMR Analysis

[0522] Apparatus: JNM-A400 FT-NMR system, JEOL Ltd., Japan

(1) Preparation of ¹H- and ¹³C-NMR Analysis Samples

[0523] About 0.3 g of sample solution were weighed followed by the addition of about 0.7 g of heavy chloroform (99.8%, Aldrich Corp., USA) and 0.05 g of internal standard in the form of tetramethyl tin (guaranteed reagent, Wako Pure Chemical Industries, Ltd., Japan) and mixing to uniformity to obtain solutions used as NMR analysis samples.

(2) Quantitative Analysis

[0524] Analyses were performed for each standard and quantitative analyses were performed on the analysis sample solutions based on the resulting calibration curve.

2) Liquid Chromatography

[0525]

5 Apparatus: LC-10AT system, Shimadzu Corp., Japan
Column: Inertsil-ODS column, GL Sciences Inc., Japan, two columns connected in series
Developing solvent: Mixed liquid of 5 mmol/L aqueous ammonium acetate solution (solution A) and acetonitrile (solution B)
10 Developing solvent flow rate: 2 mL/min
Column temperature: 35°C
Detector: R.I. detector (refractometer) and PDA detector (photodiode array detector, measuring wavelength range: 200 to 300 nm)

(1) Liquid Chromatography Analysis Samples

15 **[0526]** About 0.1 g of sample were weighed followed by the addition of about 1 g of tetrahydrofuran (dehydrated, Wako Pure Chemical Industries, Ltd., Japan) and about 0.02 g of internal standard in the form of 1,1-diethyl urea (Tokyo Chemical Industry Co., Ltd., Japan) and mixing to uniformity to obtain solutions used as liquid chromatography analysis samples.

20

(2) Quantitative Analysis

[0527] Analyses were performed for each standard and quantitative analyses were performed on the analysis sample solutions based on the resulting calibration curve.

25

3) Water Analysis

[0528] Apparatus: Micro Water Content Analyzer Model CA-21, Mitsubishi Chemical Analytech Co., Ltd., Japan

30 (1) Quantitative Analysis

[0529] About 1 g of sample was weighed out and injected into the micro water content analyzer to determine the water content of the sample.

35 4) Analysis of Ammonia Concentrations in Liquids and Solids

[0530]

40 Apparatus: IC2001 Ion Chromatograph (Tosoh Corp., Japan)
Column: SuperIC-CR
Developing solution: Solution obtained by mixing 1 L of water and about 0.25 g of 18-Crown-6 (Wako Pure Chemical Industries, Ltd., Japan) and about 2.1 mL of 2 mol/L methanesulfonic acid (Wako Pure Chemical Industries, Ltd., Japan).

45 (1) Ion Chromatography Analysis Samples

[0531] About 0.15 g of sample were weighed followed by the addition of about 1 g of toluene and about 15 g of 2 mmol/L aqueous nitric acid solution, mixing well and allowing to stand undisturbed for about 2 hours. The aqueous layer was then removed and used as the ion chromatography analysis sample.

50

(2) Quantitative Analysis

[0532] A calibration curve was prepared using Cation Mixed Standard II (Kanto Chemical Co., Inc., Japan), and the amounts of ammonia in the analysis sample solutions were quantified based on the calibration curve.

55 **[0533]** Furthermore, the names of compounds used in the following examples are explained using nomenclature rules defined by IUPAC as well as common names.

EP 2 322 504 B9

[Example 1] Production of N-substituted Carbamic Acid-O-Aryl Ester by Route 1)

Step (A): Production of Compound Having Ureido Groups

5 [0534] The apparatus used in FIG. 13 was used.

[0535] 41.84 kg of p-heptyl phenol (Schenectady Chemicals, USA) and 3.10 kg of urea were mixed in a storage tank 101 heated to 120°C with a line 13 closed to obtain a mixture for use as an aromatic hydroxy composition. The water concentration in the mixture was about 15 ppm. The mixture was transferred to a stirring tank 103 (with baffles) heated to 120°C. 1.50 kg of organic amine in the form of hexamethylenediamine were then supplied at the rate of about 20 g/min (supply rate of organic amine) from a storage tank 102 to the stirring tank 103 via a line 12 while stirring the stirring tank 103. Formation of ammonia from a line 19 was confirmed. Following completion of supplying hexamethylenediamine, stirring was continued for about 2 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain 6.3% by weight of a compound having ureido groups in the form of 6-hexamethylene diurea. In addition, the ammonia concentration in the solution was 6300 ppm. Unreacted amino group terminals were not detected. The ratio of the number of molecules of p-heptyl phenol to the number of ureido groups in the reaction liquid was 7.5.

15 [0536] Line 13 was opened and the reaction liquid was transferred to a storage tank 104 via the line 13.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

20 [0537] The apparatus shown in FIG. 13 was continued to be used.

[0538] A packed column 105 packed with a packing material (Helipack No. 3) was heated to 240°C and the pressure inside the column was set to 26kPa. The reaction liquid obtained in step (A) was fed from a line 14 provided in the packed column 105 at the rate of about 1.5 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 35.1 kg. The reaction liquid was recovered in a storage tank 110 through a line 16 provided in the bottom of the packed column 105. A gaseous phase component was condensed from a line 15 provided in the top of the packed column 105 with a condenser 106, and the resulting liquid phase component was recovered in a storage tank 109 via a gas-liquid separator 108. When reaction liquid recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain urea and p-heptyl phenol. The amount of reaction liquid recovered in the storage tank 110 was 23.0 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was about 97%. The urea content of the reaction liquid was below the detection limit. In addition, N,N'-bis(6-(p-heptylphenoxy)carbonyl) urea was not detected. The ammonia concentration of the reaction liquid was 9.0 ppm.

35 [0539] On the other hand, the amount of mixture recovered in the storage tank 109 was 13.5 kg. This mixture contained an aromatic hydroxy compound (p-heptyl phenol) and urea, and the content of the aromatic hydroxy compound (p-heptyl phenol) in the mixture was 85.4% by weight, while the urea content was 10.2% by weight.

40 Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0540] The apparatus shown in FIG. 17 was used.

[0541] A thin film distillation apparatus 602 (Kobelco Eco-Solutions Co., Ltd., Japan) having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing hexamethylene diisocyanate and p-heptyl phenol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in a condenser 610 via a line 69 and recovered in a storage tank 612 through a gas-liquid separator 611.

55 [0542] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on the organic amine of step (A) (hexamethylene diamine) was about 90%. A mixture containing p-heptyl phenol was obtained in a storage tank 614.

Step (E): Production of N-substituted Carbamic Acid Ester by Reusing Mixture Obtained in Condenser

5 [0543] The ammonia concentration of the mixture recovered in the storage tank 109 in step (B) of Example 1 was 820 ppm. 12.8 kg of p-heptyl phenol and 0.578 kg of urea were added to the mixture followed by transferring to the stirring tank 103 and carrying out the same method as step (A) using 0.92 kg of hexamethylenediamine. A solution containing 6.3% by weight of 1,6-hexanedurea was obtained. The same method as step (B) was carried out using this solution instead of the solution of step (A). The reaction liquid recovered in a storage tank 610 contained N,N'-hexanedyl-di(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanedyl-di(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was about 97%.

10 [Example 2] Production of N-substituted Carbamic Acid-O-Aryl Ester by Route 1)

Step (A): Production of Compound Having Ureido Groups

15 [0544] The apparatus shown in FIG. 14 was used.

[0545] A mixture of 1.92 kg of urea and 11.9 kg of solvent (1-butanol) was transferred from a storage tank 200 to a stirring tank 203 heated to 120°C with a line 23 closed. 0.930 kg of organic amine in the form of hexamethylenediamine were then supplied at the rate of about 5 g/min (supply rate of organic amine) from a storage tank 201 to the stirring tank 103 via a line 21 while stirring the stirring tank 203. Following completion of supplying hexamethylenediamine, stirring was continued for about 1 hour. When the reaction liquid was analyzed by liquid chromatography, it was found to contain 11.2% by weight of 1,1'-(hexane-1,6-diyl) diurea. In addition, the ammonia concentration in the solution was 7500 ppm. The ratio of unreacted amino groups to ureido groups was 0.001. 23.1 kg of aromatic hydroxy compound in the form of p-heptyl phenol were transferred from a storage tank 202 to the stirring tank 203 followed by transferring to a storage tank 204 after obtaining a homogeneous solution.

25 Step (D): Separation and Recovery of Urea

[0546] The apparatus shown in FIG. 14 was continued to be used. A packed column 205 packed with a packing (Helipack No. 3) was heated to about 120°C and the pressure inside the column was set to 10 kPa. The reaction liquid obtained in step (A) was fed to the packed column 205 at the rate of about 8.2 g/min from a line 24 provided in the packed column 205. A gaseous component was recovered from a line 25 and after condensing in a condenser 206, was recovered in a storage tank 208. The recovered liquid obtained in the storage tank 208 was a mixed liquid containing 1-butanol and urea. A residual liquid recovered in a storage tank 209 from the bottom of the packed column 205 via a line 26 was a mixed liquid containing 1,1'-(hexane-1,6-diyl) diurea and p-heptyl phenol. The recovered amount of the residual liquid was about 13.5 kg. The concentration of 1,1'-(hexane-1,6-diyl) diurea in the residual liquid was about 12.0% by weight, and the ratio of the number of p-heptyl phenol molecules to the number of ureido groups was about 2.9.

[0547] On the other hand, about 9.8 kg of the mixture of 1-butanol and urea were recovered in the storage tank 208. The amount of 1-butanol contained in the mixture was 92.5% by weight while the amount of urea was 7.1 % by weight.

40 Step (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

[0548] The apparatus shown in FIG. 14 was continued to be used. A packed column 210 packed with a packing material (Helipack No. 3) was heated to 250°C and the pressure inside the column was set to 26 kPa. The residual liquid recovered in the storage tank 209 in step (D) was fed from a line 28 provided in the packed column 210 at the rate of about 3.8 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 8.95 kg. The reaction liquid was recovered in a storage tank 216 through a line 31 provided in the bottom of the packed column 210. A gaseous phase component was extracted from a line 29 provided in the top of the packed column 210 and condensed with a condenser 211, and the resulting liquid phase component was recovered in a storage tank 213 via a gas-liquid separator 212 and circulated to the packed column 210. On the other hand, ammonia was discharged in the form of a gaseous component from a line 31. The ammonia was absorbed in water and recovered in the form of aqueous ammonia. When the reaction liquid recovered in a storage tank 216 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanedyl-di(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanedyl-di(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was about 95%. In addition, the ammonia concentration in the reaction liquid was 8.0 ppm.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0549] The apparatus shown in FIG. 17 was used.

[0550] The thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in the storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1500 g/hr via the line 60. A liquid component was extracted from the line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in the storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through the line 63. A gaseous component containing hexamethylene diisocyanate and p-heptyl phenol was extracted from the line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into the distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to the distillation column 609 from the line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in the condenser 610 via the line 69 and recovered in the storage tank 612 through the gas-liquid separator 611.

[0551] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on organic amine (hexamethylene diamine) was about 90%.

Step (E): Production of N-substituted Carbamic Acid Ester by Reusing Mixture Obtained in Condenser

[0552] The ammonia concentration of the mixture recovered in the storage tank 109 in step (D) of Example 2 was 550 ppm. 0.962 kg of urea were added to the mixture (without adding solvent) followed by transferring to the stirring tank 103 and carrying out the same method as step (A) using 0.930 kg of hexamethylenediamine. A solution containing 14.1 % by weight of 1,6-hexane bis-urea was obtained. The same method as step (B) was carried out using this solution instead of the solution of step (A). The reaction liquid recovered in the storage tank 610 contained N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was about 95%.

[Example 3]

Step (A): Production of Compound Having Ureido Groups

[0553] The apparatus used in FIG. 13 was used.

[0554] 13.6 kg of 1-butanol as the hydroxy compound and 2.49 kg of urea were mixed in the storage tank 101 heated to 120°C with the line 13 closed to obtain a mixture. The mixture was transferred to the stirring tank 103 (with baffles) heated to 120°C. 1.07 kg of organic amine in the form of hexamethylenediamine were then supplied at the rate of about 20 g/min (supply rate of organic amine) from the storage tank 102 to the stirring tank 103 via the line 12 while stirring the stirring tank 103. Following completion of supplying hexamethylenediamine, stirring was continued for about 2 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain 10.9% by weight of a compound having ureido groups in the form of 1,1'-(hexane-1,6-diyl) diurea. In addition, the ammonia concentration in the solution was 4300 ppm. Unreacted amino group terminals were not detected. 26.6 kg of a hydroxy compound in the form of p-heptyl phenol were added to the reaction liquid to obtain a homogeneous solution. The ratio of the number of molecules of p-heptyl phenol to the number of ureido groups in the reaction liquid was 7.6. Line 13 was opened and the reaction liquid was transferred to the storage tank 104 via the line 13.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

[0555] The apparatus shown in FIG. 13 was continued to be used.

[0556] The packed column 105 packed with a packing material (Helipack No. 3) was heated to 240°C and the pressure inside the column was set to 50 kPa. The reaction liquid obtained in step (A) was fed from the line 14 provided in the packed column 105 at the rate of about 3.8 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 37.8 kg. The reaction liquid was recovered in the storage tank 110 through the line 16 provided in the bottom of the packed column 105. A gaseous phase component was condensed from the line 15 provided in the top of the packed column 105 with the condenser 106, and the resulting liquid phase component was recovered in the storage tank 109 via the gas-liquid separator 108. The amount of the condensed component recovered in the storage tank 109 was 13.3 kg, and when the condensed component was analyzed by ¹H-NMR, the condensed component was found to contain urea and

1-butanol. The urea content was 9.09% by weight and the 1-butanol content was 89.1% by weight. When the reaction liquid recovered in the storage tank 110 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was about 94%. Urea was not detected in the reaction liquid. The amount of ammonia contained in the reaction liquid was 8.1 ppm.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0557] The apparatus shown in FIG. 17 was used.

[0558] The thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in the storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via the line 60. A liquid component was extracted from the line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in the storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through the line 63. A gaseous component containing hexamethylene diisocyanate and p-heptyl phenol was extracted from the line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into the distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to the distillation column 609 from the line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in the condenser 610 via the line 69 and recovered in the storage tank 612 through the gas-liquid separator 611.

[0559] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on the organic amine (hexamethylene diamine) was about 90%.

[Example 4] Production of N-substituted Carbamic Acid-O-Aryl Ester by Route 2)

Route (A): Production of Compound Having Ureido Groups

[0560] The apparatus used in FIG. 13 was used.

[0561] 43.5 kg of an aromatic hydroxy compound in the form of 4-tert-amyl phenol and 3.61 kg of urea were mixed in the storage tank 101 heated to 80°C with the line 13 closed, and the mixture was transferred to the stirring tank 103 heated to 80°C. 1.12 kg of aniline were then supplied at the rate of about 10 g/min (supply rate of aniline) from the storage tank 102 to the stirring tank 603 via the line 12 while stirring the stirring tank 103. Following completion of supplying aniline, stirring was continued for about 28 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain 4.5% by weight of N-phenylurea. The ratio of the number of molecules of 4-tert-amyl phenol to the number of ureido groups in the reaction liquid was 11. The amount of ammonia contained in the reaction liquid was 3800 ppm.

[0562] Line 63 was opened and the reaction liquid was transferred to the storage tank 604 via the line 63.

Steps (B) and (D): Production of N-substituted Carbamic Acid Mono(O-Aryl Ester)

[0563] The apparatus shown in FIG. 13 was continued to be used.

[0564] The packed column 105 packed with a packing material (Helipack No. 3) was heated to 200°C and the pressure inside the column was set to 8 kPa. The reaction liquid obtained in step (A) was fed from the line 14 provided in the packed column 105 at the rate of about 1.6 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 8.95 kg. The reaction liquid was recovered in the storage tank 110 through the line 16 provided in the bottom of the packed column 105. A gaseous phase component was introduced into the condenser 106 from the line 15 provided in the top of the packed column 105, and the resulting liquid phase component was recovered in the storage tank 109 via the gas-liquid separator 108. When the condensed component recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain urea and 4-tert-amyl phenol. The amount of reaction liquid recovered in the storage tank 110 was 8.72 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N-phenylcarbamic acid (4-tert-amylphenyl) ester, and the yield of N-phenylcarbamic acid (4-tert-amylphenyl) ester based on aniline was about 93%. The amount of ammonia contained in the reaction liquid was 5.6 ppm.

Step (C): Condensation of N-substituted Carbamic Acid Mono(-O-Aryl Ester)

[0565] The apparatus shown in FIG. 15 was used.

[0566] The reaction liquid recovered in the storage tank 110 in step (B) was placed in a stirring tank 408. The stirring tank 408 was heated to 160°C and the pressure inside was set to 2 kPa followed by distilling off the aromatic hydroxy compound. The aromatic hydroxy compound in the form of 4-tert-amyl phenol was condensed in a condenser 405 via a line 44 and recovered in a storage tank 407. Next, 1.14 kg of methylal (formaldehyde dimethyl acetal) from a storage tank 400, 4.70 kg of nitrobenzole from a storage tank 401, and 5.6 kg of sulfuric acid from a storage tank 402 were added to the stirring tank 408 followed by heating for 10 hours at 100°C while stirring the stirring tank 408. Solvent and unreacted substances were then distilled off by maintaining the temperature inside the stirring tank 408 at 100°C and reducing the pressure inside to 1 kPa. When the resulting compound was analyzed by liquid chromatography, it was found to be a mixture containing about 55% by weight of N,N'-(methanediy-diphenyl)-di(carbamic acid(4-tert-amylphenyl) ester). About 5.1 kg of an aromatic hydroxy compound (4-tert-amyl phenol) were added to the mixture to obtain a homogeneous solution followed by transferring the solution to a storage tank 404.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0567] The apparatus shown in FIG. 18 was used.

[0568] A thin film distillation apparatus 1002 (Kobelco Eco-Solutions Co., Ltd., Japan) having a heat-conducting surface area of 0.2 m² was heated to 260°C and the pressure within the thin film distillation apparatus was set to about 1.5 kPa. The reaction liquid recovered in the storage tank 404 in step (C) was placed in a storage tank 1001 and supplied to the thin film distillation apparatus at the rate of about 1200 g/hr via a line A1. A liquid component was extracted from a line A4 provided in the bottom of thin film distillation apparatus 1002 and recovered in a storage tank 1003. The liquid component recovered in the storage tank 1003 was again supplied to the thin film distillation apparatus 1002 through a line A3. A gaseous component was extracted from a line A4 provided in the upper portion of the thin film distillation apparatus 1002. The gaseous component was introduced into a distillation column 1004, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 1009 from a line A8 provided at a portion of the distillation column 1004 lower than the feed line and further subjected to distillative separation. A liquid phase component was supplied to a distillation column 1014 from a line A12 provided at a portion of the distillation column 1009 lower than the feed line and further subjected to distillative separation.

[0569] A gaseous phase component was extracted from a line A13 provided in the top of the distillation column 1014 and condensed in a condenser 1015, and the condensate was recovered in a storage tank 1019. When the condensate was analyzed by ¹H-NMR, it was found to be a solution containing about 99% by weight of 4,4'-diphenylmethane diisocyanate (MDI). The yield based on aniline was about 50%.

Step (E): Production of N-substituted Carbamic Acid Ester by Reusing Mixture Obtained in Condenser

[0570] When the ammonia content of the mixture recovered in the storage tank 109 in step (B) of Example 3 was analyzed, it was found to be 1800 ppm. 19.0 kg of 4-tert-amyl phenol and 0.690 kg of urea were added to 14.7 kg of the mixture followed by transferring to the stirring tank 603 and carrying out the same method as step (A) using 0.820 kg of aniline. A solution containing 4.5% by weight of phenylurea was obtained. The same method as step (B) was carried out using this solution instead of the solution of step (A). The yield of N-phenylcarbamic acid (4-tert-amylphenyl) ester in the reaction liquid recovered in the storage tank 110 based on aniline was about 93%.

[Example 5] Production of N-substituted Carbamic Acid-O-Aryl Ester by Route 3)

Route (A): Production of Compound Having Ureido Groups

[0571] The apparatus used in FIG. 13 was used.

[0572] 14.6 kg of a solvent (1-octanol, Wako Pure Chemical Industries, Ltd., Japan) and 1.47 kg of urea were mixed in the storage tank 101 heated to 120°C with the line 13 closed, and the mixture was transferred to the stirring tank 103 (internal volume: 80 L, provided with baffles) heated to 120°C. 0.87 kg of an organic amine in the form of 3-aminomethyl-3,5,5-trimethylcyclohexylamine were then supplied at the rate of about 10 g/min from the storage tank 102 to the stirring tank 103 via the line 12 while stirring the stirring tank 103. Following completion of supplying the 3-aminomethyl-3,5,5-trimethylcyclohexylamine, stirring was continued for about 2 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain about 7.87% by weight of 3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea. In addition, the concentration of ammonia in the reaction liquid was 7300 ppm. 13.4 kg of an aromatic hydroxy compound in the form of p-dodecyl phenol were added from the storage tank

101 to obtain a homogeneous solution. Line 13 was opened and the solution was transferred to the storage tank 104 via the line 13.

Steps (R) and (D): Production of N-substituted Carbamic Acid-O-Alkyl Ester and Recovery of Urea

[0573] The apparatus shown in FIG. 13 was continued to be used.

[0574] A packed column 105 packed with a packing material (Helipack No. 3) was heated to 190°C. The reaction liquid obtained in step (A) was fed from a line 14 provided in the packed column 105 at the rate of about 1.1 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 15.1 kg. The reaction liquid was recovered in a storage tank 110 through a line 16 provided in the bottom of the packed column 105. A gaseous phase component was condensed from a line 15 provided in the top of the packed column 105 with a condenser 106, and the resulting liquid phase component was recovered in a storage tank 109 via a gas-liquid separator 108. When a condensed component recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain 1-octanol and urea. The amount of reaction liquid recovered in the storage tank 110 was 8.80 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain 3-((1-octyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-octyl) ester, and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 95%. The ammonia concentration of the reaction liquid was 5.8 ppm.

Step (P): Transesterification Reaction

[0575] The apparatus shown in FIG. 16 was used.

[0576] 0.5% by weight of a catalyst in the form of dibutyl tin dilaurate was added to the reaction liquid obtained in the step described above, and the resulting solution was placed in a storage tank 501. A packed column 502 packed with a packing material (Helipack No. 3) was heated to 260°C and the pressure inside the column was set to 26 kPa. The mixture in the storage tank 501 was fed from a line 51 provided in the packed column 502 at the rate of about 1.9 g/min. A reaction liquid was recovered in a storage tank 505 via a line 54 provided in the bottom of the packed column 502. A gaseous phase component was introduced into a condenser 503 from a line 52 provided in the top of the packed column 502, and the resulting liquid phase component was recovered in a storage tank 504 through a gas-liquid separator 507. The amount of reaction liquid recovered in the storage tank 505 was 18.2 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to be a solution containing 3-((p-dodecylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-dodecylphenyl) ester, and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 89%.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0577] The apparatus shown in FIG. 17 was used.

[0578] A thin film distillation apparatus 602 (Kobelco Eco-Solutions Co., Ltd., Japan) having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the previous step was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1080 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing isophorone diisocyanate and p-dodecyl phenol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in a condenser 610 via a line 69 and recovered in a storage tank 612 through a gas-liquid separator 611.

[0579] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of isophorone diisocyanate. The yield based on the organic amine (3-aminomethyl-3,5,5-trimethylcyclohexylamine) was about 83%.

Step (E): Production of N-substituted Carbamic Acid Ester by Reusing Mixture Obtained in Condenser

[0580] When the ammonia concentration of the mixture recovered in the storage tank 109 in step (B) of Example 4 was analyzed, it was found to be 1300 ppm. 7.57 kg of 1-octanol and 0.70 kg of urea were added to 9.4 kg of the mixture followed by transferring to the stirring tank 103 and carrying out the same method as step (A) using 0.87 kg of 3-

aminomethyl-3,5,5-trimethylcyclohexylamine. A solution containing 6.3% by weight of 3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea was obtained. The same method as step (B) was carried out using this solution instead of the solution of step (A). The reaction liquid recovered in a storage tank 110 contained 3-((3-methylbutyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (3-methylbutyl) ester, and the yield of 3-((3-methylbutyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (3-methylbutyl) ester based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 95%.

[Example 6] Production of N-substituted Carbamic Acid-O-Aryl Ester by Route 4)

Route (A): Production of Compound Having Ureido Groups

[0581] The apparatus used in FIG. 13 was used.

[0582] 33.5 kg of a solvent (1-nonanol) and 3.34 kg of urea were mixed in the storage tank 101 heated to 90°C with the line 13 closed, and the mixture was transferred to the stirring tank 103 heated to 90°C. 1.08 kg of aniline were then supplied at the rate of about 12 g/min from the storage tank 102 to the stirring tank 603 via the line 12 while stirring the stirring tank 103. Following completion of supplying the aniline, stirring was continued for about 28 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain about 5.6% by weight of phenylurea. The concentration of ammonia in the reaction liquid was 7900 ppm. Unreacted amino groups were not detected. Following the reaction, 25.9 kg of an aromatic hydroxy compound in the form of 2-phenyl phenol were added to obtain a mixture. The ratio of the number of alcohol molecules to the number of ureido groups in the mixture was 10.1. Line 63 was opened and the mixture was transferred to the storage tank 604 via the line 63.

Steps (R) and (D): Production of N-substituted Carbamic Acid Mono(-O-R² Ester)

[0583] The packed column 105 packed with a packing material (Helipack No. 3) was heated to 210°C and the pressure inside the column was set to 50 kPa. The reaction liquid obtained in step (A) was fed from the line 14 provided in the packed column 105 at the rate of about 1.2 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 35.8 kg. The reaction liquid was recovered in the storage tank 110 through the line 16 provided in the bottom of the packed column 105. A gaseous phase component was introduced into the condenser 106 from the line 15 provided in the top of the packed column 105, and the resulting liquid phase component was recovered in the storage tank 109 via the gas-liquid separator 108. When the condensed component recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain urea and 1-nonanol. The amount of the reaction liquid recovered in the storage tank 110 was 18.9 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N-phenyl carbamic acid-(nonylester), and the yield of N-phenyl carbamic acid-(nonylester) based on aniline was about 91%.

Step (P): Production of N-substituted Carbamic Acid Mono(-O-Aryl Ester) by Transesterification Reaction

[0584] The apparatus shown in FIG. 16 was used.

[0585] 0.5% by weight of a catalyst in the form of dibutyl tin dilaurate was added to the mixture obtained in step (R) and placed in the storage tank 501. A packed column 502 packed with a packing material (Helipack No. 3) and having an inner diameter of 20 mm was heated to 260°C and the pressure inside the column was set to 26 kPa. The mixture in the storage tank 501 was fed from the line 51 provided in the packed column 502 at the rate of about 1.9 g/min. A reaction liquid was recovered in the storage tank 505 via the line 54 provided in the bottom of the packed column 502. A gaseous phase component was introduced into the condenser 503 from the line 52 provided in the top of the packed column 502, and the resulting liquid phase component was recovered in the storage tank 504 through the gas-liquid separator 507. The amount of reaction liquid recovered in the storage tank 505 was 26.4 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to be a solution containing N-phenyl carbamic acid (2-phenylphenyl) ester, and the yield of N-phenyl carbamic acid (2-phenylphenyl) ester based on aniline was about 89%.

Step (C): Condensation of N-substituted Carbamic Acid Mono(-O-Aryl Ester)

[0586] The apparatus shown in FIG. 15 was used.

[0587] The reaction liquid recovered in the storage tank 505 in step (P) was placed in the stirring tank 408. The stirring tank 408 was heated to 160°C and the pressure inside was set to 1 kPa followed by distilling off 2-phenyl phenol. The

2-phenyl phenol was condensed in the condenser 405 via the line 44 and recovered in the storage tank 407. Next, 2.04 kg of methylal from the storage tank 400, 1.94 kg of nitrobenzole from the storage tank 401, and 1.02 kg of sulfuric acid from the storage tank 402 were added to the stirring tank 408 followed by heating for 24 hours at 90°C while stirring the stirring tank 408. Solvent and unreacted substances were then distilled off by maintaining the temperature of the stirring tank 408 at 90°C and reducing the pressure inside to about 1 kPa. When the resulting compound was analyzed by liquid chromatography, it was found to be a mixture containing about 53% by weight of N,N'-(methanediy-diphenyl)-bis(carbamic acid(2-phenylphenyl) ester).

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0588] The apparatus shown in FIG. 18 was used.

[0589] A thin film distillation apparatus 1002 (Kobelco Eco-Solutions Co., Ltd., Japan) having a heat-conducting surface area of 0.2 m² was heated to 260°C and the pressure within the thin film distillation apparatus was set to about 1.5 kPa. The reaction liquid recovered in the storage tank 404 in step (C) was placed in a storage tank 1001 and supplied to the thin film distillation apparatus at the rate of about 1200 g/hr via a line A1. A liquid component was extracted from a line A4 provided in the bottom of thin film distillation apparatus 1002 and recovered in a storage tank 1003. The liquid component recovered in the storage tank 1003 was again supplied to the thin film distillation apparatus 1002 through a line A3. A gaseous component was extracted from a line A4 provided in the upper portion of the thin film distillation apparatus 1002. The gaseous component was introduced into a distillation column 1004, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 1009 from a line A8 provided at a portion of the distillation column 1004 lower than the feed line and further subjected to distillative separation. A liquid phase component was supplied to the distillation column 1014 from the line A12 provided at a portion of the distillation column 1009 lower than the feed line and further subjected to distillative separation.

[0590] A gaseous phase component was extracted from the line A13 provided in the top of the distillation column 1014 and condensed in the condenser 1015, and the condensate was recovered in the storage tank 1019. When the condensate was analyzed by ¹H-NMR, it was found to be a solution containing about 99% by weight of 4,4'-diphenylmethane diisocyanate (MDI). The yield based on aniline was about 54%.

Step (E): Production of N-substituted Carbamic Acid Ester by Reusing Mixture Obtained in Condenser

[0591] When the ammonia content of the mixture recovered in the storage tank 109 in step (R) of Example 5 was analyzed, it was found to be 1500 ppm. 11.4 kg of 1-nonanol and 1.47 kg of urea were added to 14.7 kg of the mixture followed by transferring to the stirring tank 603 and carrying out the same method as step (A) using 1.08 kg of aniline. A solution containing about 6.8% by weight of phenylurea was obtained. The same method as step (B) was carried out using this solution instead of the solution of step (A). The yield of N-phenylcarbamic acid-(nonylester) in the reaction liquid recovered in the storage tank 110 based on aniline was about 91%.

[Example 7] Production of N-substituted Carbamic Acid-O-Aryl Ester by Route 5)

Step (A): Production of Compound Having Ureido Groups

[0592] The apparatus used in FIG. 13 was used.

[0593] 25.4 kg of a solvent (1-heptanol) and 3.50 kg of urea were mixed in the storage tank 101 heated to 90°C with the line 13 closed, and the mixture was transferred to the stirring tank 103 heated to 90°C. 1.13 kg of aniline were then supplied at the rate of about 18 g/min from the storage tank 102 to the stirring tank 103 via the line 12 while stirring the stirring tank 103. Following completion of supplying the aniline, stirring was continued for about 28 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain about 7.4% by weight of phenylurea. The concentration of ammonia in the reaction liquid was 8300 ppm. Unreacted amino groups were not detected. 24.2 kg of a hydroxy compound in the form of 2,4-di-tert-amyl phenol (Tokyo Chemical Industry Co., Ltd., Japan) were added to the reaction liquid to obtain a mixture. The ratio of the number of alcohol molecules to the number of ureido groups in the mixture was 9.0.

[0594] Line 13 was opened and the mixture was transferred to the storage tank 604 via the line 13.

Steps (R) and (D): Production of N-substituted Carbamic Acid Mono(-O-Alkyl Ester)

[0595] The packed column 105 packed with a packing material (Helipack No. 3) and having a diameter of 40 mm was heated to 190°C and the pressure inside the column was set to 50 kPa. The reaction liquid obtained in step (A) was fed from the line 14 provided in the packed column 105 at the rate of about 1.0 g/min. Since the reaction is initially in an

unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 28.0 kg. The reaction liquid was recovered in the storage tank 110 through the line 16 provided in the bottom of the packed column 105. A gaseous phase component was condensed in the condenser 106 from the line 15 provided in the top of the packed column 105, and the resulting liquid phase component was recovered in the storage tank 109 via the gas-liquid separator 108. When the condensed component recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain urea and 1-heptanol. The amount of the reaction liquid recovered in the storage tank 110 was 13.8 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N-phenyl carbamic acid (1-heptyl) ester, and the yield based on aniline was about 90%.

Step (C): Condensation of N-substituted Carbamic Acid Mono(-O-Alkyl Ester)

[0596] The apparatus shown in FIG. 15 was used.

[0597] The reaction liquid recovered in the storage tank 110 in step (R) was placed in the stirring tank 408. The stirring tank 408 was heated to 160°C and the pressure inside was set to 1 kPa followed by distilling off 1-heptanol. The 1-heptanol was condensed in the condenser 405 via the line 44 and recovered in the storage tank 407. Next, 1.30 kg of methylal from the storage tank 400, 7.34 kg of nitrobenzole from the storage tank 401, and 1.33 kg of sulfuric acid from the storage tank 402 were added to the stirring tank 408 followed by heating for 10 hours at 100°C while stirring the stirring tank 408. Solvent and unreacted substances were then distilled off by maintaining the temperature of the stirring tank 408 at 100°C and reducing the pressure inside to about 1 kPa. When the resulting compound was analyzed by liquid chromatography, it was found to be a mixture containing about 63% by weight of N,N'-(methanediyl-diphenyl)-bis(carbamic acid octyl ester). 24.2 kg of an aromatic hydroxy compound in the form of 2,4-di-tert-amyl phenol were then added to the mixture to obtain a mixture.

Step (P): Production of N-substituted Carbamic Acid-O-Aryl Ester by Transesterification Reaction

[0598] The apparatus shown in FIG. 16 was used.

[0599] 0.5% by weight of a catalyst in the form of dibutyl tin dilaurate was added to the mixture obtained in step (C) and placed in the storage tank 501. The packed column 502 packed with a packing material (Helipack No. 3) and having an inner diameter of 20 mm was heated to 250°C and the pressure inside the column was set to 20 kPa. The mixture in the storage tank 501 was fed from the line 51 provided in the packed column 502 at the rate of about 1.3 g/min. A reaction liquid was recovered in the storage tank 505 via the line 54 provided in the bottom of the packed column 502. A gaseous phase component was introduced into the condenser 503 from the line 52 provided in the top of the packed column 502, and the resulting liquid phase component was recovered in the storage tank 504 through the gas-liquid separator 507. The amount of reaction liquid recovered in the storage tank 505 was 25.0 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to be a solution containing N,N'-(methanediyl-diphenyl)-bis(carbamic acid(2,4-di-tert-amylphenyl) ester).

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0600] The apparatus shown in FIG. 18 was used.

[0601] A thin film distillation apparatus 1002 (Kobelco Eco-Solutions Co., Ltd., Japan) having a heat-conducting surface area of 0.2 m² was heated to 260°C and the pressure within the thin film distillation apparatus was set to about 1.5 kPa. The reaction liquid recovered in the storage tank 505 in step (P) was placed in a storage tank 1001 and supplied to the thin film distillation apparatus at the rate of about 1200 g/hr via a line A1. A liquid component was extracted from a line A4 provided in the bottom of thin film distillation apparatus 1002 and recovered in a storage tank 1003. The liquid component recovered in the storage tank 1003 was again supplied to the thin film distillation apparatus 1002 through a line A3. A gaseous component was extracted from a line A4 provided in the upper portion of the thin film distillation apparatus 1002. The gaseous component was introduced into a distillation column 1004, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 1009 from a line A8 provided at a portion of the distillation column 1004 lower than the feed line and further subjected to distillative separation. A liquid phase component was supplied to the distillation column 1014 from the line A12 provided at a portion of the distillation column 1009 lower than the feed line and further subjected to distillative separation.

[0602] A gaseous phase component was extracted from the line A13 provided in the top of the distillation column 1014 and condensed in the condenser 1015, and the condensate was recovered in the storage tank 1019. When the condensate was analyzed by ¹H-NMR, it was found to be a solution containing about 99% by weight of 4,4'-diphenylmethane diisocyanate (MDI). The yield based on aniline was about 47%.

EP 2 322 504 B9

Step (E): Production of N-substituted Carbamic Acid Ester by Reusing Mixture Obtained in Condenser

5 **[0603]** When the ammonia content of the mixture recovered in the storage tank 109 in step (R) was analyzed, it was found to be 900 ppm. 9.48 kg of 1-heptanol and 1.54 kg of urea were added to the mixture followed by transferring to the stirring tank 603 and carrying out the same method as step (A) using 1.12 kg of aniline. A solution containing about 7.4% by weight of phenylurea was obtained. The same method as step (B) was carried out using this solution instead of the solution of step (A). The yield of N-phenylcarbamic acid-(heptylester) in the reaction liquid recovered in the storage tank 110 based on aniline was about 90%.

10 [Examples 8 to 30]

15 **[0604]** The same method as Example 1 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 8 to 30 along with the results are shown in Tables 2 and 3. In addition, the compounds and reaction conditions used in steps (B) and (D) of Examples 8 to 30 along with the results are shown in Tables 4 and 5. In addition, the compounds and reaction conditions used in step (F) of Examples 8 to 30 along with the results are shown in Tables 6 and 7. Although "FIG. 17" and "FIG. 18" are indicated in the "apparatus drawing" column for step (F), "FIG. 17" indicates that the same method as step (F) of Example 1 was carried out using an apparatus as shown in FIG. 17. On the other hand, "FIG. 18" indicates that the same method as step (F) of Example 4 was carried out using an apparatus as shown in FIG. 18. In addition, the compounds and reaction conditions used in step (E) of Examples 8 to 30 along with the results are shown in Tables 8 and 9. Furthermore, the reaction conditions and results for Example 1 are also shown in Tables 2 to 9 to clarify correspondence with the description of Example 1.

20 **[0605]** In addition, the following abbreviations are used in the tables of the examples.

25 HDA: Hexamethylenediamine

IPDA: 3-aminomethyl-3,5,5-trimethylcyclohexylamine

TDA: 2,4-toluenediamine

MDA: 4,4'-methylenedianiline

H-MDA: 4,4'-methylenedi(cyclohexylamine)

30

35

40

45

50

55

[Table 2]

Example	Step (A)		Organic amine (amount used)	Amount of urea used	Aromatic hydroxy compound			Organic amine supply rate	Solution after reaction			
	Temperature of stirring tank 103 (°C)	Name			Amount used	Water content	Compound having ureido groups formed		Concentration of compound having ureido groups	Ammonia concentration (ppm)	Ratio of number of molecules of aromatic hydroxy compound to number of ureido groups	
Example 1	120		HDA (1.50 kg)	3.10 kg	p-heptyl phenol	(41.8 kg)	15 ppm	20 g/min	1,1'-(hexane-1,6-diyl) diurea	6.3 wt%	6300 ppm	7.5
Example 8	190		HDA (1.42 kg)	3.31 kg	2-naphthol	(29.9 kg)	13 ppm	83 g/min	1,1'-(hexane-1,6-diyl) diurea	7.2 wt%	6200 ppm	8.6
Example 9	150		HDA (1.29 kg)	2.68 kg	4-phenyl phenol	(18.9 kg)	16 ppm	20 g/min	1,1'-(hexane-1,6-diyl) diurea	10 wt%	5100 ppm	5.1
Example 10	100		HDA (1.14 kg)	2.42 kg	2-ethoxyphenol	(18.9 kg)	20 ppm	15 g/min	1,1'-(hexane-1,6-diyl) diurea	11.3 wt%	4500 ppm	9.2
Example 11	130		IPDA (1.82 kg)	2.25 kg	4-cumyl phenol	(14.5 kg)	16 ppm	42 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	14.9 wt%	3500 ppm	3.2
Example 12	100		IPDA (1.22 kg)	1.64 kg	4-(1,1,3,3-tetramethylbutyl) phenol	(8.26 kg)	630 ppm	20 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	14.6 wt%	7800 ppm	3.3
Example 13	100		IPDA (1.19 kg)	1.61 kg	p-nonyl phenol	(61.6 kg)	20 ppm	20 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	2.7 wt%	6200 ppm	20.4
Example 14	110		IPDA (1.01 kg)	1.35 kg	p-dodecyl phenol	(62.3 kg)	58 ppm	20 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	2.3 wt%	3800 ppm	20.6
Example 15	100		TDA (2.11 kg)	3.38 kg	p-dodecyl phenol	(19 kg)	720 ppm	20 g/min	2,4-toluenediurea	12.2 wt%	8820 ppm	2.5
Example 16	90		TDA (3.51 kg)	1.99 kg	4-tert-butyl phenol	(16.4 kg)	14 ppm	13 g/min	2,4-toluenediurea	18.6 wt%	3600 ppm	2.5

(continued)

Example	Step (A)		Aromatic hydroxy compound			Organic amine supply rate	Solution after reaction			
	Temperature of stirring tank (°C)	Organic amine (amount used)	Amount of urea used	Name	Amount used		Water content	Compound having ureido groups formed	Concentration of compound having ureido groups	Ammonia concentration (ppm)
Example 17	70	TDA (1.19 kg)	2.46 kg	p-nonyl phenol	(38.6 kg)	530 ppm	2,4-toluenediurea	4.8 wt%	8210 ppm	9.1
Example 18	80	TDA (1.21 kg)	2.49 kg	2-naphthol	(28.6 kg)	210 ppm	2,4-toluenediurea	6.4 wt%	4200 ppm	10.1

[Table 3]

Example	Step (A)	Temperature of stirring tank 103 (°C)	Organic amine (amount used)	Amount of urea used	Aromatic hydroxy compound			Organic amine supply rate	Solution after reaction	Concentration of compound having ureido groups	Ammonia concentration (ppm)	Ratio of number of molecules of aromatic hydroxy compound to number of ureido groups
					Name	Amount used	Water content					
Example 19	80	TDA	(1.53 kg)	3.08 kg	3,5-dimethoxy phenol	(32.8 kg)	150 ppm	20 g/min	2,4-toluenediurea	6.9 wt%	3200 ppm	8.6
Example 20	100	MDA	(0.53 kg)	0.64 kg	4-(1,1,3,3-tetramethylbutyl) phenol	(44.1 kg)	35 ppm	90 g/min	4,4'-methanediyldiphenyldiurea	1.6 wt%	2250 ppm	41.2
Example 21	80	MDA	(0.53 kg)	0.75 kg	3,5-dimethoxy phenol	(51.0 kg)	40 ppm	20 g/min	4,4'-methanediyldiphenyldiurea	1.1 wt%	1080 ppm	120.7
Example 22	100	H-MDA	(0.41 kg)	2.03 kg	4-ethyl phenol	(31.9 kg)	80 ppm	25 g/min	4,4'-methanediyldicyclohexyldiurea	5.7 wt%	5210 ppm	19.4
Example 23	100	H-MDA	(1.38 kg)	2.05 kg	2-tert-amyl phenol	(37.7 kg)	120 ppm	24 g/min	4,4'-methanediyldicyclohexyldiurea	4.7 wt%	3620 ppm	17.9
Example 24	200	HDA	(0.93 kg)	8.65 kg	Hydroquinone	(52.9 kg)	330 ppm	170 g/min	1,1'-(hexane-1,6-diyl) diurea	2.3 wt%	2400 ppm	33.3
Example 25	180	IPDA	(0.83 kg)	4.39 kg	Bisphenol A	(53.4 kg)	20 ppm	180 g/min	3-(ureidomethyl)-3,5-trimethylcyclohexylurea	2.1 wt%	2200 ppm	24.7
Example 26	120	HDA	(0.93 kg)	2.02 kg	2,4-di-tert-amyl phenol	(56.3 kg)	32 ppm	42 g/min	1,1'-(hexane-1,6-diyl) diurea	2.8 wt%	2300 ppm	15.3
Example 27	120	HDA	(0.53 kg)	1.15 kg	2,4-dicumyl phenol	(55.8 kg)	50 ppm	45 g/min	1,1'-(hexane-1,6-diyl) diurea	1.6 wt%	1100 ppm	18.9
Example 28	130	HDA	(1.09 kg)	2.31 kg	2-phenyl phenol	(55.9 kg)	14 ppm	38 g/min	1,1'-(hexane-1,6-diyl) diurea	3.2 wt%	1020 ppm	17.9

(continued)

Example	Step (A)	Temperature of stirring tank (°C)	Organic amine (amount used)	Amount of urea used	Aromatic hydroxy compound		Organic amine supply rate	Solution after reaction			Ratio of number of molecules of aromatic hydroxy compound to number of ureido groups
					Name	Amount used		Water content	Compound having ureido groups formed	Concentration of compound having ureido groups	
Example 29	130	IPDA	(1.15 kg)	1.66 kg	2,6-diisopropylphenol	(32.5 kg)	29 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	4.5 wt%	1900 ppm	13.8
Example 30	100	IPDA	(1.15 kg)	2.03 kg	4-chlorophenol	(52.1 kg)	40 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	3.1 wt%	1200 ppm	30.6

[Table 4]

Example	Step (B)				Step (D)			
	Temperature of packed column 105 (°C)	Pressure of packed column 105 (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-aryl ester formed (yield based on organic amine)	Ammonia concentration in reaction liquid	Recovered amt. in storage tank 109 (kg)	Aromatic hydroxy compound content (%)	Urea content (%)
Example 1	240	26	35.1	N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) (97%)	9.0 ppm	13.5	85.4	10.2
Example 8	240	15	32.5	N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) (92%)	11.8 ppm	11.1	80.7	14.3
Example 9	280	30	21.1	N,N'-hexanediyldi(carbamic acid (4-phenylphenyl) ester) (97%)	9.5 ppm	7.5	73.5	15.2
Example 10	210	40	20.0	N,N'-hexanediyldi(carbamic acid (2-ethoxyphenyl) ester) (75%)	330 ppm	6.8	79.8	15.7
Example 11	280	30	17.3	3-(4-(α,α -dimethylbenzyl)phenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-(α,α -dimethylbenzyl)phenyl) ester (95%)	7.5 ppm	5.5	80.1	16.0
Example 12	230	20	9.3	3-(4-(1,1,3,3-tetramethylbutyl)phenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester (84%)	8.1 ppm	5.9	70.9	24.0
Example 13	210	20	60.7	3-(p-nonylphenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-nonylphenyl) ester (85%)	290 ppm	19.9	95.7	3.5
Example 14	230	40	61.5	3-(p-dodecylphenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-dodecylphenyl) ester (78%)	305 ppm	7.8	90.1	7.9
Example 15	220	15	23.8	Toluene-2,4-di(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester) (73%)	5.9 ppm	8.8	61.3	30.7

(continued)

Example	Step (B)			Step (D)				
	Temperature of packed column 105 (°C)	Pressure of packed column 105 (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-aryl ester formed (yield based on organic amine)	Ammonia concentration in reaction liquid	Recovered amt. in storage tank 109 (kg)	Aromatic hydroxy compound content (%)	Urea content (%)
Example 16	210	26	22.5	Toluene-2,4-di(carbamic acid (4-tert-butylphenyl) ester) (65%)	6.9 ppm	8.2	55.9	37.9
Example 17	250	20	40.5	Toluene-2,4-di(carbamic acid (p-nonylphenyl) ester) (91%)	8.2 ppm	13.5	89.0	8.9
Example 18	240	20	29.5	Toluene-2,4-di(carbamic acid (2-naphthyl) ester) (70%)	980 ppm	9.9	86.1	11.9

[Table 5]

Example	Step (B)				Step (D)			
	Temperature of packed column 105 (°C)	Pressure of packed column 105 (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-arylesterformed (yield based on organic amine)	Ammonia concentration in reaction liquid	Recovered amt. in storage tank 109 (kg)	Aromatic hydroxy compound content (%)	Urea content (%)
Example 19	250	30	34.6	Toluene-2,4-di(carbamic acid (3,5-dimethoxyphenyl) ester) (62%)	1050 ppm	11.6	85.4	12.5
Example 20	250	45	43.8	N,N'-(4,4'-methanediyl-diphenyl)-di(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester) (87%)	11 ppm	14.4	97.7	2.0
Example 21	220	30	43.8	N,N'-(4,4'-methanediyl-diphenyl)-di(carbamic acid (3,5-dimethoxyphenyl) ester) (88%)	15 ppm	14.6	97.1	2.3
Example 22	200	70	33.6	N,N'-(4,4'-methanediyl-dicyclohexyl)-di(carbamic acid (4-ethylphenyl) ester) (92%)	29 ppm	11.3	89.5	10.4
Example 23	230	35	43.9	N,N'-(4,4'-methanediyl-dicyclohexyl)-di(carbamic acid (2-tert-amyphenyl) ester) (93%)	11 ppm	18.1	65.5	33.4
Example 24	250	40	55.8	N,N'-hexanediyl-di(carbamic acid (4-hydroxyphenyl) ester) (68%)	9.5 ppm	22.7	69.1	30.0
Example 25	280	15	56.3	N,N'-hexanediyl-di(carbamic acid (4-(2-(4-hydroxyphenyl)-2-methyl-ethyl)phenyl) ester) (69%)	6.5 ppm	20.8	81.5	17.0
Example 26	240	30	53.9	N,N'-hexanediyl-di(carbamic acid (2,4-di-tert-amyphenyl) ester) (75%)	8.3 ppm	17.9	92.4	5.0
Example 27	280	10	55.0	N,N'-hexanediyl-di(carbamic acid (2,4-dicumylphenyl) ester) (70%)	5.4 ppm	18.2	95.1	2.9
Example 28	270	20	53.9	N,N'-hexanediyl-di(carbamic acid (2-phenylphenyl) ester) (81%)	4.4 ppm	17.9	92.2	5.6

(continued)

Example	Step (B)			Step (D)				
	Temperature of packed column 105 (°C)	Pressure of packed column 105 (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-aryl ester formed (yield based on organic amine)	Ammonia concentration in reaction liquid	Recovered amt. in storage tank 109 (kg)	Aromatic hydroxy compound content (%)	Urea content (%)
Example 29	220	20	33.5	3-((2,6-diisopropylphenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (2,6-diisopropylphenyl) ester (54%)	8.1 ppm	11.0	90.4	6.8
Example 30	210	60	50.5	3-((4-chlorophenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-chlorophenyl) ester (90%)	5.9 ppm	16.8	92.0	6.1

[Table 6]

Example	Step (F)				
	Apparatus drawing	Temperature of thin film distillation apparatus (°C)	Pressure of thin film distillation apparatus (kPa)	Recovered isocyanate (yield based on organic amine)	
Example 1	FIG. 17	220	1.3	Hexamethylene diisocyanate	(90%)
Example 8	FIG. 17	200	1.0	Hexamethylene diisocyanate	(93%)
Example 9	FIG. 17	210	2.0	Hexamethylene diisocyanate	(92%)
Example 10	FIG. 18	190	1.0	Hexamethylene diisocyanate	(71%)
Example 11	FIG. 17	220	1.5	Isophorone diisocyanate	(92%)
Example 12	FIG. 17	210	1.0	Isophorone diisocyanate	(81%)
Example 13	FIG. 17	220	1.0	Isophorone diisocyanate	(83%)
Example 14	FIG. 17	230	0.5	Isophorone diisocyanate	(75%)
Example 15	FIG. 17	190	0.8	2,4-tolylene diisocyanate	(65%)
Example 16	FIG. 18	190	0.8	2,4-tolylene diisocyanate	(58%)
Example 17	FIG. 17	200	1.2	2,4-tolylene diisocyanate	(86%)
Example 18	FIG. 17	210	1.0	2,4-tolylene diisocyanate	(65%)

[Table 7]

Example	Step (F)				
	Apparatus drawing	Temperature of thin film distillation apparatus (°C)	Pressure of thin film distillation apparatus (kPa)	Recovered isocyanate (yield based on organic amine)	
Example 19	FIG. 17	220	2.5	2,4-tolylene diisocyanate	(59%)
Example 20	FIG. 18	240	0.8	4,4'-diphenylmethane diisocyanate	(72%)
Example 21	FIG. 18	250	1.0	4,4'-diphenylmethane diisocyanate	(66%)
Example 22	FIG. 18	260	1.3	4,4'-dicyclohexylmethane diisocyanate	(89%)

EP 2 322 504 B9

(continued)

Example	Step (F)				
	Apparatus drawing	Temperature of thin film distillation apparatus (°C)	Pressure of thin film distillation apparatus (kPa)	Recovered isocyanate (yield based on organic amine)	
Example 23	FIG. 18	260	1.3	4,4'-dicyclohexylmethane diisocyanate	(89%)
Example 24	FIG. 17	250	1.0	Hexamethylene diisocyanate	(63%)
Example 25	FIG. 17	250	1.0	Isophorone diisocyanate	(56%)
Example 26	FIG. 17	250	1.0	Hexamethylene diisocyanate	(66%)
Example 27	FIG. 17	250	1.0	Hexamethylene diisocyanate	(62%)
Example 28	FIG. 17	250	1.0	Hexamethylene diisocyanate	(75%)
Example 29	FIG. 18	250	1.0	Isophorone diisocyanate	(50%)
Example 30	FIG. 18	250	1.0	Isophorone diisocyanate	(56%)

[Table 8]

Example	Step (E)						
	Ammonia content of mixture recovered in storage tank 109	Organic amine (amount used)		Amount of urea added	Aromatic hydroxy compound added (amount used)		Yield of N-substituted carbamic acid-O-aryl ester based on organic amine
Example 1	820	HDA	(0.92 kg)	3.10 kg	p-heptyl phenol	(41.8 kg)	97%
Example 8	1200	HDA	(1.18 kg)	1.03 kg	2-naphthol	(15.2 kg)	97%
Example 9	5300	HDA	(1.19 kg)	0.55 kg	4-phenyl phenol	(8.29 kg)	88%
Example 10	530	HDA	(1.14 kg)	0.63 kg	2-ethoxy phenol	(9.53 kg)	75%
Example 11	940	IPDA	(1.80 kg)	1.33 kg	4-cumyl phenol	(9.97 kg)	95%
Example 12	2200	IPDA	(1.29 kg)	0.98 kg	4-(1,1,3,3-tetramethylbutyl) phenol	(6.52 kg)	80%
Example 13	1500	IPDA	(1.19 kg)	0.89 kg	p-nonyl phenol	(42.5 kg)	85%
Example 14	1200	IPDA	(1.01 kg)	0.74 kg	p-dodecyl phenol	(55.3 kg)	78%

[Table 9]

Example	Step (E)						
	Ammonia content of mixture recovered in storage tank 109	Organic amine (amount used)		Amount of urea added	Aromatic hydroxy compound added (amount used)		Yield of N-substituted carbamic acid-O-aryl ester based on organic amine
Example 15	1350	TDA	(2.11 kg)	1.98 kg	p-dodecyl phenol	(13.7 kg)	73%
Example 16	450	TDA	(3.51 kg)	3.61 kg	4-tert-butyl phenol	(11.8 kg)	65%
Example 17	190	TDA	(1.20 kg)	1.04 kg	p-nonyl phenol	(24.6 kg)	91%
Example 18	320	TDA	(1.23 kg)	1.35 kg	2-naphthol	(20.5 kg)	70%
Example 19	1500	TDA	(1.42 kg)	2.86 kg	3,5-dimethoxy phenol	(30.5 kg)	62%
Example 20	560	MDA	(0.53 kg)	0.31 kg	4-(1,1,3,3-tetramethylbutyl) phenol	(29.9 kg)	87%
Example 21	270	MDA	(0.41 kg)	0.32 kg	3,5-dimethoxy phenol	(36.9 kg)	88%
Example 22	3200	H-MDA	(1.45 kg)	0.35 kg	4-ethyl phenol	(17.7 kg)	85%
Example 23	350	H-MDA	(1.29 kg)	0.10 kg	2-tert-amyl phenol	(22.4 kg)	93%

[Examples 31 to 42]

[0606] The same method as Example 2 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 31 to 42 along with the results are shown in Table 10. In addition, the compounds and reaction conditions used in step (D) of Examples 21 to 32 along with the results are shown in Table 11. The compounds and reaction conditions used in steps (B) and (F) of Examples 26 to 37 along with the results are shown in Table 12. Although "FIG. 17" and "FIG. 18" are indicated in the "apparatus drawing" column for step (F) in Table 12, "FIG. 17" indicates that the same method as step (F) of Example 1 was carried out using an apparatus as shown in FIG. 17. On the other hand, "FIG. 18" indicates that the same method as step (F) of Example 4 was carried out using an apparatus as shown in FIG. 18. In addition, the compounds and reaction conditions used in step (E) of Examples 31 to 42 along with the results are shown in Table 13.

[Table 10]

Example	Step (A)		Amount of urea used	Solvent (amount used)		Organic amine supply rate	Compound having ureido groups	Conc. of compound having ureido groups	Residual NH ₃	Aromatic hydroxy compound added after reaction (amount used)					
	Temp. of storage tank 203 (°C)	Organic amine (amount used)		1-butanol	2,6-dimethyl phenol					1,1'-(hexane-1,6-diyl) diurea	1,1'-(hexane-1,6-diyl) diurea	1,1'-(hexane-1,6-diyl) diurea	1,1'-(hexane-1,6-diyl) diurea	2-naphthol	4-phenyl phenol
Example 2	120	HDA (0.93 kg)	1.92 kg	1-butanol (11.9 kg)	20 g/min	1,1'-(hexane-1,6-diyl) diurea	11.2 wt%	7500 ppm	p-heptyl phenol (23.1 kg)						
Example 31	120	HDA (1.02 kg)	2.27 kg	2,6-dimethyl phenol (10.7 kg)	30 g/min	1,1'-(hexane-1,6-diyl) diurea	13.0 wt%	4300 ppm	p-nonyl phenol (19.3 kg)						
Example 32	100	HDA (1.02 kg)	2.37 kg	2-isopropyl phenol (6.21 kg)	32 g/min	1,1'-(hexane-1,6-diyl) diurea	16.4 wt%	6200 ppm	4-phenyl phenol (22.4 kg)						
Example 33	90	HDA (1.53 kg)	3.16 kg	Phenol (9.90 kg)	20 g/min	1,1'-(hexane-1,6-diyl) diurea	18.5 wt%	8200 ppm	2-naphthol (18.9 kg)						
Example 34	150	IPDA (1.42 kg)	2.15 kg	1-butanol (5.55 kg)	40 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	17.1 wt%	3400 ppm	4-tert-amyl phenol (17.8 kg)						
Example 35	100	IPDA (1.39 kg)	2.50 kg	2-methyl phenol (9.71 kg)	50 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	13.3 wt%	5600 ppm	p-dodecyl phenol (25.7 kg)						
Example 36	110	TDA (2.53 kg)	5.22 kg	2,4,6-trimethyl phenol (7.05 kg)	20 g/min	2,4-toluenediurea	16.0 wt%	3500 ppm	4-cumyl phenol (19.5 kg)						
Example 37	90	TDA (1.05 kg)	2.32 kg	2-bromophenol (14.9 kg)	20 g/min	2,4-toluenediurea	9.8 wt%	9100 ppm	3,5-dimethoxy phenol (14.6 kg)						
Example 38	80	TDA (1.14 kg)	2.24 kg	3-methyl-1-butanol (2.14 kg)	20 g/min	2,4-toluenediurea	27.3 wt%	9300 ppm	4-(1,1,3,3-tetramethylbutyl) phenol (23.1 kg)						
Example 39	100	MDA (1.64 kg)	1.99 kg	2-isopropyl phenol (12.4 kg)	40 g/min	4,4'-methanediyl diphenyl diurea	14.7 wt%	2800 ppm	1-naphthol (11.9 kg)						

(continued)

Example	Step (A)		Amount of urea used	Solvent (amount used)	Organic amine supply rate	Compound having ureido groups	Conc. of compound having ureido groups	Residual NH ₃	Aromatic hydroxy compound added after reaction (amount used)
	Temp. of storage tank 203 (°C)	Organic amine (amount used)							
Example 40	80	MDA (1.86 kg)	2.31 kg	1-butanol (10.4 kg)	30 g/min	4,4'-methanediyldiphenyldiurea	16.0 wt%	3200 ppm	p-heptyl phenol (14.4 kg)
Example 41	160	H-MDA (1.75 kg)	2.90 kg	2-methyl phenol (13.5 kg)	50 g/min	4,4'-methanediyldicyclohexyldiurea	13.6 wt%	2800 ppm	2,4,6-trimethylphenol (11.3 kg)
Example 42	130	H-MDA (1.63 kg)	2.83 kg	1-heptanol (7.02 kg)	40 g/min	4,4'-methanediyldicyclohexyldiurea	13.8 wt%	3200 ppm	4-ethoxy phenol (10.7 kg)

[Table 11]

Example	Step (D)		Storage tank 209			Storage tank 208			
	Temp. of distillation column 205 (°C)	Pressure in distillation column 205 (kPa)	Amt. recovered in storage tank 209 (kg)	Conc. of compound having ureido groups in residual liquid (wt%)	Ratio of no. of molecules of aromatic hydroxy compound to no. of ureido groups	Amt. recovered in storage tank 208 (kg)	Hydroxy compound content (%)	Urea content (%)	
Example 2	120	10	13.5	12	3.9	12.8	92.5	7.1	
Example 31	125	5	21.5	8.3	5.0	11.6	91.7	7.2	
Example 32	130	8	28.9	6.3	8.8	7.5	81.7	17.5	
Example 33	130	15	22.3	11.7	5.0	10.8	91.1	8.5	
Example 34	150	15	20.0	6.9	9.9	6.7	82.9	15.6	
Example 35	120	10	28.4	6.3	7.0	10.5	90.9	8.8	
Example 36	140	10	26.2	9.1	4.1	7.9	87.8	11.0	
Example 37	140	8	16.7	10.5	5.6	15.8	93.9	5.9	
Example 38	110	50	25.2	4.9	9.4	3.3	65.0	32.1	
Example 39	120	15	14.4	16.0	5.1	13.2	92.7	7.2	
Example 40	110	10	17.1	13.4	4.7	11.6	89.6	9.8	
Example 41	130	5	15.2	15.8	5.1	13.9	93.1	6.5	

5
10
15
20
25
30
35
40
45
50
55

(continued)

Example	Step (D)		Storage tank 209		Storage tank 208			
	Temp. of distillation column 205 (°C)	Pressure in distillation column 205 (kPa)	Amt. recovered in storage tank 209 (kg)	Conc. of compound having ureido groups in residual liquid (wt%)	Ratio of no. of molecules of aromatic hydroxy compound to no. of ureido groups	Amt. recovered in storage tank 208 (kg)	Hydroxy compound content (%)	Urea content (%)
Example 42	130	3	13.1	11.2	7.8	9.0	78.7	20.0

[Table 12]

Example	Step (B)		Step (F)					Recovered isocyanate (yield based on organic amine)
	Temp. of distillation column 210 (°C)	Pressure of distillation column 210 (kPa)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Ammonia concentration in reaction liquid	Apparatus drawing	Thin film distillation apparatus temp. (°C)	Thin film distillation apparatus pressure (kPa)	
Example 2	250	26	N,N'-hexanediyldi(carbamic acid (p-heptyphenyl) ester) (95%)	8.0 ppm	FIG. 17	220	1.3	Hexamethylene diisocyanate (90%)
Example 31	240	30	N,N'-hexanediyldi(carbamic acid (p-nonylphenyl) ester) (96%)	8.3 ppm	FIG. 17	200	2.0	Hexamethylene diisocyanate (92%)
Example 32	260	30	N,N'-hexanediyldi(carbamic acid (4-phenylphenyl) ester) (81%)	9.7 ppm	FIG. 17	220	2.0	Hexamethylene diisocyanate (73%)
Example 33	230	25	N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) (93%)	6.5 ppm	FIG. 17	200	1.0	Hexamethylene diisocyanate (89%)
Example 34	230	40	3-((4-tert-aminophenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-tert-aminophenyl) ester (62%)	3.8 ppm	FIG. 18	210	1.3	Isophorone diisocyanate (57%)
Example 35	245	20	3-((p-dodecylphenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-dodecylphenyl) ester (81%)	9.1 ppm	FIG. 17	230	2.0	Isophorone diisocyanate (73%)
Example 36	220	15	Toluene-2,4-di(carbamic acid (4-cumylphenyl) ester) (52%)	8.5 ppm	FIG. 17	200	40.0	2,4-tolylene diisocyanate (45%)

(continued)

Example	Step (B)		Step (F)				Recovered isocyanate (yield based on organic amine)	
	Temp. of distillation column 210 (°C)	Pressure of distillation column 210 (kPa)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Ammonia concentration in reaction liquid	Apparatus drawing	Thin film distillation apparatus temp. (°C)		Thin film distillation apparatus pressure (kPa)
Example 37	240	30	Toluene-2,4-di(carbamic acid (3,5-dimethoxyphenyl) ester) (88%)	5.4 ppm	FIG. 17	190	0.4	2,4-tolylene diisocyanate (82%)
Example 38	230	25	Toluene-2,4-di(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester) (61%)	9.2 ppm	FIG. 17	210	0.8	2,4-tolylene diisocyanate (54%)
Example 39	250	40	N,N'-(4,4'-methanediyl-diphenyl)-di(carbamic acid (1-naphthyl) ester) (88%)	7.7 ppm	FIG. 18	250	0.7	4,4'-diphenylmethane diisocyanate (85%)
Example 40	230	20	N,N'-(4,4'-methanediyl-diphenyl)-di(carbamic acid (p-heptylphenyl) ester) (82%)	6.9 ppm	FIG. 18	260	1.0	4,4'-diphenylmethane diisocyanate (71%)
Example 41	220	60	N,N'-(4,4'-methanediyl-dicyclohexyl)-di(carbamic acid (2,4,6-trimethylphenyl) ester) (90%)	8.1 ppm	FIG. 18	240	0.8	4,4-dicyclohexylmethane diisocyanate (87%)
Example 42	200	80	N,N'-(4,4'-methanediyl-dicyclohexyl)-di(carbamic acid (4-ethoxyphenyl) ester) (60%)	3.9 ppm	FIG. 18	250	0.8	4,4'-dicyclohexylmethane diisocyanate (51%)

[Table 13]

Example	Step (E)						
	Ammonia content of mixture recovered in storage tank 208	Organic amine (amount used)		Amount of urea added	Solvent added (amount used)		Yield of N-substituted carbamic acid-O-aryl ester based on organic amine
Example 2	550	HDA	(0.93 kg)	0.96 kg	(Not used)		95%
Example 31	640	HDA	(1.3 kg)	1.93 kg	2,6-dimethyl phenol	(3.04 kg)	96%
Example 32	950	HDA	(1.02 kg)	1.00 kg	(Not used)		81%
Example 33	2930	HDA	(1.91 kg)	3.00 kg	Phenol	(2.49 kg)	89%
Example 34	630	IPDA	(1.72 kg)	1.65 kg	1-hexanol	(1.94 kg)	95%
Example 35	590	IPDA	(1.42 kg)	1.59 kg	(Not used)		73%
Example 36	460	TDA	(2.53 kg)	4.26 kg	(Not used)		53%
Example 37	1150	TDA	(1.70 kg)	2.82 kg	2-bromophenol	(9.35 kg)	88%
Example 38	1900	TDA	(1.14 kg)	1.28 kg	(Not used)		61%
Example 39	910	MDA	(1.63 kg)	1.04 kg	(Not used)		88%
Example 41	4890	H-MDA	(1.75 kg)	1.94 kg	2-methyl phenol	(0.52 kg)	84%
Example 42	1020	H-MDA	(1.82 kg)	1.24 kg	1-heptanol	(0.96 kg)	61%

[Examples 43 to 49]

[0607] The same method as Example 3 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 43 to 49 along with the results are shown in Table 14. In addition, the compounds and reaction conditions used in steps (B) and (D) of Examples 43 to 49 along with the results are shown in Table 15. Although "FIG. 17" and "FIG. 18" are indicated in the "apparatus drawing" column for step (F) in Table 15, "FIG. 17" indicates that the same method as step (F) of Example 1 was carried out using an apparatus as shown in FIG. 17. On the other hand, "FIG. 18" indicates that the same method as step (F) of Example 4 was carried out using an apparatus as shown in FIG. 18. In addition, the compounds and reaction conditions used in step (F) of Examples 43 to 49 along with the results are shown in Table 16.

[Table 14]

Example	Step (A)		Amount of urea used	Solvent (amount used)	Organic amine supply rate	Compound having ureido groups	Conc. of compound having ureido groups	Residual amount of NH_3	Aromatic hydroxy compound added after reaction (amount added)	Ratio of aromatic hydroxy compound to ureido groups
	Temp. of distillation column (°C)	Organic amine (amount used)								
Example 3	100	HDA (1.07 kg)	2.49 kg	1-butanol (13.6 kg)	20 g/min	1,1'-(hexane-1,6-diyl) diurea	10.9 wt%	4300 ppm	p-heptyl phenol (26.6 kg)	7.7
Example 43	120	HDA (1.06 kg)	1.97 kg	1-butanol (13.5 kg)	20 g/min	1,1'-(hexane-1,6-diyl) diurea	11.2 wt%	4400 ppm	p-heptyl phenol (26.3 kg)	7.7
Example 44	120	HDA (1.05 kg)	1.19 kg	1-butanol (13.4 kg)	20 g/min	1,1'-(hexane-1,6-diyl) diurea	11.7 wt%	4200 ppm	p-heptyl phenol (26.1 kg)	7.7
Example 45	110	HDA (1.1 kg)	2.44 kg	2,6-dimethylphenol (11.5 kg)	32 g/min	1,1'-(hexane-1,6-diyl) diurea	13.0 wt%	4200 ppm	4-phenylphenol (16.1 kg)	10.1
Example 46	120	HDA (1.02 kg)	2.37 kg	2-phenyl ethanol (10.7 kg)	29 g/min	1,1'-(hexane-1,6-diyl) diurea	12.7 wt%	6500 ppm	p-nonyl phenol (29.0 kg)	7.6
Example 47	90	HDA (1.45 kg)	2.99 kg	Phenol (9.4 kg)	30 g/min	1,1'-(hexane-1,6-diyl) diurea	18.5 wt%	7300 ppm	2-naphthol (18.0 kg)	9.2
Example 48	120	IPDA (1.39 kg)	2.11 kg	Ethylene glycol monobutyl ether (19.3 kg)	43 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	9.1 wt%	4800 ppm	4-tert-amyl phenol (17.4 kg)	6.6
Example 49	120	IPDA (1.42 kg)	2.15 kg	2-methyl phenol (9.01 kg)	33 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	17.1 wt%	4200 ppm	4-cumyl phenol (23.1 kg)	11.7

[Table 15]

Example	Step (B)			Step (D)				Urea content (%)
	Temp. of distillation column 105 (°C)	Pressure of distillation column 105 (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-aryl ester (yield based on aromatic amine)	Ammonia concentration in reaction liquid	Amount recovered in storage tank 109 (kg)	Aromatic hydroxy compound content (%)	
Example 3	240	50	37.8	N,N'-hexanediy-dl(carbamic acid (p-hetpylphenyl) ester) (94%)	8.1 ppm	13.3	89.1	9.1
Example 43	240	30	36.5	N,N'-hexanediy-dl(carbamic acid (p-heptylphenyl) ester) (93%)	5.8 ppm	12.6	92.4	5.8
Example 44	240	30	35.8	N,N'-hexanediy-dl(carbamic acid (p-heptylphenyl) ester) (93%)	6.9 ppm	11.9	97.2	0.9
Example 45	240	30	30.6	N,N'-hexanediy-dl(carbamic acid (p-nonylphenyl) ester) (96%)	4.7 ppm	7.5	95.1	4.3
Example 46	260	30	16.9	N,N'-hexanediy-dl(carbamic acid (4-phenylphenyl) ester) (93%)	8.8 ppm	3.7	91.2	8.3
Example 47	230	25	18.9	N,N'-hexanediy-dl(carbamic acid (2-naphthyl) ester) (93%)	6.9 ppm	5.3	90.4	9.1
Example 48	230	40	18.6	3-(4-tert-amyphenoxy)carbonylamino-methyl)-3,5-trimethylcyclohexyl carbamic acid (4-tert-amyphenyl) ester (95%)	5.8 ppm	20.4	94.4	3.5
Example 49	240	20	23.4	3-((p-dodecylphenoxy)carbonylamino-methyl)-3,5-trimethylcyclohexyl carbamic acid (p-dodecylphenyl) ester (94%)	8.9 ppm	3.4	94.2	5.1

[Table 16]

Example	Step (F)				
	Apparatus drawing	Thin film distillation apparatus temp. (°C)	Thin film distillation apparatus pressure (kPa)	Recovered isocyanate (yield based on organic amine)	
Example 3	FIG. 17	220	1.3	Hexamethylene diisocyanate	(90%)
Example 43	FIG. 17	200	2.0	Hexamethylene diisocyanate	(84%)
Example 44	FIG. 17	200	2.0	Hexamethylene diisocyanate	(74%)
Example 45	FIG. 17	200	2.0	Hexamethylene diisocyanate	(92%)
Example 46	FIG. 17	220	2.0	Hexamethylene diisocyanate	(90%)
Example 47	FIG. 17	200	1.0	Hexamethylene diisocyanate	(89%)
Example 48	FIG. 18	210	1.3	Isophorone diisocyanate	(90%)
Example 49	FIG. 17	230	2.0	Isophorone diisocyanate	(89%)

[Examples 50 to 52]

[0608] The same method as Example 4 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 50 to 52 along with the results are shown in Table 17. In addition, the compounds and reaction conditions used in steps (B) and (D) of Examples 50 to 52 along with the results are shown in Table 18. The compounds and reaction conditions used in step (C) of Examples 50 to 52 along with the results are shown in Table 19. The reaction conditions of step (F) of Examples 50 to 52 are shown in Table 20. Furthermore, the description of "FIG. 18" in the "apparatus drawing" column in Table 20 indicates that an apparatus as shown in FIG. 18 was used for step (F).

[Table 17]

Example	Step (A)		Amount of urea used	Aromatic hydroxy compound (amount used)	Aniline supply rate	Ratio of aromatic hydroxy compound to no. of molecules of N-phenylurea	Concentration of N-phenylurea	Residual amount of NH ₃
	Temp. of stirring tank 103 (°C)	Amount of aniline used						
Example 4	80	1.12 kg	3.61 kg	4-tert-amyl phenol (43.5 kg)	50 g/min	11	4.5 wt%	3800 ppm
Example 50	150	1.14 kg	3.89 kg	2-naphthol (17.6 kg)	60 g/min	5.1	9.7 wt%	5300 ppm
Example 51	130	1.08 kg	2.79 kg	4-(1,1,3,3-tetramethylbutyl) phenol (23.9 kg)	45 g/min	5.1	7.6 wt%	6700 ppm
Example 52	90	1.21 kg	2.73 kg	p-heptyl phenol (19.9 kg)	40 g/min	4.1	9.7 wt%	9200 ppm

[Table 18]

Example	Step (B)			Step (D)				
	Temp. of packed column 105 (°C)	Pressure of packed column 105 (kPa)	Fed amount (kg)	N-substituted carbamic acid mono(O-aryl ester) (yield based on organic amine)	Ammonia concentration in reaction liquid	Amount recovered in storage tank 109 (kg)	Aromatic hydroxy compound content (%)	Urea content (%)
Example 4	200	8	8.95	N-phenyl carbamic acid (4-tert-amylphenyl) ester (93%)	5.6 ppm	14.7	86.7	13.0
Example 50	210	15	21.1	N-phenyl carbamic acid (2-naphthyl) ester (88%)	8.6 ppm	7.9	70.1	28.8
Example 51	230	20	25.3	N-phenyl carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester (84%)	6.9 ppm	8.6	84.5	15.2
Example 52	220	25	21.2	N-phenyl carbamic acid (p-heptylphenyl) ester (86%)	7.7 ppm	7.0	84.3	15.1

[Table 19]

Example	Distillation of aromatic hydroxy compound		Step (C)						Distillation of solvent, unreacted substances, etc.		Addition of aromatic hydroxy compound
	Temp. of stirring tank 408 (°C)	Pressure in stirring tank 408 (kPa)	Methylal (kg)	Nitrobenzole (kg)	Sulfuric acid (kg)	Reaction temp. (°C)	Reaction time (hr)	Temp. or stirring tank 408 (°C)	Pressure in stirring tank 408 (kPa)		
Example 4	160	2	1.14	4.7	5.6	100	10	100	1	4-tert-amyl phenol	(5.1 kg)
Example 50	150	1	3.12	7.36	2.23	100	10	100	1	1-naphthol	(3.8 kg)
Example 51	150	1	4.05	10.8	2.46	110	8	100	1	4-(1,1,3,3-tetramethylbutyl) phenol	(4.2 kg)
Example 52	150	1	2.63	8.98	2.39	100	15	100	1	p-heptyl phenol	(3.8 kg)

[Table 20]

Example	Step (F)			
	Apparatus drawing	Temp. of thin film distillation apparatus 1002 (°C)	Pressure of thin film distillation apparatus 1002 (kPa)	Yield of MDI based on aniline
Example 4	FIG. 18	260	1.5	55%
Example 50	FIG. 18	250	1.0	45%
Example 51	FIG. 18	240	0.8	51%
Example 52	FIG. 18	230	0.1	44%

[Examples 53 to 67]

[0609] The same method as Example 5 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 53 to 67 along with the results are shown in Tables 21 and 22. In addition, the compounds and reaction conditions used in steps (R) and (D) of Examples 53 to 67 along with the results are shown in Tables 23 and 24. The compounds and reaction conditions used in steps (P) and (F) of Examples 53 to 67 along with the results are shown in Tables 25 and 26. Although "FIG. 17" and "FIG. 18" are indicated in the "apparatus drawing" column for step (F) in Tables 25 and 26, "FIG. 17" indicates that the same method as step (F) of Example 1 was carried out using an apparatus as shown in FIG. 17. On the other hand, "FIG. 18" indicates that the same method as step (F) of Example 4 was carried out using an apparatus as shown in FIG. 18. In addition, the compounds and reaction conditions used in step (E) of Examples 53 to 67 along with the results are shown in Table 27.

[Table 21]

Example	Step (A)										Ratio of alcohol to no. of ureido groups	
	Reaction temp. (°C)	Organic amine (amount used)	Amount of urea used	Alcohol used	Alcohol (amount)	Organic amine supply rate	Compound having ureido groups	Conc. of compound having ureido groups	Residual amount of NH ₃	Aromatic hydroxy compound added after reaction (amount added)		
Example 5	120	IPDA (0.87 kg)	1.47 kg	1-octanol	(14.6 kg)	10 g/min	3-(ureidomethyl)-3,3,5-trimethylcyclohexylurea	7.8 wt%	7300 ppm	p-dodecyl phenol	(13.4 kg)	11.3
Example 53	100	HDA (1.11 kg)	2.29 kg	2-phenyl ethanol	(23.3 kg)	20 g/min	1,6-hexamethylene diurea	7.1 wt%	8800 ppm	4-(1,1,3,3-tetramethylbutyl) phenol	(19.7 kg)	10.3
Example 54	120	HDA (1.32 kg)	2.73 kg	Diethylene glycol monobutyl ether	(55.3 kg)	38 g/min	1,6-hexamethylene diurea	3.8 wt%	3600 ppm	2,4-di-tert-amyl phenol	(18.7 kg)	15.5

5
10
15
20
25
30
35
40
45
50
55

Example 55	120	HDA	(1.28 kg)	2.65 kg	Isodecyl alcohol	(29.6 kg)	20 g/min	1,6-hexamethylene diurea	6.5 wt%	3500 ppm	2-naphthol	(15.9 kg)	8.8
Example 56	120	HDA	(0.53 kg)	1.15 kg	4-phenyl-1-butanol	(54.8 kg)	35 g/min	1,6-hexamethylene diurea	1.1 wt%	4200 ppm	p-dodecyl phenol	(29.6 kg)	58
Example 57	110	IPDA	(1.13 kg)	1.87 kg	1-hexanol	(16.9 kg)	30 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	8.5 wt%	3900 ppm	2-phenyl phenol	(11.3 kg)	12.8
Example 58	130	IPDA	(1.29 kg)	1.73 kg	Isodecyl alcohol	(41.9 kg)	44 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	4.2 wt%	3000 ppm	2-naphthol	(7.6 kg)	18
Example 59	120	IPDA	(1.68 kg)	2.67 kg	1-nonanol	(25.6 kg)	30 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	8.3 wt%	2800 ppm	4-nonyl phenol	(26.1 kg)	9.3

[Table 22]

Example	Step (A)										Ratio of alcohol to no. of ureido groups
	Reaction temp. (°C)	Organic amine (amount used)	Amount of urea used	Alcohol (amount used)	Organic amine supply rate	Compound having ureido groups	Conc. of compound having ureido groups	Residual amount of NH_3	Aromatic hydroxy compound added after reaction (amount added)		
Example 60	120	IPDA (1.71 kg)	2.53 kg	Ethylene glycol monobutyl ether (38.3 kg)	38 g/min	3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea	5.9 wt%	1900 ppm	p-dodecyl phenol (34.3 kg)	11.3	
Example 61	70	TDA (1.33 kg)	3.29 kg	2-ethyl-1-hexanol (28.4 kg)	65 g/min	2,4-toluenediurea	6.5 wt%	3400 ppm	p-heptyl phenol (16.7 kg)	10.7	
Example 62	90	TDA (1.29 kg)	6.34 kg	Cyclohexanol (21.1 kg)	79 g/min	2,4-toluenediurea	7 wt%	7300 ppm	2-phenyl phenol (14.4 kg)	11.0	
Example 63	120	TDA (1.22 kg)	4.79 kg	3-methoxy-3-methyl-1-butanol (23.6 kg)	60 g/min	2,4-toluenediurea	4.5 wt%	3500 ppm	p-heptyl phenol (19.2 kg)	11.0	
Example 64	120	TDA (1.28 kg)	3.78 kg	2-phenyl ethanol (25.6 kg)	65 g/min	2,4-toluenediurea	6.6 wt%	4200 ppm	p-dodecylphenol (33 kg)	11.0	
Example 65	80	MDA (1.08 kg)	3.23 kg	4-phenyl-1-butanol (24.5 kg)	86 g/min	4,4'-methanediyldiphenyl diurea	5.1 wt%	8400 ppm	4-phenyl phenol (9.3 kg)	15.6	
Example 66	70	MDA (1.11 kg)	2.69 kg	Ethylene glycol mono-2-ethylhexyl ether (29.1 kg)	65 g/min	4,4'-methanediyldiphenyl diurea	4.4 wt%	6300 ppm	2,4-dicumyl phenol (14.8 kg)	16.7	
Example 67	120	H-MDA (1.42 kg)	1.99 kg	Ethylene glycol monobutyl ether (15.9 kg)	44 g/min	4,4'-methanediyldicyclohexyl diurea	9.9 wt%	4400 ppm	2,6-dimethoxy phenol (10.4 kg)	10.6	

[Table 23]

Example	Step (R)				Step (D)			
	Temp. of distillation column 105 (°C)	Distillation column 105 pressure (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Ammonia concentration in reaction liquid	Amt. recovered in storage tank 109 (kg)	Alcohol content (%)	Urea content (%)
Example 5	260	26	15.1	3-(1-octyloxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-octyl) ester (95%)	5.8 ppm	4.4	89.9	9.8
Example 53	240	13	45.2	N,N'-hexanediyldi(carbamic acid (2-phenylethyl) ester) (92%)	9.5 ppm	13.8	90.3	8.4
Example 54	240	15	75.2	N,N'-hexanediyldi(carbamic acid (2-(2-(butyloxy)ethyloxy)ethyl) ester) (93%)	8.5 ppm	29.1	94.4	4.6
Example 55	240	15	47.2	N,N'-hexanediyldi(carbamic acid isodecyloxy ester) (83%)	11.8 ppm	14.7	89.4	8.9
Example 56	240	13	66.8	N,N'-hexanediyldi(carbamic acid (4-phenylbutyloxy) ester) (81%)	4.2 ppm	15.1	94.1	4.0
Example 57	220	7	28.5	3-((4-phenylbutyloxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylbutyl) ester (92%)	7.7 ppm	9.1	91.4	7.6
Example 58	210	8	51.1	3-(isodecyloxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid isodecyl ester (89%)	7.4 ppm	21.5	95.4	3.4
Example 59	210	.10	53.2	3-(nonyloxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid nonyl ester (80%)	92 ppm	12.0	85.8	12.1

[Table 24]

Example	Step (R)			Step (D)				
	Temp. of distillation column 105 (°C)	Distillation column 105 pressure (kPa)	Fed amount (kg)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Ammonia concentration in reaction liquid	Amt. recovered in storage tank 109 (kg)	Alcohol content (%)	Urea content (%)
Example 60	220	13	75.6	3-((2-butyloxy-ethyloxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (2-butyloxy-ethyl) ester (72%)	108 ppm	16.8	90.5	7.9
Example 61	210	13	45.4	Toluene-2,4-di(carbamic acid (2-ethylhexyl) ester) (84%)	5.3 ppm	16.2	86.5	11.7
Example 62	220	13	41.2	Toluene-2,4-di(carbamic acid cyclohexyl ester) (82%)	6.1 ppm	16.6	65.8	30.2
Example 63	210	26	46.8	Toluene-2,4-di(carbamic acid (3-methoxy-3-methylbutyl) ester) (69%)	920 ppm	11.7	64.9	28.5
Example 64	220	26	61.5	Toluene-2,4-di(carbamic acid (p-dodecylphenyl) ester) (62%)	1010 ppm	19.1	76.5	20.4
Example 65	220	13	33.9	N,N'-(4,4'-methanediyldiphenyl)-di(carbamic acid hexyl ester) (83%)	3.9 ppm	14.4	76.4	20.1
Example 66	210	13	45.4	N,N'-(4,4'-methanediyldiphenyl)-di(carbamic acid (2-(2-ethylhexyloxy)ethyl) ester) (81%)	4.5 ppm	16.5	85.5	12.1
Example 67	210	8	27.2	N,N'-(4,4'-methanediyldicyclohexyl)-di(carbamic acid (2-butyloxy)ethyl ester) (88%)	7.2 ppm	9.2	86.0	12.2

[Table 25]

Example	Step (P)				Step (F)				Recovered isocyanate (yield based on organic amine)
	Catalyst (conc. based on raw material liquid)	Distillation column 502 temp. (°C)	Distillation column 502 press. (kPa)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Apparatus drawing	Thin film distillation apparatus temp. (°C)	Thin film distillation apparatus press. (kPa)	Recovered isocyanate (yield based on organic amine)	
Example 5	Dibutyl tin dilaurate 0.5 wt%	260	26	3-((p-dodecylphenoxy)carbonyl amino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-dodecylphenyl) ester (89%)	FIG. 17	220	1.3	Hexamethylene diisocyanate (83%)	
Example 53	Dibutyl tin dilaurate 0.5 wt%	220	20	N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester) (88%)	FIG. 17	220	1.3	Hexamethylene diisocyanate (83%)	
Example 54	Lead octoate 0.1 wt%	240	15	N,N'-hexanediyldi(carbamic acid (2,4-di-tert-amylphenyl) ester) (89%)	FIG. 17	230	2.0	Hexamethylene diisocyanate (83%)	
Example 55	Dibutyl tin dilaurate 0.8 wt%	250	25	N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) (81%)	FIG. 17	230	1.5	Hexamethylene diisocyanate (75%)	
Example 56	Dibutyl tin dilaurate 0.8 wt%	240	25	N,N'-hexanediyldi(carbamic acid (p-dodecylphenyl) ester) (79%)	FIG. 17	230	1.3	Hexamethylene diisocyanate (74%)	
Example 57	Zinc acetate 1.0 wt%	250	40	3-((2-phenylphenoxy)carbonyl emino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (2-phenylphenyl) ester (88%)	FIG. 17	230	1.0	Isophorone diisocyanate (82%)	

(continued)

Example	Step (P)			Step (F)			Recovered isocyanate (yield based on organic amine)	
	Catalyst (conc. based on raw material liquid)	Distillation column 502 temp. (°C)	Distillation column 502 press. (kPa)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Apparatus drawing	Thin film distillation apparatus temp. (°C)		Thin film distillation apparatus press. (kPa)
Example 58	Dibutyl tin dilaurate 1.4 wt%	230	20	3-((p-dodecylphenoxy)carbonyl amino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (2-naphthyl) ester (86%)	FIG. 18	240	1.0	Isophorone diisocyanate (81 %)
Example 59	Dibutyl tin dilaurate 0.8 wt%	230	20	3-((4-nonylphenoxy)carbonyl amino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-nonylphenyl) ester (78%)	FIG. 17	240	1.2	Isophorone diisocyanate (73%)

[Table 26]

Example	Step (P)			Step (F)				Recovered isocyanate (yield based on organic amine)
	Catalyst (conc. based on raw material liquid)	Distillation column 502 temp. (°C)	Distillation column 502 press. (kPa)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Apparatus drawing	Thin film distillation apparatus temp. (°C)	Thin film distillation apparatus press. (kPa)	
Example 60	Dibutyl tin dilaurate 1.0 wt%	230	20	3-(2-naphthyl)-carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (2-naphthyl) ester (69%)	FIG. 17	240	1.0	Isophorone diisocyanate (65%)
Example 61	Dibutyl tin dilaurate 1.3 wt%	220	15	Toluene-2,4-di(carbamic acid (p-heptylphenyl) ester) (79%)	FIG. 17	210	0.8	2,4-tolylene diisocyanate (75%)
Example 62	Lead octoate 1.0 wt%	220	25	Toluene-2,4-di(carbamic acid (2-phenylphenyl) ester) (77%)	FIG. 17	200	0.5	2,4-tolylene diisocyanate (73%)
Example 63	Dibutyl tin dilaurate 1.0 wt%	210	10	Toluene-2,4-di(carbamic acid (p-heptylphenyl) ester) (66%)	FIG. 17	200	0.8	2,4-tolylene diisocyanate (62%)
Example 64	Dibutyl tin dilaurate 1.2 wt%	210	10	Toluene-2,4-di(carbamic acid (p-dodecylphenyl) ester) (59%)	FIG. 17	200	0.8	2,4-tolylene diisocyanate (54%)
Example 65	Zinc acetate 0.9 wt%	240	10	N,N'-(4,4'-methanediyl-diphenyl)-di(carbamic acid (4-phenylphenyl) ester) (78%)	FIG. 18	270	1.0	4,4'-diphenylmethane diisocyanate (71%)
Example 66	Dibutyl tin dilaurate 0.9 wt%	240	6	N,N'-(4,4'-methanediyl-diphenyl)-di(carbamic acid (2,4-dicumylphenyl) ester) (75%)	FIG. 17	280	1.5	4,4'-diphenylmethane diisocyanate (69%)

(continued)

Example	Step (P)			Step (F)			Recovered isocyanate (yield based on organic amine)	
	Catalyst (conc. based on raw material liquid)	Distillation column 502 temp. (°C)	Distillation column 502 press. (kPa)	N-substituted carbamic acid-O-aryl ester (yield based on organic amine)	Apparatus drawing	Thin film distillation apparatus temp. (°C)		Thin film distillation apparatus press. (kPa)
Example 67	Zinc acetate 1.0 wt%	200	20	N,N'-(4,4'-methanediyl-dicyclohexyl)-di(carbamic acid (2,6-dimethoxyphenyl) ester) (80%)	FIG. 18	250	0.5	4,4'-dicyclohexylmethane diisocyanate (74%)

[Table 27]

Example	Step (E)						
	Ammonia content of mixture recovered in storage tank 109	Organic amine (amount used)		Amount of urea added	Solvent added (amount added)		Yield of N-substituted carbamic acid-O-aryl ester based on organic amine
Example 5	1300	IPDA	(0.87 kg)	0.70 kg	1-octanol	(7.57 kg)	95%
Example 53	1320	HDA	(1.21 kg)	1.40 kg	2-phenyl ethanol	(13.0 kg)	83%
Example 54	1400	HDA	(1.32 kg)	1.46 kg	Diethylene glycol monobutyl ether	(27.8 kg)	83%
Example 57	1200	IPDA	(1.22 kg)	0.98 kg	1-hexanol	(10.0 kg)	82%
Example 58	1100	IPDA	(1.29 kg)	0.94 kg	Isodecyl alcohol	(21.3 kg)	81%
Example 61	520	TDA	(1.18 kg)	1.13 kg	2-ethyl-1-hexanol	(11.1 kg)	75%
Example 62	1320	TDA	(1.52 kg)	2.72 kg	Cyclohexanol	(14.1 kg)	73%
Example 65	950	MDA	(1.28 kg)	1.90 kg	4-phenyl-1-butanol	(18.1 kg)	71%
Example 66	710	MDA	(1.10 kg)	0.79 kg	Ethylene glycol mono-2-ethyl hexyl ether	(15.0 kg)	69%
Example 67	550	H-MDA	(1.42 kg)	0.91 kg	Ethylene glycol monobutyl ether	(8.01 kg)	74%

[Examples 68 to 70]

[0610] The same method as Example 6 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 68 to 70 along with the results are shown in Table 28. In addition, the compounds and reaction conditions used in steps (R) and (D) of Examples 68 to 70 along with the results are shown in Table 29. The compounds and reaction conditions used in step (P) of Examples 68 to 70 along with the results are shown in Table 30. The compounds and reaction conditions used in step (C) of Examples 68 to 70 along with the results are shown in Table 31. The compounds and reaction conditions used in step (F) of Examples 68 to 70 along with the results are shown in Table 32. Although "FIG. 17" and "FIG. 18" are indicated in the "apparatus drawing" column for step (F) in Table 32, "FIG. 17" indicates that the same method as step (F) of Example 1 was carried out using an apparatus as shown in FIG. 17. On the other hand, "FIG. 18" indicates that the same method as step (F) of Example 4 was carried out using an apparatus as shown in FIG. 18.

[Table 28]

Example	Step (A)		Amount of urea used	Amount of aniline used	Solvent (amount used)	Organic amine supply rate	Concentration of compound having ureido groups	Residual amount of NH ₃	Aromatic hydroxy compound added after reaction (amount added)		Ratio of alcohol to no. of ureido groups
	Stirring tank temp. (°C)	Amount of urea used							Amount of urea used	Amount of urea used	
Example 6	90	(1.08 kg)	3.34 kg	1-nonanol	(33.5 kg)	12 g/min	5.6 wt%	7900 ppm	2-phenyl phenol	(25.9 kg)	10.1
Example 68	150	(1.22 kg)	6.53 kg	2-phenyl ethanol	(28.8 kg)	30 g/min	4.7 wt%	5300 ppm	4-(1,1,3,3-tetramethylbutyl) phenol	(27.0 kg)	9.6
Example 69	130	(1.32 kg)	8.51 kg	Ethylene glycol monobutyl ether	(41.9 kg)	35 g/min	3.6 wt%	6700 ppm	p-heptyl phenol	(16.4 kg)	13.3
Example 70	90	(0.98 kg)	5.69 kg	3-methoxy-3-methyl-1-butanol	(31.1 kg)	25 g/min	3.6 wt%	9200 ppm	4-ethoxy phenol	(14.5 kg)	13.4

[Table 29]

Example	Steps (R) and (D)			
	Packed column 105 temp. (°C)	Packed column 105 pressure (kPa)	N-substituted carbamic acid mono(-O-alkyl ester) (yield based on organic amine)	
Example 6	210	50	N-phenyl-carbamic acid nonyl ester	(91%)
Example 68	220	50	N-phenyl-carbamic acid (2- phenylethylester)	(88%)
Example 69	172	100	N-phenyl-carbamic acid (2-(1- butyloxy)ethyl ester)	(88%)
Example 70	175	100	N-phenyl-carbamic acid ((3- methoxy-3-methylbutyl) ester)	(85%)

[Table 30]

Example	Step (P)				
	Catalyst (concentration based on raw material liquid)		Reaction temp. (°C)	Pressure (kPa)	N-substituted carbamic acid mono(-O-aryl ester) (yield based on organic amine)
Example 6	Dibutyl tin dilaurate	0.5 wt%	260	26	N-phenyl-carbamic acid (2- phenylphenylester) (89%)
Example 68	Dibutyl tin dilaurate	0.2 wt%	250	20	N-phenyl-carbamic acid (4-(1,1,3,3-tetramethylbutyl) phenylester) (83%)
Example 69	Lead octoate	0.2 wt%	240	10	N-phenyl-carbamic acid (p- heptylphenylester) (81%)
Example 70	Zinc acetate	0.2 wt%	220	60	N-phenyl-carbamic acid (4- ethoxyphenylester) (82%)

[Table 31]

Example	Distillation of aromatic hydroxy compound		Step (C)						Distillation of solvent, unreacted substances, etc.		Addition of aromatic hydroxy compound	
	Stirring tank 408 temp. (°C)	Stirring tank 408 press.(kPa)	Methylal (kg)	Nitrobenzole (kg)	Sulfuric acid (kg)	Reaction temp. (°C)	Reaction time (hr)	Stirring tank 408 temp. (°C)	Stirring tank 408 press.(kPa)	Aromatic hydroxy compound added (amount added)	(25.9 kg)	
Example 6	160	1	2.04	1.94	1.02	90	24	90	1	2-phenyl phenol	(25.9 kg)	
Example 68	150	1	0.76	2.11	0.39	100	10	100	1	4-(1,1,3,3-tetramethylbutyl) phenol	(3.5 kg)	
Example 69	150	1	0.64	2.14	0.62	110	8	100	1	p-heptyl phenol	(5.4 kg)	
Example 70	150	1	2.63	8.98	2.39	100	15	100	1	4-ethoxy phenol	(5.8 kg)	

[Table 32]

Example	Step (F)			
	Apparatus drawing	Thin film distillation apparatus 1002 temp. (°C)	Thin film distillation apparatus 1002 pressure (kPa)	Yield of MDI based on aniline
Example 6	FIG. 18	260	1.5	91%
Example 68	FIG. 18	250	1.0	43%
Example 69	FIG. 18	240	0.8	50%
Example 70	FIG. 18	230	0.1	47%

[Examples 71 to 73]

[0611] The same method as Example 7 was carried out while changing the compounds and reaction conditions used. The compounds and reaction conditions used in step (A) of Examples 71 to 73 along with the results are shown in Table 33. In addition, the compounds and reaction conditions used in steps (R) and (D) of Examples 71 to 73 along with the results are shown in Table 34. The compounds and reaction conditions used in step (C) of Examples 71 to 73 along with the results are shown in Table 35. The reaction conditions used in steps (P) and (F) of Examples 71 to 73 along with the results are shown in Table 36. Although "FIG. 18" is indicated in the "apparatus drawing" column for step (F) in Table 36, "FIG. 18" indicates that the same method as step (F) of Example 4 was carried out using an apparatus as shown in FIG. 18.

[Table 33]

Example	Step (A)										Ratio of alcohol to no. of ureido groups
	Distillation column 105 temp. (°C)	Amount of aniline used (kg)	Amount of urea used (kg)	Solvent (amount added)	Organic amine supply rate	Conc. of compound having ureido groups	Residual amount of NH ₃	Hydroxy compound added after reaction (amount added)	Hydroxy compound added after reaction (amount added)	Ratio of alcohol to no. of ureido groups	
Example 7	90	(1.13 kg)	3.50 kg	1-heptanol	18 g/min	7.4 wt%	8300 ppm	2,4-di-tert-amyl phenol	(24.4 kg)	9.0	
Example 71	100	(1.53 kg)	9.87 kg	1-heptanol	30 g/min	3.6 wt%	4200 ppm	Phenol	(4.6 kg)	13.4	
Example 72	120	(1.39 kg)	8.96 kg	Phenol	40 g/min	7.3 wt%	3800 ppm	4-phenyl-1-butanol	(22.4 kg)	5.4	
Example 73	90	(1.29 kg)	8.32 kg	Cyclohexanol	30 g/min	4.1 wt%	5500 ppm	2-isopropyl phenol	(7.6 kg)	13.4	

[Table 34]

Example	Steps (R) and (D)		
	Distillation column 105 temp. (°C)	N-substituted carbamic acid mono(-O-alkyl) ester (yield based on organic amine)	
Example 7	190	N-phenyl carbamic acid (1-heptyl) ester	(90%)
Example 71	240	N-phenyl carbamic acid (1-heptyl) ester	(85%)
Example 72	240	N-phenyl carbamic acid (4-phenylbutyl) ester	(76%)
Example 73	220	N-phenyl carbamic acid cyclohexyl ester	(84%)

15

20

25

30

35

40

45

50

55

[Table 35]

Example	Hydroxy compound distillation		Step (C)					Hydroxy compound distillation		Addition of aromatic hydroxy compound
	Stirring tank 408 temp (°C)	Stirring tank 408 pressure (kPa)	Methylal (kg)	Nitrobenzole (kg)	Sulfuric acid (kg)	Reaction temp. (°C)	Reaction time (hr)	Stirring tank 408 temp. (°C)	Stirring tank 408 pressure (kPa)	
Example 7	160	1	1.30	7.34	1.33	100	10	100	1	Added aromatic hydroxy compound (amount added) 2,4-di-tert- amyl phenol (24.2 kg)
Example 71	150	1	0.72	2.4	0.96	100	10	100	1	4-tert-amyl phenol (16.8 kg)
Example 72	150	1	1.13	3.76	1.5	110	8	100	1	2,4-di-tert- amyl phenol (26.2 kg)
Example 73	150	1	0.75	2.5	0.86	110	9	100	1	2,6-dimethoxy phenol (15.9 kg)

[Table 36]

Example	Step (P)				Step (F)			
	Catalyst (concentration based on raw material liquid)		Reaction temp. (°C)	Pressure (kPa)	Apparatus drawing	Thin film distillation apparatus 1002 temp. (°C)	Thin film distillation apparatus 1002 pressure (kPa)	Yield of MDI based on aniline
Example 7	Dibutyl tin dilaurate	0.5 wt%	250	30	FIG. 18	250	1.0	47%
Example 71	Dibutyl tin dilaurate	1.2 wt%	250	50	FIG. 18	250	1.0	46%
Example 72	Lead octoate	1.2 wt%	220	20	FIG. 18	230	0.8	40%
Example 73	Zinc acetate	1.0 wt%	230	15	FIG. 18	220	0.1	49%

[Example 74]

Step (74-1): Production of Compound Having Ureido Groups

[0612] The apparatus shown in FIG. 19 was used.

[0613] 2.54 kg of urea were transferred from a storage tank 1100 to a stirring tank 1103 with a line B3 closed. After melting the urea by heating the stirring tank 1103 to 150°C, 0.820 kg of hexamethylenediamine were supplied at the rate of about 10 g/min from a storage tank 1101 to the stirring tank 1103 via a line A1 while stirring the stirring tank 1103. Following completion of supplying hexamethylenediamine, stirring was continued for about 1 hour and about 8.5 kg of water were placed in the stirring tank 1103 from a storage tank 1102 to form a slurry-like solution. The slurry-like solution was fed to a pressurized filtration apparatus 1104 and the solid component was separated by filtration. When the recovered solid component was analyzed by ¹H-NMR, it was found to contain a compound having ureylene groups. About 50 kg of water at about 80°C was added to the solid component followed by stirring to obtain a dispersion, and the dispersion was filtered to obtain a filtrate. A solid component that precipitated following cooling of the filtrate was separated and recovered. The recovered solid component was heated to about 100°C and dried with a dryer containing a nitrogen atmosphere to obtain 125 g of a solid. When the solid was analyzed by ¹H-NMR, it was found to be 1,1'-(hexane-1,6-diyl) diurea. The above-mentioned procedure was then repeated 10 times to obtain about 1270 g of 1,1'-(hexane-1,6-diyl) diurea.

Step (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

[0614] The apparatus shown in FIG. 20 was used.

[0615] The 1,1'-(hexane-1,6-diyl) diurea obtained in step (74-1) and 25.9 kg of 4-(1,1,3,3-tetramethylbutyl) phenol were mixed to obtain a raw material solution that was placed in a storage tank 1201.

[0616] A packed column 1202 packed with a packing material (Helipack No. 3) was heated to 240°C and the pressure inside the column was set to 26 kPa. The above-mentioned raw material solution was fed at the rate of about 3.5 g/min from a line C1 provided in the packed column 1202. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 23.2 kg. The reaction liquid was recovered in a storage tank 1205 through a line C4 provided in the bottom of the packed column 1202. A gaseous phase component was extracted from a line C2 provided in the top of the packed column 1202 and condensed with a condenser 1203, and the resulting liquid phase component was circulated to the packed column 1202 via a gas-liquid separator 1204. On the other hand, ammonia was recovered in the form of a gaseous component from the gas-liquid separator 1204. When the reaction liquid recovered in the storage tank 1205 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-

tetramethylbutyl) phenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl) phenyl) ester) based on hexamethylenediamine was about 86%.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

5 [0617] The apparatus shown in FIG. 17 was used.

10 [0618] A thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing hexamethylene diisocyanate and p-heptyl phenol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous component was condensed in the condenser 610 via a line 69 and recovered in a storage tank 612 through a gas-liquid separator 611.

15 [0619] When the condensed liquid was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylene diamine was about 80%.

[Example 75]

25 Step (75-1): Production of Compound Having Ureido Groups

30 [0620] The same method as step (74-1) of Example 74 was carried out with the exception of using 3.41 kg of urea and 1.11 kg of hexamethylenediamine. The same procedure was then repeated 10 times and the resulting 1,1'-(hexane-1,6-diyl) diurea was mixed with about 25.6 kg of 4-ethoxy phenol and obtain a homogeneous solution. When the solution was analyzed by ¹H-NMR, it was found to be a solution containing 6.3% by weight of 1,1'-(hexane-1,6-diyl) diurea and 7.7% by weight of urea.

Step (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

35 [0621] The apparatus shown in FIG. 20 was used.

The solution obtained in step (75-1) was transferred to the storage tank 401.

40 [0622] The packed column 1202 was heated to 240°C and the pressure inside the column was set to 26 kPa. The solution obtained in step (75-1) was fed at the rate of about 3.7 g/min from the line 41 provided in the packed column 1202. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 24.3 kg. The reaction liquid was recovered in the storage tank 1205 through the line 44 provided in the bottom of the packed column 1202. A gaseous phase component was extracted from the line C2 provided in the top of the packed column 1202 and condensed with the condenser 1203 maintained at about 85°C, and the resulting liquid phase component was recovered in a storage tank 1207 via the gas-liquid separator 1204. On the other hand, ammonia was recovered in the form of a gaseous component from the gas-liquid separator 1204. When the reaction liquid recovered in the storage tank 1205 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid (4-ethoxyphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (4-ethoxyphenyl) ester) based on hexamethylenediamine was about 93%. The amount of solution recovered in the storage tank 1207 was 16.1 kg, and when the solution was analyzed by ¹H-NMR, it was found to contain 11.6% by weight of urea.

50 [Example 76]

Step (76-1): Production of Compound Having Ureido Groups

55 [0623] The same method as step (74-1) of Example 74 was carried out with the exception of using 3.33 kg of urea and using 1.18 kg of 3-aminomethyl-3,5,5-trimethylcyclohexylamine instead of hexamethylenediamine. The same procedure was then repeated 10 times to obtain 1.53 kg of a solid. When the solid was analyzed by ¹H-NMR, it was found to be 3-(ureidomethyl)-3,5,5-trimethylcyclohexyl urea.

Step (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

[0624] The solid obtained in step (76-1) was mixed with 21.3 kg of p-heptyl phenol to obtain a raw material solution was placed in the storage tank 401.

[0625] The same procedure as Example (56-2) was carried out with the exception of feeding the raw material solution at the rate of about 2.8 g/min. The amount of reaction liquid fed after the reaction had reached a steady state was about 19.7 kg. When the reaction liquid recovered in the storage tank 405 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain 3-((p-heptylphenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-heptylphenyl) ester, and the yield of 3-((p-heptylphenoxy)carbonylamino-methyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-heptylphenyl) ester based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 83%.

[Example 77]

Step (77-1): Production of Compound Having Ureido Groups

[0626] The apparatus shown in FIG. 19 was used.

[0627] 3.01 kg of urea from the storage tank 1100 and 5.21 kg of water from the storage tank 1102 were transferred to the stirring tank 1103 with the line B3 closed. The stirring tank 1103 was heated to 90°C to obtain a homogeneous solution, and 0.970 kg of hexamethylenediamine were supplied at the rate of about 8 g/min from the storage tank 1101 to the stirring tank 1103 via the line B1 while stirring the stirring tank 1103. Following completion of supplying hexamethylenediamine, stirring was continued for about 1 hour. A slurry-like solution was obtained. The slurry-like solution was fed to the pressurized filtration apparatus 1104 and the solid component was separated by filtration. The recovered filtrate was cooled to about 20°C and a solid component that precipitated was separated by filtration and recovered. The solid component was heated to about 100°C and dried with a dryer containing a nitrogen atmosphere to obtain 0.32 kg of a solid. When the solid was analyzed by ¹H-NMR, it was found to be 1,1'-(hexane-1,6-diyl) diurea. The above-mentioned procedure was then repeated 5 times to obtain about 1.48 kg of 1,1'-(hexane-1,6-diyl) diurea.

Step (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

[0628] The apparatus shown in FIG. 20 was used.

[0629] The 1,1'-(hexane-1,6-diyl) diurea obtained in step (77-1) and 15.6 kg of 4-cumyl phenol were mixed to obtain a raw material solution that was placed in the storage tank 1201.

[0630] The packed column 1202 was heated to 240°C and the pressure inside the column was set to 26 kPa. The above-mentioned raw material solution was fed at the rate of about 3.5 g/min from the line C1 provided in the packed column 1202. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 15.6 kg. The reaction liquid was recovered in the storage tank 406 through the line C4 provided in the bottom of the packed column 1202. A gaseous phase component was extracted from the line C2 provided in the top of the packed column 402 and condensed with a condenser 1203, and the resulting liquid phase component was circulated to the packed column 1202 via a gas-liquid separator 1204. On the other hand, ammonia was recovered in the form of a gaseous component from the gas-liquid separator 1204. When the reaction liquid recovered in the storage tank 1205 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid (4-cumylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (4-cumylphenyl) ester) based on hexamethylenediamine was about 83%.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0631] The apparatus shown in FIG. 17 was used.

[0632] A thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing hexamethylene diisocyanate and 4-cumylphenol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation.

[0633] When the condensed liquid was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylene diamine was about 80%.

[Example 78]

Step (A): Production of Compound Having Ureido Groups

[0634] The same method as step (A) of Example 1 was carried out with the exception of using 34.3 kg of p-heptyl phenol, 2.92 kg of urea and 1.38 kg of hexamethylenediamine. Following completion of the reaction, the reaction liquid was sampled, and as a result of analyzing the reaction liquid by liquid chromatography, it was found to contain 6.1 % by weight of a compound having ureido groups in the form of 1,1'-(hexane-1,6-diyl) diurea. In addition, the ammonia concentration in the solution was 5500 ppm. Unreacted amino group terminals were not detected. The ratio of the number of molecules of p-heptyl phenol to the number of ureido groups was 7.7.

[0635] The line 13 was then opened and the reaction liquid was transferred to the storage tank 104 via the line 13.

Step (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

[0636] The apparatus shown in FIG. 13 was used.

[0637] The packed column 105 packed with a packing material (Helipack No. 3) was heated to 240°C and the pressure inside the column was set to 26 kPa. The reaction liquid obtained in step (A) was fed at the rate of about 1.5 g/min from the line 14 provided in the packed column 105. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 36.3 kg. The reaction liquid was recovered in the storage tank 110 through the line 16 provided in the bottom of the packed column 105. A gaseous phase component was condensed in the condenser 106 maintained at about 85°C from the line 15 provided in the top of the packed column 105, and the resulting liquid phase component was circulated to the packed column 105 via the gas-liquid separator 108. The amount of reaction liquid recovered in the storage tank 110 was 35.9 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) and urea. The yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 89%.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0638] The apparatus shown in FIG. 17 was used.

[0639] A thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing hexamethylene diisocyanate and p-heptyl phenol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in a condenser 610 via a line 69 and recovered in a storage tank 612 through a gas-liquid separator 611.

[0640] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on the organic amine (hexamethylene diamine) was about 79%.

[Example 79]

Steps (A) and (B): Production of N-substituted Carbamic Acid-O-Aryl Ester

[0641] The apparatus shown in FIG. 21 was used.

[0642] 1.31 kg of hexamethylenediamine and 3.39 kg of urea were mixed into 3.5 kg of water to obtain a homogeneous aqueous solution. The aqueous solution was placed in a storage tank 1300. A portion of a distillation column 1302 packed with a packing material (Helipack No. 3) above a line D1 was heated to 200°C, while a portion of the distillation column 1302 below the line D1 was heated to 240°C, and the aqueous solution in the storage tank 1300 was fed at the

rate of about 1.6 g/min from a line D0 while feeding nitrogen gas at the rate of 0.1 N L/min from a line D6. In addition, 4-(1,1,3,3-tetramethylbutyl) phenol was fed from a line 1301 at the rate of about 16.1 g/min. When reaction liquid was sampled from a sampling line D5 provided above the line D1 and analyzed by ¹H-NMR and liquid chromatography, the reaction liquid was found to contain 1,1'-(hexane-1,6-diyl) diurea. In addition, in an analysis of the reaction liquid, compounds having amino groups (such as hexamethylenediamine or 6-ureido-hexamethylenamine) were not detected.

[0643] Reaction liquid was recovered in a storage tank 1305 from a line D4 provided in the bottom of the distillation column 1302. When the reaction liquid recovered in the storage tank 1305 was analyzed by ¹H-NMR and liquid chromatography, the reaction liquid was found to be a solution containing N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester). The yield of N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenyl) ester) based on hexamethylenediamine was 78%.

[Example 80]

Steps (A) and (R): Production of N-substituted Carbamic Acid-O-Alkyl Ester

[0644] The apparatus shown in FIG. 21 was used.

[0645] 1.25 kg of hexamethylenediamine and 3.23 kg of urea were mixed into 3.3 kg of water to obtain a homogeneous aqueous solution. The aqueous solution was placed in the storage tank 1300. A portion of the distillation column 1302 packed with a packing material (Helipack No. 3) above the line D1 was heated to 200°C, while a portion of the distillation column 1302 below the line D1 was heated to 240°C, and the aqueous solution in the storage tank 1300 was fed at the rate of about 1.55 g/min from the line D0 while feeding nitrogen gas at the rate of 0.1 N L/min from the line D6. In addition, 2-phenyl ethanol was fed from the line 1301 at the rate of about 9.13 g/min. When reaction liquid was sampled from the sampling line D5 provided above the line D1 and analyzed by ¹H-NMR and liquid chromatography, the reaction liquid was found to contain 1,1'-(hexane-1,6-diyl) diurea. In addition, in an analysis of the reaction liquid, compounds having amino groups (such as hexamethylenediamine or 6-ureido-hexamethylenamine) were not detected.

[0646] Reaction liquid was recovered in the storage tank 1305 from the line D4 provided in the bottom of the distillation column 1302. When the reaction liquid recovered in the storage tank 1305 was analyzed by ¹H-NMR and liquid chromatography, the reaction liquid was found to be a solution containing N,N'-hexanediyldi(carbamic acid (2-phenylethyl) ester). The yield of N,N'-hexanediyldi(carbamic acid (2-phenylethyl) ester) based on hexamethylenediamine was 75%.

Step (P): Production of N-substituted Carbamic Acid-O-Aryl Ester by Transesterification Reaction

[0647] The apparatus shown in FIG. 16 was used.

[0648] 20.7 kg of p-heptyl phenol were added to the reaction liquid obtained in the above step to obtain a homogeneous solution that was placed in the storage tank 501.

[0649] The packed column 502 packed with a packing material (Helipack No. 3) was heated to 260°C and the pressure inside the column was set to 26 kPa. The mixture in the storage tank 501 was fed at the rate of about 2.3 g/min from the line 51 provided in the packed column 502. A reaction liquid was recovered in the storage tank 505 via the line 54 provided in the bottom of the packed column 502. A gaseous phase component was introduced into the condenser 503 from the line 52 provided in the top of the packed column 502, and the resulting liquid phase component was recovered in the storage tank 504 through the gas-liquid separator 507. When the reaction liquid recovered in the storage tank 505 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to be a solution containing N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was 71 %.

[Example 81]

Step (G): Urea Regeneration Step

[0650] Example 1 was repeated and ammonia obtained from lines 19 and 17 in steps (A) and (B) was recovered in the form of liquid ammonia using a liquefaction apparatus.

[0651] Ammonia pressurized to 17.6 MPa, heated to 150°C and supplied at the rate of 3.44 kg/hr, carbon dioxide pressurized to 17.6 MPa and supplied at the rate of 2.20 kg/hr and a condensate to be described later were supplied to a urea synthesis tube 1401 and reacted at 190°C.

[0652] The urea synthesis liquid that appeared from the urea synthesis tube was supplied to a high-pressure separator 1402, while carbon dioxide simultaneously supplied from a line 21 was contacted with the urea synthesis liquid at the rate of 2.20 kg/hr to decompose non-converted products at 195°C followed by separating a gaseous mixture containing ammonia at 4.26 kg/hr, carbon dioxide at 2.43 kg/hr and water at 0.50 kg/hr from a urea aqueous solution containing

urea at 6.0 kg/hr, ammonia at 2.88 kg/hr, carbon dioxide at 2.34 kg/hr and water at 3.01 kg/hr. The urea aqueous solution was depressurized to 1.76 MPa and then 0.20 MPa to separate residual non-converted products, and then subjected to final treatment to obtain urea at the rate of 6.0 kg/hr. The separated non-converted products were absorbed with water to obtain an ammonia carbamate aqueous solution at 1.76 MPa containing ammonia at 2.84 kg/hr, carbon dioxide at 2.34 kg/hr and water at 1.21 kg/hr.

[0653] The gaseous mixture was then supplied to a condenser 1403 to aspirate and pressurize the ammonia carbamate aqueous solution pressurized to 17.6 MPa. The resulting condensate was recirculated to the urea synthesis tube 1401.

Step (A): Production of Compound Having Ureido Groups Using Urea Produced in Step (G)

[0654] The same method as step (A) of Example 1 was carried out with the exception of using 40.0 kg of p-heptyl phenol, 3.33 kg of the urea produced in step (G) above and 1.61 kg of hexamethylenediamine. The reaction liquid contained 6.3% by weight of 1,1'-(hexane-1,6-diyl) diurea. In addition, the concentration of ammonia in the solution was 6300 ppm. Unreacted amino group terminals were not detected.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

[0655] The same method as step (B) of Example 1 was carried out with the exception of using the solution obtained in step (A) above followed by recovery of the reaction liquid in the storage tank 110. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediy-di(carbamic acid(p-heptylphenyl) ester), and the yield of N,N'-hexanediy-di(carbamic acid(p-heptylphenyl) ester) based on hexamethylenediamine was about 97%.

[Example 82]

Step (G): Urea Regeneration Step

[0656] The apparatus shown in FIG. 22 was used.

[0657] Example 5 was repeated and ammonia obtained from lines 19 and 17 in steps (A) and (R) was recovered in the form of liquid ammonia using a liquefaction apparatus.

[0658] Ammonia pressurized to 17.6 MPa, heated to 150°C and supplied at the rate of 3.44 kg/hr, carbon dioxide pressurized to 17.6 MPa and supplied at the rate of 2.20 kg/hr and a condensate to be described later were supplied to the urea synthesis tube 1401 and reacted at 190°C.

[0659] The urea synthesis liquid that appeared from the urea synthesis tube was supplied to the high-pressure separator 1402, while carbon dioxide simultaneously supplied from a line 21 was contacted with the urea synthesis liquid at the rate of 2.20 kg/hr to decompose non-converted products at 195°C followed by separating a gaseous mixture containing ammonia at 4.26 kg/hr, carbon dioxide at 2.43 kg/hr and water at 0.50 kg/hr from a urea aqueous solution containing urea at 6.0 kg/hr, ammonia at 2.88 kg/hr, carbon dioxide at 2.34 kg/hr and water at 3.01 kg/hr. The urea aqueous solution was depressurized to 1.76 MPa and then 0.20 MPa to separate residual non-converted products, and then subjected to final treatment to obtain urea at the rate of 6.0 kg/hr. The separated non-converted products were absorbed with water to obtain an ammonia carbamate aqueous solution at 1.76 MPa containing ammonia at 2.84 kg/hr, carbon dioxide at 2.34 kg/hr and water at 1.21 kg/hr.

[0660] The gaseous mixture was then supplied to the condenser 1403 to aspirate and pressurize the ammonia carbamate aqueous solution pressurized to 17.6 MPa. The resulting condensate was recirculated to the urea synthesis tube 1401.

Step (A): Production of N-substituted Carbamic Acid Ester Using Urea Regenerated in Step (G)

Production of Compound having Ureido Groups

[0661] The same method as step (A) of Example 5 was carried out with the exception of using 14.6 kg of 1-octanol, 1.47 kg of the urea produced in step (G) above and 0.87 kg of 3-aminomethyl-3,5,5-trimethylcyclohexylamine. As a result of analyzing the resulting reaction liquid by liquid chromatography, it was found to contain about 7.8% by weight of 3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea. In addition, the ammonia concentration in the solution was 7300 ppm. 13.4 kg of an aromatic hydroxy compound in the form of p-dodecyl phenol were added from the storage tank 101 to obtain a homogeneous solution. Line 13 was then opened and the solution was transferred to the storage tank 104 via the line 13.

Steps (R) and (D): Production of N-substituted Carbamic Acid-O-Alkyl Ester and Recovery of Urea

5 **[0662]** The same method as steps (R) and (D) of Example 4 was carried out with the exception of using the reaction liquid obtained in step (A) that used the regenerated urea described above. The amount of reaction liquid recovered in the storage tank 110 was 8.80 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain 3-((1-octyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-octyl) ester, and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 95%.

10 Step (P): Transesterification Reaction

15 **[0663]** The same method as step (P) of Example 4 was carried out with the exception of using the reaction liquid obtained in steps (R) and (D) above. When the reaction liquid recovered in the storage tank 505 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to be a solution containing 3-((p-(dodecylphenoxy)carbonylaminomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (p-dodecylphenyl) ester), and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was 89%.

[Example 83]

20 Step (A): Production of Compound Having Ureido Groups

[0664] The same method as step (A) of Example 1 was carried out with the exception of using 1.33 kg of hexamethylenediamine, 3.09 kg of urea, 28.1 kg of 2-naphthol instead of p-heptyl phenol and heating the storage tank 103 to 120°C.

25 **[0665]** A reaction liquid was obtained that contained 7.2% by weight of 1,1'-(hexane-1,6-diyl) diurea and 6100 ppm of ammonia.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester

30 **[0666]** The same method as steps (B) and (D) of Example 1 was carried out with the exception of heating the packed column 105 to 240°C, setting the internal pressure to 15 kPa and using the reaction liquid obtained in step (A) above.

[0667] A reaction liquid was obtained that contained N,N'-hexanediy-di(carbamic acid (2-naphthyl) ester), and the yield of N,N'-hexanediy-di(carbamic acid (2-naphthyl) ester) based on hexamethylenediamine was about 97%. The concentration of ammonia in the reaction liquid was about 8 ppm.

35 Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0668] The apparatus shown in FIG. 17 was used.

40 **[0669]** The thin film distillation apparatus 602 was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.0 kPa. The reaction liquid obtained in step (B) above was placed in the storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via the line 60. A liquid component was extracted from the line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in the storage tank 603 (the liquid component recovered in the storage tank 603 was not supplied to the thin film distillation apparatus 602). About 15.2 kg of a solution were obtained in the storage tank 603. A gaseous component containing hexamethylene diisocyanate and 2-naphthol was extracted from the line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into the distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to the distillation column 609 from the line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in the condenser 610 via the line 69 and recovered in the storage tank 612 through the gas-liquid separator 611.

50 **[0670]** When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate.

Step (A-2): Reuse of N-substituted Carbamic Acid-O-Aryl Ester Not Undergoing Thermal Decomposition

55 **[0671]** When the solution recovered in the storage tank 603 in step (F) above was analyzed by liquid chromatography, it was found to be a mixture containing N,N'-hexanediy-di(carbamic acid (2-naphthyl) ester) and 2-naphthol.

[0672] The same method as step (A) above was carried out with the exception of using a mixture of about 5.9 kg of the mixture and 22.2 kg of 2-naphthol instead of 2-naphthol, 1.33 kg of hexamethylenediamine and 3.22 kg of urea. A reaction liquid was obtained that contained 7.2% by weight of 1,1'-(hexane-1,6-diyl) diurea and 6300 ppm of ammonia.

[Example 84]

Step (B-2): Reuse of N-substituted Carbamic Acid-O-Aryl Ester Not Undergoing Thermal Decomposition

5 **[0673]** The same method as step (A) of Example 83 was carried out to obtain about 32.1 kg of a solution containing 7.2% by weight of 1,1'-(hexane-1,6-diyl) diurea.

[0674] 6.0 kg of the mixture recovered in the storage tank 603 in step (F) above were added to this solution to obtain a mixture followed by carrying out the same method as step (B) above using this mixture. A reaction liquid was obtained that contained N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) based on hexamethylenediamine was about 97%.

10 **[0675]** Furthermore, yield referred to here indicates the yield of N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) formed in the step (B). Namely, this refers to the value obtained by dividing the amount obtained by subtracting the amount of N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) contained in the mixture recovered in the storage tank 603 used in this step from the amount of N,N'-hexanediyldi(carbamic acid (2-naphthyl) ester) contained in the reaction liquid by the amount of hexamethylenediamine used in step (A).

[Example 85]

Step (A): Production of Compound Having Ureido Groups

20 **[0676]** The same method as step (A) of Example 5 was carried out with the exception of using 11.7 kg of 1-hexanol instead of 1-octanol, using 1.64 kg of urea and 1.22 kg of 3-aminomethyl-3,5,5-trimethylcyclohexylamine, and heating the storage tank 103 to 120°C. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain about 7.8% by weight of 3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea. In addition, the ammonia concentration in the solution was 7500 ppm. 12.2 kg of an aromatic hydroxy compound in the form of 4-phenyl phenol were added from the storage tank 101 to obtain a homogeneous solution. Line 13 was opened and the solution was transferred to the storage tank 104 via the line 13.

Steps (R) and (D): Production of N-substituted Carbamic Acid-O-Alkyl Ester and Recovery of Urea

30 **[0677]** The same method as steps (R) and (D) of Example 4 was carried out with the exception of heating the packed column 105 to 240°C, setting the pressure within the packed column 105 to about 10 kPa. When the reaction liquid recovered in the storage tank 110 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain 3-((1-hexyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-hexyl) ester, and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 92%. The concentration of ammonia in the reaction liquid was about 10 ppm.

Step (P): Transesterification Reaction

40 **[0678]** The same method as step (P) of Example 4 was carried out with the exception of heating the packed column 502 to 250°C and setting the internal pressure to 15 kPa. When the reaction liquid recovered in the storage tank 505 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to be a solution containing 3-((4-(phenylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylphenyl) ester, and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was 88%.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0679] The apparatus shown in FIG. 17 was used.

50 **[0680]** The thin film distillation apparatus 602 was heated to 230°C and the pressure within the thin film distillation apparatus was set to about 1.0 kPa. The reaction liquid recovered in the storage tank 505 in step (P) above was placed in the storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1080 g/hr via the line 60. A liquid component was extracted from the line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in the storage tank 603 (the liquid component recovered in the storage tank 603 was not supplied to the thin film distillation apparatus 602). A gaseous component containing isophorone diisocyanate and p-dodecyl phenol was extracted from the line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into the distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to the distillation column 609 from the line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was

condensed in the condenser 610 via the line 69 and recovered in the storage tank 612 through the gas-liquid separator 611.

[0681] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of isophorone diisocyanate.

5 Step (R-2): Reuse of Mixture Containing Unreacted N-substituted Carbamic Acid-O-Aryl Ester

[0682] When the mixture recovered in the storage tank 603 in step (F) above was analyzed by liquid chromatography, the mixture was found to be a mixture containing 3-((4-phenylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylphenyl) ester and 4-phenyl phenol, and the content of 3-((4-phenylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylphenyl) ester was about 42% by weight.

10 **[0683]** The same method as steps (R) and (D) above was carried out with the exception of adding about 1.5 kg of the mixture recovered in the storage tank 603 to the reaction liquid obtained by carrying out the same method as step (A) above to obtain a mixture, and using that mixture. When the reaction liquid recovered in the storage tank 110 was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain 3-((1-hexyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-hexyl) ester. The yield of the 3-((1-hexyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-hexyl) ester formed in this step (R-2) based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 92%. The ammonia concentration in the reaction liquid was about 10 ppm.

[Example 86]

20

Step (P-2): Reuse of Mixture Containing Unreacted N-substituted Carbamic Acid-O-Aryl Ester

[0684] The same method as steps (A) and (R) of Example 85 were carried out to obtain about 20.3 kg of a solution containing 3-((1-hexyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-hexyl) ester. About 2.5 kg of the mixture recovered in the storage tank 603 of step (F) above were mixed with this solution followed by carrying out the same method as step (P) above to obtain a solution containing 3-((4-phenylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylphenyl) ester in the storage tank 505. The yield of the 3-((4-phenylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylphenyl) ester, excluding the 3-((4-phenylphenoxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (4-phenylphenyl) ester produced in step (P-2) and contained in the mixture recovered in the storage tank 603 that was added as described above, based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was 88%.

25

30

[Example 87]

35 Step (A-2): Reuse of N-substituted Carbamic Acid-O-Aryl Ester Not Undergoing Thermal Decomposition

[0685] The same method as steps (A) and (R) of Example 85 was carried out to obtain about 21.5 kg of a solution containing 3-((1-hexyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-hexyl) ester.

[0686] The same method as step (A) above was carried out with the exception of using a mixture of about 6.8 kg of this solution and 16.9 kg of 1-octanol instead of 1-octanol alone, and using 1.41 kg of hexamethylenediamine and 2.39 kg of urea. A reaction solution was obtained that contained 7.6% by weight of 1,1'-(hexane-1,6-diyl) diurea and 5300 ppm of ammonia.

40

[Example 88]

45

Step (A): Production of Compound Having Ureido Groups

[0687] The apparatus shown in FIG. 13 was used.

[0688] 30.5 kg of p-heptyl phenol and 2.54 kg of urea were mixed in the storage tank 101 heated to 120°C with the line 13 closed to obtain a mixture. The mixture was transferred to the stirring tank 103 (with baffles) heated to 120°C. The line 19 was connected to a vacuum pump and the pressure inside the stirring tank 103 was reduced to about 70 kPa. 1.23 kg of organic amine in the form of hexamethylenediamine were supplied at the rate of about 20 g/min (organic amine supply rate) from the storage tank 102 to the stirring tank 103 via the line 12 while stirring the stirring tank 103. Following completion of supplying hexamethylenediamine, stirring was continued for about 2 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 97% based on hexamethylenediamine. In addition, the ammonia concentration in the solution was 1200 ppm. Unreacted amino group terminals were not detected.

55

[0689] Line 13 was then opened and the reaction liquid was transferred to the storage tank 104 via the line 13.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

[0690] The apparatus shown in FIG. 13 was continued to be used.

[0691] A packed column 105 packed with a packing material (Helipack No. 3) was heated to 240°C and the pressure inside the column was set to 26kPa. The reaction liquid obtained in step (A) was fed from a line 14 provided in the packed column 105 at the rate of about 1.5 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 35.1 kg. The reaction liquid was recovered in a storage tank 110 through a line 16 provided in the bottom of the packed column 105. A gaseous phase component was condensed from a line 15 provided in the top of the packed column 105 with a condenser 106 maintained at a temperature of about 85°C, and the resulting liquid phase component was recovered in a storage tank 109 via a gas-liquid separator 108. When reaction liquid recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain urea and p-heptyl phenol. The amount of reaction liquid recovered in the storage tank 110 was 23.0 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester). The yield of N,N'-hexanediyldi(carbamic acid(p-heptylphenyl) ester) based on the hexamethylene diamine was about 96%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0692] The apparatus shown in FIG. 17 was used.

[0693] A thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing hexamethylene diisocyanate and p-heptyl phenol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous phase component was condensed in a condenser 610 via a line 69 and recovered in a storage tank 612 through a gas-liquid separator 611.

[0694] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on the organic amin (hexamethylene diamine) was about 92%.

[Example 89]

Step (A): Production of Compound Having Ureido Groups

[0695] The same method as step (A) of Example 88 was carried out with the exception of using 29.5 kg of p-heptyl phenol and 2.46 kg of urea, reducing the pressure in the stirring tank 103 to about 40 kPa, and using 1.19 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 91% based on hexamethylenediamine. In addition, N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) was found to have been formed at a yield of about 0.5% based on hexamethylenediamine. The ammonia concentration was 820 ppm. Unreacted amino group terminals were not detected.

[0696] Line 13 was then opened and the reaction liquid was transferred to the storage tank 104 via the line 13.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

[0697] The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 91%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0698] The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of

step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 86%.

5 [Example 90]

Step (A): Production of Compound Having Ureido Groups

10 **[0699]** The same method as step (A) of Example 88 was carried out with the exception of using 30.3 kg of p-heptyl phenol and 2.52 kg of urea, reducing the pressure in the stirring tank 103 to about 26 kPa, and using 1.22 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 89% based on hexamethylenediamine. In addition, N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) was found to have been formed at a yield of about 0.7% based on hexamethylenediamine. The ammonia concentration was 350 ppm. Unreacted amino group terminals were not detected.

15

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

20 **[0700]** The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 90%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

25 **[0701]** The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 85%.

30 [Example 91]

Step (A): Production of Compound Having Ureido Groups

35 **[0702]** The same method as step (A) of Example 88 was carried out with the exception of using 31.8 kg of p-heptyl phenol and 2.64 kg of urea, reducing the pressure in the stirring tank 103 to about 20 kPa, and using 1.28 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 82% based on hexamethylenediamine. In addition, N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) was found to have been formed at a yield of about 5.2% based on hexamethylenediamine. The ammonia concentration was 280 ppm. Unreacted amino group terminals were not detected.

40

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

45 **[0703]** The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 85%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

50 **[0704]** The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 82%.

55

[Example 92]

Step (A): Production of Compound Having Ureido Groups

5 **[0705]** The same method as step (A) of Example 88 was carried out with the exception of using 29.5 kg of p-heptyl phenol and 2.46 kg of urea, reducing the pressure in the stirring tank 103 to about 20 kPa, and using 1.19 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 77% based on hexamethylenediamine. In addition, N, N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) was found to have been formed at a yield of about 5.0% based on hexamethylenediamine. The ammonia concentration was 120 ppm. Unreacted amino group terminals were not detected.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

15 **[0706]** The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 82%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

20 **[0707]** The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 79%.

25

[Example 93]

Step (A): Production of Compound Having Ureido Groups

30 **[0708]** The same method as step (A) of Example 88 was carried out with the exception of using 32.5 kg of p-heptyl phenol and 2.71 kg of urea, reducing the pressure in the stirring tank 103 to about 20 kPa, and using 1.31 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 68% based on hexamethylenediamine. In addition, N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) was found to have been formed at a yield of about 9.1% based on hexamethylenediamine. The ammonia concentration was 90 ppm. Unreacted amino group terminals were not detected.

35

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

40 **[0709]** The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 76%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

45

[0710] The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 71%.

50

[Example 94]

Step (A): Production of Compound Having Ureido Groups

55 **[0711]** The same method as step (A) of Example 88 was carried out with the exception of using 31.1 kg of p-heptyl phenol and 2.58 kg of urea, reducing the pressure in the stirring tank 103 to about 20 kPa, and using 1.25 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 67% based on hexamethylenediamine. In addition, N,N'-hexanediyldi(carbamic acid (p-

heptylphenyl) ester) was found to have been formed at a yield of about 10.3% based on hexamethylenediamine. The ammonia concentration was 17 ppm. Unreacted amino group terminals were not detected.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

[0712] The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 74%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0713] The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 69%.

[Example 95]

Step (A): Production of Compound Having Ureido Groups

[0714] The same method as step (A) of Example 88 was carried out with the exception of using 31.8 kg of p-heptyl phenol and 2.65 kg of urea, reducing the pressure in the stirring tank 103 to about 20 kPa, and using 1.28 kg of hexamethylenediamine. When the reaction liquid was analyzed, 1,1'-(hexane-1,6-diyl) diurea was found to have been formed at a yield of about 52% based on hexamethylenediamine. In addition, N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) was found to have been formed at a yield of about 16.1% based on hexamethylenediamine. The ammonia concentration was 8 ppm. Unreacted amino group terminals were not detected.

Steps (B) and (D): Production of N-substituted Carbamic Acid-O-Aryl Ester and Recovery of Urea

[0715] The same method as step (B) of Example 74 was carried out with the exception of using the reaction liquid of step (A) above. The reaction liquid recovered in the storage tank 110 was found to contain N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester), and the yield of N,N'-hexanediyldi(carbamic acid (p-heptylphenyl) ester) based on hexamethylenediamine was about 65%. Urea was not detected in the reaction liquid.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Aryl Ester

[0716] The same method as step (F) of Example 74 was carried out with the exception of using the reaction liquid of step (B) above. When the condensate recovered in the storage tank 612 was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 99% by weight of hexamethylene diisocyanate. The yield based on hexamethylenediamine was about 61 %.

[Comparative Example 1]

[0717] The apparatus shown in FIG. 13 was used.

[0718] 1.21 kg of hexamethylenediamine, 2.51 kg of urea and 42.9 kg of 4-(1,1,3,3-tetramethylbutyl) phenol were mixed at 100°C to obtain a raw material solution that was placed in the storage tank 104. The raw material solution was fed at the rate of about 3.0 g/min to the distillation column 105 heated to 240°C and set to an internal pressure of 30 kPa and allowed to react. A gaseous phase component was introduced into the condenser 106 via the line 15 provided in the top of the distillation column 105 and the condensate was recovered in the storage tank 109. On the other hand, a reaction liquid was recovered from the line 16 provided in the bottom of the column and recovered in the storage tank 110. During the reaction, reaction liquid was sampled from a sampling line 18 provided between the line 14 and the bottom of the column, and the sampled liquid was analyzed by ¹H-NMR and liquid chromatography. The sampled liquid was found to be a mixture containing 0.12% by weight of hexamethylenediamine, 0.42% by weight of 6-ureido-hexamethylethylamine, 1.26% by weight of 1,1'-(hexane-1,6-diyl) diurea, 3.49% by weight of N-(6-ureido-hexane-yl)-carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenylester), and 1.30% by weight of N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl) phenylester). The amount of reaction liquid recovered in the storage tank 110 was 33.5 kg. When the reaction liquid was analyzed by ¹H-NMR and liquid chromatography, it was found to be a reaction liquid that contained

N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenylester). The yield of N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenylester) based on hexamethylenediamine was 53%. In addition, the reaction liquid contained about 13 mol% of N,N'-bis(6-(4-(1,1,3,3-tetramethylbutyl)phenoxy)carbaminohexyl) urea based on N,N'-hexanediyldi(carbamic acid (4-(1,1,3,3-tetramethylbutyl)phenylester).

[Comparative Example 2]

Step (A): Production of Compound Having Ureido Groups

[0719] The apparatus used in FIG. 13 was used.

[0720] 22.5 kg of 1-octanol and 2.27 kg of urea were mixed in the storage tank 101 heated to 120°C with the line 13 closed, and the mixture was transferred to the stirring tank 103 heated to 120°C. 1.34 kg of organic amine in the form of 3-aminomethyl-3,5,5-trimethylcyclohexylamine were then supplied at the rate of about 10 g/min from the storage tank 102 to the stirring tank 103 via the line 12 while stirring the stirring tank 103. Following completion of supplying the 3-aminomethyl-3,5,5-trimethylcyclohexylamine, stirring was continued for about 2 hours and the reaction liquid was sampled. As a result of analyzing the reaction liquid by liquid chromatography, the reaction liquid was found to contain about 7.8% by weight of 3-(ureidomethyl)-3,5,5-trimethylcyclohexylurea. The concentration of ammonia in the reaction liquid was 6800 ppm. Line 13 was opened and the solution was transferred to the storage tank 104 via the line 13.

Steps (R) and (D): Production of N-substituted Carbamic Acid-O-Alkyl Ester and Recovery of Urea

[0721] The apparatus shown in FIG. 13 was continued to be used.

[0722] The packed column 105 packed with a packing material (Helipack No. 3) was heated to 190°C. The reaction liquid obtained in step (A) was fed from the line 14 provided in the packed column 105 at the rate of about 1.1 g/min. Since the reaction is initially in an unsteady state, the sample at that time was discarded. The amount of reaction liquid fed after the reaction had reached a steady state was about 23.4 kg. The reaction liquid was recovered in the storage tank 110 through the line 16 provided in the bottom of the packed column 105. A gaseous phase component was introduced into the condenser 106 from the line 15 provided in the top of the packed column 105, and the resulting liquid phase component was recovered in the storage tank 109 via the gas-liquid separator 108. When the condensed component recovered in the storage tank 109 was analyzed by ¹H-NMR, the condensed component was found to contain 1-octanol and urea. The amount of the reaction liquid recovered in the storage tank 110 was 8.80 kg. When the reaction liquid was analyzed by liquid chromatography and ¹H-NMR, the reaction liquid was found to contain 3-((1-octyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-octyl) ester, and the yield based on 3-aminomethyl-3,5,5-trimethylcyclohexylamine was about 90%.

Step (F): Production of Isocyanate by Thermal Decomposition of N-substituted Carbamic Acid-O-Alkyl Ester

[0723] The apparatus shown in FIG. 17 was used.

[0724] A thin film distillation apparatus 602 having a heat-conducting surface area of 0.2 m² was heated to 220°C and the pressure within the thin film distillation apparatus was set to about 1.3 kPa. The reaction liquid recovered in the storage tank 110 in step (B) was placed in a storage tank 601 and supplied to the thin film distillation apparatus at the rate of about 1800 g/hr via a line 60. A liquid component was extracted from a line 62 provided in the bottom of thin film distillation apparatus 602 and recovered in a storage tank 603. The liquid component recovered in the storage tank 603 was again supplied to the thin film distillation apparatus 602 through a line 63. A gaseous component containing hexamethylene diisocyanate and octanol was extracted from a line 61 provided in the upper portion of the thin film distillation apparatus 602. The gaseous component was introduced into a distillation column 604, and the low boiling point component was separated by distillation. A liquid phase component was supplied to a distillation column 609 from a line 68 provided at a portion of the distillation column 604 lower than the feed line and further subjected to distillative separation. The gaseous component was condensed in the condenser 610 via a line 69 and recovered in a storage tank 612 through a gas-liquid separator 611.

[0725] When the condensate was analyzed by ¹H-NMR and gas chromatography, the condensate was found to contain about 93% by weight of isophorone diisocyanate and about 4% by weight of 3-((1-octyloxy)carbonylamidomethyl)-3,5,5-trimethylcyclohexyl carbamic acid (1-octyl) ester. The yield based on organic amine (3-amino-methyl-3,5,5-trimethylcyclohexylamine) was about 53%.

[Example 96]

[0726] A composition containing 9% by weight of a compound having ureido groups in the form of 1,1'-(hexane-1,6-

diyl) diurea, 89% by weight of an aromatic hydroxy composition in the form of 4-(2,4,4-trimethylpentan-2-yl) phenol, 0.01% by weight of ammonia and urea at a ratio of 0.1 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.1 indicates 0.2 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the 1,1'-(hexane-1,6-diyl) diurea was contained at about 92 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the 1,1'-(hexane-1,6-diyl) diurea and aromatic hydroxy composition in the form of bis(4-(2,4,4-trimethylpentan-2-yl)phenyl)hexane-1,6-diyl carbamate was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the bis-(4-(2,4,4-trimethylpentan-2-yl)phenyl) hexane-1,6-diyl dicarbamate based on 1,1'-(hexane-1,6-diyl) diurea at the start of the storage period was 87 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.





[Examples 97 to 144 and Comparative Examples 3 to 6]

[0727] Storage and esterification (reaction for obtaining N-substituted carbamic acid-O-aryl ester by reacting ureido groups with an aromatic hydroxy compound) were carried out using 1,1'-(hexane-1,6-diyl) diurea for the compound having ureido groups under the same conditions as Example 96 with the exception of the composite ratios of the compound having ureido groups, aromatic hydroxy composition, ammonia, carbonic acid derivative and the like, and the results of distillation are shown in Tables 37 to 44. Yields of N-substituted carbamic acid-O-aryl ester are indicated as values obtained by analyzing a liquid phase component from the lower portion of the sieve plate distillation column.



[0728] In the tables, ArOH represents an aromatic hydroxy compound that composes an aromatic hydroxy composition. The content of each component in the composition is represented as a weight percentage (wt%) obtained by rounding the contents of the compound having ureido groups, aromatic hydroxy composition, water and ammonia to the number of significant digits of the analysis apparatus or less, metal components are expressed in ppm, while other components (such as carbonic acid derivative) are indicated as the ratio of the number of molecules thereof to the number of ureido groups that compose (or are contained in) the compound having ureido groups. (Unless indicated otherwise, phenomena such as clogging or solid formation did not occur during storage or transfer.)

[0729] The ¹H-NMR spectra of the compositions for transfer and storage of a compound having ureido groups of Examples 97, 106, 122 and 142 are shown in FIGS. 23, 24, 25 and 26, respectively.




[Table 37]

Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
17.0		81	0.0001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	95.0	92.0
9.7		72	0.0001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, diphenylhexane-1,6-diyl carbamate: 16.5 wt%	85.0	82.0
1.0		99	0.0001		98.0	97.0
17.7		51.5 30	0.05	Fe ion: 20 ppm, Ni ion: 15 ppm	98.3	93.7
17.7		0	0.0001	1-butanol: 79 wt%, urea: 0.01	3	(solid formation, pump clogged)
17.7		0	0.001	1-butanol: 80 wt%, dibutyl tin dilaurate: 2010 ppm	3	(solid formation, pump clogged)
96		0	0.0001	1-butanol: 0.1 wt%, urea: 0.001, total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.0	(sticking during heating, pump clogged)





[Table 38]

55	Example 101	Content of compound having ureido groups in composition (wt%)	97	ArOH		Content of aromatic hydroxy compound in composition (wt%)	0	Content of ammonia in composition (wt%)	0.001	Other components and contents thereof in composition (%)	1-butanol: 0.1 wt%, urea: 0.001	Ratio of compound having ureido groups after storage versus before storage (mol%)	98.0	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	(although unable to be transferred after storage due to being a powder, able to be transferred when a separate stirring tank with stirrer was provided and a 17.7 wt% phenol solution was prepared at 120°C; yield at that time: 70 mol%)
	Comparative Example 6	Content of compound having ureido groups in composition (wt%)	98.5		0		0	0.001	0.001	1-butanol: 0.1 wt%, urea: 0.001	1-butanol: 0.1 wt%, urea: 0.001	97.5	(unable to be transferred after storage due to being a powder, large amount of insoluble matter caused pump clogging even when a separate stirring tank with stirrer was provided and a 17.7 wt% 1-butanol solution was prepared at 110°C)		
	Example 102	17.7			51 30			0.01		Fe ion: 20 ppm, Ni ion: 15 ppm, dibutyl tin dilaurate: 2010 ppm		18.1	17.3		
	Example 103	15.8			10 72			0.01		Dibutyl tin dilaurate: 10 ppm, total carbonic acid ester: 0.001		99.4	97.6		





(continued)

	55	50	45	40	35	30	25	20	15	10	5
	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)				
Example 104	15.8		10 73.2	0.001	Water: 90 ppm	98.1	93.5				
Example 105	15.8		10 73.2	0.01	Fe ion: 20 ppm, Ni ion: 30 ppm dibutyl tin dilaurate: 300 ppm	86.1	81.7				
Example 106	14.2		14 70	0.005	Total biuret group-containing compounds: 0.005, Al ion: 40 ppm	97.9	88.4				





[Table 39]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 107	14.2		20 56	0.01	Urea: 1, Al ion: 40 ppm	98.6	96.4
Example 108	14.2		14 70	0.04	Urea: 0.005, dibutyl tin dilaurate: 590 ppm	76.1	68.6
Example 109	14.2		45 39	0.1	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 290 ppm	88.0	83.8
Example 110	14.2		45 39	0.5	Total terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	97.0	92.7




[Table 40]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 114	12.9		20 65	0.1	Total ureylene group-containing compounds: 0.005	98.4	96.4
Example 115	12.9		25 60	0.2	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 40 ppm, water: 0.5 wt%	95.3	90.4
Example 116	12.9		20 65	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.4	93.5
Example 117	11.9		20 65	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.3	88.6





[Table 41]

55	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 121	12.8		20 63	0.3	Total ureylene group-containing compounds: 0.020, terminal biuret group-containing compounds: 0.015	97.7	87.9
Example 122	9.5		79.5 10	0.1	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	95.8	94.1
Example 123	8.9		74	0.01	Naphthalene: 15wt%, total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	96.6	91.2
Example 124	10.8		76 10	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group containing compounds: 0.005	96.3	91.2




(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 125	12.3		80	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, butanol: 5 wt%	95.9	94.1
Example 126	12.3		85	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.4	96.4
Example 127	12.3		76 10	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.4	88.6




[Table 42]

Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
5.2		93.8	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	99.0	98.0
14.5		84	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.0	95.0
21.4		77	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	95.8	60.0
13.6		20 63	0.02	Total ureylene group-containing compounds: 0.022, terminal biuret-group containing compounds: 0.015	83.8	42.0




(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 132	12.8		72.10	0.05	Total ureylene group-containing compounds: 0.022, terminal biuret group-containing compounds: 0.015	76.6	38.0
Example 133	35.2		62	0.001	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	96.0	25.0
Example 134	20.0		78	0.001	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	95.9	85.0

[Table 43]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 135	17.5		60 20	0.3	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.3	88.2
Example 136	20.0		55 24	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, ditolylcarbonate: 0.01	98.2	96.3
Example 137	15.0		62 10 10	0.05	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, ditolylcarbonate: 0.01	97.3	95.3


(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 138	9.2		78 10	0.04	Urea: 0.05, terminal biuret-group containing compounds: 0.05, dixylylcarbonate: 0.06, dibutyl tin dilaurate: 650 ppm	73.9	66.6
Example 139	8.1		77 10	0.01	Urea: 0.05, terminal biuret group-containing compounds: 0.05, dixylylcarbonate: 0.06	98.8	59.0
Example 140	15.5		10 72	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.7	73.0




5
10
15
20
25
30
35
40
45
50
55

(continued)

	Content of compound having ureido groups in composition (wt%)	9.9		Content of ammonia in composition (wt%)	0.1	Other components and contents thereof in composition (%)	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	Ratio of compound having ureido groups after storage versus before storage (mol%)	98.0	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	96.4
Example 141			68								




[Table 44]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted Carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 142	7.9		90	0.2	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	73.0	51.2
Example 143	8.0		90	0.3	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	98.8	49.2
Example 144	4.5		90	0.5	Total ureylene group-containing compounds: 0.02, terminal biuret group-containing compounds: 0.05, urea: 0.01	64.4	32.0

[Example 145]

[0730] A composition containing 21% by weight of a compound having ureido groups represented by the following formula (200), 77% by weight of an aromatic hydroxy composition in the form of phenol, 0.01 % by weight of ammonia and urea at a ratio of 0.01 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.01 indicates 0.02 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the compound having ureido groups was contained in the composition at about 93 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and aromatic hydroxy composition was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the N-substituted carbamic acid-O-aryl ester based on the compound having ureido groups at the start of the storage period was 87 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.





[Examples 146 to 186 and Comparative Examples 7 to 10]

[0731] Storage and esterification (reaction for obtaining N-substituted carbamic acid-O-aryl ester by reacting ureido groups with an aromatic hydroxy compound) were carried out using the compound having ureido groups represented by formula (200) in Example 145 under the same conditions as Example 145 with the exception of the composite ratios of the compound having ureido groups, aromatic hydroxy composition, ammonia, carbonic acid derivative and the like, and the results of distillation are shown in Tables 45 to 50. Yields of N-substituted carbamic acid-O-aryl ester are indicated as values obtained by analyzing a liquid phase component from the lower portion of the sieve plate distillation column.

[0732] In the tables, ArOH represents an aromatic hydroxy compound that composes an aromatic hydroxy composition. The content of each component in the composition is represented as a weight percentage (wt%) obtained by rounding the contents of the compound having ureido groups, aromatic hydroxy composition, water and ammonia to the number of significant digits of the analysis apparatus or less, metal components are expressed in ppm, while other components (such as carbonic acid derivative) are indicated as the ratio of the number of molecules thereof to the number of ureido groups that compose (or are contained in) the compound having ureido groups. (Unless indicated otherwise, phenomena such as clogging or solid formation did not occur during storage or transfer.)

[Table 45]




55	50	45	40	35	30	25	20	15	10	5
Example 146	Example 147	Example 148	Comparative Example 7	Comparative Example 8	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester compound having ureido groups before storage (mol%)		
12.0	1.0	21.4	20.0	20.0	0.0001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, diphenylhexane-1,6-dylcarbamate: 16.5 wt%	95.0	92.0		
ArOH	99	48	0	0	0.0001	Fe ion: 20 ppm, Ni ion: 15 ppm	98.0	91.0		
Content of compound having ureido groups in composition (wt%)	68	30	0	0	0.05	1-butanol: 79 wt%, urea: 0.001	98.6	93.7		
Content of aromatic hydroxy compound in composition (wt%)					0.0001	1-butanol: 79 wt%, dibutyl tin dilaurate: 20.10 ppm	3	(solid formation, pump clogged)		
Content of ammonia in composition (wt%)	0	0	0	0	0.001		4	(solid formation, pump clogged)		

5
10
15
20
25
30
35
40
45
50
55





(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Comparative Example 9	96		0	0.01	1-butanol: 0.1 wt%, urea: 0.001, total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	99.0	(sticking during heating, pump clogged)
Example 149	98		0	0.0001	1-butanol: 0.1 wt%, urea: 0.001	99.0	(although unable to be transferred after storage due to being a powder, able to be transferred when a separate stirring tank with stirrer was provided and a 17.7 wt% phenol solution was prepared at 120°C; yield at that time: 70 mol%)




[Table 47]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 156	17.3		21 60	0.1	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 290 ppm	88.4	83.8
Example 157	45.0		44 10	0.5	Terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	97.7	34.0
Example 158	15.8		22 60	0.01	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 30 ppm, water: 0.5 wt%	99.4	88.9

(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 159	15.8		23 60	0.01	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm, water: 0.5wt%	98.1	92.7
Example 160	5.0		34 60	0.01	Total ureylene group-containing compounds: 0.005	98.0	97.0
Example 161	1.5		38 60	0.1	Total ureylene group-containing compounds: 0.005	98.0	96.4
Example 162	15.8		22 60	0.2	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 40 ppm, water: 0.5 wt%	95.6	90.4





[Table 48]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 163	15.8		23 60	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.7	93.5
Example 164	3.0		36 60	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	97.9	88.6
Example 165	14.6		23 60	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	97.3	87.8





(continued)

5									Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	
10									Ratio of compound having ureido groups after storage versus before storage (mol%)	
15									Other components and contents thereof in composition (%)	
20									Content of ammonia in composition (wt%)	
25									Content of aromatic hydroxy compound in composition (wt%)	
30									ArOH	
35									Content of compound having ureido groups in composition (wt%)	
40									Chemical structure of ArOH for Example 169: <chem>Oc1ccc(cc1)C(=O)c2ccccc2</chem>	
45									Chemical structure of ArOH for Example 170: <chem>Oc1ccc(cc1)C(=O)c2ccccc2</chem>	
50									Content of compound having ureido groups in composition (wt%)	
55										





[Table 49]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 171	13.4		75 10	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	93.3	91.7
Example 172	15.1		78	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, butanol: 5 wt%	96.0	94.1
Example 173	15.1		83	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.7	96.4
Example 174	15.1		73.5 10	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	99.3	97.2

(continued)


	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 175	6.4		92	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	96.9	94.1
Example 176	18.0		81	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	95.9	94.1
Example 177	25.6		73	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	96.1	38.0
Example 178	40.8		57	0.001	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	95.8	25.0

[Table 50]

Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield. versus compound having ureido groups before storage)
11.3		75 9	0.04	Urea: 0.005, terminal biuret group-containing compounds: 0.05, dixylylcarbonate: 0.06, dibutyl tin dilaurate: 650 ppm	74.3	66.6
10.1		76 10	0.01	Urea: 0.005, terminal biuret group-containing compounds: 0.05, dixylylcarbonate: 0.06	98.0	59.0
18.9		10 70	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.4	73.8
9.9		89	0.2	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	63.6	44.8


5
10
15
20
25
30
35
40
45
50
55

(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield. versus compound having ureido groups before storage)
Example 185	10.1		88	0.3	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	98.0	39.4
Example 186	5.6		92	0.5	Total ureylene group-containing compounds: 0.02, terminal biuret group-containing compounds: 0.05, urea: 0.01	64.3	32.0

[Example 1.87]

[0733] A composition containing 17.1% by weight of a compound having ureido groups represented by the following formula (201), 82% by weight of an aromatic hydroxy composition in the form of 4-(2-phenylpropane-2-yl) phenol, 0.01% by weight of ammonia and urea at a ratio of 0.001 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.001 indicates 0.002 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the compound having ureido groups was contained in the composition at about 98 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and aromatic hydroxy composition was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the N-substituted carbamic acid-O-aryl ester based on the compound having ureido groups at the start of the storage period was 96.4 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.






[Examples 187-1 to 226 and Comparative Examples 11 to 14]

[0734] Storage and esterification (reaction for obtaining N-substituted carbamic acid-O-aryl ester by reacting ureido groups with an aromatic hydroxy compound) were carried out using the compound having ureido groups represented by formula (201) in Example 187 under the same conditions as Example 187 with the exception of the composite ratios of the compound having ureido groups, aromatic hydroxy composition, ammonia, carbonic acid derivative and the like, and the results of distillation are shown in Tables 51 to 56. Yields of N-substituted carbamic acid-O-aryl ester are indicated as values obtained by analyzing a liquid phase component from the lower portion of the sieve plate distillation column.

[0735] In the tables, ArOH represents an aromatic hydroxy compound that composes an aromatic hydroxy composition. The content of each component in the composition is represented as a weight percentage (wt%) obtained by rounding the contents of the compound having ureido groups, aromatic hydroxy composition, water and ammonia to the number of significant digits of the analysis apparatus or less, metal components are expressed in ppm, while other components (such as carbonic acid derivative) are indicated as the ratio of the number of molecules thereof to the number of ureido groups that compose (or are contained in) the compound having ureido groups. (Unless indicated otherwise, phenomena such as clogging or solid formation did not occur during storage or transfer.)

[Table 51]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 187-1	24.0		74	0.001	Urea: 0.01	22.2	95.0	92.0
Example 188	13.0		85	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, phenyl carbamate: 0.01	12.6	93.0	91.0
Example 189	24.0		25 50	0.05	Fe ion: 20 ppm Ni ion: 15 ppm	23.6	98.3	93.7
Comparative Example 11	29.6		0	0.0001	1-butanol: 58 wt%, urea: 1	4.8	3	(solid formation, pump clogged)
Comparative Example 12	20.0		0	0.001	1-butanol: 79 wt%, dibutyl tin dilaurate: 2010 ppm	0.9	4	(solid formation, pump clogged)

(continued)


5	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)								
10									(solid formation, pump clogged)
15	Ratio of compound having ureido groups after storage versus before storage (mol%)	91.0							
20	Content of compound having ureido groups in composition after storage (wt%)	96.5							
25	Other components and contents thereof in composition (%)	1-butanol: 0.1 wt%, urea: 0.5, total ureylene group- containing compounds: 0.005, terminal biuret group- containing compounds: 0.005							
30	Content of ammonia in composition (wt%)	0.0001							
35	Content of aromatic hydroxy compound in composition (wt%)	0							
40									
45	ArOH								
50	Content of compound having ureido groups in composition (wt%)	66							
55	Comparative Example 13								
	Example 190	67							(although unable to be transferred after storage due to being a powder, able to be transferred when a separate stirring tank with stirrer was provided and a 17.7 wt% phenol solution was prepared at 120°C; yield at that time: 89 mol%)

[Table 52]





55	Comparative Example 14	Content of compound having ureido groups in composition (wt%)	67	ArOH	0	Content of aromatic hydroxy compound in composition (wt%)	0.0001	Other components and contents thereof in composition (%)	1-butanol: 0.1 wt%, urea 1	Content of compound having ureido groups in composition after storage (wt%)	96.5	Ratio of compound having ureido groups after storage versus before storage (mol%)	95.0	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	(unable to be transferred after storage due to being a powder, large amount of insoluble matter caused pump clogging even when a separate stirring tank with stirrer was provided and a 17.7 wt% 1-butanol solution was prepared at 110°C)
50	Example 191	Content of compound having ureido groups in composition (wt%)	21.5	ArOH	8 68	Content of aromatic hydroxy compound in composition (wt%)	0.01	Other components and contents thereof in composition (%)	Dibutyl tin dilaurate: 10 ppm, total carbonic acid ester: 0.001	Content of compound having ureido groups in composition after storage (wt%)	21.4	Ratio of compound having ureido groups after storage versus before storage (mol%)	99.5	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	97.6
5	Example 192	Content of compound having ureido groups in composition (wt%)	21.5	ArOH	17 60	Content of aromatic hydroxy compound in composition (wt%)	0.001	Other components and contents thereof in composition (%)	Water: 90 ppm	Content of compound having ureido groups in composition after storage (wt%)	21.2	Ratio of compound having ureido groups after storage versus before storage (mol%)	98.6	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	96.4

(continued)





5
10
15
20
25
30
35
40
45
50
55

Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	68.6
Ratio of compound having ureido groups after storage versus before storage (mol%)	76.4
Content of compound having ureido groups in composition after storage (wt%)	14.9
Other components and contents thereof in composition (%)	Urea: 0.005, dibutyl tin dilaurate: 590 ppm
Content of ammonia in composition (wt%)	0.04
Content of aromatic hydroxy compound in composition (wt%)	19
ArOH	
Content of compound having ureido groups in composition (wt%)	19.5
Example 196	60




[Table 53]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 197	19.5		19 60	0.1	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 290 ppm	17.2	88.2	83.8
Example 198	19.5		19 60	0.5	Total terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	19.1	97.9	92.7
Example 199	17.9		21 60	0.01	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 30 ppm, water: 0.5 wt%	17.7	98.9	88.9
Example 200	17.9		20 60	0.01	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm, water: 0.5 wt%	17.4	97.2	92.7






[Table 54]

Content	content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 204	17.9		20 60	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	17.6	98.3	93.5
Example 205	16.5		21 60	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	16.2	98.2	88.6
Example 206	16.5		21 60	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	16.1	97.6	87.8
Example 207	13.9		68 16	0.2	Urea: 0.001	13.6	97.8	96.4




(continued)

Content	content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 208	16.1		60 11	0.4	Total ureylene group-containing compounds: 0.015, terminal biuret group-containing compounds: 0.015	15.7	97.5	90.0
Example 209	17.7		11.5 68	0.3	Urea: 0.001	17.2	97.2	87.9
Example 210	13.4		70 15.5	0.1	Urea: 0.001	12.8	95.5	94.1





[Table 55]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of Aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 211	12.6		71	0.01	Xylene: 15 wt%, total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	12.1	96.0	94.1
Example 212	15.1		73.5 10	0.01	Urea: 0.01	14.2	94.0	91.7
Example 213	17.1		76	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, butanol: 5wt%	16.4	95.9	94.1
Example 214	17.1		71 10	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	16.9	98.8	97.2
Example 215	7.4		91	0.02	Urea: 0.001	7.1	99.0	98.0




(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of Aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 216	27.0		72	0.02	Urea: 0.001	13.2	96.4	94.1
Example 217	28.5		70	0.02	Urea: 0.001	27.3	95.8	75.0
Example 218	44.3		54	0.001	Urea: 0.001	42.5	95.9	25.0

[Table 56]


	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%) -	Content of compound having ureido groups in composition after storage (wt%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 219	34.7		64	0.001	Urea: 0.001	33.3	96.0	38.0
Example 220	20.6		66 10	0.05	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, ditolyl carbonate: 0.01	20.0	97.1	95.3
Example 221	12.9		73 10	0.04	Urea: 0.001, biuret group-containing compounds: 0.05, dixylyl carbonate: 0.06, dibutyltin dilaurate: 650 ppm	9.5	73.6	66.6
Example 222	11.5		75 10	0.01	Urea: 0.005, biuret group-containing compounds: 0.05, dixylyl carbonate: 0.06	11.3	98.3	59.0

(continued)

5	10	15	20	25	30	35	40	45	50	55
Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Content of compound having ureido groups in composition after storage (wt%)	Other components and contents thereof in composition (%) -	Content of ammonia in composition (wt%)	Content of aromatic hydroxy compound in composition (wt%)	ArOH	Content of compound having ureido groups in composition (wt%)			
73.8	98.6	20.9	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	0.01	10 68		21.2	Example 223		
44.8	64.3	7.2	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.1	0.2	85		11.2	Example 224		
39.4	98.3	11.3	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	0.3	86		11.5	Example 225		
32.0	64.1	4.1	Total ureylene group-containing compounds: 0.02, terminal biuret group-containing compounds: 0.05, urea: 0.001	0.5	92		6.4	Example 226		

[Example 227]

[0736] A composition containing 12.6% by weight of a compound having ureido groups represented by the following formula (202), 86% by weight of an aromatic hydroxy composition in the form of 4-(2-phenylpropane-2-yl) phenol, 0.01% by weight of ammonia and urea at a ratio of 0.001 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.001 indicates 0.002 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the compound having ureido groups was contained in the composition at 98.4 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and aromatic hydroxy composition was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the N-substituted carbamic acid-O-aryl ester based on the compound having ureido groups at the start of the storage period was 96.4 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.






[Examples 228 to 266 and Comparative Examples 15 to 17]





[0737] Storage and esterification (reaction for obtaining N-substituted carbamic acid-O-aryl ester by reacting ureido groups with an aromatic hydroxy compound) were carried out using the compound having ureido groups represented by formula (202) in Example 227 under the same conditions as Example 227 with the exception of the composite ratios of the compound having ureido groups, aromatic hydroxy composition, ammonia, carbonic acid derivative and the like, and the results of distillation are shown in Tables 57 to 62. Yields of N-substituted carbamic acid-O-aryl ester are indicated as values obtained by analyzing a liquid phase component from the lower portion of the sieve plate distillation column.

[0738] In the tables, ArOH represents an aromatic hydroxy compound that composes an aromatic hydroxy composition. The content of each component in the composition is represented as a weight percentage (wt%) obtained by rounding the contents of the compound having ureido groups, aromatic hydroxy composition, water and ammonia to the number of significant digits of the analysis apparatus or less, metal components are expressed in ppm, while other components (such as carbonic acid derivative) are indicated as the ratio of the number of molecules thereof to the number of ureido groups that compose (or are contained in) the compound having ureido groups. (Unless indicated otherwise, phenomena such as clogging or solid formation did not occur during storage or transfer.)




[Table 57]

Example	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 227	18.1		79	0.001	Urea: 0.1	95.0	92.0
Example 228	10.0		78	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, diphenyl-4-methyl-1,3-phenylene dicarbamate: 10 wt%	92.4	87.8
Example 229	18.1		31 50	0.05	Fe ion: 20 ppm, Ni ion: 15 ppm	98.6	93.7
Comparative Example 15	20.0		0	0.0001	1-butanol: 68 wt%, urea: 1	3	(solid formation, pump clogged)
Comparative Example 16	32.0		0	0.001	1-butanol: 67 wt%, dibutyl tin dilaurate: 2010 ppm	4	(solid formation, pump clogged)




[Table 58]

55	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 231	16.1		8 75	0.01	Dibutyl tin dilaurate: 10 ppm, total carbamic acid ester: 0.001	99.6	97.6
Example 232	16.1		18 65	0.001	Water: 90 ppm	98.4	96.4
Example 233	16.1		28 55	0.01	Fe ion: 20 ppm, Ni ion: 30 ppm, dibutyl tin dilaurate: 300 ppm	86.0	84.3
Example 234	14.6		20 64	0.005	Biuret group-containing compounds: 0.005, Al ion: 40 ppm	98.2	88.4





(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 235	14.6		30 54	0.01	Urea: 0.001, Al ion: 40 ppm	98.4	96.4
Example 236	14.6		20 64	0.04	Urea: 0.005, dibutyltin dilaurate: 590 ppm	76.2	68.6
Example 237	14.6		20 63	0.1	Total ureylene group-containing compounds: 0.005, dibutyltin dilaurate: 290 ppm	88.2	83.8




[Table 59]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 238	1.0		20.79	0.5		98.0	95.0
Example 239	2.0		20.78	0.01		98.8	94.0
Example 240	13.3		21.5 60	0.01	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm, water: 0.5 wt%	97.6	92.7





(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 241	2.0		20 78	0.01		99.0	99.0
Example 242	13.3		21 64	0.1	Total ureylene group-containing compounds: 0.005	98.4	96.4
Example 243	13.3		21 64	0.2	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 40 ppm, water: 0.5 wt%	95.2	90.4
Example 244	13.3		21 64	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.4	93.5




[Table 60]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 245	1.0		50 48.5	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.4	97.0
Example 246	12.2		22 63	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	97.6	87.8
Example 247	10.2		72 16	0.2	Urea: 0.01	98.4	96.4



(continued)

5	10	15	20	25	30	35	40	45	50	55
Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Other components and contents thereof in composition (%)	Content of ammonia in composition (wt%)	Content of aromatic hydroxy compound in composition (wt%)	AroH	Content of compound having ureido groups in composition (wt%)				
87.9	97.6	Total ureylene group-containing compounds: 0.015, terminal biuret group-containing compounds: 0.015	0.4	73 13		11.9				Example 248
93.0	97.6	Urea: 0.01	0.3	13 70		13.1				Example 249
99.0	99.0	Urea: 0.01	0.1	70 17		9.8				Example 250
94.1	96.0	Xylene: 15 wt%, total ureylene group-containing compounds: 0.002, terminal biuret-group containing compounds: 0.005	0.01	74		9.2				Example 251

[Table 61]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 252	11.1		72 15	0.01	Urea: 0.01	93.6	91.7
Example 253	12.6		81	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, butanol: 5 wt%	96.0	94.1
Example 254	12.6		86	0.01	Urea: 0.001	98.4	96.4


(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 255	12.6		71.5 14	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	99.2	97.2
Example 256	5.3		93	0.02	Urea: 0.05	99.0	98.0
Example 257	19.5		80	0.02	Urea: 0.05	96.0	94.1
Example 258	21.8		76	0.02	Urea: 0.05	96.0	75.0





5
10
15
20
25
30
35
40
45
50
55

(continued)



	Content of compound having ureido groups in composition (wt%)	35.9		Content of ammonia in composition (wt%)	0.001	Other components and contents thereof in composition (%)	Urea: 0.05	Ratio of compound having ureido groups after storage versus before storage (mol%)	96.0	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	25.0
Example 259			ArOH								



[Table 62]


	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 260	27.2		70	0.001	Urea: 0.05	96.0	38.0
Example 261	15.4		68 13	0.05	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, ditolyl carbonate: 0.01	97.2	95.3
Example 262	9.4		76 10	0.04	Urea: 0.05, terminal biuret group-containing compounds: 0.05, dixylyl carbonate: dibutyl tin dilaurate: 650 ppm	74.0	66.6
Example 263	8.4		77 10	0.01	Urea: 0.05, terminal biuret group-containing compounds: 0.05, dixylyl carbonate: 0.06	98.4	59.0

(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 264	15.9		12 70	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.4	73.8
Example 265	8.4		90	0.3	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	98.4	39.4
Example 266	4.6		93	0.5	Total ureylene group-containing compounds: 0.02, terminal biuret group-containing compounds: 0.05, urea: 0.01	64.0	32.0

[Examples 267]

[0739] A composition containing 16.5% by weight of a compound having ureido groups represented by the following formula (203), 81% by weight of an aromatic hydroxy composition in the form of 4-(2-phenylpropane-2-yl) phenol, 0.01% by weight of ammonia and urea at a ratio of 0.001 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.001 indicates 0.002 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the compound having ureido groups was contained in the composition at 98.4 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and aromatic hydroxy composition was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the N-substituted carbamic acid-O-aryl ester based on the compound having ureido groups at the start of the storage period was 96.4 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.





[Examples 268 to 304 and Comparative Example 18]

[0740] Storage and esterification (reaction for obtaining N-substituted carbamic acid-O-aryl ester by reacting ureido groups with an aromatic hydroxy compound) were carried out using the compound having ureido groups represented by formula (203) in Example 267 under the same conditions as Example 267 with the exception of the composite ratios of the compound having ureido groups, aromatic hydroxy composition, ammonia, carbonic acid derivative and the like, and the results of distillation are shown in Tables 63 to 67. Yields of N-substituted carbamic acid-O-aryl ester are indicated as values obtained by analyzing a liquid phase component from the lower portion of the sieve plate distillation column.

[0741] In the tables, ArOH represents an aromatic hydroxy compound that composes an aromatic hydroxy composition. The content of each component in the composition is represented as a weight percentage (wt%) obtained by rounding the contents of the compound having ureido groups, aromatic hydroxy composition, water and ammonia to the number of significant digits of the analysis apparatus or less, metal components are expressed in ppm, while other components (such as carbonic acid derivative) are indicated as the ratio of the number of molecules thereof to the number of ureido groups that compose (or are contained in) the compound having ureido groups. (Unless indicated otherwise, phenomena such as clogging or solid formation did not occur during storage or transfer.)

[Table 63]


	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 268	23.2		75	0.001	Urea: 0.1	95.0	92.0
Example 269	23.2		30 45	0.05	Fe ion: 20 ppm, Ni ion: 15 ppm	98.6	93.7
Comparative Example 18	20.0		0	0.0001	1-butanol: 79 wt%	3	(solid formation, pump clogged)
Example 270	98		0	0.001	1-butanol: 0.1 wt%	95.0	(although unable to be transferred after storage due to being a powder, able to be transferred when a separate stirring tank with stirrer was provided and a 10 wt% phenol solution was prepared at 120°C; yield at that time: 93 mol%)

(continued)





5		Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)							
10			96.4						
15		Ratio of compound having ureido groups after storage versus before storage (mol%)	98.4						
20		Other components and contents thereof in composition (%)	Water: 90 ppm						
25		Content of ammonia in composition (wt%)	0.001						
30		Content of aromatic hydroxy compound in composition (wt%)	15.62						
35								22	55
40		ArOH							
45									
50		Content of compound having ureido groups in composition (wt%)	20.8						
55									
	Example 271								
	Example 272								

5
10
15
20
25
30
35
40
45
50
55




(continued)

<p>Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)</p>	<p>88.4</p>
<p>Ratio of compound having ureido groups after storage versus before storage (mol%)</p>	<p>98.2</p>
<p>Other components and contents thereof in composition (%)</p>	<p>Biuret group-containing compounds: 0.005, Al ion: 40 ppm</p>
<p>Content of ammonia in composition (wt%)</p>	<p>0.005</p>
<p>Content of aromatic hydroxy compound in composition (wt%)</p>	<p>19 60</p>
<p>ArOH</p>	
<p>Content of compound having ureido groups in composition (wt%)</p>	<p>18.9</p>
<p>Example 273</p>	




[Table 64]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 274	18.9		25 54	0.01	Urea: 0.001, Al ion: 40 ppm	98.4	96.4
Example 275	18.9		18 60	0.04	Urea: 0.005, dibutyl tin dilaurate: 590 ppm	76.2	68.6
Example 276	18.9		18 60	0.1	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 290 ppm	88.2	83.8
Example 277	18.9		18 61	0.5	Terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	97.6	92.7





(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 278	17.3		20 60	0.01	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 30 ppm, water: 0.5 wt%	98.8	88.9
Example 279	17.3		21 60	0.01	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm, water 0.5 wt%	97.6	92.7
Example 280	3.0		20 76.5	0.01	Total ureylene group-containing compounds: 0.005	99.0	98.0





[Table 65]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 281	5.0		30 64.5	0.1	Total ureylene group-containing compounds: 0.005	99.0	99.0
Example 282	17.3		18 62	0.2	Total ureylene group-containing compounds: 0.005, dibutyl tin dilaurate: 40 ppm, water: 0.5 wt%	95.2	90.4
Example 283	17.3		18 62	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.4	93.5





(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 284	15.9		20 61	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005	98.4	88.6
Example 285	15.9		18 63	0.001	Total ureylene group-containing compounds: 0.005, terminal biuret group-containing compounds: 0.005, dibutyl tin dilaurate: 60 ppm	97.6	87.8
Example 286	13.4		68 16	0.2	Urea: 0.01	98.4	96.4
Example 287	15.6		70 12	0.4	Total ureylene group-containing compounds: 0.015, terminal biuret group-containing compounds: 0.015	97.6	87.9

[Table 66]

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 288	17.1		10 70	0.3	Urea: 0.01	97.6	87.9
Example 289	12.9		70 15	0.1	Urea: 0.01	96.0	94.1
Example 290	12.1		71	0.01	Xylene: 15 wt%, total ureylene group-containing compounds: 0.002, terminal biuret-group containing compounds: 0.005	96.0	94.1
Example 291	14.6		68 15	0.01	Urea: 0.01	93.6	91.7

(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 292	16.5		76	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, butanol: 5 wt%	96.0	94.1
Example 293	16.5		68 12	0.02	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	99.2	97.2
Example 294	7.1		90	0.02	Urea: 0.05	99.0	98.0
Example 295	25.0		73	0.02	Urea: 0.05	96.0	94.1

5

10

15

20

25

30

35

40

45


50

55





(continued)

	Content of compound having ureido groups in composition (wt%)	27.6				Ratio of compound having ureido groups after storage versus before storage (mol%)	96.0	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)	75.0
Example 296			70	0.02	Urea: 0.05				





ArOH



[Table 67]


	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 297	43.3		52	0.001	Urea: 0.05	96.0	25.0
Example 298	33.7		62	0.001	Urea: 0.05	96.0	38.0
Example 299	19.9		63 11	0.05	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, ditolyl carbonate: 0.01	97.2	95.3
Example 300	12.4		74 10	0.04	Urea: 0.05, terminal biuret group-containing compounds: 0.05, dixylyl carbonate: 0.06, dibutyl tin dilaurate: 650 ppm	74.0	66.6

(continued)

	Content of compound having ureido groups in composition (wt%)	ArOH	Content of aromatic hydroxy compound in composition (wt%)	Content of ammonia in composition (wt%)	Other components and contents thereof in composition (%)	Ratio of compound having ureido groups after storage versus before storage (mol%)	Yield of N-substituted carbamic acid-O-aryl ester (mol%) (molar yield versus compound having ureido groups before storage)
Example 301	11.1		72 10	0.01	Urea: 0.05, terminal biuret group-containing compounds: 0.05, dixylyl carbonate: 0.06	98.4	59.0
Example 302	20.5		10 65	0.01	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005	98.4	73.8
Example 303	11.1		85	0.3	Total ureylene group-containing compounds: 0.002, terminal biuret group-containing compounds: 0.005, urea: 0.001	98.4	39.4
Example 304	6.2		88	0.5	Total ureylene group-containing compounds: 0.02, terminal biuret group-containing compounds: 0.05, urea: 0.01	64.0	32.0

[Example 305]


[0742] A composition containing 16.5% by weight of a compound having ureido groups represented by the following formula (204) (having different methylene group crosslinking sites, and having an average structure in the form of a trimer structure as represented by the following formula), 81% by weight of an aromatic hydroxy composition in the form of 4-(2-phenylpropane-2-yl) phenol, 0.01% by weight of ammonia and urea at a ratio of 0.001 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.001 indicates 0.003 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the compound having ureido groups was contained in the composition at 98.4 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and aromatic hydroxy composition was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the N-substituted carbamic acid-O-aryl ester based on the compound having ureido groups at the start of the storage period was 96.4 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.



[Example 306]

[0743] A composition containing 12.5% by weight of a compound having ureido groups represented by the following formula (205) (having different methylene group crosslinking sites, and having an average structure in the form of a trimer structure as represented by the following formula), 85% by weight of an aromatic hydroxy composition in the form of cresol (isomer mixture), 0.01% by weight of ammonia and urea at a ratio of 0.001 (referring to the ratio of number of urea molecules to the number of ureido groups that compose (or are contained in) the compound having ureido groups, or in other words, 0.001 indicates 0.004 mole equivalents since the compound having ureido groups has two ureido groups in a molecule thereof) was placed in a 100 L SUS storage vessel to about 1/2 the volume thereof, followed by replacing the inside of the storage vessel with nitrogen, and storing for 1095 days in a storage environment found in the Kojima district of Kurashiki city in Okayama prefecture, Japan. The composition also contained other components for which the structure thereof was unclear (such as compounds containing ureylene groups and compounds containing terminal biuret bonds). During the storage period, the vessel was warmed with a circulating hot water jacket at 40°C (controlled to roughly 30 to 50°C). During the storage period, the temperature occasionally fell to about 0°C or rose to about 50°C due to the effects of water stoppages, power outages and factory utility maintenance. In addition, the temperature once rose to about 80°C due to a malfunction. When the composition was analyzed after storage, the compound having ureido groups was contained in the composition at 97 mol% as compared with prior to storage. Following the storage period, the composition was heated to 180°C and introduced through a preheater (device for

preheating the composition to 230°C) into the vicinity of the middle of a sieve tray distillation column having an inner diameter of 6.35cm (2.5 inches) and 40 theoretical plates (operation of the distillation column was carried out while reducing the pressure from normal pressure to reduced pressure within a liquid phase temperature range in the lower portion of the distillation column of 150 to 300°C and confirming operating conditions; the minimum pressure during operation was about 0.3 KPa). An N-substituted carbamic acid-O-aryl ester derived from the compound having ureido groups and aromatic hydroxy composition was obtained from the lower portion of the distillation column. Ammonia formed as a by-product in the esterification reaction, a small amount of aromatic hydroxy composition, and a component having a lower boiling point than the aromatic hydroxy composition were extracted from the upper portion of the distillation column (and included a by-product in the form of a compound having a molecular weight of 178 or less and having a carbonyl group, although the structure thereof was unable to be identified). Although the yield changed from the start to completion of operation due to fluctuations in operating conditions, at the highest level of performance during the operating period, the yield of the N-substituted carbamic acid-O-aryl ester based on the compound having ureido groups at the start of the storage period was 93 mol%. There was no clogging of lines during both storage and transfer, and formation of solid within the distillation column was not observed.



[0744] The present application is based on Japanese patent applications (Japanese Patent Application No. 2009-192250 and Japanese Patent Application No. 2009-192268) filed with the Japanese Patent Office on August 21, 2009.

Industrial Applicability

[0745] Since the N-substituted carbamic acid-O-aryl ester production method of the present embodiment inhibits side reactions and enables urea and the like used in excess in the reaction to be efficiently recovered and reused by producing an N-substituted carbamic acid-O-aryl ester from a compound having ureido groups and an aromatic hydroxy composition, N-substituted carbamic acid-O-aryl ester can be produced without impairing the amounts of urea and organic amine used. In addition, since various reaction by-products can be inhibited and can be dissolved by the aromatic hydroxy composition and removed outside the system, operating is possible over a long period of time. Moreover, a composition for transfer and storage of a compound having ureido groups can be preferably used as a production raw material of the N-substituted carbamic acid-O-aryl ester, and the N-substituted carbamic acid-O-aryl ester can be preferably used to produce isocyanate. Thus, the present invention is industrially extremely important.

Description of Reference Numericals

[0746]

(FIG. 13)

100, 101, 102, 104, 109, 110: storage tanks, 103: stirring tank, 106, 111: condensers, 107: reboiler, 108, 112: gas-liquid separator, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19: lines

(FIG. 14)

200, 201, 202, 204, 208, 209, 213, 216: storage tanks, 203: stirring tank, 206, 211: condensers, 207, 212: gas-liquid separators, 214, 215: reboilers, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31: lines

(FIG. 15)

110, 400, 401, 402, 404, 407: storage tanks, 408: stirring tank, 405: condenser, 406: gas-liquid separator, 40, 41, 42, 43, 44, 45, 46: lines

(FIG. 16)

501, 504, 505: storage tanks, 502: packed column, 503: condenser, 507: gas-liquid separator, 506: reboiler, 51, 52, 53, 54: lines

(FIG. 17)

601, 603, 608, 612, 614: storage tanks, 602: thin film distillation apparatus, 604, 609: packed columns, 605, 610: condensers, 606, 611: gas-liquid separators, 607, 613: reboilers, 60, 61, 62, 63, 64, 65, 66, 67, 68, 69, 70, 71: lines

(FIG. 18)

1001, 1003, 1008, 1013, 1019: storage tanks, 1002: thin film distillation apparatus, 1004, 1009: packed columns,

1005, 1010, 1015: condensers, 1007, 1012, 1017: reboilers, 1006, 1011, 1016: gas-liquid separators, A1, A2, A3, A4, A5, A6, A7, A8, A9, A10, A11, A12, A13, A14, A15: lines

(FIG. 19)

1100, 1101, 1102, 1105: storage tanks, 1103: stirring tank, 1104: pressurized filtration apparatus, B0, B1, B2, B3: lines

(FIG. 20)

1201, 1205, 1207: storage tanks, 1202: packed column, 1204: gas-liquid separator, 1206: reboiler, C1, C2, C3, C4: lines

(FIG. 21)


1300, 1301, 1305, 1307: storage tanks, 1302: packed column, 1303: condenser, 1304: gas-liquid separator, D1, D2, D3, D4, D5, D6: lines

(FIG. 22)

1401: urea synthesis tube, 1402: high-pressure separator, 1403: condenser, E1, E2, E3, E4, E5, E6, E7, E8: lines

Claims

1. A method for producing at least one N-substituted carbamic acid-O-aryl ester wherein the N-substituted carbamic acid-O-aryl ester refers to an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-) are bonded to an aromatic ring derived from a compound having an ureido group represented by the following formula (1) and an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2), the method comprising the step of carrying out esterification or esterification and transesterification from the compound having the ureido group and the aromatic hydroxy composition:



wherein


R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number a of ureido group(s), and the a represents an integer of from 1 to 10, and ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at arbitrary location(s) that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and is substituted by at least one substituent, and the b represents an integer of from 1 to 6; wherein the at least one substituent is selected from

- (i) a hydrogen atom,
- (ii) a group composed of carbon atoms and hydrogen atoms which may also form a ring structure by bonding with ring A,
- (iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms, but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, or a carboxyl group,
- (iv) a halogen atom, and
- (v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, a carboxyl group, a NH₂ group, a NH group, a NOH group, a SH group, a SO₃H group or a SOH groups.

2. The production method according to Claim 1, wherein the compound having the ureido group is a compound having an ureido group obtained by a process comprising the following step A:

step (A): a step of obtaining at least one type of compound having an ureido group derived from an organic primary amine represented by the following formula (3) and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product


in the ureidation reaction:



wherein

R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number c of NH₂ group(s), and the c represents an integer of from 1 to 10.

3. The production method according to Claim 2, wherein the organic primary amine is an organic primary monoamine or an organic primary diamine.
4. The production method according to Claim 2, wherein the step (A) is carried out in the presence of water and/or alcohol and/or an aromatic hydroxyl composition containing at least one type of aromatic hydroxyl compound.
5. The production method according to Claim 2, wherein the step (A) is carried out in the presence of an aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2):



wherein

ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at an arbitrary location(s) that maintain aromatic properties, which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and may be substituted by other substituents, and the b represents an integer of from 1 to 6 ; and wherein the ammonia concentration is higher than 10ppm.


6. The production method according to Claim 2, wherein the step (A) is carried out in the presence of an alcohol represented by the following formula (4):



wherein

R² represents an aliphatic group, or an aliphatic group in which an aromatic group is bonded, which contains an integral number of carbon atoms within a range of from 1 to 14, and the OH group of the alcohol represented by formula (4) is an OH group that is not bonded to an aromatic ring.

7. A composition for transfer and storage of a compound having an ureido group, wherein the number of molecules of at least one type of aromatic hydroxy compound represented by the following formula (2) in an aromatic hydroxy composition that contains the aromatic hydroxy compound, based on the number of the ureido group contained in the compound having the ureido group represented by the following formula (1) in the composition, is an integer of from 1 to 100:



wherein


R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number a of ureido group(s), and the a represents an integer of from 1 to 10, and ring A represents an organic group, which contains an aromatic group substituted by number b of hydroxy group(s) at arbitrary location(s) that maintain aromatic properties, and which contains an integral number of carbon atoms within a range of from 6 to 50, may be a single or multiple heterocyclic ring, and is substituted by at least one substituent, and the b represents an integer of from 1 to 6; wherein the at least one substituent is selected from

- (i) a hydrogen atom,
- (ii) a group composed of carbon atoms and hydrogen atoms which may also form a ring structure by bonding with ring A,
- (iii) a group composed of carbon atoms, hydrogen atoms and oxygen atoms, but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, or a carboxyl group,
- (iv) a halogen atom, and
- (v) a group composed of atoms selected from carbon atoms, hydrogen atoms, oxygen atoms, nitrogen atoms, sulfur atoms and halogen atoms but excluding a carbonyl group, an ester group, a terminal methine group and an alcoholic OH group, a carboxyl group, a NH₂ group, a NH group, a NOH group, a SH group, a SO₃H group or a SOH group.

8. The production method according to Claim 1, further comprising the following steps (A) and (B):

step (A): a step of obtaining at least one type of compound having an ureido group derived from an organic primary amine represented by the following formula (3) as defined in claim 2 and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction, and

step (B): a step of obtaining N-substituted carbamic acid-O-aryl ester by reacting the at least one type of compound having the ureido group and the aromatic hydroxy composition containing at least one type of aromatic hydroxy compound represented by the following formula (2) as defined in Claim 1 in a liquid phase, and extracting ammonia formed as a by-product to a gaseous phase:



9. The production method according to Claim 1, further comprising the following steps (A), (R) and (P):

step (A): a step of obtaining at least one type of compound having an ureido group derived from an organic primary amine represented by the following formula (3) as defined in Claim 2 and urea by ureidating the organic primary amine and the urea in a liquid phase and eliminating or extracting to a gaseous phase ammonia formed as a by-product in the ureidation reaction,


step (R): a step of obtaining N-substituted carbamic acid-O-R² ester by reacting the at least one type of compound having the ureido group and an alcohol represented by the following formula (4) in a liquid phase and extracting ammonia formed as a by-product to a gaseous phase wherein the N-substituted carbamic acid-O-R² ester represents an N-substituted carbamic acid ester in which oxygen atoms of the carbamic acid group (-NHCOO-)

12. The production method according to Claim 8 or 9, comprising the following step (E) of recycling the recovered urea to the step (A):

step (E): a step of recycling urea recovered in step (D) to step (A).

13. The production method according to Claim 1, comprising the step of obtaining an isocyanate represented by the following formula (6), which is derived from the N-substituted carbamic acid-O-aryl ester, and an aromatic hydroxy composition by carrying out thermal decomposition on the N-substituted carbamic acid-O-aryl ester in the following step (F):

step (F): a step of obtaining an isocyanate and an aromatic hydroxy composition from the N-substituted carbamic acid-O-aryl ester:




wherein

R¹ represents an organic group containing an integral number of carbon atoms within a range of from 1 to 85, that is substituted by number s of NCO group(s), and the s represents an integer of from 1 to 10.

14. The production method according to Claim 8 or 9, comprising the step of obtaining an isocyanate represented by the following formula (6), which is derived from the N-substituted carbamic acid-O-aryl ester, and an aromatic hydroxy composition by carrying out thermal decomposition on the N-substituted carbamic acid-O-aryl ester in the following step (F):


step (F): a step of obtaining an isocyanate and an aromatic hydroxy composition from the N-substituted carbamic acid-O-aryl ester:



wherein

R¹ represents an organic group containing an integral number of carbon atom within a range of from 1 to 85, that is substituted by number s of NCO group(s), and the s represents an integer of from 1 to 10 ; and the step of separating the aromatic hydroxy composition obtained in the step (F) from the isocyanate, and recycling the aromatic hydroxy composition to the step (A) and/or the step (B), or to the step (A) and/or the step (R) and/or the step (P).

15. The production method according to any one of Claims 1, 8 and 9, wherein an aromatic hydroxy compound that composes the aromatic hydroxy composition is at least one type of aromatic hydroxy compound represented by the following formula (7):




(7)

wherein

ring A represents an aromatic ring selected from a benzene ring, a naphthalene ring and an anthracene ring, the OH groups and groups R⁷ to R¹⁴ respectively represent groups substituted at arbitrary location(s) that maintain aromatic properties of ring A, groups R⁷ to R¹⁴ may respectively and independently substitute ring A, groups R⁷ to R¹⁴ may bond together to form a ring with an aromatic ring by bonding to ring A, groups R⁷ to R¹⁴ respectively and independently represent a hydrogen atom, a halogen atom or a group selected from the group consisting of an alkyl group, an cycloalkyl group, an aryl group, an aryl group having a hydroxy group, an aralkyl group and an ether group which is a substituted and/or unsubstituted alkyl ether and/or substituted and/or unsubstituted aryl ether and/or substituted and/or unsubstituted aralkyl ether group, and/or a group to which one or more types of groups selected from the group are bonded, and/or a group to which one or more types of groups selected from the groups are bonded by saturated aliphatic bonds and/or ether bonds, and ring A and groups R⁷ to R¹⁴ are composed of an integral total number of carbon atoms within a range of from 6 to 50, b represents an integer of from 1 to 6, d, e, f, g, h, i, j and k represent integers of from 0 to 5, the value of d + e + f + g + h + i + j + k represents an integer equal to 6-b in the case ring A is the benzene ring, represents an integer equal to 8-b in the case ring A is the naphthalene ring, or represents an integer equal to 10-b in the case ring A is the anthracene ring, and a group selected from groups R⁷ to R¹⁴ as described above may be cyclically bonded to ring A by carbon-carbon bonds and/or ether bonds.

16. The composition for transfer and storage of the compound having the ureido group according to Claim 7, wherein the aromatic hydroxy compound that composes the aromatic hydroxy composition is at least one type of aromatic hydroxy compound represented by the following formula (7):



(7)

wherein

ring A represents an aromatic ring selected from a benzene ring, a naphthalene ring and an anthracene ring, the OH groups and groups R⁷ to R¹⁴ respectively represent groups substituted at arbitrary location(s) that maintain aromatic properties of ring A, groups R⁷ to R¹⁴ may respectively and independently substitute ring A, groups R⁷ to R¹⁴ may bond together to form a ring with an aromatic ring by bonding to ring A, groups R⁷ to R¹⁴ respectively and independently represent a hydrogen atom, halogen atom or group selected from the group consisting of an alkyl group, a cycloalkyl group, an aryl group, an aryl group having a hydroxy group, an aralkyl group and an ether group which is a substituted and/or unsubstituted alkyl ether and/or substituted and/or unsubstituted aryl ether and/or substituted and/or unsubstituted aralkyl ether group, and/or a group to which one or more types of groups selected from the group are bonded, and/or a group to which one or more types of groups selected from the group are bonded by saturated aliphatic bonds and/or ether bonds, and ring A and groups R⁷ to R¹⁴ are composed of an integral total number of carbon atoms within a range of from 6 to 50, b represents an integer of from 1 to 6, d, e, f, g, h, i, j and k represent integers of from 0 to 5, the value of d + e + f + g + h + i + j + k represents an integer equal to 6-b in the case ring A is the benzene ring, represents an integer equal to 8-b in the case ring A is the naphthalene ring, or represents an integer equal to 10-b in the case ring A is the anthracene ring, and a group selected from groups R⁷ to R¹⁴ as described above may be cyclically bonded to ring A by a carbon-carbon bonds and/or ether bonds.

17. The production method according to any one of Claims 2, 8 and 9, wherein the aromatic hydroxy compound that composes the aromatic hydroxy composition has a standard boiling point that differs by 10 °C or more from the standard boiling point of an isocyanate having a structure in which all amino groups of the organic primary amine, primary amino groups, are converted to isocyanate groups.

18. The production method according to any one of Claims 1, 8 and 9, wherein the aromatic hydroxy compound contained in the aromatic hydroxy composition is a monovalent and/or divalent aromatic hydroxy compound, namely that in which b is 1 and/or 2.


19. The composition for transfer and storage of the compound having the ureido group according to Claim 7, wherein

ganze Zahl von Kohlenstoffatomen in dem Bereich von 6 bis 50 enthält, ein einfacher oder mehrfacher heterocyclischer Ring sein kann und mit wenigstens einem Substituenten substituiert ist, und das b eine ganze Zahl von 1 bis 6 darstellt; wobei der wenigstens eine Substituent ausgewählt ist aus

- 5 (i) einem Wasserstoffatom,
 (ii) einer Gruppe bestehend aus Kohlenstoffatomen und Wasserstoffatomen, die durch Binden mit dem Ring A auch eine Ringstruktur bilden kann,
 (iii) einer Gruppe bestehend aus Kohlenstoffatomen, Wasserstoffatomen und Sauerstoffatomen, aber ausschließlich einer Carbonylgruppe, einer Estergruppe, einer terminalen Methingruppe und einer alkoholischen OH-Gruppe und einer Carboxygruppe,
 10 (iv) einem Halogenatom und
 (v) einer Gruppe bestehend aus Atomen ausgewählt aus Kohlenstoffatomen, Wasserstoffatomen, Sauerstoffatomen, Stickstoffatomen, Schwefelatomen und Halogenatomen, aber ausschließlich einer Carbonylgruppe, einer Estergruppe, einer terminalen Methingruppe und einer alkoholischen OH-Gruppe, einer Carboxygruppe, einer NH₂-Gruppe, einer NH-Gruppe, einer NOH-Gruppe, einer SH-Gruppe, einer SO₃H-Gruppe und einer SOH-Gruppe.

2. Herstellungsverfahren gemäß Anspruch 1, wobei die Verbindung mit der Ureidogruppe eine Verbindung mit einer Ureidogruppe ist, die durch ein Verfahren erhalten ist, das den nachstehenden Schritt A umfasst:


20 Schritt (A): ein Schritt des Erhaltens wenigstens eines Typs von Verbindung mit einer Ureidogruppe abgeleitet von einem organischen primären Amin, das durch die nachstehende Formel (3) dargestellt wird, und Harnstoff durch Ureidieren des primären organischenamins und des Harnstoffs in einer flüssigen Phase und Entfernen oder Extrahieren von Ammoniak, der als Nebenprodukt bei der Ureidierungsreaktion gebildet wird, in eine gasförmige Phase:



wobei

35 R¹ eine organische Gruppe mit einer ganzen Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 85 darstellt, die mit einer Anzahl c von NH₂-Gruppe(n) substituiert ist, und das c eine ganze Zahl von 1 bis 10 darstellt.

3. Herstellungsverfahren gemäß Anspruch 2, wobei das organische primäre Amin ein organisches primäres Monoamin oder ein organisches primäres Diamin ist.
- 40 4. Herstellungsverfahren gemäß Anspruch 2, wobei Schritt (A) in Gegenwart von Wasser und/oder Alkohol und/oder einer aromatischen Hydroxyzusammensetzung, die wenigstens einen Typ von aromatischer Hydroxyverbindung enthält, durchgeführt wird.
- 45 5. Herstellungsverfahren gemäß Anspruch 2, wobei Schritt (A) in Gegenwart einer aromatischen Hydroxyzusammensetzung durchgeführt wird, die wenigstens einen Typ von aromatischer Hydroxyverbindung enthält, der durch die nachstehende Formel (2) dargestellt wird:



wobei

Ring A eine organische Gruppe darstellt, die eine aromatische Gruppe enthält, die mit einer Anzahl b von Hydroxygruppe(n) an beliebigen Stellen substituiert ist, die aromatische Eigenschaften bewahren, und die eine ganze Zahl von Kohlenstoffatomen in dem Bereich von 6 bis 50 enthält, ein einfacher oder mehrfacher heterocyclischer Ring sein kann und mit anderen Substituenten substituiert sein kann, und das b eine ganze Zahl von 1 bis 6 darstellt;

und wobei die Ammoniakkonzentration höher als 10 ppm ist.


6. Herstellungsverfahren gemäß Anspruch 2, wobei Schritt (A) in Gegenwart eines Alkohols durchgeführt wird, der durch die nachstehende Formel (4) dargestellt wird:



wobei

R² eine aliphatische Gruppe oder eine aliphatische Gruppe darstellt, in die eine aromatische Gruppe gebunden ist, die eine ganze Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 14 enthält, und die OH-Gruppe des durch Formel (4) dargestellten Alkohols eine OH-Gruppe ist, die nicht an einen aromatischen Ring gebunden ist, darstellt.

7. Zusammensetzung für die Überführung und Lagerung einer Verbindung mit einer Ureidogruppe, wobei die Anzahl von Molekülen von wenigstens einem Typ von aromatischer Hydroxyverbindung, die durch die nachstehende Formel (2) dargestellt wird, in einer aromatischen Hydroxyzusammensetzung, die die aromatische Hydroxyverbindung enthält, bezogen auf die Zahl von Ureidogruppen, die in der durch die nachstehende Formel (1) dargestellten Verbindung mit der Ureidogruppe enthalten sind, in der Zusammensetzung eine ganze Zahl von 1 bis 100 ist:



wobei


R¹ eine organische Gruppe mit einer ganzen Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 85 darstellt, die mit einer Anzahl a von Ureidogruppe (n) substituiert ist, und das a eine ganze Zahl von 1 bis 10 darstellt, und Ring A eine organische Gruppe darstellt, die eine aromatische Gruppe enthält, die mit einer Anzahl b von Hydroxygruppe(n) an beliebigen Stellen substituiert ist, die aromatische Eigenschaften bewahren, und die eine ganze Zahl von Kohlenstoffatomen in dem Bereich von 6 bis 50 enthält, ein einfacher oder mehrfacher heterocyclischer Ring sein kann und mit wenigstens einem Substituenten substituiert ist, und das b eine ganze Zahl von 1 bis 6 darstellt; wobei der wenigstens eine Substituent ausgewählt ist aus

- (i) einem Wasserstoffatom,
- (ii) einer Gruppe bestehend aus Kohlenstoffatomen und Wasserstoffatomen, die durch Binden mit dem Ring A auch eine Ringstruktur bilden kann,
- (iii) einer Gruppe bestehend aus Kohlenstoffatomen, Wasserstoffatomen und Sauerstoffatomen, aber ausschließlich einer Carbonylgruppe, einer Estergruppe, einer terminalen Methingruppe und einer alkoholischen OH-Gruppe und einer Carboxygruppe,
- (iv) einem Halogenatom und
- (v) einer Gruppe bestehend aus Atomen ausgewählt aus Kohlenstoffatomen, Wasserstoffatomen, Sauerstoffatomen, Stickstoffatomen, Schwefelatomen und Halogenatomen, aber ausschließlich einer Carbonylgruppe, einer Estergruppe, einer terminalen Methingruppe und einer alkoholischen OH-Gruppe, einer Carboxygruppe, einer NH₂-Gruppe, einer NH-Gruppe, einer NOH-Gruppe, einer SH-Gruppe, einer SO₃H-Gruppe und einer SOH-Gruppe.

8. Herstellungsverfahren gemäß Anspruch 1, ferner umfassend die nachstehenden Schritte (A) und (B):

Schritt (A): ein Schritt des Erhaltens wenigstens eines Typs von Verbindung mit einer Ureidogruppe abgeleitet von einem organischen primären Amin, das durch die nachstehende Formel (3) gemäß Anspruch 2 dargestellt wird, und Harnstoff durch Ureidieren des primären organischenamins und des Harnstoffs in einer flüssigen Phase und Entfernen oder Extrahieren von Ammoniak, der als Nebenprodukt bei der Ureidierungsreaktion gebildet wird, in eine gasförmige Phase, und

Schritt (B): ein Schritt des Erhaltens von N-substituiertem Carbaminsäure-O-arylester durch Umsetzen des wenigstens eines Typs von Verbindung mit einer Ureidogruppe und der aromatischen Hydroxyzusammensetzung, die wenigstens einen Typ von aromatischer Hydroxyverbindung enthält, der durch die nachstehende Formel (2) gemäß Anspruch 1 dargestellt wird, in einer flüssigen Phase, und Extrahieren von Ammoniak, der als Nebenprodukt gebildet wird, in eine gasförmige Phase:




9. Herstellungsverfahren gemäß Anspruch 1, ferner umfassend die nachstehenden Schritte (A), (R) und (P) :

Schritt (A): ein Schritt des Erhaltens wenigstens eines Typs von Verbindung mit einer Ureidogruppe abgeleitet von einem organischen primären Amin, das durch die nachstehende Formel (3) gemäß Anspruch 2 dargestellt wird, und Harnstoff durch Ureidieren des primären organischenamins und des Harnstoffs in einer flüssigen Phase und Entfernen oder Extrahieren von Ammoniak, der als Nebenprodukt bei der Ureidierungsreaktion gebildet wird, in eine gasförmige Phase,

Schritt (R): ein Schritt des Erhaltens eines N-substituierten Carbaminsäure-O-R²-esters durch Umsetzen des wenigstens eines Typs von Verbindung mit einer Ureidogruppe und eines durch die nachstehende Formel (4) dargestellten Alkohols in einer flüssigen Phase und Extrahieren von Ammoniak, der als Nebenprodukt gebildet wird, in eine gasförmige Phase wobei der N-substituierte Carbaminsäure-O-R²-ester einen N-substituierten Carbaminsäureester darstellt, bei dem Sauerstoffatome der Carbaminsäuregruppe (-NHCOO-) an eine von einem Alkohol abgeleitete R²-Gruppe gebunden sind, und

Schritt (P): ein Schritt des Erhaltens eines N-substituierten Carbaminsäure-O-arylestere durch Umsetzen des N-substituierten Carbaminsäure-O-R²-esters und der aromatischen Hydroxyzusammensetzung, die wenigstens einen Typ von aromatischer Hydroxyverbindung enthält, der durch die nachstehende Formel (2) gemäß Anspruch 1 dargestellt wird, in einer flüssigen Phase, und Extrahieren von Ammoniak, der als Nebenprodukt gebildet wird, in eine gasförmige Phase:




wobei

R² eine aliphatische Gruppe oder eine aliphatische Gruppe darstellt, in die eine aromatische Gruppe gebunden ist, die eine ganze Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 14 enthält, und die OH-Gruppe des durch Formel (4) dargestellten Alkohols eine OH-Gruppe ist, die nicht an einen aromatischen Ring gebunden ist.

10. Herstellungsverfahren gemäß Anspruch 8 oder 9, wobei das organische primäre Amin ein aromatisches organisches primäres Monoamin ist, das von der nachstehenden Formel (5) dargestellt wird, der nachfolgende Schritt (C) nach Schritt (B), nach Schritt (R) oder nach Schritt (P) durchgeführt wird, und N-substituierter Carbaminsäure-O-(R²- oder aryl)ester, bei dem wenigstens zwei Moleküle des N-substituierten Carbaminsäure-O-(R²- oder aryl)esters mit einer

Methylengruppe (-CH₂-) vernetzt sind, aus dem bei Schritt (B), Schritt (R) oder Schritt (P) erhaltenen N-substituierten Carbaminsäure-O-(R²- oder aryl)ester erhalten wird:

Schritt (C): ein Schritt des Erhaltens eines N-substituierten Carbaminsäure-O-(R²- oder aryl)esters, bei dem wenigstens zwei Moleküle des N-substituierten Carbaminsäure-O-(R²- oder aryl)esters mit einer Methylengruppe (-CH₂-) vernetzt sind, durch Umsetzen des N-substituierten Carbaminsäure-O-(R²- oder aryl)esters mit Formaldehyd oder einem methylenierenden Vernetzungsmittels und vernetzenden aromatischen Gruppen, die von dem aromatischen organischen primären Monoamin abgeleitet sind, das in dem N-substituierten Carbaminsäure-O-(R²- oder aryl)ester enthalten ist, mit der Methylengruppe (-CH₂-), wobei der N-substituierte Carbaminsäure-O-(R²- oder aryl)ester einen N-substituierten Carbaminsäure-O-R²-ester oder einen N-substituierten Carbaminsäure-O-arylester darstellt:



(5)

wobei

wenigstens ein Ort an der ortho-Position und/oder para-Position der NH₂-Gruppe oder einem durch Formel (5) dargestellten aromatischen organischen primären Monoamin nicht substituiert ist, Gruppen R³ bis R⁶ jeweils eine Gruppe darstellen, die an einer beliebigen Stelle substituiert ist, die aromatische Eigenschaften des Rings bewahrt, Gruppen R³ bis R⁶ jeweils und unabhängig einen aromatischen Ring substituieren können oder Gruppen R³ bis R⁶ miteinander verbunden sein können, um mit einem aromatischen Ring einen Ring zu bilden, Gruppen R³ bis R⁶ Wasserstoffatome oder Gruppen ausgewählt aus der Gruppe sind, die aus Gruppen besteht, bei denen eine Gruppe ausgewählt aus der Gruppe bestehend aus einer Alkylgruppe, einer Cycloalkylgruppe, einer Arylgruppe und einer Arylgruppe mit einer Hydroxygruppe durch gesättigte aliphatische Bindungen und/oder Etherbindungen gebunden sind, wobei die Zahl von Kohlenstoffatomen von Gruppen R³ bis R⁶ eine ganze Zahl in einem Bereich von 0 bis 7 ist und die Gesamtzahl von Kohlenstoffatomen, die das durch Formel (5) dargestellte aromatische organische primäre Monoamin bilden, eine ganze Zahl von 6 bis 13 ist.

11. Herstellungsverfahren gemäß Anspruch 8 oder 9, umfassend den Schritt des Gewinnens von Harnstoff durch Durchführen des nachstehenden Schritts (D) vor Schritt (B) oder Schritt (P) und/oder gleichzeitig mit Schritt (B) oder Schritt (P):


Schritt (D): ein Schritt des Entfernens von Harnstoff durch Destillation oder Sublimation.

12. Herstellungsverfahren gemäß Anspruch 8 oder 9, umfassend den nachstehenden Schritt (E) des Rückführens des gewonnenen Harnstoffs zu Schritt (A):

Schritt (E): ein Schritt des Rückführens von bei Schritt (D) gewonnenem Harnstoff zu Schritt (A).

13. Herstellungsverfahren gemäß Anspruch 1, umfassend den Schritt des Erhaltens eines durch die nachstehende Formel (6) dargestellten Isocyanats, das von dem N-substituierten Carbaminsäure-O-arylester abgeleitet ist, und einer aromatischen Hydroxyverbindung durch Durchführen von thermischer Zersetzung des N-substituierten Carbaminsäure-O-arylestere bei dem nachstehenden Schritt (F):

Schritt (F): ein Schritt des Erhaltens eines Isocyanats und einer aromatischen Hydroxyzusammensetzung aus dem N-substituierten Carbaminsäure-O-arylester:



wobei

R¹ eine organische Gruppe mit einer ganzen Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 85 darstellt, die mit einer Anzahl s von NCO-Gruppe (n) substituiert ist, und das s eine ganze Zahl von 1 bis 10 darstellt.

- 5 14. Herstellungsverfahren gemäß Anspruch 8 oder 9, umfassend den Schritt des Erhaltens eines durch die nachstehende Formel (6) dargestellten Isocyanats, das von dem N-substituierten Carbaminsäure-O-arylester abgeleitet ist, und einer aromatischen Hydroxyverbindung durch Durchführen von thermischer Zersetzung des N-substituierten Carbaminsäure-O-arylestere bei dem nachstehenden Schritt (F):

10 Schritt (F): ein Schritt des Erhaltens eines Isocyanats und einer aromatischen Hydroxyzusammensetzung aus dem N-substituierten Carbaminsäure-O-arylester:




wobei

20 R¹ eine organische Gruppe mit einer ganzen Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 85 darstellt, die mit einer Anzahl s von NCO-Gruppe(n) substituiert ist, und das s eine ganze Zahl von 1 bis 10 darstellt;

25 und den Schritt des Abtrennens der bei Schritt (F) erhaltenen aromatischen Hydroxyzusammensetzung von dem Isocyanat und Rückführen der aromatischen Hydroxyzusammensetzung zu Schritt (A) und/oder Schritt (B) oder zu Schritt (A) und/oder Schritt (R) und/oder Schritt (P).

- 30 15. Herstellungsverfahren gemäß einem der Schritte 1, 8 und 9, wobei eine aromatische Hydroxyverbindung, die die aromatische Hydroxyzusammensetzung bildet, wenigstens ein Typ von aromatischer Hydroxyzusammensetzung ist, die durch die nachstehende Formel (7) dargestellt wird:



wobei

40 Ring A einen aromatischen Ring ausgewählt aus einem Benzolring, einem Naphthalinring und einem Anthracenring darstellt, die OH-Gruppen und die Gruppen R⁷ bis R¹⁴ jeweils Gruppen darstellen, die an beliebigen Stellen substituiert sind, die aromatische Eigenschaften von Ring A bewahren, Gruppen R⁷ bis R¹⁴ jeweils und unabhängig Ring A substituieren können, Gruppen R⁷ bis R¹⁴ miteinander verbunden sein können, um durch Binden an Ring A einen Ring mit einem aromatischen Ring zu bilden, Gruppen R⁷ bis R¹⁴ jeweils unabhängig ein Wasserstoffatom, ein Halogenatom oder eine Gruppe ausgewählt aus der Gruppe bestehend aus einer Alkylgruppe, einer Cycloalkylgruppe, einer Arylgruppe und einer Arylgruppe mit einer Hydroxygruppe, einer Aralkylgruppe und einer Ethergruppe, die eine substituierte und/oder unsubstituierte Alkylether- und/oder substituierte und/oder unsubstituierte Arylether- und/oder substituierte und/oder unsubstituierte Aralkylethergruppe ist, und/oder eine Gruppe, an die ein oder mehrere Typen von Gruppen ausgewählt aus den Gruppen gebunden sind, und/oder eine Gruppe, an die ein oder mehrere Typen von Gruppen ausgewählt aus den Gruppen durch gesättigte aliphatische Bindungen und/oder Etherbindungen gebunden sind, und Ring A und Gruppen R⁷ bis R¹⁴ aus einer ganzen Gesamtzahl von Kohlenstoffatomen in einem Bereich von 6 bis 50 bestehen,


45 b eine ganze Zahl von 1 bis 6 darstellt, d, e, f, g, h, i, j und k ganze Zahlen von 0 bis 5 darstellen, der Wert von d + e + f + g + h + i + j + k eine ganze Zahl gleich 6-b darstellt, wenn Ring A der Benzolring ist, eine ganze Zahl gleich 8-b darstellt, wenn Ring A der Naphthalinring ist und ganze Zahl gleich 10-b darstellt, wenn Ring A der

50

55

Anthracenring ist, und eine Gruppe ausgewählt aus den vorstehend beschriebenen Gruppen R^7 bis R^{14} durch Kohlenstoff-Kohlenstoff-Bindungen und/oder Etherbindungen cyclisch an Ring A gebunden sein kann.

16. Zusammensetzung für die Überführung und Lagerung der Verbindung mit der Ureidogruppe gemäß Anspruch 7, wobei die aromatische Hydroxyverbindung, die die aromatische Hydroxyzusammensetzung bildet, wenigstens ein Typ von aromatischer Hydroxyzusammensetzung ist, die durch die nachstehende Formel (7) dargestellt wird:



(7)

wobei

Ring A einen aromatischen Ring ausgewählt aus einem Benzolring, einem Naphthalinring und einem Anthracenring darstellt, die OH-Gruppen und die Gruppen R^7 bis R^{14} jeweils Gruppen darstellen, die an beliebigen Stellen substituiert sind, die aromatische Eigenschaften von Ring A bewahren, Gruppen R^7 bis R^{14} jeweils unabhängig Ring A substituieren können, Gruppen R^7 bis R^{14} miteinander verbunden sein können, um durch Binden an Ring A einen Ring mit einem aromatischen Ring zu bilden, Gruppen R^7 bis R^{14} jeweils unabhängig ein Wasserstoffatom, ein Halogenatom oder eine Gruppe ausgewählt aus der Gruppe bestehend aus einer Alkylgruppe, einer Cycloalkylgruppe, einer Arylgruppe und einer Arylgruppe mit einer Hydroxygruppe, einer Aralkylgruppe und einer Ethergruppe, die eine substituierte und/oder unsubstituierte Alkylether- und/oder substituierte und/oder unsubstituierte Arylether- und/oder substituierte und/oder unsubstituierte Aralkylethergruppe ist, und/oder eine Gruppe, an die ein oder mehrere Typen von Gruppen ausgewählt aus den Gruppen gebunden sind, und/oder eine Gruppe, an die ein oder mehrere Typen von Gruppen ausgewählt aus den Gruppen durch gesättigte aliphatische Bindungen und/oder Etherbindungen gebunden sind, und Ring A und Gruppen R^7 bis R^{14} aus einer ganzen Gesamtzahl von Kohlenstoffatomen in einem Bereich von 6 bis 50 bestehen, b eine ganze Zahl von 1 bis 6 darstellt, d, e, f, g, h, i, j und k ganze Zahlen von 0 bis 5 darstellen, der Wert von $d + e + f + g + h + i + j + k$ eine ganze Zahl gleich $6 - b$ darstellt, wenn Ring A der Benzolring ist, eine ganze Zahl gleich $8 - b$ darstellt, wenn Ring A der Naphthalinring ist und ganze Zahl gleich $10 - b$ darstellt, wenn Ring A der Anthracenring ist, und eine Gruppe ausgewählt aus den vorstehend beschriebenen Gruppen R^7 bis R^{14} durch Kohlenstoff-Kohlenstoff-Bindungen und/oder Etherbindungen cyclisch an Ring A gebunden sein kann.

17. Herstellungsverfahren gemäß einem der Ansprüche 2, 8 und 9, wobei die aromatische Hydroxyverbindung, die die aromatische Hydroxyzusammensetzung bildet, einen Standard-Siedepunkt aufweist, der sich um 10°C oder mehr von dem Standard-Siedepunkt eines Isocyanats unterscheidet, das eine Struktur aufweist, bei der alle Aminogruppen des organischen primären Amins, primäre Aminogruppen, in Isocyanatgruppen umgewandelt sind.

18. Herstellungsverfahren gemäß einem der Ansprüche 1, 8 und 9, wobei die aromatische Hydroxyverbindung, die in der aromatischen Hydroxyzusammensetzung enthalten ist, eine einwertige und/oder zweiwertige aromatische Hydroxyverbindung ist, nämlich jene, bei der b 1 und/oder 2 ist.

19. Zusammensetzung für die Überführung und Lagerung der Verbindung mit der Ureidogruppe gemäß Anspruch 7, wobei die aromatische Hydroxyverbindung, die in der aromatischen Hydroxyzusammensetzung enthalten ist, eine einwertige und/oder zweiwertige aromatische Hydroxyverbindung ist, nämlich jene, bei der b 1 und/oder 2 ist.

20. Herstellungsverfahren gemäß Anspruch 18, umfassend den Schritt des Erhaltens eines durch die nachstehende Formel (6) dargestellten Isocyanats, das von dem N-substituierten Carbaminsäure-O-arylester abgeleitet ist, und einer aromatischen Hydroxyverbindung durch Durchführen von thermischer Zersetzung des N-substituierten Carbaminsäure-O-arylestere bei dem nachstehenden Schritt (F):

Schritt (F): ein Schritt des Erhaltens eines Isocyanats und einer aromatischen Hydroxyzusammensetzung aus dem N-substituierten Carbaminsäure-O-arylester:



wobei

5 R^1 eine organische Gruppe mit einer ganzen Zahl von Kohlenstoffatomen in dem Bereich von 1 bis 85 darstellt, die mit einer Anzahl s von NCO-Gruppe(n) substituiert ist, und das s eine ganze Zahl von 1 bis 10 darstellt; und
 10 Rückführen von nicht umgesetztem N-substituiertem Carbaminsäure-O-arylester, der bei Schritt (F) nicht thermisch zersetzt worden ist, zu Schritt (A) und/oder Schritt (B) und/oder Schritt (R) und/oder Schritt (P) und/oder Schritt (F).

21. Herstellungsverfahren gemäß Anspruch 8 oder 9, ferner umfassend den nachstehenden Schritt (G) des Gewinnens von Ammoniak, der als Nebenprodukt bei Schritt (A) und/oder Schritt (B) und/oder Schritt (R) gebildet wird; Regenerieren von Harnstoff durch Umsetzen des Ammoniaks mit Kohlendioxid; und Rückführen des Harnstoffs zu Schritt (A):
 15 (A):


Schritt (G): ein Schritt des Gewinnens von als Nebenprodukt gebildetem Ammoniak, Regenerierens von Harnstoff durch Umsetzen des Ammoniaks mit Kohlendioxid und Rückführens des Harnstoffs zu Schritt (A).

20

Revendications

1. Procédé de production d'au moins un ester (acide carbamique N-substitué)-O-aryle dans lequel l'ester (acide carbamique N-substitué)-O-aryle désigne un ester d'acide carbamique N-substitué dans lequel les atomes d'oxygène du groupe acide carbamique groupe (-NHCOO-) sont liés à un cycle aromatique dérivé d'un composé ayant un groupe uréido représenté par la formule suivante (1) et une composition hydroxy-aromatique contenant au moins un type de composé hydroxy-aromatique représenté par la formule suivante (2), le procédé comprenant l'étape de conduite d'une estérification ou d'une estérification et une transestérification à partir du composé ayant le groupe uréido et la composition hydroxy-aromatique :
 25

30



35

où

40

R^1 représente un groupe organique contenant un nombre entier d'atomes de carbone dans une plage de 1 à 85, qui est substitué par un nombre a de groupe(s) uréido, et le a représente un entier de 1 à 10, et le cycle A représente un groupe organique, qui contient un groupe aromatique substitué par un nombre b de groupe(s) hydroxy à un ou plusieurs emplacement(s) arbitraire(s) qui maintiennent les propriétés aromatiques, et qui contient un nombre entier d'atomes de carbone dans une plage de 6 à 50, peut être un cycle hétérocyclique unique ou multiple, et est substitué par au moins un substituant, et le b représente un entier de 1 à 6 ; où l'au moins un substituant est choisi parmi
 45


- (i) un atome d'hydrogène,
- 50 (ii) un groupe composé d'atomes de carbone et d'atomes d'hydrogène qui peut également former une structure cyclique par liaison avec le cycle A,
- (iii) un groupe composé d'atomes de carbone, d'atomes d'hydrogène et d'atomes d'oxygène, mais en excluant un groupe carbonyle, un groupe ester, un groupe méthine terminal et un groupe alcoolique OH, ou un groupe carboxyle,
- 55 (iv) un atome d'halogène, et
- (v) un groupe composé d'atomes choisis parmi des atomes de carbone, des atomes d'hydrogène, des atomes d'oxygène, des atomes d'azote, des atomes de soufre et des atomes d'halogène mais en excluant un groupe carbonyle, un groupe ester, un groupe méthine terminal et un groupe alcoolique OH, un groupe

EP 2 322 504 B9

carboxyle, un groupe NH_2 , un groupe NH , un groupe NOH , un groupe SH , un groupe SO_3H ou un groupe SOH .


2. Procédé de production selon la revendication 1, dans lequel le composé ayant le groupe uréido est un composé ayant un groupe uréido obtenu par un procédé comprenant l'étape suivante A :

étape (A) : étape d'obtention au moins un type de composé ayant un groupe uréido dérivé d'une amine primaire organique représentée par la formule suivante (3) et d'urée par uréidation de l'amine primaire organique et de l'urée dans une phase liquide et élimination ou extraction dans une phase gazeuse de l'ammoniac formé en tant que sous-produit dans la réaction d'uréidation :



où R^1 représente un groupe organique contenant un nombre entier d'atomes de carbone dans une plage de 1 à 85, qui est substitué par un nombre c de groupe(s) NH_2 , et le c représente un entier de 1 à 10.

3. Procédé de production selon la revendication 2, dans lequel l'amine primaire organique est une monoamine organique primaire ou une diamine organique primaire.
4. Procédé de production selon la revendication 2, dans lequel l'étape (A) est conduite en présence d'eau et/ou d'alcool et/ou une composition hydroxy-aromatique contenant au moins un type de composé hydroxy-aromatique.
5. Procédé de production selon la revendication 2, dans lequel l'étape (A) est conduite en présence d'une composition hydroxy-aromatique contenant au moins un type de composé hydroxy-aromatique représenté par la formule suivante (2) :



où le cycle A représente un groupe organique, qui contient un groupe aromatique substitué par un nombre b de groupe(s) hydroxy à un ou plusieurs emplacement(s) arbitraire(s) qui maintiennent les propriétés aromatiques, qui contient un nombre entier d'atomes de carbone dans une plage de 6 à 50, peut être un cycle hétérocyclique unique ou multiple, et peut être substitué par d'autres substituants, et le b représente un entier de 1 à 6 ; et dans lequel la concentration d'ammoniac est supérieure à 10 ppm.

6. Procédé de production selon la revendication 2, dans lequel l'étape (A) est conduite en présence d'un alcool représenté par la formule suivante (4) :



dans lequel R^2 représente un groupe aliphatique, ou un groupe aliphatique dans lequel un groupe aromatique est lié, qui contient un nombre entier d'atomes de carbone dans une plage de 1 à 14, et le groupe OH de l'alcool représenté par la formule (4) est un groupe OH qui n'est pas lié à un cycle aromatique.


7. Composition pour le transfert et le stockage d'un composé ayant un groupe uréido, dans laquelle le nombre de

EP 2 322 504 B9

molécules d'au moins un type de composé hydroxy-aromatique représenté par la formule suivante (2) dans une composition hydroxy-aromatique qui contient le composé hydroxy-aromatique, sur la base du nombre du groupe uréido contenu dans le composé ayant le groupe uréido représenté par la formule suivante (1) dans la composition, est un entier de 1 à 100 :

5

10



où

15

R¹ représente un groupe organique contenant un nombre entier d'atomes de carbone dans une plage de 1 à 85, qui est substitué par un nombre a de groupe(s) uréido, et le a représente un entier de 1 à 10, et le cycle A représente un groupe organique, qui contient un groupe aromatique substitué par un nombre b de groupe(s) hydroxy à un ou plusieurs emplacement(s) arbitraire(s) qui maintiennent les propriétés aromatiques, et qui contient un nombre entier d'atomes de carbone dans une plage de 6 à 50, peut être un cycle hétérocyclique unique ou multiple, et est substitué par au moins un substituant, et le b représente un entier de 1 à 6 ; où l'au moins un substituant est choisi parmi

20

25

30

- (i) un atome d'hydrogène,
- (ii) un groupe composé d'atomes de carbone et d'atomes d'hydrogène qui peut également former une structure cyclique par liaison au cycle A,
- (iii) un groupe composé d'atomes de carbone, d'atomes d'hydrogène et d'atomes d'oxygène, mais en excluant un groupe carbonyle, un groupe ester, un groupe méthine terminal et un groupe alcoolique OH, ou un groupe carboxyle,
- (iv) un atome d'halogène, et
- (v) un groupe composé d'atomes choisis parmi des atomes de carbone, des atomes d'hydrogène, des atomes d'oxygène, des atomes d'azote, des atomes de soufre et des atomes d'halogène mais en excluant un groupe carbonyle, un groupe

35

ester, un groupe méthine terminal et un groupe alcoolique OH, un groupe carboxyle, un groupe NH₂, un groupe NH, un groupe NOH, un groupe SH, un groupe SO₃H ou un groupe SOH.

8. Procédé de production selon la revendication 1, comprenant en outre les étapes suivantes (A) et (B) :


40

étape (A) : une étape d'obtention d'au moins un type de composé ayant un groupe uréido dérivé d'une amine primaire organique représentée par la formule suivante (3) telle que définie dans la revendication 2 et d'urée par uréidation de l'amine primaire organique et de l'urée dans une phase liquide et élimination ou extraction dans une phase gazeuse de l'ammoniac formé en tant que sous-produit dans la réaction d'uréidation, et

45

étape (B) : une étape d'obtention d'un ester (acide carbamique N-substitué)-O-aryle par réaction de l'au moins un type de composé ayant le groupe uréido et de la composition hydroxy-aromatique contenant au moins un type de composé hydroxy-aromatique représenté par la formule suivante (2) telle que définie dans la revendication 1 dans une phase liquide, et extraction de l'ammoniac formé en tant que sous-produit dans une phase gazeuse :

50



55

9. Procédé de production selon la revendication 1, comprenant en outre les étapes suivantes (A), (R) et (P) :

aryle et un groupe aryle ayant un groupe hydroxy est lié par des liaisons aliphatiques saturées et/ou des liaisons éther, le nombre d'atomes de carbone des groupes R³ à R⁶ est un nombre entier dans une plage de 0 à 7, et un nombre total d'atomes de carbone qui constituent la monoamine primaire organique aromatique représentée par la formule (5) est un entier de 6 à 13.

5

11. Procédé de production selon la revendication 8 ou 9, comprenant l'étape de récupération d'urée par conduite de l'étape suivante (D) avant l'étape (B) ou l'étape (P) et/ou en même temps que l'étape (B) ou l'étape (P) :

étape (D) : une étape d'élimination d'urée par distillation ou sublimation.

10

12. Procédé de production selon la revendication 8 ou 9, comprenant l'étape suivante (E) de recyclage de l'urée récupérée vers l'étape (A) :

étape (E) : une étape de recyclage de l'urée récupérée dans l'étape (D) vers l'étape (A).


15

13. Procédé de production selon la revendication 1, comprenant l'étape d'obtention d'un isocyanate représenté par la formule suivante (6), qui est dérivé de l'ester (acide carbamique N-substitué)-O-aryle, et d'une composition hydroxy-aromatique par conduite d'une décomposition thermique sur l'ester (acide carbamique N-substitué)-O-aryle dans l'étape suivante (F) :

20

étape (F) : une étape d'obtention d'un isocyanate et d'une composition hydroxy-aromatique à partir de l'ester (acide carbamique N-substitué)-O-aryle :

25



30

où

R¹ représente un groupe organique contenant un nombre entier d'atomes de carbone dans une plage de 1 à 85, qui est substitué par un nombre s de groupe (s) NCO, et le s représente un entier de 1 à 10.


35

14. Procédé de production selon la revendication 8 ou 9, comprenant l'étape d'obtention d'un isocyanate représenté par la formule suivante (6), qui est dérivé de l'ester (acide carbamique N-substitué)-O-aryle, et une composition hydroxy-aromatique par conduite d'une décomposition thermique sur l'ester (acide carbamique N-substitué)-O-aryle dans l'étape suivante (F) :

40

étape (F) : une étape d'obtention d'un isocyanate et d'une composition hydroxy-aromatique à partir de l'ester (acide carbamique N-substitué)-O-aryle :

45




50

où

R¹ représente un groupe organique contenant un nombre entier d'atomes de carbone dans une plage de 1 à 85, qui est substitué par un nombre s de groupe (s) NCO, et le s représente un entier de 1 à 10 ; et l'étape de séparation de la composition hydroxy-aromatique obtenue dans l'étape (F) à partir de l'isocyanate, et recyclage de la composition hydroxy-aromatique vers l'étape (A) et/ou l'étape (B), ou vers l'étape (A) et/ou l'étape (R) et/ou l'étape (P).

55

15. Procédé de production selon l'une quelconque des revendications 1, 8 et 9, dans lequel un composé hydroxy-aromatique qui constitue la composition hydroxy-aromatique est au moins un type de composé hydroxy-aromatique représenté par la formule suivante (7) :




(7)

où

le cycle A représente un cycle aromatique choisi parmi un cycle benzène, un cycle naphthalène et un cycle anthracène, les groupes OH et les groupes R⁷ à R¹⁴ représentent respectivement des groupes substitués à un ou plusieurs emplacement(s) arbitraire(s) qui maintiennent les propriétés aromatiques du cycle A, les groupes R⁷ à R¹⁴ peuvent, respectivement et indépendamment, substituer le cycle A, les groupes R⁷ à R¹⁴ peuvent se lier conjointement pour former un cycle avec un cycle aromatique par liaison au cycle A, les groupes R⁷ à R¹⁴, respectivement et indépendamment, représentent un atome d'hydrogène, un atome d'halogène ou un groupe choisi dans le groupe constitué d'un groupe alkyle, un groupe cycloalkyle, un groupe aryle, un groupe aryle ayant un groupe hydroxy, un groupe aralkyle et un groupe éther qui est un groupe éther d'alkyle substitué et/ou non substitué et/ou un éther d'aryle substitué et/ou non substitué et/ou un éther d'aralkyle substitué et/ou non substitué et/ou un groupe auquel un ou plusieurs types de groupes choisis dans le groupe sont liés, et/ou un groupe auquel un ou plusieurs types de groupes choisis dans le groupe sont liés par des liaisons aliphatiques saturées et/ou des liaisons éther, et le cycle A et les groupes R⁷ à R¹⁴ sont composés d'un nombre total entier d'atomes de carbone dans une plage de 6 à 50,

b représente un entier de 1 à 6, d, e, f, g, h, i, j et k représentent des entiers de 0 à 5, la valeur de d + e + f + g + h + i + j + k représente un entier égal à 6-b dans le cas où le cycle A est le cycle benzène, représente un entier égal à 8-b dans le cas où le cycle A est le cycle naphthalène, ou représente un entier égal à 10-b dans le cas où le cycle A est le cycle anthracène, et un groupe choisi parmi les groupes R⁷ à R¹⁴ tels que décrits ci-dessus peut être lié de façon cyclique au cycle A par des liaisons carbone-carbone et/ou des liaisons éther.

16. Composition pour le transfert et le stockage du composé ayant le groupe uréido selon la revendication 7, dans laquelle le composé hydroxy-aromatique qui constitue la composition hydroxy-aromatique est au moins un type de composé hydroxy-aromatique représenté par la formule suivante (7) :



(7)

où


le cycle A représente un cycle aromatique choisi parmi un cycle benzène, un cycle naphthalène et un cycle anthracène, les groupes OH et les groupes R⁷ à R¹⁴ représentent respectivement des groupes substitués à un ou plusieurs emplacement(s) arbitraire(s) qui maintiennent les propriétés aromatiques du cycle A, les groupes R⁷ à R¹⁴ peuvent, respectivement et indépendamment, substituer le cycle A, les groupes R⁷ à R¹⁴ peuvent se lier conjointement pour former un cycle avec un cycle aromatique par liaison au cycle A, les groupes R⁷ à R¹⁴ représentent, respectivement et indépendamment, un atome d'hydrogène, un atome d'halogène ou un groupe choisi dans le groupe constitué d'un groupe alkyle, un groupe cycloalkyle, un groupe aryle, un groupe aryle ayant un groupe hydroxy, un groupe aralkyle et un groupe éther qui est un groupe éther d'alkyle substitué et/ou non substitué et/ou un éther d'aryle substitué et/ou non substitué et/ou un éther d'aralkyle substitué et/ou non substitué et/ou un groupe auquel un ou plusieurs types de groupes choisis dans le groupe sont liés, et/ou un groupe auquel un ou plusieurs types de groupes choisis dans le groupe sont liés par des liaisons aliphatiques saturées et/ou des liaisons éther, et le cycle A et les groupes R⁷ à R¹⁴ sont composés d'un nombre total entier d'atomes de carbone dans une plage de 6 à 50,

b représente un entier de 1 à 6, d, e, f, g, h, i, j et k représentent des entiers de 0 à 5, la valeur de d + e + f + g + h + i + j + k représente un entier égal à 6-b dans le cas où le cycle A est le cycle benzène, représente un

entier égal à 8-b dans le cas où le cycle A est le cycle naphthalène, ou représente un entier égal à 10-b dans le cas où le cycle A est le cycle anthracène, et un groupe choisi parmi les groupes R⁷ à R¹⁴ tels que décrits ci-dessus peut être lié de façon cyclique au cycle A par des liaisons carbone-carbone et/ou des liaisons éther.

- 5 17. Procédé de production selon l'une quelconque des revendications 2, 8 et 9, dans lequel le composé hydroxy-aromatique qui constitue la composition hydroxy-aromatique a un point d'ébullition standard qui diffère de 10 °C ou plus du point d'ébullition standard d'un isocyanate ayant une structure dans laquelle tous les groupes amino de l'amine primaire organique, les groupes amino primaires, sont convertis en groupes isocyanate.
- 10 18. Procédé de production selon l'une quelconque des revendications 1, 8 et 9, dans lequel le composé hydroxy-aromatique contenu dans la composition hydroxy-aromatique est un composé hydroxy-aromatique monovalent et/ou divalent, à savoir celui dans lequel b est 1 et/ou 2.
- 15 19. Composition pour le transfert et le stockage du composé ayant le groupe uréido selon la revendication 7, dans laquelle le composé hydroxy-aromatique contenu dans la composition hydroxy-aromatique est un composé hydroxy-aromatique monovalent et/ou divalent, à savoir celui dans lequel b est 1 et/ou 2.
- 20 20. Procédé de production selon la revendication 18, comprenant l'étape d'obtention d'un isocyanate représenté par la formule suivante (6), qui est dérivé de l'ester (acide carbamique N-substitué)-O-aryle, et d'une composition hydroxy-aromatique par conduite de la décomposition thermique sur l'ester (acide carbamique N-substitué)-O-aryle dans l'étape suivante (F) :

25 étape (F) : une étape d'obtention d'un isocyanate et d'une composition hydroxy-aromatique à partir de l'ester (acide carbamique N-substitué)-O-aryle :



où

35 R¹ représente un groupe organique contenant un nombre entier d'atomes de carbone dans une plage de 1 à 85, qui est substitué par un nombre s de groupe (s) NCO, et le s représente un entier de 1 à 10 ; et le recyclage de l'ester (acide carbamique N-substitué)-O-aryle n'ayant pas réagi qui n'a pas été thermiquement décomposé dans l'étape (F), vers l'étape (A) et/ou l'étape (B) et/ou l'étape (R) et/ou l'étape (P) et/ou l'étape (F).

- 40 21. Procédé de production selon la revendication 8 ou 9, comprenant en outre l'étape suivante (G) de récupération de l'ammoniac formé en tant que sous-produit dans l'étape (A) et/ou l'étape (B) et/ou l'étape (R) ; régénération de l'urée par réaction de l'ammoniac avec du dioxyde de carbone ; et recyclage de l'urée vers l'étape (A) :

45 étape (G) : une étape de récupération de l'ammoniac formé en tant que sous-produit, régénération de l'urée par réaction de l'ammoniac avec du dioxyde de carbone, et recyclage de l'urée vers l'étape (A).

FIG.1




FIG.2




FIG.3




FIG.4




FIG.5




FIG.6




FIG.7




FIG.8




FIG.9




FIG.10




FIG.11




FIG.12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25





FIG. 26



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 7122697 B [0029]
- US 2677698 A [0029]
- US 4713476 A [0029]
- EP 0568782 A [0029]
- EP 0657420 A [0029]
- US 4497963 A [0029]
- US 4290970 A [0029]
- JP H641045 A [0029] [0235] [0289]
- US 2409701 A [0029]
- US 3992430 A [0029]
- US 4297501 A [0029]
- US 3873553 A [0029]
- US 4925971 A [0029]
- JP H4164060 A [0029]
- JP H2759 A [0029]
- JP H320254 A [0029]
- JP H8277255 A [0029]
- JP S5271443 A [0029]
- JP H7157463 A [0029]
- US 2692275 A [0029]
- US 3734941 A [0029]
- US 4081472 A [0029]
- US 4388426 A [0029]
- US 4482499 A [0029]
- EP 0355443 A [0029]
- JP 3382289 B [0029]
- JP 2804132 B [0029]
- WO 2008120645 A [0037]
- WO 2008084824 A [0037]
- JP H248539 B [0218]
- DD 1042891 [0268] [0375] [0423]
- WO 2008059953 A [0317] [0360] [0443]
- JP 2009192250 A [0744]
- JP 2009192268 A [0744]

Non-patent literature cited in the description

- *Berichte der Deutschen Chemischen Gesellschaft*, vol. 3, 653 [0030]
- *Journal of the American Chemical Society*, 1951, vol. 73, 1831 [0030]
- *Journal of the Chemical Society, Perkin Transactions 1: Organic and Bio-Organic Chemistry (1972-1999)*, 1976, 141-143 [0030]
- *Berichte der Deutschen Chemischen Gesellschaft*, 1970, vol. 3, 649 [0030]
- *Journal of the American Chemical Society*, 1959, vol. 81, 2138 [0030]
- *Polymer*, 1994, vol. 35, 3766 [0030]
- **YADAV et al.** *Synlett*, 2005, 3055-58 [0030]
- Yukikagaku Seikagaku Meimeihou. Nankodo Co., Ltd, 1992 [0062]